LA-UR-95- 2500

Title:

SIMULATION OF DEEPPENETRATION WELDING OF
STAINLESS STEEL USING GEOMETRIC
CONSTRAINTS BASED ON EXPERIMENTAL
INFORMATION

Author(s):

John O. Milewski, Mst-6
Samuel G. Lambrakos, Naval Research Laboratory

Submitted to:

4TH INTERNATIONAL CONFERENCE ON TRENDS IN
WELDING RESEARCH, GATLINBURG, TN., JUNE 1995

RECEIVED

AUG 29 1995

OSTI

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

MASTER

Los Alamos
NATIONAL LABORATORY

Los Alamos National Laboratory, an affirmative action/equal opportunity employer, is operated by the University of California for the U.S. Department of Energy under contract W-7405-ENG-36. By acceptance of this article, the publisher recognizes that the U.S. Government retains a nonexclusive, royalty-free license to publish or reproduce the published form of this contribution, or to allow others to do so, for U.S. Government purposes. The Los Alamos National Laboratory requests that the publisher identify this article as work performed under the auspices of the U.S. Department of Energy.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Abstract

We present a general overview of a method of numerically modelling deep penetration welding processes using geometric constraints based on boundary information obtained from experiment. We consider general issues concerning accurate numerical calculation of temperature and velocity fields in regions of the meltpool where the flow of fluid is characterized by quasi-stationary Stokes flow. It is this region of the meltpool which is closest to the heat-affected-zone (HAZ) and which represents a significant fraction of the fusion zone (FZ).

IN A PREVIOUS REPORT (1), we introduced a method based on geometric constraints for the inclusion of experimental information concerning steady-state weldpool shape into a model system. A feature of this method is that it tends to compensate for either the unavailability of experimental measurements of material properties or gaps in knowledge concerning the general char-

acter of the keyhole. In this report, we present a general overview of the geometric-constraints method and issues concerning accurate numerical calculation of temperature and velocity fields in regions of the meltpool where the flow of fluid is characterized by quasi-steady Stokes flow. The underlying motivation of our development is that it is *transport* in these regions of the meltpool which couple most *strongly* and *directly* to the heat-affected-zone (HAZ), and which, because of the rapid onset of viscous effects, represents a significant fraction of the fusion zone (FZ). The physical characteristics of all other regions of the meltpool, as well as the keyhole itself, are considered with respect to the relative strength of their coupling to regions of the meltpool that are close to the solidification boundary and within the Stokes-flow regime. Regions of the meltpool that are close to the keyhole present a particular problem because of the sharp rise in temperature. With respect to numerical discretization, these regions can be characterized effectively as

Lambrakos, Milewski

numerical singularities resulting from the type of stiffness that occurs in the integration of shock-like structures. However, regions of the melt pool that are close to the solidification boundary are characterized by fluid properties which provide a means of overcoming any ill-conditioning due to the numerically singular character of regions near the keyhole and a more accurate specification of the flow. Because the character of the flow in regions that are close to the trailing solidification boundary is not coupled to the details of the character of the flow in regions near the keyhole, a well posed input condition is a set of upstream boundary values of the temperature and fluid-flow fields. The geometric-constraints method presented in this report entails the specification of a consistent set of upstream boundary values of temperature and flow velocity rather than explicit specification of the beam energy source.

Physical Model of Deep Penetration Welding

In the context of using geometric constraints, it is the solidification boundary and top surface boundary which determine the solution rather than the boundary corresponding to the vapor-liquid interface associated with the keyhole. Given this, it follows that the flow characteristics of the liquid in regions of the melt pool near the solid-liquid boundary must be modelled accurately. The keyhole boundary or keyhole source term, depending on the fashion of implementation, is only used to adjust the characteristically monotonic flow field along the top surface and solidification boundaries. Therefore,

in our present model, it is not considered a true boundary of the system, or more precisely, of the solution domain. In our present model we adopt the approximation that the flow character of the liquid region is mostly that of quasi-steady Stokes flow.

The model system is characterized by quasi-steady mass, energy and momentum transport in a coordinate system that is fixed in the reference frame of a moving beam energy source, i.e., electron or laser beam. The boundaries of the model system are defined, at each timestep, by the sides of a finite-sized rectangular region containing the beam and by the temperature of vaporization, or T_G isotherm which is taken to represent the vapor-liquid boundary of the keyhole. Outflow boundary conditions are imposed on the downstream boundaries.

The system is assumed to be symmetric about the xz -face at $y = 0$, (see Figure 1); thus, only one half the system is modelled. The equations of transport governing the model system are as follows. The equation of energy transport is

$$\frac{\partial T}{\partial t} + \nabla \cdot [UT] + \delta_{1j} V_B \frac{\partial T}{\partial x_j} = \kappa(T) \nabla^2 T(\mathbf{x}, t) + \nabla \cdot \mathbf{q}, \quad (1)$$

where

$$\kappa(T) = \frac{k(T)}{\rho(T)C_p(T)}. \quad (2)$$

The term $\nabla \cdot \mathbf{q}$ represents the total energy transferred into the system from different types of sources. The equation of momentum transport

is

$$\frac{\partial \mathcal{U}_j}{\partial t} = \nu(T) \nabla^2 \mathcal{U}_j - \frac{1}{\rho(T)} \frac{\partial P}{\partial x_j} \quad (3)$$

where

$$\nu(T) = \frac{\mu(T)}{\rho(T)} \quad (4)$$

and $j = 1, 2, 3$ denotes the Cartesian coordinates x, y and z , respectively. And lastly, the equation of mass transport,

$$\nabla \cdot \mathbf{U} = 0, \quad (5)$$

The quantity $\mathbf{U} = (U_1, U_2, U_3) = (u, v, w)$ is the velocity field at a given point, and $\mathbf{x} = (x_1, x_2, x_3) = (x, y, z)$ is the Cartesian coordinate of that point. The quantity V_B is the speed of the beam, moving in the direction of increasing x and δ_{ij} is the Kronecker delta function. The quantity P is the pressure at a given point and T is the temperature. In our model the density $\rho(T)$, coefficient of viscosity $\mu(T)$, conductivity $k(T)$ and heat capacity $C_p(T)$ are functions of temperature T (see reference 1 for values). The thermal coefficient of surface tension is given by

$$\frac{\partial \gamma}{\partial T} = -A_n f_s(x, y) \quad (6)$$

where A_n is a constant and $f_s(x, y)$ is a two-dimensional modulation function whose form is specified according to experimental information about melt pool shape. The quantity given by Eq.(6), which is formally equivalent to the coefficient of surface tension is for the purpose of lumping the influence of phenomena occurring in the vicinity of the keyhole and at the top surface of the melt pool which are not included explicitly in the model system. This function provides a means of including experimentally obtained in-

formation concerning the shape of the melt pool. The boundary on the molten region is defined by the solid-liquid interface. The boundary condition on this boundary is given by $\mathcal{U}_j = -\delta_{1j} V_B$.

Fig. 1 - Schematic of model system showing relative coordinates of system boundaries

Overview of the Geometric-Constraints Method

The geometric-constraints method described here is based on the following mathematical properties which can be associated with the character of heat and fluid flow occurring in a melt pool resulting from a deep penetration welding process.

Firstly, the solution domain defined by the melt pool resulting from a deep penetration welding process includes subregions within which the flow of fluid is characteristically quasi-steady Stokes. This is especially true of downstream regions of the melt pool. A property of the equations of quasi-steady Stokes flow is that there

is a unique solution U which satisfies prescribed boundary conditions.

Secondly, we observe that if within a bounded domain the solution U is known to be monotonic, it is not necessary to have boundary value information over the entire boundary in order to effect a reasonably accurate determination of U within a subregion of the domain. Given the condition of monotonicity and a set of specified values of U at different points on the boundary, we can effect an approximation to a boundary value problem via constraints on the equations governing the flow of fluid.

Thirdly, we observe that because the character of the flow in regions near the trailing solidification boundary is weakly coupled to the details of the character of the flow in regions near the keyhole (where the flow is not quasi-steady Stokes), an effective keyhole boundary or an effective energy source may not represent a well posed *input* quantity. The character of the flow in *downstream* regions of the meltpool suggests that a well posed input condition is that of an *upstream* boundary upon which are specified values of the temperature and Stokes-flow fields.

Fourthly, we observe that the values of the temperature and flow fields specified at an upstream boundary within a region of quasi-steady Stokes flow are not arbitrary and must be consistent with *downstream* boundary values. The uniqueness of U implies that if the magnitude of the quasi-steady flow field decreases monoton-

ically in the downstream direction then there can be only one upstream boundary specification that is consistent with a given downstream boundary specification.

And lastly, adopting upstream boundary conditions as input conditions on the system implies that the effective keyhole no longer has physical significance but represents a *generator* of the temperature and flow field over the upstream boundary. The procedure of generating a global upstream boundary from a local effective keyhole source is typically not unique. Any effective source representation and associated local-to-global mapping is suitable if it generates upstream boundary values which are consistent with (or map into) specified downstream boundary values.

Given the above mathematical properties of the meltpool and interrelation between its subregions, a specific approach for applying the procedure for calculating the temperature and flow fields according to the geometric-constraints method can be effected. In detailing this approach we refer to Figure 2 which gives a two-dimensional schematic description of the partitioning of the weld meltpool into subregions. The initial step of the procedure for calculating U and T is to specify a relatively well distributed set of *measured* downstream boundary values, e.g., Figure 3. Shown in Figure 3 are: the maximum separation between the center of the beam energy source and the trailing solidification boundary along the top surface of the workpiece (C_1):

the lateral cross section of the weld that is perpendicular to the direction of travel of the beam (C_2); and the solidification curve corresponding to the intersection of the trailing solidification boundary and the plane passing through the center of the beam and parallel to the direction of beam travel (C_3).

Fig. 2 - Top-surface schematic description of the partitioning of weld melt pool into a subregion where the flow of fluid is quasi-steady Stokes and a subregion containing an effective energy source

Fig. 3 - Example of a set of downstream boundary values obtained from experimental measurements.

The next step of the procedure is the selection and adjustment of the modulation function $f(x, y)$ defined by Eq.(6) and of the effective energy source. The criterion for adjustment of these functions is *not* the generation of a temperature and flow field which generates the entire solid-liquid boundary defining the dynamic weld melt pool. The criterion for adjusting these functions is only that a specified set of downstream boundary values is satisfied. This less restrictive criterion provides a high level of flexibility with respect to adjustment and selection of $f(x, y)$ and the effective energy source. Any combination of functions $f(x, y)$ and effective energy sources is sufficient if that combination generates boundary values on the upstream boundary of the quasi-steady Stokes flow region (see Figure 2) which in turn generates U and T fields which map into specified boundary values on the downstream boundary. Examples demonstrating the high level of flexibility with respect to adjustment of $f(x, y)$ and the effective energy source are given by Figures 4 and 5. For these figures the same modulation function $f(x, y)$ is adopted. It is assumed that for the energy-source adjustments shown in Figures 4 and 5 that one is seeking T and U fields that would satisfy downstream boundary values such as are given by curve C_3 in Figure 3. In Figure 4 adjustment of the energy source is effected by variation of the shape of a surface having a fixed temperature, i.e., T_G . As is seen in this figure, many of the qualitative features of curve C_3 in Figure 3 can be obtained via simple changes in the shape of the surface. Quan-

titative agreement in accordance with specified downstream-boundary values would of course require more detailed changes in the shape of the surface. In Figure 5 adjustment of the energy source is effected by variation of the temperature of a surface having a fixed shape.

Fig. 4 - Adjustment of effective keyhole source based on variation of shape of boundary of a given temperature

Fig. 5 - Adjustment of effective keyhole source based on variation of temperature of boundary of a given shape

Conclusion

In one sense our approach represents an extension of the methods which employ a phenomenological heat source moving through a solid whose parameters are adjusted such that the calculated temperature of solidification (or liquification) isotherm matches experimental measurements (2). Our approach entails the specification of upstream boundary values of the temperature fields and flow fields which are such that downstream boundary values match experimental measurements. However, our approach differs from those which employ a phenomenological heat source since it entails a complete accounting of all the physical transport, i.e., mass, energy and momentum. Because of this distinct feature, adjustment of upstream boundary values in accordance with experimental measurements does not represent an arbitrary-parameter adjustment. The mathematical properties of a bounded quasi-steady Stokes-flow region assure that there exists only one set of upstream values of T and U which are consistent with a given set of downstream boundary values, i.e., the solidification boundary.

References

1. S.G. Lambrakos, E.A. Metzbower, J. Milewski, G. Lewis, R. Dixon and D. Korzekwa, *J. Materials Engineering and Performance*, 3 (5), 639 (1994).
2. E.A. Metzbower, *Weld. J.*, 69 (7), 272 1990.