Environmental Applications of XANES: Speciation of Tc in Cement After Chemical Treatment and Se After Bacterial Uptake

D.K. Shuh,¹ N. Kaltsoyannis,¹ J.J. Bucher,¹ N.M. Edelstein,¹ S.B. Clark,² H. Nitsche,^{3†}
E. Hudson,⁴ T. Reich,⁵ I. Almahamid,³ P. Torretto,³ W. Lukens,¹ K. Roberts,³ B.C. Yee,⁶
D.E. Carlson,⁶ A. Yee,³ B.B. Buchanan,⁶ T. Leighton,⁷ W.-S. Yang,⁸ and J.C. Bryan⁹

¹Chemical Sciences Division, Lawrence Berkeley Laboratory, University of California, Berkeley, CA 94720

²The University of Georgia, Savannah River Ecology Laboratory (SREL), Aiken, SC 29802

³Earth Sciences Division, Lawrence Berkeley Laboratory, University of California, Berkeley, CA 94720

⁴G.T. Seaborg Institute of Transactinium Science, Lawrence Livermore National Laboratory, Livermore, CA 94551

⁵Forschungszentrum Rossendorf e. V., Institut für Radiochemie, Dresden, Germany

⁶Department of Plant Biology, University of California, Berkeley, CA 94720

⁷Department of Molecular and Cell Biology, University of California, Berkeley, CA 94720

⁸Department of Biology, Jackson State University, Jackson, MS 39217

⁹Inorganic and Structural Chemistry, CST-3, LANL, Los Alamos, NM 87545

[†]Present Address: Forschungszentrum Rossendorf e. V., Institut für Radiochemie, Postfach 51 01 19, D-01314 Dresden, Germany

March 1994

This work was supported by the Director, Office of Energy Research, Office of Basic Energy Sciences, Chemical Sciences Division, of the U.S. Department of Energy under Contract No. DE-AC03-76SF00098 and DE-AC09-76SR00819. This work is also supported by the Bioremediation Education Science and Technology (BEST) Consortium at LBL. This work was performed in part at SSRL and NSLS which are operated by the U.S. Department of Energy, Office of Basic Energy Sciences, Divisions of Chemical Sciences and Materials Science. The SSRL Biotechnology Program is supported by the NIH, Biomedical Resource Technology Program, Division of Research Resources. Further support is provided by the Department of Energy, Office of Health and Environmental Research. N. Kaltsoyannis would like to thank the SERC/NATO for a postdoctoral fellowship.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

TS

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, make any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

ENVIRONMENTAL APPLICATIONS OF XANES: SPECIATION OF Tc IN CEMENT AFTER CHEMICAL TREATMENT AND Se AFTER BACTERIAL UPTAKE

D. K. SHUH,¹ N. KALTSOYANNIS,¹ J. J. BUCHER,¹ N. M. EDELSTEIN,¹ S. B. CLARK,² H. NITSCHKE,^{3†} E. HUDSON,⁴ T. REICH,⁵ I. ALMAHAMID,³ P. TORRETTO,³ W. LUKENS,¹ K. ROBERTS,³ B. C. YEE,⁶ D. E. CARLSON,⁶ A. YEE,³ B. B. BUCHANAN,⁶ T. LEIGHTON,⁷ W.-S. YANG,⁸ AND J. C. BRYAN⁹

¹ Chemical Sciences Division, LBL, Berkeley, CA 94720

² The University of Georgia, Savannah River Ecology Laboratory (SREL), Aiken, SC 29802

³ Earth Sciences Division, LBL, Berkeley, CA 94720

⁴ G. T. Seaborg Institute of Transactinium Science, LLNL, Livermore, CA 94551

⁵ Forschungszentrum Rossendorf e. V., Institut für Radiochemie, Dresden, Germany

⁶ Department of Plant Biology, Univ. of California, Berkeley, CA 94720

⁷ Department of Molecular and Cell Biology, Univ. of California, Berkeley, CA 94720

⁸ Department of Biology, Jackson State Univ., Jackson, MS 39217

⁹ Inorganic and Structural Chemistry, CST-3, LANL, Los Alamos, NM 87545

ABSTRACT

XANES (X-ray Absorption Near Edge Spectroscopy) has been employed to evaluate the efficacy of a process designed to encapsulate and reduce TcO_4^- in cement matrices, thereby immobilizing Tc. The oxidation state of Se following bioremediation of Se by bacteria has also been determined by XANES. The XANES measurements were performed at the Stanford Synchrotron Radiation Laboratory (SSRL) and the National Synchrotron Light Source (NSLS) at the respective K edges of Tc (21.0 keV) and Se (12.7 keV). Comparison of the XANES spectra of Tc in untreated cement to Tc in slag treated cement and to the chemical shifts of reference materials, shows that the oxidation state of Tc is the same in both cements. Thus, the addition of a reducing agent to the cement formulation does not significantly reduce the TcO_4^- . The common soil bacterium, *Bacillus subtilis*, is known to incorporate Se on or within the cell wall when exposed to a Se(IV) solution. The Se XANES spectra of *B. subtilis*, as well as bacillus isolated from selenium rich soil, show that the organisms reduce selenite to the red allotrope of elemental Se.

INTRODUCTION

X-ray Absorption Spectroscopy (XAS) techniques are useful, non-destructive probes employed to determine the oxidation states of materials from X-ray Absorption Near Edge Structure (XANES), and local structural information can be extracted from Extended X-ray Absorption Fine Structure (EXAFS) measurements.¹ XAS investigations are well-suited for the study of radioactive and hazardous materials systems in the hard X-ray regime since samples may be safely contained for *in-situ* measurements at storage ring facilities. XAS methodologies are compatible with low concentration samples and are also highly amenable for studies of solutions and amorphous materials, both of which are of importance for environmental purposes. Thus, these techniques provide an ideal means for detailed electronic and structural investigations of fission product materials and other environmentally-relevant materials systems.

In XANES, the energy of the absorption edge is directly related to the oxidation state of the atom of interest.¹ Two studies of environmental contaminant speciation utilizing XANES to determine oxidation states have been performed. The first investigation was to evaluate the effectiveness of a chemical reaction designed to slow the release of $^{99}\text{TcO}_4^-$ in nuclear wasteform cements. The liquid waste is encapsulated in the cement with a reducing agent intended to reduce the Tc(VII) to less soluble Tc(IV). Previous XANES measurements have

demonstrated that CrO_4^{2-} is quantitatively reduced to less soluble Cr(III) under these conditions.² The efficacy of the process was determined by measurements of wasteform cements with and without the reducing agent. The second investigation was to characterize the oxidation state of Se after microbial uptake from an aqueous solution by common soil bacteria, in order to provide information about the possible mechanisms of bioremediation.

EXPERIMENTAL

The XANES measurements were performed at the storage rings of the Stanford Synchrotron Radiation Laboratory (SSRL) on beamline 4-1 and the National Synchrotron Light Source on beamline X23A2. The Tc K edge (~21.0 keV) measurements were made exclusively on the wiggler branch beamline 4-1, utilizing Si(220) monochromator crystals detuned ~50% to reduce contributions from higher order harmonics. The Se K edge (~12.7 keV) spectra were recorded at the bend magnet beamline X23A2 at the NSLS with Si(311) monochromator crystals and at beamline 4-1 in an identical manner as for the Tc studies. The convoluted experimental resolution is ~3 eV for Tc, ~1 eV for Se at 4-1, and ~1 eV for Se at X23A2. The detection techniques employed ionization chambers for transmission measurements at both facilities. A single element Si detector and Stern Heald detector were employed for fluorescence measurements at SSRL only. All spectra were collected simultaneously with Se or Tc reference materials to establish the respective chemical shifts and to ensure photon energy calibrations. The edge positions were determined using the first derivative method. Data reduction was accomplished with the SSRL EXAFSPAK program suite.

The Tc cements were prepared and packaged at SREL, whereas the Tc reference materials were prepared at LBL and LANL. The untreated cement was prepared by combining 25 wt. % Portland cement, 25 wt. % fly ash, 50 wt. % of a simulated aqueous waste solution containing 1000 ppm $^{99}\text{TcO}_4^-$. The composition of the simulated wastestream has been reported elsewhere.² The cement containing the reducing agent was composed of 50 wt. % simulated waste solution, 20 wt. % fly ash, 10 wt. % $\text{Ca}(\text{OH})_2$, 10 wt. % Portland cement, and 10 wt. % blast furnace slag. Slag is a source of ferrous iron and sulfide, which is believed to reduce TcO_4^- to TcO_2 . The TcO_2 was prepared by the thermal decomposition of ammonium pertechnetate and the TcO_2 sub-oxide by controlled electrodeposition. The samples were contained in thin-wall silica or polyethylene tubes, followed by the application of a heat shrink polyethylene tube. Vegetative cells of *B. subtilis* and of an unidentified bacillus isolated from Kesterson soil were exposed to aqueous Se solutions of different oxidation states, either selenite (IV) or selenate (VI). The bacteria did incorporate Se from the selenite growth solution, however, there was no uptake from the selenate solution. The bacteria were purified by repeated steps of centrifugation and washing. The centrifugal pellets were prepared for XANES by lyophilization and subsequent double encapsulation in polyethylene.

RESULTS AND DISCUSSION

Speciation of Tc in Wasteform Cement

The nuclide ^{99}Tc is a by-product of nuclear fission, with large quantities of TcO_4^- stored for disposal as solid, low-level radioactive waste. Immobilization of ^{99}Tc is essential for adequate disposal due to its long half-life ($t_{1/2}=2 \times 10^5$ years) and the propensity for TcO_4^- to migrate in the geosphere.³ One method for disposal involves microencapsulation of the liquid waste in a cement matrix.⁴ In addition, chemical reduction of the mobile TcO_4^- to a less soluble Tc^{4+} species is desirable. However, reduction to a lower oxidation state requires chemical additives in the form of a reducing agent such as slag.

XANES spectra were collected from wasteform cements prepared at the SREL with and without slag from a simulated nuclear waste stream spiked with pertechnetate. The XANES

Figure 1. Technetium K edge XANES spectra from the treated and untreated Tc-containing cements, as well the Tc reference materials. The pre-edge feature, indicative of the tetrahedral coordination of the TcO₄⁻ species, is clearly evident. The spectra have been normalized and aligned with respect to the Tc metal edge at 21,044 eV.

spectra of the Tc-containing cements and the Tc reference materials (Tc metal, $\text{TcO}_2(\text{IV})$, and a TcO_4^- (VII) solution) are presented in Fig. 1. The range of chemical shifts for the Tc K edge has been characterized for the first time and spans ~20 eV between the metallic and the Tc^{7+} state. The chemical shift from TcO_4^- (VII) to tetravalent $\text{TcO}_2(\text{IV})$ is ~7 eV, therefore resolving the difference in oxidation state solely on the basis of edge position is quite straightforward. Additionally, there is a characteristic pre-edge feature present in the TcO_4^- spectra that clearly fingerprints the tetrahedral TcO_4^- moiety.^{2,5-6} The spectra of Tc metal and TcO_2 have no such pre-edge features and exhibit edge positions significantly shifted to lower binding energies from that of TcO_4^- . Comparison of the XANES spectra of Tc in untreated cement to Tc in slag treated cement, shows that the primary oxidation state of Tc is the same in both cements since both display the distinctive pre-edge signature and have the same edge positions. Several locations within the treated cement were characterized and the results were the same throughout. Thus, the addition of slag to the cement formulation does not significantly reduce the TcO_4^- to TcO_2 (or any other Tc^{4+} compound) in the cement samples examined in this investigation. The same cement samples were re-examined several months later employing the same experimental techniques and the results were duplicated exactly. Additionally, the analysis of the EXAFS from the Tc metal and TcO_2 provides some of the first detailed structural information about these materials.⁷

Speciation of Se After Bacterial Uptake

The concentration and stabilization of hazardous materials by microbial agents offers great potential for use in environmental remediation technologies.⁸⁻¹⁰ Possible applications of bioremediation technologies are to oil refinery waste streams containing selenite and to the severely Se contaminated site at the Kesterson Reservoir in California. The aerobic soil bacterium, *B. subtilis*, is known to incorporate Se within or on the vegetative cell wall, although the exact mechanism of uptake is not fully understood.¹¹ The Se appears to be reduced and bound as red elemental Se, although there is no rigorous spectroscopic evidence to support this contention. The elucidation of the microbial mechanisms responsible for effective bioremediation will lead to improved bioremediation technologies.

The *in-situ* analysis of selenium following uptake by common soil bacteria *B. subtilis* and the Kesterson bacillus has been investigated by XANES, to elucidate the speciation of the Se contaminant in the biomass. The oxidation state of Se in the bacteria were determined by the chemical shifts at the Se K edge in comparison to those of the Se reference materials. Fig. 2 presents the Se K edge XANES spectra from the well-defined oxidation states of elemental Se (red and grey allotropes), a Na_2SeO_3 powder, and a Na_2SeO_4 powder. The chemical shifts at the Se K edge span ~9 eV from the elemental allotropes of Se to the selenate(VI). There is a discernible difference between the red and grey allotropes of elemental Se in the near-edge region, even though the actual edge positions are indistinguishable. The structural differences are also clearly evident from the preliminary analysis of the EXAFS from these materials. The Se XANES spectra of the two bacteria are also shown after uptake of Se from a growth medium containing sodium selenite(IV) for comparison to that from the reference materials (Fig. 2). The spectra in Fig. 2 show that both *B. subtilis* and the Kesterson bacillus reduce the selenite to red elemental Se. This result is consistent with the conclusion that red elemental Se is the biologically active form.

CONCLUSIONS

XANES techniques have been successfully employed to characterize the *in-situ* speciation of two hazardous environmental contaminants. A proposed chemical process to immobilize Tc in nuclear wasteform cements has been evaluated by XANES and there was no experimental evidence of a significant reduction of TcO_4^- to TcO_2 (or any other Tc^{4+} compound). The complete range of the chemical shifts with oxidation state at the Tc K edge

Figure 2. The Se K edge XANES spectra from *B. subtilis* and the Kesterson bacillus after growth in a selenite medium and the Se reference materials. The spectra have been normalized and aligned with respect to Se metal at 12,658 eV.

have been determined. The distinctive pre-edge signature of TcO_4^- , coupled with the chemical shift information, clearly differentiates it from the lower oxidation states of Tc.

The reduction of Se(IV) to red elemental Se by *B. subtilis* in culture has been documented by XANES and by comparison to known Se materials. The electronic and structural differences between the red and grey allotropes of elemental Se were found in the both XANES and EXAFS regions, respectively. The results support the view that organisms like *B. subtilis* offer a promising means for removing selenite (IV) from contaminated aqueous environments such as oil refinery waste streams. Future application of XANES techniques to the monitoring of *in-situ* selenium bioremediation activity is desirable.

ACKNOWLEDGMENTS

This work was supported in part by the Director, Office of Energy Research, Office of Basic Energy Sciences, Chemical Sciences Div. of the U.S. Dept. of Energy under Contracts No. DE-AC03-76SF00098 and DE-AC09-76SR00819. This work is also supported by the Bioremediation Education Science & Technology (BEST) Consortium at LBL. This work was performed in part at SSRL and NSLS which are operated by the U.S. Dept. of Energy, Office of Basic Energy Sciences, Divisions of Chemical Sciences and Materials Science. The SSRL Biotechnology Program is supported by the NIH, Biomedical Resource Technology Program, Div. of Research Resources. Further support is provided by the Dept. of Energy, Office of Health and Environmental Research. NK would like to thank the SERC/NATO for a postdoctoral fellowship. The authors would like thank J. Woicik of NIST for his assistance at beamline X23A2 and C. Rossington of LBL for the use of the single element Si detector.

† Present Address: Forschungszentrum Rossendorf e. V., Institut für Radiochemie, Postfach 51 01 19, D-01314 Dresden, Germany

REFERENCES

1. *X-ray Absorption. Principles, Applications, Techniques of EXAFS, SEXAFS, and XANES*, edited by D.C. Koningsberger and R. Prins, (John Wiley and Sons Inc., 1988).
2. S. Bajt, S.B. Clark, S.R. Sutton, M.L. Rivers, and J.V. Smith, *Anal. Chem.* **65**, 1800 (1993).
3. R.E. Meyer, W.D. Arnold, F.I. Case, and G.D. O'Kelley, *Radiochimica Acta* **55**, 11 (1991).
4. C.A. Langton, in *Proceedings of the Ninth Annual DOE Low-level Waste Management Conference* (Denver, CO, 1987).
5. R.C. Elder and M. K. Eidsness, *Chem. Rev.* **87**, 1027 (1987).
6. A. Bianconi, J. Garcia, and M. Bennefatto, *XANES in Condensed Systems*, in *Synchrotron Radiation in Chemistry and Biology I*, edited by E. Mandelkow, *Topics in Current Chemistry*, Vol. 145, (Springer-Verlag, Berlin, 1988), p. 40.
7. N. Kaltsoyannis et al., to be published.
8. F.A. Tomei, L.L. Barton, C.L. Lemanski, and T.G. Zocco, *Can. J. Microbiol.* **32**, 1328 (1992).
9. R.S. Oremland, J.T. Hollobaugh, A.S. Maest, T.S. Presser, L.G. Miller, and C.W. Culbertson, *Appl. Environ. Microbiol.* **55**, 2333 (1994).
10. C.J. Dodge, A. J. Francis, F. Lu, G.P. Halada, S.V. Kagwade, and C.R. Clayton, *Mater. Res. Soc. Proc.* **307**, 89 (1993).
11. B.B. Buchanan, T. Leighton, J. Liu, B.C. Yee, S. Jovanovich, A. Yee, W.-S. Yang, S. Ekunwe, and B. Chapman, "Bioremediation of Selenium Using the Bacterium, *Bacillus subtilis*". Abstracts of Fifth International Symposium on *Selenium in Biology and Medicine*, (Vanderbilt University School of Medicine, Nashville, TN, 1992) p. 30.