12
8-4-95 JS (1)

UCRL-ID-118655

Final Report for Hydrogen Chemisorption on Diamond Surfaces

R. Daley
R. Musket

September 1994

Lawrence
Livermore
National
Laboratory

Work performed under the auspices of the U.S. Department of Energy by the
Lawrence Livermore National Laboratory under Contract W-7405-ENG-48.

DISCLAIMER

This document was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor the University of California nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise, does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or the University of California. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or the University of California, and shall not be used for advertising or product endorsement purposes.

This report has been reproduced
directly from the best available copy.

Available to DOE and DOE contractors from the
Office of Scientific and Technical Information
P.O. Box 62, Oak Ridge, TN 37831
Prices available from (615) 576-8401, FTS 626-8401

Available to the public from the
National Technical Information Service
U.S. Department of Commerce
5285 Port Royal Rd.,
Springfield, VA 22161

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Final Report
for
Hydrogen Chemisorption on Diamond Surfaces

Richard S. Daley and Ronald G. Musket

Lawrence Livermore National Laboratory
Livermore, CA 94550

Abstract

Previously we demonstrated the ability to measure submonolayer quantities of surface hydrogen on insulating glasses. The present study builds on this by examining hydrogen coverages on another insulating material: the technologically important diamond (100) surface. The information to be obtained in the present study will allow us to deduce the correct structures for the diamond (100)-(1X1) and -(2X1) surface phases and provide information on the kinetics of hydrogen desorption from the (100) surface. Such experiments are essential for a complete understanding of hydrogen surface chemistry during the chemical vapor deposition of thin diamond films. This report summarizes progress made in FY93 for measuring surface hydrogen concentrations on the diamond (100) surface. Although the available LDRD resources were insufficient to finish this study in FY93, completion of the study is planned using other resources and this detailed report as a reference.

MASTER

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

na

1. Introduction

Recently we demonstrated the ability to measure submonolayer quantities of surface hydrogen on insulating glasses by forward recoil spectroscopy (FRS) using 2-3 MeV helium ions [1,2]. The advantages of this technique over other methods for hydrogen analysis are: (a) surface hydrogen can be detected and profiled in depth, (b) essentially no hydrogen (or host material) is destroyed or displaced, and (c) quantitative measurements at submonolayer coverages are possible. The present study builds on our previous work by examining hydrogen coverages on another insulating material: the technologically important diamond (100) surface.

The information obtained in this study will allow us to deduce the correct structures for the diamond (100)-(1x1) and -(2x1) surface phases, as well as provide information on the kinetics of hydrogen desorption from the (100) surface. These quantitative results are essential if a complete understanding of the role of surface hydrogen during the chemical vapor deposition of thin diamond films is to be obtained. In particular, this research will help bridge a gap that has recently been created between current experiment and theory on the structure of the diamond (100)-(1x1) and -(2x1) surfaces. To date hydrogen coverages have only been inferred by indirect measurement techniques.

The difference between a mono- and di-hydrated (1x1) surface is 0.5 monolayers (ML) of hydrogen (1 ML = two hydrogen atoms per surface carbon), easily resolvable by forward recoil spectroscopy (FRS), that permits measurements of < 0.05 ML. By measuring the surface hydrogen concentrations the correct surface structures can easily be deduced for the (1x1) and (2x1) surfaces. If an intermediate coverage ($0.5 \text{ ML} > q > 0$) is found for the (1x1) surface then a combination of mono- and di-hydrated surface states is indicated, as predicted by theory. For the (2x1) surface the absolute difference between a mono-hydrated and hydrogen free surface is again 0.5 ML. A finding near 0.5 ML suggests the carbon atoms have formed dimers and are predominately mono-hydrated while coverages below 0.25 ML would indicate most of the surface carbons are dehydrogenated, and carbon-carbon π -bonds have formed.

2. Experimental Considerations

To measure surface hydrogen coverages under controlled conditions, an ultra-high vacuum (UHV) chamber attached to an accelerator beam line is required. An existing Varian UHV chamber has been modified and equipped with the appropriate surface analysis equipment required for the experiment. This chamber will be connected to an existing beam line of a 4 MV ion accelerator via a differential pumping section. The following paragraphs give detailed experimental design/operating procedures for each element of the vacuum system. A top view of the UHV chamber is shown in figure 1. Except for the sputter ion gun and the 168° Rutherford backscattering (RBS) detector, all identified units have their beams or detection axes in the horizontal plane at the center of the chamber. The corresponding centerline chamber distances are shown in figure 2. The low-energy electron diffraction (LEED) optics unit is required to establish the surface structure and the changes caused by the chemisorption of hydrogen. The

particular unit is a Varian 4-grid model. The retractable Faraday cup unit is a copy of the Faraday cup design described in reference 2. The only difference is that the present assembly can be baked to 200° C.

2.1 Hydrogen Dosing

The hydrogen doser consists of a tungsten filament for dissociating the molecular hydrogen and a stainless steel tube for delivering the hydrogen to the filament. The filaments are hand wound from 15 cm of 1/4 mm diameter wire. The filament is mounted to threaded Mo rod for electrical contact. The Mo rod is passed through a Macor block that isolates the filament electrical connections from the supporting stainless steel tube. The Macor block and the threaded rod are designed to provide positioning of the filament to accommodate any filament-to-sample distance. Currently, the distance is ≈ 2.5 cm when dosing. The dosing assembly is attached to the chamber through a $\pm 10^\circ$ gimbaled mount. This allows the filament to be moved away from the sample when not in use. The hydrogen (or any other gas from the manifold) is emitted to the chamber through the stainless steel tube via a Varian leak valve. During heating of the filament after an air exposure, the specimen surface must be hidden from line-of-sight of the filament to avoid deposition of evaporated tungsten oxide. Typical operating currents needed are 6 to 6.5 amps (≈ 15 VDC) to produce a filament temperature ($\approx 2000^\circ\text{C}$), which dissociates H_2 with a suitable cross section. Filament power is supplied by a HP high current power supply. The hydrogen needs to be continuously leaked into the chamber because it readily adsorbs on the chamber walls. It is recommended that cooling be applied to the specimen when the filament is operating to keep the surface temperature low. With cooling present the surface reached a maximum temperature of 20°C , without the cooling the temperature increased to 250°C .

2.2 Sputter Ion Gun

An ion sputter gun is needed for surface cleaning. The PHI sputter ion gun is mounted above the LEED viewport at a 29° angle from horizontal. The ion gun should not be necessary for diamond experiments since the only way to clean diamond is through annealing. However, it will be needed if Si is used for an extended period of time. If extensive sputtering experiments are undertaken, a turbo pump should be attached to the chamber to allow dynamic flow of the remove the Ar gas. Currently the gas is removed through the roughing manifold.

2.3 RBS Detector

A 168° Rutherford backscattering spectroscopy (RBS) detector provides spectra for bulk and surface impurity ($Z > 6$, for diamond surfaces) analysis. The 168° RBS detector is an Ortec ULTRA (200°C bakeable) surface barrier detector with an active area of 150 mm^2 and maximum resolution of 14 keV for alpha particles. The detector is mounted in an aluminum block that is attached to the vacuum side of a 15 cm to 7.0 cm reducing flange by two stainless steel mounting brackets. The mounting brackets are located 2.5 cm above the ion beam axis (Cornell geometry) and place the opening of the detector 15.5 cm from the inside flange edge. Additional holes are provided in the flange to move the detector to a height of 0.5 cm above the beam axis if desired. Electrical

connections are through a welded BNC feedthrough. The aluminum block allows a collimator of any size to be placed in front of the detector. Currently a circular aperture of the collimator (0.5 mm thick Mo) has a diameter of 8 mm. An additional collimator with an opening of 6.4 mm is available. The detector dark count was tested before entry into the chamber and was found to be acceptable. Given the detector geometry, the sample-to-detector distance is 12.1 cm with an estimated solid angle of 3.5 msr.

2.4 FRS Detector

This detector provides energy spectra for forward recoiled hydrogen atoms [1]. The 30° FRS detector is also an Ortec ULTRA (200° C bakeable) surface barrier detector with an active area of 150 mm² and maximum resolution of 14 keV for alpha particles. The detector is mounted in an aluminum block that fits snugly inside a stainless steel tube. The stainless steel tube is welded to the vacuum side of a 7.0 cm BNC feedthrough flange. This mounting scheme allows ± 2.54 cm linear travel of the detector along the horizontal axis to the specimen. At the midpoint of travel the detector is located ≈ 5 cm from the center of the chamber. A rectangular slit collimator (0.5 mm thick Mo) with dimensions of 1.25 cm high by 1 mm wide covers the detector. To eliminate scattered He ions a 11.90 μ m Al stopper foil is inserted between the slit and the detector. The foil is actually two 5.95 μ m Al foils (manufactured by Goodfellow Industries) Torr sealed to either side of an Al support ring. The 5.95 μ m Al foil was supplied by Tom Felter (Sandia) and the thickness was determined in house by H⁺ RBS. This detector geometry is expected to give a solid angle of 3.6 msr at 5 cm from the sample. The measured energy resolution due mainly to the Al stopper foil is ≈ 80 keV using 2.9 MeV He⁺.

2.5 Sample Holder

A Vacuum Generators manipulator with a custom designed sample holder is used for sample positioning and heating/cooling. A schematic of the heater detail is given in figure 3. The manipulator provides rotary as well as three degrees of translational motion (X, Y, and Z). The rotary motion is constrained to $\pm 180^\circ$ by the stainless steel cooling coils attached to the sample foot. Heating of the sample is accomplished through a Spectramat E-292 sample heater rated to 1200° C. Heating electrical connections consist of a single mini-conflat BNC feedthrough with the stem of the heater grounded for return current flow. Typical operating current to reach 1250° C is 4.25 amps @ 14 VDC. The same HP power supply used for dosing is also used for heating the sample (Note: the rear connections on the HP power supply need to be changed when going from sample heating to filament operation). The sample (7 mm diameter max. dimension) is clamped on the heater surface using a Mo cap (1/4 mm thick) with a 6.4 mm ID opening. A W-5% Re vs. W-26% Re thermocouple is placed under the Mo cap next to the sample to measure surface temperatures.

The heater stem is set in a stainless steel block that is screwed to the Z-stage of the manipulator. This block is also brazed to a loop in the stainless steel cooling coils. This provides a heat sink for cooling the sample when liquid nitrogen is passed through the coil assembly. A liquid nitrogen dewar and transfer hose from Cryogenics is designed to deliver liquid nitrogen at a pressure of 50 psi. This is adequate to force liquid completely through the coils. The liquid exhaust should be adequately vented away

from the chamber to prevent partial cooling of chamber walls and possible leaks at gasket seals. Normal liquid nitrogen dewars deliver liquid at pressures of 20 psi. This pressure may not be adequate to achieve liquid flow through the cooling coils. Active cooling must be present when heating the sample! Failure to do this could result in heating of the coil braze material to temperatures above the braze melting point.

3. Results and Discussion

Initial progress was made with silicon specimens. A Si(100) sample was inserted into the holder and was used to trouble shoot the UHV system. Si(100) is similar to diamond (100) in that it shows a (1X1) to (2X1) surface reconstruction upon heating, and the structural effects of the interaction of the surface with atomic hydrogen is well documented. Dosing of the Si(100)-(2X1) surface with atomic hydrogen returns the surface to a (1X1) surface, as is the case for diamond.

The following experiments were performed:

- (a) Tested the sample heating and cooling system. A temperature range of -125°C to 1250°C was achieved.
- (b) Checked the LEED system by observing the Si(100)-(1X1) to (2X1) reconstruction at a temperature of ~ 1100°C.
- (c) Verified the operation of the filament and gas dosing assembly by dosing the Si(100)-(2X1) surface with atomic hydrogen. We dosed the Si(100)-(2x1) surface with 120 Langmuir (1 Langmuir = 1×10^{-6} Torr • sec) of (H/H₂) at 2×10^{-7} Torr with and without the filament operating. Without the filament there was no change in the LEED pattern (i.e. molecular hydrogen does not affect the surface reconstruction). With the filament operating, a 120 L exposure resulted in the reconstruction of the Si(100)-(2x1) surface to a (1x1) surface.

4. Summary

Although no MeV ion-beam data has yet been collected, the UHV analysis system is ready to be attached to the analysis beam line of the 4-MV ion accelerator. When this system becomes operational, we will analyze the surface hydrogen coverages on diamond under controlled and reproducible conditions. The data and results should lead to a better understanding of the role of chemisorbed hydrogen in determining surface structure and on the growth of CVD diamond films.

5. References

1. R.G. Musket, A.A. Tesar, and R.S. Daley, *Hydrogen content of polished glass surfaces using forward recoil spectroscopy*, J. Non-Cryst. Solids, 167 (1994) 149.
2. R.G. Musket, R.G. Patterson, and R.S. Daley, *Spinning-wire dosimetry for ion-beam analysis of materials*, Nucl. Instr. and Meth. B83 (1993) 425.

Figure 1: Top view of the UHV chamber showing the layout of the ion detectors, gas doser/filament assembly, LEED optics, sputter gun, and retractable faraday cup.

Figure 2: Top view of the UHV chamber showing the centerline dimensions to each flange face.

Figure 3: Detail of Spectramat E-292 heater assembly.