FINAL REPORT

on

DESIGN REVIEW OF THE D-ZERO CENTRAL
CALORIMETER MODULE ASSEMBLY

to

FERMI NATIONAL ACCELERATOR LABORATORY

November, 1987

by

M. Rosenfeld

BATTELLE
Columbus Division
505 King Avenue
Columbus, Ohio 43201-2693

EXECUTIVE SUMMARY

The D-Zero Central Calorimeter Module Assembly is a segmented ring structure consisting of an assemblage of trapezoidal modules. It is housed inside a vessel containing liquid argon. The modules contain specialized equipment for use in particle physics experiments.

The design review of the D-Zero Central Calorimeter Module Assembly evaluated all major structural elements for adequacy for their design loads. They were evaluated in accordance with applicable specifications from Reference 1. The allowable stresses of the Specifications provide an approximate safety factor of 2.0 or more on failure and 1.67 on serviceability of the structure. This margin is typical of buildings, bridges, and other large structures executed in steel. To the extent that calculated stresses are less than the allowable stresses, the margin is proportionately greater. For additional conservatism to account for inherent uncertainties in estimating design loads, an arbitrary load factor of 1.25 was also applied. Design loads were calculated for deadweighted plus thermal expansion, neglecting the effects of friction, and for deadweight only, considering postulated effects of friction.

All of the major structural elements were found to be provisionally acceptable for their intended service and the predicted design loads. The provisions are as follows:

1. That the connect pins be fabricated of Inconel 718 or functional equivalent, instead of the originally specified Type 304 stainless steel.
2. That conditions on bearing surfaces be modified to effectively reduce the potential coefficient of friction. The affected bearing interfaces include those between the CH, FH, and EM rings, and between the CH ring and its support members.

Item 1 has been effectively accomplished in that Fermilab has indicated verbally that this change was specified. Item 2 may be accomplished by treatment of affected surfaces with friction-reducing coatings. Candidate materials are molybdenum disulfide (MoS_2), polytetrafluoroethylene (PTFE), or ultrahigh molecular weight polyethylene (UHMWPE). These materials are relatively chemically inert, functional at cryogenic temperatures, and need be

LIST OF FIGURES

	<u>Page</u>
Figure 1. Schematic of the D-Zero Central Calorimeter Module Assembly	3
Figure 2. Schematics of the Principal Structural Elements	6
Figure 3. Resolution of Connection Loads	19

1.0 INTRODUCTION

The D-Zero Central Calorimeter Module Assembly is a segmented ring structure consisting of an assemblage of trapezoidal modules. It is housed inside a vessel containing liquid argon. The modules contain specialized equipment for use in particle physics experiments. The assembly design was reviewed to verify structural integrity and adequacy for service. Components that were evaluated were the main support beams, main support straps, module endplate brackets, module endplates, endplate connection pins, and transition pieces. Loading conditions considered were deadweight and differential thermal expansion due to specified temperature gradients. The American Institute of Steel Construction Specifications for The Design Fabrication and Erection of Structural Steel for Buildings Eighth Edition, referred to hereinafter as the AISC Specifications, were the primary acceptance criteria, where applicable. Other guidelines and engineering judgment were applied as appropriate.

The reader is alerted to the fact that the text reports general aspects and results of the design review. All calculations and computer output supporting the conclusions are provided as an appendix. The calculations fully document assumptions and methodologies, and should be referred to for specific information not reported in the text.

2.0 DESCRIPTION OF THE MODULE ASSEMBLY

2.1 Geometry

The Central Calorimeter Module Assembly consists of a number of trapezoidal members (modules) assembled in the form of three concentric ring structures. Refer to Figure 1. The rings are oriented about a horizontal axis of revolution.

The outer ring, referred to as the CH ring, is made up of 16 Coarse Hadronic (CH) Modules. The CH ring inside and outside radii are 67.225 inches and 88.199 inches, respectively. The CH ring is 104.796 inches in length at the inside diameter, and 89.616 inches in length at the outside diameter. The CH modules weigh 15,900 lbs each, for a total ring weight of 254,400 lbs.

The middle ring, referred to as the FH ring, is made up of 16 Fine Hadronic (FH) Modules. The FH ring inside and outside radii are 41.600 inches and 66.975 inches, respectively. The FH ring is 104.76 inches in length. The FH modules weigh 18,300 lbs each, for a total ring weight of 292,800 lbs.

The inner ring, referred to as the EM ring, consists of 32 Electro-Magnetic (EM) Modules. The EM ring inner and outer radii are 33.125 inches and 41.350 inches, respectively. The EM ring is 104.26 inches in length. The EM modules weigh 1,350 lbs each, for a total ring weight of 43,200 lbs.

The modules are densely packed with metal and instrumentation which perform scientific functions. The assembly is housed inside an insulated vessel containing liquid argon at a temperature of 90 K (-300 F) and a pressure of 30 psig at the top of the vessel. The modules do not perform a pressure-retaining function.

2.2 Construction

Each module is a trapezoidal box constructed of sheet or thin plate sides, welded to comparatively thick endplates. The endplate edges are milled to the inside and outside radii of their respective rings. The CH, FH, and EM modules are assembled to form their respective rings by means of lap or splice plates referred to as endplate brackets. The endplate brackets fasten to the module endplates by means of pins located at the corners of the module

FIGURE 1. SCHEMATIC OF THE D-ZERO CENTRAL CALORIMETER MODULE ASSEMBLY

endplates and brackets. Thus, all moment, shear and circumferential loads are transferred between modules via the endplate brackets. The pins are held in place by pin retainers.

Spacer blocks, referred to as transition pieces, are located between the circumferential edges of the endplates of the EM and FH rings, and similarly between the endplates of the FH and CH rings. The weight of the rings are transmitted from the module endplates through the spacers to the endplates of the next outermost ring below it, over a 180 degree arc. A clearance is maintained between rings above this arc. The transition pieces function as bearing surfaces. They also are flanged to correctly locate the rings axially. The rings are located circumferentially by keys at the bottom of each ring.

The outer (CH) ring assembly, which is supporting the two inner rings, is supported by two beams parallel to the ring axis, located symmetrically at 56.25 degrees from bottom dead center. There are two tension straps milled to the outside radius of the CH ring, slung between the beams and beneath the CH ring. The straps prevent horizontal displacement of the beams. The beams in turn are supported by four pedestals which penetrate the enclosing vessel. The pedestals allow thermal expansion and contraction of the assembly. Located between the outer (CH) ring assembly and the support beams and straps are thin strips of electrical insulating material.

Table 1 summarizes the important design data. Figure 2 provides schematic representations of the main components.

2.3 Materials

Most of the structural components are fabricated from annealed AISI Type 304 18Cr-8Ni austenitic stainless steel in the form of plate, sheet, bar or castings. The modules are fabricated by welding the sheet and plate members. The endplates, endplate brackets, and transition pieces are plate product, while the main support beams and straps are castings. The tension straps are butt welded to the ends of the main support beams. The pins used to fasten the module endplates and brackets are currently specified to be fabricated from Inconel 718, a precipitation-hardening nickel-based alloy.

TABLE 1. MODULE ASSEMBLY DATA

	CH	FH	EM
Number of Modules	16	16	32
Module Weight, lbs.	15,900	18,300	1,350
Ring Weight, lbs.	254,400	292,800	43,200
Inside Radius, inches	67.225	41.600	33.125
Outside Radius, inches	88.199	66.975	41.350
Module Length, inches	(1)	104.76	104.26
Connection Pin Diameter, inches	2.0	2.0	0.75
Endplate Thickness, inches	1.74	1.24	0.74
Module Skin, Top/Bottom, inches	.1875	.1875	.125
Module Skin, Sides, inches	.1054	.1054	.075
Bracket Thickness, inches	1.50	1.25	0.75
Bracket Dimension A, inches ⁽²⁾	16.239	18.750	5.778
Bracket Dimension B, inches ⁽²⁾	4.672	4.500	1.600

1. The CH module length is 104.88 inches at the inside diameter and 89.62 inches at the outside diameter.
2. Bracket dimension A is the radial pin spacing. Dimension B is the tangential pin spacing. Refer to Figure 2.

FIGURE 2. SCHEMATICS OF THE PRINCIPAL STRUCTURAL ELEMENTS

The connection pins used in the CH and FH rings had been specified as AISI Type 304 stainless steel at the time this design review was initiated.

For the purpose of analysis, the annealed Type 304 austenitic stainless steel was assumed to possess a minimum tensile yield strength of 30 ksi and a minimum tensile ultimate strength of 75 ksi, based on material specifications from References 2 and 3. These properties correspond to ASTM A-666, Grade 1 and other ASTM designations. It is noted that many Type 304 product forms may possess greater yield and ultimate strength values in annealed, solution-treated, and cold work hardened conditions. Type 304 is available in free-machining and weldable grades. It is often used as-welded (i.e., without post-weld heat treatment).

The Inconel 718 precipitation hardening nickel-based alloy specified for the pins was considered to have a minimum tensile yield strength of 150 ksi and minimum tensile ultimate strength of 180 ksi, in accordance with Reference 3. These properties correspond to ASTM B-637, and others.

The electrical insulation material located between the CH ring assembly and the support beams and straps is a glass fiber-reinforced composite commonly used in cryogenic applications as an insulating structural component. It is a heat-activated, amine-catalyzed, bisphenol A solid epoxy resin reinforced with continuous filament E-glass woven fabrics. It meets the specifications of ASTM D-709, Grade G-10, and is commonly referred to as NEMA/ASTM G-10. The material is anisotropic, with effective properties depending on fiber orientation with respect to the applied loading. Citing the full range of properties from Reference 3, the tensile strength is 35 to 40 ksi, the compressive strength is 35 to 60 ksi, the elastic modulus is 2.0×10^6 to 2.7×10^6 psi, and Poisson's ratio is .14 to .21. Actual properties will vary with orientation, temperature, load history, and manufacturer.

2.4 Loadings

The primary loading is the weight of the module assembly contents. The distribution of the load is uniform around each ring. The deadweight loads are transferred as described in Section 2.2 of this report. Fermilab personnel performed 2-D and 3-D finite element analyses of the structure to

determine the distribution of forces through the rings. The results of the analyses were reviewed by Battelle as part of this effort.

The operating environment of the rings is at cryogenic temperatures. The rings are cooled very slowly to -300 F by the gradual introduction and circulation of chilled gases or liquids. Fermilab estimated a nonlinear temperature gradient in the vertical direction and a linear temperature gradient in the axial direction. Battelle cannot comment on the validity of the assumed temperature gradient, except that it appears plausible. The internal forces due to differential thermal expansion were estimated using the same finite element models as for deadweight. These analyses were also reviewed by Battelle.

The module assembly was designed for static or quasistatic loadings only. Live loads were postulated not to exist. Loadings which were not addressed in this design review include the following:

1. Operational dynamic loads, such as nozzle thrust, wind load, vibration from reciprocating equipment, electromagnetic forces, etc.
2. Seismic accelerations and accidental loads.
3. Static loads from miscellaneous attached equipment.
4. Loads which may occur during fabrication, construction, or transportation.

Based on conversations with Fermilab personnel, the probability of occurrence of the above loadings at significant magnitudes is remote, with the exception of Item 4. Construction loads were outside the scope of this review, and Fermilab has indicated that appropriate methods of support will be employed in construction.

3.0 RESULTS OF THE DESIGN REVIEW

The design review process began with a critical assessment of the finite element analyses performed by Fermilab personnel. The analyses were required to accurately estimate the distribution of internal loads throughout the structure. After establishing that the predicted loads were reasonable and appropriate, the major structural components were evaluated for structural integrity and adequacy for service. The loadings considered were due to deadweight and differential thermal expansion due to a prescribed temperature distribution. The AISC Specifications were the primary acceptance criteria, where applicable. Justification was developed for applying the AISC allowable stresses to the materials of construction, AISI Type 304 austenitic stainless steel and Inconel 718 nickel-based alloys, which are not standard materials for the construction of steel structures. In specific cases where the AISC Specifications were not met, engineering judgment was applied to assess the component.

3.1 Review of Finite Element Analyses

Fermilab provided results of detailed finite element analyses performed by Fermilab personnel. The initial analyses considered 2-D and 3-D geometry, fixed or movable supports, deadweight, and thermal expansion due to a prescribed distribution of temperature. At Battelle's suggestion, an analysis was also performed to consider a stick-slip condition between maximally loaded bearing surfaces.

The modeling techniques, assumptions, and final results were carefully reviewed and discussed with Fermilab personnel. A discussion of the items addressed may be found in calculation CC-MOD-01 in the Appendix. As part of the review, an independent check was performed by means of a highly simplified finite element analysis of the CH ring alone. The interaction between the CH and FH rings and between the CH ring and the supports is complex and was not documented in the condensed output provided by Fermilab. However, the structural interactions were crudely approximated by simplified assumptions regarding the loads and boundaries on the CH ring, for checking

purposes. The check analysis was in good agreement with the 3-D FEA results insofar as order of magnitude, sense and distribution of the hoop and bending loads were concerned, although they were in variance with respect to specific values, which was expected. This was considered adequate to establish the credibility of the much more sophisticated and detailed analyses performed by Fermilab.

3.2 Consideration of Frictional Loads on Bearing Surfaces

Each of the individual ring subassemblies is supported in bearing. As-designed, all inter-ring bearing surfaces are bare stainless steel-on-stainless steel. Stainless steel has a notoriously high stick-slip coefficient of friction, typically 0.5 to 1.0. The outer ring assembly is supported in bearing on strips of G-10. References 4 and 5 report metal-insulator static coefficients of friction for uncoated G-10 between 0.3 and 0.5, at both room and cryogenic temperatures. Metals sliding on hard glass-fiber reinforced epoxy generally showed stable (stick-slip-free) slip, but at high coefficients of friction. It is therefore not impossible that significant frictional forces may be generated at the bearing surfaces if there is any tendency for relative motion between the components. This tendency may occur in two situations. One situation is during the construction process, where the frictional loads interfere with the tendency for the structure to settle in. This could occur either with the small incremental build-up of load as the rings are assembled, or by the introduction of large increments of load as major subassemblies are attached. However, analysis of the construction procedure was not within the scope of this review. The second situation is during the cool down process. The prescribed temperature distribution admits of a vertical temperature variation with increasing temperature differential moving downward. It would seem plausible that this may induce a tendency for relative motion between ring assemblies tangentially, in the areas of bearing support.

In both the construction and cool down situations, the distribution of internal forces may be radically different for the finite friction condition than for the zero-friction condition. This was confirmed by the finite element analyses. The actual condition in the physical structure is probably,

but not necessarily, intermediate between the conditions represented in the analyses. The effective coefficient of friction may be reduced to near zero by the application of friction-reducing material on the bearing surfaces, by hydrodynamic lubrication, or by vibration/impact loads. None of these conditions was considered present in the module assembly, as designed. Therefore, the extent to which friction will affect the structural response of the module assembly to loadings was considered unknown, but not trivial. However, the module component designs were based on the zero-friction condition. For the purpose of evaluating components, the following policy was therefore employed. The larger of the loads on a particular component, as calculated by the assumptions friction versus no friction, would be used to evaluate the component. However, if the component design could not be accepted for the loads which considered the effects of friction, a recommendation was made for reducing the possibility of generating friction.

3.3 Relevance of the AISC Specifications to Structures Constructed of AISI Type 304 and Inconel 718

The AISC Specifications for the Design, Fabrication, and Erection of Structural Steel for Buildings were used as the primary criteria for acceptance. A valid concern is whether these criteria are applicable to the structure of interest. The question is a matter of scope, material properties, function of the structure, and appropriate margins of safety.

The AISC Specifications are intended primarily for beam and column structures executed in steel, e.g., buildings. The structures are categorized as three types: rigid-framing or continuous framing, simple framing (shear connections only), and semi-rigid framing, which is intermediate between rigid and simple framing.

The module assembly is not a beam and column structure. However, many of its structural elements perform load carrying functions similar to load carrying elements employed in beam and column construction. This comparison can be made between the endplates or endplate brackets and the splice plates and end connection details used with beams and columns; the endplates or endplate brackets and certain flexural members bent about their major axes; between the endplate connection pins and eyebolt pins; between the main support

beam and general flexural members; between the main straps and general tension members; and between the support frame outside the vessels and general structural members, although this item was not included in this design review. As such, the module assembly is susceptible to similar modes of failure as the analogous members used in more conventional construction. The AISC Specifications are therefore applicable to the module assembly in principle.

As to materials, the AISC Specifications recognize a number of plain carbon and low alloy steels as suitable for framing members, and other steels as suitable for high-strength bolts and rivets. These are listed in Table 2. This list is based on factors such as availability in common structural shapes, economy, weldability, corrosion resistance, and maintenance requirements. Type 304 stainless steel and Inconel 718 are not included in the AISC list because building construction does not require the special properties, and cannot bear the high costs, associated with these materials. The allowable stresses in the Specifications are based on material strength. It can be seen in Table 3 that in terms of material strength, the Type 304 stainless steel and Inconel 718 are the functional equivalent of many of the common structural materials. They also possess the low-temperature toughness and nonmagnetic properties demanded in Fermilab's application. The AISC Specifications therefore are generally applicable to a structure executed in these materials.

The AISC Specifications, being intended for structures that may be utilized by the general public and/or may represent significant monetary investment, are based on an overall safety factor of 2.0 or more on failure, and somewhat less (approximately 1.67) on impairment of the structure (deformation). The various Specifications are based on strength of materials, laboratory tests, general history and experience, and statistical analyses. The module assembly is a unique device intended for rather exotic uses. However, a structural failure could endanger laboratory personnel in the vicinity and result in the loss of costly equipment, and so cannot be tolerated any more than the collapse of a building. To this extent, the factors of safety offered by the AISC Specifications would appear to be appropriate.

TABLE 2. STRENGTH PROPERTIES OF AISC-APPROVED STRUCTURAL STEELS

Steel Type	ASTM Designation	Grade	Minimum Yield Strength, F_y , ksi	Minimum Tensile Strength, F_u , ksi	F_y/F_u
Carbon	A36	-	36	58 - 80	.45 - .62
	A529	-	42	60 - 85	.49 - .70
HSLA	A441	-	40	60	.67
		-	42	63	.67
		-	46	67	.69
		-	50	70	.71
	A-572	42	42	60	.70
		50	50	65	.77
		60	60	75	.80
		65	65	80	.81
	A242 and A588	-	42	63	.67
		-	46	67	.69
		-	50	70	.71
Quenched and Tempered Alloy	A514	-	90	100 - 130	.69 - .90
		-	100	110 - 130	.77 - .91
ERW and Seamless Pipe	A53	B	35	60	.58
Structural Tubing Cold Formed, Round	A500	A	33	45	.73
		B	42	58	.72
		C	46	62	.74
Rectangular		A	39	45	.87
		B	46	58	.79
		C	50	62	.81
Hot Formed, Round	A501	-	36	58	.62
HSLA, Round	A618	I, II, III	50	65 - 70	.71 - .77

TABLE 3. STRENGTH PROPERTIES OF AISC TYPE 304 STAINLESS STEEL AND INCONEL 718

Type	ASTM Designation	Grade	Minimum Yield Strength, F_y , ksi	Minimum Tensile Strength, F_u , ksi	F_y/F_u
18Cr-8Ni Plate, Bar	A-240, A-479, and A-666	302	30	75	.40
		304L	25	70	.36
		304	30	75	.40
		304H	30	75	.40
		304N	35	80	.44
18Cr-8Ni Casting	A-351	CF3, CF8	30	70	.43
19Cr-9Ni Casting	A-743	CF3, CF8	30	70	.43
Precipitation Hardening Nickel Alloy Plate, Sheet and Strip	B-637	-	150	180 - 190	.79 - .83

3.4 Main Support Beams

The two main support beams are oriented parallel to the ring axes, located on the outside circumference of the CH ring at ± 56.25 degrees from bottom dead center of the rings. The beam transfers load from the tension strap, and some portion of the module assembly weight directly, to the pedestals external to the vessels.

The beams are cast Type 304 stainless steel, A-743, Grade CF8. The beams are approximately $93\frac{1}{4}$ inches long, 30 inches deep by $5\frac{1}{2}$ inches thick, tapering to 20 inches deep by 2 inches thick at its ends. The depth of the beam is curved to fit the outside radius of the CH ring, 88.199 inches. It therefore subtends an arc of 19.5 degrees. Bosses are located approximately 19 inches from each end, on which the beam mounts to the external supports. The strap tension and direct module loads are applied at the beam ends. The beams thus act as double overhung cantilevers, loaded in both principal axes.

A free-body analysis was performed to determine the strap tension and direct bearing loads. The analysis assumed a zero coefficient of friction between the contacting surfaces of the beam tip and endplate edges. This analysis determined that the beam is subject to a strap tension (circumferential) load of 123,312 lbs, and a bearing (radial) load of 104,270 lbs at each end. This results in a maximum bending stress of 16,040 psi at the uppermost edge of the beam, or a stress of 20,050 psi with the arbitrary load factor of 1.25. This is less than the allowable bending stress of $0.75 F_y = 22,500$ psi per 1.5.1.4.3* for solid beam sections. The loads also produce a torsional moment and transverse shears. The resultant gross shear was 4,037 psi which was less than the allowable shear stress of $0.40 F_y = 12,000$ psi per 1.5.1.2.1. The maximum local shear due to torsion was 12,657 psi which marginally exceeded $0.40 F_y$. This is considered acceptable because the actual shear resistance is much greater inboard from the beam tips. Refer to calculations CC-MOD-02 of the Appendix.

* This refers to Article 1.5.1.4.3 of the AISC Specifications. All such references are cited by the article number only.

3.5 Support Straps

The two main support straps are slung between the ends of the main support beams, below the module assembly. The endplates of the CH modules in the lower 112 degrees of arc of the CH ring are seated on the straps. The straps thus transfer the weight of the modules to the beam ends in tension. The straps also serve to prevent lateral (horizontal) displacement of the main beams.

The straps are 2 inches thick (radial dimension) and 5 inches wide. They are cast Type 304 stainless steel. The straps are milled to the outside radius of the CH ring, 88.199 inches. They are butt welded to tabs extending circumferentially downward from the main beam castings.

The tension load in each strap was determined to be 123,312 lbs, producing a tensile stress over the gross section area of 12,331 psi, or 15,414 psi with the 1.25 load factor. This is less than the allowable tensile stress of $0.60 F_y = 18,000$ psi, per 1.5.1.1. Some bending may occur in the strap as it deforms to fit the contour of the CH ring. However, these bending stresses are secondary and self-limiting in nature, and cannot be accurately estimated.

The tensile stress of 12,331 psi poses no problem for the butt weld, assuming full penetration, good weld quality, selection of a weld metal of strength equal to or greater than the base material and full radiographic inspection. Post-weld heat treatment may or may not be necessary for this weld, depending on the specific grades of base and weld material.

3.6 Endplate Connection Pins

The modules are assembled into rings by means of lap or splice plates referred to as endplate brackets. The module endplates and brackets are fastened by means of shear pins which comprise bearing connections. The pins are held in place by pin retainers.

The pins used in the CH and FH rings are nominally 2 inches in diameter. The pins used in the EM ring are nominally 3/4 inch in diameter. The pin clearances are 3.5 to 6.3 mils. The original material specification was Type 304 stainless steel. This was later revised by Fermilab to Inconel 718.

Table 1.5.2.1 of Reference 1 specifies allowable shear stresses for various fasteners. These are reproduced in Table 4 for fasteners in bearing connections, with threaded portions excluded from the shear planes. On the basis of this table, an allowable shear stress of $.20 F_U$ would be appropriate. For annealed Type 304 stainless steel, $.20 F_U = 15$ ksi, which is below the working stress of the most highly loaded pin in each ring. For solution-treated and strain-hardened Type 304 (A-193 or A-320, Grade 8, Class 2) suitable for bolts 3/4-inch in diameter or less, $.20 F_U = 25$ ksi. In sizes greater than $1\frac{1}{2}$ inches in diameter, $.20 F_U = 18$ ksi. For Inconel 718, $.20 F_U = 36$ ksi. Reference 2 cites the ultimate shear strength of Inconel 718 as 50 ksi.

The pin forces were calculated using the distribution of radial, circumferential, and bending loads calculated in Fermilab's finite element

TABLE 4. AISC ALLOWABLE SHEAR STRESS FOR RIVETS, PINS, AND BOLTS IN BEARING CONNECTIONS

ASTM Designation	Minimum Yield Strength, F_y , ksi	Minimum Tensile Strength, F_U , ksi	Allowable Shear Stress F_v , ksi	F_v/F_y	F_v/F_U
A-502, Grade 1	40	60	17.5	.44	.29
A-502, Grades 2 and 3	50	70	22.0	.44	.31
A-307, Grade A	36	60	10.0	.27	.17
A-325(a)	81	105	30.0	.37	.29
A-490(a)	130	150	40.0	.31	.27
A-449(b)	58 - 92	90 - 120	20 - 26	.28 - .34	.22

- (a) For threaded portion of fastener excluded from shear planes.
 (b) Material strength varies with fastener size.

TABLE 5. SHEARING STRESSES IN CONNECTION PINS

Ring Type	Pin Diameter, inches	Estimated Stresses, ksi		Allowable Stresses, ksi		
		No Friction	Friction	Annealed 304	Hardened 304 Grade 8, Class 2	Inconel 718
CH	2.0	23.4	39.3	15.0	18.0	36.0
FH	2.0	22.0	18.2	15.0	18.0	36.0
EM	.75	22.9	30.0	15.0	25.0	36.0

may be entirely supported by them. The plates are milled such that when assembled, they form a ring. The general dimensions are as indicated in Table 1.

The pin loads as calculated in Section 3.5 are applied to the plates in-plane, at the pin holes in the corners of the plates. Three modes of failure of the endplates may be identified as a result of these loads. These are bearing (crushing), shear tear-out, and net tensile failure. The AISC Specifications provide allowable stresses and minimum hole-to-hole and hole-to-edge spacings to prevent such failures. Careful review and interpretation of the various Specifications and Commentary(1) was conducted in calculation CC-MOD-04. It was determined that the following allowables are applicable.

Bearing load,

$$P_b \leq .90dtF_y, \text{ per 1.5.1.5.1} \quad (3)$$

Tearout load,

$$P_t \leq .50etF_u, \text{ per 1.16.5.2} \quad (4)$$

or minimum edge distance

$$e \geq \frac{2P}{F_u t}$$

and,

$$P_t \leq (.30A_v + .50A_t)F_u, \text{ per 1.5.1.2.2 Commentary} \quad (5)$$

Table 1.5.2.1 of Reference 1 specifies allowable shear stresses for various fasteners. These are reproduced in Table 4 for fasteners in bearing connections, with threaded portions excluded from the shear planes. On the basis of this table, an allowable shear stress of $.20 F_U$ would be appropriate. For annealed Type 304 stainless steel, $.20 F_U = 15$ ksi, which is below the working stress of the most highly loaded pin in each ring. For solution-treated and strain-hardened Type 304 (A-193 or A-320, Grade 8, Class 2) suitable for bolts 3/4-inch in diameter or less, $.20 F_U = 25$ ksi. In sizes greater than $1\frac{1}{2}$ inches in diameter, $.20 F_U = 18$ ksi. For Inconel 718, $.20 F_U = 36$ ksi. Reference 2 cites the ultimate shear strength of Inconel 718 as 50 ksi.

The pin forces were calculated using the distribution of radial, circumferential, and bending loads calculated in Fermilab's finite element

TABLE 4. AISC ALLOWABLE SHEAR STRESS FOR RIVETS, PINS, AND BOLTS IN BEARING CONNECTIONS

ASTM Designation	Minimum Yield Strength, F_y , ksi	Minimum Tensile Strength, F_U , ksi	Allowable Shear Stress F_v , ksi	F_v/F_y	F_v/F_U
A-502, Grade 1	40	60	17.5	.44	.29
A-502, Grades 2 and 3	50	70	22.0	.44	.31
A-307, Grade A	36	60	10.0	.27	.17
A-325(a)	81	105	30.0	.37	.29
A-490(a)	130	150	40.0	.31	.27
A-449(b)	58 - 92	90 - 120	20 - 26	.28 - .34	.22

(a) For threaded portion of fastener excluded from shear planes.

(b) Material strength varies with fastener size.

analyses. The finite element analyses incorporated both assumptions of zero friction and finite friction between bearing surfaces. The ring loads were resolved onto the endplate brackets to obtain the pin forces, as shown in Figure 3. The resultant pin force is then

$$F_R = [(F_{1-4})^2 + (\frac{1}{2}F_S)^2]^{\frac{1}{2}} \quad . \quad (1)$$

The magnitude of this force varies with the circumferential position around each ring. The pin shear stresses calculated by Equation 1 are summarized in Table 5.

It is imaginable that, as a result of the pin "floating" in its clearances and relative rotations of connected members, load components normally distributed to two pins as shown in Figure 3 may be carried by a single pin. The maximum such load would be equal to

$$F_R = [(|F_N| + |\frac{M}{A}| + |F_S \frac{B}{A}|)^2 + (F_S)^2]^{\frac{1}{2}} \quad . \quad (2)$$

Resultant loads calculated as above would be approximately 50 percent greater than as calculated by Equation 1. However, this condition may be discounted as highly unlikely because (a) any pin hole thus loaded would yield locally (if the pin does not fail in shear) resulting in redistribution of the loads, and (b) the pin clearances, 3.5 to 6.3 mils are very tight, thus requiring very small deflections of the structure to take up slack and generate bearing loads. Refer to calculation CC-MOD-03 of the Appendix for analysis details.

Review of Table 5 indicates that Inconel 718 should be used for the connection pins in all three ring assemblies, and also suggests that means of reducing the high coefficients of friction be considered.

3.7 Module Endplates

The module endplates are the main structural elements of the ring assembly. They comprise the front and back faces of the modules. The width and depth of the endplates exceed those of the modules, so that the modules

FIGURE 3. RESOLUTION OF CONNECTION LOADS

TABLE 5. SHEARING STRESSES IN CONNECTION PINS

Ring Type	Pin Diameter, inches	Estimated Stresses, ksi		Allowable Stresses, ksi		
		No Friction	Friction	Annealed 304	Hardened 304 Grade 8, Class 2	Inconel 718
CH	2.0	23.4	39.3	15.0	18.0	36.0
FH	2.0	22.0	18.2	15.0	18.0	36.0
EM	.75	22.9	30.0	15.0	25.0	36.0

may be entirely supported by them. The plates are milled such that when assembled, they form a ring. The general dimensions are as indicated in Table 1.

The pin loads as calculated in Section 3.5 are applied to the plates in-plane, at the pin holes in the corners of the plates. Three modes of failure of the endplates may be identified as a result of these loads. These are bearing (crushing), shear tear-out, and net tensile failure. The AISC Specifications provide allowable stresses and minimum hole-to-hole and hole-to-edge spacings to prevent such failures. Careful review and interpretation of the various Specifications and Commentary⁽¹⁾ was conducted in calculation CC-MOD-04. It was determined that the following allowables are applicable.

Bearing load,

$$P_b \leq .90dtF_y, \text{ per 1.5.1.5.1} \quad (3)$$

Tearout load,

$$P_t \leq .50etF_u, \text{ per 1.16.5.2} \quad (4)$$

or minimum edge distance

$$e \geq \frac{2P}{F_u t}$$

and,

$$P_t \leq (.30A_v + .50A_t)F_u, \text{ per 1.5.1.2.2 Commentary} \quad (5)$$

where

$A_v = (e_v - \frac{d}{2})t$ = effective shear area

$A_t = (e_t - \frac{d}{2})t$ = effective tensile area

e_v = distance from the hole center to the plate edge in the direction of the shear force component

e_t = distance from the hole center to the plate edge in the direction of the tensile force component

d = pin or bolt and hole diameters

t = plate thickness

P = applied load.

The commentary on the Specifications indicate that these criteria provide a safety factor of 2.0 or more. For additional conservatism, and to account for uncertainties in the differential thermal expansion loading, a factor of 1.25 was applied on loads. The designs of the CH, FH, and EM endplates were found not to comply with the minimum edge distance requirements for pin holes specified by 1.16.5.1. This deviation from specifications may be accepted because the above criteria are consistent with the intent and philosophy of the Specifications.

The load capacities of the joints as estimated by Equation 3, 4, and 5 are summarized in Table 6. Refer to calculation CC-MOD-06 for analysis details.

3.8 Module Endplate Brackets

The module endplate brackets are splice plates which connect the module and plates together to form the rings. The connection fasteners are the previously discussed shear pins.

The endplate brackets experience the same pin hole bearing and tear-out loads as the end plates. The stresses were thus evaluated by the same criteria as the end plates, Equations 3, 4, and 5. The internal loads in the rings also result in bending loads in the brackets about their major axis. These were evaluated in accordance with the Specifications for bending.

TABLE 6. MODULE ENDPLATE CONNECTION LOAD CAPACITIES

Ring Type	Loading	Estimated Capacity, kips	Estimated Load, (1) kips	
			No Friction	Friction
CH	Equation 3	94.0	73.4	123.5
	Equation 4	137.2	38.4	90.3
	Equation 5	143.3	38.4	90.3
FH	Equation 3	67.0	69.0	57.1
	Equation 4	73.2(2)	69.0	57.1
	Equation 5	61.3(2)	69.0	57.1
EM	Equation 3	15.0	10.1	13.3
	Equation 4	19.3(2)	10.1	13.3
	Equation 5	22.7(2)	10.1	13.3

(1) Estimated loads include a Load Factor $LF = 1.25$.

(2) The design of these endplates incorporates cut-outs sufficiently near the connection holes that the ligaments must resist the calculated compression forces.

The pin hole loadings and capacities of the brackets are summarized in Table 7. It can be seen in this table that there is insufficient capacity in the CH bracket for the assumed friction loads, while still retaining an overall safety factor of 2.0. The FH bracket experiences a slight overload of 2.2 percent in bearing with the zero-friction loads. This can be accepted by engineering judgment.

Calculated bending stresses were compared to the specified allowable bending stress in 1.5.1.4.5 of $.60 F_y = 18.0$ ksi. The brackets were checked for effectiveness of the unstiffened web in resisting lateral buckling per the requirements of 1.5.1.4.5 and 1.9.1.2. In all cases the bracket sections were fully effective, and no reduction in allowable compression was required. Transverse shear stresses were compared to the allowable shear stress of $0.40 F_y = 12.0$ ksi, per 1.5.1.2.1. The results are summarized in Table 8. The FH bracket exceeded the allowable bending stress for the friction load case, with a 1.25 load factor, by 2.6 percent. This is acceptable

TABLE 7. ENDPLATE BRACKET CONNECTION LOAD CAPACITIES

Ring Type	Loading	Estimated Capacity, kips	Estimated Load, (1) kips	
			No Friction	Friction
CH	Equation 3	81.0	73.3	123.6
	Equation 4	109.0	38.4	90.2
	Equation 5	84.4	38.4	90.2
FH	Equation 3	67.5	69.0	57.1
	Equation 4	93.8	16.2	17.3
	Equation 5	75.0	16.2	17.3
EM	Equation 3	15.2	10.1	13.3
	Equation 4	21.1	2.7	2.5
	Equation 5	16.9	2.7	2.5

(1) All loads estimated using Equation (1) with a Load Factor
LF = 1.25.

TABLE 8. ENDPLATE BRACKET BENDING AND DIRECT SHEAR STRESSES

Ring Type	Estimated Bending, ksi		Allowable Bending, ksi	Estimated Shear, ksi		Allowable Shear, ksi
	No Friction	Friction		No Friction	Friction	
CH	11.38	16.08	18.0	3.66	4.47	12.0
FH	13.71	18.46	18.0	2.40	3.23	12.0
EM	6.72	5.40	18.0	1.64	1.32	12.0

by engineering judgment. All other stresses were acceptable. Refer to calculations CC-MOD-04 and CC-MOD-05 of the Appendix for the analysis details.

3.9 Module Sheathing

The modules are long trapezoidal-section boxes. The end plates are relatively thick, while the sides are thin plate or heavy gage sheet. All materials are AISI Type 304 stainless steel. The sheet or thin plate elements of the FH and EM modules are tack welded to the endplates and along their lengths. The sheet elements of the CH modules are welded to their endplates all-around, and tack welded along their lengths. The sides typically are perforated. The modules contain numerous layers of uranium plate and other items. The modules are densely packed such that clearances between the sheathing and contents is on the order of the sheathing thickness. The contents weight is supported by the endplates and/or the skins, depending on module orientation.

The modules resemble simply-supported beams in that they are supported by their endplates. Bending or buckling strength of the modules due to self-weight was proven by the fabrication of the modules.

The CH modules are shorter in length at their outside diameters than at their inside diameters. The weight of the FH and EM modules bear on the CH ring inside diameter, which is outboard of the outside diameter. The modules in the lower 180 degree arc of the ring are thus loaded in bending in a double overhung cantilever mode.

The above bending moment was estimated to be 400,000 inch-lbs. This bending moment results in membrane tension and compression stresses in the upper and lower skins of 4,325 psi and -3,385 psi, respectively. These are well within the material strength of the plate or sheet elements, as well as properly executed end weldments.

The buckling stress of the lower skin in membrane compression, treated as a plate with a simple edge support condition all around, was 3,260 psi. This was about the same as the calculated membrane compression stress. However, it was concluded that gross buckling was unlikely because (a) the actual load transfer to the lowermost module may be less due to friction, (b) the selfweight of the module may reduce the applied bending moment,

(c) the welded joints provide some rotational restraint at the edges, and
(d) the tight internal clearances will support or restrain any gross out-of-plane deflections. At worst, some local wrinkling may occur. This was judged not to result in a threat to the structural integrity of the overall assembly. Refer to calculation CC-MOD-07 of the Appendix for the analysis data. Subsequent to the above analysis, Fermilab tested a sample CH module by applying a bending moment of 700,000 in-lb. No damage was observed as a result of this load.

3.10 Transition Pieces

The weight of the EM and FH rings are transferred in bearing by spacers inserted between the rings. The spaces are referred to as transition pieces. They are milled to the radii of the adjacent ring endplates. They also are flanged to correctly locate the rings axially.

Bearing stresses on the transition pieces were well within the allowable bearing stress of $.90F_y = 18.0$ ksi. Refer to calculation CC-MOD-08 of the Appendix for analysis details.

The entire assembly weight bears on the strips of G-10 between the CH ring and the support members. Bearing stress in the G-10 was well within the compressive strength of the material.

4.0 CONCLUSIONS AND RECOMMENDATIONS

The assembly design was reviewed to verify structural integrity and adequacy for service. Components that were evaluated were the main support beams, main support straps, module endplate brackets, module endplates, endplate connection pins, and transition pieces. Loading conditions considered were deadweight and differential thermal expansion due to specified temperature gradients. The American Institute of Steel Construction (AISC) Specifications for The Design Fabrication and Erection of Structural Steel for Buildings were the primary acceptance criteria, where applicable. Other guidelines and engineering judgment were applied as appropriate.

The design review of the various components showed that they are adequate for the intended service, subject to the qualifications stated in this and the next paragraph. The stresses in the main support beams and straps were within the allowables of the AISC Specifications. The designs of the endplates and endplate brackets were found not to comply with certain Specifications addressing minimum edge distances for pin holes. However, they were analyzed in accordance with the bases for the specifications, and found to possess a degree of safety consistent with the intent and philosophy of the specifications. The connection pin stresses were acceptable with the use of Inconel 718 as the material of fabrication. This material is recommended over the originally specified Type 304 stainless steel in any form or grade. The CH module sheathing was determined to be theoretically susceptible to local buckling or wrinkling. However, due to details of construction, such damage is unlikely to occur. This was verified in tests performed by Fermilab which subjected a sample CH module to a 75% overload. Furthermore, if such damage were to occur, it would not threaten the integrity of the structure.

The design of the assembly was based on the assumption that no friction is generated at bearing surfaces. Inter-ring assembly bearing surfaces as-designed are bare stainless steel-on-stainless steel, with a probable unstable (stick-slip) coefficient of friction of 0.5 to 1.0. The assembly-support interface is metal-on-G-10, with a probable stable coefficient of friction of 0.3 to 0.5. Analysis showed that significantly different load distribution within the assembly could occur if certain assumed frictional

5.0 REFERENCES

1. "Specifications for the Design, Fabrication, and Erection of Structural Steel for Buildings", Manual of Steel Construction, Eighth Edition, AISC, 1980.
2. "Metallic Materials and Elements for Aerospace Vehicle Structures, Volumes 1 and 2", Military Standardization Handbook 5E, June 1, 1987.
3. 1987 Annual Book of ASTM Standards, various parts, American Society for Testing and Materials.
4. Friedrich, K., Friction and Wear of Polymer Composites, Composite Materials Series, Volume 1, Elsevier Science Publishers, 1986.
5. Kensley, R. S., and Iwasa, Y., "Frictional Properties of Metal Insulator Surfaces at Cryogenic Temperatures", Cryogenics, Volume 20, January 1980.