Submitted to Journal of the Chemical
Society, Chemical Communications
(In press)

RECEIVED
LAWRENCE
BERKELEY LABORATORY

LBL-6948
Preprint *c.j.*

MAR 8 1978

LIBRARY AND
DOCUMENTS SECTION

NOVEL SALTS OF GRAPHITE AND A BORON NITRIDE SALT

Neil Bartlett, R. N. Biagioni,
B. W. McQuillan, A. S. Robertson, and A. C. Thompson

December 1977

Prepared for the U. S. Department of Energy
under Contract W-7405-ENG-48

TWO-WEEK LOAN COPY

This is a Library Circulating Copy
which may be borrowed for two weeks.
For a personal retention copy, call
Tech. Info. Division, Ext. 5716

LBL-6948
c.j.

— LEGAL NOTICE —

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the Department of Energy, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Novel Salts of Graphite and a Boron Nitride Salt

By Neil Bartlett,* R. N. Biagioni, B. W. McQuillan, A. S. Robertson and A. C. Thompson

(The Chemistry Department, University of California, the Materials and Molecular Research Division, and the Laboratory of Chemical Biodynamics, Lawrence Berkeley Laboratory, Berkeley, California 94720.)

Summary: Graphite is oxidized by $O_2^+AsF_6^-$ and by OsF_6 to give first-stage graphite salts $C_8^+MF_6^-$ and $S_2O_6F_2$ oxidizes both graphite and boron nitride to yield the salts $C_{12}^+SO_3F^-$ and $(BN)_4^+SO_3F^-$, the latter being the first example of a first-stage boron nitride salt.

Salts of graphite in which stable anions such as NO_3^- , HSO_4^- , ClO_4^- , FSO_3^- are intercalated in the galleries of the graphite have long been known.^{1,2} and those derived from well oriented graphite have been shown by Ubbelohde and his coworkers³ to be excellent electrical conductors. We have prepared new graphite salts containing anions of high ionization potential (AsF_6^- , OsF_6^- , SO_3F^-) and the first example of a first-stage boron nitride salt. Our findings support salt formulations also for the highly conducting graphite/ AsF_5 materials.^{4,5}

Treatment of graphite single crystals with OsF_6 yields, at room temperature, material of approximate composition C_8OsF_6 . This, like, MoF_6 and UF_6 relatives,⁶ is blue. The magnetic susceptibility obeys the Curie-Weiss law over the

temperature range $20 \rightarrow 77^\circ$ K with a Weiss constant of 40° and $\mu_{\text{eff}} = 3.5$ B.M.⁷ This magnetic behavior is like that of OsF_6^- salts, typified⁸ by cubic $\text{SF}_3^+\text{OsF}_6^-$, for which the Weiss constant is 4° and $\mu_{\text{eff}} = 3.44$ B.M. Evidently the intercalated osmium species is OsF_6^- . Single crystals of C_8OsF_6 , are hexagonal and the spacing of the carbon sheets is $8.06(10)$ Å and $a_0 = 4.92(5)$ Å- values consistent with C_8X . The former dimension is in harmony with the location of the OsF_6^- species with a threefold axis parallel to $\underline{c}_0$.

Oxidation of graphite single crystals by $\text{O}_2^+\text{AsF}_6^-$, in suspension in SO_2ClF at -63° , yields a blue first stage salt. The crystals are hexagonal with $a = 4.90(5)$, $c = 8.06(6)$ Å. This is in harmony with the composition C_8AsF_6 and, as in the osmium case, suggests that the anions may be oriented with a threefold axis parallel to $\underline{c}_0$. This salt is evidently related to the graphite intercalate, $\text{C}_{10}\text{AsF}_5$, first made⁴ by Selig and his co-workers from graphite and AsF_5 . Vogel and his co-workers have recently demonstrated⁵ that the in-plane electrical conductivity of some graphite/ AsF_5 materials can exceed that of copper. It has been widely supposed that much of the intercalate in these materials is molecular AsF_5 .⁹ Single crystal precession photographs of the first stage graphite compound, obtained by intercalating AsF_5 at $\sim 20^\circ$, are very like those for $\text{C}_8^+\text{AsF}_6^-$ and the unit cell parameters are not significantly different. Moreover, As atom K-shell

absorption edge spectra,¹⁰ shown in the Figure, indicate only one As species in C_8AsF_6 , with absorption edge characteristics similar to those for the As atom in $Cs^+AsF_6^-$, $Xe_2F_3^+AsF_6^-$ and $XeF^+AsF_6^-$ salts.¹¹ For $C_{10}AsF_5$, however, there are two As K-shell absorption edge peaks, one consistent with As(V) and the other, shifted to lower energy by 7.4 eV, and coincident with that of As(III) in As_2O_3 . Evidently the AsF_5 intercalation by graphite is following a course common¹² to AsF_5 oxidations: $3 AsF_5 + 2 e^- \rightarrow 2 AsF_6^- + AsF_3$.

Graphite is quickly oxidized by liquid $S_2O_6F_2$ at room temperature to give a blue first-stage compound of composition $C_{12}SO_3F$. X-ray precession photography shows the graphite interplanar spacing to be $7.86(8) \text{ \AA}$ and loss of $S_2O_6F_2$ at $\sim 20^\circ$ gives a second stage material with a c_0 axis of $11.3(1) \text{ \AA}$. Layer form boron nitride (white) is also oxidized by this oxidant and a deep blue material of approximate composition $(BN)_4SO_3F$ is obtained. X-ray powder photographs show a close similarity to photographs of known first stage graphite salts and the 00 ℓ lines indicate $c_0 = 8.02(5) \text{ \AA}$. A bulk sample of the microcrystalline blue solid proved to be an electrical conductor in contrast with BN which is an insulator. This behavior is consistent with removal of electrons from the highest filled Brillouin zone of the BN. We believe that this

is the first example of a first-stage boron nitride salt.¹³

CAUTION: The boron nitride salt appears to be thermodynamically unstable since on occasions when the $\text{BN/S}_2\text{O}_6\text{F}_2$ reaction mixture has been heated to $\sim 40^\circ$, detonations have occurred. Moreover boron trifluoride is detectable as a decomposition product of the solid. Glemser and his coworkers¹⁴ had previously shown that elemental fluorine converts BN to BF_3 and N_2 and HF converts it to NH_4BF_4 .

We acknowledge support from the Energy Research and Development Authority and an I.B.M. fellowship to R. N. Biagioni.

References

1. F. R. Gamble, and T. H. Geballe, "Inclusion Compounds"
Treatise on Solid State Chemistry, ed, N. B. Hannay,
Plenum Press, New York, 1976, Vol. 3, pp. 89.
2. L. B. Ebert, Annual Review of Material Science, 1976, 6,
181.
3. A. R. Ubbelohde, Nature, 1966, 210(5034), 404; M. J.
Bottomley, G. S. Parry, A. R. Ubbelohde, and D. A. Young,
J. Chem. Soc., 1963, 5674; A. R. Ubbelohde, Proc. Roy.
Soc. A, 1969, 309, 297.
4. Lin Chun-Hsu, H. Selig, M. Rabinovitz, I. Agranat, and
S. Sarig, Inorg. Nucl. Chem. Lett., 1975, 11(9), 601.
5. E. R. Falardeau, G. M. T. Foley, C. Zeller and F. L.
Vogel, J. C. S. Chem. Comm., 1977, 389.
6. J. Binenboym, H. Selig, S. Sarig, J. Inorg. Nucl. Chem.,
1976, 38, 2313; A. A. Opalovskii, Z. M. Kuznetsova,
Yu. V. Chichagov, A. S. Nazarov, A. A. Uminskii,
Russian Journal of Inorganic Chemistry, 1974, 19(8), 1134.
7. Below 16°C, the C_8OsF_6 samples show evidence of anti-
ferromagnetic coupling.
8. N. K. Jha, Ph.D. Thesis, The University of British
Columbia, 1965, p. 104.

References (Contd.)

9. J. E. Fisher in "Electronic Properties of Graphite Intercalation Compounds" Physics and Chemistry of Materials with Layered Structures, ed. F. Levy, D. Reidel, Dordrecht Holland 1977, Vol. 5. in press. L. B. Ebert and H. Selig in Abstracts Franco-American Conference on Intercalation Compounds of Graphite (May 23-27, La Napoule, France).
10. The X-ray absorption experiments at the Stanford Synchrotron Facility were carried out with the help of N. Kafka, J. A. Kirby, M. Klein, J. P. Smith, and T. P. Walker.
11. N. Bartlett, B. G. DeBoer, F. J. Hollander, F. O. Sladby, D. H. Templeton, and A. Zalkin, Inorg. Chem., 1974, 13, 780. A Zalkin, D. L. Ward, R. N. Biagioni, D. H. Templeton, and N. Bartlett, submitted for publication.
12. J. Ballard and T. Birchall, J. Chem. Soc. Dalton, 1976, 18, 1859.
13. A. G. Freeman and J. P. Larkindale, J. Chem. Soc. A, 1969, 1307; A. F. Freeman and J. P. Larkindale, Inorg. Nucl. Chem. Lett., 1969, 5, 937.
14. O. Glemser, and H. Haeseler, Z. anorg. allgem. Chem. 1955, 279, 141.

Figure. X-Ray K-Shell absorption edge spectra of $\text{C}_8^+\text{AsF}_6^-$, $\text{C}_{10}\text{AsF}_5$ and As_2O_3 .

XBL 7710-6305

This report was done with support from the United States Energy Research and Development Administration. Any conclusions or opinions expressed in this report represent solely those of the author(s) and not necessarily those of The Regents of the University of California, the Lawrence Berkeley Laboratory or the United States Energy Research and Development Administration.