Oxy-Combustion Boiler Material Development Final Report

Cooperative Agreement No. DE-NT0005262

Foster Wheeler Project No. 65123579-00

**Prepared by:
Michael Gagliano
Andrew Seltzer
Hans Agarwal
Archie Robertson
Lun Wang**

January 30, 2012

**Foster Wheeler North America Corp.
53 Frontage Road
Hampton, NJ 08827-9000**

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe upon privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

Neither the author, nor any affiliate, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility including, but not limited to, in regard to the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe upon privately owned rights whether such liability or responsibility is of a direct, indirect, special, punitive, incidental, consequential, or other nature and whether arising in contract, warranty, tort including negligence, strict liability or other legal theory. Utilization of the information is with the above understanding.

ABSTRACT

Under U.S. Department of Energy Cooperative Agreement No. DE-NT0005262 Foster Wheeler North America Corp conducted a laboratory test program to determine the effect of oxy-combustion on boiler tube corrosion. In this program, CFD modeling was used to predict the gas compositions that will exist throughout and along the walls of air-fired and oxy-fired boilers operating with low to high sulfur coals. Test coupons of boiler tube materials were coated with deposits representative of those coals and exposed to the CFD predicted flue gases for up to 1000 hours. The tests were conducted in electric tube furnaces using oxy-combustion and air-fired flue gases synthesized from pressurized cylinders. Following exposure, the test coupons were evaluated to determine the total metal wastage experienced under air and oxy-combustions conditions and materials recommendations were made. Similar to air-fired operation, oxy-combustion corrosion rates were found to vary with the boiler material, test temperature, deposit composition, and gas composition. Despite this, comparison of air-fired and oxy-fired corrosion rates showed that oxy-firing rates were, for the most part, similar to, if not lower than those of air-firing; this finding applied to the seven furnace waterwall materials (wrought and weld overlay) and the ten superheater/reheater materials (wrought and weld overlay) that were tested. The results of the laboratory oxy-combustion tests, which are based on a maximum bulk flue gas SO₂ level of 3200 ppmv (wet) / 4050 ppmv (dry), suggest that, from a corrosion standpoint, the materials used in conventional subcritical and supercritical, air-fired boilers should also be suitable for oxy-combustion retrofits. Although the laboratory test results are encouraging, they are only the first step of a material evaluation process and it is recommended that follow-on corrosion tests be conducted in coal-fired boilers operating under oxy-combustion to provide longer term (one to two year) data. The test program details and data are presented herein.

TABLE OF CONTENTS

1.0	EXECUTIVE SUMMARY	1
2.0	INTRODUCTION	7
3.0	PREDICTION OF BOILER GAS COMPOSITIONS.....	7
3.1	FW-FIRE Computer Program Description	7
3.2	Wall-Fired Boiler Furnace Description and Model	9
3.3	Tangential-Fired Boiler Furnace Description and Model	10
3.4	Boiler Performance Under Air and Oxy-Firing	12
4.0	EXPERIMENTAL METHODS.....	21
4.1	Test Parameters and Matrices	21
4.1.1	Materials Selection.....	21
4.1.2	Composition of Test Deposits.....	22
4.1.3	Compositions of Test Gases.....	23
4.1.4	Test Matrices.....	25
4.2	Test Coupons Description and Pre-characterization	25
4.2.1	Pre-characterization of Thermal Spray Coupons	26
4.3	Test Facility.....	37
4.4	Test Procedure.....	39
4.5	Post Test Examinations	39
4.5.1	Rectangular Coupons	39
4.5.2	Thermal Spray Coupons	40
4.5.3	Calculation of Total Metal Wastage and Material Rankings	40
5.0	WATERWALL MATERIALS: RESULTS AND DISCUSSION	43
5.1	Results – Wrought and Overlay Materials.....	43
5.1.1	1% O ₂ Microclimate	44
5.1.2	2% CO Microclimate	44
5.1.3	5% CO Microclimate	45
5.1.4	20% CO Microclimate	46
5.2	Discussion – Wrought and Overlay Materials	64
5.2.1	Effect of Alloy Composition on Total Metal Wastage	64
5.2.2	Effect of Temperature on Total Metal Wastage	64
5.2.3	Effect of Deposit Composition on Total Metal Wastage.....	65

5.2.4	Effect of Gas Composition on Total Metal Wastage	65
5.2.5	Effect of Firing Condition (Air/Oxy) on Total Metal Wastage	66
5.3	Results - Thermal Spray Coatings.....	81
5.3.1	1% O ₂ Microclimate.....	81
5.3.2	2% CO Microclimate	82
5.3.3	5% CO Microclimate	83
5.3.4	20% CO Microclimate	84
5.4	Discussion – Thermal Spray Materials	84
6.0	SUPERHEATER/REHEATER MATERIALS: RESULTS AND DISCUSSION.....	88
6.1	Results	88
6.2	Discussion	100
6.2.1	Effect of Alloy Composition on Total Metal Wastage	100
6.2.2	Effect of Temperature on Total Metal Wastage	100
6.2.3	Effect of Deposit Composition on Wastage.....	101
6.2.4	Effect of Gas Composition on Total Metal Wastage	102
7.0	COMPARISON WITH COAL-FIRED FIELD TEST DATA	111
7.1	Schwarze Pumpe Plant.....	111
7.2	University of Utah.....	111
7.3	Comparison with Electric Furnace Data	112
8.0	CONCLUSIONS.....	114
9.0	REFERENCES	116
10.0	ACRONYMS AND ABBREVIATIONS	117

LIST OF FIGURES

Figure 3.2.1: Outline dimensions of nominal 500 MWe Wall-Fired Boiler.....	9
Figure 3.2.2: Computational model of Wall-Fired Boiler with right side wall removed	10
Figure 3.3.1: Outline dimensions of nominal 500 MWe Tangential-Fired Boiler	11
Figure 3.3.2: Computational model of Tangential-Fired Boiler with right side wall removed ...	12
Figure 3.4.1: Illinois No. 6 wall-fired furnace flue gas temperatures and wall heat fluxes.....	17
Figure 3.4.2: Illinois No. 6 wall-fired furnace wall CO and H ₂ S Levels.....	17
Figure 4.1.1: Waterwall test matrix	28
Figure 4.1.2: Superheater/Reheater test matrix.....	29
Figure 4.2.1: (a) Typical rectangular-shaped corrosion test coupon; (b) Representative arrangement of suspended coupons for corrosion testing (post exposure)	30
Figure 4.2.2: (a and b) Rectangular coupons machined from thick-walled tubing.....	31
Figure 4.2.3: Weld overlay material deposited onto a carbon steel plate (a) top view; (b) cross sectional view.....	31
Figure 4.2.4: Thermal spray coating applied to a carbon steel substrate.....	32
Figure 4.2.5: As received UTE _x 5-450 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface.....	34
Figure 4.2.6: As received UTE _x 5-480 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface.....	35
Figure 4.2.7: As received UTE _x 5-500 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface.....	36
Figure 4.3.1: Simplified Test Furnace Schematic.....	38
Figure 4.5.1: Waterwall coupons after completing 1000 hours of testing under reducing conditions (2% CO)	42
Figure 5.1.1: Representative appearance of wrought and thermal spray coupons after 1000 hours of exposure to 1% O ₂ and 20% CO waterwall conditions	47
Figure 5.1.2: Post cleaning appearance of SA210-A1 and T2 (bottom) coupons after 1000 hours of exposure to 2% CO air-firing (left) and oxy-firing (right) waterwall conditions.....	48
Figure 5.1.3: Post cleaning appearance of 309L and 622 weld overlay (bottom) coupons after 1000 hours of exposure to 2% CO air-firing (left) and oxy-firing (right) waterwall conditions..	49
Figure 5.1.4: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O ₂ air and oxy-firing waterwall test conditions at 399°C (750°F).....	54
Figure 5.1.5: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O ₂ air and oxy-firing waterwall test conditions at 468°C (875°F).....	54
Figure 5.1.6: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O ₂ air and oxy-firing waterwall test conditions at 538°C (1000°F).....	55

Figure 5.1.7: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 399°C (750°F).....	55
Figure 5.1.8: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 468°C (875°F).....	56
Figure 5.1.9: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 538°C (1000°F).....	56
Figure 5.1.10: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 399°C (750°F).....	57
Figure 5.1.11: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 468°C (875°F).....	57
Figure 5.1.12: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 538°C (1000°F).....	58
Figure 5.1.13: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at 399°C (750°F).....	58
Figure 5.1.14: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at 468°C (875°F).....	59
Figure 5.1.15: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at (538°C) 1000°F.....	59
Figure 5.1.16: Photomicrographs showing the surface appearance and subsurface penetration (if evident) on T2 coupons exposed for 1000 hrs at 538°C (1000°F) to deposits containing 5% FeS (top), 20% FeS (middle) and 50% FeS (bottom) under 2%CO air and oxy-firing conditions	60
Figure 5.1.17: Photomicrographs showing the surface appearance and subsurface penetration (if evident) on 309WO coupons exposed for 1000 hrs at 468°C (875°F) to deposits containing 5% FeS (top), 20% FeS (middle) and 50% FeS (bottom) under 2%CO air and oxy-firing conditions	61
Figure 5.1.18: X-Ray dot maps showing the distribution of various elemental constituents on the surface of a T2 coupon exposed to 50% FeS deposits (HSW) at 468°C (875°F) under slightly reducing (2%CO waterwall) air-firing conditions for 1000 hrs.....	62
Figure 5.1.19: X-Ray dot maps showing the distribution of various elemental constituents on the surface of a T2 coupon exposed to 50% FeS deposits (HSW) at 468°C (875°F) under slightly reducing (2%CO waterwall) oxy-firing conditions for 1000 hrs.....	63
Figure 5.2.1: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the slightly oxidizing (1% O ₂) gas composition.....	67
Figure 5.2.2: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the slightly oxidizing (1% O ₂) gas composition.....	67
Figure 5.2.3: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the slightly oxidizing (1% O ₂) gas composition	68
Figure 5.2.4: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the slightly reducing (2% CO) gas composition	68

Figure 5.2.5: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the slightly reducing (2% CO) gas composition	69
Figure 5.2.6: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the slightly reducing (2% CO) gas composition	69
Figure 5.2.7: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the moderately reducing (5% CO) gas composition	70
Figure 5.2.8: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the moderately reducing (5% CO) gas composition	70
Figure 5.2.9: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the moderately reducing (5% CO) gas composition	71
Figure 5.2.10: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the severely reducing (20% CO) gas composition	71
Figure 5.2.11: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the severely reducing (20% CO) gas composition	72
Figure 5.2.12: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the severely reducing (20% CO) gas composition	72
Figure 5.2.13: Influence of flue gas composition on TMW for T2 coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions	73
Figure 5.2.14: Influence of flue gas composition on TMW for T2 coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions	73
Figure 5.2.15: Influence of flue gas composition on TMW for T11 coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions	74
Figure 5.2.16: Influence of flue gas composition on TMW for T11 coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions	74
Figure 5.2.17: Influence of flue gas composition on TMW for 622WO coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions	75
Figure 5.2.18: Influence of flue gas composition on TMW for 622WO coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions	75
Figure 5.2.19: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)	76
Figure 5.2.20: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)	76
Figure 5.2.21: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)	77
Figure 5.2.22: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 468°C (875°F)	77
Figure 5.2.23: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 463°C (875°F)	78

Figure 5.2.24: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 463°C (875°F)	78
Figure 5.2.25: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)	79
Figure 5.2.26: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)	79
Figure 5.2.27: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)	80
Figure 5.3.1: Backscatter SEM image (top) and corresponding spot EDS spectrum taken at the thermal/spray metal interface of UTEx 5-480 exposed to 20% FeS deposits at 538°C (1000°F) for 1000 hr under 2% CO, oxy-firing conditions.....	87
Figure 6.1.1: Representative photomacrographs showing the spent ash deposits covering the surfaces of all 10 SH/RH material coupons following the last 100 hour cycle of the 1000 hour exposure to air-firing (left) and oxy-firing (right) SH/RH test conditions.	89
Figure 6.1.2: Post cleaning appearance of T91 (top) and T22 (bottom) coupons after 1000 hours of exposure to air-firing (right) and oxy-firing (left) SH conditions	90
Figure 6.1.3: Post cleaning appearance of 347H (top) and 304H (bottom) coupons after 1000 hours of exposure to air-firing (right) and oxy-firing (left) SH conditions	91
Figure 6.1.4: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 538°C (1000°F)	94
Figure 6.1.5: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 593°C (1100°F)	94
Figure 6.1.6: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 649°C (1200°F)	95
Figure 6.1.7: Photomicrographs showing the surface appearance and subsurface penetration on 347H material exposed for 1000 hours at 649°C (1200°F) to a deposit containing 0% alkali sulfates (top), 5% alkali sulfates (middle) and 10% alkali sulfates (bottom) under air-firing (left) and oxy-firing (right) conditions.....	96
Figure 6.1.8: Photomicrographs showing the surface appearance and subsurface penetration on T11 – 304H welded coupons exposed for 1000 hours at 649°C (1200°F) to a deposit containing 10% alkali sulfates under air and oxy-firing conditions. Note T22 has experienced significant wastage relative to the Ni-based weld metal, particularly adjacent to the fusion line.....	97
Figure 6.1.9: X-Ray dot maps showing the distribution of various elemental constituents on the surface of 347H exposed to HSS deposit (10% alkali sulfate) at 649°C (1200°F) under synthetic air-firing conditions. Note the presence of high concentrations of oxygen, chromium and sulfur in the intergranularly penetrated region.	98
Figure 6.1.10: X-Ray dot maps showing the distribution of various elemental constituents on the surface of 347H exposed to HSS deposit (10% alkali sulfate) at 649°C (1200°F) under synthetic oxy-combustion conditions. Sodium and potassium species are present in the outer deposits, while the innermost products are rich in chromium, oxygen and sulfur.	99

Figure 6.2.1: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 0% alkali sulfate deposits formulation under air-firing conditions.....	103
Figure 6.2.2: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 0% alkali sulfate deposits formulation under oxy-firing conditions.....	103
Figure 6.2.3: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 5% alkali sulfate deposits formulation under air-firing conditions.....	104
Figure 6.2.4: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 5% alkali sulfate deposits formulation under oxy-firing conditions.....	104
Figure 6.2.5: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 10% alkali sulfate deposits formulation under air-firing conditions.....	105
Figure 6.2.6: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 10% alkali sulfate deposits formulation under oxy-firing conditions.....	105
Figure 6.2.7: Total Metal Wastage vs. Temperature for all T22 coupons tested under SH/RH conditions.....	106
Figure 6.2.8: Total Metal Wastage vs. Temperature for all T22-304H welded coupons tested under SH/RH conditions.....	106
Figure 6.2.9: Total Metal Wastage vs. Temperature for all T91 coupons tested under SH/RH conditions.....	107
Figure 6.2.10: Total Metal Wastage vs. Temperature for all 347H coupons tested under SH/RH conditions.....	107
Figure 6.2.11: Total Metal Wastage vs. Temperature for all 304H coupons tested under SH/RH conditions.....	108
Figure 6.2.12: Total Metal Wastage vs. Temperature for all NF709 coupons tested under SH/RH conditions.....	108
Figure 6.2.13: Total Metal Wastage vs. Temperature for all HR3C coupons tested under SH/RH conditions.....	109
Figure 6.2.14: Total Metal Wastage vs. Temperature for all 622WO coupons tested under SH/RH conditions.....	109
Figure 6.2.15: Total Metal Wastage vs. Temperature for all 33WO coupons tested under SH/RH conditions.....	110
Figure 6.2.16: Total Metal Wastage vs. Temperature for all 72WO coupons tested under SH/RH conditions.....	110

LIST OF TABLES

Table 1.1: Waterwall and Superheater/Reheater Materials Tested.....	4
Table 1.2: Deposit Compositions (in weight %).....	5
Table 1.3: Gas Compositions (in volume %).....	6
Table 3.4.1: As Received Coal Analyses.....	13
Table 3.4.2: Recycle Flue Gas Compositions.....	14
Table 3.4.3: Nominal 500 MWe Wall-Fired Boiler Performance	15
Table 3.4.4: Nominal 500 MWe Tangential-Fired Boiler Performance	16
Table 3.4.5: Wall-Fired Boiler Furnace Wall Microclimates and Bulk Gas Compositions	19
Table 3.4.6: Tangential-Fired Boiler Furnace Wall Microclimates and Bulk Gas Compositions.....	20
Table 4.1.1: Predicted Gas Compositions for a High-Sulfur Wall-Fired 500 MWe Boiler (in volume %).....	24
Table 4.2.1: Nominal Compositions of Thermal Spray Coatings Based on Feed Stock	32
Table 4.2.2: Semi-quantitative EDS Analysis of the As-received Thermal Spray Coating Materials	33
Table 5.1.1a: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 1% O ₂ Air and Oxy-firing Test Conditions.....	50
Table 5.1.1b: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 2% CO Air and Oxy-firing Test Conditions	51
Table 5.1.1c: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 5% CO Air and Oxy-firing Test Conditions	52
Table 5.1.1d: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 20% CO Oxy-firing Test Conditions	53
Table 5.3.1: Depth of Penetration (by Sulfur and/or Oxygen) into the Thermal Spray Coatings	86
Table 6.1.1a: Total Metal Wastage Data (in mils/1000 hr) for all Superheater/Reheater Material Exposed to Air-firing Test Conditions.....	92
Table 6.1.1b: Total Metal Wastage Data (in mils/1000 hr) for all Superheater/Reheater Material Exposed to Oxy-firing Test Conditions	93

1.0 EXECUTIVE SUMMARY

When oxy-combustion is retrofitted to a pulverized coal-fired (PC) boiler, the combustion air is replaced with oxygen and flue gas is recycled back to the boiler to maintain the original heat absorption; in addition the recycle limits the boiler flame temperatures and avoids excessive slagging and fouling. Under this condition, the boiler will operate without de-rating or major changes to the heat transfer surfaces. With the recycle flue gas containing products of combustion (i.e., CO₂, CO, SO₂, *etc.*), it was anticipated that oxy-combustion flue gas may be more corrosive than air-based flue gas. To facilitate oxy-combustion retrofits, Foster Wheeler North America Corp. (FW) conducted a series of laboratory tests to evaluate the corrosiveness of oxy-combustion flue gas vis-à-vis air-fired flue gas. In those tests, coupons of boiler tube alloys, weld overlays, and thermal spray coatings were covered with simulated coal-ash deposits, placed in electric furnaces operating at typical boiler tube metal temperatures, and exposed for 1000 hours to simulated oxy and air-based flue gases that were synthesized from pressurized cylinder gases. Post-test analyses of the coupons were performed, the corrosiveness of oxy-combustion relative to air-fired combustion was evaluated, and materials recommendations were made for this new boiler environment.

A total of ten furnace and ten superheater/reheater materials, listed in Table 1.1, encompassing conventional tube materials, conventional weld overlays, thermal spray coatings, and advanced alloys were tested. Each material was coated with deposits representative of high, medium, and low sulfur coals; the deposits were produced from reagent grade powders to the compositions indicated in Table 1.2. Each material was tested at temperatures that spanned the operating temperatures of subcritical and supercritical boilers.

The corrosion tests were conducted at FW's Livingston, New Jersey, R&D laboratory from October 2009 – March 2011. The program consisted of 27 – 1000-hr test runs; six investigated superheater/reheater corrosion under air-firing and oxy-firing conditions at 538°C, 593°C, and 649°C (1000°F, 1100°F, and 1200°F). The remaining 21 runs investigated furnace waterwall microclimates; four under oxy-firing and three under air-firing each at waterwall metal temperatures of 399°C, 468°C, and 538°C (750°F, 875°F, and 1000°F).

The flue gases used in the test program were synthesized from gas cylinders to compositions established by Computational Fluid Dynamic (CFD) analyses. The U.S. fleet of large electric utility boilers consists primarily of wall and tangential-fired units burning low to high sulfur coals. In Task 2 of this project, FW conducted CFD analyses of nominal 500 MWe wall and tangential-fired boilers operating with low and high sulfur coal under air-firing and oxy-firing conditions. The analyses identified gas compositions throughout the boiler and especially along the furnace walls where potentially corrosive microclimates can develop. If the recycled flue gas is not “cleaned” before returning to the boiler, corrosive species may increase three to fivefold in the boiler. For the case of a 2.5% sulfur, Illinois No. 6 coal, failure to clean the flue gas increased the boiler bulk gas SO₂ level from 2000 ppmv (wet) under traditional air-firing conditions to 9100 ppmv (wet) under oxy-firing. Since the latter would most probably result in excessive superheater/reheater corrosion and require expensive tube material upgrades/replacement not consistent with “saving the boiler”, the flue gas recycle of high sulfur coal units should be cleaned before being returned to the boiler. Although flue gas desulfurization (FGD)

systems can be purchased with sulfur capture efficiencies as high as 98%, if the FGD was operating with only 86% efficiency, the minimum required by New Source Performance Standards for this particular coal, the boiler bulk gas SO₂ levels would increase from 2000 ppmv (wet) to 3200 ppmv (wet). For 0.3% low sulfur and 0.7% medium sulfur coals, failure to clean the flue gas recycle streams (as the plant may not have an FGD system) would result in oxy-firing bulk gas SO₂ levels of 1200 and 2500 ppmv (wet), respectively. With the 3200 ppmv (wet) / 4050 ppmv (dry) bulk gas SO₂ level encompassing low, medium and high sulfur coal conditions, it was selected as an upper limit for oxy-combustion retrofits.

CFD analyses of the tangential and wall-fired boiler showed that the wall-fired configuration produced the highest levels of reducing gases (CO and H₂S) along the furnace walls and that the values were highest for the 3200 ppmv (wet) bulk gas SO₂ oxy-firing condition. As such, the highest CO and H₂S levels (microclimate) recorded by the CFD models served as the upper bound for the simulated test conditions; gas microclimates corresponding to intermediate and low levels of H₂S and CO were also identified under air-firing and oxy-firing environments. The experimental air-firing and oxy-firing gas compositions used in the test program are presented in Table 1.3.

Similar to air-fired operation, oxy-combustion corrosion rates were found to vary with material, temperature, deposit composition and gas composition. Despite this, comparison of air-fired and oxy-fired corrosion test data showed that oxy-firing rates were, for the most part, similar to, if not lower than those of air-firing; this finding applied to the four furnace waterwall, seven superheater, and six weld overlay materials that were tested. Testing of the three thermal spray materials proposed for furnace waterwall applications showed that all allowed sulfur and/or oxygen species to diffuse/penetrate into them. In 186 of the 189 thermal spray coupons tested under the various waterwall environments, sulfur and/or oxygen species penetrated completely through the coatings, whereas in the remaining three coupons half of the coating thickness had been penetrated. At best, the thermal spray coatings would only provide short-term protection.

Laboratory electric furnace testing is a valuable screening tool and a first step for providing short-term corrosion data for a large number of materials subjected to specific, static environments. However, due to the dynamic nature of the boiler environment, there are limitations on the number of variables and critical test parameters that can be addressed with this type of testing. For instance, in a coal-fired boiler ash deposits are constantly replenished, deposit and gas compositions vary as the coal quality/compositions change, large temperature gradients can exist across the ash deposits, etc., and all of the above can vary as the boiler firing rate is adjusted to follow load. As a result, electric furnace tests cannot duplicate all conditions, but instead, attempt to approximate key conditions to gain insight into the corrosion phenomena involved, thereby serving as a first step in evaluating tube materials for potentially harsh combustion environments.

The electric furnace test data suggests that, from a corrosion standpoint, the conventional materials used in subcritical and supercritical pressure air-fired boilers should also be suitable for oxy-combustion retrofits. With the tests having been conducted at conditions that approximate coal-fired conditions, a literature search was performed for comparison with actual coal-fired test data. Unfortunately only limited corrosion data from two different studies were found and the test programs involved different coals, different materials, different temperatures, and different measurement techniques; the results are discussed in Section 7. The data published for a 250-

hour, lignite coal-fired, superheater/reheater corrosion test yielded corrosion rates so low that no measurable difference could be discerned between oxy- and air-firing, while a short term Electrochemical Noise test conducted on the one furnace wall material investigated yielded oxy-fired corrosion rates that were lower than air-firing. Although both of these findings are consistent with the electric furnace tests, in one of the tests, flue gas from a 4% sulfur coal was recycled to the furnace without “cleaning”, resulting in a superheater/reheater environment that showed approximately a fivefold increase in SO₂ concentration (17642 ppmv dry versus 3219 ppmv dry) and, consequently, a corrosion rate on 347H material that was more than 50 times higher than that of air firing. Thus, as indicated by the authors, such conditions “may not be acceptable for utility boiler operation”.

Although there are some inconsistencies between the two aforementioned studies, the agreement of the electric furnace data with the few common data points is encouraging. Nevertheless, follow-up testing, wherein the electric furnace materials are inserted in operating boilers and removed after one- and two-year exposures for evaluations, is recommended. In any event, the fact that the weld overlay materials exhibited excellent corrosion resistance under all test conditions suggests they may provide adequate protection should a corrosion problem develop in a PC boiler retrofitted with oxy-combustion.

Table 1.1: Waterwall and Superheater/Reheater Materials Tested

Waterwall Materials			Superheater/Reheater Materials		
Material	Material Type	Nominal Composition	Material	Material Type	Nominal Composition
SA210-A1	Tubing	Fe-0.27C	SA213-T22	Tubing	Fe-2¼C-1Mo
SA213-T2	Tubing	Fe-½Cr-½Mo	SA213-T304H	Tubing	Fe-18Cr-8Ni
SA213-T11	Tubing	Fe-1¼C-1Mo	SA213-T347H	Tubing	Fe-18Cr-9Ni
T11-T11	Butt Weld	Fe-1¼C-1Mo	T22-T304H	Butt Weld	NA
309L SS	Weld Overlay	Fe-24Cr-13Ni	SA213-91	Tubing	Fe-9Cr-1Mo-V-N
Inco 622	Weld Overlay	Ni-21Cr-13Mo-3W	NF709	Tubing	Fe-21Cr-25Ni-1.5Mo-Nb
VDM Alloy 33	Weld Overlay	33Cr-32Fe-31Ni-1.6Mo	HR3C	Tubing	Fe-25Cr-20Ni-Nb-N
IGS UTE _x 5-500*	Thermal Spray	Fe-15Cr	Inco 622	Weld Overlay	Ni-21Cr-13Mo-3W
IGS UTE _x 5-480*	Thermal Spray	Ni-26Cr-11Mo-2W	VDM Alloy 33	Weld Overlay	33Cr-32Fe-31Ni-1.5Mo
IGS UTE _x 5-450*	Thermal Spray	Ni-40Cr-1Mo	Inco 72	Weld Overlay	Ni-44Cr-Ti

* Composition determined by semi-quantitative EDS

Table 1.2: Deposit Compositions (in weight %)

Compound	Waterwall			Superheater/Reheater		
	LSW	MSW	HSW	LSS	MSS	HSS
Fe ₃ O ₄	5.00	15.00	20.00	0.00	0.00	0.00
FeS	5.00	20.00	50.00	0.00	0.00	0.00
NaCl	0.05	0.10	0.25	0.00	0.00	0.00
KCl	0.05	0.10	0.25	0.00	0.00	0.00
C	5.00	5.00	5.00	10.00	10.00	10.00
SiO ₂	32.45	29.90	12.25	23.00	28.00	26.00
Al ₂ O ₃	32.45	29.90	12.25	23.00	28.50	27.00
CaSO ₄	20.00	0.00	0.00	20.00	0.00	0.00
Fe ₂ O ₃	0.00	0.00	0.00	24.00	28.50	27.00
Na ₂ SO ₄	0.00	0.00	0.00	0.00	2.50	5.00
K ₂ SO ₄	0.00	0.00	0.00	0.00	2.50	5.00
Total	100.00	0.00	0.00	100.00	100.00	100.00

LS = Low Sulfur

MS = Medium Sulfur

HS = High Sulfur

W = Waterwall Deposit

S = Superheater/Reheater Deposit

Table 1.3: Gas Compositions (in volume %)

Gas	Waterwall: Oxy-fired				Waterwall: Air-fired			Superheater/ Reheater	
	1% O ₂	2% CO	5% CO	20% CO	1% O ₂	2% CO	5% CO	Oxy-fired	Air-fired
CO ₂	70.00	69.00	67.00	55.00	14.00	14.00	13.00	69.00	14.00
N ₂	7.66	8.65	7.62	6.55	75.78	74.74	72.71	7.66	73.78
H ₂ O	21.00	20.00	20.00	18.00	9.00	9.00	9.00	21.00	9.00
O ₂	1.00	0.00	0.00	0.00	1.00	0.00	0.00	2.00	3.00
CO	0.00	2.00	5.00	20.00	0.00	2.00	5.00	0.00	0.00
SO ₂	0.32	0.30	0.29	0.17	0.20	0.21	0.19	0.32	0.20
H ₂ S	0.00	0.03	0.07	0.26	0.00	0.03	0.08	0.00	0.00
HCl	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02	0.02
Total	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00	100.00

2.0 INTRODUCTION

When oxy-combustion is retrofitted to a pulverized-coal fired boiler, the combustion air is replaced with oxygen and flue gas is recycled back to the boiler to maintain the original heat absorption; in addition the recycle limits the boiler flame temperatures and avoids excessive slagging and fouling. Under this condition, the boiler will operate without de-rating or major change to its heat transfer surfaces. With the recycle flue gas containing the products of combustion (i.e., CO₂, CO, SO₂, *etc.*) it was anticipated that oxy-combustion flue gas may be more corrosive than air-based flue gas. The objective of FW's program was to assess the corrosion characteristics of oxy-combustion relative to air-based combustion, determine the effect(s) that oxy-combustion has on conventional PC boiler tube materials and coatings, and, if necessary, evaluate the suitability of advanced materials for this new mode of combustion.

In the corrosion test program, coupons of conventional boiler tube materials, conventional weld overlays, thermal spray coatings under development, and alternative/advanced materials were coated with various synthetic deposits that bracketed the range expected for high to low sulfur coals. After coating, the coupons were placed in electric furnaces and exposed to representative air-fired and oxy-fired flue gases for 1000 hours. The flue gases were synthesized from gas cylinders to compositions established by Computational Fluid Dynamic (CFD) analyses. After exposure, the test coupons were removed and analyzed to determine the total metal wastage experienced. Based on the data collected, the corrosiveness of oxy-combustion relative to traditional air-firing was determined, the effects of corrosion on existing boiler tube materials identified, and the possible need for new/alternative materials assessed.

The corrosion tests were conducted at FW's Livingston, New Jersey R&D laboratory from October 2009 – March 2011. The program consisted of 27 – 1000 hr test runs; six investigated superheater/reheater corrosion under air-firing and oxy-firing conditions at 538°C, 593°C, and 649°C (1000°F, 1100°F, and 1200°F). The remaining 21 runs investigated furnace waterwall microclimates; four under oxy-firing and three under air-firing each at waterwall metal temperatures of 399°C, 468°C, and 538°C (750°F, 875°F, and 1000°F). The details of the corrosion test program follow.

3.0 PREDICTION OF BOILER GAS COMPOSITIONS

3.1 FW-FIRE Computer Program Description

FW used its CFD boiler design tool FW-FIRE to predict the gas compositions that would exist along the gas flow path, and especially along furnace waterwalls where highly localized microclimates can exist, of nominal 500 MWe boilers. The boilers were first analyzed operating under air-firing and then when retrofitted with oxy-firing; their predicted gas compositions were compared and a range of gas compositions selected for the corrosion testing.

FW-FIRE (Fossil Fuel, Water-Walled Furnace Integrated Reaction and Emission Simulation) simulates furnace combustion, heat transfer and pollutant formation based on fundamental principles of mass, momentum, and energy conservation. FW-FIRE is an extended and enhanced

version of PCGC-3, a three-dimensional, steady state computer model developed over a period of ten years by the Advanced Combustion Engineering Research Center operated jointly by Brigham Young University and the University of Utah. The FW-FIRE computer program incorporates the latest state-of-the-art coal combustion/gasification, pollutant formation, and physical analysis techniques based on extensive empirical research.

The FW-FIRE code performs general three dimensional, multiphase, gas combustion, steady state analysis of reactive fluid flows. Although FW-FIRE was initially tailored for pulverized coal combustion and gasification, the program is fully capable of analyzing gas-fired and coal-fired boilers.

The FW-FIRE program models the gas flow field as a three dimensional (Cartesian or cylindrical) turbulent reacting continuum that is described locally by the Newtonian form of the Navier-Stokes equations coupled with the energy equation and other appropriate constitutive equations. These equations are solved in Eulerian framework to predict gas properties such as pressure, temperature, velocity, and pollutants and other species concentrations.

The Reynolds stress terms, which result from Favre-averaging of the conservation equations, are approximated using the Boussinesq assumption and effective eddy viscosity. The value of the eddy viscosity and subsequent closure of the turbulence equations is made using either a linear or non-linear k-epsilon two-equation model. The effects of turbulence of the flow field on the combustion reactions are included.

The turbulent flow field is also coupled with the combustion chemistry. Since gaseous reactions are limited by mixing rates and not reaction kinetics, the process chemistry is calculated using locally instantaneous equilibrium based on the degree of mixing of the species. Rate constants for processes such as devolatilization (two step process) and char oxidation are built into the program based on empirical testing.

A Lagrangian model of the particle conservation equations is used to predict particle transport by characterizing the particle field as a series of discrete particle trajectories through the gas continuum. Particles interact with the gas field via mass, momentum, and energy exchange. Particle properties such as burnout, velocities, temperatures, and particle component compositions are obtained by integrating the governing equations along the trajectory paths. The program possesses the capability to input a particle size distribution and chemical composition.

In a pulverized coal flame, the radiation field is a multi-component, non-uniform, emitting, absorbing, gas-particle system. The coal particles cause anisotropic and multiple scattering and the flame is surrounded by non-uniform, emitting, reflecting, absorbing surfaces. The radiation field calculations are based on an energy balance on a beam of radiation passing through a volume element containing the absorbing-reflecting-emitting medium. An Eulerian framework using a discrete-ordinates approach is used to model this process. Heat transfer via radiation and convection to waterwall and tube banks is determined by specifying a local wall temperature and emissivity.

The set of non-linear differential equations is discretized and combined by an upwind and weighted central-differencing scheme. The resulting gas flow field finite difference equations are solved using variations of the SIMPLE/SIMPER algorithm.

The wall-fired unit selected for study was a 460 MWe (gross power) natural circulation boiler similar to one built by FW (plant elevation = 7000 ft). The unit produces 16.65 MPa (2415 psia) 844K (1060°F) steam at a rate of 346 kg/s (2.75 Milb/hr) and 4.14 MPa (600 psia) 844K (1060°F) reheat steam at a rate of 305 kg/s (2.42 Milb/hr). The boiler's outline dimensions are given in Figure 3.2.1. The furnace has a total of 24 opposed wall-fired burners (3 vertical x 4 horizontal x 2 walls) and 10 over-fire air ports. The radiant heat transfer surface consists of 70 mm (2.75") outside diameter (OD) tube waterwalls and five 51 mm (2.0") OD tube partial divisional wall panels. The FW-FIRE model simulates the furnace, in height from the bottom of the hopper to the roof, in depth from the front wall to the rear wall, and in width from the left side wall to the right side wall. Furnace partial division walls were also included in the model. The model contains 528,840 (117x113x40) nodes and is shown in Figure 3.2.2.

Computational Model

Figure 3.2.2: Computational model of Wall-Fired Boiler with right side wall removed

3.3 Tangential-Fired Boiler Furnace Description and Model

The tangential-fired unit selected for study was a 575 MWe (gross power) natural circulation boiler. The unit produces 16.65 MPa (2415 psia) 844K (1060°F) steam at a rate of 479 kg/s (3.80 Mlb/hr) and 4.14 MPa (600 psia) 844K (1060°F) reheat steam at a rate of 421 kg/s (3.34 Mlb/hr). The boiler's outline dimensions are given in Figure 3.3.1. The furnace has six elevations of tilting tangential fuel nozzles and separated over-fire air ports. The radiant heat transfer surface consists of 70 mm (2.75") OD tube waterwalls and twelve 51 mm (2.0" OD) tube partial division wall panels. The FW-FIRE model extends in height from the bottom of the hopper to the roof, in depth from the front wall to the rear wall, and in width from the center wall to the right side wall. Because the furnace is symmetric with respect to the center wall, only half of the furnace was modeled. The panel and platen super heaters were also included in the model. The model contains 113,627 (83x37x37) nodes and is shown in Figure 3.3.2.

Figure 3.3.1: Outline dimensions of nominal 500 MWe Tangential-Fired Boiler

Figure 3.3.2: Computational model of Tangential-Fired Boiler with right side wall removed

3.4 Boiler Performance Under Air and Oxy-Firing

The full load performance of the two boilers was calculated using the Illinois No. 6 and Eagle Butte coals shown in Table 3.4.1, first under air-firing and then retrofitted for oxy-firing. The boilers operated with nominal 3% excess oxygen in their flue gas under air-firing with 20% over-fire air admitted one burner pitch above their top burner row. The oxygen required for oxy-combustion was supplied by a cryogenic air separation unit (ASU) at a purity level of 95% (volume). Both boilers were assumed to have been “tightened” during their retrofit to reduce air-in leakage; recognizing that the air-in leakage will vary from boiler to boiler, for a worst case/maximum reducing conditions analysis a leakage of 1% was assumed and the flue gas excess oxygen level was reduced to a nominal 2% to reduce oxygen consumption, costs, and parasitic power loss.

Table 3.4.1: As Received Coal Analyses

Ultimate Analysis		Illinois 6	Eagle Butte
Ash	%	9.99%	5.70%
S	%	2.51%	0.29%
H	%	4.50%	3.45%
C	%	63.75%	54.09%
H ₂ O	%	11.12%	23.57%
N	%	1.25%	0.72%
O	%	6.88%	12.18%
Total	%	100.00%	100.00%
Volatile Matter (daf)	%	44.35%	44.54%
HHV, as received	Btu/lb	11,666	9,074

In an oxy-combustion retrofit the flue gas recycle rate to the boiler will be set at a value that enables the total heat absorption (furnace plus heat recovery area) of the air-fired boiler to be maintained; this will eliminate the need for either boiler derating or major changes to its heat transfer surfaces and enable the boiler to operate with the same air-fired coal flow rate and feedwater/steam conditions. The temperature and composition of the recycle flue gas, especially its moisture and sulfur levels, can affect the performance of the boiler and its pulverizers and increase corrosion risks. As a result, assumptions had to be made about the equipment provided downstream of the boiler. Since newer boilers are the most likely candidates for oxy-combustion retrofits, the boilers studied herein were assumed to incorporate low NO_x burners, 20% over fire air, an SCR, and a wet flue gas desulfurization systems. DOE/NETL Report 2007/1291 entitled “Pulverized Coal Oxy-combustion Power Plants” presents a design of an Illinois No. 6, oxy-fired plant incorporating those features and in that design the recycle was extracted downstream of a 98% efficient FGD, cooled to 70°C (158°F) to reduce moisture levels, reheated to 66°C (151°F) to minimize corrosion risks to the ducting and downstream components, and mixed with the oxygen supplied to their boiler. To establish a maximum sulfur level that should bracket candidate boilers, the FGD efficiency was reduced to that required by the revised 1979 New Source Performance Standards; this corresponds to a FGD capture efficiency of 86% for the Illinois and 70% for the Eagle Butte coals, and the resulting flue gas compositions are given in Table 3.4.2.

The input data required by FW-FIRE include fuel analysis, coal particle size distribution (mass percentage for each size), waterwall fluid temperatures, and the velocities, flow rates and temperatures of primary and secondary gas streams. The waterwalls of the furnace were assumed to be gray and diffusive. The wall temperature at each location was calculated based on the fluid temperature and the heat flux at the wall cell. For coal devolatilization kinetic properties, Ubhayakar rate parameters were employed for bituminous coal. For Illinois No. 6 coal char oxidation, Sandia kinetic and burning mode parameters were applied for Illinois No. 6 coal. For Eagle Butte coal char oxidation, Sandia kinetic parameters were applied.

Table 3.4.2: Recycle Flue Gas Compositions

(Case 5 Stream 25 from DOE/NETL Report 2007/1291 with modified SO₂)

Component	Mole Fraction		
	Illinois 6	Eagle Butte	
FGD	yes	yes	no
Ar	0.0307	0.0310	0.0310
CO ₂	0.7092	0.7092	0.7081
H ₂	0.0000	0.0000	0.0000
H ₂ O	0.1514	0.1514	0.1514
N ₂	0.0834	0.0834	0.0834
O ₂	0.0249	0.0249	0.0249
SO ₂	0.0004	0.0002	0.0013
Total	1.0000	1.0000	1.0000

The boundary conditions were applied to the computational model and FW-FIRE was run until steady state conditions were achieved. The modeling results are summarized in Tables 3.4.3 and 3.4.4 for the wall-fired and tangential-fired boilers respectively. The coal burnout shown in the tables is the percentage of dry ash-free based coal burned. The furnace exit gas temperature (FEGT) shown in the tables is the average temperature of flue gas before the platen superheater. The Total Boiler Absorption listed is the total energy absorbed by water walls and partial division walls prior to the platen superheater.

Table 3.4.3: Nominal 500 MWe Wall-Fired Boiler Performance

		Illinois 6		Eagle Butte	
		air	O2	air	O2
Coal Flow	lb/hr	319,000	319,000	418,000	418,000
Air Flow	lb/hr	3,299,687	0	3,450,000	0
Oxygen Flow	lb/hr	0	686,109	0	716,118
Recycle Flue Gas Flow	lb/hr	0	2,077,114	0	2,547,250
Flue Gas Flow	lb/hr	3,586,818	3,050,132	3,844,174	3,657,474
Flue Gas Oxygen	%	3.00	2.00	3.00	2.00
Flue Gas Recycle	%, mass	0.0	68.1	0.0	70.0
Inlet O2	%, vol	20.6	28.4	20.6	25.5
	%, mass	23.0	25.0	23.0	22.3
Burnout	%	99.91	99.97	99.87	99.88
LOI	%	0.69	0.21	1.64	1.47
Total Furnace Absorption	M Btu/hr	1768	1819	1652	1619
	MW	518	533	484	474
Division Wall Absorption	M Btu/hr	457	498	438	460
	MW	134	146	128	135
FEGT	F	2108	2092	2122	2088
	K	3335	3306	3360	3299
Total Boiler Absorption	M Btu/hr	3334	3335	3275	3303
	MW	977	977	960	968
Furnace Steam Generation	kg/sec	327	325	322	312
Superheater Spray	kg/sec	19	21	23	34
Total Steam Generation	kg/sec	346	346	345	346
Furnace Steam Generation	M lb/hr	2.60	2.58	2.55	2.48
Superheater Spray	M lb/hr	0.15	0.17	0.18	0.27
Total Steam Generation	M lb/hr	2.75	2.75	2.74	2.75

Table 3.4.4: Nominal 500 MWe Tangential-Fired Boiler Performance

		Illinois 6		Eagle Butte	
		air	O ₂	air	O ₂
Coal Flow	lb/hr	426,338	426,338	558,448	558,448
Air Flow	lb/hr	4,409,974	0	4,609,200	0
Oxygen Flow	lb/hr	0	916,973	0	956,734
Recycle Flue Gas Flow	lb/hr	0	3,179,645	0	3,403,126
Flue Gas Flow	lb/hr	4,793,721	4,480,365	5,135,816	4,886,385
Flue Gas Oxygen	%	3.00	2.00	3.00	2.00
Flue Gas Recycle	%, mass	0.0	71.0	0.0	70.0
Inlet O ₂	%, vol	20.6	25.9	20.6	25.5
	%, mass	23.0	22.7	23.0	22.3
Burnout	%	99.92	99.91	99.83	99.76
LOI	%	0.63	0.71	1.32	1.90
Total Furnace Absorption	M Btu/hr	2144	2004	1985	1831
	MW	628	587	582	536
Division Wall Absorption	M Btu/hr	352	365	338	360
	MW	103	107	99	105
FEGT	F	2302	2286	2286	2246
	K	3685	3655	3656	3582

Plots of furnace flue gas velocities, gas temperatures, particle trajectories, wall heat fluxes, wall temperatures, and wall CO, O₂, and H₂S concentrations were made for each boiler under air and oxy-firing for each fuel and they are discussed in detail in the Project Task 2 Topical Report entitled “Identification of Representative Gas Conditions”. As an example of some of the data, Figure 3.4.1 plots furnace wall heat fluxes and the furnace flue gas temperatures in a vertical plane through the second burner column of the wall-fired boiler under air and oxy-firing with Illinois No. 6 coal. Under air-firing the maximum furnace flue gas temperature is approximately 2072°K (3270°F) and the maximum wall heat flux, located on the side wall at the top of the burner zone, is approximately 207 kW/m² (65,700 Btu/hr-ft²). The maximum temperature of the waterwalls is approximately 694°K (790°F) and of the division walls is approximately 746K (884°F). Under oxy-firing, 68% of the flue gas is recycled to the boiler (boiler operates with 28.4% oxygen by volume) and it results in approximately the same maximum adiabatic flame temperature as the air-fired case. The maximum heat flux is approximately 197 kW/m² (62,300 Btu/hr-ft²), which is about 5% lower than that of the air-fired case and the maximum furnace waterwall temperature is approximately 691°K (785°F), slightly less than the air-fired case.

Figure 3.4.2 presents the CO and H₂S concentrations that exist along the furnace walls with Illinois No. 6 coal under air and oxy-firing. Under air-firing the maximum CO level peaks at approximately 9% due to the sub-stoichiometric staged combustion conditions of the lower furnace and the H₂S peaks at about 1400 ppm (middle of burner zone on the side wall). Under oxy-firing, the wall CO and H₂S concentrations increase significantly peaking at about 20% and 0.26%, respectively.

Figure 3.4.1: Illinois No. 6 wall-fired furnace flue gas temperatures and wall heat fluxes

Figure 3.4.2: Illinois No. 6 wall-fired furnace wall CO and H₂S Levels

The CFD results were post processed to identify the location of and the highest levels of H₂S and CO gases along the furnace walls together with the balance of their gas species. As expected, the CFD analyses showed that the high sulfur coal produced the highest levels of sulfur in the

boilers; in addition, a comparison of furnace wall microclimates showed that the wall-fired boiler had higher levels of CO and H₂S than the tangential-fired boiler. Under oxy-firing the maximum SO₂ level in the superheater/reheater regions and the maximum H₂S levels along the furnace walls of the wall-fired boiler were observed to be about 50% higher than air-firing. With the wall-fired configuration producing the most corrosive furnace microclimates, it was established as a starting point baseline to which four additional study cases were compared. Those additional cases investigated alternate arrangements i.e. extracting the recycle upstream of the FGD, increasing the FGD efficiency, operating with a maximum SO₂ emission rate of 1.2 lbs of SO₂ per million BTU, etc., and their results were compared to the baseline.

In the first two cases, the FGD sulfur capture efficiency was set to zero to investigate either the absence of an FGD or extracting the recycle upstream of the FGD. For the low sulfur coal case, elimination of sulfur removal from the recycle increased the boiler sulfur levels, but they were still well below those of the baseline. For the high sulfur coal case, however, elimination of sulfur removal from the recycle stream significantly increased the boiler sulfur levels; the maximum H₂S level along the furnace walls was observed to be about 2½ times higher and the superheater/reheater SO₂ levels about 4½ times higher than with air-firing. These markedly higher sulfur levels will increase furnace wall corrosion risks and the SA213 type T22 and T91 tubes used in superheaters/reheaters would be especially vulnerable to attack by coal ash corrosion. As a result, when firing high sulfur coals, the flue gas recycled to the boiler should undergo sulfur removal to minimize those corrosion risks. The last cases investigated operating with a higher FGD efficiency or with a maximum SO₂ emission rate of 1.2 lbs of SO₂ per million Btu and their boiler sulfur levels were also seen to be less than the baseline.

Tables 3.4.5 and 3.4.6 identify maximum and intermediate levels of H₂S and CO gases together with the balance of their gas species found along the furnace walls of each of the cases studied. Also identified is the average gas composition exiting the furnace and proceeding to superheater/reheater surfaces located downstream of the furnace. The tables show that the baseline configuration highlighted in bold e.g., the Illinois No. 6 wall-fired boiler resulted in the most corrosive furnace conditions, and it was the basis for selecting the gas compositions for electric furnace corrosion testing presented in Section 4.1.3.

Table 3.4.5: Wall-Fired Boiler Furnace Wall Microclimates and Bulk Gas Compositions

Coal	FGD Eff	Flue Gas Recycle Flow	Location	Condition	CO	H2S	CO2	H2O	SO2	N2	O2	Misc	Total
Air - High S Bit. (Illinois 6)	NA	0%	Lower Furnace	Max CO H2S	9%	0.14%	11%	8%	0.16%	66%	0.5%	5.5%	99.8%
			Lower Furnace	Medium CO, H2S	5%	0.08%	13%	9%	0.19%	69%	0.9%	3.3%	99.9%
			Lower Furnace	Low CO, H2S	2%	0.03%	14%	9%	0.21%	71%	1.5%	1.3%	99.9%
			Furnace Outlet	Average	0.2%	0.00%	14%	9%	0.20%	73%	3.0%	0.2%	100.0%
O2 - High S Bit. (Illinois 6)	98%	71%	Lower Furnace	Max CO H2S	20%	0.24%	47%	17%	0.14%	7%	0.4%	7.3%	99.9%
			Lower Furnace	Medium CO, H2S	10%	0.13%	58%	19%	0.21%	8%	1.0%	3.8%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.06%	63%	20%	0.25%	8%	1.7%	1.8%	99.9%
			Lower Furnace	Low CO, H2S	2%	0.02%	66%	20%	0.26%	8%	2.9%	0.7%	99.9%
			Furnace Outlet	Average	0.5%	0.01%	68%	20%	0.27%	8%	2.7%	0.3%	100.0%
O2 - High S Bit. (Illinois 6)	86%	71%	Lower Furnace	Max CO H2S	19%	0.25%	48%	17%	0.16%	7%	0.5%	6.7%	99.9%
			Lower Furnace	Medium CO, H2S	10%	0.13%	58%	19%	0.23%	8%	1.0%	3.9%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.06%	63%	20%	0.27%	8%	1.6%	1.7%	99.9%
			Lower Furnace	Low CO, H2S	2%	0.02%	66%	20%	0.29%	8%	2.6%	0.7%	99.9%
			Furnace Outlet	Average	0.7%	0.01%	67%	20%	0.29%	8%	2.6%	0.4%	100.0%
O2 - High S Bit. (Illinois 6)	86%	68%	Lower Furnace	Max CO H2S	20%	0.26%	48%	18%	0.17%	7%	0.6%	6.6%	99.8%
			Lower Furnace	Medium CO, H2S	10%	0.13%	58%	19%	0.25%	8%	1.2%	3.6%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.07%	63%	20%	0.29%	8%	1.8%	2.2%	100.0%
			Lower Furnace	Low CO, H2S	2%	0.03%	65%	20%	0.30%	8%	3.0%	0.7%	99.9%
			Furnace Outlet	Average	0.6%	0.01%	67%	21%	0.32%	8%	2.7%	0.3%	100.0%
O2 - High S Bit. (Illinois 6) No FGD	0%	71%	Lower Furnace	Max CO H2S	19%	0.43%	48%	17%	0.48%	7%	0.5%	6.7%	99.8%
			Lower Furnace	Medium CO, H2S	10%	0.23%	58%	19%	0.70%	8%	1.0%	3.7%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.11%	63%	20%	0.83%	8%	1.7%	1.7%	99.9%
			Lower Furnace	Low CO, H2S	2%	0.04%	65%	20%	0.89%	8%	2.9%	0.7%	99.9%
			Furnace Outlet	Average	0.6%	0.02%	67%	20%	0.91%	8%	2.6%	0.3%	100.0%
O2 - Med S Bit. No FGD	0%	71%	Lower Furnace	Max CO H2S	19%	0.12%	48%	17%	0.13%	7%	0.5%	7.6%	99.9%
			Lower Furnace	Medium CO, H2S	10%	0.07%	57%	19%	0.18%	8%	1.0%	5.1%	100.0%
			Lower Furnace	Low CO, H2S	5%	0.04%	63%	20%	0.22%	8%	1.4%	2.5%	100.0%
			Lower Furnace	Low CO, H2S	2%	0.01%	66%	20%	0.24%	8%	3.1%	0.8%	99.9%
			Furnace Outlet	Average	0.7%	0.01%	67%	20%	0.25%	8%	2.7%	0.4%	100.0%
Air - Low S Sub-Bit (Eagle Butte)	NA	0%	Lower Furnace	Max CO H2S	9%	0.02%	12%	11%	0.02%	61%	0.3%	6.4%	99.9%
			Lower Furnace	Medium CO, H2S	5%	0.01%	13%	12%	0.03%	65%	0.8%	3.7%	99.9%
			Lower Furnace	Low CO, H2S	1%	0.00%	14%	11%	0.03%	70%	2.7%	0.6%	99.9%
			Furnace Outlet	Average	0.2%	0.00%	14%	11%	0.03%	71%	3.1%	0.2%	100.0%
O2 - Low S Sub-Bit (Eagle Butte)	70%	70%	Lower Furnace	Max CO H2S	14%	0.03%	52%	21%	0.03%	7%	0.4%	6.3%	99.9%
			Lower Furnace	Medium CO, H2S	10%	0.02%	56%	21%	0.03%	7%	0.5%	4.7%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.01%	61%	22%	0.04%	8%	1.2%	2.2%	99.9%
			Lower Furnace	Low CO, H2S	1%	0.00%	65%	22%	0.04%	8%	3.4%	0.5%	99.9%
			Furnace Outlet	Average	0.5%	0.00%	66%	22%	0.05%	8%	2.4%	0.3%	100.0%
O2 - Low S Sub-Bit (Eagle Butte) No FGD	0%	70%	Lower Furnace	Max CO H2S	14%	0.05%	51%	21%	0.07%	7%	0.4%	6.5%	99.9%
			Lower Furnace	Medium CO, H2S	10%	0.04%	56%	21%	0.08%	7%	0.7%	4.8%	99.9%
			Lower Furnace	Low CO, H2S	5%	0.02%	61%	22%	0.10%	8%	1.4%	2.7%	100.0%
			Furnace Outlet	Average	0.6%	0.00%	66%	22%	0.12%	8%	2.5%	0.4%	100.0%

Table 3.4.6: Tangential-Fired Boiler Furnace Wall Microclimates and Bulk Gas Compositions

Coal	Location	Condition	CO	H2S	CO2	H2O	SO2	N2	O2	Misc
Air - High S Bit. (Illinois 6)	Lower Furnace	Max CO H2S	3%	0.06%	13%	9%	0.19%	70%	1.1%	2.5%
	Lower Furnace	Low CO, H2S	1%	0.02%	14%	9%	0.20%	73%	2.7%	0.7%
	Furnace Outlet	Average	0.2%	0.00%	14%	9%	0.20%	74%	3.1%	0.1%
O2 - High S Bit. (Illinois 6)	Lower Furnace	Max CO H2S	6%	0.09%	62%	20%	0.26%	8%	1.2%	2.5%
	Lower Furnace	Medium CO, H2S	5%	0.07%	63%	20%	0.27%	8%	1.4%	2.0%
	Lower Furnace	Low CO, H2S	1%	0.02%	66%	19%	0.27%	8%	4.2%	0.7%
	Furnace Outlet	Average	1.0%	0.01%	67%	20%	0.29%	8%	2.8%	0.5%
Air - Low S Sub- Bit (Eagle Butte)	Lower Furnace	Max CO H2S	3%	0.01%	14%	12%	0.03%	67%	1.0%	2.5%
	Lower Furnace	Low CO, H2S	1%	0.00%	14%	11%	0.03%	70%	2.7%	0.6%
	Furnace Outlet	Average	0.2%	0.00%	14%	11%	0.03%	71%	3.2%	0.1%
O2 - Low S Sub- Bit (Eagle Butte)	Lower Furnace	Max CO H2S	6%	0.01%	60%	22%	0.04%	8%	1.0%	2.9%
	Lower Furnace	Medium CO, H2S	5%	0.01%	61%	22%	0.04%	8%	1.2%	2.5%
	Lower Furnace	Low CO, H2S	1%	0.00%	65%	21%	0.04%	8%	4.3%	0.4%
	Furnace Outlet	Average	0.9%	0.00%	65%	22%	0.04%	8%	2.8%	0.5%

4.0 EXPERIMENTAL METHODS

4.1 Test Parameters and Matrices

4.1.1 Materials Selection

Due to their relatively low cost, ease of fabrication, fairly high thermal conductivities and low coefficients of thermal expansion, furnace walls of coal-fired boilers are generally fabricated from plain carbon and low alloy steel tubing material. Factors influencing the choice of material selection include steamside pressure, tube metal temperatures, and fireside corrosion; however, for most conventional coal-fired boilers, SA210 Type A1 and SA213 Types T2, T11, and T22 steels are frequently used. In subcritical pressure boilers the furnace walls are cooled with boiling water and, with heat absorption rates varying with furnace location, a 16.7 MPa (2415 psia) natural circulation boiler can have nominal outside furnace wall temperatures of about 427°C (800°F). In supercritical pressure boilers the temperature of the supercritical fluid cooling the furnace tubes steadily increases as it sweeps the walls, such that the outside tube metal temperatures are typically 55°C (100°F) hotter than subcritical pressure units.

Unlike wall tubes which are cooled by direct contact with boiler water, superheater and reheater tubing is cooled by flowing steam. As such, it is not uncommon for tube metal temperatures to be up to 55°C to 110°C (100°F to 200°F) hotter than the steam temperature. With tube strength decreasing and corrosion rates generally increasing with increasing temperatures, different metallurgies are often used in superheater and reheater coils, progressing from perhaps plain carbon or low alloy ferritic tubing to high chromium austenitic stainless steel tubing materials. Superheater/reheater tube materials typically used in 538°C (1000°F) boilers are SA213 ferritic Types T22 (2-1/4 % Cr) and T91 (9% Cr) followed by austenitic materials such as 304H (18% Cr), and 347H (17% Cr) stainless steels.

When boilers were modified to incorporate staged combustion for NO_x reduction, the combustion air stoichiometries within the burner zones were reduced to levels between 0.7 and 0.9. Under these substoichiometric/localized reducing conditions, together with iron sulfide, alkali-chloride, and unburned carbon deposits generated from incomplete coal combustion, significant increases in waterwall corrosion rates have been encountered. Since supercritical pressure boilers operate with higher tube metal temperatures, such units have experienced the most severe corrosion rates, especially those firing high sulfur coals. To extend the life of boiler waterwall tubes, corrosion resistant coatings have been applied to areas along furnace walls experiencing excessive corrosion. The installation of low-NO_x burners has, in some cases, also produced conditions in the heat recovery area that have exacerbated coal ash corrosion. Incomplete coal combustion (promoted by low NO_x burners) can generate carbon-containing ashes that deposit on tube surfaces and may facilitate carburization of superheater/reheater tube surfaces.

To protect boiler tubing from excessive corrosion, thermal spray coatings and weld overlays are frequently employed. Both can be applied in the field but require meticulous cleaning of tube surfaces and strict adherence to application procedures to insure quality control. The thermal spray process can apply a variety of materials (i.e., metal alloys, ceramics, *etc.*) to the outside of boiler tubes in thicknesses ranging from 0.125 to 0.625 mm (5 to 25 mils). Thermal spray coatings, however, only provide protection for a limited time as they typically contain some

degree of porosity and are prone to cracking and spallation, ultimately leading to subsequent attack of the substrate material. Laser claddings and diffusion coatings can also provide corrosion resistance; but among other drawbacks, they require shop installation which generally makes them a less economical choice for existing units. As a result, high chromium weld overlay materials are most often used for long lasting corrosion protection.

With fireside corrosion resistance generally increasing with increasing chromium concentration (and to a lesser extent nickel), a wide variety of weld overlays have been utilized. Type 309 stainless steel (25Cr-13Ni), Inconel 622 (21Cr-55Ni), and Alloy 33 (33Cr-31Ni) are promising or commonly used waterwall weld overlays, whereas, Inconel 622 (21Cr-57Ni) and Inconel 72 (44Cr-55Ni) are currently being investigated/evaluated for use on superheater/reheater tubing. Although these weld overlays can provide the requisite protection, they are expensive to apply and the electric utility industry is looking for less expensive, more easily applied coverings. As a result, manufacturers and developers are conducting research to improve the quality of alternative coating materials, and several thermal spray coatings are showing promise.

Ten waterwall and ten superheater/reheater materials were selected for the Task 4 electric furnace corrosion tests; the materials are identified in Table 1.1. The first seven waterwall materials are wrought tube alloys, similar metal weldments, and weld overlays that are typically used in the U.S. electric utility boiler fleet. The last three materials are thermal spray coatings that have been installed in boilers as test panels for testing/evaluation purposes, and they appear promising.

As for the superheater/reheater materials, the first four are frequently used tubing materials (T22, 304H, and 347H) and a dissimilar metal weldment (T22 to 304H) that is commonly used to join the ferritic to the austenitic portion of the superheater/reheater. T91 is a high strength ferritic steel that began use in utility boiler superheaters/reheaters during the 1990s, whereas, NF709 and HR3C are high creep-strength, advanced austenitic alloys that were developed as lower cost alternatives to high nickel alloys such as Incoloy 800. Although NF709 and HR3C are envisioned for use in future, supercritical and advance-ultrasupercritical pressure boilers, the higher chromium and nickel concentrations make them suitable alternatives to 304H and 347H, should the latter prove vulnerable to corrosion under oxy-combustion conditions. Weld overlays made from Inconel 622, Alloy 33, and Inconel 72 are viable candidates for enhanced corrosion protection on the lower chromium steels.

4.1.2 Composition of Test Deposits

The compositions of the deposits that collect on boiler tube surfaces can have a profound influence on the corrosion behavior. Waterwall deposits typically contain varying concentrations of iron sulfide, alkali chlorides, and carbon, while superheater/reheater deposits are characterized by differing levels of alkali sulfates, chlorides and carbon. The concentration of each deposit constituent fluctuates along the flue gas path, especially along the furnace walls where variations in coal fineness, burner imbalance, and air flow distributions can markedly affect the trajectories, burn-out, and accumulation of coal, char, and ash particles. As a result, there is no “one” standard waterwall deposit composition or superheater/reheater composition, but rather ranges of compositions that may prevail in each area of a given boiler, and these ranges will be dependent on the type of coal being burned.

Coals high in sulfur, such as Illinois No. 6, are typically high in pyritic sulfur and chlorine, whereas, coals low in sulfur, such as Eagle Butte sub-bituminous coal, are typically low in both pyrites and chlorides. Medium sulfur coals, such as Pittsburgh No. 8, typically have values that fall between these two. The amount of iron sulfide and chloride-containing species present in a deposit are related to the levels of pyritic sulfur and chlorides present in the coal. Table 1.2 presents the deposit compositions that were used in the Task 4 electric furnace corrosion test program. In this table LS, MS, and HS designate low, medium, and high sulfur and W and S designate waterwall and superheater/reheater deposits. The proposed deposits collectively bracket the range of corrosive species typically found in the furnace and superheater/reheater sections of boilers burning a variety of North American coals. The deposits were produced by mixing reagent grade powders, adding an organic binder to make a paste, and applying the paste to both sides of the coupons.

4.1.3 Compositions of Test Gases

In Task 2 (CFD modeling), the wall-fired boiler burning high sulfur coal and operating under oxy and air-firing conditions was found to have the highest levels of corrosive constituents (CO and H₂S) along the furnace walls. Cleaning the recycled flue gas limited the boiler bulk SO₂ level to 3200 ppmv (wet) and the resulting flue gas compositions from this case, which also served as a basis for the gas compositions used in the corrosion test program, are presented in Table 4.1.1. Due to high costs of oxygen, oxy-fired boilers with lower levels of excess oxygen are preferred over air-fired boilers; however, doing so may increase the corrosion risks. In order to investigate this, the oxy-fired boiler was assumed to operate nominally with 2% rather than 3% excess oxygen.

Comparing the oxy and air-fired furnace wall micro-climates reveals different levels of O₂ despite similar levels of CO and H₂S. To enable the CO and H₂S effects to be more clearly seen, the small levels of O₂ at the walls were ignored. Chlorine contained in the coal can increase boiler tube corrosion and, since the CFD modeling did not address this gas, a small amount of HCl was added to each test gas. At furnace over-fire air ports, the gas atmosphere can oscillate between slightly oxidizing to slightly reducing and, to study this condition, a 1% O₂ test condition was included in the waterwall test matrix.

After air injection and mixing, the local micro-climates dissipate and the heat recovery areas (SH/RH) operate with a more uniform gas composition labeled “Furnace Outlet” in Table 4.1.1. The 1% O₂ test condition reflects the furnace outlet condition but with the oxygen content reduced to 1%. The gas compositions used in the corrosion tests are presented in Table 1.3. Individual gases from pressurized cylinders were blended to produce the synthetic flue gas. These values approximate the compositions determined from the CFD modeling as presented in Table 4.1.1.

Table 4.1.1: Predicted Gas Compositions for a High-Sulfur Wall-Fired 500 MWe Boiler (in volume %)

Coal	Location	Condition	CO	H₂S	CO₂	H₂O	SO₂	N₂	O₂	Other
Air-fired, High S Bituminous (Illinois #6)	Lower Furnace	Max. CO, H ₂ S	9.00	0.14	11.00	8.00	0.16	65.50	0.50	5.70
	Lower Furnace	Medium CO, H ₂ S	5.00	0.08	13.00	9.00	0.19	68.43	0.90	3.40
	Lower Furnace	Low CO, H ₂ S	2.00	0.03	14.00	9.00	0.21	71.86	1.50	1.40
	Furnace Exit	Average	0.20	0.00	14.00	9.00	0.20	73.40	3.00	0.20
O ₂ -fired, High S, Bituminous (Illinois #6)	Lower Furnace	Max. CO, H ₂ S	20.00	0.26	48.00	18.00	0.17	6.17	0.60	6.80
	Lower Furnace	Medium CO, H ₂ S	10.00	0.13	58.00	19.00	0.25	7.72	1.20	3.70
	Lower Furnace	Low CO, H ₂ S	5.00	0.07	63.00	20.00	0.29	7.64	1.80	2.20
	Lower Furnace	Low CO, H ₂ S	2.00	0.03	65.00	20.00	0.30	8.87	3.00	0.80
	Furnace Exit	Average	0.60	0.01	67.00	21.00	0.32	8.07	2.70	0.30

4.1.4 Test Matrices

The test program was conducted in FW's six, 152.4 mm (6") diameter electric tube furnaces. Each furnace accommodated 30 material coupons which allowed for ten unique materials to be simultaneously tested with three different deposits. The furnaces were operated in groups of three; within each group, each furnace was set at a different temperature, but all three shared a common gas feed.

Figures 4.1.1 and 4.1.2 schematically illustrate the program test matrices; the program involved 21 waterwall furnace test runs and six superheater/reheater furnace test runs.

The waterwall tests utilized the following test conditions:

- Oxidizing case under oxy-combustion gases – 1% O₂
- Oxidizing case under air-fired gases – 1% O₂
- Reducing cases under oxy-combustion gases – 2%, 5% and 20% CO
- Reducing cases under air-fired gases – 2% and 5% CO.

Furnace temperatures used for these waterwall tests were 399°C, 468°C, and 538°C (750°F, 874°F, and 1000°F). Each waterwall coupon was coated with high sulfur (HSW), medium sulfur (MSW) or low sulfur (LSW) deposits.

The superheater/reheater tests utilized one oxy-combustion gas (3200 ppmv [wet]) and one air-combustion gas (2000 ppmv [wet]). The furnace temperatures for these superheater/reheater tests were 538°C, 593°C, and 649°C (1000°F, 1100°F, and 1200°F). Each superheater/reheater coupon was coated with high sulfur (HSS), medium sulfur (MSS) or low sulfur (LSS) deposits. With each furnace containing 30 coupons (10 materials each with three different deposits), a total of 810 coupons were investigated.

4.2 Test Coupons Description and Pre-characterization

The nominal compositions of the wrought alloys and weld overlay materials tested under waterwall and superheater/reheater conditions are presented in Table 1.1. For the most part, the non-thermal spray coated coupon materials used in the test program were rectangular in shape, measuring approximately 19.1 mm (¾") wide by 25.4 mm (1") high by 3.2 mm (⅛") thick, Figure 4.2.1a, and each contained a 2.78 mm (0.11") diameter hole at the top to facilitate hanging from alumina rods that spanned "U" shaped test racks, Figure 4.2.1b. Depending upon the product type (tube versus overlay), the coupons were machined either from thick-walled tubing, Figures 4.2.2 a and b, or weld overlay material that was deposited onto plain carbon steel plate, Figures 4.2.3 a and b. The overlay materials were applied to a thickness of approximately 15.9 mm (⅝") and the rectangular samples were cut from the upper-most portion of the deposited weld overlay to ensure that composition of the weld overlay was consistent with the material requirements (as indicated in the weld wire Material Test Report).

Before the start of the first test series, each rectangular coupon was stamped with a unique identifier along the topmost portion of the coupon. Once identified, pre-test wall thickness

measurements were made using a digital point micrometer at four locations (typically corresponding to a box measuring roughly 13mm [1/2"] x 13 mm [1/2"] square) near the center of the coupon. The measured wall thickness values were recorded and averaged to yield an initial (pre-test) thickness.

Since corners are points of weakness for thermal spray coatings, the thermal spray coupons were bullet shape (see Figure 4.2.4), as recommended by their supplier, Integrated Global Services (IGS). The bullet shaped coupons were machined from 25.4 mm (1") diameter bar stock to a 19.1 mm (3/4") diameter by 38.1 mm (1 1/2") height and the top end was machined to a 9.05 mm radius (3/8"). A tapped hole drilled in the bottom/flat end enabled each coupon to be held while the appropriate coating composition was applied by IGS. The flat end also facilitated bottom support and enabled the bullet shaped coupons to be set into 6.4 mm (1/4") deep recesses that were drilled into the bottoms of "U" shaped racks. Prior to testing, "proof test" coupons of each thermal spray coating were pre-characterized in a scanning electron microscope (SEM) for composition (semi-quantitative, see Table 1.1) and microstructure.

With the thermal spray coated specimens being bullet shaped, each coupon identification number was scribed on the flat bottom. After completion of a 1000-hour test a circumferential cross section was dry cut from the midpoint of the coupon (as recommended by the thermal spray supplier) and the depth of penetration of the corrosive species was evaluated.

4.2.1 Pre-characterization of Thermal Spray Coupons

Upon receiving the bullet-shaped thermal spray coupons, sacrificial samples of each coating were sectioned and subjected to microscopic analysis. The purpose of the evaluation was to pre-characterize the as-supplied coating composition, thickness, and uniformity, and to identify potential flaws or defects that may be inherent to the coating. The nominal composition of the bulk material based on feedstock is presented in Table 4.2.1, while the as-supplied compositions (bulk and individual phase) of the thermal spray coatings by standardless semi-quantitative energy dispersive x-ray spectrometer (EDS) analysis is presented in Table 4.2.2. Note that there are some discrepancies in compositions between the feedstock and what was supplied. These discrepancies are due in part to the thermal spray process, but also due to the limitations of the EDS detector and/or software (i.e., cannot quantify carbon or boron).

Figures 4.2.5 – 4.2.7 are representative SEM backscatter electron images of each thermal spray coating. Since SEM/EDS allows for compositional information, preliminary evaluation was carried out almost exclusively with the SEM. What follows is a brief description of the defining characteristics for each as-supplied coating.

UTEx 5-450 (Figure 4.2.5)

UTEx 450 is a very high chromium (~38%), nickel-based thermal spray coating material. Thickness measurements performed in the SEM indicated that the coating was fairly uniform and generally measured between 0.356 mm and 0.406 mm (0.014" and 0.016"). Relatively high concentrations of oxygen (and oxide particles) were detected in the coating (~10%) as well as voids and/or particles that pulled out during polishing; the voids were apparent both in the bulk coating and along the thermal spray/based metal interface. Partial separation of the coating from the substrate was evident in scattered locations, but no significant evidence of cracking is

apparent anywhere on the prepared cross-sections. The surfaces of all the thermal spray coupons were covered with a thin protective boron, silicon and oxygen-rich coating.

UTEx 5-480 (Figure 4.2.6)

UTEx-480 is a nickel-based thermal spray coating that contains relatively high concentrations of chromium (~25%) and molybdenum (~10%). In the as-supplied condition, fairly high concentrations of oxygen-rich species were identified in the coating, which measures roughly 0.330 mm – 0.381 mm (0.013” – 0.015”) in thickness (not including the translucent boron, silicon and oxygen-rich coating that covers the surface). While no significant cracking is evident, the coating appeared to be partially de-bonded from the substrate in a few scattered locations. Several voids and/or pores were also present throughout the coating thickness. In some places, a few scattered oxides were apparent along or immediately adjacent to the interface; however, EDS reveals very little iron in these oxides.

UTEx 5-500 (Figure 4.2.7)

UTEx-500 is a moderately low Cr (16%), iron-based spray coating that was introduced into this test program as a lower cost alternative to the aforementioned high-Cr, nickel-based thermal spray coatings. The as-supplied thickness was comparatively thinner than both the UTEx-450 and UTEx-480, measuring approximately 0.239 mm – 0.279 mm (0.009” – 0.011”) thick. Although the cross sections were prepared in the same manner as the other spray coatings, a high number density of voids and fairly significant cracking is apparent in most locations. Dark, angular, oxygen-rich particles were scattered along the interface between the thermal spray and base metal.

Figure 4.1.1: Waterwall test matrix

Figure 4.1.2: Superheater/Reheater test matrix

(a)

(b)

Figure 4.2.1: (a) Typical rectangular-shaped corrosion test coupon; (b) Representative arrangement of suspended coupons for corrosion testing (post exposure)

Figure 4.2.2: (a and b) Rectangular coupons machined from thick-walled tubing

Figure 4.2.3: Weld overlay material deposited onto a carbon steel plate (a) top view; (b) cross sectional view

Figure 4.2.4: Thermal spray coating applied to a carbon steel substrate

Table 4.2.1: Nominal Compositions of Thermal Spray Coatings Based on Feed Stock

Material	B	C	Si	Cr	Fe	Ni	Mo	Nb	Ti, Mn, W
UTEx 5-450	1.6	1.0	1.6	38.4	0.0	Bal.	1.2	0.0	0.3
UTEx 5-480	1.6	1.0	1.6	25.2	0.0	Bal.	7.0	1.2	0.0
UTEx 5-500	0.8	NA	0.0	17.0	Bal.	4.2	0.0	0.0	0.0

Table 4.2.2: Semi-quantitative EDS Analysis of the As-received Thermal Spray Coating Materials

Coating ID	Composition	O	Si	Ti	Cr	Fe	Ni	Mo	Nb	W
UTEx 5-450	Bulk	9.00	0.32	0.40	37.12	0.16	50.63	0.91	0.00	0.66
	Light metallic phase	1.67	0.28	0.26	11.23	0.11	21.76	63.79	0.00	0.90
	Light oxide-rich phase	18.42	0.06	0.29	25.89	0.12	56.10	0.13	0.00	0.00
	Dark oxide-rich phase	18.33	0.07	2.58	69.74	0.12	8.00	0.12	0.00	0.54
UTEx 5-480	Bulk	6.71	0.61	0.00	24.89	1.10	56.47	10.29	0.00	0.00
	Bright metallic phase	5.33	0.10	0.00	18.72	0.52	19.78	55.56	0.00	0.00
	Dull metallic phase	3.55	0.15	0.00	66.12	0.61	19.66	9.41	0.00	0.00
	Dark oxide phase	18.98	0.21	0.00	71.29	0.00	6.82	1.94	0.00	0.00
UTEx 5-500	Bulk	1.18	0.85	0.00-	15.93	81.77	0.77	0.00	0.00	0.00
	Light metallic phase	0.77	0.94	0.00-	16.86	81.40	0.23	0.00	0.00	0.00
	Dark metallic phase	0.77	1.04	0.00-	13.92	84.12	0.21	0.00	0.00	0.00
	Oxide-rich phase	18.31	0.56	0.00-	11.79	69.17	0.17	0.00	0.00	0.00

Figure 4.2.5: As received UTEX 5-450 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface

Figure 4.2.6: As received UTEX 5-480 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface

Figure 4.2.7: As received UTEX 5-500 thermal spray coating – (top) full thickness coating; (bottom left) outer surface; (bottom right) thermal spray/base metal interface

4.3 Test Facility

The six electric furnaces used in the test program all have a 152.4 mm (6") inside diameter and were operated at atmospheric pressure. The furnaces were divided into two groups of three with near identical equipment arrangements; a simple schematic representation of the furnace arrangement is shown in Figure 4.3.1. The gases used in the tests were blended from pressurized cylinders to reflect the compositions shown in Table 1.3. Omega precision variable area rotameters were used to set the gas flow to each furnace at approximately 1.9 liters per minute (4 CFH). Since several of the gases were toxic, flammable, and/or asphyxiants, each test area was monitored and alarmed for levels of CO, HCl, H₂S, SO₂, and O₂. The cylinders of toxic and flammable gases were placed in separate gas cabinets that were ventilated by a suction blower that discharged to atmosphere through the roof. In addition, air was continuously withdrawn from the test areas and exhausted to atmosphere to prevent the accumulation of any gases. For safety, the system was interlocked to shut-off all gas flow in the event of a gas detector alarm or the loss of gas cabinet or test area ventilation.

The bulk gases (N₂, CO₂ and CO) were supplied from single component cylinders, while corrosive gases such as SO₂, HCl and H₂S were fed as a blend in 95% N₂; oxygen was fed as air. The bulk gases and air were blended and humidified (by volume) in a temperature controlled humidifying column that saturated the gas stream with the prescribed amount of water vapor. The humidified gas stream was then divided among three heated/insulated lines that maintained the gas temperature at 121°C (250°F) to prevent condensation. Each gas stream was individually introduced into separate furnaces through a mixing chamber. The corrosive gases were also individually metered and introduced directly into the mixing chamber of each furnace. From the mixing chambers, the gases passed over the coupons, exited the furnace, bubbled through a sodium carbonate-water solution, which captured sulfur and chloride compounds, and was discharged through the building roof.

Regarding the superheater/reheater tests, prior to entering the furnace, the gas streams were passed over a platinum catalyst in order to convert a portion of the SO₂ to SO₃, a primary constituent required for the formation of alkali iron tri-sulfates. No catalyst was used during the waterwall tests.

Figure 4.3.1: Simplified Test Furnace Schematic

4.4 Test Procedure

The synthetic ash deposits that were applied to the corrosion coupons were produced by mixing measured amounts of reagent grade powders in batch sizes sufficient for a 1000 hour test run. Once blended, the synthetic ash deposits were sealed in a container and thoroughly mixed for a period of at least 24 hours. A sample of material was removed from the batch before each test interval and subjected to SEM/EDS to ensure homogeneity of the mixture relative to the mix recipe; sulfur analyses were also run to ensure that the sulfur content within each deposit was consistent with the test parameters.

Prior to application, an organic camphor binder dissolved in ethanol was added to each powder to form a paste. This paste was applied to an approximate thickness of 3 mm ($\frac{1}{8}$ ") around the circumference of the bullet shaped coupons and on both sides of the rectangular test coupons. The specimens were then mounted onto two "U" shaped fixtures and placed end to end in each furnace. The first ten coupons were coated with low sulfur deposit, the second ten with medium sulfur, and the third ten with high sulfur deposit; the direction of gas flow was from the low sulfur-containing deposits to the high sulfur-containing deposits.

Once loaded, the furnaces were sealed, purged with inert gas (argon) to prevent premature corrosion from taking place, and slowly heated overnight. Upon reaching the test temperature the following morning, the purge gas was switched off and the appropriate flue gas mixture was introduced and maintained at a steady flow rate throughout the test cycle. To ensure that fresh corrodent species were continuously in contact with the metal surfaces, the appropriate synthetic ash mixtures were replenished at 100 hour intervals. After each 100 hour test cycle, the furnaces were cooled under an argon purge until ambient temperature was reached; the specimens were then removed and cleaned of the spent ash mixture. Cleaning was accomplished by tapping the side of the coupon, and/or lightly brushing the surface with a nylon brush. This allowed friable, loosely adherent material to be removed from the surface, while the harder, more tenacious deposit, oxide and or corrosion product layers remained on the coupons. The coupons were visually inspected and recoated with fresh deposits to facilitate further corrosion. The intention of the cleaning procedure was not to re-expose bare metal surfaces at each 100 hour interval, but rather to replenish the supply of corrodents. After coating, the coupons were returned to the furnace and the cycle repeated until the total exposure period of 1000 hours was completed.

4.5 Post Test Examinations

Following 1000 hours of exposure, the samples were removed from the furnace; representative photographs of several coupon samples taken after exposure to various test conditions are shown in Figure 4.5.1. The type of analysis that was performed differed for each of the coupon types.

4.5.1 Rectangular Coupons

The rectangular shaped coupons were evaluated both macroscopically and microscopically for evidence of gross wall loss and subsurface penetration; the combination of which was reported as the total metal wastage (TMW). Specimens measuring approximately 6.4 mm x 19.1 mm x 3.2 mm ($\frac{1}{4}$ " x $\frac{3}{4}$ " x $\frac{1}{8}$ ") were dry cut from the lower portion of each rectangular coupon, and

carefully mounted in a phenolic-based thermosetting mounting media to minimize loss of the deposit and corrosion products. After mounting, the samples were rough ground with abrasive media (no water cooling) and dry polished to retain any possible water soluble species. Optical microscopy was used to evaluate the corrosion morphology (including pitting), quantify the depth of intergranular penetration (e.g., sulfidation, oxidation and/or carburization), and assess any other adverse reactions, and/or microstructural alterations that may have occurred. Pit depths and subsurface penetrations were quantified using a calibrated video imaging system that was interfaced with a metallographic microscope. Further evaluations of the deposits, scales and/or corrosion products, as well as the nature of the subsurface penetration (oxides, sulfides, carbides) were performed on select samples using an SEM equipped with an EDS system.

The surfaces of the remaining portions of the coupons were lightly grit-blasted to remove the deposits, corrosion products and oxides, and measured with a calibrated point micrometer at the locations corresponding to the initial thickness measurements. Although grit blasting was found to reduce the total coupon thickness by approximately 0.005 mm (0.0002"), or roughly 0.0025 mm (0.0001") per side, this loss was both systemic and considered negligible, and therefore not included in the final thickness calculation. The average and maximum wall loss resulting from corrosion was determined based upon the differences in initial and final coupon thicknesses.

It should be pointed out that the data were generated for relatively short exposure times and were intended for comparative purposes to aid in the determination of the most suitable candidate material under such conditions. Thus, the reported values for wall loss, depth of subsurface penetration and maximum total metal wastage were not extrapolated, neither linearly nor parabolically, to yield expected corrosion rates based on one or more years of service, but instead, expressed as mils/1000 hours, which represented the test duration.

4.5.2 Thermal Spray Coupons

One circumferential cross section was dry cut from near the midpoint (as recommended by IGS) of each bullet shaped coupon. Evaluation of these coupon samples was much different than the wrought or overlay samples in that no macroscopic evaluation was performed. This was due to the fact that, unlike weld overlays, which form a metallurgical bond with the substrate material, thermal spray coatings are applied on top of the substrate material and only form mechanical bonds making them susceptible to spallation. Furthermore, the thermal spray process produces microstructures consisting of many different metallurgical, intermetallic, and oxide phases, along with a small amount of porosity, which may allow corrosive species to penetrate through the coating and react with the substrate material. Since optical microscopy is inadequate for phase identification (namely the aggressive ash constituent), SEM was employed to assess whether the thermal spray coatings provided adequate protection by preventing reactions with the substrate materials, and quantify the depth of penetration into the coating.

4.5.3 Calculation of Total Metal Wastage and Material Rankings

Total metal wastage (TMW) was calculated based on the combination of the maximum measured wall loss (macroscopic) and the maximum measured depth of subsurface penetration (microscopic). Although the deepest penetration was generally not observed directly beneath the area exhibiting the maximum wall loss, by calculating the total metal wastage as the combination of the two, the reported values represent a conservative "worst case" estimate. The calculation

for maximum wall loss (WL) resulting from corrosion was determined based upon the differences in average initial wall thickness ($AVG_{initial}$) and final minimum measured wall thickness (MIN_{final}), when pitting was not present. Since each coupon has two surfaces exposed to the corrosive ash, the measured difference between the initial and final values was divided by two in order to determine the wall loss per side such that:

$$WL = (AVG_{initial} - MIN_{final})/2 \quad \text{[when no pitting is present]}$$

Where only a few discrete pits or localized areas of deeper metal loss were noted, pitting was quantified either by direct measurement or through optical microscopy, and wall loss was calculated as the difference in average initial thickness, $AVG_{initial}$, and average final thickness, AVG_{final} , per side plus the depth of the deepest measured pit (DP):

$$WL = (AVG_{initial} - AVG_{final})/2 + DP \quad \text{[when pitting is present]}$$

Regarding the microscopic wastage, subsurface penetration (Pen) was quantified by measuring the maximum depth to which oxygen or sulfur-containing species penetrated and/or carburization was noted. The total metal wastage (TMW) is:

$$TMW = WL + Pen$$

Based on the results of the air-fired and oxy-fired test conditions, a relative ranking for each material under air and oxy-fired conditions will be assigned; the extent to which corrosion may be influenced by oxy-firing (relative to air-firing) will be determined; whether or not conventional boiler materials possess the requisite corrosion resistance for such environments will be evaluated, and the need and suitability of the tested high chromium wrought tube materials and weld overlay/coatings for oxy-combustion conditions assessed.

Low Sulfur Deposit

High Sulfur Deposit

Figure 4.5.1: Waterwall coupons after completing 1000 hours of testing under reducing conditions (2% CO)

5.0 WATERWALL MATERIALS: RESULTS AND DISCUSSION

5.1 Results – Wrought and Overlay Materials

Following exposure to the prescribed waterwall environments for 1000 hours, the surfaces of the coupons were generally covered with fairly thick and tenacious deposits with color ranging from bright orange to grayish-black depending on the gas condition and deposit type, Figures 4.5.1 and 5.1.1. The thickness and tenacity of the oxide and/or corrosion product layers beneath the ash deposit, as well as the degree of metal wastage, varied significantly with gas composition, combustion environment (air-firing or oxy-firing), deposit composition, testing temperature, and material composition. The deposits were removed by light grit blasting and the coupons photographed to visually record their conditions. Figure 5.1.2 and 5.1.3 are photographs of four post test material coupon arrays and the reader is referred to the Task 4 Topical Report for the balance of the photographs.

The maximum measured wall loss value for each material exposed to various temperatures and deposits under 1% O₂ (air and oxy), 2% CO (air and oxy), 5% CO (air and oxy) and 20% CO, are summarized in Tables 5.1.1a – 5.1.1d, respectively, and expressed graphically (for each exposure temperature) by the bar graphs presented in Figures 5.1.4 - 5.1.15. In general, most of the wrought materials (including the T11 to T11 weld) sustained some degree of metal wastage for most test conditions, especially at 468°C (875°F) and 538°C (1000°F), with the notable exception being the 1% O₂ case where little to no evidence of wall loss was observed regardless of the gas, temperature and deposit conditions. For the most part, the weld overlay materials exhibited excellent corrosion resistance under all testing conditions, as evidenced by their smooth, even surface contours.

Figures 5.1.16 and 5.1.17 are select optical micrographs showing the deposits, oxides and/or corrosion products covering the surfaces of T2 and 309LWO waterwall materials, as well as the surface profile and degree of subsurface penetration; micrographs of coupons tested under the corresponding air and oxy-firing conditions are presented for comparison. Relative to the wrought materials, subsurface penetration was slightly more prevalent on the weld overlay materials exposed to the highest testing temperatures (875°F and 1000°F) under reducing conditions (2% CO and 20% CO); however, most overlay samples exhibited little to no penetration (<0.5 mils) due to the relatively low test temperatures (≤1000°F). The one exception was 309WO which exhibited moderately deep penetration upon exposure to 20% and 50% FeS deposits at 468°C (875°F) and 538°C (1000°F) under slightly reducing conditions, Figure 5.1.17. The maximum measured depth of penetration was quantified using a calibrated video imaging system interfaced with a metallographic microscope at magnifications between 100x and 500x; the results for all 1% O₂, 2% CO, 5% CO and 20% CO test conditions are presented in Tables 5.1.1a through 5.1.1d, respectively. For wrought alloys, the deposit, oxide and/or corrosion product layers on coupon exposed to air-firing conditions were generally thicker and more tenacious than those on coupons exposed to the same oxy-firing condition, Figure 5.1.16.

Total metal wastage was calculated as the combination of the maximum measured wall loss (including pitting) and the maximum depth of subsurface penetration. While the deepest penetration may not have occurred in conjunction with the maximum wall loss, by calculating

the total metal wastage as the combination of the two, the reported values represent a conservative “worst case” estimate. Based on the results of the waterwall tests, under the same test gas compositions (i.e., 1% O₂, 2% CO, and 5% CO), total metal wastage was generally less severe under oxy-firing conditions than for air-firing. However, when considering the “worst case” gas composition for each firing condition (e.g., 2% CO air versus 20% CO oxy), the 20% CO oxy-combustion condition was slightly more corrosive than the 2% CO air-firing case. It was interesting to note that the total metal wastage data for the three wrought and one butt-welded ferritic material were fairly consistent, suggesting that, similar to air-firing experience, small incremental increases in chromium for materials containing $\leq 2\frac{1}{4}\%$ provided little to no benefit against waterwall (FeS) corrosion.

In addition to the macroscopic and microscopic assessments, samples exposed to the various gas conditions were also evaluated by SEM and EDS. Due to the overwhelming number of coupon samples in the waterwall test matrix, x-ray maps showing the distribution of elemental constituents were constructed on only select coupon samples with 20% and 50% FeS deposits as they exhibited the most severe metal loss and/or wastage; two representative x-ray maps showing the elemental distribution at the surface of a T2 coupon exposed to 50% FeS deposits at 468°C (875°F) under slightly reducing (2% CO) air and oxy-firing conditions are presented in Figures 5.1.18 and 5.1.19, respectively. In general, for each test condition, sulfur and oxygen-containing species were found throughout the deposit and corrosion products covering the coupon surfaces. For the most part, sulfur was generally more prevalent than oxygen in the outer deposits and, in some cases, outermost corrosion products (away from the metal), while oxygen was more prevalent within the innermost corrosion products (near the corrosion product/metal interface). As the gas condition became more reducing, however, the concentration of sulfur within the corrosion products significantly increased, such that under highly reducing conditions, much higher concentrations of sulfur, relative to oxygen, were noted throughout the deposit and corrosion products, even for the 20% FeS deposit.

5.1.1 1% O₂ Microclimate

As indicated previously, Figures 5.1.4 through 5.1.6 graphically present the total metal wastage for each material exposed to various deposit compositions under slightly oxidizing (1% O₂) air and oxy-firing conditions at 399°C (750°F), 468°C (875°F) and 538°C (1000°F), respectively. The ferritic materials showed an increase in wastage with increasing temperature under both air-firing and oxy-combustion atmospheres, whereas the weld overlay materials showed virtually no change. Regardless of the deposit type, gas condition, and testing temperature, metal loss and subsurface wastage was minimal; for the wrought ferritic materials total metal wastage was less than 127 μm (0.005”), while total metal wastage on the overlay materials was typically less than 25 μm (0.001”). With wastage rates being so small, there was little difference between air and oxy-firing.

5.1.2 2% CO Microclimate

Unlike the 1% O₂ which showed very little change in wastage (total magnitude) with temperature, wastage was highly dependent on temperature for the 2% CO air and oxy-firing gas condition. With the exception of the SA-210 A1 sample coated with 20% FeS deposits and exposed to air-firing conditions, which sustained 221 μm (0.0087”) of wastage, all of the other wrought and weld overlay materials exposed to the slightly reducing (2% CO) gas condition at

399°C (750°F) exhibited only shallow wastage in the form of wall loss. Wastage was typically less than 0.004” (4 mils) and was fairly similar for air and oxy-firing conditions.

At 468°C (875°F), the wrought materials exposed to air-firing conditions exhibited considerably more wastage than those tested under oxy-firing conditions. In fact, the resulting wall loss (little to no penetration) upon exposure to air-firing condition was typically more than double, as illustrated in Figure 5.1.8. Regarding the overlays, 622WO and alloy 33WO generally exhibited excellent corrosion resistance under both air and oxy-firing conditions; however, all of the 309L weld overlay samples exposed to deposits containing 20% and 50% FeS at 468°C (875°F) – air and oxy-firing – sustained relatively deep subsurface penetration along interdendritic phase boundaries.

At 538°C (1000°F), the wrought materials generally exhibited significant wastage under both air and oxy-firing conditions; however, wall loss was considerably more severe under air-firing conditions (all other variables being equal). Under air-firing conditions, the maximum measured wastage was 838 μm (0.033”) and occurred on the T11-T11 weld samples covered with a 20% FeS deposit mixture; for oxy-firing conditions, the maximum observed wastage of 882 μm (0.019”) was noted on the unwelded T11 sample exposed to the same deposit mixture. As with the 468°C (875°F) exposure, with the exception of the 309WO sample coated with the 50% FeS deposit mixture, the weld overlay materials generally exhibited excellent corrosion resistance under both air and oxy-firing condition, with total metal wastage typically less than 100 μm (0.004”).

5.1.3 5% CO Microclimate

Following the post test evaluation of coupons subjected to the 5% CO oxy-firing condition, analysis revealed that all of the wrought and overlay materials tested at 468°C (875°F) and 538°C (1000°F) showed little to no evidence of wall loss or penetration. In fact, all of the wrought materials exposed to 399°C (750°F) exhibited significantly more wastage than those exposed at the higher temperatures. Although the overall consistency of the deposits was unlike most of the other test exposures (including the air-fired case), testing progressed as there was no basis for aborting the furnace test run. Only after the completion of the 1000 hour test, when the coupons were sectioned and cleaned, was the absence of corrosion noted.

In light of these findings, the decision was made to retest several of the wrought (T2 and T11) and all of the overlay (309WO, 633WO and 33WO) materials under the same test conditions to determine whether the extremely low corrosion rate values were indeed valid (the full gamut of ferritic materials was not tested as the wastage experienced by the A1 and the T11-T11 materials in all other test runs had been similar to T2 and T11). Since scheduling and budgetary constraints did not allow for the 1000 hours of testing, the results of a short-term 300 hour re-test were linearly extrapolated (by multiplying by 3.33) for comparison with the other test data. The maximum measured wastage for the 1000 hours air-firing test and the linearly extrapolated estimate for the 300 hour re-test under oxy-combustion conditions are presented in Table 5.1.1c (the original data ruled suspect was recorded and can be found in Appendix A of the Task 4 Topical Report). For the most part, the short-term re-test results were fairly consistent with the results from other test conditions, including the 5% CO air-firing condition, in that it showed that wastage generally increased with increasing temperature and concentration of FeS in the deposits, up to 20%.

All of the wrought materials tested under the 5% CO at 399°C (750°F) exhibited less than 100 μm (0.004”) under air-firing conditions and less than 40 μm (0.0014”) of wastage under oxy-firing conditions. At 468°C (875°F) moderate to severe wastage was noted under air-firing conditions, with corrosion losses ranging between 175 μm and 330 μm (0.0070” – 0.0013”), and only shallow wastage of less than 135 μm (0.0053”) observed under oxy-firing conditions. Results from the highest temperature, however, were significantly different as wastage of the wrought materials under air-firing conditions were somewhat similar to what was observed at 468°C (875°F), but much greater (nearly 2x) under oxy combustion conditions. Under air-firing conditions, the maximum measured wastage was 381 μm (0.0150”) and occurred on the T11-T11 weld samples covered with a 20% FeS deposit mixture; for oxy-firing conditions, the maximum observed wastage of 676 μm (0.0266”) was noted on the T2 coupon sample coated with the 20% FeS deposit mixture (although very similar results were also noted for the 5% FeS deposit mixture). Regardless of the combustion mode (air or oxy), the weld overlay materials generally exhibited excellent corrosion resistance for all temperatures and deposit compositions with maximum total metal wastage values less than 75 μm (0.003”).

5.1.4 20% CO Microclimate

Since CFD analyses had predicted that the 20% CO condition could only occur under oxy-combustion conditions (a maximum of 9% was predicted under air-firing), only oxy-firing data are presented in Figures 5.1.13 – 5.1.15. The corrosion behavior of the wrought materials exposed to the 20% CO gas condition was highly dependent on the test temperature, but relatively insensitive to deposit composition and chromium content. While the ferritic materials exposed at 399°C (750°F) sustained little to no wastage (less than 50 μm [0.002”]), significant metal loss (in excess of 610 μm [0.024”]) was noted on all four wrought ferritic materials tested at 538°C (1000°F). In fact, of all the test conditions evaluated in this study, the 20% CO (oxy-fired) at 538°C (1000°F) proved the most corrosive, with maximum metal loss values slightly higher than those observed for the most severe air-fired condition (2% CO at 538°C [1000°F]). Although corrosion losses on the wrought materials was significant, the weld overlays exhibited excellent resistance to corrosion for all temperatures and deposit compositions as the maximum observed wastage was 92 μm (0.0037”) for all weld overlay materials.

1% O₂, High Sulfur Deposits

20% CO, High Sulfur Deposit

Figure 5.1.1: Representative appearance of wrought and thermal spray coupons after 1000 hours of exposure to 1% O₂ and 20% CO waterwall conditions

SA210 A1: Air-fired, 2% CO

SA210 A1: Oxy-fired, 2% CO

T2: Air-fired, 2% CO

T2: Oxy-fired, 2% CO

Figure 5.1.2: Post cleaning appearance of SA210-A1 and T2 (bottom) coupons after 1000 hours of exposure to 2% CO air-firing (left) and oxy-firing (right) waterwall conditions

309WO: Air-fired, 2% CO

309WO: Oxy-fired, 2% CO

622WO: Air-fired, 2% CO

622WO: Oxy-fired, 2% CO

Figure 5.1.3: Post cleaning appearance of 309L and 622 weld overlay (bottom) coupons after 1000 hours of exposure to 2% CO air-firing (left) and oxy-firing (right) waterwall conditions

Table 5.1.1a: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 1% O2 Air and Oxy-firing Test Conditions

Temp.	Material	Oxy-5% FeS			Air-5% FeS			Oxy-20% FeS			Air-20% FeS			Oxy-50% FeS			Air-50% FeS		
		WL	Pene.	TMW	WL	Pene.	TMW	WL	Pene.	TMW	WL	Pene.	TMW	WL	Pene.	TMW	WL	Pene.	TMW
750°F	A1	1.24	0.00	1.24	1.36	0.00	1.36	2.25	0.00	2.25	1.51	0.00	1.51	2.25	0.00	2.25	2.14	0.00	2.14
	T2	1.11	0.00	1.11	2.56	0.00	2.56	2.30	0.00	2.30	1.89	0.00	1.89	2.21	0.00	2.21	2.30	0.00	2.30
	T11	0.86	0.00	0.86	1.00	0.00	1.00	1.26	0.20	1.46	2.15	0.00	2.15	1.09	0.00	1.09	2.06	0.00	2.06
	T11-T11	0.72	0.60	1.33	0.79	0.00	0.79	1.30	0.00	1.30	0.60	0.00	0.60	1.44	0.40	1.84	0.92	0.00	0.92
	309WO	0.40	0.00	0.40	0.11	0.00	0.11	0.20	0.00	0.20	0.07	0.00	0.07	0.23	0.00	0.23	0.19	0.00	0.19
	622WO	0.15	0.00	0.15	0.70	0.00	0.70	0.13	0.00	0.13	0.69	0.00	0.69	0.25	0.00	0.25	0.24	0.00	0.24
	33WO	0.35	0.00	0.35	0.39	0.00	0.39	0.31	0.00	0.31	0.49	0.00	0.49	0.24	0.00	0.24	0.93	0.00	0.93
875°F	A1	1.25	0.00	1.25	0.91	0.00	0.91	1.64	0.00	1.64	1.91	0.00	1.91	1.33	0.00	1.33	2.55	0.00	2.55
	T2	0.91	0.00	0.91	1.08	0.00	1.08	2.01	0.00	2.01	1.47	0.00	1.47	4.11	0.00	4.11	3.20	0.00	3.20
	T11	0.99	0.40	1.39	2.24	0.00	2.24	1.19	0.40	1.59	2.35	0.00	2.35	2.20	0.40	2.60	4.39	0.00	4.39
	T11-T11	1.00	0.30	1.30	1.49	0.00	1.49	1.29	0.00	1.29	2.20	0.00	2.20	1.49	0.30	1.79	3.23	0.00	3.23
	309WO	0.27	0.20	0.47	0.49	0.00	0.49	0.09	0.20	0.29	0.29	0.00	0.29	0.79	0.20	0.99	0.14	0.00	0.14
	622WO	0.25	0.00	0.25	0.50	0.00	0.50	0.05	0.00	0.05	0.35	0.00	0.35	0.36	0.00	0.36	0.62	0.00	0.62
	33WO	0.30	0.00	0.30	0.30	0.00	0.30	0.25	0.00	0.25	0.62	0.00	0.62	0.30	0.00	0.30	0.31	0.00	0.31
1000°F	A1	2.66	0.00	2.66	3.23	0.00	3.23	2.63	0.00	2.63	3.53	0.00	3.53	2.39	0.00	2.39	3.76	0.00	3.76
	T2	1.94	0.00	1.94	2.90	0.00	2.90	2.69	0.00	2.69	3.10	0.00	3.10	2.73	0.00	2.73	4.22	0.00	4.22
	T11	1.50	0.50	2.00	3.34	0.00	3.34	2.78	0.60	3.38	4.10	0.00	4.10	1.49	0.40	1.89	3.91	0.00	3.91
	T11-T11	1.79	0.30	2.09	2.93	0.00	2.93	2.23	0.50	2.73	2.66	0.00	2.66	2.34	0.80	3.14	3.91	0.00	3.91
	309WO	0.20	0.00	0.20	0.00	0.00	0.00	0.08	0.30	0.38	0.34	0.00	0.34	0.22	0.50	0.72	0.27	0.00	0.27
	622WO	0.43	0.00	0.43	0.45	0.00	0.45	1.05	0.00	1.05	0.41	0.00	0.41	0.44	0.00	0.44	0.56	0.00	0.56
	33WO	0.38	0.00	0.38	0.45	0.00	0.45	0.30	0.00	0.30	0.40	0.00	0.40	0.40	0.00	0.40	0.45	0.00	0.45

Table 5.1.1b: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 2% CO Air and Oxy-firing Test Conditions

Temp.	Material	Oxy-5% FeS			Air-5% FeS			Oxy-20% FeS			Air-20% FeS			Oxy-50% FeS			Air-50% FeS		
		WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW
750°F	A1	2.28	0.00	2.28	1.63	0.00	1.63	1.71	0.00	1.71	8.73	0.00	8.73	1.68	0.50	2.18	2.76	0.00	2.76
	T2	1.77	0.00	1.77	2.15	0.00	2.15	2.19	0.00	2.19	1.40	0.00	1.40	2.84	0.00	2.84	3.94	0.00	3.94
	T11	2.19	0.00	2.19	1.57	0.00	1.57	2.81	0.00	2.81	1.59	0.00	1.59	2.31	0.00	2.31	3.58	0.00	3.58
	T11-T11	1.13	0.00	1.13	2.49	0.10	2.59	1.43	0.10	1.53	3.03	0.10	3.13	3.26	0.60	3.86	3.55	0.00	3.55
	309WO	0.34	0.50	0.84	0.59	0.00	0.59	0.25	0.30	0.55	0.56	0.40	0.96	3.54	0.20	3.74	1.54	0.60	2.14
	622WO	2.35	0.10	2.45	3.44	0.20	3.64	1.84	0.20	2.04	2.93	0.20	3.13	1.95	0.10	2.05	1.65	0.20	1.85
	33WO	1.56	0.00	1.56	2.16	0.10	2.26	1.79	0.00	1.79	1.40	0.10	1.50	2.09	0.50	2.59	1.75	0.20	1.95
875°F	A1	2.23	0.00	2.23	7.93	0.00	7.93	1.63	0.00	1.63	12.38	0.00	12.38	2.78	0.00	2.78	10.14	0.00	10.14
	T2	2.20	0.00	2.20	7.65	0.00	7.65	1.74	0.00	1.74	11.18	0.40	11.58	5.57	0.00	5.57	7.41	0.00	7.41
	T11	2.31	0.00	2.31	13.03	0.00	13.03	1.76	0.00	1.76	17.34	0.10	17.44	2.49	0.10	2.59	10.23	3.00	13.23
	T11-T11	5.10	0.40	5.50	13.79	0.10	13.89	0.74	0.20	0.94	17.19	0.10	17.29	3.82	0.10	3.92	12.84	0.10	12.94
	309WO	0.91	2.40	3.31	1.25	2.00	3.25	1.11	6.40	7.51	1.60	8.00	9.60	0.80	9.20	10.00	1.32	8.60	9.92
	622WO	1.65	0.10	1.75	2.61	0.20	2.81	2.57	0.00	2.57	2.60	0.20	2.80	2.01	0.10	2.11	3.21	0.10	3.31
	33WO	0.95	0.00	0.95	2.68	0.20	2.88	1.86	0.00	1.86	2.61	0.20	2.81	2.20	0.20	2.40	1.16	0.00	1.16
1000°F	A1	8.50	0.00	8.50	9.91	0.00	9.91	12.85	0.00	12.85	23.54	0.00	23.54	17.38	0.00	17.38	18.24	0.00	18.24
	T2	4.00	0.00	4.00	16.54	0.00	16.54	11.11	0.00	11.11	23.33	0.00	23.33	15.38	0.00	15.38	22.96	0.00	22.96
	T11	5.50	0.00	5.50	19.11	0.00	19.11	19.04	0.00	19.04	27.05	0.00	27.05	14.28	0.00	14.28	23.93	0.00	23.93
	T11-T11	3.63	0.30	3.93	17.99	0.30	18.29	16.58	0.20	16.78	33.72	0.10	33.82	15.22	0.00	15.22	23.11	0.00	23.11
	309WO	0.76	1.30	2.06	0.31	1.30	1.61	0.96	2.10	3.06	0.92	1.30	2.23	1.10	10.10	11.20	1.45	1.20	2.65
	622WO	3.10	0.10	3.20	1.79	0.00	1.79	2.00	0.00	2.00	1.84	0.40	2.24	2.87	0.00	2.87	1.91	1.00	2.91
	33WO	3.33	0.10	3.43	1.90	0.10	2.00	1.76	0.50	2.26	2.99	0.50	3.49	4.09	0.30	4.39	1.68	0.30	1.98

Table 5.1.1c: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 5% CO Air and Oxy-firing Test Conditions

Temp.	Material	Oxy-5% FeS			Air-5% FeS			Oxy-20% FeS			Air-20% FeS			Oxy-50% FeS			Air-50% FeS		
		WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW
750°F	A1	-	0.00	-	1.63	0.00	1.63	-	0.00	-	3.34	0.00	3.34	-	0.00	-	3.98	0.00	3.98
	T2	0.00	0.00	0.00	2.14	0.00	2.14	0.08	0.00	0.08	3.91	0.00	3.91	0.42	0.00	0.42	3.34	0.00	3.34
	T11	0.79	0.00	0.79	1.76	0.00	1.76	0.42	0.00	0.42	3.27	0.00	3.27	0.87	0.00	0.87	3.68	0.00	3.68
	T11-T11	-	0.00	-	1.49	0.00	1.49	-	0.00	-	2.49	0.00	2.49	-	0.00	-	3.67	0.00	3.67
	309WO	0.00	0.00	0.00	1.07	0.00	1.07	0.00	0.00	0.00	0.04	0.00	0.04	0.29	0.00	0.29	0.91	0.00	0.91
	622WO	1.29	0.00	1.29	0.71	0.00	0.71	0.00	0.00	0.00	0.64	0.00	0.64	1.37	0.00	1.37	0.36	0.00	0.36
	33WO	0.83	0.00	0.83	0.61	0.00	0.61	0.42	0.00	0.42	0.59	0.10	0.69	1.04	0.00	1.04	0.29	0.00	0.29
875°F	A1	-	0.00	-	9.78	0.00	9.78	-	0.00	-	12.85	0.00	12.85	-	0.00	-	10.54	0.00	10.54
	T2	0.71	0.00	0.71	8.34	0.00	8.34	3.70	0.00	3.70	10.94	0.00	10.94	4.50	0.00	4.50	9.51	0.00	9.51
	T11	0.00	0.00	0.00	8.58	0.20	8.78	1.91	0.00	1.91	6.65	0.30	6.95	5.29	0.00	5.29	8.35	0.20	8.55
	T11-T11	-	0.00	-	10.75	0.00	10.75	-	0.00	-	10.29	0.20	10.49	-	0.00	-	9.70	0.00	9.70
	309WO	0.00	0.00	0.00	0.74	0.00	0.74	1.75	0.00	1.75	0.56	0.00	0.56	2.04	0.00	2.04	0.23	0.00	0.23
	622WO	0.08	0.00	0.08	0.50	0.00	0.50	0.83	0.00	0.83	0.91	0.30	1.21	2.83	0.00	2.83	0.40	0.00	0.40
	33WO	0.46	0.00	0.46	0.46	0.00	0.46	0.58	0.00	0.58	0.63	0.00	0.63	2.29	0.00	2.29	0.60	0.00	0.60
1000°F	A1	-	0.00	-	9.87	0.20	10.08	-	0.00	-	11.13	0.20	11.33	-	0.00	-	8.04	0.00	8.04
	T2	26.35	0.00	26.35	10.46	0.20	10.66	26.60	0.00	26.60	12.50	0.30	12.80	20.02	0.00	20.02	9.30	0.00	9.30
	T11	18.11	0.00	18.11	10.61	0.30	10.91	13.57	0.00	13.57	14.08	0.40	14.48	13.78	0.00	13.78	9.18	0.20	9.37
	T11-T11	-	0.00	-	12.51	0.20	12.71	-	0.00	-	14.81	0.20	15.01	-	0.00	-	9.41	0.40	9.81
	309WO	0.00	0.00	0.00	0.34	0.00	0.34	0.21	0.00	0.21	0.25	0.00	0.25	0.50	0.00	0.50	0.43	0.00	0.43
	622WO	1.29	0.00	1.29	1.18	0.00	1.18	1.67	0.00	1.67	0.67	0.00	0.67	1.46	0.00	1.46	0.43	0.00	0.43
	33WO	1.50	0.00	1.50	0.49	0.00	0.49	0.50	0.00	0.50	0.44	0.00	0.44	0.33	0.00	0.33	0.27	0.00	0.27

Table 5.1.1d: Total Metal Wastage Data (in mils/1000 hr) for all Waterwall Materials Exposed to 20% CO Oxy-firing Test Conditions

Temp.	Material	Oxy-5% FeS			Oxy-20% FeS			Oxy-50% FeS		
		WL	Pen.	TMW	WL	Pen.	TMW	WL	Pen.	TMW
750°F	A1	1.08	0.20	1.28	1.28	0.30	1.58	1.56	0.40	1.96
	T2	0.87	0.20	1.07	1.14	0.40	1.54	1.55	0.00	1.55
	T11	0.40	0.40	0.80	0.45	0.20	0.65	1.10	0.20	1.30
	T11-T11	0.66	0.00	0.66	0.61	0.00	0.61	1.06	0.00	1.06
	309WO	0.75	0.00	0.75	0.46	0.00	0.46	0.69	0.30	0.99
	622WO	0.40	0.00	0.40	0.54	0.00	0.54	0.82	0.00	0.82
	33WO	0.51	0.00	0.51	0.58	0.00	0.58	0.32	0.00	0.32
875°F	A1	7.41	0.00	7.41	10.46	0.00	10.46	11.05	0.00	11.05
	T2	8.08	0.30	8.38	11.46	0.50	11.96	11.86	0.00	11.86
	T11	7.10	0.50	7.60	9.28	0.30	9.58	9.31	0.10	9.41
	T11-T11	8.55	0.60	9.15	11.60	0.00	11.60	10.85	0.00	10.85
	309WO	0.93	0.20	1.13	0.66	0.50	1.16	0	0.80	0.80
	622WO	0.68	0.00	0.68	0.62	0.00	0.62	0.92	0.00	0.92
	33WO	0.46	0.00	0.46	0.46	0.00	0.46	0.84	0.00	0.84
1000°F	A1	25.64	0.30	25.94	33.33	0.30	33.63	35.10	0.30	35.40
	T2	29.28	0.20	29.48	34.00	0.30	34.30	32.94	0.00	32.94
	T11	23.91	0.50	24.41	32.43	0.70	33.13	31.74	0.30	32.04
	T11-T11	27.01	0.30	27.31	33.18	0.20	33.38	27.60	0.10	27.70
	309WO	1.65	1.00	2.65	0.89	0.60	1.49	2.85	0.80	3.65
	622WO	1.31	0.20	1.51	1.14	0.30	1.44	0.73	0.50	1.23
	33WO	1.79	1.10	2.89	0.65	0.90	1.55	1.39	1.10	2.49

Figure 5.1.4: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O₂ air and oxy-firing waterwall test conditions at 399°C (750°F)

Figure 5.1.5: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O₂ air and oxy-firing waterwall test conditions at 468°C (875°F)

Figure 5.1.6: Total Metal Wastage for wrought and weld overlay materials exposed to 1% O₂ air and oxy-firing waterwall test conditions at 538°C (1000°F)

Figure 5.1.7: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 399°C (750°F)

Figure 5.1.8: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 468°C (875°F)

Figure 5.1.9: Total Metal Wastage for wrought and weld overlay materials exposed to 2% CO air and oxy-firing waterwall test conditions at 538°C (1000°F)

Figure 5.1.10: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 399°C (750°F)

Figure 5.1.11: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 468°C (875°F)

Figure 5.1.12: Total Metal Wastage for wrought and weld overlay materials exposed to 5% CO air and oxy-firing waterwall test conditions at 538°C (1000°F)

Figure 5.1.13: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at 399°C (750°F)

Figure 5.1.14: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at 468°C (875°F)

Figure 5.1.15: Total Metal Wastage for wrought and weld overlay materials exposed to 20% CO oxy-firing waterwall test conditions at (538°C) 1000°F

Figure 5.1.16: Photomicrographs showing the surface appearance and subsurface penetration (if evident) on T2 coupons exposed for 1000 hrs at 538°C (1000°F) to deposits containing 5% FeS (top), 20% FeS (middle) and 50% FeS (bottom) under 2%CO air and oxy-firing conditions

Figure 5.1.17: Photomicrographs showing the surface appearance and subsurface penetration (if evident) on 309WO coupons exposed for 1000 hrs at 468°C (875°F) to deposits containing 5% FeS (top), 20% FeS (middle) and 50% FeS (bottom) under 2%CO air and oxy-firing conditions

Figure 5.1.18: X-Ray dot maps showing the distribution of various elemental constituents on the surface of a T2 coupon exposed to 50% FeS deposits (HSW) at 468°C (875°F) under slightly reducing (2%CO waterwall) air-firing conditions for 1000 hrs

Figure 5.1.19: X-Ray dot maps showing the distribution of various elemental constituents on the surface of a T2 coupon exposed to 50% FeS deposits (HSW) at 468°C (875°F) under slightly reducing (2%CO waterwall) oxy-firing conditions for 1000 hrs

5.2 Discussion – Wrought and Overlay Materials

5.2.1 Effect of Alloy Composition on Total Metal Wastage

In general, high temperature corrosion resistance increases with increasing chromium concentrations above ~9%. The wrought materials tested in this programs, which represent those used in the construction of conventional waterwalls for sub-critical and supercritical PC boilers, had chromium levels $\leq 1.25\%$ and their slight differences in chromium concentrations (0.00% - 1.13%) were not sufficient to promote noticeable changes in their corrosion behavior. Although subtle differences in total wastage were noted for the various test conditions, the same general trends (i.e., increased wastage with temperature; more severe corrosion with 20% FeS deposits) were observed with little to no distinction between the materials. Thus, chromium had little to no influence on corrosion behavior for materials containing $\leq 1.25\%$ (T11) chromium.

Figures 5.2.1 – 5.2.12 are bar charts showing the wastage rates for each material with respect to temperature for the various deposit compositions and gas conditions. As seen in most of the figures, with the exception of 309WO exposed at 468°C (875°F) (and to a lesser extent 538°C [1000°F]) to the 2% CO air and oxy-firing gas condition, the weld overlay materials exhibited excellent corrosion resistance under even the most aggressive waterwall conditions. In general, the degree of metal wastage was only a fraction of what was observed relative to the wrought alloys, and the appreciable increase in corrosion resistance was primarily due to the much higher concentrations of chromium ($>20\%$) in the overlay materials. The fact that systemic wall loss was not observed on any of the high chromium weld overlay materials indicates that such materials may provide suitable protection to plain carbon and low alloy ferritic materials under either air and oxy-firing conditions.

5.2.2 Effect of Temperature on Total Metal Wastage

For the vast majority of the wrought ferritic alloys tested under the various air and oxy-firing conditions, total metal wastage increased with increasing test temperature, as shown in Figures 5.2.1 - 5.2.12. Under the 2% CO air-firing condition and the 20% CO oxy-firing condition, both representing the most severe corrosive conditions for their respective firing mode, the wrought materials displayed significant increases in wastage (~15x) when increasing the temperature from 399°C (750°F) to 538°C (1000°F). Under the least aggressive (1% O₂) air and oxy-fired test conditions, wastage also generally increased with increasing temperature; however, the extent of the increase was relatively minor when compared to the aforementioned test condition.

The influence of testing temperature for the overlay materials tested under the various air and oxy-fired conditions are also presented in Figures 5.2.1 – 5.2.12. Most of these materials exhibited excellent corrosion resistance for all test temperatures, although slightly higher metal wastage was typically noted at the highest test temperature. Thus, with the exception of 309WO tested at 468°C (875°F) (and to a lesser extent 538°C [1000°F]) under air and oxy-firing conditions, the degree of metal wastage noted on the overlay materials was generally only a fraction of what was observed on the wrought alloys due to their much higher chromium content.

5.2.3 Effect of Deposit Composition on Total Metal Wastage

Several short-term (100 hr) laboratory corrosion studies^(1, 2) conducted with air-firing atmospheres have shown corrosion rates to increase significantly with increasing concentrations of FeS to about 20%, and only slightly thereafter with further FeS additions. As such, three different deposits containing high, medium, and low concentrations of FeS were coated on the materials subjected to 1000 hours of testing. As expected, results of the testing indicated that, for the most part, the wrought and overlay materials exposed to the medium and high sulfur deposits (MSW and HSW) sustained more wastage than those exposed to the low-sulfur deposit (LSW); however, under certain test conditions, moderate to relatively severe wastage was noted on several coupon coated with 5% FeS deposit.

Wrought materials tested under oxy-combustion conditions generally exhibited increased wastage with increasing FeS content up to 20%, but the wastage difference between the three different deposits was fairly small (with the exception of the 2% CO case). This is particularly evident for the 20% CO case exposed at 538°C (1000°F) where severe wastage was noted for all three deposit types, and the maximum observed wastage ranged from 750 μm (0.0295") for the LSW (5% FeS) deposit to 900 μm (0.0354") for the HSW (50% FeS) deposit. Under air-fired conditions the wrought materials typically exhibited maximum wastage for deposits containing 20% FeS with somewhat less wastage observed for the 50% FeS and 5% FeS deposits.

With regards to the weld overlays, with the exception of the 309WO coupons exposed to 2% CO at 468°C (875°F), the deposit composition has little to no effect on the corrosion behavior of the overlay materials.

5.2.4 Effect of Gas Composition on Total Metal Wastage

Figures 5.2.13 – 5.2.16 show the effect of flue gas composition on wastage rates for select wrought materials exposed to the various deposit formulations at 468°C (875°F) and 538°C (1000°F) under air-firing and oxy-combustion conditions. Maximum wastage was generally noted for slightly reducing (2% CO) gas conditions under air-firing, and highly reducing gas conditions (20% CO) for oxy-firing. The trends shown in Figures 5.2.13 and 5.2.15 for T2 and T11, respectively under air-firing conditions are consistent with those observed by Seitz *et al.*,⁽²⁾ during short-term thermal gradient corrosion tests on T2 coupons with FeS and chloride-containing deposits. Seitz observed that corrosion losses on T2 material were generally low under moderately reducing (7% CO) and slightly oxidizing conditions (1% O₂), and significantly higher under slightly reducing conditions (2% CO).

Under oxy-firing conditions, the plots shown in Figures 5.2.14 and 5.2.16 for T2 and T11, respectively, indicate that wastage increased as the furnace microclimate became more reducing, especially at high temperatures. Analysis of the wastage data for the wrought materials further suggests that as the environment becomes more reducing, the extent of wastage becomes less dependent on deposit composition, as evidenced by the comparable corrosion losses noted for the various deposits exposed to 5% CO and 20% CO at 538°C (1000°F). This suggests that under severely reducing, and perhaps even moderately reducing oxy-combustion conditions, corrosion may be dominated by gas-phase attack from H₂S (and CO) rather than by the decomposition of FeS in the solid deposits (as speculated for slightly reducing and slightly oxidizing air-firing environments). Unfortunately, the air-fired 9% CO case was not tested for comparison. In any

case, aside from the highly reducing 20% CO condition, wastage of wrought materials under oxy-firing conditions was generally less than or comparable to air-firing.

With regard to the overlay materials, while maximum wastage was noted for the 2% CO under air and oxy-firing conditions, corrosion losses were generally negligible (compared to wrought materials); the effect of flue gas composition on wastage for 622WO under air-firing and oxy-combustion conditions, is shown in Figures 5.2.17 and 5.2.18, respectively.

5.2.5 Effect of Firing Condition (Air/Oxy) on Total Metal Wastage

The bar charts shown in Figure 5.2.19 – 5.2.27 present the total metal wastage for all of the waterwall materials (listed in order of increasing chromium concentrations) after 1000 hours of exposure to the three deposit formations and temperatures under air-firing and oxy-combustion conditions. For the three micro-climates (1% O₂, 2% CO and 5% CO) that were tested under both air and oxy-firing conditions, only the moderately reducing (5% CO) gas condition tested at the highest temperature (538°C [1000°F]) showed corrosion losses that were greater under oxy-firing gas conditions. That maximum wastage (see Figure 5.1.12), however, was similar to the maximum wastage observed under the most aggressive air-firing condition, per Figure 5.1.9 – 2% CO at 538°C (1000°F). Hence, over the range of O₂ and CO levels that were tested under both air and oxy-firing conditions, oxy-combustion wastage was similar to, if not less than that of air-firing.

At the 20% CO oxy-firing gas condition, the wastage experienced by the wrought ferritic materials at 399°C (750°F) and 468°C (875°F) were similar to, if not less than those experienced under 2% CO and 5% CO air-firing condition. At 538°C (1000°F) under oxy-firing conditions, the wrought materials exposed to the 20% CO gas condition sustained about 25% more wastage than those exposed to the 5% CO gas condition. Since test were not conducted at the maximum CO level predicted for air-firing, it is unknown whether the corrosion losses at the maximum CO oxy-combustion level would have been greater, comparable to, or less than the maximum CO air-firing level. Should the corrosion losses at the 20% CO, 538°C (1000°F) oxy-combustion condition prove to be a problem, the data suggest that any of the three weld overlay materials would provide adequate corrosion protection under such conditions.

Figure 5.2.1: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the slightly oxidizing (1% O₂) gas composition

Figure 5.2.2: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the slightly oxidizing (1% O₂) gas composition

Figure 5.2.3: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the slightly oxidizing (1% O₂) gas composition

Figure 5.2.4: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the slightly reducing (2% CO) gas composition

Figure 5.2.5: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the slightly reducing (2% CO) gas composition

Figure 5.2.6: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the slightly reducing (2% CO) gas composition

Figure 5.2.7: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the moderately reducing (5% CO) gas composition

Figure 5.2.8: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the moderately reducing (5% CO) gas composition

Figure 5.2.9: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the moderately reducing (5% CO) gas composition

Figure 5.2.10: Total Metal Wastage for all waterwall materials coated with a 5% FeS deposit mixture (LSW) and exposed to the severely reducing (20% CO) gas composition

Figure 5.2.11: Total Metal Wastage for all waterwall materials coated with a 20% FeS deposit mixture (MSW) and exposed to the severely reducing (20% CO) gas composition

Figure 5.2.12: Total Metal Wastage for all waterwall materials coated with a 50% FeS deposit mixture (HSW) and exposed to the severely reducing (20% CO) gas composition

Figure 5.2.13: Influence of flue gas composition on TMW for T2 coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions

Figure 5.2.14: Influence of flue gas composition on TMW for T2 coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions

Figure 5.2.15: Influence of flue gas composition on TMW for T11 coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions

Figure 5.2.16: Influence of flue gas composition on TMW for T11 coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions

Figure 5.2.17: Influence of flue gas composition on TMW for 622WO coupons exposed to high and medium sulfur deposits at various temperatures under air-firing conditions

Figure 5.2.18: Influence of flue gas composition on TMW for 622WO coupons exposed to high and medium sulfur deposits at various temperatures under oxy-firing conditions

Figure 5.2.19: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)

Figure 5.2.20: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)

Figure 5.2.21: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 399°C (750°F)

Figure 5.2.22: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 468°C (875°F)

Figure 5.2.23: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 463°C (875°F)

Figure 5.2.24: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 463°C (875°F)

Figure 5.2.25: Total Metal Wastage for all waterwall materials with deposit containing 5% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)

Figure 5.2.26: Total Metal Wastage for all waterwall materials with deposit containing 20% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)

Figure 5.2.27: Total Metal Wastage for all waterwall materials with deposit containing 50% FeS exposed to air and oxy-firing test conditions at 538°C (1000°F)

5.3 Results - Thermal Spray Coatings

Following 1000 hours of exposure to the various waterwall environments, the surfaces of the thermal spray coatings were mostly covered with relatively thick deposits. Depending on the gas conditions that they were exposed to, the deposits ranged in color from bright orange (oxidizing) to grayish-black (reducing). Visual examination did not reveal any evidence of coating spallation, severe cracking or complete coating consumption.

Unlike the wrought and weld overlay materials, the relative corrosion resistance of the thermal spray coatings could not be quantified by physical measurements of the remaining material. Instead, the thermal spray coatings had to be evaluated based upon the depth to which the aggressive constituents (namely sulfur and, to a lesser extent, oxygen) penetrated into the coating. If sulfur and oxygen species were detected at the substrate interface (by EDS), the coating performance was considered unsatisfactory as the presence of such species suggested that the coating would not offer adequate, long-term protection. In situations when sulfurous and/or oxygen containing species were not identified at the thermal spray/base metal interface, the remaining coating thickness was measured and the depth of subsurface penetration was quantified.

Table 5.3.1 presents the results of the thermal spray evaluation. The evaluations were performed by searching the entire 360° circumference of the polished metallographic cross section and qualitatively recording the findings; the presence of oxide and sulfide species at the interface was verified through EDS. The “O” and “S” designations in the table indicate that either sulfur and oxygen (S) or just oxygen (O) species were identified at the thermal spray/base metal interface of the thermal spray coupons. Although every sample was analyzed, due to the large number of coupons tested, backscatter SEM images and corresponding EDS spectrums such as shown in Figure 5.3.1 were only generated for a relatively small number of representative samples (see Task 4 topical report for additional images and spectrums). Figure 5.3.1 presents a backscatter SEM image and corresponding spot EDS spectrums taken at the interface between the thermal spray and metal interface (where the gray-colored oxide and sulfur-containing species are present). As indicated in Table 5.3.1 and SEM images/EDS spectra, with the exception of the UTEX 5-500 coupons exposed to all three deposit compositions at 538°C (1000°F) under the 1% O₂ air-firing condition, every thermal spray coupon contained sulfur and/or oxygen containing species at the thermal spray/base metal interface. Although the three referenced UTEX 5-500 coupons did not evidence oxides and/or sulfur-containing species at the interface, the depth of penetration into the coating was unacceptable (~50% within 1000 hours). As a result, none of the thermal spray coatings showed adequate resistance to sulfur and/or oxygen ingress under any of the test conditions; however, UTEX 5-500 did perform slightly better than UTEX 5-450 and UTEX 5-480 under several test conditions. What follows is a general assessment for the behavior of each of the thermal spray coatings under a given gas condition.

5.3.1 1% O₂ Microclimate

Under both air and oxy-firing conditions, the post-test UTEX 5-450 thermal spray coupons exposed to the 1% O₂ gas condition generally sustained moderate to severe cracking, with the vast majority of relatively large, wide, open cracks running parallel to the surface and tighter, discontinuous fissures running perpendicular to the surface. Although no evidence of gross

wastage was apparent at the thermal spray surface, oxide and sulfur-rich species filled or lined the cracks and fissures in many locations and extended down to the base metal/thermal spray interface where iron-rich sulfur and oxide species were identified by EDS.

The UTE_x 5-480 thermal spray coupons also exhibited some degree of cracking following exposure to the 1% O₂ air and oxy-firing gas condition. While cracking was somewhat less severe than that of the UTE_x 5-450 coupons, some samples displayed partial spallation of the coating (not through entire thickness) in isolated locations. The interface between the base metal and thermal spray was typically lined with a thin, discontinuous layer of iron-rich oxide and sulfur-containing species, although sulfur was much more prevalent at the interface of the oxy-fired samples. No significant evidence of gross wastage was apparent on the coating surface of any UTE_x 5-480 samples exposed to the 1% O₂ gas condition.

The post-exposed UTE_x 5-500 coated coupons generally contained a large number of cracks and fissures, most of which were fairly tight and tended to run perpendicular to the coating surface (through the thickness). For the most part, the thermal spray/base metal interfaces were lined with a thin, discontinuous iron oxide/sulfide layer; however, contrary to expectation, this layer was notably absent on all three air-fired samples exposed to the highest temperature (1000°F). In fact, of all the thermal spray samples tested and examined, only these three samples did not exhibit complete penetration of oxide and/or sulfur-rich species through the coating thickness, although the penetration experienced in the 1000 hours tests was unacceptably high. No evidence of gross coating wastage was observed on any of the UTE_x 5-500 thermal spray samples tested under the 1% O₂ gas condition.

5.3.2 2% CO Microclimate

UTE_x 5-450 thermal spray coupons exposed to the 2% O₂ gas conditions (air and oxy-firing) contained comparatively fewer cracks than those exposed to 1% O₂, but did contain numerous oxide and sulfide-rich veins that ran completely through the coating thickness. In a few samples, some oxide and corrosion products covered the outer coupons surface, but no significant evidence of gross wastage was observed.

The UTE_x 5-480 thermal spray coating did not perform particularly well under the 2% CO gas conditions as a few samples exhibited some degree of gross wastage at the surface and all displayed significant evidence of oxygen and sulfur ingress. While the coatings were generally intact (i.e., no gross cracking), several samples, namely those exposed to the highest test temperature, irrespective of deposit composition, sustained significant internal wastage, ultimately resulting in the formation of scattered oxide and sulfide-filled cracks that penetrated through the coating thickness to the base metal. In general, attack to the underlying base metal was relatively minor.

Much like the pre-characterized samples, the UTE_x 5-500 thermal spray coated samples exposed to the 2% CO gas conditions (air and oxy) exhibited significant cracking and fissuring throughout the coating thickness, resulting in debonding and/or partial spallation on a few coupons. In many locations, the cracks and fissures, especially those running perpendicular to the surface (through the coating), were filled or lined with oxide and sulfide-containing deposits and/or corrosion products that penetrated down to and along the thermal spray/base metal interface. Exposure to the highest test temperature also produced some gross wastage along the surface of the thermal spray coating.

5.3.3 5% CO Microclimate

As mentioned previously, during the original test run for the 5% CO oxy-firing gas condition very little wastage was observed for all wrought and weld overlay samples that were tested at 468°C (875°F) and 538°C (1000°F). All throughout the exposure period, upon removal from the furnaces following each 100 hour cycle, the spent ash deposits covering the surfaces of these samples were fairly friable and easily removed by light brushing. Although the overall consistency of the deposits was somewhat different than the previous furnace runs, having never performed tests under such conditions, there was no basis for testing to be aborted. Thus, only after the 1000-hour test period was complete, when the samples were examined for total metal wastage, was it discovered that none of the coupons experienced significant wastage. In fact, the wastage observed on the coupons exposed at 399°C (750°F) showed significantly more wastage than at either 875°F or 1000°F, which was in stark contrast to expectation and all of the previous furnace runs. Even with such little wastage noted on the wrought and overlay materials under the aforementioned test conditions, evaluation of the thermal spray coupons revealed evidence of oxygen and sulfur-containing compounds at the base metal/thermal spray interface on all samples, suggesting that follow-up testing on these materials was unwarranted.

The UTEX 5-450 thermal spray coupons tested under the original 1000-hr. 5% CO air-firing condition and oxy-firing at 399°C (750°F) all showed evidence of significant oxygen and sulfur ingress, resulting in a discontinuous layer of iron-rich oxide and sulfide corrosion products at the base metal/thermal spray interface. Sulfur and oxygen-rich species were detected all throughout the coating, and in some samples, along interconnecting veins that ran through the coating thickness. For the samples tested at 468°C (875°F) and 538°C (1000°F) under 5% CO oxy-firing conditions, copious amounts of iron-rich oxides were detected at the interface, strongly suggesting that oxygen-containing species penetrated through the nickel-based coating and reacted with the iron-based substrate material. No significant evidence of gross coating wastage was apparent on any of the samples examined.

The UTEX 5-480 thermal spray coating exposed to the 5% CO gas conditions was relatively intact and exhibited little to no evidence of gross wastage. Evidence of oxide and sulfur-rich species was present in all samples examined, and the degree of penetration varied with both gas condition and temperature. Samples tested at the highest temperature under air-firing conditions generally experienced severe through-thickness penetration along sulfur and oxygen-rich veins, resulting in a nearly continuous layer of oxide and sulfide corrosion products along the base metal/thermal spray interface; coupons tested under other conditions showed considerably less internal wastage and a thinner, discontinuous oxide or oxide/sulfide layer at the interface.

The UTEX 5-500 thermal spray coupon generally exhibited cracking and fissuring through much of the coating thickness. The interfaces between the thermal spray and substrates on all samples showed some evidence of iron-rich oxide and/or sulfur species, which penetrated through the coating thickness along a network of oxide and sulfide lined fissures. No gross coating wastage was observed on any of the UTEX 5-500 thermal spray samples tested under the 5% O₂ gas condition.

5.3.4 20% CO Microclimate

The UTE_x 5-450 thermal spray coating exposed to the 20% CO oxy-firing gas condition remained relatively intact, displaying only scattered, wide, open cracks running parallel to the coating surface. For all samples tested, however, iron-rich oxide and sulfide species were present along the interface between the thermal spray coating and substrate material. Spot EDS analyses throughout the coating thickness also revealed evidence of oxygen and sulfur-containing species, especially within some tight veins or fissures that were more prevalent at the highest test temperature. In addition, samples tested at 538°C (1000°F) also tended to show some degree of gross wastage along the surface of the coating.

The UTE_x 5-480 thermal spray coupons tested under the 20% CO oxy-firing gas condition all exhibited complete penetration of oxygen and sulfur-containing species, culminating in the formation of iron-rich oxide and sulfide corrosion products along the thermal-spray/base metal interface. While those tested at 399°C (750°F) did not show any significant evidence of coating degradation (relative to the pre-test sample) other than the appearance of thin, discontinuous sulfur and oxide-rich corrosion products at the interface, samples tested at 538°C (1000°F) sustained significant gross wastage and severe penetration along a network of interconnected diffusion paths.

UTE_x 5-500 thermal spray coupons exposed to the 20% CO oxy-firing gas condition contained a fair number of relatively wide cracks that ran parallel to the coating surface and tighter fissures that ran perpendicular to the coating surface (through the thickness). In every sample, oxide and sulfur-containing species filled or lined the fissures and penetrated down to form discontinuous iron oxide/sulfide rich corrosion products along the thermal spray/base metal interface. In addition to penetration, the three samples exposed to the highest temperature also showed evidence of gross wastage along the coating surface.

5.4 Discussion – Thermal Spray Materials

Aside from a few coupons that showed minor evidence of partial coating spallation, all of the thermal spray coupons tested under various air-firing and oxy-fired conditions remained intact for the duration of the 1000 hour test period. While only a select few samples, namely those exposed to the highest test temperature under the most corrosive test gas conditions experienced some level of bulk coating wastage, nearly every sample showed evidence of iron-rich oxide and/or sulfur-containing species at the thermal spray/base metal interface, indicating reaction with the plain carbon steel substrate. In many cases, fine cracks, fissures or boundary separations containing variable concentrations of sulfur and oxide species were noted at various depths through the coating thickness. Sulfur and oxide species were also found at the thermal spray/base metal interface on all but three test coupons, indicating that even in the absence of through thickness cracks and fissures, diffusion pathways existed for the aggressive constituents to diffuse through and react with the substrate material. Of the three coupons that did not exhibit interfacial oxides and sulfurous species, the depth of penetration of those species into the coating was unacceptably high amounting to about half the coating thickness in 1000 hours.

It should be mentioned that under the same test conditions, some of the wrought ferritic materials showed corrosion losses on the order of 890 μm (0.035”), while penetration into the carbon steel

substrate material was generally minimal (typically $<50\text{ }\mu\text{m}$ [$<0.002''$]). This suggests that the thermal spray coatings did provide some protection by greatly minimizing the extent of gross metal wastage to the carbon steel substrate. However, the presence of oxygen and sulfur-containing species at the interface suggests that prolonged exposure to aggressive flue gas and iron sulfide-containing deposits may cause the oxide and sulfur-rich layers to thicken, and eventually generate stresses that are large enough to cause complete spallation of the coating. In the absence of longer term data, the coatings appear to provide, at best, only short-term corrosion protection.

Table 5.3.1: Depth of Penetration (by Sulfur and/or Oxygen) into the Thermal Spray Coatings

Gas Condition	Material	399°C (750°F)			468°C (875°F)			538°C (1000°F)		
		5% FeS	20% FeS	50% FeS	5% FeS	20% FeS	50% FeS	5% FeS	20% FeS	50% FeS
1% O ₂ - Air	5-450	S	S	S	S	S	S	S	S	S
	5-480	S	S	S	S	S	S	S	O	O
	5-500	S	S	S	S	S	S	5.7 mils	11.1 mils	11.0 mils
1% O ₂ - Oxy	5-450	S	S	S	S	S	S	S	O	S
	5-480	S	S	S	S	S	S	S	S	S
	5-500	S	S	S	S	S	S	O	O	O
2% CO - Air	5-450	S	S	S	S	O	S	S	S	S
	5-480	S	S	S	S	S	S	S	S	S
	5-500	S	S	S	S	S	S	S	S	S
2% CO - Oxy	5-450	S	S	S	S	S	S	S	S	S
	5-480	S	S	S	S	S	S	S	S	S
	5-500	S	S	S	S	S	S	S	S	S
5% CO - Air	5-450	S	S	S	S	S	S	S	S	S
	5-480	S	S	S	S	S	S	S	S	S
	5-500	S	S	S	S	S	S	S	S	S
5% CO - Oxy	5-450	S	S	S	O	O	S	O	O	O
	5-480	S	S	S	O	S	S	O	O	O
	5-500	S	S	S	O	O	O	S	S	S
20% CO - Oxy	5-450	S	S	S	S	S	S	S	S	S
	5-480	S	S	S	S	S	S	S	S	S
	5-500	S	S	S	S	S	S	S	S	S

S = Indicates that sulfur and oxygen containing species were identified at the thermal spray/base metal interface.

O = Indicates that only oxygen containing species (no sulfur) were identified at the thermal spray/base metal interface, but the incidence of oxygen-containing species was much more pronounced than in the as-supplies coatings

The samples highlighted in blue correspond to those that were in the same furnaces as the wrought and overlay materials that inexplicably showed very little evidence of wastage. Although the thermal spray samples showed little evidence of distress, oxygen and/or sulfur species were identified at the at the interface of every sample.

Figure 5.3.1: Backscatter SEM image (top) and corresponding spot EDS spectrum taken at the thermal/spray metal interface of UTEX 5-480 exposed to 20% FeS deposits at 538°C (1000°F) for 1000 hr under 2% CO₂ oxy-firing conditions

6.0 SUPERHEATER/REHEATER MATERIALS: RESULTS AND DISCUSSION

6.1 Results

Following exposure, the synthetic ash deposits covering the superheater/reheater (SH/RH) coupon surfaces were generally reddish-colored and overlaid with scattered patches of light-colored material (see Figure 6.1.1). The deposits were generally hard, tightly adherent, and the thickness and tenacity of the underlying oxide and corrosion product layers beneath the ash deposits, as well as the degree of metal loss, varied significantly with gas condition, testing temperature, material composition, and ash composition. The deposits were removed by light grit blasting and the coupons photographed to visually record their conditions; Figure 6.1.2 and 6.1.3 show the post test T22, T91, 304H, and 347H material coupon arrays and the reader is referred to the Task 4 Topical Report for the balance of the photographs.

The maximum measured wall loss, penetration depth, and TMW for every material exposed to the various testing temperatures under air and oxy-firing conditions is summarized in Tables 6.1.1a and 6.1.1b, respectively. The materials are listed in order of increasing chromium content.

Figures 6.1.4 – 6.1.6 are bar chart comparisons of the TMW loss for each material exposed to the deposit formulations at 538°C (1000°F), 593°C (1100°F), and 649°C (1200°F), respectively. The materials (both wrought alloys and overlays) are listed in order of increasing chromium concentration, as chromium is essential for providing high temperature corrosion resistance and oxidation resistance. The low chromium ferritic materials, T22 and T22–304H weld, generally exhibited gross macroscopic wall loss in the form of general corrosion, such that the distribution and depth of attack was fairly consistent over most of the exposed surface, as shown in Figure 6.1.2 (bottom). For the austenitic and overlay materials, gross macroscopic wastage was typically in the form of pitting attack with very few samples experiencing general metal loss.

In addition to metal loss, most of the coupons, especially the austenitic and overlay materials exposed to the highest temperatures, exhibited some degree of subsurface degradation resulting from the diffusion of sulfur and/or oxygen into the metal. Penetration tended to occur within the matrix grains (not along the grain boundaries) on most of the samples tested under a majority of the conditions; however a few materials showed either a combination of matrix and intergranular penetration or only intergranular penetration. The maximum measured depth of penetration for a given material under all exposure conditions was quantified using a calibrated video imaging system interfaced with a metallographic microscope at magnifications between 100x and 500x; the results are presented in Tables 6.1.1a and 6.1.1b for air and oxy-firing, respectively. Figures 6.1.7 and 6.1.8 are representative optical micrographs showing the distribution of ash deposits (if still remaining after metallographic preparation) and degree of subsurface penetration on the 347H and T11-304H coupons and additional photomicrographs can be found in the Task 4 Topical Report.

As mentioned previously, total metal wastage was calculated as the combination of the maximum measured wall loss (including pitting) and the maximum depth of subsurface penetration. Although the deepest penetration was generally not observed directly beneath the area exhibiting the maximum wall loss, by calculating the total metal wastage as the combination of the two, the reported values represent a conservative “worst case” estimate. Based on the

results of the SH/RH tests, both bulk metal loss and depth of subsurface penetration was typically less severe under oxy-firing conditions than under air-firing. In fact, aside from the T22-304H coupon coated with the medium sulfur superheater/reheater deposit, every oxy-fired sample tested at 649°C (1200°F) showed considerably less wastage than its air-fired counterpart.

In addition to the macroscopic and microscopic assessments, select samples were also evaluated by SEM and EDS. Due to the large number of samples and multitude of testing conditions (18 different deposit/temperature combinations for each material), detailed EDS evaluation was only performed on select coupons samples for each gas conditions. Where appropriate, x-ray maps showing the distribution of elemental constituents were constructed on samples exhibiting the most severe wastage. Two representative x-ray maps showing the surface of 347H coupons exposed to 10% alkali sulfate deposits at 649°C (1200°F) under air and oxy-firing conditions are presented in Figures 6.1.9 and 6.1.10, respectively.

Figure 6.1.1: Representative photomacrographs showing the spent ash deposits covering the surfaces of all 10 SH/RH material coupons following the last 100 hour cycle of the 1000 hour exposure to air-firing (left) and oxy-firing (right) SH/RH test conditions.

T91: Air-fired

T91: Oxy-fired

T22: Air-fired

T22: Oxy-fired

Figure 6.1.2: Post cleaning appearance of T91 (top) and T22 (bottom) coupons after 1000 hours of exposure to air-firing (right) and oxy-firing (left) SH conditions

347H: Air-fired

347H: Oxy-fired

304H: Air-fired

304H: Oxy-fired

Figure 6.1.3: Post cleaning appearance of 347H (top) and 304H (bottom) coupons after 1000 hours of exposure to air-firing (right) and oxy-firing (left) SH conditions

Table 6.1.1a: Total Metal Wastage Data (in mils/1000 hr) for all Superheater/Reheater Material Exposed to Air-firing Test Conditions

Temp.	Material	Air – 0% Alkali Sulfates			Air - 5% Alkali Sulfates			Air - 10% Alkali Sulfates		
		Wall Loss	Penetration	TMW	Wall Loss	Penetration	TMW	Wall Loss	Penetration	TMW
1000°F	T22-304H	1.81	0.30	2.11	1.73	0.40	2.13	1.60	0.50	2.10
	T22	1.07	0.30	1.37	1.66	0.60	2.26	2.91	0.50	3.41
	T91	1.01	0.30	1.31	2.20	0.30	2.50	1.90	0.30	2.20
	347H	0.77	0.30	1.08	0.56	0.30	0.86	0.61	0.30	0.91
	304H	0.64	0.20	0.84	0.86	0.40	1.26	1.99	0.30	2.29
	NF709	0.17	0.60	0.77	0.66	0.30	0.96	1.05	0.20	1.25
	622WO	1.09	0.00	1.09	1.15	0.20	1.35	0.73	0.00	0.73
	HR3C	0.56	0.20	0.76	0.43	0.00	0.43	0.00	0.00	0.00
	33WO	0.30	0.60	0.90	1.10	0.30	1.40	0.95	0.20	1.15
	72WO	1.34	0.30	1.64	0.55	0.00	0.55	0.65	0.40	1.05
1100°F	T22-304H	4.74	0.60	5.34	4.58	0.90	5.48	4.16	0.20	4.36
	T22	5.22	0.80	6.02	7.83	0.50	8.33	4.92	0.80	5.72
	T91	2.10	0.30	2.40	1.43	0.50	1.93	0.74	0.30	1.04
	347H	1.30	0.40	1.70	1.44	0.50	1.94	1.52	0.30	1.82
	304H	0.88	0.30	1.18	1.96	0.40	2.36	1.40	0.40	1.80
	NF709	1.56	0.50	2.06	1.94	0.60	2.54	1.70	0.30	2.00
	622WO	1.43	0.30	1.73	1.19	0.40	1.59	1.33	0.00	1.33
	HR3C	1.24	0.40	1.64	0.65	0.60	1.25	0.58	0.30	0.88
	33WO	1.31	1.00	2.31	0.66	1.10	1.76	1.26	0.80	2.06
	72WO	0.47	0.70	1.17	0.60	0.90	1.50	0.71	0.70	1.41
1200°F	T22-304H	11.85	1.00	12.85	6.09	1.10	7.19	11.56	2.30	13.86
	T22	11.45	0.50	11.95	10.85	0.80	11.65	17.29	0.80	18.09
	T91	2.20	0.70	2.90	3.49	0.90	4.39	4.08	0.60	4.68
	347H	3.43	0.50	3.93	1.76	1.70	3.46	4.40	6.90	11.30
	304H	0.77	0.60	1.38	3.35	1.00	4.35	3.76	2.90	6.66
	NF709	1.74	0.80	2.54	1.51	0.90	2.41	1.25	0.90	2.15
	622WO	2.15	0.70	2.85	2.30	0.90	3.20	5.83	0.30	6.13
	HR3C	0.66	0.50	1.16	1.11	0.80	1.91	0.67	2.30	2.97
	33WO	0.61	1.80	2.41	0.70	1.00	1.70	1.76	1.40	3.16
	72WO	0.61	1.40	2.01	4.65	2.80	7.45	0.91	2.80	3.71

Table 6.1.1b: Total Metal Wastage Data (in mils/1000 hr) for all Superheater/Reheater Material Exposed to Oxy-firing Test Conditions

Temp.	Material	Oxy – 0% Alkali Sulfates			Oxy - 5% Alkali Sulfates			Oxy - 10% Alkali Sulfates		
		Wall Loss	Penetration	TMW	Wall Loss	Penetration	TMW	Wall Loss	Penetration	TMW
1000°F	T22-304H	1.50	0.20	1.70	1.55	0.10	1.65	2.30	0.20	2.50
	T22	1.64	0.00	1.64	2.44	0.00	2.44	2.40	0.30	2.70
	T91	1.30	0.20	1.50	1.39	0.20	1.59	0.02	0.10	0.12
	347H	0.59	0.00	0.59	1.06	0.00	1.06	0.74	0.00	0.74
	304H	0.59	0.20	0.79	0.59	0.10	0.69	0.81	0.20	1.01
	NF709	0.44	0.10	0.54	0.98	0.10	1.08	0.71	0.00	0.71
	622WO	0.80	0.00	0.80	0.96	0.10	1.06	1.04	0.00	1.04
	HR3C	0.38	0.20	0.58	0.56	0.30	0.86	0.86	0.50	1.36
	33WO	0.96	0.20	1.16	0.66	0.30	0.96	0.51	0.20	0.71
	72WO	0.55	0.20	0.75	0.74	0.20	0.94	0.35	0.20	0.55
1100°F	T22-304H	1.40	0.20	1.60	4.50	0.00	4.50	4.39	0.00	4.39
	T22	1.43	0.00	1.43	2.14	0.40	2.54	2.34	0.40	2.74
	T91	1.29	0.20	1.49	1.76	0.30	2.06	1.50	0.30	1.80
	347H	0.69	0.40	1.09	1.23	0.50	1.73	0.85	0.40	1.25
	304H	0.92	0.20	1.13	0.87	0.50	1.37	1.04	0.40	1.44
	NF709	0.69	0.00	0.69	0.39	0.30	0.69	0.32	0.20	0.52
	622WO	1.11	0.50	1.61	1.03	0.50	1.53	1.61	0.30	1.91
	HR3C	0.74	0.20	0.94	0.57	0.20	0.77	0.34	0.20	0.54
	33WO	0.42	0.80	1.22	0.56	0.70	1.26	0.66	0.50	1.16
	72WO	0.43	0.50	0.93	0.35	0.00	0.35	0.32	0.00	0.32
1200°F	T22-304H	8.59	0.80	9.39	9.90	1.40	11.30	9.70	1.30	11.00
	T22	5.01	0.80	5.81	5.03	0.80	5.82	5.10	0.70	5.80
	T91	2.39	0.60	2.99	2.13	0.70	2.83	2.05	0.60	2.65
	347H	0.74	0.30	1.04	1.33	0.90	2.23	1.65	0.80	2.45
	304H	0.79	0.40	1.19	1.30	0.90	2.20	1.54	0.80	2.34
	NF709	1.18	0.30	1.48	1.13	0.20	1.33	0.90	0.30	1.20
	622WO	1.10	0.50	1.60	1.57	0.80	2.37	2.44	0.50	2.94
	HR3C	0.40	0.30	0.70	0.97	0.30	1.27	1.12	0.50	1.62
	33WO	0.80	1.00	1.80	0.90	0.30	1.20	0.48	0.60	1.08
	72WO	0.50	0.20	0.70	0.59	0.00	0.59	1.10	0.00	1.10

Figure 6.1.4: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 538°C (1000°F)

Figure 6.1.5: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 593°C (1100°F)

Figure 6.1.6: Total Metal Wastage for all SH/RH materials exposed to air and oxy-firing test conditions at 649°C (1200°F)

Figure 6.1.7: Photomicrographs showing the surface appearance and subsurface penetration on 347H material exposed for 1000 hours at 649°C (1200°F) to a deposit containing 0% alkali sulfates (top), 5% alkali sulfates (middle) and 10% alkali sulfates (bottom) under air-firing (left) and oxy-firing (right) conditions

Figure 6.1.8: Photomicrographs showing the surface appearance and subsurface penetration on T11 – 304H welded coupons exposed for 1000 hours at 649°C (1200°F) to a deposit containing 10% alkali sulfates under air and oxy-firing conditions. Note T22 has experienced significant wastage relative to the Ni-based weld metal, particularly adjacent to the fusion line.

Figure 6.1.9: X-Ray dot maps showing the distribution of various elemental constituents on the surface of 347H exposed to HSS deposit (10% alkali sulfate) at 649°C (1200°F) under synthetic air-firing conditions. Note the presence of high concentrations of oxygen, chromium and sulfur in the intergranularly penetrated region.

Figure 6.1.10: X-Ray dot maps showing the distribution of various elemental constituents on the surface of 347H exposed to HSS deposit (10% alkali sulfate) at 649°C (1200°F) under synthetic oxy-combustion conditions. Sodium and potassium species are present in the outer deposits, while the innermost products are rich in chromium, oxygen and sulfur.

6.2 Discussion

6.2.1 Effect of Alloy Composition on Total Metal Wastage

The charts presented in Figures 6.1.4 – 6.1.6 illustrate the effect of increasing chromium content on wastage for all materials exposed to the different synthetic deposit/flue gas combinations. Examination of these figures, coupled with the photomacrographs indicate that, with the exception of a few materials, wastage typically decreases with increasing chromium concentration in the alloy, regardless of the gas and deposit conditions. These results are consistent with high temperature, air-fired corrosion experience, especially where the presence of low melting temperature compounds is possible. Previous corrosion testing programs⁽³⁻⁵⁾, specifically with regard to coal ash corrosion, showed that high temperature corrosion resistance generally increases with increasing chromium content up to about 22 - 25%. In the present study, the corrosion resistance of materials tested under air-fired conditions typically increased with increasing chromium content up to about 22%, while only the low chromium (<2.5%) T22 material tested under oxy-firing conditions showed any significant evidence of corrosion for all deposit/temperature combinations.

Although the metal loss typically decreased with increasing chromium concentration, the depth of subsurface penetration was not significantly influenced by the amount of chromium in the material. In fact, under air combustion conditions, particularly at the highest test temperature (649°C [1200°F]), most of the high chromium (>18%) materials experienced deeper (and in some cases, significantly deeper) internal penetration than the low(er) chromium ferritic materials. This was likely due to the limited bulk corrosion that most of the higher chromium materials experienced. That is, as wall loss progressed in the low chromium materials, sustained reaction with the bulk metal may have consumed areas where penetration was on-going, thereby minimizing the total depth of subsurface penetration, but increasing the contribution from wall loss. Thus, in the absence of wall loss, it is probable that the depth of penetration would have decreased with increasing chromium content. It is interesting to note that, aside from the T22 materials (welded and unwelded), the highest degree of subsurface penetration (and subsequently total metal wastage) was observed on 347H exposed to the highest temperature and most severe ash under air-firing conditions. As shown in Figure 6.1.9, penetration progressed almost exclusively along the grain boundaries and penetrated several grains deep. In contrast, no evidence of significant subsurface penetration was noted on the 347H coupon tested under oxy-combustion conditions.

Although several other alloying elements, such as Ni, Si, Mo and Al, may have a profound influence on corrosion resistance under specific environmental conditions, no obvious trends were observed for TMW as a function of specific alloying additions. This was primarily due to the limited number of materials tested, as the test program was limited to the materials typical of the current U.S. boiler fleet.

6.2.2 Effect of Temperature on Total Metal Wastage

The influence of test temperature on total metal wastage loss for all ten superheater/reheater materials exposed to the various flue gas/deposit combinations is shown in Figures 6.2.1 - 6.2.16. In general, all of the materials tested, regardless of deposit and gas composition showed an increase in wastage with increasing temperature, even though the extent of the increase was

relatively minimal for the high(er) chromium materials. Coal ash corrosion generally shows a bell-shaped dependence with temperature, brought about by the increasing stability of molten alkali-iron trisulfates on the alloy surface with increasing metal temperatures up to about 691°C (1275°F), followed by dissociation at higher temperatures. However, the temperature associated with peak wall loss is driven by various factors including the composition of the alloy and resulting corrosion products, the level of alkali-sulfates and impurities (such as chlorides) in the deposits, the SO₃ concentration in the flue gas, and the electrochemical relationship between the molten salt liquid and alloy surface. As such, the temperature at which peak loss may occur can be highly variable. In fact, in a previous coal ash corrosion study, Wolowodiuk⁽³⁾ suggested that the peak loss temperatures for various alloys may range from about 593°C (1100°F) for highly resistant alloys (which may show very little total wastage) to 704°C (1300°F) for materials that show poor resistance to coal-ash corrosion resistance. In the present study, with the exception of NF709, which exhibited peak corrosion at 593°C (1100°F), nearly every material showed a continuous increase in wastage rate with temperature up to the maximum test temperature of 649°C (1200°F) for all test conditions. Thus, the limited temperature range was not sufficient to represent the bell-shaped dependence typical of coal-ash corrosion.

Much like general wastage, the majority of the test specimens exhibited an increase in penetration depth with increasing test temperature, especially for the more aggressive ash compositions. This behavior is not surprising considering that oxidation and sulfidation are diffusion controlled processes, whereby the formation of oxide and/or sulfide phases is dependent upon temperature and availability of penetrating species. Assuming that sufficient concentrations of the penetrating species are present in the ash and that the bulk wastage rate is slow enough to allow diffusion into the substrate, deeper penetration would be expected at higher temperatures. The depth and extent of penetration is also dependent on the state (e.g., solid or liquid) of the deposits from which the species are diffusing.

6.2.3 Effect of Deposit Composition on Wastage

Comparison of the wastage data as a function of temperature for materials exposed to synthetic superheater/reheater deposit under air-firing and oxy-firing test conditions (see Figures 6.2.1 - 6.2.16) suggests that wastage rates generally increased with increasing concentrations of alkali sulfates. For the same levels of SO₂ and O₂ in the flue gas (for the given gas condition), higher concentrations of alkali sulfates in the HSS deposits would be expected to generate greater volumes of alkali-iron trisulfates, resulting in more severe metal loss. Thus, the observed results were somewhat consistent with expectation. Furthermore, the substitution of calcium sulfate in the LSS deposits for alkali sulfates in the MSS and HSS would not only act to suppress the formation of alkali-iron trisulfates, even in the presence of some alkali sulfate, but also minimize the molten salt acidity and limit corrosion losses.

A closer examination of Figures 6.2.7 – 6.2.16 reveals that under air-firing conditions, essentially all materials showed increased wastage with increased alkali sulfate levels, albeit with the high chromium materials the increase was minimal, and undetectable with the high chromium, high nickel NF709 alloy. Under oxy-combustion conditions, the high chromium materials continued to exhibit little to no increase with increasing sulfate levels and the wastage increase observed by the ferritic materials was also less pronounced.

6.2.4 Effect of Gas Composition on Total Metal Wastage

The bar charts shown in Figure 6.1.4 – 6.1.6 present the total metal wastage for all SH/RH test materials (listed in order of increasing chromium concentrations) after 1000 hours of exposure to low, medium and high alkali-sulfate containing deposits under air and oxy-firing test conditions at 538°C (1000°F), 593°C (1100°F) and 649°C (1200°F), respectively. Comparison of the air-firing and oxy-firing results shows air-firing to be higher than oxy-firing with the increase growing from slightly higher at 538°C (1000°F) and low alkali sulfates to moderately higher at 649°C (1200°F) and high alkali sulfates. Examination of Tables 6.1.1a and 6.1.1b also reveals that the increase in total metal wastage was not due solely to increased wall loss or penetration, but rather the combination of the two.

In PC boilers, especially those burning high sulfur coals, severe fireside wastage of superheater and reheater tube surfaces is generally caused by coal ash corrosion resulting from the formation of molten alkali iron trisulfates.⁽⁶⁻¹⁰⁾ The process by which corrosion occurs has been described previously^(3, 7-10) and essentially involves SO_3 , contained in the flue gas and released in the deposits, migrating to the colder tube surface to form relatively low melting temperature compounds at the metal interface. Once formed, the molten deposits flux the protective oxides from the tube surface and cause internal sulfidation and oxidation of the tube metal.

Wolowodiuk *et al.* showed that for a fixed SO_2 concentration (1%) and deposit composition (10% alkali sulfate), weight loss at 649°C (1200°F) due to corrosion generally increased as the O_2 concentration was increased from 2% O_2 to 4% O_2 . Thus, in the present study, the lower O_2 level in the oxy-combustion case relative to the air-fired case (2% vs. 3%), may have contributed to the lower corrosion rates observed under oxy-combustion conditions.

Figure 6.2.1: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 0% alkali sulfate deposits formulation under air-firing conditions

Figure 6.2.2: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 0% alkali sulfate deposits formulation under oxy-firing conditions

Figure 6.2.3: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 5% alkali sulfate deposits formulation under air-firing conditions

Figure 6.2.4: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 5% alkali sulfate deposits formulation under oxy-firing conditions

Figure 6.2.5: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 10% alkali sulfate deposits formulation under air-firing conditions

Figure 6.2.6: Total Metal Wastage vs. Temperature for all SH/RH materials exposed to the 10% alkali sulfate deposits formulation under oxy-firing conditions

Figure 6.2.7: Total Metal Wastage vs. Temperature for all T22 coupons tested under SH/RH conditions

Figure 6.2.8: Total Metal Wastage vs. Temperature for all T22-304H welded coupons tested under SH/RH conditions

Figure 6.2.9: Total Metal Wastage vs. Temperature for all T91 coupons tested under SH/RH conditions

Figure 6.2.10: Total Metal Wastage vs. Temperature for all 347H coupons tested under SH/RH conditions

Figure 6.2.11: Total Metal Wastage vs. Temperature for all 304H coupons tested under SH/RH conditions

Figure 6.2.12: Total Metal Wastage vs. Temperature for all NF709 coupons tested under SH/RH conditions

Figure 6.2.13: Total Metal Wastage vs. Temperature for all HR3C coupons tested under SH/RH conditions

Figure 6.2.14: Total Metal Wastage vs. Temperature for all 622WO coupons tested under SH/RH conditions

Figure 6.2.15: Total Metal Wastage vs. Temperature for all 33WO coupons tested under SH/RH conditions

Figure 6.2.16: Total Metal Wastage vs. Temperature for all 72WO coupons tested under SH/RH conditions

7.0 COMPARISON WITH COAL-FIRED FIELD TEST DATA

7.1 Schwarze Pumpe Plant

At the Schwarze Pumpe Plant in Germany⁽¹¹⁾ Vattenfall has constructed and is testing a 30 MWt coal-fired pilot plant under air-fired and oxy-fired conditions. The pilot plant fires pre-dried lignite in a three pass furnace-boiler arrangement and incorporates an electrostatic precipitator (ESP), a wet flue gas desulfurization (FGD) system, a flue gas cooler, and a CO₂ processing system. Although flue gas from the outlet of the flue gas cooler is used to transport the coal into the boiler, the bulk of the recycled flue gas under oxy-firing is extracted from a point between the ESP and FGD. Since the extraction point is upstream of the FGD and has not undergone desulfurization, boiler SO₂ levels are about four times higher than that of air-firing (7000 versus 1600 mg/Nm³). A variety of probes have been inserted at several flue gas path locations to obtain deposit and corrosion data with the following being observed:

- Deposit Probes: Oxy-combustion deposition rates were generally higher than air-fired and, aside from higher sulfur levels attributed to much higher flue gas SO₂ levels, the composition of the oxy-fired and air-fired fly ash deposits were similar.
- Waterwall Probes: Under oxy-firing conditions, three of the four materials tested experienced corrosion rates deemed unacceptably high; no air-fired data, however, was available for comparison and the authors indicate that the high wastage rates may have been attributed to the particular design of the test unit rather than oxy-combustion. The probe was operated at 430°C (806°F) for 1472 hours.
- Superheater Probes: The superheater probes experienced low corrosion rates with no discernible difference between oxy and air-firing. The probes were operated for 250 hours at a metal temperature of 580°C (1076°F) and inserted into 760°C (1400°F) oxy-fired and 840°C (1544°F) air-fired flue gas.
- Carburization: All test specimens were etched with Murakami's reagent to reveal carbides; no significant difference was noted between air and oxy-firing.

7.2 University of Utah

Air and oxy-fired corrosion tests have been conducted at a nominal 1 MWt scale in the University of Utah's L1500 horizontal, refractory lined, pulverized coal-fired combustor⁽¹²⁾. The combustor had a one meter square cross section and three coals were tested (e.g., 0.23% sulfur Powder River Basin (PRB) coal, 0.53% sulfur Utah coal, and a 3.98% sulfur Illinois No. 6 coal). The facility did not incorporate flue gas desulfurization and, with the flue gas recycle returned to the furnace without cleaning, the levels of pollutants under oxy-firing were much higher than under air-firing (a factor of 2.2 for the low sulfur, 3.9 for the medium sulfur, and 5.5 for the high sulfur coals). Cooled probes containing waterwall (SA210A1) and superheater (T22, P91, and 347H) materials were inserted in the unit and operated under air and oxy-firing conditions. The unit was operated for only eight to ten hours during the day and the probes were removed each night. Electrochemical Noise Technology (EN) was used to obtain a real time indication and relative ranking of corrosion rates and the following was observed:

- Waterwall Probes: The waterwall probes were typically maintained at 382°C (720°F) and inserted in the furnace section operating with a 0.9 burner stoichiometry at a flue gas temperature of 1260°C (2300°F). The SA210A1 waterwall material corrosion rates were relatively low and oxy-firing corrosion rates were lower than air-firing rates for all three coals; about 25% lower for the low sulfur PRB coal and about 50% lower for the medium and high sulfur coals.
- Superheater Probes: The superheater probes were typically maintained at 488°C (910°F) and they were inserted into 982°C (1800°F) flue gas downstream of the point of secondary air injection that increased the flue gas oxygen content to 3% dry basis. When moving from air to oxy-firing, corrosion rates mostly increased by amounts that depended upon the materials and coals being fired. For the 0.23% sulfur PRB coal, wherein the bulk flue gas SO₂ level increased from 129 to 289 ppmv (dry), the 347H corrosion rate nearly doubled, whereas, the T22 and P91 rates increased by about 1/3 and 1/4, respectively. For the 0.53% sulfur Utah coal, wherein the bulk flue gas SO₂ level increased from 446 to 1754 ppmv (dry), the P91 corrosion rate increased by about a factor of 5, whereas, the 347H and T22 rates nearly doubled. For the 3.98% sulfur Illinois No 6 coal, wherein bulk flue gas SO₂ levels increased from 3219 to 17642 ppmv (dry), the 347H corrosion rate increased by more than 50 times, whereas, the P91 rate increased by about 1/4 and the T22 rate decreased slightly.

7.3 Comparison with Electric Furnace Data

The University of Utah waterwall corrosion data was conducted with one material (SA210A1) at one temperature and the microclimate condition at the probe location was unknown; the Utah finding that waterwall corrosion rates decreased under oxy-firing is consistent with the electric furnace findings, wherein, oxy-fired waterwall corrosion rates/losses were found to be similar to, if not less than, those of air-firing. When operating with low sulfur coal, the Utah superheater data showed that 347H corrosion rates doubled when moving from air to oxy-firing, whereas, at Schwarze Pumpe the corrosion experienced in 250 hours of testing was very small and a difference between air and oxy-firing could not be discerned. It is not known if longer testing at Schwarze Pumpe would have revealed a difference between air and oxy-firing but the limited Schwarze Pumpe data appear to be in conflict with the Utah data, but in agreement with FW's electric furnace data.

The Foster Wheeler electric furnace test program approximated air and oxy-firing conditions using synthesized gases and synthetic deposits; the deposits, which were produced from reagent grade powders, were refreshed at 100 hour intervals and operated at isothermal conditions (no temperature gradient across the deposit). Despite the differences between real world boiler operating conditions and the electric furnace conditions that attempted to approximate them, the electric furnace data appear to agree with the Schwarze Pumpe superheater and Utah waterwall coal-fired test data. In addition, both the Schwarze Pumpe and electric furnace data indicated no evidence of carburization. This similarity in findings, although based on very limited coal-fired data, is encouraging and strengthens the electric furnace program suggestions that oxy-firing corrosion rates will be similar to, if not less than those of air-firing. Finally, the 50 fold increase

in 347H corrosion rates when moving from air to oxy-firing with high sulfur coal indicates the need to clean the recycle flue gas before it returns to the boiler.

8.0 CONCLUSIONS

Similar to air-fired operation, corrosion losses resulting from simulated oxy-combustion corrosion conditions were found to vary with material, temperature, deposit composition and gas composition. Despite all the variables and with bulk gas SO₂ levels limited to a maximum value of 3200 ppmv (wet) / 4050 ppmv (dry), the maximum level tested in this program, oxy-firing wastage was found to be similar to, if not less than wastage observed under air-firing conditions. These results were applicable to the four furnace waterwall, seven superheater, and six weld overlay materials that were tested. Analysis of the three thermal spray materials proposed for furnace waterwall applications revealed sulfur and/or oxygen species at the base-metal/thermal spray coating interface in overwhelming majority of specimens tested under air and oxy-firing conditions, suggesting that thermal spray coatings would only provide short-term protection.

Based on the results of such testing, specifically with regard to waterwall conditions, the following conditions can be drawn:

- In general, materials (wrought, weld overlay and thermal sprays) tested under the same air and oxy-firing gas compositions (e.g., 1% O₂, 2% CO and 5% CO) showed fairly similar wastage behavior for most test conditions. Under slightly oxidizing (1% O₂) and slightly reducing (2% CO) conditions, oxy-firing was somewhat less corrosive than air-firing and under moderate reducing (5% CO) conditions was comparable to air-firing.
- With respect to the wrought materials the most corrosive conditions for air-firing (2% CO, 538°C [1000°F], 20% FeS) and oxy-firing (20% CO, 538°C [1000°F], 50% FeS) showed comparable corrosion losses.
- Wrought materials coated with MSW and HSW deposits generally exhibited comparable corrosion losses under both air and oxy-firing conditions, and were typically much higher than those coated with LSW deposits (except for the 20% CO oxy-firing condition). This trend was consistent with previous studies which showed that corrosion losses increase with FeS up to about 20% and essentially plateau further additions of FeS.
- Although all of the proposed wrought materials exhibited significant wastage under certain test conditions (namely 2% CO air-firing; 20% CO oxy-firing), acceptable corrosion losses were observed for all weld overlay materials under all test conditions, regardless of temperature, deposit composition and gas/firing condition.
- The conventional materials used in the furnace areas of air-fired units should be acceptable for oxy-combustion retrofits, provided the bulk SO₂ concentration does not exceed 3200 ppmv (wet) / 4050 ppmv (dry), the maximum value tested in this program.
- Thermal spray materials may provide some short-term corrosion protection, but are not recommended for long term protection under air or oxy-firing conditions.

With regard to the SH/RH test conditions, the following conclusions can be made:

- For all materials tested, wastage resulting from simulated oxy-firing corrosion conditions was generally about half that observed for air-firing under the same temperatures and deposit compositions.
- No evidence of carburization was noted on any specimen under simulated air or oxy-combustion conditions.

Laboratory electric furnace testing is a valuable screening tool or first step for providing short-term corrosion data for a large number of materials subjected to specific, static environments. However, due to the dynamic nature of the boiler environment, there are limitations on the number of variables and critical test parameters that can be addressed. Thus, the laboratory tests conducted herein should only be considered a first step in evaluating the applicability of materials for a new, potentially harsh environment. Nevertheless, the results of the electric furnace laboratory tests suggest that provided PC oxy-combustion retrofits are limited to a bulk gas SO₂ levels of 3200 ppmv (wet) / 4050 ppmv (dry), the maximum value evaluated in this program, from a corrosion standpoint, the materials used in conventional subcritical and supercritical air-fired boilers should be suitable for oxy-combustion. Furthermore, if for some unknown reason a localized corrosion problem should develop, all of the weld overlay materials tested in this program have the potential for providing adequate corrosion protection.

9.0 REFERENCES

1. C. Kung "Effect of Iron Sulfide on Furnace Wall Corrosion", Electric Power Research Institute, Palo Alto, CA, 1998. TR 111152.
2. W. Seitz, G. Stanko, S. Niska, J. Sanchez, R. Hassanen, and W. Bakker, "Waterwall Wastage Root Causes: Or How to Predict Wastage Rates from Coal Chemistry" EPRI, Palo Alto, CA, 2004. 1004737 TR112823.
3. W. Wolowodiuk, S. Kihara, and K. Nakagawa, "Laboratory Coal Ash Corrosion Tests," Palo Alto, CA: Electric Power Research Institute, July 1989. GS6449.
4. J. L. Blough, M. T. Krawchuk, G. J. Stanko, and W. Wolowodiuk, "Superheater Corrosion Field Test Results," Palo Alto, CA: Electric Power Research Institute, November 1993. TR103438.
5. H. Hack and G. Stanko, "Update on Fireside Corrosion Resistance of Advanced Materials for Ultrasupercritical Coal-Fired Power Plants" The 31st International Technical Conference on Coal Utilization & Fuel Systems, May 21 – 26, 2006, Clearwater, Florida, USA.
6. W. Nelson and C. Cain, Jr., "Corrosion of Superheaters and Reheaters of Pulverized Coal Fired Boilers," Transactions of the ASME, Journal of Engineering for Power, July 1960, pp. 194 - 204.
7. W. T. Reid, "Formation of Alkali Iron Trisulphates and Other Compounds Causing Corrosion in Boilers and Gas Turbines," Project Review July 1, 1966, June 30, 1968, prepared by Battelle Memorial Institute, Columbus, OH, June 1968.
8. W. T. Reid, External Corrosion and Deposits: Boilers and Gas Turbines, American Elsevier Publishing Company, New York, 1974.
9. G. J. Hills, "Corrosion of Metals by Molten Salts," Proceedings of the Marchwood Conference: Mechanism of Corrosion by Fuel Impurities, Johnson and Littler, eds., Butterworths, London, 1963.
10. S. Kihara, K. Nakagawa, A. Ohtomo, H. Aoki, and S. Ando, "Simulating Test Results for Fireside Corrosion of Superheater & Reheater Tubes Operating at Advanced Steam Conditions in Coal-Fired Boilers", High Temperature Corrosion in Energy Systems, TMS/AIME, M. F. Rothman, ed., 1984, pp. 361-376.
11. A. Hjörnhede, M. Montgomery, M. Bjurman, P. Henderson, A. Gerhardt, " Preliminary Experiences with materials Testing at the Oxy-fuel Pilot Plant at Schwarzepumpe" The 9th Liège Conference on Materials for Advanced Power Engineering, September 27 – September 29, 2010, Liège, Belgium.
12. A. Fry, B. Adams, K. Davis, D. Swensen, S. Munson, "Fireside Corrosion of Heat Transfer Surface Materials for Air- and Oxy-coal Combustion" The 36th International Technical Conference on Clean Coal & Fuel Systems, June 5 – June 9, 2011, Clearwater, Florida, USA.

10.0 ACRONYMS AND ABBREVIATIONS

Ar	Argon
AVG _{initial}	Average Initial Wall Thickness
Btu	British Thermal Unit
Btu/hr-ft ²	British Thermal Units per Hour per Square Foot
°C	Degrees Centigrade
CD	Deepest Carburization Depth
CFD	Computational Fluid Dynamics
CO	Carbon Monoxide
CO ₂	Carbon Dioxide
Cr	Chromium
CR	Corrosion Rate
DP	Depth of Deepest Measured Pit
EDS	Energy Dispersive X-Ray Spectroscopy
EN	Electrochemical Noise Technology
°F	Degrees Fahrenheit
FEGT	Furnace Exit Gas Temperature
FGD	Flue Gas Desulfurization System
WL	Wall Loss
H ₂ O	Water/Steam
H ₂ S	Hydrogen Sulfide
HCl	Hydrogen Chloride
HSW/HSS	High-Sulfur Coal Waterwall/Superheater Deposit
IGS	Integrated Global Services
°K	Degrees Kelvin
LSW/LSS	Low-Sulfur Coal Waterwall/Superheater Deposit
LV	Larger Value of CD versus SP
M	Million
mil	0.001"
MIN _{final}	Final Minimum Measured Wall Thickness
mm	Millimeters
MPa	Mega-Pascal
MSW/MSS	Medium-Sulfur Coal Waterwall/Superheater Deposit
MWe	Mega Watt Electric
N ₂	Nitrogen
Ni	Nickel
NO _x	Oxides of Nitrogen
O ₂	Oxygen
PEN	Depth of Subsurface Penetration
ppm	Parts per Million
ppmv	Parts per Million (Volume)
psia	Pressure in Pounds per Square
SCR	Selective Catalytic Reduction

SEM	Scanning Electron Microscope
SH/RH	Superheater/Reheater
SO ₂	Sulfur Dioxide
SO ₃	Sulfur Trioxide
SP	Deepest Subsurface Penetration/Pit
TMW	Total Metal Wastage
WL	Wall Loss