Researchers Demonstrate Microstructure and Charge Yield in Semiconducting Polymers

Microstructure determines the yield of free charge in neat semiconducting polymers.

Understanding the fundamental photophysics of poly(3-hexylthiophene) films, and that of conjugated polymers in general, is essential if we are to realize their full potential as low-cost active layers for coal-competitive solar power generation. Yet, the value of one of the most basic photophysical parameters of these materials—the yield of free charges upon photoexcitation of neat films—has remained controversial because of a wide variation between previous measurements.

Researchers at the National Renewable Energy Laboratory (NREL) have resolved this controversy by showing that the yield of free charges depends sensitively on the solid-state microstructure of the film. The microstructure was varied systematically through control of the polymers' molecular weight and processing conditions, while the charge carrier yield was measured using time-resolved microwave conductivity—a unique technique to which only a few groups in the world have access. The researchers found that the yield of long-lived free charges depends on the co-existence of amorphous and crystalline domains in the polymer, and this behavior was attributed to charge separation at the interface between these two domains of order.

The research was done in collaboration with Imperial College London, and was supported by the Laboratory Directed Research and Development (LDRD) Program at NREL.

Technical Contact: Obadiah Reid, obadiah.reid@nrel.gov

Reference: Reid, O. G.; Malik, J. A. N.; Latini, G.; Dayal, S.; Kopidakis, N.; Silva, C.; Stingelin, N.; Rumbles, G. "The influence of solid-state microstructure on the origin and yield of long-lived photogenerated charge in neat semiconducting polymers." *J. Polym. Sci. B Polym. Phys.* (2011).

The figure above shows the yield of charge carriers (holes) per photon of incident light as a function of molecular weight. Low molecular weight P3HT samples had a yield of only 1% while high molecular weight samples displayed a yield of up to 10%. The insets show illustrations of the differing microstructure in the low and high molecular weight regimes. Illustration by Obadiah Reid, NREL, and Natalie Stingelin, Imperial College London

Key Research Results

Achievement

Researchers demonstrated that by controlling molecular weight and processing conditions, the yield of free charges in conjugated polymers can be controlled.

Key Result

The yield of free charges was shown to depend sensitively on the solid-state microstructure of neat film.

Potential Impact

Understanding the origin and yield of free photogenerated charges in neat conjugated polymers may help realize their full potential as low-cost active materials for solar power generation.