Final PI Report and Proceedings Information for Grant No. DE-FG02-08ER15945

Support for Students and Young Scientists to Participate in the 25th Rare Earth Research Conference (RERC08) at The University of Alabama

Total Support: \$5000

Conference Dates: June 22-26, 2008

PI: Robin D. Rogers

Address: Center for Green Manufacturing
Department of Chemistry/Box 870336
3006D Shelby Hall, 250 Hackberry Lane
The University of Alabama
Tuscaloosa, AL 35487
+1-205/348-4323/RDRogers@as.ua.edu

Grant Purpose, Expenditures, and Outcomes

This grant provided \$5000 to enable increased participation of students and young scientists at the 25th Rare Earth Research Conference (RERC08), June 22-26, 2008 at The University of Alabama, Tuscaloosa, AL (URL: <http://bama.ua.edu/~rdrogers/RERC08/>.) Several activities were designed to encourage participation of students and young scientists, including registration fee waivers, assistance with travel and hotel costs, poster prize and best presentation awards, and a career roundtable.

Except for the \$500 administration fee, all funds were used to support the participation of students and young scientists. These funds allowed students and young scientists to attend the premier US meeting in the field and network with the top international scientists in the field. They had the opportunity not only to learn about the state-of-the-art in the field, but also interact with motivational scientists from around the World. It is anticipated that new contacts and collaborations were generated and many left with an increased interest in the field of f-element chemistry.

Conference Information

Conference Chair: [Dr. Robin D. Rogers: RDRogers@bama.ua.edu](mailto:RDRogers@bama.ua.edu)

Program Chair: [Dr. John Sarrao: sarrao@lanl.gov](mailto:sarrao@lanl.gov)

Spedding Award Organizer: [Dr. Peter Dorhout: peter.dorhout@colostate.edu](mailto:peter.dorhout@colostate.edu)

Conference Assistant: [Ms. Mihaela Gurau: lerc08@bama.ua.edu](mailto:lerc08@bama.ua.edu)

International Advisory Committee:

J.-C. Bunzli (Switzerland)

Ji Chen (China)

David A. Dixon (USA)

Anja Mudring (Germany)

Dale L. Perry (USA)

J. Takats (Canada)

M. F. Tweedle (USA)
A. E. Visser (USA)

Program Committee:

[Dr. John Sarrao: sarrao@lanl.gov](mailto:sarrao@lanl.gov) (Program Chair)
Jean-Claude Bunzli, Lausanne (bio/med applications)
Paul Canfield, Iowa State/Ames Laboratory (condensed matter physics and magnetism)
Julia Chan, Louisiana State (solid state/coordination chemistry)
Dhanesh Chandra, University of Nevada-Reno (materials science)
Sue Clark, Washington State (environmental chemistry)
Dave Dixon, Alabama (theoretical chemistry)
Anita Gianotto, INL (mass spectroscopy)
Gordon Jarvinen, Los Alamos (nuclear materials)
Jackie Kiplinger, Los Alamos (organometallic chemistry)
Guo-Kui Liu, Argonne (spectroscopy)
Anja Mudring, Bochum (ionic liquids)
Ann Visser, Savannah River (separations science)
Zhiping Zheng, Arizona (functional materials)

Proceedings Editors:

Peter Dorhout, Editor: Peter.Dorhout@ColoState.EDU
Vitalij Pecharsky, Editor: vitkp@ameslab.gov
Michael Reid, Chief Editor: mike.reid@canterbury.ac.nz

The program of the 25th Rare Earth Research Conference (RERC08) integrated basic and applied multidisciplinary research centered on the f-elements. Leading science was featured in the form of invited oral presentations and contributed posters on topics in f-element chemistry, physics, and material, earth, environmental, and biological sciences. The conference was held in Shelby Hall, located on The University of Alabama's Tuscaloosa, AL campus. The final program and list of attendees is available at URL <http://bama.ua.edu/~rdrogers/RERC08/>.

Spedding Award

A highlight of the meeting was the recognition of the accomplishments of an internationally-recognized scientist, Professor William Evans, with the presentation of the Spedding Award. This prestigious award is given in recognition of excellence and achievement in research centered on the science and technology of rare earths. The awardee is selected by a committee from submitted nominations. The award consists of a medal mounted on a plaque and a monetary sum of \$1,000, sponsored by [Bracco Research USA Inc.](#) The Spedding Award winner was asked to present a lecture on the highlights of his or her work at the meeting.

Plenary Lectures

Spedding Awardee: William J. Evans (University of California, Irvine)
Paul C. Canfield (Iowa State University/Ames Laboratory)
Luis Echegoyen (U.S. National Science Foundation)
John C. Miller (U.S. Department of Energy)

Lynne Soderholm (Argonne National Laboratory)
Hiroshi Tsukube (Osaka City University)

Topical Themes

Solid State and Coordination Chemistry
Organometallic Chemistry
Theoretical Chemistry
Environmental Chemistry
Condensed Matter Physics & Magnetism
Ionic Liquids and Molten Salts
Separations Science
Mass Spectrometry
Spectroscopy and Optical Materials
Functional Materials
Oxide Materials
Nuclear Materials Research
Medicinal Applications

Invited Lectures

Hwan Kyu Kim (Korea University)
Polly Arnold (University of Edinburgh)
Frederic Aubriet (University of Metz)
David Berg (University of Victoria, Canada)
Aurora Clark (Washington State University)
Bert deJong (Pacific Northwest National Laboratory)
Carsten Detlefs (ESRF Grenoble)
Pieter Dorenbos (Delft University of Technology)
David Emslie (McMaster University, Canada)
Gregory Faris (SRI International)
Gary Groenewold (Idaho National Laboratory)
David Hobbs (Savannah River National Laboratory)
Zhaomin Hou (RIKEN Discovery Research Institute, Japan)
Arthur Mar (University of Alberta)
Marinella Mazzanti (CEA-Grenoble, France)
Maria Miritello (University of Catania)
Francois Nief (Ecole Polytechnique, France)
Jun Okuda (Aachen University)
Stephane Petoud (University of Pittsburgh)
Annie Powell (University of Karlsruhe)
Monica Regalbuto (Argonne National Laboratory)
Don (Dong-Kyun) Seo (Arizona State University)
Toshiro Takabatake (Hiroshima University)
Enzo Terreno (University of Torino)
Michael J Van Stipdonk (Wichita State University)
Xiaojun Wang (Georgia Southern University)

Proceedings: The proceedings from this meeting were published in *Journal of Alloys and Compounds* **2009**, Vol. 488, Iss. 2, pp 491-656
(<http://www.sciencedirect.com/science/journal/09258388/488/2>).

Preface

Twenty-Fifth Rare Earth Research Conference

The Rare Earth Research Conferences (North America) alternates on a three year cycle with the International Conference on f-Elements (Europe) and the International Conference on Rare Earths (rest of the world). The 25th Rare Earth Research Conference in Alabama (RERC08), followed the successful 24th RERC in Keystone, Colorado held June, 2005.

RERC08 was held in Shelby Hall, located on The University of Alabama's campus in Tuscaloosa, AL. The program (Dr. John Sarrao, Program Chair) integrated basic and applied research centered on the f-elements. Leading science was featured in the form of invited oral presentations and contributed posters on topics in f-element chemistry, physics, and materials, earth, environmental, and biological sciences. Highlighting the program was the presentation of the Frank H. Spedding Award for excellence in rare earth research.

The topical themes of RERC08 truly exemplified the breadth of the field. These included Solid State and Coordination Chemistry, Organometallic Chemistry; Theoretical Chemistry, Environmental Chemistry, Condensed Matter Physics & Magnetism, Ionic Liquids and Molten Salts, Separations Science, Mass Spectrometry, Spectroscopy and Optical Materials, Functional Materials, Oxide Materials, Nuclear Materials Research, and Medicinal Applications.

The RERC08 Program Committee, Chaired by Dr. John Sarrao, is to be congratulated on putting together such an interesting program. Members of the *Program Committee* consisted of:

Dr. John Sarrao: sarrao@lanl.gov (Program Chair)
 Jean-Claude Bunzli, Lausanne (bio/med applications)
 Paul Canfield, Iowa State/Ames Laboratory (condensed matter physics and magnetism)
 Julia Chan, Louisiana State (solid state/coordination chemistry)
 Dhanesh Chandra, University of Nevada-Reno (materials science)
 Sue Clark, Washington State (environmental chemistry)
 Dave Dixon, Alabama (theoretical chemistry)
 Anita Gianotto, INL (mass spectroscopy)
 Gordon Jarvinen, Los Alamos (nuclear materials)
 Jackie Kiplinger, Los Alamos (organometallic chemistry)
 Guo-Kui Liu, Argonne (spectroscopy)
 Anja Mudring, Bochum (ionic liquids)
 Ann Visser, Savannah River (separations science)
 Zhiping Zheng, Arizona (functional materials)

At RERC08, as at all the Rare Earth Research Conferences, the participant experiences were enriched by the strong international

participation. This is in no small part due to the efforts of the *International Advisory Committee*, with members:

J.-C. Bunzli (Switzerland)
 Ji Chen (China)
 David A. Dixon (USA)
 Anja Mudring (Germany)
 Dale L. Perry (USA)
 J. Takats (Canada)
 M. F. Tweedle (USA)
 A. E. Visser (USA)

The RERC08 *Proceedings Editorial Board* consisted of:

Michael F. Reid, *Proceedings Editor-in-Chief*
 Danesh Chandra
 Peter K. Dorhout
 Vitalij K. Pecharsky

And the Spedding Award Committee Chair was:

Peter K. Dorhout

Every conference also needs strong financial supporters and RERC08 was no different. We are grateful for the financial and personal participation of the RERC08 sponsors, Bracco Research USA Inc., the U.S. Department of Energy Office of Basic Energy Sciences; Ames Laboratory, Argonne National Laboratory, and The University of Alabama.

Finally, I need to thank all of my staff and students that contributed to the local arrangements and the smooth operation of the meeting. The Conference Coordinator, Ms. Mihaela Rogers, also sends her thanks to all of the participants and their good humor which all led to a pleasant conference experience from both participants and organizers.

Conference Chair
 Robin D. Rogers
 University of Alabama, Department of Chemistry,
 Tuscaloosa, AL 35487-0036,
 United States

Advances in f element reductive reactivity as a paradigm for expanding lanthanide and actinide science and technology[☆]

William J. Evans*

Department of Chemistry, University of California, Irvine, CA 92697-2025, USA

ARTICLE INFO

Article history:

Received 24 June 2008

Received in revised form

23 December 2008

Accepted 2 February 2009

Available online 20 February 2009

Keywords:

Lanthanides

Actinides

Reduction

Sterically induced reduction

Cyclopentadienyl

Dinitrogen

Divalent

ABSTRACT

Although f element chemistry has progressed enormously since the time when it was investigated by F.H. Spedding, much still remains to be discovered in this area. This address will describe some recent developments in a fundamental type of f element reaction, reduction, that show just how much new chemistry is still to be discovered in a heavily studied area of f element chemistry that was thought to be mature. This lecture should serve to encourage new efforts to challenge conventional ideas in other “mature” areas of f element science and technology.

For 90 years, lanthanide-based reduction chemistry was accomplished with just three divalent ions, Eu^{2+} , Yb^{2+} , and Sm^{2+} . Now there are many new ways to accomplish molecular reductive chemistry equivalent to that of the traditional Ln^{2+} ions, but with all the metals in the lanthanide series, La–Lu. Several years ago such an idea would have been unthinkable. This lecture will describe the development of these new types of reduction and their implications in both lanthanide and actinide chemistry.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

The purpose of this Spedding Award Address and written summary is to stimulate *all* researchers to be highly ambitious in their efforts to expand their respective fields of activity. As research advances, there is a tendency to think that some fields are mature and that most of the major discoveries in these areas have already been made [1,2]. We need to remind ourselves that major breakthrough discoveries are always awaiting us and we must not complacently think that we are restricted only to incremental advances in knowledge in “mature” fields.

To illustrate this point, the major changes that have occurred in recent years in a fundamental type of reaction long studied in f element chemistry, namely reduction chemistry, will be described. Redox reactions along with acid–base reactions are the two most common types of processes in chemistry. They have been heavily studied and well developed. Consistent with this, the area of f element reduction chemistry was considered to be mature. However, as we shall see, many advances were waiting to be discovered.

These recent advances are even more surprising considering the surge of development in f element chemistry in recent years. As background for the discussion on recent reduction chemistry, it will be beneficial to examine the development of f element chemistry in a broader historical context. This will be presented in two parts: advances during the research career of Frank Spedding from 1929 to 1972 and developments from the early 1970s until the late 1990s, the point at which the discussion of recent developments in f element reduction chemistry will start. These historical perspectives have some important lessons for us as researchers. As I was preparing this address, I talked with a student who had not known that there was a time when most organometallic lanthanide chemistry was limited primarily to the smaller metals later in the series. They were surprised to learn that there was a time when working with a metal as large as samarium was pushing the outer limits of what was possible in organolanthanide chemistry. Since this type of information rarely gets published, it seemed worthwhile to consider the status of rare earth chemistry in some earlier times and to examine how our vision of the field has changed. Hopefully, this will encourage us to experiment boldly as we pursue the next wave of major advances in this field.

2. Background

It is difficult to imagine the state of f element chemistry when Spedding began his research career in 1929. Only a few points

[☆] Award Address for the 12th Frank H. Spedding Award for Outstanding Contributions to the Science and Technology of the Rare Earths, 25th Rare Earth Research Conference, Tuscaloosa, Alabama, June 22, 2008.

* Tel.: +1 949 824 5174.

E-mail address: wevans@uci.edu.

are presented here, but full details are available in a fascinating description of Spedding's research written by the 11th Spedding Awardee, John Corbett [3]. Spedding began his academic career just as the Great Depression hit. There were few jobs and little money for academic salaries. However, the major challenge in pursuing rare earth research in the 1930s was acquiring samples of lanthanide compounds. Spedding's first lanthanide research sample was obtained as a loan with the promise that it would not be consumed in any way! In the 1940s obtaining pure f element starting materials was a major goal. As part of the Manhattan project, Spedding's research involved the preparation of large amounts of pure uranium and later cerium and yttrium for nuclear applications. The following titles of papers illustrate how basic the f element chemistry was at that time; these were papers published from patents written in the 1940s that were later declassified.

"The Preparation of Samarium and Yttrium Metals" J. Am. Chem. Soc. 75 (1953) 2272.

"The Separation of Adjacent Rare Earths with Ethylenediaminetetra-acetic Acid by Elution from an Ion-exchange Resin" J. Am. Chem. Soc. 76 (1954) 612.

"Vapor Pressure of Thulium Metal" J. Am. Chem. Soc. 79 (1957) 5160.

So much was unknown and awaited discovery in the f element area at that time. So many frontiers were available, that discovering new results retrospectively seemed easy.

From the start of Spedding's career in 1929 until 1972 when he retired, enormous development of the basic chemistry of the lanthanides occurred. Once the metals could be separated and obtained in pure form, the classical coordination chemistry of these metals could be explored. Tremendous progress was made in establishing the chemistry of these elements, primarily in aqueous solution, and many aspects appeared to be fully explored and mature. The chemistry was dominated by oxygen donor atom ligands and it appeared that the limits of metal ligand chemistry were well defined. As late as 1964, it was thought that Ln–N bonds were not very stable [4] and hence ligands with donor atoms other than oxygen were expected to contribute little additional chemistry to this area.

Given the dominance of oxygen ligands for the electropositive ionic lanthanides, the prospects for organometallic chemistry looked bleak. Despite major advances in the organometallic

chemistry of the transition metals, only a few types of organolanthanide complexes were known. Review articles from that period in the early 1970s [5,6] focused only on the compounds in Scheme 1.

Tris(cyclopentadienyl) lanthanide complexes, $(C_5H_5)_3Ln$, had been made by Wilkinson in the 1950s [7,8] and by Fischer in the 1960s [9] as part of research programs focused not on the rare earths, but on the $(C_5H_5)^{1-}$ ligand. Some years later, Tsutsui made six (tris)indenyl analogs, $Ln(C_9H_7)_3$ [10]. Researchers at Ethyl Corporation, then in Detroit, reported $(C_5H_5)_3Eu$ [11] as well as complexes formulated as $(C_5H_5)_2LnCl$ [12] and $(C_5H_5)LnCl_2$ [13] as part of a project to find octane enhancing additives for gasoline. However, the bis- and mono-cyclopentadienyl complexes were available only for the smaller lanthanides, later in the series, specifically Sm–Lu. Bis(cyclopentadienyl) complexes of divalent Eu and Yb were synthesized by Fischer and Fischer [14] and the THF-insoluble samarium analog was later reported by Watt and Gillow [15]. Streitwieser's synthesis of uranocene, $(C_8H_8)_2U$, in 1968 [16] stimulated the field and cyclooctatetraenyl complexes of both trivalent [17–19] and divalent [20] lanthanides were subsequently reported. The only crystal structure of an organolanthanide with a Ln–C single bond was that of the aryl "ate" salt, $[Lu(2,6-Me_2C_6H_3)_4][Li(THF)_4]$, which was reported in 1972 [21].

In the early 1970s when Spedding retired and when I was starting my independent academic career (April 1, 1975), organolanthanide chemistry was limited to the few classes of compounds described above. There were no hydrides, no alkyls, and no catalysis. Retrospectively, there was much to be discovered, but at the time, the limits appeared to have been reached. For example, there was a pervasive view that the lanthanides early in the series were so large and so prone to ligand redistribution reactions, that only ligand sets involving three cyclopentadienyl ligands or cyclooctatetraenyl ligands would provide tractable compounds with the large lanthanides. The following quotes show that little organolanthanide chemistry was expected from with these early lanthanides.

Regarding the synthesis of $(C_5H_5)_2LnCl$ complexes [5]:

"Any lanthanide from samarium through lutetium may be used in these reactions, but the light lanthanides, from lanthanum through neodymium, will not react. ...The compounds of the light lanthanides do not form."

Scheme 1. Organolanthanide complexes in the early 1970s.

Scheme 2. Organolanthanides act as alkali metal reagents with other metal halides.

Regarding the synthesis of $(\text{C}_5\text{H}_5)_2\text{LnCl}_2$ complexes [6]:

“As was observed in the $(\text{C}_5\text{H}_5)_2\text{MCl}$ series, the compounds below samarium cannot be prepared.”

Regarding $[\text{Lu}(\text{2,6-Me}_2\text{-C}_6\text{H}_3)_4]^{1-}$ [21]:

“Our attempts to prepare analogous compounds of lighter lanthanides have so far failed.”

In addition, both Wilkinson and Streitwieser had shown the cyclopentadienyl and cyclooctatetraenyl lanthanide complexes would react like alkali metal reagents and give up their organic ligands to other metals, Scheme 2. Hence their chemistry was thought to be analogous to alkali or alkaline earth metal chemistry and consequently quite limited.

Think about this situation! Organolanthanide chemistry was thought to be an area with limited potential. The complexes were considered to be highly reactive and difficult to handle due to high air and water sensitivity and a propensity to undergo ligand redistribution. The early metals did not form analogous complexes and samarium was the limit of what you could obtain in many cases. Lutetium was the limit in complexes with Ln–C single bonds.

Today we take for granted that we can use all of the lanthanides large and small for any type of organometallic chemistry we want. The chemistry is almost unlimited in terms of what ligands and donor atoms we can use. Certainly the introduction of the permethylated cyclopentadienyl ligand, $(\text{C}_5\text{Me}_5)^{1-}$, to lanthanide chemistry in the early 1980s [22–24] helped in this regard, but the organometallic chemistry of cyclopentadienyl-free metal complexes is now a major successful endeavor with many groups. In the early 1970s, it would have been inconceivable to build ancillary ligand platforms with nitrogen donor ligands, to do hydride much less polyhydride chemistry, to have a broad variety of alkyl complexes, and to have many varieties of organometallic catalysis.

Retrospectively, it is clear that there was much to discover in the 1970s. During Spedding's career, basic separation and purification was developed as well as aqueous and oxygen donor chemistry. Since Spedding's retirement, the non-aqueous and organometallic chemistry of the f elements flourished.

One can now ask, “Are there any major new developments still to be found in f element chemistry?” I will argue that the answer to that question is an emphatic “Yes!” I expect that there are just as many new opportunities waiting to be developed now as there were when Spedding started in 1929 or when I started in 1975. I predict that in 10 years the f element community will look back, just as we are now, and say “In 2008, the whole community thought this... but they did not realize that this whole new set of options was waiting to be discovered.”

I can make that prediction because of what has happened in f element reduction chemistry in the past 10 years just in my own lab. This is the main topic described in the remainder of this article.

3. f element reduction chemistry before 1997

My view of lanthanide chemistry when I started research in this area can be summarized by the following statement from an early paper [25]:

Table 1

Properties of the most common divalent lanthanide ions traditionally available in solution as molecular species.

	$\text{Ln}^{3+} + \text{e}^{1-} \rightarrow \text{Ln}^{2+}$ ($E_{1/2}$ vs. NHE)	Electron configuration of Ln^{2+}	Ionic radius of eight coordinate Ln^{2+}
Eu^{2+}	−0.35 V	$[\text{Xe}]4f^7$	1.25
Yb^{2+}	−1.15 V	$[\text{Xe}]4f^{14}$	1.14
Sm^{2+}	−1.55 V	$[\text{Xe}]4f^6$	1.27

Fig. 1. $(\text{C}_5\text{Me}_5)_2\text{Sm}(\text{THF})_2$ and $(\text{C}_5\text{Me}_5)_2\text{Sm}$.

“Although the lanthanide metals at times have been regarded as trivalent versions of the alkali and alkaline earth metals, and at other times have been compared to the transition metals, in fact, the lanthanides are unique. The radial properties, electronic properties, ionization potentials, and electron affinities of the lanthanide metals clearly distinguish them from any other metals. The challenge in the lanthanide area, therefore, is to place the lanthanide metals in chemical environments which allow exploitation of their chemical uniqueness.”

To develop the new chemical environments, my group and I focused on reductive lanthanide chemistry [26–30]. The three divalent ions that were available in solution when I started my career were Eu^{2+} , Yb^{2+} , and Sm^{2+} as shown in Table 1 [31].

We sought to develop the chemistry of the most reactive of those three ions, Sm^{2+} , and this proved to be very productive. We were able to synthesize the first soluble, crystallographically characterizable, metallocene of Sm^{2+} , namely the solvated $(\text{C}_5\text{Me}_5)_2\text{Sm}(\text{THF})_2$, [32,33] and subsequently, the surprisingly bent, unsolvated decamethylsamarocene, $(\text{C}_5\text{Me}_5)_2\text{Sm}$, Fig. 1 [34,35]. A wealth of new chemistry was provided to the f elements from just these two divalent compounds [28–30].

To illustrate the capacity of these compounds to open up new f element chemistry and to show the importance of reductive chemistry to the f element field, two examples of Sm^{2+} reactivity are shown in Eqs. (1) [36] and (2) [37]. The first reaction is unusual in

(1)

La	Ce	Pr	Nd	Pm	Sm	Eu	Gd
1.216	1.196	1.179	1.163	1.144	1.132	1.120	1.107
Tb	Dy	Y	Ho	Er	Tm	Yb	Lu
1.095	1.083	1.075	1.072	1.062	1.052	1.042	1.032

Scheme 3. Ionic radii (Å) for 9-coordinate trivalent lanthanide ions (circles drawn to scale to show the relative size of each ion).

that the alkene and carbon monoxide substrates were not expected to have significant reactivity with the ionic lanthanides at the time this reaction was discovered. Due to the limited radial extension of the 4f orbitals [38], little backbonding was expected between π acceptor ligands like these and the lanthanides. Consequently, little reactivity was expected. The transformation shown is a unique way to effect a double homologation of a C=C double bond.

Eq. (2) shows how Sm^{2+} reductive chemistry provided the first dinitrogen complex of an f element [37]. Again, due to the limited radial extension of the 4f orbitals, such dinitrogen complexes were unexpected. Of broader importance was the fact that this was the first example of a new coordination mode between dinitrogen and metals of any kind. The $\text{M}_2(\mu-\eta^2:\eta^2-\text{N}_2)$ co-planar arrangement of two metals and the two nitrogens had never been observed before in metal dinitrogen chemistry [39].

$(\text{C}_5\text{Me}_5)_2\text{Sm}(\text{THF})_2$ and $(\text{C}_5\text{Me}_5)_2\text{Sm}$ also provided distinctive chemistry with CO [40], CO_2 [41], azobenzene [42], and alkynes [43,44] among others [30,45]. We expected that compounds of this type and Sm^{2+} would continue to define the leading edge of f element reduction chemistry. However, there were also many reactions involving these compounds in which fully definable products were not obtainable. Although neither Sm^{2+} nor Sm^{3+} are highly paramagnetic ($\mu = 3.5$ and 1.7 BM, respectively [46]), this paramagnetism limited the amount of definitive information that could be obtained from NMR spectroscopy. Unless crystals suitable for X-ray crystallography could be grown, it was often not possible to define the new reduction chemistry. A common solution to this problem in trivalent lanthanide chemistry is to change the size of the metal to get quality single crystals. Frequently, the size of a given ligand set does not match the size of all the metals in the series to give high quality crystals for each metal. Choosing from among the many options shown in Scheme 3 [47] can provide such crystals. However, this option is not available for Sm^{2+} reductive chemistry. Only two other divalent ions, Eu^{2+} and Yb^{2+} , were available and they were significantly less reducing than Sm^{2+} , Table 1.

This metal size optimization is important not only for obtaining crystals, but it often can determine the success or failure of a reaction. Scheme 4 [48] shows one of many examples in the literature [49–51]. In this case, an erbium alkyl is readily hydrogenolyzed to a hydride, but the analogous reactions fails for the slightly smaller ytterbium, even though the hydride product is known and accessible by other routes.

Hence, one of the limitations of Sm^{2+} reductive chemistry is that it could not be size optimized based on the metal. Prior to 1997, this

Scheme 4. Sensitivity of hydrogenolysis reactivity to metal radius.

problem seemed insurmountable. The outlook for reductive Sm^{2+} chemistry in 1997 was that it was a productive area that would continue to grow by variation of substrate, reaction conditions, and ligands on the Sm^{2+} complexes. Since it was well established that Nature had provided only three divalent ions that were accessible in solution and since Sm^{2+} was the most reactive, this was the only option.

The following sections show that this narrow view of lanthanide reduction chemistry was far too limited. The assumption that reductive lanthanide chemistry was restricted only to Eu^{2+} , Yb^{2+} , and Sm^{2+} has been overturned by the discovery of five different ways of accomplishing the equivalent of this Ln^{2+} reductive reactivity.

4. New molecular divalent oxidation states in solution

The first development involved the discovery that divalent ions besides Eu^{2+} , Yb^{2+} , and Sm^{2+} were available in solution for reaction chemistry. The first example involves Tm^{2+} . This $4f^{13}$ ion is the next most likely divalent ion to be accessible based on its calculated redox potential of -2.3 V [31]. However, since it was much more reducing than Sm^{2+} and all previous reports on Tm^{2+} described highly colored solutions that had only transient existence [52–55], it was assumed that it was too reactive to use in solution reaction chemistry.

When Professor Mikhail N. Bochkarev of Nizhny Novgorod, Russia suggested to me that we collaborate to obtain structural information on what he thought was the first example of an isolable molecular Tm^{2+} complex, I was skeptical. Although initial attempts to obtain crystallographic data on samples of “ TmI_2 ” were unsuccessful, preparation of a fresh sample made in our lab by the Bochkarev method [56], provided the first example of a molecular divalent thulium complex, $\text{TmI}_2(\text{DME})_3$, Eq. (3) [57].

This was a very exciting development since Tm^{2+} was more reactive than the Sm^{2+} ion that had given a broad range of new chemistry to the lanthanide area. However, for the next three years neither my lab nor the Bochkarev lab obtained any significant new reductive reactivity from this Tm^{2+} complex [56,58–60,61]. The intensely colored green compound reacted quickly with many substrates to give colorless Tm^{3+} products, but TmI_3 was the only product readily identified. These results suggested that Tm^{2+} might be too reactive to provide useful divalent lanthanide chemistry as had been assumed prior to the discovery of $\text{TmI}_2(\text{DME})_3$ and the latter complex might be just an anomaly.

Reagent	X	Time	Isolated Yield
SmI_2/HMPA	I	<1 min	92%
TmI_2	I	<1 min	99%
SmI_2/HMPA	Br	15 min	65%
TmI_2	Br	<1 min	92%
SmI_2/HMPA	Cl	18 h	(no reaction)
TmI_2	Cl	<3 min	95%

Scheme 5. *In situ* $\text{TmI}_2(\text{DME})_x$ reactivity with alkyl halides relative to SmI_2/HMPA .

However, a breakthrough in Tm^{2+} chemistry occurred when attempts were made to use it *in situ* [62]. Examination of alkyl halide ketone coupling reactions effective with SmI_2/HMPA (HMPA = hexamethylphosphoramide), Scheme 5, *in situ* showed that TmI_2 could effect equivalent results without the carcinogenic HMPA additive. Moreover, TmI_2 could couple alkyl chlorides that were unreactive with SmI_2/HMPA [62].

Subsequent attempts to use the *in situ* method to accomplish organometallic chemistry with Tm^{2+} revealed the reason that Tm^{2+} chemistry previously had been so intractable. Efforts to make the thulium analog of $(\text{C}_5\text{Me}_5)_2\text{Sm}$ for *in situ* reactions by addition of two equivalents of KC_5Me_5 to a TmI_2 solution resulted in a reduction reaction before a substrate could be added! The addition of KC_5Me_5 to TmI_2 resulted in the reduction of the dinitrogen atmosphere that had been assumed to be inert, Eq. (4) [63]. As described later,

the reduction of dinitrogen by addition of ligands to TmI_2 is quite general. Hence, the rapid fading of the intense color of Tm^{2+} solutions observed in previous attempts to make Tm^{2+} derivatives presumably occurred because dinitrogen was being reduced.

Examination of Tm^{2+} , *in situ*, under argon instead of the reactive dinitrogen, demonstrated the high reactivity of this ion. Eq. (5) shows that Tm^{2+} can cleave diethyl ether to make ethoxide and oxide ligands [63].

Once it was established that Tm^{2+} could be accessed in solution, the assumptions that Dy and Nd were too unstable to be isolated as molecular species were suspect. It should be noted that TmX_2 , DyX_2 and NdX_2 ($\text{X} = \text{Cl, Br, I}$) had all been identified previously in the solid state and had been shown to contain divalent ions [64,65]. Encouraged by the Tm^{2+} result, the synthetic method of Bochkarev and Fagin [56] was used in our lab to obtain crystallographic data on the first molecular complex of Dy^{2+} , Eq. (6) [66]. Both linear and bent DyI_2 components were observed in the same single crystal as had previously been found with the isomorphous samarium analog [61].

Like TmI_2 , DyI_2 in the presence of cyclopentadienyl salts reduces dinitrogen in analogy to Eq. (4) above [67]. However, the more reducing Dy^{2+} is also capable of reducing naphthalene as shown in Eq. (7) [66]. Hydrolysis of the $(\text{C}_{10}\text{H}_8)^{2-}$ product to dihydronaphthalene parallels the type of reactivity found in Birch reductions [68]. However, with Dy^{2+} , an ether soluble molecular species can be used instead of an alkali metal in liquid ammonia.

The first molecular complex of Nd^{2+} was subsequently identified by Professor Bochkarev and Professor Schumann of the Technical

Table 2

Properties of the most common divalent lanthanide ions available in solution as molecular species.

	$\text{Ln}^{3+} + \text{e}^{1-} \rightarrow \text{Ln}^{2+}$ ($E_{1/2}$ vs. NHE)	Electron configuration of Ln^{2+}	Ionic radius of eight coordinate Ln^{2+}
Eu ²⁺	−0.35 V	[Xe]4f ⁷	1.25
Yb ²⁺	−1.15 V	[Xe]4f ¹⁴	1.14
Sm ²⁺	−1.55 V	[Xe]4f ⁶	1.27
Tm ²⁺	−2.3 V	[Xe]4f ¹³	1.09
Dy ²⁺	−2.5 V	[Xe]4f ¹⁰	1.19
Nd ²⁺	−2.6 V	[Xe]4f ⁴	1.29

University of Berlin, Eq. (8) [69].

Taken all together this meant that the number of divalent ions available in soluble form for lanthanide-based reductions had doubled from 1997 to 2001. After some 90 years of using Table 1, Table 2 became the appropriate list of divalent ions for which fully characterized molecular compounds were available. Imagine if someone suggested that in the next few years the number of oxidation states you commonly use would double. This seems impossible. However, it happened in lanthanide chemistry.

Although the number of divalent oxidation states accessible in solution had doubled, size optimization of the Sm^{2+} reductive chemistry was still not possible. Although six divalent ions were now available and had different sizes, the Ln^{2+} ions also had significantly different reaction chemistry. Size optimization of Sm^{2+} -like chemistry awaited further advances in reductive lanthanide chemistry.

5. Sterically induced reduction

A second major development in reductive lanthanide chemistry arose from a series of sterically crowded complexes that we have termed “long bond organometallics.” This class of complexes was discovered in the course of defining the reductive chemistry of $(\text{C}_5\text{Me}_5)_2\text{Sm}$ [34,35]. Reactions of $(\text{C}_5\text{Me}_5)_2\text{Sm}$ with unsaturated hydrocarbons of known redox potentials were being studied to define the reductive capacity indirectly since solution electrochemistry with these species was so challenging [70]. The reaction of $(\text{C}_5\text{Me}_5)_2\text{Sm}$ with 1,3,5,7-cyclooctatetraene was investigated because it was anticipated that two equivalents of $(\text{C}_5\text{Me}_5)_2\text{Sm}$ would reduce C_8H_8 to a dianion, Eq. (9), and the resulting “ $[(\text{C}_5\text{Me}_5)_2\text{Sm}]_2(\text{C}_8\text{H}_8)^{2-}$ ” composition would be very crowded and could display unusual structure or reactivity.

As shown in Eq. (10), C_8H_8 is reduced in this reaction to $(\text{C}_8\text{H}_8)^{2-}$ but a mono-

Fig. 2. Tris(pentamethylcyclopentadienyl) samarium, $(\text{C}_5\text{Me}_5)_3\text{Sm}$.

metallic product, $(\text{C}_8\text{H}_8)\text{Sm}(\text{C}_5\text{Me}_5)$, is isolated not the bimetallic composition cited above. The components remaining after the stable $(\text{C}_8\text{H}_8)\text{Sm}(\text{C}_5\text{Me}_5)$ compound forms are three $(\text{C}_5\text{Me}_5)^{1-}$ ligands and Sm^{3+} . With no better way to satisfy their electrostatic needs these assemble to generate the first structurally characterized tris(pentamethylcyclopentadienyl) complex, $(\text{C}_5\text{Me}_5)_3\text{Sm}$, Fig. 2 [71].

This was surprising since for decades it was assumed that it was impossible to put three of these large ligands around one metal center. As the cone angle of a $(\text{C}_5\text{Me}_5)^{1-}$ ring was estimated to be approximately 142° [72–74], $(\text{C}_5\text{Me}_5)_3\text{M}$ compounds seemed inaccessible because the sum of the cone angles would exceed 360° . Decades of studies on $(\text{C}_5\text{Me}_5)^{1-}$ chemistry by numerous research groups had not generated any $(\text{C}_5\text{Me}_5)_3\text{M}$ complexes.

However, the synthesis of $(\text{C}_5\text{Me}_5)_3\text{Sm}$ showed that the cone angle of a $(\text{C}_5\text{Me}_5)^{1-}$ ligand could be 120° in some cases. How was this possible? One way to reduce the cone angle of a ligand is to move it further away from the metal as shown in Fig. 3. Indeed, the $\text{Sm}-\text{C}(\text{C}_5\text{Me}_5)$ distances in $(\text{C}_5\text{Me}_5)_3\text{Sm}$ [71] were significantly longer than those observed in previously characterized Sm^{3+} complexes of $(\text{C}_5\text{Me}_5)^{1-}$. The 2.82 (5) Å average was larger than the typical averages, 2.71 (2)–2.75 (2) Å [75], and the three crystallographically independent $\text{Sm}-\text{C}(\text{C}_5\text{Me}_5)$ distances displayed the larger than normal values of 2.782 (2), 2.817 (2), and 2.910 (3) Å. Bending the methyl substituents back out of the plane of the $(\text{C}_5\text{Me}_5)^{1-}$ ring would also reduce the cone angle. Subsequent analyses have shown that this is a complicated situation in these long bond organometallics in which only one of the three crystallographically unique methyl groups has unusual bending out of the plane [76].

Since the $(\text{C}_5\text{Me}_5)^{1-}$ rings are much further from the Sm^{3+} cation than in conventional complexes, the electrostatic stabilization of the rings is not optimal. Consequently, the rings are much

Fig. 3. Effect of changing the metal cyclopentadienyl distance on cone angle.

more reactive than those in “sterically normal” complexes. This enhanced reactivity is observed in several types of unusual reactions. Eqs. (11)–(14) show that the $(C_5Me_5)^{1-}$ rings in $(C_5Me_5)_3Sm$ can ring open THF [77], initiate the polymerization of ethylene [77], engage in the first example of insertion chemistry between CO and $(C_5Me_5)^{1-}$ ligands [78], and undergo hydrogenolysis [77].

Eqs. (11)–(14) can be rationalized if an η^1 -intermediate such as $(\eta^5-C_5Me_5)_2Sm(\eta^1-C_5Me_5)$ is accessible, Eq. (15), since the reactivity is consistent with that of a $Ln-C$ single bond.

In efforts to obtain structural evidence for an η^1 -complex such as $(\eta^5-C_5Me_5)_2Sm(\eta^1-C_5Me_5)L$, $(C_5Me_5)_3Sm$ was reacted with numerous ligands, L. This revealed a new type of reduction chemistry.

When ligands such as $O=PPh_3$, $S=PPh_3$, and $Se=PPh_3$ were added to $(C_5Me_5)_3Sm$, the ligands were reduced [77]. Eqs. (16) and (17) show that $S=PPh_3$ and $Se=PPh_3$ are

reduced to PPh_3 and $(S)^{2-}$ or $(Se)^{2-}$ complexes previously synthesized by reduction of $S=PPh_3$ and $Se=PPh_3$ with the divalent $(C_5Me_5)_2Sm$, Eqs. (18) and (19) [79]. Reactions (16) and (17) are

analogous to reactions (18) and (19), respectively, with identical stoichiometries and samarium products. The difference is that the reductions in Eqs. (16) and (17) are accomplished with a trivalent samarium complex, not the divalent complex of Eqs. (18) and (19).

The parallel reaction chemistry of trivalent $(C_5Me_5)_3Sm$ and divalent $(C_5Me_5)_2Sm$ was also observed with other types of substrates. Eqs. (20) and (21) show that $(C_5Me_5)_3Sm$ reduces azobenzene [77] to the same product obtained by the reaction of one equivalent of $(C_5Me_5)_2Sm$ with azobenzene [42].

1,3,5,7- C_8H_8 is also reduced similarly. Hence, $(C_5Me_5)_3Sm$ reduces C_8H_8 to form a $(C_8H_8)^{2-}$ dianion, Eq. (22) [77], in a reaction parallel to that originally used to make $(C_5Me_5)_3Sm$ from C_8H_8 and $(C_5Me_5)_2Sm$, Eq. (10) [71].

Since the reductions in Eqs. (16), (17), (21) and (22) were occurring without a change in the metal oxidation state, i.e. both

Scheme 6. Comparison of sterically induced reduction (SIR) vs. traditional divalent Sm^{2+} reduction.

reactants and products contained Sm^{3+} , this meant that the formal reducing agent must be the ligand, $(\text{C}_5\text{Me}_5)^{1-}$. Consistent with this, $(\text{C}_5\text{Me}_5)_2$ is found as a byproduct of the above reactions and the fully balanced transformations are shown in Eqs. (23)–(26). If the $(\text{C}_5\text{Me}_5)^{1-}$ ligand acted as a one-electron reductant to generate

an electron and a C_5Me_5 radical, the dimerized product $(\text{C}_5\text{Me}_5)_2$ would be expected, Eq. (27).

The reason that $(\text{C}_5\text{Me}_5)_3\text{Sm}$ effects reduction analogous to $(\text{C}_5\text{Me}_5)_2\text{Sm}$ is that both reagents provide one electron and form a $[(\text{C}_5\text{Me}_5)_2\text{Sm}]^{1+}$ cation that can complex the reduced substrate, Scheme 6. Since the $(\text{C}_5\text{Me}_5)^{1-}$ reduction reaction, Eq. (27), has only been observed in sterically crowded molecules, it has been termed sterically induced reduction (SIR) [30].

The sterically induced reduction observed with $(\text{C}_5\text{Me}_5)_3\text{Sm}$ suggested that with the right amount of steric crowding, reduction could be accomplished without the need for a divalent metal ion. If $(\text{C}_5\text{Me}_5)_3\text{Sm}$ is a reductant only because of the steric crowding, then other $(\text{C}_5\text{Me}_5)_3\text{Ln}$ complexes could also be reductants. If $(\text{C}_5\text{Me}_5)_3\text{Ln}$ complexes could be made and had reduction chemistry analogous to $(\text{C}_5\text{Me}_5)_2\text{Sm}$, this would allow size optimization of this $(\text{C}_5\text{Me}_5)_2\text{Sm}$ chemistry for the first time. Sm^{2+} reductive reactivity would be available to all of the lanthanides and the metal could be selected, not because it had a divalent ion, but because it had the desired crystallizability or optical and magnetic properties.

The extension of SIR to the other lanthanides initially was problematic since the only routes to $(\text{C}_5\text{Me}_5)_3\text{Sm}$ involved the special

reactivity of Sm^{2+} precursors, i.e. Eq. (10) [71] above and Eq. (28) [80] and 29 [81].

However, this synthetic barrier was overcome by identifying two additional synthetic routes to $(\text{C}_5\text{Me}_5)_3\text{Sm}$ that started with trivalent precursors, $[(\text{C}_5\text{Me}_5)_2\text{SmH}]_2$ [82] and $(\text{C}_5\text{Me}_5)_2\text{Sm}(\mu\text{-Ph}_2\text{BPh}_2)$ [83], Eqs. (30) [84] and (31) [83], respectively. In both

of these reactions, as in Eqs. (10), (28) and (29), and virtually all the syntheses subsequently discovered for $(\text{C}_5\text{Me}_5)_3\text{M}$ complexes (vide infra), a stable byproduct is made that leaves three $(\text{C}_5\text{Me}_5)^{1-}$ rings and the M^{3+} with no better alternative than to form a sterically crowded $(\text{C}_5\text{Me}_5)_3\text{M}$ complex. In Eq. (30), the combination of a hydride ligand and tetramethylfulvene makes a stable $(\text{C}_5\text{Me}_5)^{1-}$ entity and leaves the $[(\text{C}_5\text{Me}_5)_2\text{Sm}]^{1+}$ ion and the $(\text{C}_5\text{Me}_5)^{1-}$ product [84]. In Eq. (31), KBPh_4 forms leaving $[(\text{C}_5\text{Me}_5)_2\text{Sm}]^{1+}$ and $(\text{C}_5\text{Me}_5)^{1-}$ [83].

The metallocene cation route in Eq. (31) was initially used to generate $(\text{C}_5\text{Me}_5)_3\text{Nd}$ [83], which allowed an examination of sterically induced reduction with a metal other than samarium. Although SIR appeared to be based on steric crowding, with $(\text{C}_5\text{Me}_5)_3\text{Sm}$, there was the possibility that the reaction was occurring via an undetected Sm^{2+} intermediate.

Trivalent $(\text{C}_5\text{Me}_5)_3\text{Nd}$ is in fact a reducing agent as shown with Se=PPh_3 in Eq. (32) [85], but it does not generate a reduction product analogous to that in the $(\text{C}_5\text{Me}_5)_3\text{Sm}$ reaction, Eq. (17).

Along with $(C_5Me_5)_2$ and PPh_3 , a $(Se_2)^{2-}$ organolanthanide product is formed instead of the $(Se)^{2-}$ product in Eq. (17). This indicated that $(C_5Me_5)_3Nd$ was a reductant, but was not as powerful as $(C_5Me_5)_3Sm$. Since $(C_5Me_5)_3Nd$ is not as sterically crowded as $(C_5Me_5)_3Sm$, this suggested that SIR could be moderated by the degree of steric crowding. This meant that metal size optimization could be used to control the reducing capacity of these sterically crowded complexes. Subsequent syntheses of $(C_5Me_5)_3Ln$ complexes of La, Ce, Pr, and Gd via Eq. (31) allowed this aspect to be examined further and the data indicate that reduction capacity can be modulated by varying the size of the metal and consequently the amount of steric crowding [81].

Extension of Eq. (31) to the larger metals, La and Ce, which have less crowded $(C_5Me_5)_3Ln$ complexes was surprisingly more difficult than the syntheses of $(C_5Me_5)_3Nd$ and $(C_5Me_5)_3Sm$. It was essential to use silylated glassware and freshly recrystallized $[(C_5Me_5)_2Ln][(\mu-Ph)_2BPh_2]$ with the larger metals [81,86]. Synthesis of $(C_5Me_5)_3Ln$ complexes of the smaller metals, proved to be even more challenging. Application of Eq. (31) to yttrium did not yield $(C_5Me_5)_3Y$, but instead formed $(C_5Me_5)_2YPh$ in benzene, Eq. (33), and $(C_5Me_5)_2YCH_2Ph$ in toluene, Eq. (34) [87]. C_5Me_5H was the byproduct.

Formation of C_5Me_5H ($pK_a=26$) from benzene ($pK_a=43$) and toluene ($pK_a=40$) was surprising. To avoid the use of arene solvents, the synthesis of $(C_5Me_5)_3Y$ was attempted from the hydride $[(C_5Me_5)_2YH]_2$ and tetramethylfulvene according to Eq. (35). This

provided $(C_5Me_5)_3Y$, the most crowded $(C_5Me_5)_3M$ isolated to date. Subsequent reaction of pure, isolated $(C_5Me_5)_3Y$ with benzene generated $(C_5Me_5)_2YPh$ and C_5Me_5H , Eq. (36), and demonstrated that

the steric crowding was severe enough to allow $(C_5Me_5)_3Y$ to engage in C–H bond activation of benzene. Attempts to isolate $(C_5Me_5)_3Lu$ have not yet been successful, but have led to additional unusual C–H bond activation chemistry [88].

The results obtained with the $(C_5Me_5)_3Ln$ complexes show that the one-electron reduction chemistry of divalent $(C_5Me_5)_2Sm$

can be extended across the lanthanide series from La to Y by synthesizing sterically crowded tris(pentamethylcyclopentadienyl) complexes. In addition, the reduction capacity appears to be tunable by varying the amount of steric crowding. Hence, the powerful aspect of metal size optimization can be applied to reduction chemistry.

The results obtained with the $(C_5Me_5)_3Ln$ complexes show more generally that new ligand reactivity can be accessed by making sterically crowded complexes. It seems that this result should not be limited only to $(C_5Me_5)_3M$ complexes and could be quite general for ligands with reducing capacity. An example of SIR with a $(C_5Me_5)_2M$ (large ligand) is described below and it is expected that complexes such as $(large\ ligand)_2M(C_5Me_5)$ and even $(large\ ligand)_xM$ could also display sterically induced reduction if the ligands are sufficiently reducing. In fact it seems plausible that sterically induced reduction reactivity has been observed before, but perhaps was not recognized. Attempts to synthesize sterically crowded complexes that gave unexpected reduction products or C–H bond activation products or ring-opened products, might have remained unpublished because the results did not make sense. It is possible that the sterically crowded product did form in these reactions and then went on to do unexpected chemistry.

6. Multi-electron reduction by combining SIR with metal based reduction

The synthesis of $(C_5Me_5)_3U$ via Eq. (37) [84] provided an

opportunity to determine if sterically induced reduction could be combined with metal based reduction. $(C_5Me_5)_3U$ has U–C(C_5Me_5) distances that are much longer than those in previously observed $(C_5Me_5)_3U^{3+}$ complexes of U^{3+} and is sterically crowded enough to do SIR. However, the U^{3+} ion is redox active on its own [89]. Hence, $(C_5Me_5)_3U$ could function as a two-electron reductant that converts a U^{3+} precursor to a U^{4+} product. It should be noted that once it was determined that $(C_5Me_5)_3U$ could exist, four other syntheses of were subsequently identified [90].

To examine the reductive capacity of $(C_5Me_5)_3U$, the 1:1 reaction of $(C_5Me_5)_3U$ and 1,3,5,7- C_8H_8 was studied since cyclooctatetraene can be reduced by two electrons, Eq. (9), that $(C_5Me_5)_3U$ could provide. A reaction occurred and formed $(C_5Me_5)_2$, the signature byproduct of sterically induced reduction, as well as a new uranium product, but some $(C_5Me_5)_3U$ starting material was left over. A clean reaction was obtained with a 2:3 $(C_5Me_5)_3U:C_8H_8$ ratio and the unusual mixed ligand product, $[(C_5Me_5)(C_8H_8)U]_2(\mu-\eta^3-\eta^3-C_8H_8)$, was isolated, Scheme 7 [91]. This product is structurally unique in that the $(C_8H_8)^{2-}$ ligand is not planar and is bound in a bis(allyl) mode in which one carbon is part of each coordinating allyl moiety.

The transformation in Scheme 7 is also unusual in terms of the reaction stoichiometry. Three equivalents of C_8H_8 are reduced to form the three $(C_8H_8)^{2-}$ ligands in the U^{4+} product, an overall six-electron reduction, but this was accomplished with just two equivalents of trivalent $(C_5Me_5)_3U$. Hence, this sterically crowded U^{3+} functions as a three-electron reductant to make U^{4+} complexes rather than acting as the two-electron reductant originally expected. Each $(C_5Me_5)_3U$ formally provides one electron from U^{3+}

and two electrons from sterically induced reduction involving two $(C_5Me_5)^{1-}$ ligands per uranium.

The fact that SIR could be combined with U^{3+} reduction raised the question of which redox process occurred first. Although most $(C_5Me_5)_3U$ reactions are too rapid to obtain this information, the reaction of $(C_5Me_5)_3U$ with chlorobenzene allowed the sequence to be determined [92]. $(C_5Me_5)_3U$ reacts with C_6H_5Cl primarily as a two-electron reductant to form $(C_5Me_5)_2UCl_2$, $(C_5Me_5)_2$, and biphenyl as primary products, Eq. (38).

This reaction occurs in a stepwise fashion in which one equivalent of C_6H_5Cl reacts quickly to make an isolable intermediate, whereas the second equivalent reacts slowly to form $(C_5Me_5)_2UCl_2$ from the intermediate in Eq. (39). If the first reduction occurred

via SIR, the metal would stay at the +3 oxidation state, a $(C_5Me_5)^{1-}$ would be lost, the reduction product, Cl^{1-} , would be added, and the intermediate would be the known complex $[(C_5Me_5)_2UCl]_3$ [93]. If U^{3+} reduction occurred first, the intermediate would be a U^{4+} complex that still has three $(C_5Me_5)^{1-}$ rings and possibly the Cl^{1-} product. This product, “ $(C_5Me_5)_3UCl$,” would be much more crowded than the $(C_5Me_5)_3U$ starting material. Hence, it seemed most likely that SIR would occur first to make $[(C_5Me_5)_2UCl]_3$ as the intermediate.

As shown in Eq. (40), the isolated intermediate is $(C_5Me_5)_3UCl$

[92]. This indicated that U^{3+} reduction occurred first, but more importantly it showed that it was possible to add another ligand to the already sterically crowded $(C_5Me_5)_3$ ligand set. The limits of steric crowding in $(C_5Me_5)_3M$ complexes had evidently not been reached. As expected from the overall reaction, Eq. (38), the U^{4+} intermediate, $(C_5Me_5)_3UCl$, reacts with a second equivalent of

Scheme 7. $(C_5Me_5)_3U$ as a three-electron reductant.

Scheme 8. Six-electron reduction via both metal and ligand based reduction.

C_6H_5Cl to make the U^{4+} product, $(C_5Me_5)_2UCl_2$, via SIR, Eq. (41).

As in the case of $(C_5Me_5)_3Sm$ and $(C_5Me_5)_3U$, once it was known that $(C_5Me_5)_3UCl$ could be synthesized, four additional new syntheses were discovered [92].

Another example of combining SIR with metal based reduction and the first example of sterically induced reduction with a bis(pentamethylcyclopentadienyl) complex was discovered with $[(C_5Me_5)_2U]_2(\mu-\eta^6:\eta^6-C_6H_6)$. This compound, obtained via Eq. (42) [94], has a non-planar C_6H_6 ligand derived from benzene sandwiched between

two uranium metallocenes. This complex, as well as the analogs previously reported in which a ligand derived from toluene is sandwiched between two bis(arylamide) uranium units, $[(ArRN)_2U]_2(C_6H_5CH_3)$ ($R = CMe_3$, $Ar = C_6H_3Me_2-3,5$) [95], are interesting in that there are several ways to assign oxidation states. $[(C_5Me_5)_2U]_2(\mu-\eta^6:\eta^6-C_6H_6)$ is considered to be a U^{3+} complex of a $(C_6H_6)^{2-}$ dianion on the basis of its structure and reactivity. In addition to the reduction capacity of the U^{3+} and $(C_6H_6)^{2-}$ components, the $U-C(C_5Me_5)$ distances in $[(C_5Me_5)_2U]_2(\mu-\eta^6:\eta^6-C_6H_6)$ are in the long bond range appropriate for sterically induced reduction chemistry.

The reaction chemistry of $[(C_5Me_5)_2U]_2(\mu-\eta^6:\eta^6-C_6H_6)$ with cyclooctatetraene showed that all of these sources of reduction reactivity could combine to make this complex a six-electron reductant, Scheme 8. Formally, two electrons are obtained from two U^{3+} centers, two electrons from $(C_6H_6)^{2-}$, and two from sterically induced reduction from two $(C_5Me_5)^{1-}$ ligands. This reaction showed that SIR can be combined with both metal and ligand reduction reactivity to accomplish multi-electron reduction [94].

In addition to the two, three, and six-electron reduction reactions shown above, examples of four and eight-electron reductions were obtained by examining reactions of azobenzene with

Scheme 9. Four-electron reduction via both metal and ligand-based reduction. **Scheme 10.** Eight-electron reduction via both metal and ligand based reduction.

$(C_5Me_5)_3U$ and $[(C_5Me_5)_2U]_2(\mu-\eta^6:\eta^6-C_6H_6)$, respectively [96]. As shown in Schemes 9 and 10, both reactions generate the U^{6+} bis(imido) complex $(C_5Me_5)_2U(=NPh)_2$ previously reported by Burns and coworkers [97]. In Scheme 9, a one-electron SIR process is combined with the U^{3+} to U^{6+} transformation. In Scheme 10, the uranium redox chemistry combines with reduction from the $(C_6H_6)^{2-}$ ligand.

The growing list of sterically crowded complexes shown in Table 3 demonstrates that it is possible to make an entire class of new complexes that have bond distances significantly longer than those previously observed. Once the first example of these so-called “long bond organometallics” was discovered as part of the investigation of $(C_5Me_5)_2Sm$ reduction chemistry, researchers had the confidence to try to make such complexes in other ways. Subsequently, at least 19 different reactions have been discovered that lead to $(C_5Me_5)_3M$ compounds. All of these retrospectively look reasonable, but none had been attempted because it was believed that the product could not exist.

The long bond organometallics are not only structurally interesting, but they also display enhanced ligand reactivity due to the long metal ligand distances. It is surprising that these sterically crowded complexes generate new reductive chemistry since redox chemistry of metal complexes is usually manipulated by controlling the electronic, not steric, aspects of the complexes. In this case, redox reactivity is generated with normally inert ligands via steric crowding.

Table 3
Long-bond organometallics in approximate order of discovery.

$(C_5Me_5)_3Sm$
$(C_5Me_5)_3U$
$(C_5Me_5)_3Nd$
$(C_5Me_5)_3UCl$, $(C_5Me_5)_3UF$
$(C_5Me_5)_3La$, $(C_5Me_4R)_3La$ $R = Et, ^iPr, SiMe_3$, $(C_5Me_4Et)_3Sm$
$(C_5Me_5)_3ThH$
$(C_5Me_5)_3Ce$, $(C_5Me_5)_3Pr$
$[(C_5Me_5)_2U]_2(C_6H_6)$
$(C_5Me_5)_3UMe$,
$(C_5Me_5)_3Gd$, $(C_5Me_5)_3Y$

7. Divalent reduction chemistry from trivalent reagents and alkali metals, “ LnZ_2/M ”

A third new option in reductive f element chemistry arose from investigations of the reduced dinitrogen complexes accessible via the recently discovered molecular complexes of Nd^{2+} , Dy^{2+} , and Tm^{2+} discussed above. The reaction exemplified by the synthesis of $[(C_5R_5)_2Tm]_2(\mu-\eta^2:\eta^2-N_2)$, $\{C_5R_5 = [1,3-(Me_3Si)_2C_5H_3]$ and $(C_5H_4SiMe_3)\}$, in Eq. (4) [63] is quite general. As shown in Eq. (43), a variety of anionic ligands, Z^{1-} , can be added to the diiodides of Tm^{2+} , Dy^{2+} , and Nd^{2+} under nitrogen to generate

(43)

$[Z_2Ln(THF)_x]_2(\mu-\eta^2:\eta^2-N_2)$ products. The applicable ancillary anionic ligands are $(Z)^{1-} = [1,3-(Me_3Si)_2C_5H_3]^{1-}$ and $(C_5H_4SiMe_3)^{1-}$ [63,67], $[N(SiMe_3)_2]^{1-}$ [98], and $(OC_6H_3^tBu_2-2,6)^{1-}$ [98]. Eq. (44) specifically shows the bis(trimethylsilylamide)

(44)

example. In each of these reactions it was assumed that ionic metathesis between the added ligand salt and LnI_2 reagent generated a reactive divalent intermediate of formula “ LnZ_2 ”, i.e. “ $Ln[N(SiMe_3)_2]_2$ ” in the case of Eq. (44), that reduced dinitrogen. The only case in which we could isolate an intermediate, however, was $[1,3-(Me_3Si)_2-C_5H_3]_2Tm(THF)$ [67,99,100].

In efforts to find alternative routes to these reactive “ LnZ_2 ” intermediates, the reduction of $Ln[N(SiMe_3)_2]_3$ with potassium metal was investigated [101,102]. Bradley showed in the 1970s that these $Ln[N(SiMe_3)_2]_3$ complexes can be readily synthesized from $LnCl_3$ and $[N(SiMe_3)_2]^{1-}$ salts [103]. As shown in Eq. (45), $\{[(Me_3Si)_2N]_2Ln\}_2(\mu-\eta^2:\eta^2-N_2)$ complexes of Tm, Dy, and Nd can be made in this way. Since the precursor complexes, $Ln[N(SiMe_3)_2]_3$,

(45)

are easier to synthesize and handle than the LnI_2 reagents, this was an important synthetic breakthrough.

Eq. (44) was also mechanistically interesting because no evidence for the anticipated divalent intermediates was observed during the reactions. Since divalent lanthanide complexes are intensely colored, color changes were expected during these reactions. It was possible that the divalent intermediates were so short lived that they could not be observed, but it was also possible that the reaction did not proceed through the anticipated intermediate.

To examine this point, Eq. (45) was conducted with $Ho[N(SiMe_3)_2]_3$. Holmium had no previously identified molecular divalent oxidation state chemistry in solution. Holmium was chosen because it had a size similar to Dy and Tm and its calculated reduction potential was closer to the known divalent ions than many of the other lanthanides of that size, Table 4 [31]. Surprisingly, dinitrogen is reduced in this holmium reaction, Eq. (46), $Ln = Ho$,

Table 4Calculated values of the $\text{Ln}^{3+} + \text{e}^{1-} \rightarrow \text{Ln}^{2+}$ half reaction vs. NHE and electronic configurations.³¹

Ln	Ln(III)/Ln(II) vs. NHE	Ln(II) electron configuration	Ln	Ln(III)/Ln(II) vs. NHE	Ln(II) electron configuration
Eu	−0.35 V	[Xe]4f ⁷	Er	−3.1 V	[Xe]4f ¹²
Yb	−1.15 V	[Xe]4f ¹⁴	La	−3.1 V	[Xe]4f ¹
Sm	−1.55 V	[Xe]4f ⁶	Ce	−3.2 V	[Xe]4f ²
Tm	−2.3 V	[Xe]4f ¹³	Tb	−3.7 V	[Xe]4f ⁹
Dy	−2.5 V	[Xe]4f ¹⁰	Gd	−3.9 V	[Xe]4f ⁸
Nd	−2.6 V	[Xe]4f ⁴	Lu	^a	[Xe]4f ¹⁴ 5d ¹
Pr	−2.7 V	[Xe]4f ³	Y	^a	[Kr]4d ¹
Ho	−2.9 V	[Xe]4f ¹¹			

^a No calculated value.

and examination of all the other lanthanides began. Dinitrogen

is also reduced according to Eq. (46) for Ln = Er, Tb, Gd, Y, and Lu [101]. Er, Tb, and Gd have calculated $\text{Ln}^{3+}/\text{Ln}^{2+}$ reduction potentials (Table 4) more negative than the reduction potential of the potassium reductant, −2.9 V vs. NHE! A comparison with potassium cannot be made for Y and Lu, since there are no calculated values for the Y^{2+} or Lu^{2+} . These ions had never been observed either in solution or the solid state [65].

The results in Eq. (46) suggested that divalent-like lanthanide reduction can be obtained by combining a trivalent precursor with potassium. This LnZ_3/M combination in which M is an alkali metal generates “ LnZ_2 ” reactivity. This is almost arithmetically trivial, a +3 metal plus a reagent that delivers a −1 electron generates +2 metal reactivity [65]. However, with many of these metals, this is the first time +2 reactivity has been observed in solution. Alkali metal reductions of metal complexes are common in the literature, but they generally involve intermediates of lower valent ions that are isolable. The reactions most closely related to Eq. (46) in the literature are Lappert’s alkali metal reductions of $(\text{C}_5\text{H}_3\text{R}_2)_3\text{Ln}$ complexes (Ln = La, Ce; R = CMe_3 , SiMe_3) [104–107].

If the dinitrogen reductions in Eqs. (45) and (46) involve divalent “ $\text{Ln}[\text{N}(\text{SiMe}_3)_2]_2$ ” intermediates, this would be the first evidence of soluble, molecular species containing Ho^{2+} , Er^{2+} , Tb^{2+} , Gd^{2+} , Y^{2+} , and Lu^{2+} . If the reactions did not involve a “ $\text{Ln}[\text{N}(\text{SiMe}_3)_2]_2$ ” pathway, then alternative methods of dinitrogen reduction involving trivalent intermediates like “ $(\eta^1\text{-N}_2)\text{Ln}[\text{N}(\text{SiMe}_3)_2]_3$ ” would have to be considered. Although species such as $(\eta^1\text{-N}_2)\text{M}(\text{NR}_2)_3$ are well known in transition metal chemistry [108,109], they are much less likely with the lanthanides particularly in THF solution. The only fully characterized, monometallic, end-on dinitrogen complex of an f element, $(\text{C}_5\text{Me}_5)_3\text{U}(\eta^1\text{-N}_2)$, is stable only under dinitrogen pressure in non-coordinating solvents [110]. The THF solvent of Eqs. (45) and (46) would be expected to bind the lanthanide centers before N_2 both because of lanthanide preferences for polar ligands and the higher concentration of the solvent.

Although the mechanisms of Eqs. (45) and (46) remain to be determined, the LnZ_3/K reaction constitutes another method to accomplish divalent “ LnZ_2 ” chemistry. This also provides an additional route to size optimization of Ln^{2+} -like reductive chemistry and allows reduction chemistry with diamagnetic Y and Lu.

Although Eq. (46) was successful with most of the lanthanides, crystals of $\{[(\text{Me}_3\text{Si})_2\text{N}]_2\text{Ln}\}_2(\mu\text{-}\eta^2\text{-}\eta^2\text{-N}_2)$ products were not obtainable for Ln = La, Ce, and Pr [102]. Examination of Table 4 shows that this does not correlate with calculated reduction potentials, i.e. these ions are not the most difficult to reduce. On the other hand, since these are the three largest lanthanides in the series, a size correlation was suggested.

If Eq. (46) was not successful with La, Ce, and Pr because size of the metals was not commensurate with this ligand set for crystal formation, it should be possible to change the size of the ligand and achieve successful dinitrogen reduction with these metals. This was achieved with $\text{Ln}(\text{C}_5\text{Me}_4\text{H})_3$ complexes [111–113]. These are desirable precursors since they can be synthesized directly from LnCl_3 and $\text{KC}_5\text{Me}_4\text{H}$ for most of the lanthanides [51]. The LnZ_3/K reaction is successful with $(\text{Z})^{1-} = (\text{C}_5\text{Me}_4\text{H})^{1-}$ for the largest lanthanide, La, as well as the smallest, Lu, Eq. (47). Examples with Ln = Ce, Pr, and Nd were also identified and the reaction presumably is general for the entire series.

Accessing “ LnZ_2 ” reactivity via LnZ_3/K with $\text{Z}^{1-} = (\text{C}_5\text{Me}_5)^{1-}$ was desirable due to the large amount of information already in the literature on bis(pentamethylcyclopentadienyl) complexes. However, as described in Section 5, synthesis of the $(\text{C}_5\text{Me}_5)_3\text{Ln}$ precursors is challenging and the diamagnetic Ln = Lu complex has not yet been isolated [88]. As an alternative, the reduction chemistry of the tetraphenylborate salts, $(\text{C}_5\text{Me}_5)_2\text{Ln}(\mu\text{-Ph}_2\text{BPh}_2)$ [83], that are precursors to $(\text{C}_5\text{Me}_5)_3\text{Ln}$ according to Eq. (31) was examined. These tetraphenylborate salts also can be used as precursors to the dinitrogen complexes, Eq. (48) [111], and this established that heteroleptic $\text{LnZ}_2\text{Z}'/\text{K}$ reactions as well as homoleptic LnZ_3/K reactions can provide “ LnZ_2 ”-like reactivity.

8. Divalent reduction chemistry from reduced dinitrogen complexes, “ $(\text{Z}_2\text{LnL}_x)_2\text{N}_2$ ”

A fourth method of effecting Ln^{2+} -like reductive reactivity was discovered while examining the reactivity of the $[\text{Z}_2(\text{THF})\text{Ln}]_2(\mu\text{-}\eta^2\text{-}\eta^2\text{-N}_2)$ complexes broadly obtainable from LnZ_3/M and $\text{LnZ}_2\text{Z}'/\text{M}$ reactions. Since these compounds contain a reduced dinitrogen ligand, $(\text{N}_2)^{2-}$, they have considerable reductive capacity on their own. Accordingly their reactivity with reducible substrates was examined for comparison with the other reduction systems described above.

Scheme 11. Similarity of $[(\text{C}_5\text{Me}_5)_2(\text{THF})\text{La}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$ and $(\text{C}_5\text{Me}_5)_2\text{Sm}$ in reduction of anthracene.

Scheme 12. Reduction of CO_2 by $[(\text{C}_5\text{Me}_4\text{H})_2(\text{THF})\text{Lu}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$.

As shown in Scheme 11 [114], the trivalent lanthanum complex, $[(\text{C}_5\text{Me}_5)_2(\text{THF})\text{La}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$, reduces anthracene to make a $(\text{C}_{14}\text{H}_{10})^{2-}$ complex analogous to that obtained previously with $(\text{C}_5\text{Me}_5)_2\text{Sm}$ [70]. Carbon dioxide can be reductively coupled to form an oxalate as shown in Scheme 12 by an analogous tetramethylcyclopentadienyl lutetium complex, $[(\text{C}_5\text{Me}_4\text{H})_2(\text{THF})\text{Lu}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$ [115].

The reducing capacity of $[(\text{C}_5\text{Me}_5)_2(\text{THF})\text{La}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$ is best shown in its reaction with CO [114]. This involves a complicated two-electron reductive homologation of three molecules of carbon monoxide to a carboxylic acid derivative of ketene. The product is obtained as a dimer, Scheme 13. This remarkable transformation involves complete cleavage of CO triple bonds since each $(\text{O}_2\text{CC}=\text{C}=\text{O})^{2-}$ ligand contains one carbon free of oxygen. A simi-

lar reaction had previously been observed with $(\text{C}_5\text{Me}_5)_2\text{Sm}(\text{THF})_2$ [40], but the product was too insoluble to obtain full NMR characterization. By size optimizing the metal via the “ Ln_2N_2 ” reductive system, full ^1H and ^{13}C NMR characterization of the ^{12}CO and ^{13}CO products was possible.

Since the $(\text{N}_2)^{2-}$ ligand delivers two electrons as it reverts to N_2 in these reactions, the trivalent bimetallic $[\text{Z}_2(\text{THF})\text{Ln}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$ complexes effectively react to generate two equivalents of “ LnZ_2 ”. Since the Ln_2N_2 reduction system involves a single molecular species, it is experimentally simpler than the two-component LnZ_3/M method. In some cases, the Ln_2N_2 method is complementary to LnZ_3/M reduction in that it can generate products not readily obtainable from any other currently available reductive lanthanide metal system. For example, reductions of CO and CO_2 via $(\text{C}_5\text{Me}_5)_2\text{Ln}[(\mu\text{-Ph})_2\text{BPh}_2]/\text{K}$ reactions are not as clean as those in Schemes 12 and 13.

9. Reduction chemistry from “innocent” ligands

In the course of examining “control” reactions to evaluate sterically induced reduction, yet another type of reduction option was identified, namely the use of common ligands to effect reduction. This can be viewed as an outgrowth of the SIR reaction that uses $(\text{C}_5\text{Me}_5)^{1-}$ ligands for reduction and the Ln_2N_2 method that uses $(\text{N}_2)^{2-}$ ligands, but it involves neither sterically crowded complexes nor ligands that are clearly in a highly reduced state.

Scheme 13. Reductive homologation of CO by $[(\text{C}_5\text{Me}_5)_2(\text{THF})\text{La}]_2(\mu\text{-}\eta^2\text{:}\eta^2\text{-N}_2)$.

Scheme 14. Reduction by a tetraphenylborate complex.

This fifth approach to f element reduction chemistry was identified by examining a blank reaction for comparison with the reduction of azobenzene with $(\text{C}_5\text{Me}_5)_3\text{U}$, Scheme 9 [96]. To determine how a “sterically normal” U^{3+} metallocene would react with PhN=NPh in the absence of steric crowding, the reaction with $(\text{C}_5\text{Me}_5)_2\text{U}[(\mu\text{-Ph})_2\text{BPh}_2]$ was examined. Surprisingly, $(\text{C}_5\text{Me}_5)_2\text{U}[(\mu\text{-Ph})_2\text{BPh}_2]$ was found to reduce azobenzene to the same organoactinide product as $(\text{C}_5\text{Me}_5)_3\text{U}$, i.e. the U^{6+} bis(imido) complex, $(\text{C}_5\text{Me}_5)_2\text{U(=NPh)}_2$, Scheme 14. This involves a four-electron reduction of azobenzene. Although it was anticipated that three electrons could come from a $\text{U}^{3+}/\text{U}^{6+}$ couple, the origin of the fourth electron was not clear. In $(\text{C}_5\text{Me}_5)_3\text{U}$, this came from a $(\text{C}_5\text{Me}_5)^{1-}$ ligand via SIR. As shown in Scheme 14, the fourth electron arises from the $(\text{BPh}_4)^{1-}$ ligand. Although this $(\text{BPh}_4)^{1-}$ redox couple has been known for a long time [116], this was the first time, to our knowledge, that it was used in conjunction with a metal based reduction to accomplish a multi-electron reduction. It is interesting to note that $(\text{BPh}_4)^{1-}$ is often avoided as the counteranion in olefin polymerization reactions involving cationic metal alkyl complexes. One reason is that it is presumed to give poor catalyst performance by blocking the incoming olefin substrates. However, if reduction reactions occur as shown in Scheme 14 during these polymerization reactions, this would be another reason that other counteranions are preferred.

In light of the $(\text{BPh}_4)^{1-}$ result we wondered what other “innocent” ligands common in f element chemistry could act as reductants. One obvious choice is the hydride ligand. This is a well known reductant, although it usually adds to substrates as reduction occurs and does not simply provide an electron and an inert byproduct as observed for $(\text{C}_5\text{Me}_5)^{1-}$ in sterically crowded complexes, $(\text{N}_2)^{2-}$, and $(\text{BPh}_4)^{1-}$ as described above. Moreover with f element hydrides, sigma bond metathesis is a common reaction in addition to reductive addition to unsaturated substrates [117]. Nonetheless, we opted to examine the possibility that hydride ligands could provide reduction according to Eq. (49).

Comparison of hydride reductive reactivity with the $(\text{C}_5\text{Me}_5)^{1-}$ and $(\text{BPh}_4)^{1-}$ reactions described above was complicated by the fact that the relevant uranium hydrides exist as an equilibrium mixture of trivalent and tetravalent species as shown in Eq. (50) [118,119]. Fortunately, conditions were found to obtain relatively pure examples of both the U^{3+} and U^{4+} hydrides so their reduction chemistry could be examined [119].

Scheme 15. Uranium hydride reduction of diphenyldisulfide.

Scheme 16. Uranium hydride reduction of cyclooctatetraene.

As shown in Scheme 15, $[(\text{C}_5\text{Me}_5)_2\text{UH}]_2$ effects a four-electron reduction of two equivalents of PhSSPh to form two equivalents of $(\text{C}_5\text{Me}_5)_2\text{U(SPh)}_2$ [119]. The reductive capacity formally derives from two $\text{U}^{3+}/\text{U}^{4+}$ redox couples and two H^{1-}/H processes. In Scheme 16, $[(\text{C}_5\text{Me}_5)_2\text{UH}]_2$ reduces three equivalents of C_8H_8 to make $[(\text{C}_5\text{Me}_5)(\text{C}_8\text{H}_8)\text{U}]_2(\mu\text{-}\eta^3\text{:}\eta^3\text{-C}_8\text{H}_8)$, in a reaction analogous to Scheme 7 above. In this case, hydride reduction according to Eq. (49) is combined with $\text{U}^{3+}/\text{U}^{4+}$ redox couples and SIR. Scheme 17 shows that $[(\text{C}_5\text{Me}_5)_2\text{UH}]_2$ can function as an eight-electron reduc-

Scheme 17. Uranium hydride reduction of azobenzene.

Scheme 18. Reduction chemistry of tetravalent $[(C_5Me_5)_2UH_2]_2$.

tant with $PhN=NPh$. In this case the hydride reductive reactivity is combined with a U^{3+}/U^{6+} redox couple [119].

Scheme 18 shows that the analogous transformations can be accomplished starting from the U^{4+} hydride $[(C_5Me_5)_2UH_2]_2$ [119]. Although it is possible that all of these reactions go through $[(C_5Me_5)_2UH]_2$, via the equilibrium in Eq. (50), the half reactions shown indicate the hydride origin of the reducing equivalents.

The reductive reactivity of $[(C_5Me_5)_2ThH_2]_2$ was examined since thorium does not have a readily accessible trivalent state and reduction from the hydride ligands alone would be better defined. Indeed, as shown in Scheme 19, $[(C_5Me_5)_2ThH_2]_2$ also reduces $PhSSPh$ and C_8H_8 in analogy to the uranium reactions above [119]. In the four-electron $PhSSPh$ reaction, all the reduction arises from hydride ligands. In the six-electron reduction of C_8H_8 , four electrons arise from the hydrides and two from SIR. This provided the thorium analog of $[(C_5Me_5)(C_8H_8)U]_2(\mu-\eta^3:\eta^3-C_8H_8)$, for the first time. Since $[(C_5Me_5)(C_8H_8)U]_2(\mu-\eta^3:\eta^3-C_8H_8)$, was made from U^{3+} precursors for which there were no Th^{3+} analogs, there was no obvious route to $[(C_5Me_5)(C_8H_8)Th]_2(\mu-\eta^3:\eta^3-C_8H_8)$. However, these reactions show that $An^{4+}-H^{1-}$ hydrides can provide reactivity equivalent to An^{3+} .

Examination of the analogous hydride reductive chemistry with lanthanides has shown that although $Ln^{3+}-H^{1-}$ units can deliver reductive reactivity equivalent to Ln^{2+} , i.e. this “ Z_2LnH ” is another approach to “ LnZ_2 ”, there are additional side reactions that occur [120]. Hence, the $[(C_5Me_5)_2LnH]_x$ complexes with $Ln = La, Sm$, and Y cleanly reduce $PhSSPh$ to $[(C_5Me_5)_2LnSPh]_2$ products, Eq. (51). $[(C_5Me_5)_2SmSPh]_2$ was previously accessible from divalent

(51)

$(C_5Me_5)_2Sm$, but there was no analogous route for the lanthanum and yttrium complexes.

Although the $PhSSPh$ reactions with the $[(C_5Me_5)_2LnH]_x$ complexes were straightforward, reactions with C_8H_8 and $PhN=NPh$ are more complicated with the metals larger and smaller than samarium. $[(C_5Me_5)_2SmH]_2$ reacts with C_8H_8 according to Eq. (52).

This is equivalent to the $(C_5Me_5)_2Sm$ reaction with C_8H_8 , Eq. (10), that was the original synthesis of $(C_5Me_5)_3Sm$. Hence, $(C_5Me_5)_3Sm$ could have been discovered via $Sm^{3+}-H^{1-}$ chemistry rather than by Sm^{2+} chemistry.

The reactions of $[(C_5Me_5)_2YH]_x$ with C_8H_8 are more complicated and have provided some insight into opportunities for expanding f element metallocene chemistry in new directions [120]. The main reaction between $[(C_5Me_5)_2YH]_x$ and C_8H_8 is a reduction analogous to that shown above with $(C_5Me_5)_2Sm$ in Eq. (10). Hence $[(C_5Me_5)_2YH]_x$ provides divalent-like reactivity and the equivalent of “ $(C_5Me_5)_2Y$ ” to form $(C_5Me_5)Y(C_8H_8)$ and $(C_5Me_5)_3Y$, Eq. (53).

(53)

However, two unusual byproducts have been isolated from this reaction that show the capacity for future possibilities in f element metallocene chemistry, Scheme 20. In benzene, a $(C_5Me_5)Y[(\eta^5-C_5Me_4CH_2-C_5Me_4CH_2-\eta^3)]$ complex forms in which two $(C_5Me_5)^{1-}$ rings are linked to make a new type of *ansa*-allyl-cyclopentadienyl dianion that binds as a pentahapto-trihapto chelate. In cyclohexane, a $(C_5Me_5)_2Y(\mu-\eta^8:\eta^1-C_8H_7)Y(C_5Me_5)$ complex forms in which a $(C_8H_8)^{2-}$ ring is metalated to form the first example of a bridging $(C_8H_7)^{3-}$ trianion [120].

Collectively, the $(BPh_4)^{1-}$ and H^{1-} reactions suggest that a wider variety of ligands common in f element chemistry should be inves-

Scheme 19. Reduction chemistry of tetravalent $[(\text{C}_5\text{Me}_5)_2\text{ThH}_2]_2$.

Scheme 20. Unusual byproducts from $[(\text{C}_5\text{Me}_5)_2\text{YH}]_2$ reduction of C_8H_8 .

tigated for their ability to deliver electrons and provide access to lower oxidation state reactivity.

10. Conclusion

For over 90 years, reductive lanthanide chemistry via Ln^{2+} ions was limited to just three elements, Eu^{2+} , Yb^{2+} , and Sm^{2+} . Extensive experimental research as well as thermodynamic and spectroscopic analyses suggested that these were the only divalent species available for reductive chemistry in solution.

During the past 10 years, five new options for accessing Ln^{2+} -like reactivity have become available. The number of fully characterized divalent lanthanides available in solution has doubled. Reductive chemistry has been found in “long bond organometallics” that were thought to be too sterically crowded to exist. The combination of an alkali metal with a trivalent lanthanide complex has provided access to Ln^{2+} -like reactivity even with elements for which no divalent ions are known in solution. Reduced dinitrogen complexes containing $(\text{N}_2)^{2-}$ ligands made by the LnZ_3/M and $\text{LnZ}_2\text{Z}'/\text{M}$ reduction methods provide yet another class of effective and powerful reducing agents. This type of ligand based reduction chemistry has also been identified in sterically normal lanthanide complexes with “innocent ligands” like hydrides and tetraphenylborates. These methods extend options for productive lanthanide reduction chemistry beyond Eu^{2+} , Yb^{2+} , and Sm^{2+} to all the other elements in the series including complexes of diamagnetic La^{3+} , Y^{3+} , and Lu^{3+} .

The reductive chemistry of the 5f elements has also been expanded in the course of these lanthanide studies. Sterically induced reduction and the reductive chemistry of traditional ligands like hydride and tetraphenylborate in sterically normal

compounds have been exceptionally valuable in uranium and thorium chemistry. These approaches have provided access to the equivalent of reduced oxidation states for these actinides that are not normally accessible. This has expanded the reductive reactivity possible and led to new types of organoactinides.

The results demonstrate that it is possible to access the reactivity of “virtual” divalent oxidation states, even if they have never been isolated under the reaction conditions. This research also provides methods to access multi-electron redox reactivity with f elements including examples with two, three, four, six, and eight-electron reductions. Multi-electron reductions with mono- and bimetallic complexes of this type are unusual not only in f element chemistry, but in chemistry in general. These studies have also shown that traditional assumptions about the distances of stable bond lengths in f element chemistry were limited.

Considering that reduction chemistry is such a fundamental reaction and has been studied so long and thoroughly, it is remarkable that this many new options were waiting to be discovered. The fact that this heavily studied area can provide fertile ground for new types of reaction chemistry suggests that similar advances are awaiting us in many other areas of f element research. Just as there was much to be discovered during Spedding’s four decade research career, during the 1970–1997 period, and during the past decade, it is likely that we now are on the brink of many equally incredible discoveries in f element science and technology. The recent developments in reductive chemistry should be used as an example of the benefits of moving beyond traditional assumptions and should be used to stimulate us to attempt *major* breakthroughs in each of the areas that we currently do our research. As stated by John Corbett in his 11th Spedding Award Address, “It is always difficult to predict the unimaginable.” We must use our imagination to try to push the limits of our fields no matter how much has been discovered to date. History suggests that advances as fundamental as those described here are just waiting to be discovered.

Acknowledgments

I am grateful to the people who started me in science, my mentors, Professor Donald F. Gaines, Professor M. Frederick Hawthorne, and the late Professor Earl L. Muetterties. I would also like to thank Professor Kenneth N. Raymond for his support and encouragement

when I was a novice in f element chemistry. This research would not have been possible without the many fine students who have worked so hard to advance this experimentally difficult area of chemistry. Without such a group of talented and motivated students, none of these discoveries would have been made. Many thanks also to the crystallographers and especially Dr. Joseph W. Ziller for providing the structural data essential to defining this new chemistry. Significant funding is also necessary for the advancement of science and I thank the National Science Foundation and the Chemical Sciences, Geosciences, and Biosciences Division of the Office of Basic Energy Sciences of the Department of Energy for support of this research. I also wish to thank Bracco Research USA for supporting the Spedding Award. Finally, many thanks to Thomas J. Mueller, Benjamin M. Schmiede, and Michael K. Takase for their help in assembling this manuscript.

References

- [1] W.I.B. Beveridge, *The Art of Scientific Investigation*, 3rd ed., Vintage Books, New York, 1957.
- [2] S. Ramón y Cajal, *Advice to a Young Investigator* (N. Swanson, L.W. Swanson, Trans.), MIT Press, Cambridge, MA, 1999.
- [3] J.D. Corbett, F.H. Spedding, *Biographical Memoirs of the National Academy of Sciences*, Vol. 80, 2001, <http://www.nap.edu/html/biomems/>.
- [4] J.H. Forsberg, *Coord. Chem. Rev.* 10 (1973) 195.
- [5] R.G. Hayes, J.L. Thomas, *Organomet. Chem. Rev. A* 7 (1971) 1.
- [6] H. Gysling, M. Tsutsui, *Adv. Organomet. Chem.* 9 (1970) 361.
- [7] G. Wilkinson, J.M. Birmingham, *J. Am. Chem. Soc.* 76 (1954) 6210.
- [8] J.M. Birmingham, G. Wilkinson, *J. Am. Chem. Soc.* 78 (1956) 42.
- [9] E.O. Fischer, H. Fischer, *J. Organomet. Chem.* 6 (1966) 141.
- [10] M. Tsutsui, H.J. Gysling, *J. Am. Chem. Soc.* 91 (1969) 3175.
- [11] S. Manastyrskij, M. Dubeck, *Inorg. Chem.* 3 (1964) 1647.
- [12] R.E. Maginn, S. Manastyrskij, M. Dubeck, *J. Am. Chem. Soc.* 85 (1963) 672.
- [13] S. Manastyrskij, R.E. Maginn, M. Dubeck, *Inorg. Chem.* 2 (1963) 904.
- [14] E.O. Fischer, H. Fischer, *J. Organomet. Chem.* 6 (1966) 181.
- [15] G.W. Watt, E.W. Gillow, *J. Am. Chem. Soc.* 91 (1969) 775.
- [16] A. Streitwieser Jr., U. Müller-Westerhof, *J. Am. Chem. Soc.* 90 (1968) 7364.
- [17] R. Mares, K. Hodgson, A. Streitwieser Jr., *J. Organomet. Chem.* 24 (1970) C68.
- [18] R. Mares, K. Hodgson, A. Streitwieser Jr., *J. Organomet. Chem.* 28 (1971) C24.
- [19] K.O. Hodgson, F. Mares, D.F. Starks, A. Streitwieser Jr., *J. Am. Chem. Soc.* 95 (1973) 8650.
- [20] R.G. Hayes, J.L. Thomas, *J. Am. Chem. Soc.* 91 (1969) 6876.
- [21] S.A. Cotton, F.A. Hart, M.B. Hursthouse, A.J. Welch, *J. Chem. Soc., Chem. Commun.* (1972) 1225.
- [22] W.J. Evans, A.L. Wayda, *Inorg. Chem.* 19 (1980) 2190.
- [23] P.L. Watson, *J. Chem. Soc., Chem. Commun.* (1980) 652.
- [24] T.D. Tilley, R.A. Anderson, B. Spencer, H. Ruben, A. Zalkin, D.H. Templeton, *Inorg. Chem.* 19 (1980) 2999.
- [25] W.J. Evans, S.C. Engerer, P.A. Piliero, A.L. Wayda, in: M. Tsutsui (Ed.), *Fundamental Research in Homogeneous Catalysis*, vol. 3, Plenum, New York, 1979, p. 941.
- [26] W.J. Evans, *Inorg. Chem.* 46 (2007) 3435.
- [27] W.J. Evans, B.L. Davis, *Chem. Rev.* 102 (2002) 2119.
- [28] W.J. Evans, *J. Organomet. Chem.* 647 (2002) 2.
- [29] W.J. Evans, *J. Organomet. Chem.* 652 (2002) 61.
- [30] W.J. Evans, *Coord. Chem. Rev.* 206 (2000) 263.
- [31] L.R. Morss, *Chem. Rev.* 76 (1976) 827.
- [32] W.J. Evans, I. Bloom, W.E. Hunter, J.L. Atwood, *J. Am. Chem. Soc.* 103 (1981) 6507.
- [33] W.J. Evans, J.W. Grate, H.W. Choi, I. Bloom, W.E. Hunter, J.L. Atwood, *J. Am. Chem. Soc.* 107 (1985) 941.
- [34] W.J. Evans, L.A. Hughes, T.P. Hanusa, *J. Am. Chem. Soc.* 106 (1984) 4270.
- [35] W.J. Evans, L.A. Hughes, T.P. Hanusa, *Organometallics* 5 (1986) 1285.
- [36] W.J. Evans, D.K. Drummond, *J. Am. Chem. Soc.* 110 (1988) 2772.
- [37] W.J. Evans, T.A. Ulibarri, J.W. Ziller, *J. Am. Chem. Soc.* 110 (1988) 6877.
- [38] A.J. Freeman, R.E. Watson, *Phys. Rev.* 127 (1962) 2058.
- [39] W.J. Evans, D.S. Lee, *Can. J. Chem.* 83 (2005) 375.
- [40] W.J. Evans, J.W. Grate, L.A. Hughes, H. Zhang, J.L. Atwood, *J. Am. Chem. Soc.* 107 (1985) 3728.
- [41] W.J. Evans, C.A. Seibel, J.W. Ziller, *Inorg. Chem.* 37 (1998) 770.
- [42] W.J. Evans, D.K. Drummond, L.R. Chamberlain, R.J. Doedens, S.G. Bott, H. Zhang, J.L. Atwood, *J. Am. Chem. Soc.* 110 (1988) 4983.
- [43] W.J. Evans, L.A. Hughes, D.K. Drummond, H. Zhang, J.L. Atwood, *J. Am. Chem. Soc.* 108 (1986) 1722.
- [44] W.J. Evans, D.G. Giarikos, C.B. Robledo, V.S. Leong, J.W. Ziller, *Organometallics* 20 (2001) 5648.
- [45] A. Recknagel, D. Stalke, H.W. Roesky, F.T. Edelmann, *Angew. Chem., Int. Ed* 28 (1989) 445.
- [46] H.J. Emeleus, A.G. Sharpe, *Modern Aspects of Inorganic Chemistry*, 4th ed., Wiley, New York, 1973.
- [47] R.D. Shannon, *Acta. Cryst.* A32 (1976) 751.
- [48] W.J. Evans, R. Dominguez, T.P. Hanusa, *Organometallics* 5 (1986) 263.
- [49] D. Alvarez, K.G. Caulton, W.J. Evans, J.W. Ziller, *J. Am. Chem. Soc.* 112 (1990) 5674.
- [50] G. Jeske, H. Lauke, H. Mauermann, H. Schumann, T.J. Marks, *J. Am. Chem. Soc.* 107 (1985) 8111.
- [51] H. Schumann, M. Glanz, H. Hemling, F.E. Hahn, Z. Anorg. Allg. Chem. 621 (1995) 341.
- [52] L.B. Asprey, B.B. Cunningham, *Prog. Inorg. Chem.* 2 (1960) 267.
- [53] A.N. Kamenskaya, K. Bukietynska, N.B. Mikheev, V.I. Spitsyn, B. Jezowska-Trzebiatowska, *Zhurnal Neorganicheskoi Khimii* 24 (1979) 1139.
- [54] A.N. Kamenskaya, N.B. Mikheev, N. Kholmogorova, *Zhurnal Neorganicheskoi Khimii* 28 (1983) 2499.
- [55] A.N. Kamenskaya, *Zhurnal Neorganicheskoi Khimii* 29 (1984) 439.
- [56] M.N. Bochkarev, A.A. Fagin, *Chem. Eur. J.* 5 (1999) 2990.
- [57] M.N. Bochkarev, I.L. Fedushkin, A.A. Fagin, T.W. Petrovskaya, J.W. Ziller, R.N.R. Broomhall-Dillard, W.J. Evans, *Angew. Chem., Int. Ed* 36 (1997) 133.
- [58] M.N. Bochkarev, I.L. Fedushkin, A.A. Fagin, H. Schumann, J. Demtschuk, *Chem. Comm.* (1997) 1783.
- [59] M.N. Bochkarev, I.L. Fedushkin, V.I. Nevodchikov, V.K. Cherkasov, H. Schumann, H. Hemling, R. Weimann, *J. Organomet. Chem.* 524 (1996) 125.
- [60] I.L. Fedushkin, F. Girgsdies, H. Schumann, M.N. Bochkarev, *Eur. J. Inorg. Chem.* (2001) 2405.
- [61] W.J. Evans, R.N.R. Broomhall-Dillard, J.W. Ziller, *Polyhedron* 17 (1998) 3361.
- [62] W.J. Evans, N.T. Allen, *J. Am. Chem. Soc.* 122 (2000) 2118.
- [63] W.J. Evans, N.T. Allen, J.W. Ziller, *J. Am. Chem. Soc.* 123 (2001) 7927.
- [64] J.D. Corbett, *J. Alloy Compds.* 418 (2006) 1 (11th Spedding Award address).
- [65] G. Meyer, *Chem. Rev.* 88 (1988) 93.
- [66] W.J. Evans, N.T. Allen, J.W. Ziller, *J. Am. Chem. Soc.* 122 (2000) 11749.
- [67] W.J. Evans, N.T. Allen, J.W. Ziller, *Angew. Chem., Int. Ed* 41 (2002) 359.
- [68] P.W. Rabideau, Z. Marcinow, *Org. React.* 41 (1992) 1.
- [69] M.N. Bochkarev, I.L. Fedushkin, S. Dechert, A.A. Fagin, H. Schumann, *Angew. Chem., Int. Ed* 40 (2001) 3176.
- [70] W.J. Evans, S.L. Gonzales, J.W. Ziller, *J. Am. Chem. Soc.* 116 (1994) 2600.
- [71] W.J. Evans, S.L. Gonzales, J.W. Ziller, *J. Am. Chem. Soc.* 113 (1991) 7423.
- [72] D. White, B.C. Taverner, P.G.L. Leach, N.J. Coville, *J. Comput. Chem.* 14 (1993) 1042.
- [73] L. Stahl, R.D. Ernst, *J. Am. Chem. Soc.* 109 (1987) 5673.
- [74] T.V. Lubben, P.T. Wolczanski, *J. Am. Chem. Soc.* 109 (1987) 424.
- [75] W.J. Evans, S.E. Foster, *J. Organomet. Chem.* 433 (1992) 79.
- [76] W.J. Evans, S.A. Kozimor, J.W. Ziller, *Inorg. Chem.* 44 (2005) 7960.
- [77] W.J. Evans, K.J. Forrestal, J.W. Ziller, *J. Am. Chem. Soc.* 120 (1998) 9273.
- [78] W.J. Evans, K.J. Forrestal, J.W. Ziller, *J. Am. Chem. Soc.* 117 (1995) 12635.
- [79] W.J. Evans, G.W. Nyce, J.W. Ziller, R.J. Doedens, *Inorg. Chem.* 33 (1994) 2719.
- [80] W.J. Evans, K.J. Forrestal, J.T. Leman, J.W. Ziller, *Organometallics* 15 (1996) 527.
- [81] W.J. Evans, J.M. Perotti, B.L. Davis, S.A. Kozimor, G.W. Nyce, C.H. Fujimoto, R.D. Clark, M.A. Johnston, J.W. Ziller, *Organometallics* 24 (2005) 3916.
- [82] W.J. Evans, I. Bloom, W.E. Hunter, J.L. Atwood, *J. Am. Chem. Soc.* 105 (1983) 1401.
- [83] W.J. Evans, C.A. Seibel, J.W. Ziller, *J. Am. Chem. Soc.* 120 (1998) 6745.
- [84] W.J. Evans, K.J. Forrestal, J.W. Ziller, *Angew. Chem., Int. Ed* 36 (1997) 774.
- [85] W.J. Evans, G.W. Nyce, R.D. Clark, R.J. Doedens, J.W. Ziller, *Angew. Chem., Int. Ed* 38 (1999) 1801.
- [86] W.J. Evans, B.L. Davis, J.W. Ziller, *Inorg. Chem.* 40 (2001) 6341.
- [87] W.J. Evans, B.L. Davis, T.M. Champagne, J.W. Ziller, *Proc. Nat. Acad. Sci.* 103 (2006) 12678.
- [88] W.J. Evans, T.M. Champagne, J.W. Ziller, *J. Am. Chem. Soc.* 128 (2006) 14270.
- [89] W.J. Evans, S.A. Kozimor, *Coord. Chem. Rev.* 250 (2006) 911.
- [90] W.J. Evans, G.W. Nyce, J.W. Ziller, *Organometallics* 21 (2002) 1050.
- [91] W.J. Evans, G.W. Nyce, J.W. Ziller, *Angew. Chem. Int. Ed* 39 (2000) 240.
- [92] W.J. Evans, G.W. Nyce, M.A. Johnston, J.W. Ziller, *J. Am. Chem. Soc.* 122 (2000) 12019.
- [93] P.J. Fagan, J.M. Manriquez, T.J. Marks, C.S. Day, S. Vollmer, V.W. Day, *Organometallics* 1 (1982) 170.
- [94] W.J. Evans, S.A. Kozimor, J.W. Ziller, N. Kaltsayannis, *J. Am. Chem. Soc.* 126 (2004) 14533.
- [95] P.L. Diaconescu, P.L. Arnold, T.A. Baker, D.J. Mindiola, C.C. Cummins, *J. Am. Chem. Soc.* 122 (2000) 6108.
- [96] W.J. Evans, S.A. Kozimor, J.W. Ziller, *Chem. Comm.* (2005) 4681.
- [97] D.S.J. Arney, C.J. Burns, D.C. Smith, *J. Am. Chem. Soc.* 114 (1992) 10068.
- [98] W.J. Evans, G. Zucchi, J.W. Ziller, *J. Am. Chem. Soc.* 125 (2003) 10.
- [99] F. Jaroschik, F. Nief, X.-F. Le Goff, L. Ricard, *Organometallics* 26 (2007) 3552.
- [100] J. Cheng, J. Takats, M.J. Ferguson, R. McDonald, *J. Am. Chem. Soc.* 130 (2008) 1544.
- [101] W.J. Evans, D.S. Lee, J.W. Ziller, *J. Am. Chem. Soc.* 126 (2004) 454.
- [102] W.J. Evans, D.S. Lee, D.B. Rego, J.M. Perotti, S.A. Kozimor, E.K. Moore, J.W. Ziller, *J. Am. Chem. Soc.* 126 (2004) 14574.
- [103] D.C. Bradley, J.S. Ghotra, F.A. Hart, *J. Chem. Soc. Dalton Trans.* (1973) 1021.
- [104] M.C. Cassani, Y.K. Gun'ko, P.B. Hitchcock, M.F. Lappert, *Chem. Commun.* (1996) 1987.
- [105] M.C. Cassani, D.J. Duncalf, M.F. Lappert, *J. Am. Chem. Soc.* 120 (1998) 12958.
- [106] M.C. Cassani, Y.K. Gun'ko, P.B. Hitchcock, M.F. Lappert, F. Laschi, *Organometallics* 18 (1999) 5539.
- [107] Y.K. Gun'ko, P.B. Hitchcock, M.F. Lappert, *Organometallics* 19 (2000) 2832.

- [108] J.C. Peters, J.F. Cherry, J.C. Thomas, L. Baraldo, D.J. Mindiola, W.M. Davis, C.C. Cummins, *J. Am. Chem. Soc.* 121 (1999) 10053.
- [109] M.B. O'Donoghue, W.M. Davis, R.R. Schrock, W.M. Reiff, *Inorg. Chem.* 38 (1999) 243.
- [110] W.J. Evans, S.A. Kozimor, J.W. Ziller, *J. Am. Chem. Soc.* 125 (2003) 14264.
- [111] W.J. Evans, D.S. Lee, C. Lie, J.W. Ziller, *Angew. Chem., Int. Ed* 43 (2004) 5517.
- [112] W.J. Evans, D.S. Lee, M.A. Johnston, J.W. Ziller, *Organometallics* 24 (2005) 6393.
- [113] W.J. Evans, D.B. Rego, J.W. Ziller, *Inorg. Chem.* 45 (2006) 10790.
- [114] W.J. Evans, D.S. Lee, J.W. Ziller, N. Kaltsoyannis, *J. Am. Chem. Soc.* 128 (2006) 14176.
- [115] W.J. Evans, S.E. Lorenz, J.W. Ziller, *Inorg. Chem.* 48 (2009) 2001.
- [116] P.K. Pal, S. Chowdhury, M.G.B. Drew, D. Datta, *New J. Chem.* 26 (2002) 367.
- [117] M. Ephritikhine, *Chem. Rev.* 97 (1997) 2193.
- [118] T.J. Marks, P.J. Fagan, J.M. Manriquez, E.A. Maatta, A.M. Seyam, *J. Am. Chem. Soc.* 103 (1981) 6650.
- [119] W.J. Evans, K.A. Miller, S.A. Kozimor, J.W. Ziller, A.G. DiPasquale, A.L. Rheingold, *Organometallics* 26 (2007) 3568.
- [120] W.J. Evans, B.M. Schmiede, S.E. Lorenz, K.A. Miller, T.M. Champagne, J.W. Ziller, A.G. DiPasquale, A.L. Rheingold, *J. Am. Chem. Soc.* 130 (2008) 8555.

Structural chemistry and magnetic properties of $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$): Four new rare-earth metal intermetallic compounds with germanium zig-zag chains and tin square-nets

Paul H. Tobash^a, Svilen Bobev^{a,*}, Filip Ronning^b, Joe D. Thompson^b, John L. Sarrao^b

^a Department of Chemistry, University of Delaware, Newark, Delaware 19716, United States

^b Materials Physics and Application Division (MPA-10), Los Alamos National Laboratory, Los Alamos, New Mexico 87545, United States

ARTICLE INFO

Article history:

Received 16 May 2008

Received in revised form 6 October 2008

Accepted 14 October 2008

Available online 2 December 2008

Keywords:

Intermetallics

Chemical synthesis

Crystal structure

X-ray diffraction

Magnetic measurements

ABSTRACT

Four new rare-earth metal tin germanides with general formulae $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$; $x \approx 0.25-0.3$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$; $x \approx 0.2-0.25$) have been synthesized from the corresponding elements by high temperature reactions using Sn flux. Their structures have been established from single-crystal and powder X-ray crystallography: orthorhombic space group $Cmcm$ (No. 63) with cell parameters $a = 4.1057(6) \text{ \AA}$, $b = 35.992(5) \text{ \AA}$, $c = 4.2534(6) \text{ \AA}$ for $Nd_2[Sn_xGe_{1-x}]_5$; $a = 4.0707(8) \text{ \AA}$, $b = 35.550(7) \text{ \AA}$, $c = 4.2095(8) \text{ \AA}$ for $Sm_2[Sn_xGe_{1-x}]_5$; $a = 4.2248(11) \text{ \AA}$, $b = 30.451(8) \text{ \AA}$, $c = 4.0013(11) \text{ \AA}$ for $Gd[Sn_xGe_{1-x}]_2$, and $a = 4.1936(13) \text{ \AA}$, $b = 30.230(9) \text{ \AA}$, $c = 3.9793(12) \text{ \AA}$ for $Tb[Sn_xGe_{1-x}]_2$, respectively. The structures of the two families can be described as being stacking variants of the $ZrSi_2$ and $DyGe_3$ types, respectively. They represent another example of site preferences between two group 14 elements, where the lighter Ge atoms preferentially form zig-zag chains while the square sheets (or double square sheets) are made up of Sn atoms, respectively. Magnetic susceptibility measurements show that all of the compounds order antiferromagnetically at low temperatures and their respective ordering temperatures are further corroborated by specific heat measurements.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Recently, we reported on a series of nearly equiatomic rare-earth metal tin germanides with a general formula $RESn_{1+x}Ge_{1-x}$ ($RE = Y, Gd-Tm$) [1]. In these nearly stoichiometric compounds ($x \approx 0.15$), two group 14 elements, Ge and Sn, preferentially occupy different crystallographic sites, which is a rare demonstration of site preferences between elements from the same group [2–5]. Our initial interest in this system was motivated by the success in growing single-crystals of the ternary phases RE_2InGe_2 ($RE = Sm, Gd-Ho, Yb$) from In flux [6], and from the speculation that intriguing physics could result if the isostructural stannides (electron-richer) could be synthesized. This line of thinking originated from the fact that computational studies on a series of compounds with the same structure type in which the RE_2InGe_2 compounds crystallize (U_3Si_2 or its ternary version Mo_2FeB_2 – space group $P4/mbm$, Pearson's symbol $tP10$) [7], suggest that the atom with the square planar coordination, In if the $[InGe_2]$ layers are considered, has an oxidation state of 0 [8].

Throughout our systematic investigations of the phase space in the $RE-Sn-Ge$ systems ($RE = Ce-Tm$), besides the $RESn_{1+x}Ge_{1-x}$ compounds, we came across four new ternary phases, which are the subject of this study. Their chemical formulae are $RE_2[Sn_xGe_{1-x}]_5$ ($x \approx 0.25-0.3$) for $RE = Nd$ or Sm , and $RE[Sn_xGe_{1-x}]_2$ ($x \approx 0.2-0.25$) for $RE = Gd$ and Tb , respectively. The structures of these new intermetallics are abbreviated hereafter as **I** and **II**, respectively, and exemplify the same site preferences mentioned above for the $RESn_{1+x}Ge_{1-x}$ ($RE = Y, Gd-Tm$) compounds [1], despite that they are subtly different. Herein, we discuss the results from the single-crystal X-ray diffraction work and reconcile them with periodic trends in the lanthanide family. Reported as well are the temperature dependent magnetization and specific heat measurements for all four compounds, which indicate antiferromagnetic ordering at low temperatures.

2. Experimental

2.1. Synthesis

Handling of the starting materials, pure elements from Alfa (purity > 99.9% metal basis), was done inside an argon-filled glove-box or under vacuum. Stoichiometric mixtures of the elements, used as received, were loaded in alumina crucibles, which were encapsulated in fused silica ampoules. The ampoules were evacuated (ca. 10^{-3} Torr) and flame-sealed. The reaction conditions were identical to those used

* Corresponding author. Tel.: +302 831 8720 fax: +302 831 6335.

E-mail address: bobev@udel.edu (S. Bobev).

for the synthesis of the recently reported $RESn_{1+x}Ge_{1-x}$ ($RE = Y, Gd-Tm$) [1]. The only difference is that in the previous studies, the ratio $RE:Ge$ was 1:1, thereby yielding nearly equiatomic compounds. In the present case, the reactions were loaded with 50% more Ge, yielding **I** and **II**, respectively. Further and more elaborate details can be found elsewhere [1].

The crystals isolated from the reactions appeared like platelets with silver-metallic luster. They are air- and moisture-stable over periods of time greater than 12 months.

2.2. X-ray diffraction studies

X-ray powder diffraction patterns were taken at room temperature on a Rigaku Miniflex powder diffractometer using filtered $Cu\ K\alpha$ radiation. The typical scans were in $\theta - \theta$ mode ($2\theta_{max} = 80^\circ$) with a step-size of 0.05° and 10 s/step counting time. The collected powder patterns were used for phase identification only. This was done using the JADE 6.5 software package [9]. The intensities and the positions of the experimental and the calculated from the crystal structures peaks were in excellent agreement.

X-ray single-crystal data collections were carried out on a Bruker SMART CCD diffractometer at 120 K. This was necessary since the crystals were mounted on glass fibers using Paratone-N oil, which freezes at low temperature and keeps the crystals from moving. Full spheres of intensity data for multiple crystals from all compounds were collected using monochromated $Mo\ K\alpha$ radiation. The data acquisition strategy involved batch runs at different ω and ϕ angles, which were handled using the SMART software [10]. SAINTplus [11] was used for data integration and global unit cell refinements taking into account all reflections. Semi-empirical absorption correction based on equivalents was applied with SADABS [12]. The systematic absence of reflections with indexes hkl for $h+k \neq 2n$; confirmed the C-centering. The presence of glide symmetry was also evident based on the observed reflection conditions, narrowing the possible choices of a space group to $Ama2$, $Cmc2_1$ and $Cmcm$ —among them, the latter was favored according to the intensity statistics. The structures were solved in $Cmcm$ and refined by full-matrix least-squares methods on F^2 using the SHELX package [13]. Further details of the data collection and structural refinement parameters are summarized in Table 1. In the last refinement cycles the atomic coordinates were standardized using TIDY [14]. Final positional and equivalent displacement parameters are given in Table 2 and selected bond distances are provided in Table 3. The crystallographic information files (CIF) have also been deposited with Fachinformationszentrum Karlsruhe de [76344 Eggenstein, Leopoldshafen, Germany; fax: +49 7247 808 666 email: crysdata@fiz.karlsruhe.de; depositary numbers CSD-419481 ($Nd_2[Sn_xGe_{1-x}]_5$), CSD-419482 ($Sm_2[Sn_xGe_{1-x}]_5$), CSD-419483 ($Gd[Sn_xGe_{1-x}]_2$), and CSD-419484 ($Tb[Sn_xGe_{1-x}]_2$).

We also note here that once the basic atomic arrangement in **II** was established from single-crystal work, it was found that it is similar to that in $DyGe_{1.85}$ [15] and $ErGe_{1.83}$ [16], close relatives of the common $ZrSi_2$ type [7]. However, the so-called $DyGe_{1.85}$ type is reported with the non-centrosymmetric $Cmc2_1$ space group (No. 36). It has the same reflection conditions as the centrosymmetric $Cmcm$ (No. 63), making the differentiation between them virtually impossible. The same ambiguity was encountered with **I** as well. Therefore, trial-and-error solutions and refinements were carried out in both groups, but the exchange of the mirror plane with a 2_1 -screw axis and the corresponding loss of inversion symmetry did not

Table 2
Atomic coordinates, isotropic displacement parameters (U_{eq}) for $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, AtomTb$).

Atom	Site	x	y	z	U_{eq} [$\text{\AA}^2$]
$Nd_2[Sn_xGe_{1-x}]_5$					
Nd1	4c	0	0.44946(1)	1/4	0.0052(1)
Nd2	4c	0	0.85457(1)	1/4	0.0047(1)
Sn1/Ge1 ^a	4c	0	0.21330(2)	1/4	0.0125(2)
Sn2/Ge2 ^a	4c	0	0.28818(2)	1/4	0.0104(2)
Ge3	4c	0	0.07812(2)	1/4	0.0080(2)
Ge4	4c	0	0.62143(2)	1/4	0.0054(2)
Ge5A ^b	8f	0	0.00627(1)	0.074(1)	0.0050(5)
Ge5B ^b	8f	0	0.01249(6)	0.193(1)	0.0050(5)
$Sm_2[Sn_xGe_{1-x}]_5$					
Sm1	4c	0	0.44926(2)	1/4	0.0045(2)
Sm2	4c	0	0.85468(2)	1/4	0.0040(2)
Sn1/Ge1 ^a	4c	0	0.21311(3)	1/4	0.0120(4)
Sn2/Ge2 ^a	4c	0	0.28844(4)	1/4	0.0113(5)
Ge3	4c	0	0.07785(5)	1/4	0.0073(4)
Ge4	4c	0	0.62207(4)	1/4	0.0050(3)
Ge5A ^b	8f	0	0.0058(2)	0.067(2)	0.003(1)
Ge5B ^b	8f	0	0.0116(1)	0.189(2)	0.003(1)
$Gd[Sn_xGe_{1-x}]_2$					
Gd1	4c	0	0.44111(3)	1/4	0.0073(2)
Gd2	4c	0	0.66734(3)	1/4	0.0064(2)
Sn1/Ge1 ^a	4c	0	0.24758(4)	1/4	0.0073(4)
Ge2	4c	0	0.09014(6)	1/4	0.0094(4)
Ge3	4c	0	0.85655(6)	1/4	0.0077(4)
Ge4A ^b	8f	0	0.0070(2)	0.097(2)	0.009(1)
Ge4B ^b	4c	0	0.0121(2)	1/4	0.009(1)
$Tb[Sn_xGe_{1-x}]_2$					
Tb1	4c	0	0.44093(3)	1/4	0.0089(2)
Tb2	4c	0	0.66747(3)	1/4	0.0079(2)
Sn1/Ge1 ^a	4c	0	0.24783(5)	1/4	0.0096(4)
Ge2	4c	0	0.09015(7)	1/4	0.0109(4)
Ge3	4c	0	0.85583(7)	1/4	0.0094(4)
Ge4A ^b	8f	0	0.0067(2)	0.095(2)	0.009(1)
Ge4B ^b	4c	0	0.0117(2)	1/4	0.009(1)

^a Refined as statistical mixtures of Sn and Ge.
^b Disordered sites, partially occupied.

yield statistically significant improvements. The refinements showed almost no difference in the refined coordinates and both converged to very similar residuals. Because the disorder we describe in greater detail further on is persistent in both $Cmc2_1$ and $Cmcm$, and since we find no compelling geometric arguments against the inversion symmetry, we report both **I** and **II** in the higher symmetry space group $Cmcm$.

Table 1
Selected single crystal collection and refinement parameters for $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$).

	I		II	
Empirical formula	Nd ₂ Sn _{1.24(1)} Ge _{3.55}	Sm ₂ Sn _{1.24(1)} Ge _{3.55}	GdSn _{0.41(1)} Ge _{1.47}	TbSn _{0.40(1)} Ge _{1.47}
Formula weight	693.53	700.82	311.85	312.39
Space group, Z	Cmcm (No. 63), Z = 4		Cmcm (No. 63), Z = 8	
Radiation, λ	Mo Kα, 0.71073 Å			
Temperature	120 K			
Unit cell parameters				
a (Å)	4.1057(6)	4.0707(8)	4.2248(11)	4.1936(13)
b (Å)	35.992(5)	35.550(7)	30.451(8)	30.230(9)
c (Å)	4.2534(6)	4.2095(8)	4.0013(11)	3.9793(12)
V (Å ³)	628.5(2)	609.2(2)	514.8(2)	504.5(3)
Crystal size	68 μm × 65 μm × 55 μm	54 μm × 50 μm × 42 μm	43 μm × 42 μm × 38 μm	41 μm × 32 μm × 31 μm
ρ _{calc} (g/cm ³)	7.329	7.642	8.048	8.226
μ (cm ^{−1})	376.7	409.3	460.1	485.9
Data/parameter	505/35	456/35	412/28	408/28
Absorption correction method	Semi-empirical, based on equivalents			
Final R values ^a (I > 2σ _I)	R1 = 0.0196 wR2 = 0.0423	R1 = 0.0208 wR2 = 0.0461	R1 = 0.0311 wR2 = 0.0678	R1 = 0.0322 wR2 = 0.0647
Largest peak/hole	0.89/−1.20 e [−] /Å ³	1.45/−1.07 e [−] /Å ³	1.98/−1.67 e [−] /Å ³	1.90/−2.11 e [−] /Å ³

^a $R1 = \sum ||F_o| - |F_c|| / \sum |F_o|$; $wR2 = [\sum (w(F_o^2 - F_c^2))^2 / \sum (w(F_o^2))^2]^{1/2}$, where $w = 1/[\sigma^2(F_o^2) + (A \cdot P)2 + B \cdot P]$, $P = (F_o^2 + 2F_c^2)/3$; A and B: weight coefficients.

Table 3

Selected distances (Å) in $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$). The distances within the disordered chains are not included.

$Nd_2[Sn_xGe_{1-x}]_5$			$Sm_2[Sn_xGe_{1-x}]_5$		
Nd1	4 × Ge3	3.118(4)	Sm1	4 × Ge3	3.083(5)
	2 × Ge4	3.322(8)		2 × Ge4	3.297(9)
	2 × Nd2	3.985(2)		2 × Sm2	3.931(2)
	4 × Ge4	3.079(4)		4 × Ge4	3.042(5)
	2 × Sn2	3.150(7)		2 × Sn2	3.112(9)
Nd2	2 × Ge3	3.224(8)	Sm2	2 × Ge3	3.190(2)
	2 × Sn1	3.239(6)		2 × Sn1	3.201(8)
	2 × Nd1	3.985(2)		2 × Sm1	3.931(2)
	Sn2	2.695(3)		Sn2	2.676(2)
	4 × Sn2	2.956(3)		4 × Sn2	2.929(4)
Sn1 ^a	2 × Nd2	3.239(6)	Sn2 ^a	2 × Sm2	3.201(8)
	Sn1	2.695(3)		Sn1	2.676(2)
	4 × Sn1	2.956(3)		4 × Sn1	2.929(4)
Sn2 ^a	2 × Nd2	3.150(7)	Ge3	2 × Sm2	3.112(9)
	4 × Sn1	2.578(8)		2 × Ge4	2.572(2)
	4 × Nd1	3.118(4)		4 × Sm1	3.083(5)
Ge3	2 × Nd2	3.224(8)	Ge4	2 × Sm2	3.190(2)
	2 × Ge3	2.578(8)		2 × Ge3	2.572(2)
	4 × Nd2	3.079(4)		4 × Sm2	3.042(5)
Ge4	2 × Nd1	3.322(8)		2 × Sm1	3.297(9)
$Gd[Sn_xGe_{1-x}]_2$			$Tb[Sn_xGe_{1-x}]_2$		
Gd1	4 × Ge2	3.061(8)	Tb1	4 × Ge2	3.039(9)
	2 × Ge3	3.331(2)		2 × Ge3	3.319(2)
	2 × Gd2	3.861(2)		2 × Tb2	3.834(2)
Gd2	4 × Ge3	2.999(7)	Tb2	4 × Ge3	2.975(8)
	2 × Ge2	3.161(2)		2 × Ge2	3.140(2)
	2 × Sn1	3.230(2)		2 × Sn1	3.209(2)
	2 × Sn1	3.273(2)		2 × Sn1	3.243(2)
	2 × Gd1	3.861(2)		2 × Tb1	3.834(2)
Sn1 ^a	4 × Sn1	2.913(6)	Sn1 ^a	4 × Sn1	2.894(6)
	2 × Gd2	3.230(2)		2 × Tb2	3.209(2)
	2 × Gd2	3.273(2)		2 × Tb2	3.243(2)
Ge2	2 × Ge3	2.576(2)	Ge2	2 × Ge3	2.574(2)
	4 × Gd1	3.061(8)		4 × Tb1	3.039(9)
	2 × Gd2	3.161(2)		2 × Tb2	3.140(2)
Ge3	2 × Ge2	2.576(2)	Ge3	2 × Ge2	2.574(2)
	4 × Gd2	2.999(7)		4 × Tb2	2.975(8)
	2 × Gd1	3.331(2)		2 × Tb1	3.319(2)

^a Refined as statistical mixtures of Sn and Ge.

2.3. Magnetic and specific heat measurements

Field-cooled dc magnetization (M) measurements were carried out using a Quantum Design MPMS SQUID magnetometer. The measurements were taken on single-crystalline samples in the temperature range from 2 to 350 K and in an applied field (H) of 1000 Oe. For each sample, the susceptibility was measured with crystals aligned in parallel direction with the external field and the raw magnetization data were corrected for the holder contribution and subsequently converted to molar susceptibility ($\chi_m = M/H$). The specific heat data were measured in a Quantum Design PPMS using the thermal relaxation method within the temperature range of 2–300 K.

3. Results

3.1. Synthesis

Attempts to extend both the $RE_2[Sn_xGe_{1-x}]_5$ and the $RE[Sn_xGe_{1-x}]_2$ series to the early or late rare-earth metals were not successful. In the case of the early rare-earth metals, the cubic $RESn_3$ ($RE = La\text{--}Pr$) [7] were solely formed in the reactions; for the late rare-earth metals, the above-discussed $RESn_{1+x}Ge_{1-x}$ ($RE = Dy\text{--}Tm$) compounds were formed [1]. The same is also true even for Ge-rich reactions loaded with a nominal composition $RE:Ge = 1:2$, and/or decreasing the amount of Sn flux.

After the structures were established and the small admixture of Ge and Sn was detected, additional syntheses were undertaken in order to explore the homogeneity range. Comparison of the shifts of the lines in the corresponding powder diffraction patterns immediately confirmed the dependence of the unit cell volume on the

reaction conditions. Refinements on single-crystal data provided additional evidence to suggest that there was indeed a small, but not negligible stoichiometry breadth [17]. This is the case for the structurally related $RESn_{1+x}Ge_{1-x}$ ($RE = Y, Gd\text{--}Tm$) [1], where the homogeneity range is also narrow. Nevertheless, to ascertain consistency, the very same flux-grown crystals, which were used for all physical property measurements were also used for the single-crystal X-ray data collections.

3.2. Crystal structure

Schematic representations of the structures of **I** and **II** are shown in Fig. 1. To begin our brief account, it is easy and most fitting to discuss the structures considering only the polyanionic sub-network. From this point of view, **I** can be envisioned as an alternate stacking arrangement of germanium zig-zag chains, ${}^1_\infty[Ge_2]$, and tin double-square sheets, ${}^2_\infty[Sn_2]$, where every second ${}^2_\infty[Sn_2]$ slab is replaced by a disordered ${}^1_\infty[Ge_2]$ chain. An important detail that needs to be specifically mentioned is the fact the disordered chains and the regular zig-zag chains are orthogonal (Fig. 1). This arrangement is reminiscent to that of the $\alpha\text{-ThSi}_2$ type [7] and we can also describe the structure as being an intergrowth of $\alpha\text{-ThSi}_2$ -like and $DyGe_3$ -like fragments (i.e., $REGe_2 + RESn_3 = RE_2[Sn_xGe_{1-x}]_5$). Similarly, **II** can be described as an alternate stacking arrangement of germanium zig-zag chains, ${}^1_\infty[Ge_2]$, and tin square sheets, ${}^2_\infty[Sn_2]$, where every second ${}^2_\infty[Sn_2]$ slab is replaced by a disordered zig-

Fig. 1. The C-centered orthorhombic crystal structures of the $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) (**I**) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$) (**II**) compounds, viewed perpendicular to the direction of the layer-stacking. Unit cells and axes directions are outlined in each case. The rare-earth metal atoms are shown as empty circles, Ge atoms are depicted as black spheres, and the Sn atoms are drawn as grey spheres. The disordered Ge-chains are shown as white spheres.

Fig. 2. Contour diagram, calculated from the difference Fourier synthesis, showing the electron density above $5.0\text{ e}^-/\text{\AA}^3$ around the disordered Ge sites in $\text{Sm}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$. Similar problems persist for $\text{Nd}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$, as well as for $\text{Gd}[\text{Sn}_x\text{Ge}_{1-x}]_2$ and $\text{Tb}[\text{Sn}_x\text{Ge}_{1-x}]_2$.

zig chain. An important difference with **I** is that the disordered chains here run parallel to the neighboring $\frac{1}{\infty}[\text{Ge}_2]$ groups. Thus, the $\text{RE}[\text{Sn}_x\text{Ge}_{1-x}]_2$ structure can also be described as a superstructure of the ZrSi_2 type and is analogous to $\text{DyGe}_{1.85}$ [15] and $\text{ErGe}_{1.83}$ [16].

The Ge–Ge distances in the $\frac{1}{\infty}[\text{Ge}_2]$ zig-zag chains in both families measure ca. $2.57\text{ \AA}$ (Table 3) with the “corresponding” Ge–Ge–Ge angles on the order of 105° in **I** and 101° in **II**. The distances are consistent with the Ge–Ge contacts found in many other germanides: DyGe_3 [18], RE_3Ge_5 [19], RE_3Ge_4 [20], Yb_4MgGe_4 [21], EuGe_2 [22], to name a few. Turning attention to the square nets in both compounds which are composed of Sn (along with a small admixture of Ge as evidenced from the refinements), the distances measure between 2.89 and $2.95(1)\text{ \AA}$. These are indeed longer than those found in α -Sn, but shorter than those in the metallic β -Sn allotrope [7]. They are also consistent with distances found in the square nets in $\text{RESn}_{1+x}\text{Ge}_{1-x}$ [1]. For comparison, Sn–Sn distances in the Sn sheets reported for the series of binary $\text{RE}_n\text{Sn}_{3n-2}$ compounds measure from 3.18 to $3.26\text{ \AA}$ [23]. The interlayer distances in the double square nets in **I** measure $2.69(1)\text{ \AA}$. Since Ge and Sn are mixed on the two sites that form this slab, it is evident why these are longer than those found in the isomorphous DyGe_3 , $d_{\text{Ge–Ge}} = 2.44(2)\text{ \AA}$ [18].

The last point of relevance to this discussion concerns the disordered zig-zag chains in both structures. The disorder there is extensive and as evidenced by the difference Fourier map shown in Fig. 2, is difficult to model. These chains therefore had to be modeled by two positions (Table 2), which are with fractional occupancies. Such disorder and crystallographic approach is not without a precedent, and is reported for $\text{ErGe}_{1.83}$ [16], $\text{LaSn}_{0.75}\text{Sb}_2$ [24], and $\text{Er}_8\text{Si}_{17}\text{B}_3$ [25], among others.

3.3. Magnetic susceptibility

Plots of the magnetic susceptibility as a function of the temperature for all four $\text{RE}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$ ($\text{RE} = \text{Nd}, \text{Sm}$) and $\text{RE}[\text{Sn}_x\text{Ge}_{1-x}]_2$ ($\text{RE} = \text{Gd}, \text{Tb}$) are shown in Fig. 3. Presented herein are the data gathered when the plate-like single-crystals used in the measurements were mounted parallel to the direction of the external field, although there were no discernable differences in the measurements in orthogonal direction. As seen from the figure, excluding $\text{Sm}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$, the remaining three compounds exhibit the typical Curie–Weiss paramagnetic behavior in wide temperature intervals. The cusp-like features visible in the $\chi(T)$ data are indicative of the onsets of long-range antiferromagnetic order. The corresponding Néel temperatures (T_N) were determined by taking

the midpoint of the jump in $d\chi/dT$: $T_N = 5\text{ K}$ for $\text{Nd}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$, $T_N = 13\text{ K}$ for $\text{Sm}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$, $T_N = 25\text{ K}$ for $\text{Gd}[\text{Sn}_x\text{Ge}_{1-x}]_2$, and $T_N = 26\text{ K}$ for $\text{Tb}[\text{Sn}_x\text{Ge}_{1-x}]_2$, respectively. Below the Néel temperature, there is an upturn the $\chi(T)$ data for $\text{Gd}[\text{Sn}_x\text{Ge}_{1-x}]_2$, which likely relates to the unusual C_p vs. T dependence discussed below.

The insets in Fig. 3 show the dependence of the inverse susceptibility with the temperature, which is linear in all three cases. Fitting $\chi^{-1}(T)$ yields effective moments (normalized per one RE atom) of $3.48\mu_B$ for the Nd-compound, $7.99\mu_B$ for the Gd-compound and $9.65\mu_B$ for the Tb-compound, respectively. These values are in very good agreement with the values calculated for free-ion Nd^{3+} , Gd^{3+} and Tb^{3+} according to the Hund's rules [26]. The negative Weiss temperatures on the order of -30 to -80 K corroborate the strong antiferromagnetic coupling in these compounds. In the case of Sm, the small effective moment along with the significant van Vleck paramagnetic contributions to the magnetization, required a non-linear fitting of the $\chi(T)$ data with the modified Curie–Weiss equation $\chi(T) = \chi_0 + C/(T - \theta_p)$ resulting in a small effective moment of $0.63\mu_B$ for Sm^{3+} and $\theta_p = -8\text{ K}$. The temperature independent contributions were estimated to be $\chi_0 = 8.8 \times 10^{-4}\text{ emu/mol}$.

3.4. Specific heat

The specific heat data are presented in Fig. 3 in the representation $C_p(T)/T$ vs. T . This is done so that a side-by-side comparison with the magnetic susceptibility can be made. In all four cases, well-defined λ -shaped peaks are seen in the plots—the temperature of the maxima correlate with the T_N 's deduced from the susceptibility measurements and are characteristic of magnetically ordered systems [27]. In the case of Sm, a second anomaly near 8 K evident in the $C_p(T)$ data is also observed (Fig. 3). Its origin is unknown and could be attributed to splitting of the states for the Sm^{3+} ion, which are very close in energy, due to crystal field effects. We also note another peculiarity concerning the specific heat data for $\text{Gd}[\text{Sn}_x\text{Ge}_{1-x}]_2$ (Fig. 3). Aside from the well-defined peak at 25 K , the specific heat data also shows a broad anomaly below this temperature. Similar plateau in the $C_p(T)/T$ vs. T data below the Néel temperature is also seen for $\text{GdSn}_{1+x}\text{Ge}_{1-x}$ [1], as well as for other Gd intermetallics, such as Gd_2CdPd_2 [28] and GdNi_2Ge_2 [29]. The nature of this effect has been suggested to originate from the coexistence of a number of commensurately and incommensurately antiferromagnetic or equal moment structures [29,30]. Currently, further studies, looking at field dependent specific heat measurements are underway.

4. Discussion

The structures of **I** and **II** are closely “rooted” from one ubiquitous structure type, CrB, which exemplifies the $\frac{1}{\infty}[\text{Ge}_2]$ zig-zag chains seen here and in other REGe monogermanides [7]. As we schematically illustrate in Fig. 4, many more structures, including those of another common type, ZrSi_2 [7], can be “designed” by a simple “cut-and-paste” approach, where orthogonal chains or square sheets are inserted between the depicted zig-zag fragments. Starting with a CrB-like REGe monogermanide for example, and following this formalism, the simplest structure to build is that of REGe_2 , where every other $\frac{1}{\infty}[\text{Ge}_2]$ chain is replaced by a square sheet, $\frac{2}{\infty}[\text{Ge}_2]$, leading to doubling of the stacking sequence and an arrangement of the ZrSi_2 type [7]. If every other $\frac{1}{\infty}[\text{Ge}_2]$ chain is replaced by not one, but two square sheets that come in contact, i.e. double-square nets $\frac{2}{\infty}[\text{Ge}_2]$, this will lead to an arrangement analogous to that in the DyGe_3 type [18]. Further “fine-tuning” of the latter structures by replacing every other $\frac{2}{\infty}[\text{Ge}_2]$ -single or $\frac{2}{\infty}[\text{Ge}_2]$ -double square sheet with different $\frac{1}{\infty}[\text{Ge}_2]$ chains, will lead again

Fig. 3. Temperature dependence of the magnetic susceptibility (χ) and heat capacity (C_p) plots for $\text{RE}_2[\text{Sn}_x\text{Ge}_{1-x}]_5$ ($\text{RE} = \text{Nd}, \text{Sm}$) and $\text{RE}[\text{Sn}_x\text{Ge}_{1-x}]_2$ ($\text{RE} = \text{Gd}, \text{Tb}$). Inverse magnetic susceptibility $\chi^{-1}(T)$ plots are shown in the insets. The specific heat data are shown in the representation C_p/T vs. T .

Fig. 4. Schematic representation of the way the $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) and $RE[Sn_xGe_{1-x}]_2$ ($RE = Gd, Tb$) structures can be related to those of $REGe$ (CrB type), $REGe_2$ (ZrSi₂ type) and $REGe_3$ (DyGe₃ type). Labeling of the atoms is identical to that in Fig. 1.

to doubling of the stacking sequence and structural arrangements analogous to those in I and II, respectively. It is also appropriate to mention the closely related $TmGe_{1.9}$ [31], the structure of which is composed of the same motifs except that one out of every three $\infty[Ge_2]$ sheets is substituted by another Ge zig-zag chain. One can also envision various intergrowths, such as the depicted RE_2Ge_5 , which is exemplified by the Er_2Ge_5 type [32]. The latter is built from three distinct moieties: (i) double square sheets, (ii) CrB type zig-zag chains, and (iii) single square sheets in an alternating

arrangement. Obviously, although the overall chemical formula of the $RE_2[Sn_xGe_{1-x}]_5$ ($RE = Nd, Sm$) compounds bears resemblance to that of Er_2Ge_5 , the two structures are not isotypic.

Such a design by homology allows for the prediction of new compounds and their possible structures that are likely to exist, but not yet synthesized. For instance, we can hypothesize that a possible new member of the series will be RE_3Ge_7 , the structure of which is an intergrowth of $REGe_2$ and RE_2Ge_5 . This particular structure is yet unknown for the RE–Ge systems; however, several RE_3Sn_7 , the second to last members of the RE_nSn_{3n-2} (where $n = 1-4$) homologue series are already reported [23]. Although their structures are different than the ones discussed herein, a similar “building-up” approach by starting from $RESn_3$ (AuCu₃ type) relates the structures of all members of the family [23,33].

On this note, it is also important to mention that there seems to be a size requirement not only for the RE metal but also for the tetrel atom, Ge or Sn, which must be met in order for a particular structure to be realized. This hypothesis is based on the observed chemical trends across the lanthanide series (see Section 2), and a previous study on the stability limits of the rare-earth metal germanides with the ZrSi₂- and DyGe₃ types [31]. It is further supported by the fact that Gd and Tb can form compounds with two distinct structures, $RESn_{1+x}Ge_{1-x}$ and $RE[Sn_xGe_{1-x}]_2$, whereas Nd and Sm seem to be able to afford only $RE_2[Sn_xGe_{1-x}]_5$. We also recall that the previously stated observation that RE–Ge–Sn reactions for the early lanthanides (La, Ce, Pr) result in the cubic $RESn_3$ phases and no Ge–Sn mixing [1]. These also are the very same rare-earth metals, for which the RE_nSn_{3n-2} (where $n = 1-4$) homologue series is known [23]. However, as one moves to the right of the 4f-block, due to the lanthanide contraction, the ionic sizes decrease and new pseudo-binary compounds with mixed Ge and Sn begin to appear [1]. Noteworthy, the mixing of these elements is not random and there seem to be preferred places for each—Ge preferentially forms zig-zag chains while Sn prefers the planar nets. It is of no surprise that the title compounds portray a “coloring effect” between two group 14 elements, Ge and Sn, being that parallel studies in the closely related $RESn_{1+x}Ge_{1-x}$ compounds also did [1]. As discussed elsewhere, rationalizing the site preferences in solids has become an integral part for understanding the reason behind why atoms arrange in a given structure [34].

Acknowledgements

SVilen Bobev acknowledges financial support from the National Science Foundation through a grant DMR-0743916 (CAREER). PHT wishes to thank the University of Delaware for the University Graduate Fellowship and the International Centre for Diffraction Data (ICDD) for the Ludo Frevel Crystallography Scholarship. Work at LANL was done under the auspices of the US DOE.

References

- [1] P.H. Tobash, J.J. Meyers, G. DiFilippo, S. Bobev, F. Ronning, J.D. Thompson, J.L. Sarrao, *Chem. Mater.* 20 (2008) 2151.
- [2] S. Ponou, T.F. Fässler, *Inorg. Chem.* 43 (2004) 6124.
- [3] T. Kyratsi, D.Y. Chung, M.G. Kanatzidis, *J. Alloys Compd.* 338 (2002) 36.
- [4] Y. Mozharivskij, D. Kaczorowski, H.F. Franzen, *J. Solid State Chem.* 155 (2000) 259.
- [5] W. Choe, G.J. Miller, J. Meyers, S. Chumbley, A.O. Pecharsky, *Chem. Mater.* 15 (2003) 1413.
- [6] P.H. Tobash, D. Lins, S. Bobev, A. Lima, M.F. Hundley, J.D. Thompson, J.L. Sarrao, *Chem. Mater.* 17 (2005) 5567.
- [7] P. Villars, L.D. Calvert, *Pearson's Handbook of Crystallographic Data for Intermetallic Phases*, second ed., American Society for Metals, Materials Park, OH, 1991.
- [8] M.-H. Whangbo, C. Lee, J. Köhler, *Angew. Chem. Int. Ed.* 45 (2006) 7465.
- [9] JADE Version 6.5, Materials Data, Inc., Livermore, CA, 2003.
- [10] SMART NT, version 5.63, Bruker Analytical X-Ray Systems, Inc., Madison, WI, 2003.

- [11] SAINT NT, version 6.45, Bruker Analytical X-Ray Systems, Inc., Madison, WI, 2003.
- [12] SADABS NT, version 2.10, Bruker Analytical X-Ray Systems, Inc., Madison, WI, 2001.
- [13] SHELXTL, version 6.12, BrukerAnalytical X-Ray Systems, Inc., Madison, WI, 2001.
- [14] L.M. Gelato, E. Parthe, *J. Appl. Crystallogr.* 20 (1987) 139.
- [15] I.R. Mokra, V.K. Pecharsky, Z.M. Shpyrka, O.I. Bodak, V.K. Belsky, I.E. Pats, *Dop. AN Ukr. SSR, Ser. B* 3 (1989) 48.
- [16] O. Oleksyn, P. Schobinger-Papamantellos, C. Ritter, C.H. de Groot, K.H.J. Buschow, *J. Alloys Compd.* 252 (1997) 53.
- [17] For example, crystals from $\text{Sm}_2\text{Sn}_{1.22(1)}\text{Ge}_{3.54(1)}$ were obtained from a reaction loaded with the same nominal composition as the sample listed in Table 1, but heat-treated differently. Unit cell dimensions: $a = 4.0735(9) \text{ \AA}$, $b = 35.576(8) \text{ \AA}$, $c = 4.2130(9) \text{ \AA}$, $V = 610.5(2) \text{ \AA}^3$. Similar effect on the cell constants is seen for $\text{TbSn}_{0.44(1)}\text{Ge}_{1.45(1)}$, synthesized from a reaction loaded with slightly different nominal composition and treated at the same temperature. Unit cell dimensions: $a = 4.207(3) \text{ \AA}$, $b = 30.31(1) \text{ \AA}$, $c = 3.995(3) \text{ \AA}$, $V = 509(2) \text{ \AA}^3$.
- [18] P. Schobinger-Papamantellos, D.B. de Mooij, K.H.J. Buschow, *J. Alloys Compd.* 183 (1992) 181.
- [19] P.H. Tobash, D. Lins, S. Bobev, N. Hur, J.D. Thompson, J.L. Sarrao, *Inorg. Chem.* 45 (2006) 7286.
- [20] P.H. Tobash, G. DiFilippo, S. Bobev, N. Hur, J.D. Thompson, J.L. Sarrao, *Inorg. Chem.* 46 (2007) 8690.
- [21] P.H. Tobash, S. Bobev, *J. Am. Chem. Soc.* 128 (2006) 3532.
- [22] S. Bobev, E.D. Bauer, J.D. Thompson, J.L. Sarrao, G.J. Miller, B. Eck, R. Dronskowski, *J. Solid State Chem.* 177 (2004) 3545.
- [23] F. Weitzer, K. Hiebl, P. Rogl, *J. Solid State Chem.* 98 (1992) 291.
- [24] M.J. Ferguson, R.W. Hushagen, A. Mar, *Inorg. Chem.* 35 (1996) 4505.
- [25] R. Jardin, V. Babizhetskyy, R. Guérin, J. Bauer, *J. Alloys Compd.* 353 (2003) 233.
- [26] J.S. Smart, *Effective Theories of Magnetism*, Saunders, Philadelphia, PA, 1966.
- [27] C. Kittel, *Introduction to Solid State Physics*, seventh ed., John Wiley and Sons, Hoboken, NJ, 1996.
- [28] A. Dogan, S. Rayaprol, R. Pöttgen, *J. Phys.: Condens. Matter* 19 (2007) 026209.
- [29] N.P. Duong, J.C.P. Klaasse, E. Brück, P.E. Brommer, F.R. de Boer, K.H.J. Buschow, *J. Magn. Magn. Mater.* 262 (2003) 458.
- [30] W. Good, J. Kim, A.I. Goldman, D. Wermeille, P.C. Canfield, C. Cunningham, Z. Islam, J.C. Lang, G. Srajer, I.R. Fisher, *Phys. Rev. B* 71 (2005) 224427.
- [31] G. Venturini, *J. Alloys Compd.* 308 (2000) 200.
- [32] G. Venturini, I. Ijjaali, B. Malaman, *J. Alloys Compd.* 288 (1999) 183.
- [33] J.X. Boucherle, F. Givord, P. Lejay, J. Schweizer, A. Stunault, *Acta Crystallogr.* B44 (1988) 377.
- [34] G.J. Miller, *Eur. J. Inorg. Chem.* 523 (1998).

Insertion reactions of scandium pyridyl complexes supported by a ferrocene diamide ligand

Colin T. Carver, Paula L. Diaconescu*

Department of Chemistry & Biochemistry, University of California, Los Angeles, CA 90095, United States

ARTICLE INFO

Article history:

Received 30 May 2008

Received in revised form

25 September 2008

Accepted 6 October 2008

Available online 25 November 2008

Keywords:

Scandium

Pyridyl

Ferrocene

Ethylene

Alkyne

Butadiene

ABSTRACT

Unlike reported examples of early transition metal $\eta^2(\text{N,C})$ -pyridyl complexes, scandium $\eta^2(\text{N,C})$ -pyridyl complexes supported by a ferrocene diamide ligand react further with pyridines to give coupling products. Although most of their insertion reactions with unsaturated substrates are similar to those of previous yttrocene and zirconocene complexes, in the reaction with butadiene, higher reactivity than the one reported for the yttrocene complex was observed. Herein are discussed reactions of $\eta^2(\text{N,C})$ -pyridyl scandium complexes supported by a 1,1'-ferrocene diamide ligand with ethylene, 2-butyne, and 1,3-butadiene.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Methods to functionalize heterocycles have been of long standing interest given the ubiquitous presence of these structures in biological compounds [1–8]. Pioneered by Jordan in the early 1990s, [9–12] the functionalization of N-heterocycles using early transition metal alkyl complexes has found numerous applications [13–25]. These reactions usually involve the insertion of an unsaturated substrate into the metal–carbon bond of a strained metallaaziridine and the formation of a new four or five-member ring metalocycle.

We have recently reported on scandium and yttrium alkyl complexes supported by a 1,1'-ferrocene diamide ligand [26] and their reactions with aromatic heterocycles [27]. Unlike Cp^*_2ScMe , [28] these complexes react with pyridines to give C–C coupled products and ring-open imidazole to give an imidazole–imine–amide product. Given this different reactivity behavior, we became interested in isolating an $\eta^2(\text{N,C})$ -scandium complex analogous to $\text{Cp}^*_2\text{Sc}(\eta^2\text{-N,C-pyridyl})$ and explore its reactions with unsaturated substrates.

2. Experimental

All experiments were performed under a dry nitrogen atmosphere using standard Schlenk techniques or an MBraun inert-gas glovebox. Solvents were purified using a two-column solid-state purification system by the method of Grubbs [29] and transferred to the glovebox without exposure to air. NMR solvents were obtained from Cambridge Isotope Laboratories, degassed, and stored over activated molecular sieves prior to use. Scandium oxide was purchased from Stanford Materials Corporation, 4 Meadowpoint, Aliso Viejo, CA 92656, and used as received. $\text{Sc}(\text{fc}[\text{NSi}^i\text{BuMe}_2]_2)(\text{CH}_2\text{Xy-3,5})(\text{THF})$ ($1^{\text{CH}_2\text{Ar}}\text{-THF}$), [26] $\text{Sc}(\text{fc}[\text{NSi}^i\text{BuMe}_2]_2)\text{Me}(\text{THF})_2$ (1^{Me}-THF), [26] and $\text{Sc}(\text{fc}[\text{NSi}^i\text{BuMe}_2]_2)(\eta^2\text{-N,C-6-Ph-pyridyl})(\text{THF})$, 2- py^{ph} , [27] were prepared following published procedures. The aromatic heterocycles were distilled or recrystallized before use; all other materials were used as received. ^1H NMR spectra¹ were recorded on Bruker300 or Bruker500 spectrometers at room temperature in C_6D_6 unless otherwise specified. Chemical shifts are reported with respect to internal solvent, 7.16 ppm (C_6D_6). CHN analyses were performed by UC Berkeley Micro-Mass facility, 8 Lewis Hall, College of Chemistry, University of California, Berkeley, CA 94720.

2.1. Synthesis of $\text{Sc}(\text{fc}[\text{NSi}^i\text{BuMe}_2]_2)(\eta^2\text{-N,C-pyridyl})(\text{py})$, 2-py

1^{Me}-THF (150 mg, 0.232 mmol) was placed in a Schlenk tube in toluene (10 mL), and 4 equiv of pyridine (73.4 mg, 0.928 mmol) was added. The reaction mixture was warmed to 70 °C for 5 h. The solvent was removed and the resulting yellow solid was extracted with hexanes. Yield 79.8 mg, 53.4%, as two crops from hexanes. ^1H NMR (300 MHz, C_6D_6): δ , ppm: 9.12 (d, 2H, NC_5H_5), 8.32 (d, 1H, NC_5H_5 or NC_5H_4), 8.02 (d, 1H, NC_5H_5 or NC_5H_4), 7.23 (m, 1H, NC_5H_5 or NC_5H_4), 6.94 (m, 1H, NC_5H_5

* Corresponding author.

E-mail address: pld@chem.ucla.edu (P.L. Diaconescu).

¹ This material is based upon work supported by the NSF grant CHE-9974928.

or NC_5H_4), 6.80 (m, 1H, NC_5H_5 or NC_5H_4), 6.71 (m, 2H, NC_5H_5), 4.19 (bs, 4H, fc-CH), 3.62 (bs, 4H, fc-CH), 0.84 (s, 18H, $\text{Si}(\text{CH}_3)_3$), -0.16 (s, 12H, $\text{Si}(\text{CH}_3)_2$). ^{13}C NMR (126 MHz, C_6D_6): δ , ppm: 144.1, 134.1, 130.4, 122.3, 104.6, 67.6, 27.7, 20.6, -3.0 . Anal. for $\text{C}_{32}\text{H}_{47}\text{FeN}_4\text{Si}_2\text{Sc}$. Calcd.: C, 59.61%; H, 7.35%; N, 8.69%. Found: C, 59.65%; H, 7.51%; N, 8.51%.

2.2. Reaction of $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\eta^2\text{-N,C-pyridyl})(\text{py})$, 2-py, with ethylene

2-py (15 mg, 0.0232 mmol) was dissolved in C_6D_6 (1.5 mL); this solution was placed in a J-Young tube and 10 psi of ethylene was introduced. The reaction mixture was allowed to stand at room temperature and monitored by ^1H NMR spectroscopy. The reaction is complete in 4 h and quantitative. Alternately, the insertion product can be formed directly from $1^{\text{CH}_2\text{Ar}}\text{-THF}$ and pyridine under an atmosphere of ethylene. In a 50-mL Schlenk tube, $1^{\text{CH}_2\text{Ar}}\text{-THF}$ (200 mg, 0.295 mmol) was combined with 2 equiv of pyridine (46.6 mg, 0.589 mmol) in toluene (8 mL) and ethylene (10 psi) was introduced. The reaction mixture was stirred at 70°C for 18 h. The solvent was removed and the resulting yellow solid was extracted in hexanes and filtered through Celite. Yield 167 mg, 84.3%, as 2 crops from hexanes. ^1H NMR (300 MHz, C_6D_6): δ , ppm: 9.30 (bs, 2H, NC_5H_5), 8.59 (d, 1H, NC_5H_5 or NC_5H_4), 6.98 (tr, 1H, NC_5H_5 or NC_5H_4), 6.89 (tr, 1H, NC_5H_5 or NC_5H_4), 6.85 (d, 1H, NC_5H_5 or NC_5H_4), 6.70 (tr, 2H, NC_5H_5), 6.60 (tr, 1H, NC_5H_5 or NC_5H_4), 4.15 (bs, 2H, fc-CH), 3.93 (bs, 2H, fc-CH), 3.77 (t, 2H, $\text{ScCH}_2\text{CH}_2\text{Py}$), 3.60 (bs, 2H, fc-CH), 2.99 (bs, 2H, fc-CH), 0.99 (s, 18H, $\text{Si}(\text{CH}_3)_3$), 0.93 (t, 2H, $\text{ScCH}_2\text{CH}_2\text{Py}$), 0.35 and 0.01 (s, 12H, $\text{Si}(\text{CH}_3)_2$). ^{13}C NMR (126 MHz, C_6D_6): δ , ppm: 172.9, 150.9, 147.0, 137.9, 124.1, 123.9, 119.9, 102.0, 71.1, 67.9, 67.3, 66.8, 66.0, 28.0, 25.2, 20.8, -2.0 . Anal. for $\text{C}_{34}\text{H}_{51}\text{FeN}_4\text{Si}_2\text{Sc}$. Calcd.: C, 60.70%; H, 7.64%; N, 8.33%. Found: C, 60.70%; H, 7.95%; N, 8.23%.

2.3. Reaction of $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\eta^2\text{-N,C-6-Ph-pyridyl})(\text{py})$, 2-py^{Ph}, with ethylene

2-py^{Ph} (100 mg, 0.140 mmol) was dissolved in toluene (10 mL) and placed in a 100-mL Schlenk tube. Ethylene (0.680 atm) was introduced. The reaction mixture was allowed to stir for 3 h at room temperature. The solvent was removed and the resulting yellow solid was extracted in hexanes and filtered through Celite. Yield 78.3 mg, 83.4%. ^1H NMR (500 MHz, C_6D_6): δ , ppm: 7.79 (d, 2H, C_6H_5), 7.20 (t, 2H, C_6H_5), 7.09 (t, 1H, NC_5H_3 or C_6H_5), 7.04 (t, 1H, NC_5H_3 or C_6H_5), 6.88 (d, 1H, NC_5H_3 or C_6H_5), 6.78 (d, 1H, NC_5H_3 or C_6H_5), 4.21 (s, 2H, fc-CH), 3.88 (s, 2H, fc-CH), 3.78 (t, 2H, $\text{ScCH}_2\text{CH}_2\text{Py}$), 3.61 (s, 2H, fc-CH), 3.18 (s, 2H, fc-CH), 0.93 (t, 2H, $\text{ScCH}_2\text{CH}_2\text{Py}$), 0.93 (s, 18H, $\text{Si}(\text{CH}_3)_3$), 0.02 and -0.15 (s, 12H, $\text{Si}(\text{CH}_3)_2$). ^{13}C NMR (126 MHz, C_6D_6): δ , ppm: 173.2, 158.4, 140.1, 138.7, 130.0, 127.2, 123.5, 120.6, 106.7, 70.0, 68.4, 67.1, 66.6, 36.6, 27.8, 20.4, -3.2 , -3.4 . Anal. $\text{C}_{35}\text{H}_{50}\text{FeN}_3\text{Si}_2\text{Sc}$. Calcd.: C, 62.77%; H, 7.52%; N, 6.27%. Found: C, 62.72%; H, 7.87%; N, 6.25%.

2.4. Reaction of $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\eta^2\text{-N,C-6-Ph-pyridyl})(\text{py})$, 2-py^{Ph}, with 2-butyne

2-py^{Ph} (200 mg, 0.280 mmol) was placed in a J-Young tube with 2-butyne (76 mg, 1.40 mmol) in C_6D_6 . The reaction mixture was heated for 48 h at 50°C . The volatiles were removed and the resulting brownish-yellow solid was washed with 1.5 mL hexanes, giving a yellow solid. Yield 152 mg, 70.6%. ^1H NMR (500 MHz, C_6D_6): δ , ppm: 7.78 (d, 2H, C_6H_5), 7.20 (m, 4H, C_6H_5 and NC_5H_4), 7.05 (m, 1H, NC_5H_4), 7.01 (m, 1H, NC_5H_4), 6.74 (d, 1H, NC_5H_4), 4.18 (s, 2H, fc-CH), 3.99 (s, 2H, fc-CH), 3.54 (s, 2H, fc-CH), 3.04 (s, 2H, fc-CH), 2.29 (s, 3H, $\text{CH}_3\text{-CC}$), 1.98 (s, 3H, $\text{CH}_3\text{-CC}$), 0.91 (s, 18H, $\text{Si}(\text{CH}_3)_3$), 0.04 and -0.10 (s, 12H, $\text{Si}(\text{CH}_3)_2$). ^{13}C NMR (126 MHz, C_6D_6): δ , ppm: 167.2, 158.0, 141.3, 139.4, 135.2, 131.1, 129.8, 126.5, 118.7, 118.3, 104.3, 69.2, 68.4, 67.6, 67.2, 27.7, 22.1, 20.2, 12.3, -2.9 , -3.9 . Anal. for $\text{C}_{37}\text{H}_{52}\text{FeN}_3\text{Si}_2\text{Sc}$. Calcd.: C, 63.87%; H, 7.53%; N, 6.04%. Found: C, 63.63%; H, 7.87%; N, 6.25%.

2.5. Reaction of $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\eta^2\text{-N,C-6-Ph-pyridyl})(\text{py})$, 2-py^{Ph}, with 1,3-butadiene

2-py^{Ph} (200 mg, 0.280 mmol) was dissolved in toluene (10 mL) and placed in a 100-mL Schlenk tube. Butadiene was introduced (ca. 3 atm). The reaction was stirred overnight at room temperature. The volatiles were removed and the product was washed with 1.5 mL hexanes. Yield 148 mg, 75.9%. ^1H NMR (300 MHz, C_6D_6): δ , ppm: 7.69 (d, 2H, C_6H_5), 7.24 (t, 2H, C_6H_5 and/or NC_5H_4), 7.09 (m, 1H, C_6H_5 and/or NC_5H_4), 6.92 (m, 1H, C_6H_5 and/or NC_5H_4), 6.84 (td, 1H, $\text{CH}_2\text{CHCHCH}_2$), 6.65 (m, 2H, C_6H_5 and/or NC_5H_4), 4.37 (m, 1H, $\text{CH}_2\text{CHCHCH}_2$), 4.24 (s, 1H, $\text{CH}_2\text{CHCHCH}_2$), 4.18 (s, 1H, $\text{CH}_2\text{CHCHCH}_2$), 3.89 and 3.49 (m, 8H, fc-CH), 3.10 (s, 1H, $\text{CH}_2\text{CHCHCH}_2$), 2.63 (s, 1H, $\text{CH}_2\text{CHCHCH}_2$), 1.00 and 0.92 (s, 18H, $\text{Si}(\text{CH}_3)_3$), -0.02 , -0.03 , -0.18 , and -0.22 (s, 12H, $\text{Si}(\text{CH}_3)_2$). ^{13}C NMR (126 MHz, C_6D_6): δ , ppm: 174.5, 160.8, 149.0, 140.2, 138.7, 129.4, 129.3, 128.9, 128.4, 124.0, 122.5, 103.7, 103.6, 89.5, 73.2, 70.4, 69.7, 69.5, 69.4, 69.0, 67.6, 65.9, 65.8, 40.9, 28.1, 28.0, 21.2, 20.7, -2.8 , -3.2 , -3.3 , -3.6 . Anal. for $\text{C}_{37}\text{H}_{52}\text{FeN}_3\text{Si}_2\text{Sc}$. 0.5 toluene (consistent with X-ray crystal structure). Calcd.: C, 65.57%; H, 7.61%; N, 5.66%. Found: C, 65.15%; H, 7.67%; N, 5.68%.

2.6. X-ray crystal structures

X-ray quality crystals were obtained from various concentrated solutions placed in a -35°C freezer in the glove box. Inside the glove box, the crystals were coated with oil (STP Oil Treatment) on a microscope slide, which was brought outside the glove box. The X-ray data collections were carried out on a Bruker AXS single crystal X-ray diffractometer using Mo K α radiation and a SMART APEX CCD detector. The data was reduced by SAINTPLUS and an empirical absorption correction was applied using the package SADABS. The structures were solved and refined using SHELXTL (Bruker 1998, SMART, SAINT, XPREF AND SHELXTL, Bruker AXS Inc., Madison, Wisconsin, USA). All atoms were refined anisotropically and hydrogen atoms were placed in calculated positions unless specified otherwise. Tables with atomic coordinates and equivalent isotropic displacement parameters, with all the bond lengths and angles, and with anisotropic displacement parameters are listed in the cif files.

2.6.1. 2-py

X-ray quality crystals were obtained from a concentrated toluene:pentane solution placed in a -35°C freezer in the glove box. A total of 14784 reflections ($-13 \leq h \leq 13$, $-14 \leq k \leq 14$, $-20 \leq l \leq 20$) were collected at $T = 110(2)\text{K}$ with $2\theta_{\text{max}} = 56.39^\circ$, of which 7992 were unique ($R_{\text{int}} = 0.0203$). The residual peak and hole electron density were 1.34 and $-0.78\text{ e}\text{\AA}^{-3}$. The least-squares refinement converged normally with residuals of $R_1 = 0.0423$ and $\text{GOF} = 1.035$. Crystal and refinement data for 2-py: formula $\text{C}_{32}\text{H}_{47}\text{N}_4\text{Si}_2\text{ScFe}$, space group P_1 , $a = 10.4265(11)$, $b = 10.7864(11)$, $c = 15.3460(16)$, $\alpha = 88.151(2)$, $\beta = 84.251(1)$, $\gamma = 75.721(2)^\circ$, $V = 1664.1(3)\text{\AA}^3$, $Z = 2$, $\mu = 0.739\text{ mm}^{-1}$, $F(000) = 684$, $R_1 = 0.00547$ and $wR_2 = 0.1138$ (based on all 7992 data, $I > 2\sigma(I)$).

2.6.2. 3-py^{Ph}

X-ray quality crystals were obtained from a concentrated toluene: pentane solution placed in a -35°C freezer in the glove box. The data were not very good and only connectivity information could be obtained. Only cell parameters will be included. A total of 34831 reflections ($-46 \leq h \leq 46$, $-21 \leq k \leq 21$, $-19 \leq l \leq 19$) were collected at $T = 100(2)\text{K}$ with $2\theta_{\text{max}} = 60.94^\circ$, of which 10233 were unique. Crystal data for 3-py^{Ph}: formula $\text{C}_{35}\text{H}_{50}\text{N}_3\text{Si}_2\text{ScFe}$, space group $C2/c$, $a = 32.9742$, $b = 15.5417$, $c = 13.8670$, $\beta = 95.891^\circ$, $V = 7068.96\text{\AA}^3$, $Z = 8$, $\mu = 0.70\text{ mm}^{-1}$, $F(000) = 2848$.

2.6.3. 5-py^{Ph}

X-ray quality crystals were obtained from a concentrated toluene: pentane solution placed in a -35°C freezer in the glove box. A molecule of toluene was found. The toluene molecule is sitting on a special position and is disordered such that one of the aromatic carbon atoms is also the methyl group of the other half of the molecule. The occupancy for this carbon atom was fixed to 75% and of three other carbons to 50%. One of the solvent atoms was not refined anisotropically; also hydrogen atoms were not added to the solvent carbon atoms. The allyl group (C2 and C3 atoms) is disordered over two positions. This disorder was model such that each position is occupied 50%. The two components of C2 (C2a and C2b) were not refined anisotropically. This atom (C2) is thermally disordered, accounting for the high electron density found next to it. The disorder was not refined. A total of 34875 reflections ($-13 \leq h \leq 13$, $-21 \leq k \leq 21$, $-30 \leq l \leq 30$) were collected at $T = 100(2)\text{K}$ with $2\theta_{\text{max}} = 56.66^\circ$, of which 9535 were unique ($R_{\text{int}} = 0.0904$). The residual peak and hole electron density were 2.20 and $-0.90\text{ e}\text{\AA}^{-3}$. The least-squares refinement converged normally with residuals of $R_1 = 0.0593$ and $\text{GOF} = 1.032$. Crystal and refinement data for 5-py^{Ph}: formula $\text{C}_{40.25}\text{H}_{52}\text{N}_3\text{Si}_2\text{ScFe}$, space group $P2(1)/c$, $a = 10.376(3)$, $b = 16.437(5)$, $c = 22.721(7)$, $\beta = 93.281(3)^\circ$, $V = 3868.7(19)\text{\AA}^3$, $Z = 4$, $\mu = 0.644\text{ mm}^{-1}$, $F(000) = 1558$, $R_1 = 0.1111$ and $wR_2 = 0.1568$ (based on all 9535 data, $I > 2\sigma(I)$).

3. Results and discussion

Although the reaction between the ferrocene 1,1'-diamide scandium benzyl complex, $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\text{CH}_2\text{Xy-3,5})(\text{THF})$ ($1^{\text{CH}_2\text{Ar}}\text{-THF}$, $\text{Xy} = \text{xylyl}$) [26] and pyridine or 2-picoline gave mixtures of compounds, employing $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2]\text{Me}(\text{THF})_2$ (1^{Me}-THF) [26] allowed the isolation of an $\eta^2(\text{N,C})$ -pyridyl complex, $\text{Sc}[\text{fc}(\text{NSi}^t\text{BuMe}_2)_2](\eta^2\text{-N,C-pyridyl})(\text{py})$ (2-py, Eq. (1)). Complex 2-py was characterized by X-ray crystallography, which shows the pyridyl and pyridine ligands coplanar and coordinated in a plane perpendicular to the $\text{N}_{\text{amide}}\text{-Fe-N}_{\text{amide}}$ one (Fig. 1).

Fig. 1. ORTEP representation of 2-py with thermal ellipsoids at 50% probability (H atoms and solvent molecules were omitted for clarity).

(1)

(2)

Scheme 1. Reaction of a zirconocene pyridyl cation with ethylene and 2-butyne [10,30,31].

The reaction between 2-py and ethylene occurs at room temperature in 4 h to give the insertion product 3-py (Eq. (2)). It was not surprising that the reaction was rather slow since the analogous zirconocene pyridyl cationic complex featuring a pyridine molecule coordinated to the metal center did not react with ethylene [10]. Given the low reactivity of 2-py we decided to focus on a different pyridyl complex. Jordan et al. showed (Scheme 1) that using the steric pressure of a methyl substituent close to the metal center increased the rate of the insertion reactions [10,30,31]. We reasoned that a similar effect would be observed in our system. The phenylpyridyl complex 2-py^{Ph} seemed to be an appropriate choice because it coordinates THF instead of an additional 2-phenylpyridine molecule. Compound 2-py^{Ph} was prepared from 1^{CH₂Ar}-THF in the presence of one equivalent of 2-phenylpyridine. The use of more than one equivalent of 2-phenylpyridine leads to the formation of a product in which the two pyridine rings are coupled in the 2,2'-positions [27].

As expected, the reaction between ethylene and 2-py^{Ph} took place faster than the analogous reaction with 2-py (Eq. (2), 0.5 h vs 4 h). Characterization of the insertion product 3-py^{Ph} by X-ray crystallography (Fig. 2) confirms the solution structure indicated by ¹H NMR spectroscopy. Inspection of the X-ray crystal structure shows that the pyridine ring is tilted with respect to the ferrocene backbone. This tilting, absent in the case of 2-py, is likely caused by steric factors, since it allows the phenyl ring and the ethylene arm to avoid interactions with the silyl substituents.

Fig. 2. Molecular structure of 3-py^{Ph} (H atoms and solvent molecules were omitted for clarity).

Another reaction of interest with an unsaturated substrate is the reaction between pyridyl complexes and 2-butyne. The zirconocene pyridyl cationic complex reported by Jordan et al. inserted 2-butyne to form a five-member azometalocycle (Scheme 1) [10]. The yttrocene pyridyl complex reported by Teuben et al. showed different reactivity behavior: instead of an insertion reaction, a protonation reaction involving the methyl butyne protons took place (Scheme 2) [32]. The reaction between 2-py^{Ph} and 2-butyne led to the isolation of an insertion product, 4-py^{Ph}, analogous to the one obtained with the zirconocene complex (Eq. (3)). Complex 4-py^{Ph} presented ¹H and ¹³C NMR spectroscopy signatures similar to the values reported for the analogous zirconocene complex.

(3)

(4)

Scheme 2. Reaction of a yttrocene pyridyl complex with 2-butyne and 1,3-butadiene [32].

Fig. 3. ORTEP representation of 5-py^{Ph} with thermal ellipsoids at 50% probability (H atoms and solvent molecules were omitted for clarity). Both allyl orientations are shown.

As part of our attempt to compare the reactivity of scandium pyridyl complexes with the reactivity of analogous yttrium and zirconium complexes, we also carried out the reaction with 1,3-butadiene (Eq. (4)). Teuben reported that butadiene did not react with the yttrium complex $\text{Cp}^*_2\text{Y}(\eta^2\text{-}N,C\text{-pyridyl})$ [32]. No information related to a reaction of butadiene with the zirconium cationic pyridyl complexes could be found in the reports published by Jordan [10]. When a solution of 2-py^{Ph} was allowed to react with 1 equiv of 1,3-butadiene we observed the formation of one major product, 5-py^{Ph}. Inspection of this product by ^1H NMR spectroscopy indicated that the fragment originating in the butadiene molecule is coordinated to the scandium center since all olefinic protons are shifted from the values in butadiene.

Coordination of the allyl moiety to the scandium center was confirmed by X-ray crystallography (Fig. 3), which indicates that the Sc–C bonds to the three carbon atoms are rather similar. We also found that the carbon atoms of the allyl backbone are disordered, analogously to the disorder reported by Bercaw et al. [33] for a non-substituted allyl scandocene complex. The thermal disorder was modeled as a 50:50 population of sites, showing two different orientations for the allyl ligand.

4. Conclusions

The insertion of unsaturated substrates into scandium pyridyl complexes supported by a ferrocene diamide ligand bears similarities and dissimilarities to analogous reactions of zirconocene and yttrocene pyridyl complexes. Although the scandium complexes studied here show heterocycle coupling behavior analogous

to the yttrocene complexes, the insertion chemistry is rather different in some aspects. All compounds react with ethylene to form a 5-member ring azometallacycle. However, in the reaction with 2-butyne, the scandium pyridyl complex forms a product analogous to the zirconocene complex, but not to the yttrocene pyridyl complex. The yttrocene pyridyl complex did form a similar insertion product when 2-pentyne was used instead of 2-butyne. Finally, the scandium pyridyl complex reacted with 1,3-butadiene while the yttrocene complex showed no reactivity.

Acknowledgments

The authors thank Dr. Saeed Khan for help with crystallography. This work was supported by UCLA.

References

- [1] D.M. D'Souza, T.J.J. Muller, *Chem. Soc. Rev.* 36 (2007) 1095–1108.
- [2] G. Zeni, R.C. Larock, *Chem. Rev.* 104 (2004) 2285–2310.
- [3] I. Nakamura, Y. Yamamoto, *Chem. Rev.* 104 (2004) 2127–2198.
- [4] G. Balme, E. Bossharth, N. Monteiro, *Eur. J. Org. Chem.* 2003 (2003) 4101–4111.
- [5] H.M.L. Davies, S.J. Hedley, *Chem. Soc. Rev.* 36 (2007) 1109–1119.
- [6] S.R. Chemler, P.H. Fuller, *Chem. Soc. Rev.* 36 (2007) 1153–1160.
- [7] M.D. Mihovilovic, P. Stanetty, *Angew. Chem. Int. Ed.* 46 (2007) 3612–3615.
- [8] A. Padwa, S.K. Bur, *Tetrahedron* 63 (2007) 5341–5378.
- [9] R.F. Jordan, A.S. Guram, *Organometallics* 9 (1990) 2116–2123.
- [10] R.F. Jordan, D.F. Taylor, N.C. Baenziger, *Organometallics* 9 (1990) 1546–1557.
- [11] A.S. Guram, R.F. Jordan, *Organometallics* 10 (1991) 3470–3479.
- [12] R.F. Jordan, *Adv. Organomet. Chem.* 32 (1991) 325–387.
- [13] J.C. Lewis, R.G. Bergman, J.A. Ellman, *J. Am. Chem. Soc.* 129 (2007) 5332–5333.
- [14] K.L. Tan, R.G. Bergman, J.A. Ellman, *J. Am. Chem. Soc.* 123 (2001) 2685–2686.
- [15] K.L. Tan, R.G. Bergman, J.A. Ellman, *J. Am. Chem. Soc.* 124 (2002) 13964–13965.
- [16] K.L. Tan, S. Park, J.A. Ellman, R.G. Bergman, *J. Org. Chem.* 69 (2004) 7329–7335.

- [17] S.H. Wiedemann, R.G. Bergman, J.A. Ellman, *Org. Lett.* 6 (2004) 1685–1687.
- [18] S.H. Wiedemann, J.A. Ellman, R.G. Bergman, *J. Org. Chem.* 71 (2006) 1969–1976.
- [19] F. Kakiuchi, S. Murai, *Acc. Chem. Res.* 35 (2002) 826–834.
- [20] N. Fujii, F. Kakiuchi, N. Chatani, S. Murai, *Chem. Lett.* (1996) 939–940.
- [21] N. Fujii, F. Kakiuchi, A. Yamada, N. Chatani, S. Murai, *Chem. Lett.* (1997) 425–426.
- [22] N. Fujii, F. Kakiuchi, A. Yamada, N. Chatani, S. Murai, *Bull. Chem. Soc. Jpn.* 71 (1998) 285–298.
- [23] Z. Zhang, X. Wang, R.A. Widenhoefer, *Chem. Commun.* (2006) 3717–3719.
- [24] C. Liu, X. Han, X. Wang, R.A. Widenhoefer, *J. Am. Chem. Soc.* 126 (2004) 3700–3701.
- [25] X. Han, R.A. Widenhoefer, *Org. Lett.* 8 (2006) 3801–3804.
- [26] C.T. Carver, M.J. Monreal, P.L. Diaconescu, *Organometallics* 27 (2008) 363–370.
- [27] C.T. Carver, P.L. Diaconescu, *J. Am. Chem. Soc.* (2008), ASAP.
- [28] M.E. Thompson, S.M. Baxter, A.R. Bulls, B.J. Burger, M.C. Nolan, B.D. Santarsiero, W.P. Schaefer, J.E. Bercaw, *J. Am. Chem. Soc.* 109 (1987) 203–219.
- [29] A.B. Pangborn, M.A. Giardello, R.H. Grubbs, R.K. Rosen, F.J. Timmers, *Organometallics* 15 (1996) 1518–1520.
- [30] R.F. Jordan, D.F. Taylor, *J. Am. Chem. Soc.* 111 (1989) 778–779.
- [31] A.S. Guram, R.F. Jordan, D.F. Taylor, *J. Am. Chem. Soc.* 113 (1991) 1833–1835.
- [32] B.-J. Deelman, W.M. Stevels, J.H. Teuben, M.T. Lakin, A.L. Spek, *Organometallics* 13 (1994) 3881–3891.
- [33] M.B. Abrams, J.C. Yoder, C. Loeber, M.W. Day, J.E. Bercaw, *Organometallics* 18 (1999) 1389–1401.

Phase transition induced by pressure in TbCrO₄ oxide: Relationship structure–properties

E. Climent^a, J.M. Gallardo^a, J. Romero de Paz^b, N. Taira^a, R. Sáez Puche^{a,*}

^a Dpto. Química Inorgánica, Facultad Ciencias Químicas, Universidad Complutense de Madrid, Ciudad Universitaria, E-28040 Madrid, Spain

^b CAI Técnicas Físicas, Facultad de Ciencias Físicas, Universidad Complutense de Madrid, E-28040 Madrid, Spain

ARTICLE INFO

Article history:

Received 30 May 2008

Received in revised form 9 October 2008

Accepted 14 October 2008

Available online 2 December 2008

Keywords:

Dimorphism

High-pressure synthesis

Antiferromagnetism

Ferromagnetism

Metamagnetism

ABSTRACT

Terbium chromate TbCrO₄, which has been described as belonging to the zircon-type structure showing tetragonal symmetry, space group *I*4₁/*amd*, has been prepared as a dimorphic compound. When the zircon-type TbCrO₄ polymorph is treated at 40 kbar and 833 K takes place a phase transition to the tetragonal scheelite-type TbCrO₄ polymorph, space group *I*4₁/*a*, with lattice parameters *a* = 5.0315(10) Å and *c* = 11.3740(2) Å. Magnetic susceptibility measurements reveal dramatic changes concerning the magnetic behavior of these two polymorphs. In this sense, the zircon-type TbCrO₄ polymorph behaves as ferromagnetic with a Curie temperature of 22 K, while the scheelite-type TbCrO₄ polymorph is antiferromagnetic with *T*_N = 29 K. *M* vs. *H* plots at different temperatures show the presence of a metamagnetic transition for the scheelite-type TbCrO₄ polymorph with a critical field of 2.6 T. The change of the sign of the magnetic interaction has been explained taking into account the differences found in the distances and bond angles of the superexchange Tb–O–Cr pathway through these interactions take place in both zircon and scheelite polymorphs.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

RCrO₄ oxides (*R* = rare earth) form a family of compounds with very interesting magnetic properties [1] and structural behavior [2]. The first member LaCrO₄ crystallizes with monazite-type structure, space group *P*2₁/*n* [3]. In the case of the remaining rare earths show the zircon-type structure with tetragonal symmetry, space group *I*4₁/*amd* [4]. Recently we have found that PrCrO₄ is a dimorphic oxide showing the mentioned zircon or monazite-type structure depending on the synthesis conditions [5].

Although phase transitions induced by pressure from zircon- to scheelite-type structure have been studied in some detail for the vanadate and arsenate families *R*XO₄ (*X* = V and As) [6,7], however only few studies have been recently reported for the analogous HoCrO₄ [8] and YCrO₄ [9] oxides. This could be due to the difficulty to prepare these oxides as pure phases because of the trouble to achieve the stabilization of the unusual 5+ oxidation state of chromium present in these phases. In fact, these high pressure scheelite phases show minor impurities of the perovskite-type RCrO₃ oxides [8,9]. Accompanying this structural phase transition from zircon to scheelite the magnetic properties change dramati-

cally. The coexistence of two paramagnetic cations, namely Cr⁵⁺ and R³⁺, in these oxides constitutes a very interesting scenario to study 3d–4f magnetic interactions and the predominant role that the rare earth anisotropy plays in the resulting magnetic properties of these two forms of the RCrO₄ oxides. In this sense, the most of the zircon-type RCrO₄ oxides being ferromagnetic [10] become antiferromagnetic for the corresponding known scheelite polymorph [8,9].

The aims of this work are the determination of the specific synthesis conditions such as pressure and temperature necessary to prepare the scheelite-type TbCrO₄ polymorph and the subsequent structural characterization using X-ray diffraction. Magnetic properties have been also studied from magnetic susceptibility and magnetization measurements at different temperatures and magnetic field strengths.

2. Experimental details

The zircon-type TbCrO₄ polymorph was prepared by using a precursor method based on the decomposition of stoichiometric amounts of Tb(NO₃)₃ · 6H₂O and Cr(NO₃)₃ · 9H₂O according to the experimental procedure described elsewhere [2]. Then this zircon TbCrO₄ oxide was placed within a platinum capsule and treated in a Belt-type apparatus at different high pressures, temperatures and reaction times. In order to eliminate the perovskite TbCrO₃ impurity different synthesis conditions were explored and 40 kbar and 833 K for 30 min were inferred as the optimized synthesis conditions.

X-ray powder diffraction data were collected on a Philips Analytical X'Pert MPD diffractometer using the monochromatic Cu Kα₁ radiation (λ = 1.54056 Å). X-ray

* Corresponding author. Tel.: +34 913944353; fax: +34 913944352.

E-mail address: rsp92@quim.ucm.es (R.S. Puche).

Fig. 1. Refined X-ray powder diffraction data for the scheelite-type TbCrO_4 oxide. Vertical marks indicate the position of the allowed reflections for the scheelite-type – 91.4(7)% – (upper) and for the perovskite-type – 8.6(3)% – oxides (lower).

diffraction data using for the Rietveld refinement were collected between 5 and 110 (2θ) with a step width 0.033° over a total exposure time period of 9 h. The X-ray diffraction data were refined with the Rietveld method using the FullProf program package [11].

Magnetic susceptibility measurements were made at different magnetic field strengths over the temperature range of 2–300 K using a SQUID Quantum Design XL-MPMS magnetometer. The variation of the magnetization as a function of the magnetic field was measured up to 5 T at different temperatures.

3. Results and discussion

3.1. Structural characterization

The Rietveld refinement of the X-ray diffraction data given in Fig. 1 for TbCrO_4 indicates that crystallizes with the scheelite-type structure showing tetragonal symmetry, space group $I4_1/a$, which has been obtained under high pressure and temperature from the zircon-type TbCrO_4 oxide. The metallic atoms Tb and Cr were located on 4b (0, 1/4, 5/8) and 4a (0, 1/4, 1/8) atomic positions, respectively, while the oxygen was located on 16f (x,y,z) position. Minor impurities of TbCrO_3 (8.6(3)%) are included in the refinement because appear during the high-pressure synthesis procedure as consequence of the mentioned previously high instability of Cr^{5+} .

Fig. 2. Perspective view of the ac -plane of the scheelite-type structure showing the arrangement of $[\text{TbO}_8]$ bisdisphenoids polyhedra (light grey) and $[\text{CrO}_4]$ tetrahedra (dark grey).

However, this impurity will not influence the magnetic properties of the scheelite phase as it will be discussed later.

The corresponding structural parameters for zircon and scheelite forms of TbCrO_4 are included in Table 1. According to these crystallographic data the crystal structure of the scheelite-type TbCrO_4 is shown in Fig. 2. As in the case of the zircon-type structure each Tb/Cr ion is also coordinated by eight and four oxygen atoms forming bisdisphenoids and tetrahedra polyhedra in this scheelite structure. This structure given in Fig. 2 can be described as formed by chains of alternate $[\text{RO}_8]$ bisdisphenoids and $[\text{CrO}_4]$ tetrahedra units along the a -axis of the structure, which are sharing corners. The $[\text{RO}_8]$ polyhedra of two consecutive chains are sharing edges along the c -axis giving rise to dimmers of $[\text{R}_2\text{O}_{14}]$ composition. As in the case of the zircon-type polymorph, the $[\text{CrO}_4]$ tetrahedra are well isolated one from another.

Moreover, the point symmetry of terbium atoms D_{2d} in the zircon-type polymorph changes to S_4 for scheelite type structure. The increasing density about 10% that takes place in this structural transition has been explained by Kusaba et al. [12] for ZrSiO_4 and more recently by Wang et al. [13] by means a two-step mechanism where a simple shearing coupled with a small displacements of atoms were involved giving as result a more efficient packing in

Table 1
Rietveld refined lattice parameters, atomic positions and reliability factors for the polymorph of the TbCrO_4 oxide.

TbCrO_4	Zircon-type				Scheelite-type			
Space group	$I4_1/\text{amd}$				$I4_1/a$			
Cell parameters	a (Å)				7.1650 (17)			
	c (Å)				6.2282 (15)			
Rietveld R-factors	R_p				0.0204			
	R_{wp}				0.0287			
	χ^2				1.90			
Bragg R-factors	R_B				0.0320			
	R_f				0.0258			
Atoms, wyckoff positions, occupations, x/a , y/b , z/c	R	4a	1	0, 3/4, 1/8	4b	1	0, 1/4, 5/8	
	Cr	4b	1	0, 1/4, 3/8	4a	1	0, 1/4, 1/8	
	O	16h	1	0.0	16f	1	0.2456 (11)	
				0.4399 (8)			0.6104 (16)	
				0.2058 (9)			0.5501 (6)	
Overall tem. factor	0.10 (4)				0.10 (3)			

Table 2Main interatomic distances, bond angles and volume for the zircon and scheelite polymorphs of the TbCrO₄ oxide.

TbCrO ₄	V (Å ³)	d(Cr–O) (Å)	O–Cr–O (°)	d(Tb–O) (Å)	O–Tb–O (°)	Cr–O–Tb (°)
Zircon-type	322.813 (13)	1.727 (4) × 4	112.3 (2) × 2 103.9 (2) × 4	2.279 (6) × 4 2.481 (5) × 4	154.24 (16) × 2 134.46 (15) × 4	92.85 (16) × 4 66.38 (15) × 2
Scheelite-type	287.965 (10)	1.690 (7) × 4	119.5 (7) × 2 104.7 (7) × 4	2.354 (6) × 4 2.447 (7) × 4	137.6 (5) × 2 131.5 (5) × 4	97.5 (4) × 4 70.2 (2) × 2

Fig. 3. Thermal variation of the magnetic susceptibility for the zircon-type TbCrO₄ polymorph.

the scheelite form due to the cooperative rotation of the tetrahedral polyhedra. Furthermore, structural refinements show that the Cr–O and Tb–O distances do not change very much in both polymorphs, but there are remarkable changes in O–Cr–O and Cr–O–Tb bond angles between the zircon and scheelite polymorphs that are the responsible of the mentioned increase in the density in the zircon–scheelite transition (see Table 2).

3.2. Magnetic properties

Figs. 3 and 4 show the thermal variation of the magnetic susceptibility for the zircon- and scheelite-type TbCrO₄ polymorphs, respectively. In both cases the magnetic susceptibility follows a

Fig. 4. Magnetic susceptibility as a function of the temperature for the scheelite-type TbCrO₄ polymorph.

Curie–Weiss behavior of the type $\chi = C/T - \theta$ between 50 and 300 K, where C is the Curie constant and θ denotes the Weiss constant ($\theta_{\text{Zircon}} = 7.31$ K; $\theta_{\text{Scheelite}} = -1.94$ K). The obtained effective magnetic moment for both compounds is $9.6 \mu_B$, after discounting the value expected for Cr⁵⁺ which is $1.63 \mu_B$, which agrees well with the calculated for the ⁷F₆ ground state associated to the free ion Tb³⁺. However, at low temperature dramatic changes have been observed in the magnetic behavior. In this sense, in the case of the zircon-type TbCrO₄ polymorph (Fig. 3), a sudden jump is observed in the susceptibility at 22 K which is indicative of the onset of ferromagnetic interactions. This behavior has been confirmed from our recent neutron diffraction results where the terbium and chromium sublattices are ferromagnetic aligned along the c-axis of the zircon-type structure [10]. By contrast, in the case of the scheelite polymorph the observed net maximum at 29 K in the magnetic susceptibility (Fig. 4), indicates the presence of antiferromagnetic interactions. The small increasing found in the susceptibility below 10 K are due to presence of a small amount of TbCrO₃, around 8%, also detected from X-ray diffraction and included in the Rietveld refinement as it can be observed in Fig. 1 [14].

Magnetization measurements performed at different temperatures for the scheelite-type TbCrO₄ polymorph are shown in Fig. 5. It can be observed that the isotherm obtained at 40 K exhibits a lineal behavior as it was expected above the ordering temperature. However, the corresponding M vs. H plots obtained below the ordering temperature shows a S-shape feature characteristic for an antiferromagnetic material showing a metamagnetic transition. The critical field of such a metamagnetic transition is 2.6 T.

Recent results obtained from neutron diffraction experiments confirm this antiferromagnetic behavior, and the Néel temperature determined from the thermal evolution of the integrated intensities of the (0 1 1) and (1 1 0) reflections is almost coincident with the estimated one from the magnetic susceptibility measurements (see

Fig. 5. Magnetization versus magnetic field plots at different temperatures for scheelite-type TbCrO₄ polymorph.

Fig. 5). We are currently analyzing these data in order to determine the magnetic structure that presents this new scheelite polymorph of TbCrO_4 oxide [15].

The analysis of the structure of both polymorphs will be very important to explain the different magnetic behavior that they present. As it was reported in a previous paper [8] the main operative pathway through these interactions take place is of superexchange-type $\text{Tb}^{3+}\text{--O--Cr}^{5+}$ in which the $[\text{CrO}_4]$ and $[\text{TbO}_8]$ polyhedra are involved. It can be observed that both Cr–O and Tb–O distances do not change very much from zircon to scheelite polymorph by contrast important changes are observed in the Cr–O–Tb angles which could be considered as the main parameter to justify the change of the sign of the magnetic interaction in going from zircon to scheelite (see Table 2).

4. Conclusions

The scheelite-type TbCrO_4 has been obtained from the zircon polymorph at 40 kbar and 833 K. This new polymorph shows antiferromagnetic behavior ($T_N = 29$ K) while the zircon form is ferromagnetic ($T_C = 22$ K). The change of the sign of magnetic interactions has been explained taking into account the changes in the bond angles and distances through the superexchange $\text{Tb}^{3+}\text{--O--Cr}^{5+}$ pathways going from zircon to scheelite.

Acknowledgment

We acknowledge financial support from MEC, project MAT 2003-08465-CO1-02.

References

- [1] E. Jiménez, N.H. Van Dijk, W.H. Kraan, P.C.M. Gubbens, J. Isasi, R. Sáez Puche, J. Magn. Magn. Mater. 288 (2005) 1.
- [2] R. Sáez Puche, E. Jiménez, J. Isasi, M.T. Fernández Díaz, J.L. García Muñoz, J. Solid State Chem. 171 (2003) 161.
- [3] J.D. Carter, H.U. Anderson, M.G. Shumsky, J. Mater. Sci. 31 (1996) 551.
- [4] G. Buisson, F. Bertaut, J. Mareschal, C. R. Acad. Sci. Paris 259 (1964) 411.
- [5] E. Jiménez, J. Isasi, R. Sáez Puche, J. Alloys Compd. 323–324 (2001) 115.
- [6] V.S. Stubican, R. Roy, Zeitschrift für Kristallogr. 119S (1963) 90.
- [7] S.J. Duclos, A. Jayaraman, G.P. Espinosa, A.S. Cooper, R.G. Maines, J. Phys. Chem. Solids 50 (1) (1989) 769.
- [8] E. Climent, J. Romero de Paz, J.M. Gallardo Amores, R. Sáez Puche, Solid State Sci. 9 (2007) 574–579.
- [9] Y.W. Long, L.X. Yang, Y. Yu, F.Y. Li, R.C. Yu, C.Q. Jin, Phys. Rev. B 75 (2007) 104402.
- [10] E. Jiménez, Doctoral thesis, Universidad Complutense de Madrid, June 2005.
- [11] J. Rodríguez-Carvajal, T. Roisnel, *FullProf*, *WinPLOTR*, and accompanying programs, 2005. <http://www-llb.ccea.fr/fullweb/powder.htm>.
- [12] K. Kusaba, T. Yagi, M. Kikuchi, Y. Syono, J. Phys. Chem. Solids 47 (1986) 675.
- [13] X. Wang, I. Loa, K. Syassen, M. Hanfland, B. Ferraud, Phys. Rev. B 70 (2004) 064109.
- [14] F.E. Bertaut, J. Mareschal, R. Pauthenet, J.P. Rebouillat, Bull. Soc. Franc. Ceram. (1966) 43.
- [15] E. Climent, R. Sáez Puche, J. Romero, L. Chappon, unpublished results.

Stability of cyclopentadienyl aryloxy complexes of calcium and barium

Melanie J. Harvey, David J. Burkey, Stephen C. Chmely, Timothy P. Hanusa*

Department of Chemistry, Vanderbilt University, Nashville, TN 37235, United States

ARTICLE INFO

Article history:

Received 6 June 2008

Received in revised form 6 August 2008

Accepted 25 August 2008

Available online 17 November 2008

To Professor William J. Evans, a mentor and friend.

Keywords:

Chemical synthesis

Crystal structure

X-ray diffraction

ABSTRACT

The synthesis of mono(cyclopentadienyl)aryloxy complexes of calcium and barium has been investigated. The reaction of $\text{ICa}(\text{ODipp})(\text{thf})_4$ ($\text{ODipp} = [2,6\text{-}i\text{-Pr-OC}_6\text{H}_3\text{O}]^-$) with $\text{K}[\text{C}_5\text{Me}_5]$, $(\text{Cp}^{3\text{Si}})_2\text{Ca}$ ($\text{Cp}^{3\text{Si}} = \text{C}_5(\text{SiMe}_3)_3\text{H}_2$) with $\text{K}(\text{ODipp})$, and $\text{IBa}(\text{BHT})(\text{thf})_3$ ($\text{BHT} = [2,6\text{-}t\text{-Bu-4-Me-C}_6\text{H}_2\text{O}]^-$) with $\text{K}[\text{C}_5\text{Me}_5]$ in THF produces $\text{Cp}^*\text{Ca}(\text{ODipp})(\text{thf})_3$, $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{ODipp})(\text{thf})_2$, and $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$, respectively. The crystal structures of the two monomeric calcium complexes are reported. All three compounds are stable against Schlenk rearrangement in THF and aromatic solvents. DFT calculations suggest that the presence of THF has less of an effect on the thermodynamics of Schlenk rearrangements of the aryloxy systems than it does on comparable Cp^*CaI compounds.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Half-sandwich cyclopentadienyl complexes (Cp^*MX) serve as useful synthons for the stoichiometric [1–3] and catalytic [4,5] chemistry of the heavy alkaline-earth metals calcium, strontium, and barium. Nevertheless, the highly electropositive character of these metals and the lack of valence electrons in their cations are associated with high kinetic lability in many Cp^*MX compounds [6]. Archetypal examples include $\text{Cp}^*\text{CaI}(\text{thf})_n$ ($\text{Cp}^* = \text{C}_5\text{Me}_5$ or $\text{C}_5\text{Me}_4\text{Et}$) complexes, which undergo Schlenk-type rearrangement in THF solution to form 2:1:1 mixtures of $\text{Cp}^*\text{CaI}(\text{thf})_n$, Cp^*_2Ca , and CaI_2 , respectively [7,8]. The position of equilibrium can be shifted somewhat by the solvent (aromatic solvents favor the heteroleptic species) and by the use of “encapsulating” cyclopentadienyl rings such $\text{C}_5(i\text{-Pr})_4\text{H}$ ($=\text{Cp}^{4i}$) [1,3], $\text{C}_5(\text{SiMe}_3)_3\text{H}_2$ ($=\text{Cp}^{3\text{Si}}$) [2] and $\text{C}_5(t\text{-Bu})_3\text{H}_2$ [9], which sterically interfere with the rearrangement process. The identity of the X ligand in Cp^*CaX complexes also affects the position of Schlenk equilibrium, and the present work demonstrates how the use of aryloxy ligands can make possible the isolation of rearrangement-resistant complexes in the absence of encapsulating Cp^* rings or with easily displaceable Cp^* rings such as $\text{Cp}^{3\text{Si}}$.

2. Experimental

2.1. General considerations

All manipulations were performed with the rigorous exclusion of air and moisture using high vacuum, Schlenk, or drybox techniques. Proton (^1H) and carbon (^{13}C) NMR spectra were obtained on a Bruker NR-300 spectrometer at 300 and 75.5 MHz, respectively, and were referenced to the residual resonances of C_6D_6 (δ 7.15 and 128.0) or $\text{THF-}d_8$ (δ 3.58 and 67.4). Infrared data were measured with KBr pellets as previously described [10]. Elemental analyses were performed by Desert Analytical Laboratory, Tucson, AZ or by Oneida Research Services, Whitesboro, NY.

2.2. Materials

2,6-Diisopropylphenol (HODipp) and potassium hydride were purchased from Aldrich. $\text{K}[\text{Cp}^{3\text{Si}}]$ [11], $(\text{Cp}^{3\text{Si}})_2\text{Ca}$ [9] and $\text{IBa}(\text{BHT})(\text{thf})_3$ [12] were prepared as previously described. $\text{K}(\text{ODipp})$ and KCp^* ($\text{Cp}^* = \text{C}_5\text{Me}_5$) were prepared from potassium hydride and HODipp or HCp^* , respectively. $\text{ICa}(\text{ODipp})(\text{thf})_4$ was prepared from the reaction of CaI_2 and $\text{K}(\text{ODipp})$ in THF [13]. Solvents for reactions were distilled under nitrogen from sodium or potassium benzophenone ketyl. NMR solvents were vacuum distilled from Na/K (22/78) alloy and stored over type 4A molecular sieves.

2.3. Synthesis of $\text{Cp}^*\text{Ca}(\text{ODipp})(\text{thf})_3$

$\text{ICa}(\text{ODipp})(\text{thf})_4$ (0.781 g, 1.23 mmol) and KCp^* (0.215, 1.23 mmol) were dissolved in THF (20 mL), and the reaction mixture was stirred overnight. The precipitate was allowed to settle, and the clear supernatant solution was decanted. The solution was concentrated under vacuum until the volume was reduced to about 5 mL. Slow evaporation of the remaining solvent under ambient pressure resulted in the isolation of 0.474 g (60% yield) of $\text{Cp}^*\text{Ca}(\text{ODipp})(\text{thf})_3$ as air-sensitive, colorless crystals, mp 48–50 °C. Acceptable elemental analysis could not be obtained, perhaps

* Corresponding author. Tel.: +1 615 322 4667; fax: +1 615 343 1234.
E-mail address: t.hanusa@vanderbilt.edu (T.P. Hanusa).

because of the high air-sensitivity of the compound. ^1H NMR (C_6D_6 , 20°C): $\delta = 7.22$ (d, $J = 6$ Hz, 2H, meta-(OAr)), 6.84 (t, $J = 6$ Hz, 1H, para-(OAr)), 2.23 (s, 15H, Cp- CH_3), 1.37 (d, $J = 6$ Hz, 12H, CHMe_2). ^1H NMR ($\text{THF}-d_8$, 20°C): $\delta = 6.70$ (d, $J = 7$ Hz, 2H, meta-(OAr)), 6.18 (t, $J = 7$ Hz, 1H, para-(OAr)), 3.45 (septet, $J = 7$ Hz, 2H, CHMe_2), 2.02 (s, 15H, Cp- CH_3), 1.07 (d, $J = 7$ Hz, 12H, CHMe_2). ^{13}C NMR (75.5 MHz, $\text{THF}-d_8$, 20°C): $\delta = 161.7$ (iPr-C(Ar)), 135.8 (O-C(Ar)), 122.5 (meta-C(Ar)), 112.3 (para-C(Ar)), 111.5 (ring- CCH_3), 25.9 (CH(iPr)), 24.7 (CH_3 (iPr)), 11.6 (Cp- CH_3). Principal IR bands (KBr, cm^{-1}): 2966 (vs, br), 2871 (s), 1587 (w), 1438 (vs), 1342 (br, m), 1263 (m), 1042 (br, s), 885 (w), 748 (w), 543 (br, w). Crystals for X-ray structural analysis were grown by slow evaporation of a saturated THF solution of $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ at room temperature.

2.4. Synthesis of $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$

$(\text{Cp}^{3\text{Si}})_2\text{Ca}$ (0.320 g, 0.53 mmol) and $\text{K}[\text{Odipp}]$ (0.117, 0.54 mmol) were dissolved in THF (40 mL), and the reaction mixture was stirred overnight, evaporated to dryness, and the residue extracted with toluene. The extract was filtered, and the filtrate evaporated to an oil that crystallized upon standing, yielding $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ as air-sensitive, colorless crystals (0.277 g, 81%), mp $102\text{--}104^\circ\text{C}$. Anal. Calcd. for $\text{C}_{34}\text{H}_{62}\text{CaO}_3\text{Si}_3$: C, 63.49; H, 9.72. Found: C, 64.27; H, 9.87. ^1H NMR ($\text{THF}-d_8$, 20°C): $\delta = 6.92$ (s, 2H, ring-CH), 6.72 (d, $J = 7$ Hz, 2H, meta-(OAr)), 6.26 (t, $J = 7$ Hz, 1H, para-(OAr)), 3.35 (septet, $J = 7$ Hz, 2H, CHMe_2), 1.12 (d, $J = 7$ Hz, 12H, CHMe_2), 0.31 (s, 18H, $\text{Si}(\text{CH}_3)_3$), 0.16 (s, 9H, $\text{Si}(\text{CH}_3)_3$). ^{13}C NMR (75.5 MHz, $\text{THF}-d_8$, 20°C): $\delta = 160.9$ (iPr-C(Ar)), 135.7 (O-C(Ar)), 131.3 (2C, ring-CH), 126.8 (ring- $\text{CSi}(\text{CH}_3)_3$), 122.7 (ring- $\text{CSi}(\text{CH}_3)_3$), 122.5 (meta-C(Ar)), 113.3 (para-C(Ar)), 26.5 (CH(iPr)), 24.6 (CH_3 (iPr)), 2.6 ($\text{Si}(\text{CH}_3)_3$), 1.1 ($\text{Si}(\text{CH}_3)_3$). Principal IR bands (KBr, cm^{-1}): 2952 (vs, br), 2895 (s), 1587 (w), 1434 (vs), 1345 (m), 1281 (m), 1248 (s, sh), 1093 (m), 1028 (s), 942 (w), 844 (vs, br), 748 (s), 687 (m), 420 (s). Crystals for X-ray structural analysis were grown by slow evaporation of a saturated toluene solution of $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ at room temperature.

2.5. Synthesis of $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$

$\text{IBa}(\text{BHT})(\text{thf})_3$ (0.82 g, 1.17 mmol) and KCp^* (0.20 g, 1.17 mmol) were combined in 20 mL of THF in an Erlenmeyer flask. The white reaction mixture was stirred for 8 h and then set aside to allow the precipitate to settle. The clear supernatant liquid was transferred to another flask with a pipet and the THF was removed under vacuum to a volume of 2 mL; a white solid precipitated as the THF was removed. The remaining THF solution was decanted, and the solid was allowed to dry at ambient pressure, giving 0.51 g (77% yield) of $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$ as an ivory powder. Anal. Calcd. for $\text{C}_{29}\text{H}_{46}\text{BaO}_2$: C, 61.76; H, 8.22; Ba, 24.35. Found: C, 62.44; H, 8.45; Ba, 24.59. ^1H NMR (C_6D_6): δ 7.19 (s, 2H, Ar-H); 3.54 (t, $J = 6.5$ Hz, 4H, $\alpha\text{-C}_4\text{H}_8\text{O}$); 2.41 (br s ($\omega_{1/2} = 30$ Hz), 3H, Ar- CH_3); 1.79 (br s ($\omega_{1/2} = 60$ Hz), 15H, Cp- CH_3); 1.52 (br s ($\omega_{1/2} = 30$ Hz), 18H, Ar-C(CH_3)); 1.39 (m, 4H, $\beta\text{-C}_4\text{H}_8\text{O}$). ^1H NMR ($\text{THF}-d_8$): δ 6.61 (br s, 2H, Ar-H); 3.60 (m, 4H, $\alpha\text{-C}_4\text{H}_8\text{O}$); 2.04 (br s, 3H, Ar- CH_3); 1.94 (br, partially resolved doublet, 15H, Cp- CH_3); 1.76 (m, 4H, $\beta\text{-C}_4\text{H}_8\text{O}$); 1.35 (br, partially resolved doublet, 18H, Ar-C(CH_3)). ^{13}C NMR ($\text{THF}-d_8$): δ 165.7 (Ar-1); 136.2 (Ar-2,6); 125.0 (Ar-3,5); 120.3 (Ar-4); 112.8 (Cp ring- CCH_3); 68.2 ($\alpha\text{-C}_4\text{H}_8\text{O}$); 35.3 (Ar-C(CH_3)); 31.9 (Ar-C(CH_3)); 26.4 ($\beta\text{-C}_4\text{H}_8\text{O}$); 21.6 (Ar- CH_3); 11.5 (Cp- CH_3). Principal IR bands (KBr, cm^{-1}): 2901 (s, vbr), 2723 (m, sh), 1602 (w), 1548 (w), 1421 (s), 1380 (s), 1343 (m), 1286 (s, br), 1216 (m), 1199 (m), 1035 (s), 886 (s), 818 (s), 800 (s), 667 (w), 577 (w), 498 (m).

2.6. X-ray crystallography

Data collection and structure solution were conducted at the X-ray Crystallographic Laboratory at the University of Minnesota. Details of the data collection and refinement can be found in Section 5.

2.7. Computational details

All calculations were performed with the Gaussian 03W suite of programs [14]. For geometry optimization and energy calculations, the B3PW91 functional, which incorporates Becke's three-parameter exchange functional [15] with the 1991 gradient-corrected correlation functional of Perdew and Wang [16] was used. For C, H, and O, the standard 6-31G(d) basis set was used. For Ca, the TZV basis of Ahlrich [17] was supplemented with five d functions (the diffuse d ($\alpha = 0.013$) was not included); [18] for Ba and I, the Stuttgart/Dresden ECPs were employed [19]. Frequency calculations confirmed that structures were either minima on their potential energy surfaces or, in the case of the some barium complexes and solvated calcium species, had relatively minor ($< -24\text{ cm}^{-1}$) imaginary frequencies. In the latter case, structures were reoptimized using an ultrafine grid, which left only positive or very small negative ($< -9\text{ cm}^{-1}$) frequency values. The same grid type (regular or ultrafine) was used for the energy calculations in the separate reactions.

3. Results and discussion

3.1. Synthesis of $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$

The reaction of $\text{ICa}(\text{Odipp})(\text{thf})_4$ with one equivalent of KCp^* generates the mono(ring)calcium aryloxide complex $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ (Eq. (1)).

The compound was characterized with spectroscopic methods and X-ray crystallography. It is stable against rearrangement in both THF and aromatic solvents.

3.2. Synthesis of $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$

The stability of $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ suggests that related $[\text{Odipp}]^-$ -containing complexes with other Cp' rings should also be stable. In fact, early attempts to isolate $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_n$ from the reaction of $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{thf})$ and $\text{K}[\text{Odipp}]$ were unsuccessful, owing to facile ring loss from calcium (Eq. (2)) [2]. A reinvestigation of the system indicates that the direct reaction of $\text{K}[\text{Cp}^{3\text{Si}}]$ and $\text{ICa}(\text{Odipp})(\text{thf})_4$ does form the mono(ring)calcium aryloxide complex $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_n$, but in low yield (23%; Eq. (3)); the majority of the starting materials remains unreacted. When the same reactants are mixed in toluene, $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_n$ is produced in 63% yield, but $\text{K}[\text{Cp}^{3\text{Si}}]$ and $\text{ICa}(\text{Odipp})(\text{thf})_n$ are also present in the reaction mixture (Eq. (4)).

An effective synthesis for $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_n$ was found in the reaction of $(\text{Cp}^{3\text{Si}})_2\text{Ca}$ [9] with $\text{K}[\text{Odipp}]$ (Eq. (5)).

With this approach, the potassium cyclopentadienide is intentionally formed and can subsequently be removed from the desired product by extraction with toluene. $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ was characterized with spectroscopic methods and X-ray crystallography. The ^1H NMR resonances for the $[\text{Cp}^{3\text{Si}}]^-$ and $[\text{Odipp}]^-$ ligands are shifted from those of the corresponding homoleptic compounds [9]. As with the related mono(ring) alkaline-earth iodide $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{thf})$, the aryloxide derivative is resistant to ligand redistribution in both THF and aromatics.

3.3. Synthesis of $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$

The reaction of $\text{IBa}(\text{BHT})(\text{thf})_3$ with one equiv of KCp^* generates the off-white mono(ring)barium alkoxide complex $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$ (Eq. (6)). As with the other heteroleptic alkaline-earth alkoxides described above, the mono(ring) complex was isolated by precipitation from small volumes of THF.

Satisfactory elemental analysis was obtained for the compound, and spectroscopic data (^1H and ^{13}C NMR, IR) were consistent with its proposed formulation. Attempts to obtain crystals of

Fig. 1. ORTEP diagrams of $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ (a) and $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ (b), with thermal ellipsoids drawn at the 50% level. Hydrogen atoms have been omitted for clarity.

$\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$ suitable for an X-ray structural analysis have been unsuccessful.

The proton NMR resonances for the $[\text{Cp}^*]^-$ and $[\text{BHT}]^-$ ligands in both C_6D_6 and $\text{THF}-d_8$ are shifted from those of the corresponding homoleptic compounds [20,21]. Interestingly, the peaks of the ^1H NMR spectra in both solvents are substantially broadened; such broadening is especially unusual for the methyl proton resonance of the $[\text{Cp}^*]^-$ ligand ($\omega_{1/2}$ as high as 60 Hz), which is normally a sharp singlet in related compounds [22,23]. It is possible that the wider lines reflect some aggregation in solution; no broadening of the resonances is observed in the ^{13}C NMR spectra of the complex in $\text{THF}-d_8$, however. Also unusual is the upfield shift observed for the $[\text{Cp}^*]^-$ resonance in C_6D_6 (1.79 ppm), when compared to the analogous peak for the metallocene Cp_2Ba (1.97 ppm). This contrasts with that of the corresponding mono(ring) complexes of calcium $\text{Cp}^*\text{CaX}(\text{thf})_n$, which have $[\text{Cp}^*]^-$ resonances shifted downfield from the same peak for Cp^*_2Ca [7,8].

C_6D_6 and $\text{THF}-d_8$ solutions of isolated $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$ allowed to stand for up to 72 h under ambient conditions do not exhibit any noticeable changes in their ^1H NMR spectra. However, removal of toluene from a solution of $\text{Cp}^*\text{Ba}(\text{BHT})(\text{thf})$ under vacuum leads to partial desolvation and subsequent decomposition of the complex in solution, as proton NMR spectra (C_6D_6) now contain resonances for the corresponding homoleptic products $\text{Cp}^*_2\text{Ba}(\text{thf})_n$ [23] and $\text{Ba}(\text{BHT})_2(\text{thf})_n$ [21].

3.4. Solid state structure of $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3 \cdot \text{THF}$

$\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ crystallizes from THF solution as a monomer in which each calcium atom is coordinated by one $\eta^5\text{-Cp}^*$ ring, one $[\text{Odipp}]^-$ ligand, and three thf molecules; a THF of crystallization is also present in the lattice (Fig. 1a). The $\text{Ca}-\text{O}(\text{aryloxide})$ bond distance of 2.177(2) Å is comparable to that of 2.1063(16) Å in $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ when the difference in the radii between 6- and 7-coordinate Ca^{II} (1.00 Å and 1.06 Å, respectively) is considered [24]. The average $\text{Ca}-\text{C}(\text{ring})$ and the $\text{Ca}-\text{centroid}$ bond lengths of 2.731(8) Å and 2.45 Å are longer than those in $[\text{Cp}^*\text{Ca}(\text{thf})_2]_2$ (2.67(1) Å) [7]. The average $\text{Ca}-\text{O}(\text{thf})$ distance of 2.443(5) Å is also slightly longer than the average $\text{Ca}-\text{O}(\text{thf})$ distances of 2.422(6) Å and 2.387(7) Å in $[\text{Cp}^*\text{Ca}(\text{thf})_2]_2$.

3.5. Solid state structure of $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$

$(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_2$ crystallizes from THF solution as a monomer in which each calcium atom is coordinated by one $\eta^5\text{-Cp}^{3\text{Si}}$ ring, one $[\text{Odipp}]^-$ ligand, and two thf molecules (Fig. 1b). The average $\text{Ca}-\text{C}(\text{ring})$ and the $\text{Ca}-\text{centroid}$ bond distances of 2.706(4) and 2.42 Å are slightly longer than those in $[(\text{Cp}^{3\text{Si}})\text{Ca}(\text{thf})_2]_2$ (2.65(4) and 2.36(2) Å), $[(\text{C}_5(\text{tBu})_3\text{H}_2)\text{Ca}(\text{thf})_2]_2$ (2.677(4) and 2.39 Å), and $\{[(\text{C}_5(\text{tBu})_3\text{H}_2)\text{Ca}(\text{thf})_2]_2\}$ (2.63(2) Å and 2.34 Å) [25]. This lengthening is similar to that observed in $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$. As noted above, the $\text{Ca}-\text{O}(\text{aryloxide})$ bond distance in $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_3$ of 2.1063(16) Å is comparable with the analogous distance observed in $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ when the difference in coordination number-adjusted radii Ca^{II} are considered [24]. The same is true of the average $\text{Ca}-\text{O}(\text{thf})$ distances (i.e., 2.36(2) Å in $(\text{Cp}^{3\text{Si}})\text{Ca}(\text{Odipp})(\text{thf})_3$; 2.443(5) Å in $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$). The $\text{Ca}-\text{O}(1)-\text{C}(1)$ angle of 166.76(16)° is indistinguishable from the analogous angle in $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3$ (166.6(2)°), suggesting that the steric interactions between the aryloxide and thf ligands are similar in the two complexes [12].

3.6. Computational results

The energetics of the exchange reactions of the mono(aryloxide) complexes were studied with model systems and DFT methods. As a first level of approximation, the models were kept as simple as possible ($\text{Cp}' = \text{C}_5\text{H}_5$; $\text{OAr} = \text{OC}_6\text{H}_5$) to remove undue influence from steric effects. The dissociation of CpCaOPh into Cp_2Ca and $\text{Ca}(\text{OPh})_2$ is found to be slightly endothermic ($\Delta H^\circ = +3.8 \text{ kcal mol}^{-1}$) and nonspontaneous ($\Delta G^\circ = +4.8 \text{ kcal mol}^{-1}$) (Fig. 2). The same reaction with barium ($2 \text{ CpBaOPh} \rightleftharpoons \text{Cp}_2\text{Ba}$ and $\text{Ba}(\text{OPh})_2$) is essentially thermoneutral ($\Delta H^\circ = -0.7 \text{ kcal mol}^{-1}$) but still nonspontaneous ($\Delta G^\circ = +3.9 \text{ kcal mol}^{-1}$). Adding a THF molecule to each complex (i.e., $2 \text{ CpMOPh}(\text{thf}) \rightleftharpoons \text{Cp}_2\text{M}(\text{thf}) + \text{M}(\text{OPh})_2(\text{thf})$) leaves the energetics of CpMOPh exchange essentially unaltered ($\Delta H^\circ = +3.8 \text{ kcal mol}^{-1}$; $\Delta G^\circ = +3.3 \text{ kcal mol}^{-1}$ for $\text{M} = \text{Ca}$; $\Delta H^\circ = +1.7 \text{ kcal mol}^{-1}$; $\Delta G^\circ = +3.0 \text{ kcal mol}^{-1}$ for $\text{M} = \text{Ba}$). The energetics of an even more fully solvated calcium system are not appreciably different; for

Fig. 2. Calculated structures for the organocalcium species (see the text). The structures of the barium analogues are similar, but with ca. 15% longer M–L bond lengths.

the reaction $2 \text{ CpCaOPh}(\text{thf})_2 \rightleftharpoons \text{Cp}_2\text{Ca}(\text{thf})_2 + \text{Ca}(\text{OPh})_2(\text{thf})_2$, $\Delta H^\circ = +3.4 \text{ kcal mol}^{-1}$ and $\Delta G^\circ = +5.6 \text{ kcal mol}^{-1}$.

Analogous calculations on the $2 \text{ CpCa}(\text{thf})_n \rightleftharpoons \text{Cp}_2\text{Ca}(\text{thf})_n + \text{Ca}_2(\text{thf})_n$ system reveal a more substantial change in the free energy on the addition of THF. For the unsolvated system, $\Delta G^\circ = +15.9 \text{ kcal mol}^{-1}$; with one THF ligand on each metal center, ΔG° decreases to $+9.6 \text{ kcal mol}^{-1}$. The fully solvated reaction $2 \text{ CpCa}(\text{thf})_3 \rightleftharpoons \text{Cp}_2\text{Ca}(\text{thf})_2 + \text{Ca}_2(\text{thf})_4$ is both exothermic ($\Delta H^\circ = -5.5 \text{ kcal mol}^{-1}$) and spontaneous ($\Delta G^\circ = -7.0 \text{ kcal mol}^{-1}$), which is consistent with the observation of extensive Schlenk equilibrium in THF solutions of mono(cyclopentadienyl)calcium iodides [7,8]. Although a larger variety of systems need to be studied to extend this point, evidently the addition of solvent has less of an effect on the thermodynamics of the aryloxide systems than on their iodide counterparts.

4. Conclusions

Cyclopentadienyl mono(aryloxide) complexes provide a unique platform for studying the organometallic chemistry of the heavier alkaline-earth metals. Although the use of sterically demanding, “encapsulating” cyclopentadienyl rings can be used to produce $\text{Cp}'\text{MX}(\text{thf})_n$ complexes that are resistant to rearrangement reactions in solution (this includes $\text{X} = \text{aryloxide}$ [1]), the present work demonstrates that such bulky rings are not always necessary with aryloxide derivatives. As the bonding in these systems is considered highly polar, the enhanced stability compared to related cyclopentadienyl iodide compounds may be attributed to the superior match of the hard, Lewis acidic metal center with the hard, basic aryloxide ligand rather than to the softer iodide ligand. This phenomenon, also observed in the ability of neutral phosphine oxide ligands to displace a charged iodide ligand from calcium [26], should be an important principle in the design of new organoalkaline-earth systems.

5. Supplementary material

Crystallographic data (excluding structure factors) have been deposited with the Cambridge Crystallographic Data Centre,

CCDC 690299 and 690300, for $\text{Cp}^*\text{Ca}(\text{Odipp})(\text{thf})_3 \cdot \text{THF}$ and $(\text{Cp}^{351})\text{Ca}(\text{Odipp})(\text{thf})_2$, respectively. Copies of this information may be obtained free of charge from The Director, CCDC, 12 Union Road, Cambridge, CB2 1EZ, UK (Fax: +44-1223-336033; e-mail: deposit@ccdc.cam.ac.uk or <http://www.ccdc.cam.ac.uk>).

Acknowledgements

We thank the National Science Foundation for support of this research. Dr. Maren Pink and Dr. Victor G. Young, Jr. of the X-ray Crystallographic Laboratory, Chemistry Department, University of Minnesota, Minneapolis, Minnesota are thanked for the collection and refinement of crystallographic data.

References

- [1] D.J. Burkey, E.K. Alexander, T.P. Hanusa, *Organometallics* 13 (1994) 2773.
- [2] M.J. Harvey, T.P. Hanusa, *Organometallics* 19 (2000) 1556.
- [3] H. Sitzmann, F. Weber, M.D. Walter, G. Wolmershaeuser, *Organometallics* 22 (2003) 1931.
- [4] A. Weeber, S. Harder, H.H. Brintzinger, K. Knoll, *Organometallics* 19 (2000) 1325.
- [5] S. Harder, F. Feil, A. Weeber, *Organometallics* 20 (2001) 1044.
- [6] T.P. Hanusa, in: Crabtree, Mingos (Eds.), *Comprehensive Organometallic Chemistry-III*, Elsevier, Oxford, 2007.
- [7] M.J. McCormick, S.C. Sockwell, C.E.H. Davies, T.P. Hanusa, J.C. Huffman, *Organometallics* 8 (1989) 2044.
- [8] S.C. Sockwell, T.P. Hanusa, J.C. Huffman, *J. Am. Chem. Soc.* 114 (1992) 3393.
- [9] M.J. Harvey, K.T. Quisenberry, T.P. Hanusa, V.G. Young Jr., *Eur. J. Inorg. Chem.* (2003) 3383.
- [10] R.A. Williams, K.F. Tesh, T.P. Hanusa, *J. Am. Chem. Soc.* 113 (1991) 4843.
- [11] M.J. Harvey, T.P. Hanusa, M. Pink, *J. Chem. Soc. Dalton Trans.* (2001) 1128.
- [12] K.F. Tesh, D.J. Burkey, T.P. Hanusa, *J. Am. Chem. Soc.* 116 (1994) 2409.
- [13] Details of the synthesis and structure of $\text{ICa}(\text{Odipp})(\text{thf})_4$ will be reported elsewhere.
- [14] M.J. Frisch, G.W. Trucks, H.B. Schlegel, G.E. Scuseria, M.A. Robb, J.R. Cheeseman, J.A. Montgomery, Jr., T. Vreven, K.N. Kudin, J.C. Burant, J.M. Millam, S.S. Iyengar, J. Tomasi, V. Barone, B. Mennucci, M. Cossi, G. Scalmani, N. Rega, G.A. Petersson, H. Nakatsuji, M. Hada, M. Ehara, K. Toyota, R. Fukuda, J. Hasegawa, M. Ishida, T. Nakajima, Y. Honda, O. Kitao, H. Nakai, M. Klene, X. Li, J.E. Knox, H.P. Hratchian, J.B. Cross, C. Adamo, J. Jaramillo, R. Gomperts, R.E. Stratmann, O. Yazyev, A.J. Austin, R. Cammi, C. Pomelli, J.W. Ochterski, P.Y. Ayala, K. Morokuma, G.A. Voth, P. Salvador, J.J. Dannenberg, V.G. Zakrzewski, S. Dapprich, A.D. Daniels, M.C. Strain, O. Farkas, D.K. Malick, A.D. Rabuck, K. Raghavachari, J.B. Foresman, J.V. Ortiz, Q. Cui, A.G. Baboul, S. Clifford, J. Cioslowski, B.B. Stefanov, G. Liu, A. Liashenko, P. Piskorz, I. Komaromi, R.L. Martin, D.J. Fox, T. Keith, M.A. Al-Laham, C.Y. Peng, A. Nanayakkara, M. Challacombe, P.M.W. Gill, B. Johnson, W. Chen,

- M.W. Wong, C. Gonzalez, J.A. Pople, Gaussian 03, Revision E.1, Gaussian, Inc., Pittsburgh, PA, 2003.
- [15] A.D. Becke, *J. Chem. Phys.* 98 (1993) 5648.
- [16] J.P. Perdew, Y. Wang, *Phys. Rev. B* 45 (1992) 13244.
- [17] A. Schafer, C. Huber, R. Ahlrichs, *J. Chem. Phys.* 100 (1994) 5829.
- [18] C.W. Bauschlicher Jr., S.R. Langhoff, H. Partridge, *J. Chem. Phys.* 84 (1986) 901.
- [19] (a) Barium: M. Kaupp, P.v.R. Schleyer, H. Stoll, H. Preuss, *J. Chem. Phys.* 94 (1991) 1360;
(b) Iodine: G. Igel-Mann, H. Stoll, H. Preuss, *Mol. Phys.* 65 (1988) 1321.
- [20] R.A. Williams, Ph.D. Thesis, Vanderbilt University (1991).
- [21] K.F. Tesh, T.P. Hanusa, J.C. Huffman, C.J. Huffman, *Inorg. Chem.* 31 (1992) 5572.
- [22] C.J. Burns, R.A. Andersen, J. Organomet. Chem. 325 (1987) 31.
- [23] M.J. McCormick, R.A. Williams, L.J. Levine, T.P. Hanusa, *Polyhedron* 7 (1988) 725.
- [24] R.D. Shannon, *Acta Crystallogr. Sect. A* 32 (1976) 751.
- [25] M.J. Harvey, T.P. Hanusa, V.G. Young Jr., *J. Organomet. Chem.* 626 (2001) 43.
- [26] K.C. Jayaratne, L.S. Fitts, T.P. Hanusa, V.G. Young Jr., *Organometallics* 20 (2001) 3638.

Polymorphism in binary rare-earth metal germanides. Synthesis, structure and properties of the new hexagonal forms of Tb_3Ge_5 and Dy_3Ge_5

Paul H. Tobash^a, Svilen Bobev^{a,*}, Joe D. Thompson^b, John L. Sarrao^b

^a Department of Chemistry, University of Delaware, Newark, DE 19716, United States

^b Materials Physics and Application Division (MPA-10), Los Alamos National Laboratory, Los Alamos, NM 87545, United States

ARTICLE INFO

Article history:

Received 12 May 2008

Received in revised form 7 October 2008

Accepted 14 October 2008

Available online 2 December 2008

Keywords:

Rare-earth germanides

Crystal structure

Polymorphism

Magnetic measurements

Tb_3Ge_5

Dy_3Ge_5

ABSTRACT

Reported are the synthesis, crystal structure determination and magnetic properties of new polymorphic forms of the rare-earth metal germanides Tb_3Ge_5 and Dy_3Ge_5 . Both compounds are isostructural and crystallize with the hexagonal space group $P6_2c$ (No. 190, $Z=2$) with unit-cell parameters $a=6.861(2)$ Å; $c=8.339(6)$ Å for Tb_3Ge_5 and $a=6.8387(10)$ Å; $c=8.293(2)$ Å for Dy_3Ge_5 , respectively. The structures are derivatives of the ubiquitous AlB_2 type and can be regarded as its 6-fold superstructure ($a'=a \times 3^{1/2}$ and $c'=c \times 2$), arising from the long range ordering of Ge vacancies. They are therefore best described as flat Ge-layers, stacked in a hexagonal close-packed manner along the crystallographic c -axis, which are separated by layers of rare-earth metal atoms. Magnetic susceptibility measurements reveal that both Tb_3Ge_5 and Dy_3Ge_5 exhibit antiferromagnetic order at temperatures below 23 K and 9 K, respectively.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Rare-earth metal (*RE* hereafter) germanides are intermetallic compounds, whose structures feature copious bonding patterns [1–3]. This is particularly true for the digermanides, many of which were originally thought to be fully stoichiometric REGe_2 binary phases crystallizing with the ubiquitous AlB_2 and $\alpha\text{-ThSi}_2$ structure types [3]. However, this rarely holds true and almost exclusively, non-stoichiometric REGe_{2-x} compounds are formed ($0 \leq x \leq 0.5$) [4–12]. Our recent efforts in exploring this rich structural chemistry have been facilitated through the use of the metal flux method [13] for the synthesis and the crystal growth of several new binary and ternary compounds [4–6,14–18]. On one extreme, we have demonstrated the reactive nature of the metal flux, as evidenced from the formation of the ternary compounds RE_2InGe_2 ($\text{RE}=\text{Sm}, \text{Gd}-\text{Ho}, \text{Yb}$) [14] and $\text{RESn}_{1+x}\text{Ge}_{1-x}$ ($\text{RE}=\text{Y}, \text{Gd}-\text{Tm}$) [16]. On the other side, owing to its function as a solvent, the metal-flux has played a beneficial role in our attempts to synthesize the new Gd_3Ge_4 [6] and RE_3Ge_5 compounds ($\text{RE}=\text{Sm}, \text{Gd}$) [4] or the metastable polymorph of the alkaline-earth phase CaGe_2 [18]. Herein, we exploit again the

utility of the flux method for structural studies within a few more *RE*–Ge binary systems and present the synthesis of two new hexagonal polymorphs of the binary compounds Tb_3Ge_5 and Dy_3Ge_5 , referred hereafter to as their β -forms (the known orthorhombic polymorphs of Tb_3Ge_5 [19] and Dy_3Ge_5 [20] are designated as the α -forms, respectively). Crystals have been grown from their respective elements using In flux, and their structures elucidated from single-crystal X-ray diffraction. Both compounds crystallize in the hexagonal Sm_3Ge_5 type [4] with the space group $P6_2c$ (Pearson's symbol $hP16$). Along with the structural relationship to the AlB_2 type [3], brought about through a long range ordering of vacant Ge sites, discussed as well are the temperature-dependent magnetization measurements on both compounds and a short description of the structural trends across the series.

2. Experimental

2.1. Synthesis

The reactants were pure elements from Alfa (purity > 99.9% metal basis), which were used as received. They were stored and handled inside an argon-filled glove-box with controlled oxygen and moisture levels below 1 ppm or under vacuum. The reaction conditions were identical to those used for the synthesis of the recently reported Sm_3Ge_5 and Gd_3Ge_5 [4]. Stoichiometric mixtures of the elements in a ratio of $\text{RE}:\text{Ge}:\text{In}=3:5:30$ were loaded in alumina crucibles (Coors®, 2 cm³), which were encapsulated in fused silica ampoules. The ampoules were evacuated (*ca.* 10^{-3} Torr) and flame-sealed. The reactions took place in muffle furnaces at 1373 K for 3 h, followed by a cooling step (rate 30°/h) to 773 K, where the flux was removed as described in detail previously [14]. Upon opening the sealed tubes, needle-like

* Corresponding author at: Department of Chemistry and Biochemistry, University of Delaware, Newark, DE 19716, United States. Tel.: +1 302 831 8720; fax: +1 302 831 6335.

E-mail address: bobev@udel.edu (S. Bobev).

crystals were isolated and later characterized by single-crystal and powder X-ray diffraction as being new hexagonal polymorphs of the known compounds Tb₃Ge₅ [19] and Dy₃Ge₅ [20]. Other metal fluxes were also explored – Cd and Pb for example worked as well – but the quality of the grown crystals was inferior. The crystals of Tb₃Ge₅ and Dy₃Ge₅ exhibit a silver-metallic luster and appear air- and moisture-stable over periods of time greater than 1 year.

It was initially found [4], and confirmed by this study, that the cooling rate in the aforementioned flux reactions is of particular importance with regard to the formation of either RE₃Ge₅ polymorph—cooling at slower rates (e.g. 5–10°/h) leads to the formation of the orthorhombic phase, while faster cooling (above) yields the hexagonal phase. This could be understood if one realizes that in molten In (or another suitable metal flux), the rates of nucleation and crystallization are under kinetic control and that upon slow cooling, the slower growing α-RE₃Ge₅ will be the major product; fast cooling will yield the faster growing β-RE₃Ge₅ polymorph as a majority phase. These observations, combined with the fact that polycrystalline samples of β-Tb₃Ge₅ and β-Dy₃Ge₅ could not be made by arc-melting and annealing are suggestive of β-polymorphs being metastable, kinetic phases, whereas the α-forms are the thermodynamically stable phases at ambient pressure and temperature. This conclusion is further corroborated by the irreversible single-crystal to single-crystal phase transition, discussed later on, and confirmed by the exclusive formation of the α-polymorphs by direct fusion of the corresponding elements.

2.2. X-ray diffraction studies

X-ray powder diffraction patterns were taken at room temperature on a Rigaku MiniFlex powder diffractometer using filtered Cu Kα radiation. The typical scans were in θ–θ mode (2θ_{max} = 80°) with a step-size of 0.05° and 10 s/step counting time. The collected powder patterns were used for phase identification only. This was done using the JADE 6.5 software package [21]. The intensities and the positions of the experimental and the calculated from the crystal structures peaks were in excellent agreement.

Single-crystal data collections were carried out on a Bruker SMART CCD diffractometer using monochromated Mo Kα radiation. The crystals were mounted on glass fibers with the aid of Paratone-N oil, which required the use of cryogenic temperatures (120 K in this case) in order for the viscous liquid to freeze and prevent the crystals from moving during the data collection. Full spheres of intensity data for crystals from both compounds were collected in 4 batch runs at different ω and φ angles. Data collections were handled in a routine fashion using the SMART software; the collected frames were integrated using the SAINTplus program [22]. The latter was also used for global unit cell refinement taking into account all reflections. Semi-empirical absorption correction based on equivalents was applied with SADABS [23]. The structures were refined on F² using the SHELX package; the coordinates from the isostructural Sm₃Ge₅ [4] were used as the starting model. In the last refinement cycles, all atomic positions were refined with anisotropic displacement parameters, leading to quick convergences and excellent goodness of fit. Final residuals and other relevant data collection and structural refinement parameters are summarized in Table 1. Positional and equivalent displacement parameters are given in Table 2 along with selected interatomic distances in Table 3. The crystallographic information files (CIF) have also been deposited with Fachinformationszentrum Karlsruhe [76344 Eggenstein, Leopoldshafen, Germany; fax: +49 7247 808 666; email: crysdata@fiz.karlsruhe.de; depositary numbers CSD-419457 (β-Tb₃Ge₅) and CSD-419458 (β-Dy₃Ge₅)]. Since single crystals of the orthorhombic α-Tb₃Ge₅ polymorph were available for first a time, and since its structure had been established before from powder diffraction work only, we carried out structure refinements based on single-crystal X ray diffraction data. The results are not discussed herein, but are in excellent agreement with the earlier Rietveld refinement on the orthorhombic α-Tb₃Ge₅ structure [19]. The corresponding CIF has been deposited under CSD-419459.

2.3. Magnetic measurements

Field-cooled dc magnetization (M) measurements were completed for both compounds using a Quantum Design MPMS SQUID magnetometer. The measurements were taken on single-crystalline samples in the temperature range from 2 K to 350 K and in an applied field (H) of 1000 Oe. The raw magnetization data were corrected for the holder contribution and subsequently converted to molar susceptibility (χ_m = M/H).

3. Results and discussion

3.1. Crystal structure

Only a brief account of the structure of the new hexagonal polymorphs of Tb₃Ge₅ and Dy₃Ge₅ (Pearson's symbol *hP16*) will be given here; for a more comprehensive description and comparison between the structures of the two polymorphs, we refer the reader to the report on similar dimorphism in Sm₃Ge₅ [4].

Table 1

Selected single-crystal collection and refinement parameters for Tb₃Ge₅ and Dy₃Ge₅.

Empirical formula	Tb ₃ Ge ₅	Dy ₃ Ge ₅
Formula weight	839.71	850.45
Space group, Z		<i>P</i> 6 ₂ <i>c</i> , 2
Radiation, λ		Mo Kα, 0.71073 Å
Temperature		120 K
Unit-cell parameters		
<i>a</i> (Å)	6.861(2)	6.8387(10)
<i>c</i> (Å)	8.339(6)	8.293(2)
<i>V</i> (Å ³)	340.0(3)	335.90(12)
Crystal size	40 μm × 40 μm × 30 μm	50 μm × 40 μm × 40 μm
ρ _{calc} (g/cm ³)	8.203	8.408
μ (cm ^{−1})	524.16	548.38
Data/parameter	262/18	261/18
absorption correction method	Semi-empirical, based on equivalents	
Final R1 ^a (<i>I</i> > 2σ _{<i>I</i>})	R1 = 0.0193 wR2 = 0.0388	R1 = 0.0195 wR2 = 0.0469
Final wR2 ^b (<i>I</i> > 2σ _{<i>I</i>})	R1 = 0.0258 wR2 = 0.0419	R1 = 0.0265 wR2 = 0.0510
Largest peak/hole	0.89/−1.20 e [−] /Å ³	0.80/−1.29 e [−] /Å ³

^a $R1 = \sum ||F_o| - |F_c|| / \sum |F_o|$.
^b $wR2 = [\sum [w(F_o^2 - F_c^2)^2] / \sum [w(F_o^2)^2]]^{1/2}$, where $w = 1/[\sigma^2 F_o^2 + (A \cdot P)^2 + B \cdot P]$, $P = (F_o^2 + 2F_c^2)/3$; A and B: weight coefficients.

A schematic representation of the structure of β-Tb₃Ge₅ and β-Dy₃Ge₅ is shown in Fig. 1. Using the already communicated ideas [4], this arrangement can be regarded as a long-range ordered superstructure of the non-stoichiometric TbGe_{2−x} and DyGe_{2−x} phases (*x* ≈ 1/3) [3]. The relationship between the defect AlB₂ type and the structure in question is straightforward—the periodic array of planar Ge atoms shown in Fig. 2 represents the topology of the $\frac{2}{3}$ [Ge₅]-layers in β-RE₃Ge₅, where every 6th atom from the honeycomb-like arrangement in the idealized RE₃Ge₆ (AlB₂ type, formula tripled for convenience) is vacated in a regular fashion. The resultant super-structure, *a'*, will be related to the unit cell of the sub-structure via the simple geometric relationship *a'* ≈ *a* × 3^{1/2}. In addition, since the newly formed layers are not eclipsed as in the AlB₂-structure, but rather staggered, the *c*-edge doubles (*c'* ≈ *c* × 2), yielding an overall 6-fold increase of the cell-volume. Similar approach can be used towards rationalizing the structure of the α-polymorphs (Pearson's code *oF64*), which in turn can be derived from the α-ThSi₂ type through ordering of Ge vacancies. In this case, the defect Ge network can be seen as an array of orthogonal zig-zag chains, $\frac{1}{3}$ [Ge₂], which are interconnected. The imaginary removal of every 6th atom from the chains can result in a three-dimensional lattice (*a'*, *b'*, *c'*) related to its tetragonal “parent” via the relationships: *a'* ≈ *a* × 2^{1/2};

Table 2

Atomic coordinates, isotropic displacement parameters (*U*_{eq}^a) for Tb₃Ge₅ and Dy₃Ge₅.

Atom	Wyckoff index	<i>x</i>	<i>y</i>	<i>z</i>	<i>U</i> _{eq} (Å ²)
Tb ₃ Ge ₅					
Tb1	6g	0.3314(1)	0	0	0.0085(2)
Ge1	6h	0.4007(3)	0.3317(3)	1/4	0.0109(3)
Ge2	2d	1/3	2/3	1/4	0.0095(6)
Ge3	2b	0	0	1/4	0.0104(6)
Dy ₃ Ge ₅					
Dy1	6g	0.33144(9)	0	0	0.0073(2)
Ge1	6h	0.4015(3)	0.3314(3)	1/4	0.0124(4)
Ge2	2d	1/3	2/3	1/4	0.0098(6)
Ge3	2b	0	0	1/4	0.0111(6)

Table 3
Selected interatomic distances (Å) in Tb₃Ge₅ and Dy₃Ge₅.

Atom pair		Distance
Tb₃Ge₅		
Ge1–	Ge3	2.545(2)
	Ge2	2.561(2)
	Tb × 2	2.945(2)
	Tb × 2	2.970(2)
	Tb × 2	3.450(2)
Ge2–	Ge1 × 3	2.561(2)
	Tb × 6	3.100(5)
Ge3–	Ge1 × 3	2.546(2)
	Tb × 6	3.085(2)
Tb–	Ge1 × 2	2.945(2)
	Ge1 × 2	2.970(2)
	Ge3 × 2	3.085(2)
	Ge2 × 2	3.100(5)
	Ge1 × 2	3.450(2)
Dy₃Ge₅		
Ge1–	Ge3	2.540(2)
	Ge2	2.558(2)
	Dy × 2	2.929(1)
	Dy × 2	2.956(2)
	Dy × 2	3.441(2)
Ge2–	Ge1 × 3	2.558(2)
	Dy × 6	3.086(2)
Ge3–	Ge1 × 3	2.540(2)
	Dy × 6	3.072(2)
Dy	Ge1 × 2	2.929(1)
	Ge1 × 2	2.956(2)
	Ge3 × 2	3.072(2)
	Ge2 × 2	3.086(2)
	Ge1 × 2	3.441(2)

$b' \approx a \times 2^{1/2} \times 3$; $c' \approx c$. More detailed description can be found elsewhere [4,9,10].

From a different standpoint, both “3–5” structures can also be envisioned as built from triangular prisms made of rare-earth metal atoms that share common faces, and which are centered by germanium atoms (Fig. 1 depicts this for β -RE₃Ge₅). Of worthwhile mention is the fact that not all of these prisms are filled, in fact one out of every six is empty, but this does not cause any distortions in the rare-earth metal sub-lattice.

Fig. 1. (a) Crystal structure of the hexagonal β -Tb₃Ge₅ and β -Dy₃Ge₅, viewed down the [110] plane and with the unit cell outlined. The rare-earth metal atoms are shown as white spheres while Ge atoms are depicted as smaller, black spheres. The 12-membered polygons of Ge, which are the result of the long-range order of vacant Ge sites are shaded. The trigonal prisms formed by the rare-earth metal atoms are drawn with dotted lines.

Fig. 2. Schematic representation of the long-range vacancy order in the honeycomb-like layers of Ge in the hexagonal β -Tb₃Ge₅ and β -Dy₃Ge₅. The corresponding subcell-supercell interrelation is also illustrated by dotted and solid lines, respectively.

As discussed in an earlier study [4], there are several key indications, which suggest that the chemical bonding in the non-stoichiometric TbGe_{2-x} and DyGe_{2-x} phases ($x \approx 1/3$) cannot be accurately explained using the AlB₂-type as a model. The first and most significant one has something to do with the fact that the Ge atoms are in special positions in the AlB₂-type (Wyckoff index 2d), and have no variable parameters [3]. Thus, the Ge–Ge distances will be interrelated by the lattice constants only, which if the published lattice constants for TbGe_{2-x} and DyGe_{2-x} are taken into consideration [3], amounts to unrealistically short Ge–Ge contacts (on the order of 2.2–2.3 Å). In the 6-fold superstructure (Fig. 2), due to the small distortion around the vacant site in order to compensate for the empty space, the Ge–Ge distances become normal and measure from 2.545(2) Å to 2.561(2) Å in β -Tb₃Ge₅ and 2.540(2) Å to 2.558(2) Å in β -Dy₃Ge₅ (Table 3), along with the Ge–Ge–Ge bonds angles decreasing from 120° to ca. 103°. Although these parameters are slightly different than those found in elemental Ge [24], they are comparable to the ones in the recently reported binary germanides such as RE₃Ge₄ (RE = Gd through Tm) [6], RE₃Ge₅ (RE = Sm, Gd) [4], EuGe₂ [17] and CaGe₂ [18]. Ultimately, the RE–Ge contacts (in which the rare-earth metal is surrounded by 10 next nearest germanium neighbors) are comparable to those found in the latter compounds and measure between ca. 2.92 Å and 3.45 Å. A comparison of the RE–Ge distances for the known RE₃Ge₅ compounds with this structure shows a good correlation with the decreasing size of the rare-earth metal cations when moving across the lanthanide series. The Ge–Ge distances, however, are invariant upon changing the RE metal.

3.2. Phase relationships and structural transformations

It has been known for some time that the binary germanides around 50–67 at.% Ge show large stoichiometry breadths and are often described as REGe_{2-x} ($0 \leq x \leq 0.5$) [3,9,10]. For the early rare-earth metals, the prevailing structure type is the tetragonal α -ThSi₂ (Pearson's symbol *tI*12), while for the mid-to-late rare-earth metals, the layered hexagonal AlB₂ type (Pearson's symbol *hP*3) is more common [1–3]. We have already examined several such REGe_{2-x} phases ($x \approx 1/4$, $x \approx 1/3$, and $x \approx 1/5$), all of which show evidence for superstructures derived from either α -ThSi₂ or AlB₂ types through ordering of vacant Ge sites [4–6]. Some of these “line compounds” are not indicated in the corresponding phase diagrams [25], hinting

at the possibility that their interpretation may not be as trivial as it may seem at a first glance. Even more surprising is the fact that polymorphic forms and phase transitions are also absent or misrepresented in the diagrams. Take for example the Tb–Ge system [25]—it indicates the possible existence of polymorphic TbGe_{2-x} binaries with compositions $\text{TbGe}_{1.6-1.7}$ (62–63 at.% Ge) and $\text{TbGe}_{1.5}$ (60 at.% Ge). The structures of the low-temperature forms (LT) remain elusive; the high-temperature form (HT) of $\text{TbGe}_{1.6-1.7}$ is with the $\alpha\text{-ThSi}_2$ and the latter with the AlB_2 type. The Dy–Ge system [25], in turn, suggests the possible existence of three polymorphic forms of $\text{DyGe}_{1.5}$ (type AlB_2 for LT) and only one $\text{DyGe}_{1.63}$ (structure unknown). It disagrees with a 1966 paper [26], which describes, perhaps erroneously, two DyGe_{2-x} polymorphs with the $\alpha\text{-ThSi}_2$ and AlB_2 type. Several structural studies have subsequently shown that the most thermodynamically stable phases in both diagrams at around 63 at.% Ge are indeed Tb_3Ge_5 and Dy_3Ge_5 (ordered $\alpha\text{-ThSi}_2$ superstructures, crystallizing in the Fdd2 space group) [19,20]. These compounds have been prepared by direct fusion of the elements and subsequent annealing at between 800 °C and 1000 °C. Such findings are corroborated by our results using the flux growth technique—the formation of the orthorhombic polymorph is facilitated by slow cooling and/or annealing at intermediate temperatures (500–700 °C), whereas the hexagonal form, which is believed to be the metastable (kinetic) phase can be “trapped” when using fast cooling rates only. Another, even more definitive evidence for the α – β phase relationship is the fact that single crystals of the hexagonal phase (β), when annealed in vacuum at temperatures between 500 °C and 700 °C for one week, undergo single-crystal to single-crystal phase transition to the orthorhombic form. This transformation was confirmed by X-ray diffraction (see Section 2) and it appears to be irreversible—annealing of the orthorhombic phase in a large temperature range (from 320 °C to 1000 °C), as detailed in previous studies, does not result in any structural change. The results are fully consistent with the α – β phase relationships reported for Dy_3Ge_5 [20].

3.3. Magnetic properties

Plots of the magnetic susceptibility $\chi = M/H$ as a function of the temperature for both $\beta\text{-Tb}_3\text{Ge}_5$ and $\beta\text{-Dy}_3\text{Ge}_5$ are shown in Fig. 3. As seen from the figure, the two compounds exhibit paramagnetic behavior in wide temperature intervals, according to the Curie–Weiss law: $\chi(T) = C/(T - \theta_p)$, where $C = N_A\mu_{\text{eff}}^2/3k_B$ is the Curie constant and θ_p is the Weiss temperature (μ_{eff} is the experimental effective moment (in Bohr-magneton units, μ_B) N_A is the Avogadro number ($6.022 \times 10^{23} \text{ mol}^{-1}$), k_B is the Boltzmann's constant ($1.381 \times 10^{-23} \text{ J K}^{-1}$). Above ca. 50 K, the dependence of the inverse susceptibility with the temperature is linear. Applying a linear fit to $\chi^{-1}(T)$ yields effective moments of $9.63 \mu_B$ and $10.47 \mu_B$ for Tb_3Ge_5 and Dy_3Ge_5 , respectively. These values are in very good agreement with the values calculated for free-ion Tb^{3+} and Dy^{3+} according to $\mu_{\text{eff}} = g[J(J+1)]^{1/2}$ [27]. For both compounds, cusp-like features at temperature of 23 K for Tb_3Ge_5 and 9 K for Dy_3Ge_5 indicate the onset of long-range magnetic order. The magnetic order is probably not simple. The maxima in the $\chi(T)$ plots can be thought as the respective Néel temperatures, and the Weiss temperatures θ_p for Tb_3Ge_5 and Dy_3Ge_5 are both negative: -34 K and -27 K , respectively.

It is worth comparing the magnetic properties of the title compound with those, published for other Tb–Ge and Dy–Ge binaries. For example, TbGe_2 (presumed to be a stoichiometric compound) [28] and Tb_3Ge_5 (orthorhombic polymorph) [20] are both antiferromagnetic with Néel temperatures $T_N = 42 \text{ K}$ and 17 K , respectively. DyGe_2 and the orthorhombic Dy_3Ge_5 also undergo antiferromagnetic ordering at 28 K and 12 K , respectively [20]. The difference in

Fig. 3. Temperature dependence of the magnetic susceptibility (χ) plots for $\beta\text{-Tb}_3\text{Ge}_5$ and $\beta\text{-Dy}_3\text{Ge}_5$. Inverse magnetic susceptibility $\chi^{-1}(T)$ plots are shown in the insets.

the T_N values in both cases could indicate that increasing the concentration of Ge vacancies leads to lowering of the corresponding Néel temperature. Of special mention also is the magnetic order in the Dy–Ge compounds described by Sekizawa [26]. This work reports a HT phase with the $\alpha\text{-ThSi}_2$ type and a LT form with the AlB_2 type, which have Néel temperatures of 6.5 K and 23 K , respectively. These data are inconsistent with the neutron diffraction data on the orthorhombic $\alpha\text{-Dy}_3\text{Ge}_5$ (LT form) [20] and the discussed herein results on the hexagonal β -polymorph. Such disagreements with earlier studies are not uncommon in the literature, and are most likely due to unrecognized impurities or the presence of secondary phases. After all, the complexity of the corresponding phase diagrams [25] is such that high-quality samples with desired compositions are very difficult to obtain.

4. Conclusion

We have reported the synthesis and single-crystal structures of new polymorphs of Tb_3Ge_5 and Dy_3Ge_5 . The crystals have successfully been grown from a flux, emphasizing the benefit of the flux-growth method for discovery and facile preparation of single-crystalline compounds. $\beta\text{-Tb}_3\text{Ge}_5$ and $\beta\text{-Dy}_3\text{Ge}_5$ crystallize with hexagonal structures, which are derivatives of the AlB_2 type. The results from these studies are consistent with the earlier reports on polymorphism in Sm_3Ge_5 , which all suggest that the hexagonal forms (AlB_2 superstructures, space group $\text{P6}_2\text{c}$) are the metastable phases, while the more thermodynamically sta-

ble phases in the three RE -Ge systems ($RE = \text{Sm, Tb, Dy}$) are the orthorhombic $RE_3\text{Ge}_5$ (α - ThSi_2 superstructures, space group $Fdd2$). Temperature dependent magnetization measurements show that β - Tb_3Ge_5 and β - Dy_3Ge_5 order antiferromagnetically below 23 K and 9 K, respectively.

Acknowledgements

Svilen Bobev acknowledges financial support from the National Science Foundation through a grant DMR-0743916 (CAREER). PHT wishes to thank the University of Delaware for the University Graduate Fellowship and the International Centre for Diffraction Data (ICDD) for the Ludo Frevel Crystallography Scholarship. Work at Los Alamos was performed under the auspices of the US Department of Energy, Office of Science.

References

- [1] A. Szytula, J. Leciejewicz (Eds.), Handbook of Crystal Structures and Magnetic Properties of Rare Earth Intermetallics, CRC Press, Boca Raton, FL, 1994.
- [2] A. Iandelli, A. Palenzona, in: K.A. Gschneidner Jr., L. Eyring (Eds.), Handbook on the Physics and Chemistry of Rare Earths, vol. 2, North Holland, Amsterdam, 1979, p. 1.
- [3] P. Villars, L.D. Calvert, Pearson's Handbook of Crystallographic Data for Intermetallic Phases, second ed., American Society for Metals, Materials Park, OH, 1991.
- [4] P.H. Tobash, D. Lins, S. Bobev, N. Hur, J.D. Thompson, J.L. Sarrao, Inorg. Chem. 45 (2006) 7286.
- [5] P.H. Tobash, S. Bobev, W. Pryz, D. Buttrey, N. Hur, J.D. Thompson, J.L. Sarrao, in preparation.
- [6] P.H. Tobash, G. DiFilippo, S. Bobev, N. Hur, J.D. Thompson, J.L. Sarrao, Inorg. Chem. 46 (2007) 8690.
- [7] G. Venturini, I. Ijjaali, B. Malaman, J. Alloys Compd. 289 (1999) 168.
- [8] A.M. Guloy, J.D. Corbett, Inorg. Chem. 30 (1991) 4789.
- [9] G. Venturini, I. Ijjaali, B. Malaman, J. Alloys Compd. 284 (1999) 262.
- [10] G. Venturini, I. Ijjaali, B. Malaman, J. Alloys Compd. 285 (1999) 194.
- [11] G. Venturini, I. Ijjaali, B. Malaman, J. Alloys Compd. 289 (1999) 116.
- [12] O. Zaharko, P. Schobinger-Papamantellos, C. Ritter, J. Alloys Compd. 280 (1998) 4.
- [13] M.G. Kanatzidis, R. Pöttgen, W. Jeitschko, Angew. Chem. Int. Ed. 44 (2005) 6996.
- [14] P.H. Tobash, D. Lins, S. Bobev, A. Lima, M.F. Hundley, J.D. Thompson, J.L. Sarrao, Chem. Mater. 17 (2005) 5567.
- [15] P.H. Tobash, S. Bobev, J. Am. Chem. Soc. 128 (2006) 3532.
- [16] P.H. Tobash, J.J. Meyers, G. DiFilippo, S. Bobev, F. Ronning, J.D. Thompson, J.L. Sarrao, Chem. Mater. 20 (2008) 2151.
- [17] S. Bobev, E.D. Bauer, J.D. Thompson, J.L. Sarrao, G.J. Miller, B. Eck, R. Dronskowski, J. Solid State Chem. 177 (2004) 3545.
- [18] P.H. Tobash, S. Bobev, J. Solid State Chem. 180 (2007) 1575.
- [19] P. Schobinger-Papamantellos, K.H.J. Buschow, J. Less-Common Met. 146 (1989) 279.
- [20] P. Schobinger-Papamantellos, D.B. de Mooij, K.H.J. Buschow, J. Less-Common Met. 163 (1990) 319.
- [21] JADE Version 6.5, Materials Data, Inc., Livermore, CA, 2003.
- [22] SAINT NT, Version 6.45, Bruker Analytical X-Ray Systems, Inc., Madison, WI, 2003.
- [23] SADABS NT, version 2.10, Bruker Analytical X-Ray Systems, Inc., Madison, WI, 2001.
- [24] L. Pauling, The Nature of the Chemical Bond, third ed., Cornell University Press, Ithaca, NY, 1960.
- [25] T.B. Massalski, Binary Alloy Phases Diagrams, American Society for Metals, Materials Park, OH, 1990.
- [26] K. Sekizawa, J. Phys. Soc. Jpn. 21 (1966) 1137.
- [27] J.S. Smart, Effective Theories of Magnetism, Saunders, Philadelphia, PA, 1966.
- [28] P. Schobinger-Papamantellos, D.B. de Mooij, K.H.J. Buschow, J. Less-Common Met. 144 (1988) 265.

Crystal growth of nanoscaled europium selenide having characteristic crystal shapes

Atsushi Tanaka, Taka-aki Adachi, Yasuchika Hasegawa*, Tsuyoshi Kawai

Graduate School of Materials Science, Nara Institute of Science and Technology, 8916-5 Takayama, Ikoma, Nara 630-0192, Japan

ARTICLE INFO

Article history:

Received 2 June 2008

Received in revised form

24 November 2008

Accepted 25 November 2008

Available online 6 December 2008

Keywords:

Rare earth alloys and compounds
Nanostructured materials

ABSTRACT

Tetrapod-shaped EuSe nanocrystals were prepared through the thermal reduction of europium chloride an organic selenide complex, n-hexadecylamine, and two additives oleic acid and oleylamine. The obtained EuSe nanoparticles were characterized by X-ray diffraction (XRD). The crystal grain size from the XRD spectrum was estimated to be 50 nm. In contrast, observation of the transmission electron microscope (TEM) gave larger sized EuSe (average size: 200 nm). Anisotropic crystal-growth of EuSe nanocrystals was achieved by addition of a small amount of oleic acid in the crystal growth process.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Europium chalcogenides (EuO, EuS and EuSe) are characteristic semiconductors which have the localized 4f electrons distributed between the conduction band (5d orbitals of Eu(II)) and the valence band (2p (O^{2-}), 3p (S^{2-}) and 4p (Se^{2-}) orbitals) [1–3]. The 4f–5d electronic transition and spin configuration of europium(II) chalcogenides are responsible for large Faraday and Kerr effects, which make them promising candidates for active materials in magneto-optical devices [4–10]. These magneto-optical properties are strongly dependent on their sizes [9]. Especially the photophysical properties of nano-sized materials are affected by size, shape, surface conditions and surrounding environment of the crystals [11,12].

It is known that size affects magneto-optic properties of nano-sized europium chalcogenides. Recently, we have reported on the enhancement of EuSe nanocrystals' magneto-optical properties, which are significantly dependent on the size and shape of each crystal [12]. These crystal grain sizes were calculated using the Scherrer equation based on their XRD spectrum, and were estimated to be 11 and 20 nm. The saturation magnetization of EuSe nanocrystals was less than the expected value of $7.0 \mu_B$ for the $^8S_{7/2}$ state of Eu(II). The disorderly arrangement of tiny crystal on the surface of the nanocrystals caused a decrease in the exchange interaction between Eu(II) ions. Thus, the large saturation magnetization of EuSe nanocrystals for magneto-optical devices

requires a novel process for crystal growth of nano-scaled EuSe crystals.

Here, we report on the crystal growth of nano-scaled EuSe crystals by using specific additives, oleic acid and oleylamine, for the first time. The crystal growth of EuSe nanocrystals was achieved by way of europium nitrate with organic selenium compound and the additives (Fig. 1). We also prepared EuSe nanocrystals without the additives in order to compare the crystal growth. The EuSe nanocrystals were characterized by XRD and TEM measurements. It was concluded that the crystal growth process of EuSe nanocrystals could be developed in order to optimize nano-scaled magneto-optical materials.

2. Experimental

2.1. Apparatus

1H nuclear magnetic resonance (NMR), ^{13}C NMR, and ^{31}P NMR data were measured by a JEOL AL-300 (300 MHz) and ECP-400 (400 MHz) spectrometer. 1H NMR and ^{13}C NMR chemical shifts were determined using tetramethylsilane (TMS) as an internal standard. ^{31}P NMR chemical shifts were determined using H_3PO_4 as an internal standard. Elemental analyses were performed with a PerkinElmer 2400II CHNS/O. Microwave induced plasma mass spectrometry (MIP-MS) were recorded on a HITACHI P-6000. High-resolution images of the EuSe nanocrystals were obtained with a Hitachi JEM-3100FEF TEM equipped with a tilting device (10°) and operated at 300 kV.

2.2. Materials

Europium(III) chloride hexahydrate ($EuCl_3 \cdot 6H_2O$) (99.95%) was purchased from Kanto Chemical Co. Inc. Selenium powder (99.9%) was purchased from Nakalai tesque. Inc. 1-Hexadecylamine (HDA) (90%) was obtained from Tokyo Chemical Industry Co., Ltd. Oleic acid (99%) and Oleylamine was purchased from Wako Pure Chemical Industries, Ltd. Potassium diphenylphosphide (5 M) in tetrahydrofuran

* Corresponding author. Tel.: +81 743 6171; fax: +81 743 6171.
E-mail address: hasegawa@ms.naist.jp (Y. Hasegawa).

Fig. 1. Reaction schemes of EuSe nanoparticles 1 and 2.

was obtained from Aldrich Chemical Co., Inc. All other chemicals were reagent grade and were used as received.

2.3. Preparation of potassium diphenylphosphinediselenide $K(Se_2P(C_6H_5)_2)$

Potassium diphenylphosphinediselenide was following the reported method [12]. Yield: 74%. 1H NMR (CD_3SOCD_3) δ = 8.02 (m, PC_6H_5 4H), 7.24 (m, PC_6H_5 6H) ppm. ^{13}C NMR (CD_3SOCD_3) δ = 130.87, 130.72, 128.30, 128.25, 126.77, 126.61 ppm. ^{31}P NMR (CD_3SOCD_3) 24.02 ppm. ESI-MS: 344.88. Anal. Calcd for $C_{12}H_{10}KPSe_2$: C, 37.71; H, 2.64%. Found: C, 36.75; H, 2.66%.

2.4. Preparation of EuSe nanocrystals 1

A solution of $K(Se_2P(C_6H_5)_2)$ (0.45 g, 1.2 mmol) in acetonitrile (10 ml) was added to $EuCl_3 \cdot 6(H_2O)$ (0.2 g, 0.44 mmol) dissolved in acetonitrile (30 ml) by stirring under nitrogen atmosphere for 2 h. The reaction mixture was concentrated, and hexadecylamine (HDA: 6.0 g, 25 mmol) was added at 330 °C under nitrogen atmosphere. After the reaction for 6 h, the resulting powder was cooled to room temperature. This powder was separated by centrifugation and washed with *n*-hexane. After washing, a brown powder was obtained.

2.5. Preparation of EuSe nanocrystals 2

A solution of $K(Se_2P(C_6H_5)_2)$ (0.45 g, 1.2 mmol) in acetonitrile (10 ml) was added to $EuCl_3 \cdot 6(H_2O)$ (0.2 g, 0.44 mmol) dissolved in acetonitrile (30 ml) by stirring under nitrogen atmosphere for 2 h. The reaction mixture was concentrated, and HDA (6.0 g, 25 mmol), oleylamine (0.67 g, 2.5 mmol) and oleic acid (0.70 g, 2.5 mmol) was added

Fig. 2. XRD profiles of (a) EuSe nanoparticles 1; (b) EuSe nanoparticles 2; and (c) EuSe bulk.

at 330 °C under nitrogen atmosphere. After the reaction for 6 h, the resulting powder was cooled to room temperature. This powder was separated by centrifugation and washed with *n*-hexane. After washing, a red powder was obtained.

2.6. Results and discussion

The formation of EuSe nanocrystals was carried out in situ generated europium diselenophosphinate compounds with HDA, oleylamine and oleic acid. The XRD pro-

Fig. 3. TEM images of EuSe nanocrystals: (a and b) high-resolution TEM images of EuSe nanocrystals 1; (c) size distribution histogram of EuSe nanocrystals 1; (d and e) high-resolution TEM images of EuSe nanocrystals 2; and (f) size distribution histogram of EuSe nanocrystals 2.

files of crystalline EuSe nanocrystals 1 and 2 are shown in Fig. 2. Diffraction peaks $2\theta = 24.5^\circ, 28.6^\circ, 41.0^\circ, 48.6^\circ, 51.0^\circ, 59.5^\circ, 67.4^\circ$ and 75.0° were assigned to the (1 1 1), (2 0 0), (3 1 1), (2 2 2), (4 0 0), (4 2 0) and (4 2 2) planes of NaCl type EuSe, respectively. The intensity ratio of the diffraction patterns agreed with those of the bulk EuSe. We evaluated the fwhm (full width at half-maxim) of $2\theta = 28.6^\circ$ (2 0 0), which corresponds to the Bragg diffraction using the EuSe (2 0 0) plane. The crystal grain EuSe nanocrystals 1 and 2 were calculated using the Scherer equation from the XRD spectrum, and were found to be 20.5 and 51.0 nm, respectively. The XRD signals of EuO, Eu₂O₃, and Eu₂Se₃ were not observed in the XRD spectra of EuSe nanocrystals 1. However, in XRD signals of EuSe nanocrystals 2, we found that we observed the signals at around 20° and 30° that were not assigned to EuSe signals. The signal at around 30° is similar to that of EuSe₂ (30.18°) [12]. We propose that the small EuSe₂ might be existed on the surface of EuSe nanoparticles 2. We also observed that the XRD spectrum of organic capping ligands (HDA) gave the signals at around 20° [12]. Typical TEM images of EuSe nanocrystals 1 are shown in Fig. 3a and b. According to EuSe nanocrystals 1, the aspect ratio between the long and short sides of the rectangular particles was evaluated for 300 nanocrystals. The average aspect ratio was about 1.1, indicating well-ordered cubic nanocrystals. The average crystal size evaluated by the TEM observations was found to be 23 nm, and similar to the size measured by XRD (20.5 nm). The characteristic cubic shapes might be due to the NaCl-type fcc-structure of the EuSe lattice. On the other hand, we observed anisotropic crystal growth of the EuSe nanocrystals 2 from the images of TEM measurements (Fig. 3d). The average size was found to be 200 nm, and we obtained the characteristic “tetrapod-shapes” of the EuSe nanocrystals 2. These results indicated that the EuSe nanocrystals 2 were constructed by concentration of EuSe nanocrystal blocks (grain size = 50 nm).

The crystal growth and characteristic shapes of EuSe nanocrystals 2 are directly linked to the addition of oleic acid and oleylamine. In the first step of crystal growth, Eu(III) precursor complexes formed by coordination of organic-selenide ligands. However, we found that Eu(III) complexes with organic selenide ligands are unstable under air coordination, decomposing to Eu(III) ions and selenide powder. Stabilizing the Eu(III) precursor complexes in HDA might be a key process for crystal growth of EuSe. We consider that carboxyl groups of oleic acid would play an important role in stabilizing of the Eu(III) precursor complexes. Eu(III) precursor complexes might be stabilized with oleic acid. The coordination ability of the carboxyl group is stronger than that of HDA. Oleylamine would also support the stabilization of the Eu(III) precursor in HDA. We propose that the crystal growth of EuSe nanocrystals 2 is due to formation of stable Eu(III) precursor complexes as a result of adding oleic acid and oleylamine.

3. Conclusion

In summary, we have succeeded in growing crystals of nano-scale EuSe by adding of oleylamine and oleic acid for the first time. To the best of our knowledge, the present study is the first report on the synthesis of starpod-shaped EuSe nanocrystals and the successful manipulation of EuSe nanocrystal size. We expect that EuSe nanocrystals will have varied size when other additives are applied during crystal growth. We suggest that the crystal growth of EuSe depends on the coordination ability of the organic capping ligands. The coordination ability of carboxyl group in oleic acid might be stronger than that of corresponding amine group in HDA. The size and shape-controlled lanthanide nanocrystals are expected to open up pioneering fields in nano/micro materials, chemistry and magneto-optic science.

References

- [1] P. Wachter, Handbook on the Physics and Chemistry of Rare Earths, 2nd ed., North-Holland Publishing Company, 1979, pp. 189–241.
- [2] T. Kasuya, A. Yanase, Rev. Mod. Phys. 40 (1968) 684–696.
- [3] D.E. Eastman, F. Holtzberg, S. Methfessel, Phys. Rev. Lett. 23 (1969) 226–229.
- [4] C. Muller, H. Lippitz, J.J. Paggel, P. Fumagalli, J. Appl. Phys. 95 (2004) 7172–7174.
- [5] J. Schoenes, J. Phys.: Condensed Matter 15 (2003) S707.
- [6] M. Umehara, Phys. Rev. B 65 (2002) 205208/1–205208/9.
- [7] Y.A. Uspenskii, B.N. Harmon, Phys. Rev. B 61 (2000) R10571–R10574.
- [8] C. Muller, H. Lippitz, J.J. Paggel, P. Fumagalli, J. Appl. Phys. 91 (2002) 7535–7537.
- [9] K. Tanaka, N. Tatehata, K. Fujita, K. Hirao, J. Appl. Phys. 89 (2001) 2213–2219.
- [10] P. Fumagalli, A. Schirmeisen, R.J. Gambino, J. Appl. Phys. 79 (1996) 5929–5931.
- [11] T. Kataoka, Y. Tsukahara, Y. Hasegawa, Y. Wada, Chem. Commun. (2005) 6038–6040.
- [12] Y. Hasegawa, T.-a. Adachi, A. Tanaka, M. Afzaal, P. O'Brien, T. Doi, Y. Hinatsu, K. Fujita, K. Tanaka, T. Kawai, J. Am. Chem. Soc. 130 (2008) 5710–5715.

Phase transition of the orthorhombic fluorite-related compounds Ln_3IrO_7 ($Ln = \text{Pr, Nd, Sm, Eu}$)

Yukio Hinatsu^{a,*}, Yoshihiro Doi^a, Hiroaki Nishimine^a, Makoto Wakeshima^a, Mineo Sato^b

^a Division of Chemistry, Graduate School of Science, Hokkaido University, Sapporo 060-0810, Japan

^b Department of Chemistry and Chemical Engineering, Faculty of Engineering, Niigata University, 8050 Ikarashi 2-nocho, Niigata 950-2181, Japan

ARTICLE INFO

Article history:

Received 2 June 2008

Received in revised form 7 October 2008

Accepted 14 October 2008

Available online 26 November 2008

Keywords:

Magnetically ordered materials

Powder metallurgy

X-ray diffraction

Heat capacity

Thermal analysis

ABSTRACT

Rare earth iridium oxides Ln_3IrO_7 ($Ln = \text{Pr, Nd, Sm, and Eu}$) were prepared and their structures were determined by X-ray diffraction measurements. At room temperature, Pr_3IrO_7 crystallized in an orthorhombic superstructure of cubic fluorite with space group $Cmcm$. The differential thermal analysis (DTA) and specific heat measurements for Ln_3IrO_7 ($Ln = \text{Pr, Nd, Sm, and Eu}$) showed a phase transition at 262, 342, 420, and 485 K, respectively. At low temperatures, Ln_3IrO_7 crystallized in a monoclinic structure with the space group $P2_1/n$. The transition temperatures increased with decreasing the ionic radius of rare earths, which indicates that the transition is stress-induced and occurs with the lattice contraction on cooling. These results for Ln_3IrO_7 were compared with the phase transitions observed for Ln_3MoO_7 , Ln_3RuO_7 , Ln_3ReO_7 , and Ln_3OsO_7 .

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Among rare earth elements, cerium, praseodymium, and terbium in the tetravalent state form a dioxides MO_2 with a fluorite structure. Although the trivalent rare earth does not form a dioxide with the fluorite structure, ternary rare earth oxides of the general formula Ln_3MO_7 ($Ln = \text{rare earths, } M = \text{Nb, Ru, Ta, Re, etc.}$) have a defect-fluorite structure. The relationship to the fluorite structure is as follows. The fluorite unit cell for oxides has the composition $M^{4+}_4O_8$. If the four tetravalent metal ions are replaced by three trivalent ions (Ln) and one pentavalent ion (M), one oxide-vacancy is formed per fluorite cell. Due to the significant differences in radii between the Ln^{3+} and M^{5+} ions, cation ordering occurs on the metal sites and the oxide-vacancy orders on the anion sites. In 1979, Rossell first determined the crystal structure for La_3NbO_7 [1]. It is well described in the orthorhombic space group $Cmcm$: The M^{5+} ion is coordinated with six oxygen ions, forming a MO_6 octahedron. These octahedra share corners forming one-dimensional chains which are oriented along the c -axis. The same space group $Cmcm$ has been applied for Ln_3RuO_7 ($Ln = \text{La–Gd}$) [2–13], Ln_3ReO_7 ($Ln = \text{Pr, Nd, Sm–Tb}$) [14–17], Ln_3OsO_7 ($Ln = \text{Pr, Nd, Sm–Gd}$) [11,18,19], Ln_3TaO_7 ($Ln = \text{La–Nd}$) [20–24], Ln_3IrO_7 ($Ln = \text{Pr, Nd, Sm, Eu}$) [25,26], Pr_3NbO_7 [23] and Pr_3SbO_7 [23]. For Ln_3TaO_7 ($Ln = \text{Y,}$

Sm–Ho) [20–22,24], Ln_3SbO_7 ($Ln = \text{Y, Dy, Ho}$) [20,27], Ln_3ReO_7 ($Ln = \text{Dy, Ho}$) [16,17], and Gd_3NbO_7 [20], the space group $C222_1$ has been applied. On the other hand, the structure for Ln_3MoO_7 ($Ln = \text{La–Nd, Sm, Eu}$) is well described with different space group $P2_12_12_1$ [28–30], and the one-dimensional MO_6 alignment is the same for the structures with the space groups $Cmcm$ and $C222_1$, but the zig-zag chains of the corner-sharing MO_6 octahedra are parallel to the b -axis in this case.

Due to this unique crystal structures and possible related magnetic properties, many studies have been performed, especially for the magnetic properties of compounds containing Ru^{5+} ion at the M -site because of its largest possible spin ($S = 3/2$) [2–12].

Another topic for Ln_3MO_7 is that detailed magnetic and thermal investigations on the ruthenium-, iridium- and osmium-containing members of the Ln_3MO_7 family show low-temperature structural phase transitions [8–10,12,13,19,26,30]. However, the low-temperature structures are, in most cases, not known, or different structures were presented for the same compounds [9,12,13].

As for Ln_3IrO_7 compounds, Vente and Ijdo reported the synthesis and their crystal structures [25]. They reported that Ln_3IrO_7 ($Ln = \text{Pr, Nd, Sm, and Eu}$) compounds are isomorphous, and their structures were described with the same space group $Cmcm$. Our X-ray diffraction and neutron diffraction measurements showed that only the structure for Pr_3IrO_7 is actually applied for such space group, and the other compounds were not the case [26]. The results for the specific heat and differential thermal analysis (DTA) indicated that

* Corresponding author. Tel.: +81 11 706 2702; fax: +81 11 706 2702.

E-mail address: hinatsu@sci.hokudai.ac.jp (Y. Hinatsu).

the phase transitions have been observed for any of these Ln_3IrO_7 ($\text{Ln} = \text{Pr, Nd, Sm, and Eu}$) compounds. The high-temperature structure is well described with the space group Cmcm . However, the low-temperature structure has not yet been known. Concerning the magnetic properties, only the Nd_3IrO_7 showed an antiferromagnetic transition at 2.6 K [26].

In this study, we re-examined the structure and thermal properties for the Ln_3IrO_7 compounds. After checking the existence of the phase transition in these compounds, we performed the X-ray diffraction measurements in order to determine their low-temperature crystal structures. The relationship between the high- and low-temperature structures was discussed.

2. Experimental

As starting materials, rare earth oxides Ln_2O_3 ($\text{Ln} = \text{Nd, Sm, Eu}$) and Pr_6O_{11} , and iridium metal powders Ir were used. They were weighed in an appropriate metal ratio and were ground in an agate mortar. The mixtures were pressed into pellets and then heated in an oxygen atmosphere up to 1473–1523 K at a rate of 0.5 K min^{-1} , held at this temperature for 12 h, and then cooled down to room temperature at the same rate. After several intermediate regrindings and repelletizing, this heating procedure was repeated again. The heating in an oxygen atmosphere was necessary to avoid the formation of pyrochlore-type compounds $\text{Ln}_2\text{Ir}_2\text{O}_7$ ($\text{Ln} = \text{Pr, Nd, Sm, and Eu}$) in which the Ir^{4+} ions are present [31].

Powder X-ray diffraction profiles were measured using a Rigaku Multi-Flex diffractometer with $\text{Cu-K}\alpha$ radiation equipped with a curved graphite monochromator. The data were collected by step-scanning in the angle range of $10^\circ \leq 2\theta \leq 120^\circ$ at a 2θ step-size of 0.02° . The X-ray diffraction data were analyzed by the Rietveld technique, using the programs RIETAN2000 [32].

Specific heat measurements for Ln_3IrO_7 were performed using a relaxation technique by a commercial heat capacity measuring system (Quantum Design, PPMS) in the temperature range of 1.8–400 K. The sintered sample in the form of a pellet was mounted on a thin alumina plate with Apiezon for better thermal contact.

DTA measurements were performed with a TG-DTA 2000S (Mac Science) over the temperature range of 300–800 K. As a standard material, $\alpha\text{-Al}_2\text{O}_3$ was used and the rates of heating and cooling were both controlled at 10 K min^{-1} .

3. Results and discussion

3.1. Preparation and crystal structure

We have successfully prepared a series of compounds Ln_3IrO_7 ($\text{Ln} = \text{Pr, Nd, Sm, Eu}$) in an oxygen atmosphere. Fig. 1 shows their X-ray diffraction (XRD) profiles measured at 298 K and the fitting results by the Rietveld analysis. Vente et al. reported that the crystal structures for Ln_3IrO_7 ($\text{Ln} = \text{Pr, Nd, Sm, Eu}$) were orthorhombic with space group Cmcm . Following them, we also refined the structures with the same space group. The fitting results by the Rietveld analysis shown in Fig. 1 appear to indicate that the structures for Ln_3IrO_7 ($\text{Ln} = \text{Pr, Nd, Sm, Eu}$) were refined with the space group Cmcm and the goodness of the fit (S) [32] was below 1.30 for all the compounds. However, the detailed X-ray diffraction profiles in the low 2θ angles (the inset of Fig. 1) indicate that some additional diffraction lines which cannot be fitted with the Cmcm space group appeared at $2\theta \sim 22^\circ$ and 25° for Ln_3IrO_7 ($\text{Ln} = \text{Nd, Sm, Eu}$).

Fig. 2 shows the temperature dependence of the specific heat for Pr_3IrO_7 and Nd_3IrO_7 . Specific heat anomalies corresponding to the first-order phase transitions were observed at 261 K and 342 K for Pr_3IrO_7 and Nd_3IrO_7 , respectively. For Sm_3IrO_7 and Eu_3IrO_7 , corresponding anomalies were observed in the DTA measurements, i.e., the endothermic peaks during heating were found at 420 K for Sm_3IrO_7 and 485 K for Eu_3IrO_7 . We consider that this transition is due to the phase transition. The transition temperature (T_p) increased with decreasing Ln ionic radius ($\text{Pr} \rightarrow \text{Eu}$). Only the Pr_3IrO_7 has a high-temperature structure at room temperature ($T_p = 261 \text{ K}$). Therefore, Nd_3IrO_7 , Sm_3IrO_7 and Eu_3IrO_7 should show a phase transition when the temperature is increased above room temperature.

Fig. 1. Powder X-ray diffraction profiles for Ln_3IrO_7 ($\text{Ln} = \text{Pr, Nd, Sm, Eu}$) measured at 298 K. The calculated and observed profiles are shown on the top solid line and cross-markers, respectively. The vertical marks in the middle show positions calculated for Bragg reflections. The lower trace is a plot of the difference between calculated and observed intensities. The insets show the X-ray diffraction profiles measured for Nd_3IrO_7 , Sm_3IrO_7 , and Eu_3IrO_7 in the $12^\circ \leq 2\theta \leq 28^\circ$. Arrows show diffraction lines which cannot be assigned with the space group Cmcm .

We performed high-temperature XRD measurements for Nd_3IrO_7 in the temperature range of 298–550 K. Fig. 3 shows the XRD profiles in the low 2θ range measured at 298 and 400 K. The XRD profile measured at 298 K has some weak diffraction lines (for example, at $2\theta \sim 22^\circ$ and 25°) which cannot be assigned with space group Cmcm . When the temperature was increased above 342 K, such diffraction lines disappeared and the XRD profile was successfully refined with the space group Cmcm . The same situation was observed in the temperature dependence of the XRD profiles for

Fig. 2. Temperature dependence of the specific heat for Pr_3IrO_7 and Nd_3IrO_7 . The inset shows the detailed specific data for Nd_3IrO_7 at low temperatures.

Fig. 3. XRD profiles for Nd_3IrO_7 measured at 298 and 400 K in the 2θ range of $13\text{--}27^\circ$. Diffraction lines marked with arrows disappeared when the temperature is raised up to 400 K.

Sm_3IrO_7 and Eu_3IrO_7 . The high-temperature structure for Ln_3IrO_7 is well described with the space group $Cmcm$, and this structure has been observed for most of the Ln_3MO_7 type compounds [2–27].

The analysis of the X-ray diffraction data measured below the transition temperature showed that all additional diffraction peaks could be indexed to a primitive monoclinic cell. Refinement in the $P2_1/n$ space group of the structural model yielded satisfactory results. Trial refinements in other space groups resulted in physically unreasonable displacement parameters, as well as high residual factors R . The refined atomic coordinates and lattice parameters for the low-temperature structure of Nd_3IrO_7 with

those for the high-temperature structure are compiled in Table 1. The high-temperature structure is described in the orthorhombic space group $Cmcm$ with two independent neodymium positions (Nd1_o , Nd2_o , where the subscript “o” means orthorhombic), one unique iridium site (Ir1_o), and three independent oxygen atom positions (O1_o , O2_o , O3_o). The low-temperature structures are best described in the primitive monoclinic space group $P2_1/n$ with three independent neodymium positions, two unique iridium sites, and seven independent oxygen atom positions. Due to this transition (orthorhombic $\rightarrow$ monoclinic), Ir1_o transforms into Ir1_m and Ir2_m (where the subscript “m” means monoclinic), Nd1_o transforms into Nd1_m , Nd2_o transforms into Nd2_m and Nd3_m . As for oxygen atoms, O1_o , O2_o , and O3_o transform into (O2_m , O3_m , O4_m and O5_m), (O6_m and O7_m), and O1_m , respectively.

Fig. 4 shows the low-temperature structure of Nd_3IrO_7 as well as its high-temperature structure. Similar to the high-temperature structure, the structure features chains of vertex-shared IrO_6 octahedra running along the c -axis. In the high-temperature $Cmcm$ structure (Fig. 4(a)), the chains of trans vertex-sharing IrO_6 connect to the chains of edge-sharing NdO_8 pseudo-cubes via pairs of equatorial IrO_6 oxygen atoms. In the low-temperature $P2_1/n$ structure (Fig. 4(b)), the vertex-shared IrO_6 octahedra are tilted greatly. The tilting of the IrO_6 chains caused one of the equatorial oxygen atoms to rotate away from the neodymium cation. This resulted in the reduction of the coordination number of the associated Nd^{3+} from 8 to 7. The $\text{Nd}\text{--O}$ bond length 2.75 Å which is included in the NdO_8 pseudo-cube at 400 K ($\text{Nd1}_o\text{--O1}_o$ with space group $Cmcm$) extends to 3.11 Å at 298 K ($\text{Nd1}_m\text{--O2}_m$ with space group $P2_1/n$). The O2_m at a distance of 3.11 Å from the Nd1 does not form the coordination polyhedron. This oxygen shift is the most remarkable change through the phase transition, and it corresponds to a dramatic change of the lattice parameters against the temperature. We measured the temperature dependence of the lattice parameters for Nd_3IrO_7 [26], and it is shown in Fig. 5. In the case that the lattice parameters were refined with the same space group $Cmcm$, they changed drastically near 342 K, at which the specific heat anomaly was observed. When the temperature was decreased through 342 K, the lattice parameter b was found to increase, while the lattice parameters a and c decreased rapidly. It should be noted that the IrO_6 octahedra

Fig. 4. Crystal structures of Nd_3IrO_7 . (a) High-temperature structure, $Cmcm$; (b): low-temperature structure, $P2_1/n$. The relationship between the monoclinic unit cell (the low-temperature structure) and the orthorhombic unit cell (the high-temperature structure) is also indicated.

Table 1
Crystal structure data for Nd₃IrO₇.

Site		x	y	z	B/Å ²
High-temperature structure (400 K)					
Space group: <i>Cmcm</i>					
<i>a</i> = 10.8991(1) Å, <i>b</i> = 7.4464(7) Å, <i>c</i> = 7.4930(8) Å, <i>V</i> = 608.12(10) Å ³					
<i>R</i> _i = 2.37%, <i>R</i> _{wp} = 12.10%					
Nd1	4 <i>a</i>	0	0	0	0.99(2)
Nd2	8 <i>g</i>	0.2234(2)	0.3051(2)	1/4	0.99
Ir	4 <i>b</i>	0	1/2	0	0.29(5)
O1	16 <i>h</i>	0.1286(8)	0.3150(3)	0.9580(7)	0.815(2)
O2	8 <i>g</i>	0.1314(9)	0.0243(1)	1/4	0.5(1)
O3	4 <i>c</i>	0	0.4066(2)	1/4	0.5
Low-temperature structure (298 K)					
Space group: <i>P2₁/n</i>					
<i>a</i> = 6.6024(7) Å, <i>b</i> = 12.4268(1) Å, <i>c</i> = 7.4938(6) Å, <i>γ</i> = 98.35°, <i>V</i> = 608.32(10) Å ³					
<i>R</i> _i = 2.01%, <i>R</i> _{wp} = 11.73%					
Nd1	4 <i>e</i>	0.2340(4)	0.7577(5)	−0.0022(2)	0.63(7)
Nd2	4 <i>e</i>	0.4318(5)	0.0141(2)	0.2521(2)	0.63
Nd3	4 <i>e</i>	0.7618(6)	0.7914(5)	0.2521(3)	0.63
Ir1	2 <i>a</i>	0	0	0	0.21(5)
Ir2	2 <i>c</i>	1/2	1/2	0	0.21
O1	4 <i>e</i>	0.5578(4)	0.4569(1)	0.2486(3)	0.55(5)
O2	4 <i>e</i>	0.2006(2)	0.5070(1)	0.0465(1)	0.55
O3	4 <i>e</i>	0.7131(5)	0.0043(1)	0.0344(1)	0.55
O4	4 <i>e</i>	0.5644(4)	0.6641(1)	0.0194(1)	0.55
O5	4 <i>e</i>	0.0630(1)	0.1619(1)	0.0699(1)	0.55
O6	4 <i>e</i>	0.9574(5)	0.3326(1)	0.2628(2)	0.55
O7	4 <i>e</i>	0.5611(4)	0.2040(1)	0.2819(3)	0.55

maintain their edge-sharing connectivity with the Nd1O₇ polyhedra. In the low-temperature structure, the IrO₆ chains still connect to the neodymium chains to form sheets, as shown in Fig. 4(b). The Ir–Nd–O slabs are more distorted in the low-temperature structure. The remaining two-thirds of the neodymium cations, Nd2 and Nd3, exist in two crystallographically unique sites.

On the other hand, the Ir–O distances are not affected by the phase distortion, and the average Ir–O distances are 1.97–1.98 Å for any of the Ln₃IrO₇ (*Ln* = Pr, Nd, Sm, Eu) compounds. These distances are in good agreement with lengths calculated from the Shannon's ionic radii [33].

Fig. 6 shows the variation of the phase transition temperatures for a series of Ln₃MO₇ (*M* = Mo, Ru, Re, Os, Ir) compounds against the ionic radius of Ln³⁺ [12,16,19,26,30]. For each of the five series

Fig. 5. Temperature dependence of lattice parameters for Nd₃IrO₇.

Fig. 6. Phase transition temperature for Ln₃MO₇ (*M* = Mo, Ru, Re, Os, Ir) against the ionic radius of Ln³⁺.

of Ln_3MO_7 compounds, the phase transition temperatures decrease with increasing the ionic radius of Ln^{3+} , i.e., it has been observed that the phase transition of Ln_3MO_7 is clearly influenced by the size of the Ln^{3+} cation. The transition is stress-induced and occurs with lattice contraction on cooling. Each transition temperature within a series is separated by approximately the same temperature interval except for the case of Ln_3MoO_7 . The trend of the transition temperature against Ln^{3+} radius for Ln_3MoO_7 is different from those for Ln_3MO_7 ($M = Ru, Re, Os, Ir$). The reason for this may be related to the difference in their high-temperature structures, that is, the Ln_3MoO_7 ($Ln = La-Eu$) exists in $P2_12_12_1$ structure, whereas the other Ln_3MO_7 ($M = Ru, Re, Os, Ir$) exists in the $Cmcm$ structure.

4. Summary

Lanthanide iridates Ln_3IrO_7 ($Ln = Pr, Nd, Sm, \text{ and } Eu$) were formed in the orthorhombic superstructure of cubic fluorite with space group $Cmcm$. These compounds show a phase transition at 262, 342, 420, and 485 K for $Ln = Pr, Nd, Sm, \text{ and } Eu$, respectively. At low temperatures, they crystallize in a monoclinic structure with the space group $P2_1/n$. The transition temperatures increased with decreasing the ionic radius of rare earths, which indicates that the transition is stress-induced and occurs with the lattice contraction on cooling.

Acknowledgement

This work was supported by Grant-in-aid for Scientific Research, No. 20550052 from the Ministry of Education, Science, Sports and Culture of Japan.

References

- [1] H.J. Rossell, J. Solid State Chem. 27 (1979) 115–122.
- [2] F.P.F. van Berkel, D.J.W. IJdo, Mater. Res. Bull. 21 (1986) 1103–1106.
- [3] W.A. Groen, F.P.F. van Berkel, D.J.W. IJdo, Acta Crystallogr. Sec. C 43 (1986) 2262–2264.
- [4] P. Khalifah, R.W. Erwin, J.W. Lynn, Q. Huang, B. Batlogg, R.J. Cava, Phys. Rev. B 60 (1999) 9573–9578.
- [5] P. Khalifah, Q. Huang, J.W. Lynn, R.W. Erwin, R.J. Cava, Mater. Res. Bull. 35 (2000) 1–7.
- [6] F. Wiss, N.P. Raju, A.S. Wills, J.E. Greedan, Int. J. Inorg. Mater. 2 (2000) 53–59.
- [7] B.P. Bontchev, A.J. Jacobson, M.M. Gospodinov, V. Skumryev, V.N. Popov, B. Lorenz, R.L. Meng, A.P. Litvinchuk, M.N. Iliev, Phys. Rev. B 62 (2000) 12235–12240.
- [8] D. Harada, Y. Hinatsu, J. Solid State Chem. 158 (2001) 245–253.
- [9] D. Harada, Y. Hinatsu, Y. Ishii, J. Phys.: Condens. Matter 13 (2001) 10825–10836.
- [10] D. Harada, Y. Hinatsu, J. Solid State Chem. 164 (2002) 163–168.
- [11] R. Lam, F. Wiss, J.E. Greedan, J. Solid State Chem. 167 (2002) 182–187.
- [12] W.R. Gemmill, M.D. Smith, H.-C. zur Loye, Inorg. Chem. 43 (2004) 4254–4261.
- [13] N. Ishizawa, K. Hiraga, D. du Boulay, H. Hibino, T. Ida, S. Oishi, Acta Cryst. E62 (2006) i13–i16.
- [14] G. Wltschek, H. Paulus, I. Svoboda, H. Ehrenberg, H. Fuess, J. Solid State Chem. 125 (1996) 1–4.
- [15] R. Lam, T. Langet, J.E. Greedan, J. Solid State Chem. 171 (2002) 317–323.
- [16] Y. Hinatsu, M. Wakeshima, N. Kawabuchi, N. Taira, J. Alloys Compd. 374 (2004) 79–83.
- [17] M. Wakeshima, Y. Hinatsu, J. Solid State Chem. 179 (2006) 3575–3581.
- [18] J.R. Plaisier, R.J. Drost, D.J.W. IJdo, J. Solid State Chem. 169 (2002) 189–198.
- [19] W.R. Gemmill, M.D. Smith, Y.A. Mozharivsky, G.J. Miller, H.-C. zur Loye, Inorg. Chem. 44 (2005) 7047–7055.
- [20] J.G. Allpress, H.J. Rossell, J. Solid State Chem. 27 (1979) 105–114.
- [21] Y. Yokogawa, M. Yoshimura, S. Somiya, Mater. Res. Bull. 22 (1987) 1449–1456.
- [22] Y. Yokogawa, M. Yoshimura, S. Somiya, Solid State Ionics 28 (1988) 1250–1253.
- [23] J.F. Vente, R.B. Helmholtz, D.J.W. IJdo, J. Solid State Chem. 108 (1994) 18–23.
- [24] M. Wakeshima, Y. Hinatsu, J. Phys.: Condens. Matter 16 (2004) 4103–4120.
- [25] J.F. Vente, D.J.W. IJdo, Mater. Res. Bull. 26 (1991) 1255–1262.
- [26] H. Nishimine, M. Wakeshima, Y. Hinatsu, J. Solid State Chem. 177 (2004) 739–744.
- [27] T. Fennell, S.T. Bramwell, M.A. Green, Can. J. Phys. 79 (2001) 1415–1419.
- [28] J.E. Greedan, N.P. Raju, A. Wegner, P. Gougeon, J. Padiou, J. Solid State Chem. 129 (1997) 320–327.
- [29] N. Barrier, P. Gougeon, Acta Crystallogr. E59 (2003) i22–i24.
- [30] H. Nishimine, M. Wakeshima, Y. Hinatsu, J. Solid State Chem. 178 (2005) 1221–1229.
- [31] N. Taira, M. Wakeshima, Y. Hinatsu, J. Phys.: Condens. Matter 13 (2001) 5527–5534.
- [32] F. Izumi, T. Ikeda, Mater. Sci. Forum 198 (2000) 321–324.
- [33] R.D. Shannon, Acta Crystallogr. A32 (1976) 751–767.

Formation of featured nano-structure in thermal stable La-doped alumina composite catalyst

Yoshitoyo Nishio, Masakuni Ozawa*

CRL, Nagoya Institute of Technology, Asahigaoka, Tajimi, Gifu 5070071, Japan

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 26 June 2009

Accepted 5 October 2009

Available online 12 October 2009

Keywords:

Alumina

Catalyst

Lanthanum

Solid-state reaction

Phase transition

ABSTRACT

Nanometer-order structural changes of lanthanum-modified γ -alumina at elevated temperature were examined for application toward heat-stable catalytic support. The composite powder was prepared by aqueous process using lanthanum (III) nitrate and alumina. The La added aluminas were heated in the temperature range of 600–1200 °C, and then characterized by surface area measurement, X-ray powder diffraction, scanning electron microscope (SEM), and transmission electron microscope (TEM). The solid-state reaction between lanthanum oxide and alumina lead to the nano-structure where the nanometer-size particles of LaAlO_3 are dispersed in the secondary particles of alumina. The tailored microstructure provides a new nano-structured catalyst of La-alumina, which is stable catalytic support at high temperatures.

© 2009 Published by Elsevier B.V.

1. Introduction

For catalytic combustion, especially for the automotive three-way catalytic (TWC) processes, $\gamma\text{-Al}_2\text{O}_3$ is required to maintain a high surface area for dispersion of the precious metals [1]. The thermal stabilization is important even if the temperature in the catalyst bed rises to over 1000 °C. The phase transformation of $\gamma\text{-Al}_2\text{O}_3$ to thermodynamically stable $\alpha\text{-Al}_2\text{O}_3$ is observed at around 1100 °C and the sintering behavior of alumina itself decreases the surface area. Therefore, the stabilization of $\gamma\text{-Al}_2\text{O}_3$ support is vital to high temperature applications. The previous results of transition aluminas have showed that the impurities or the additives greatly influence the sintering and phase transformations of aluminas. Lanthanum has extremely positive effect of inhibition on the sintering and α -phase transformation [2–16]. However, the chemical state of this additive in aluminas and the formation of microstructure of La-aluminas are still of open question, so that the mechanism of stabilization has not been fully established regarding with the nanometer-level microstructural assessment of lanthanum-modified aluminas. When the high-temperature interaction between $\gamma\text{-Al}_2\text{O}_3$ and La_2O_3 results in the other phase, the morphology and stability of structure are also the subject on heat-stable support. The stabilization of transition aluminas concerns the dependence of processing such as pre-heat treatment.

Here we study the nanometer-ordered structural feature and its development in lanthanum-modified alumina after high temperature treatment around at 1000 °C, regarding with nanometer-size LaAlO_3 formation. Based on the solid-state reaction at the interface between $\gamma\text{-Al}_2\text{O}_3$ and La_2O_3 at high temperature, we provide the controlled nano-composite catalytic alumina support, which is heat-stable at around 1000 °C.

2. Experimental

2.1. Sample preparation

The starting powder of $\gamma\text{-Al}_2\text{O}_3$ is a sample from Sumitomo chemical (Japan), and lanthanum nitrate is high grade reagent of Wako chemicals (Japan). The La-modified samples with different atomic ratios of lanthanum to aluminum (La/Al) were prepared by impregnation of $\gamma\text{-Al}_2\text{O}_3$ with aqueous lanthanum nitrate. The obtained La-modified products were then freeze-dried after freezing at -30°C , and heated at 600 °C for 3 h in air, and then heated at 800–1200 °C for 3 h in air.

2.2. Characterization

The measurements of BET specific surface areas of samples were performed by nitrogen adsorption of N_2 at 77 K after pre-heat treatment of powders at 200 °C for 1 h to remove adsorbed water. The X-ray powder diffraction (XRD) data were measured with a Rigaku rint-2000 diffractometer using $\text{Cu K}\alpha$ radiation, operated at 40 kV and 40 mA. X-ray photoemission spectra were measured using JEOL Jump10 spectrometer for the heat-treated samples. The surface atomic ratio was calculated by software from the each XPS intensity. The microstructure was investigated by transmission electron microscopy (JEOL 2000FX) at 160 kV and a scanning electron microscopy (JEOL JSM6000F) with EDS element analysis apparatus.

* Corresponding author.

E-mail address: ozawa@nitech.ac.jp (M. Ozawa).

3. Results and discussion

3.1. Specific surface area

Table 1 summarizes the BET specific surface areas of some samples that vary with lanthanum content and heat treatment temperature. The effect of La_2O_3 on stabilizing alumina appeared at the temperatures over 1100°C , however at 1000°C the surface area decreased as the La content increased. The thermal stabilization strongly depended on the adding content of lanthanum species, and the optimal content of lanthanum was the La/Al of 0.003–0.015 regarding with surface area if we selected heat treatment temperature at 1200°C . Such results indicate the effect of small amount and well-dispersed lanthanum species on alumina surface to inhibit surface area loss of aluminas. An optimal content of lanthanum modification located in small amount range of La/Al atomic ratio is also observed in practice, depending on processing catalytic powders and operation temperature. As lanthanum content increases to La/Al = 0.05, the retarding influence of lanthanum species relatively decreases at lower temperatures, however the surface area is as high enough as over $70\text{ m}^2/\text{g}$ if a support is used at around 1000°C . The effect of La at around La/Al = 0.05 at elevated temperatures is not a simple inhibition to sintering and transformation but the interaction between alumina and La added. Thus, it suggests the influence of microstructure of La-modified alumina support, which can have surface modified structure and/or complex nanostructure from solid-state reactions.

3.2. Solid-state reaction

Fig. 1 is the XRD patterns of a series of samples heated at 1000°C . The bulk phase changes of aluminas and solid phase interaction between $\gamma\text{-Al}_2\text{O}_3$ and La_2O_3 at high temperature was characterized by XRD. Up to La/Al = 0.015 only γ phase was observed at 1000°C . It should be noted that no reflection characteristic of lanthanum-containing species in XRD patterns for a sample below La/Al = 0.015 was observed at 1000°C . However, for a series of La-modified samples when La/Al is over 0.03 after 1000°C heat treatment, a new phase corresponding to LaAlO_3 was found as in Fig. 1. The LaAlO_3 phase is derived from the solid-state reaction between Al_2O_3 and La_2O_3 at these temperatures, when La content is large. For La-modified alumina with La/Al = 0.05, LaAlO_3 appeared at 800°C , and the content increased as heat treatment temperature was elevated. The crystallite size, which was measured by XRD peak width using the Scherrer's equation was 13 nm at 800°C , 19 nm at 1000°C , and 21 nm at 1100°C . Even when the La/Al goes up to 0.1, the XRD pattern corresponding to crystalline phase is LaAlO_3 at 1000°C . No other phase due to lanthanum species was observed from XRD patterns for these samples at 1000°C . Fig. 2 is the XRD patterns of a series of samples heated at 1200°C . Up to La/Al = 0.03 the other phase corresponding to $\text{LaAl}_{11}\text{O}_{18}$ was formed through further solid-state reaction between Al_2O_3 and LaAlO_3 . However, since the diffraction lines from $\text{LaAl}_{11}\text{O}_{18}$ phase are weak, the main phases are still γ phase and LaAlO_3 phase at these samples. The result should suggest that LaAlO_3 strongly influence both the stability of

Fig. 1. XRD (Cu K α radiation source) patterns of La-modified aluminas heated at 1000°C ((●) $\gamma\text{-Al}_2\text{O}_3$, (▲) LaAlO_3). La/Al ratio; (a) 0, (b) 0.015, (c) 0.03, (d) 0.05.

alumina and its microstructure during solid-state reactions. The XPS data indicated that surface La can react with alumina resulting in nanometer bulk phase when the surface coverage of La exceeds a content of a monolayer oxide (La_2O_3). If the high-temperature interaction between $\gamma\text{-Al}_2\text{O}_3$ and La_2O_3 results in the LaAlO_3 , the morphology depends on the stability of LaAlO_3 on alumina support. Actually, since some amount of La has to be often contained in catalysts as a component besides stabilization additives, this question is important. The XRD suggests that the LaAlO_3 exist as the crystal with a certain volume including spheres with a few nm in diameter, which is corresponding to the coherent length of X-ray wave to produce diffraction amplitude. The practical surface coverage content of La on alumina particles is much lower than

Fig. 2. XRD (Cu K α radiation source) patterns of La-modified aluminas heated at 1200°C ((●) $\gamma\text{-Al}_2\text{O}_3$, (▲) LaAlO_3 , (■) $\text{LaAl}_{11}\text{O}_{18}$). La/Al ratio; (a) 0, (b) 0.015, (c) 0.03, (d) 0.05.

Table 1
Specific surface area of La-modified alumina heated at various temperatures.

Temperature ($^\circ\text{C}$)	Surface area (m^2/g)				
	La/Al				
	0	0.3	1.5	5	10
800	104	95	96	76	—
1000	103	95	92	74	55
1200	45	82	82	59	48

Fig. 3. SEM image of La-modified aluminas with La/Al = 0.05, heated at 1000 °C. (a) Secondary electron image, (b) reflection electron image.

Fig. 4. TEM image of La-modified aluminas with La/Al = 0.05, heated at 1000 °C. (a) Bright field image, (b) dark field image.

La content when La/Al = 0.05, the sample has two parts of purely La-modified alumina and LaAlO₃ particle. This indicates that the small amount of lanthanum can effectively retard the sintering between alumina particles as well as phase transformation of γ to α phase of Al₂O₃. In addition, the LaAlO₃ as particulate state should have some role to maintain the microstructure of alumina catalyst, because LaAlO₃ thus its complex microstructure is thermodynamically stable phase. We have examined the effect of lanthanum to stabilize alumina catalyst support regarding on microstructural aspect, using the data of SEM and TEM, which are newly observed.

3.3. Microstructure

Fig. 3 shows the secondary electron (SEM) and reflection electron images (REM), which are carefully taken using SEM apparatus with high magnification and electron beam width of <3 nm in diameter. The sample is La-modified alumina with La/Al = 0.05 which was heated at 1000 °C for 3 h in air. The SEM indicates the microstructure of the agglomeration of alumina with 100 nm in size after heat treatment. The microstructure is the same as of the initial sample, however the grain growth is slightly higher as the effect of heat treatment. The REM image provided the novel information on microstructure, because the emission efficient of reflection electron is different between the elements including Al and La. In Fig. 3, the bright particles are observed only in the reflection electron image. The bright contrast suggests the high concentration of La, which is a heavier metal element than Al. The particle-size was determined as 10–20 nm in diameter, and existed at the inner part of the secondary particle of alumina, as in (b) of Fig. 3, which demonstrates the novel structure of alumina/LaAlO₃ nano-composite. Since the XRD indicates the crystalline phases of γ -Al₂O₃ and LaAlO₃, this

bright contrast should correspond to LaAlO₃. The solid-state reaction between Al₂O₃ and La₂O₃ lead to thermodynamically stable LaAlO₃. Then, the structure was analyzed by TEM as in Fig. 4. The TEM micrograph shows a set of bright and dark field image with high magnification. The electron diffraction contains ring-type polycrystalline patterns and some reciprocal lattice spots that correspond to γ -Al₂O₃ and LaAlO₃, respectively. The dark field image is obtained using a diffraction spot from (0 1 2) of LaAlO₃, so that the LaAlO₃ particle is highlighted as a bright area. The corresponding microstructure to both image are agreed as that the particles of LaAlO₃ exit in the nanometer particulate matrix of γ -Al₂O₃. Both phases consist of small grains in nanometer-size and combined each other to make a composite where particles with 10–20 nm in size are intersecting LaAlO₃ phase and its dispersing structure become due to the solid-sate reaction after heat treatment, so that the composite catalyst is stable and heat resistant with respect of microstructure. The nano-composite, where LaAlO₃ particles have dispersed to stabilize the metastable γ -Al₂O₃ matrix, and its formation process are revealed for the first time in our study. Thus we propose an interesting nano-structured alumina catalytic material that is novel, stable and providing possible catalytic function.

4. Conclusion

Nanometer-ordered structural changes of lanthanum-modified γ -alumina at elevated temperature were examined for application toward novel heat-stable catalytic support. The SEM and TEM determined that the solid-state reaction between lanthanum oxide and alumina lead to the nanometer-ordered structure, where LaAlO₃ particles are dispersed in the secondary particles of alumina after heat treatment. The tailored La-modification to alumina support and its processing provides a novel nano-structured catalyst in

the system of La and alumina, which is very stable catalytic support at elevated temperatures.

Acknowledgment

Work partially supported by City-area program project in Western-Tono “Development of Environmentally friendly ceramics” by Ministry of Education, Culture, Sports, Science and Technology of Japan Government.

References

- [1] Y.F. Chu, E. Ruckenstein, *J. Catal.* 55 (1978) 281.
- [2] H. Schaper, E.B.M. Doesburg, L.L. Van Reijen, *Appl. Catal.* 7 (1983) 211.
- [3] H. Schaper, E.B.M. Doesburg, P.H.M. De Korte, L. Van Reijen, *Solid State Ionics* 16 (1985) 261.
- [4] P. Burtin, J.P. Brunelle, M. Soustelle, *Appl. Catal.* 34 (1987) 225.
- [5] F. Oudet, P. Courtine, A. Vejux, *J. Catal.* 144 (1988) 122.
- [6] M. Bettman, R.E. Chase, K. Otto, W.H. Weber, *J. Catal.* 117 (1989) 447.
- [7] M. Ozawa, M. Kimura, A. Isogai, *J. Less-Common Met.* 162 (1990) 297.
- [8] M. Ozawa, M. Kimura, *J. Mater. Sci. Lett.* 9 (1990) 291.
- [9] B. Beguin, E. Garbowski, M. Primet, *Appl. Catal.* 75 (1991) 119.
- [10] J.S. Church, N.W. Cant, D.L. Trimm, *Appl. Catal. A* 101 (1993) 105.
- [11] M. Ozawa, H. Toda, S. Suzuki, *Appl. Catal. B* 8 (1996) 141.
- [12] K.-N.P. Kumar, J. Tranto, J. Kumar, J.E. Engell, *J. Mater. Sci. Lett.* 15 (1996) 266.
- [13] C.-K. Loong, J.W. Richardson Jr., M. Ozawa, *J. Alloys Compd.* 250 (1997) 356.
- [14] M. Ozawa, S. Suzuki, H. Toda, *J. Am. Ceram. Soc.* 80 (1997) 1957.
- [15] Y. Nishio, M. Ozawa, *J. Alloys Compd.* 374 (2004) 397.
- [16] Y. Nishio, M. Ozawa, *J. Ceram. Soc. Jpn.* 115 (2007) 633.

Spontaneous generation of voltage in the magnetocaloric compound $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ and elemental Gd

M. Zou^{a,b}, V.K. Pecharsky^{a,b,*}, K.A. Gschneidner Jr.^{a,b}, D.L. Schlager^a, T.A. Lograsso^a

^a Ames Laboratory of the US DOE, Iowa State University, Ames, IA 50011–3020, USA

^b Department of Materials Science and Engineering, Iowa State University, Ames, IA 50011–2300, USA

ARTICLE INFO

Article history:

Received 5 June 2008

Accepted 6 September 2008

Available online 23 October 2008

Keywords:

Intermetallics

Electronic transport

Magnetically ordered materials

Magnetocaloric effect

ABSTRACT

The spontaneous generation of voltage (SGV) in single crystalline $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ and Gd has been studied. Temperature-induced SGVs were observed along the three principal crystallographic axes of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$, but not in Gd. Field-induced SGVs were observed with magnetic fields less than 40 kOe applied along the *a*-axis of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$, and the *c*-axis of Gd. The absence of the temperature-induced SGV in Gd indicates the key role first-order phase transformations play in the appearance of the effect when temperature varies. The anisotropy of the magnetic field-induced SGV in $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ and the existence of the field-induced SGV in Gd, highlight the importance of the magnetocaloric effect in bringing about the SGV.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Interesting physical properties, such as the giant magnetocaloric effect (GMCE), giant magnetoresistance (GMR), colossal magnetostriction, and spontaneous generation of voltage (SGV) [1–3] are known to occur in rare earth intermetallic compounds $\text{R}_5(\text{Si}_x\text{Ge}_{1-x})_4$, where R is a lanthanide element. All of these effects originate from first-order coupled magnetic and crystallographic phase transformations when $\text{R} = \text{Gd}$ [1]. When $0 < x \leq 0.3$, the phase transformation is between a ferromagnetic orthorhombic phase [O(I)/FM] and a different orthorhombic phase in its antiferromagnetic state [O(II)/AFM]. When $0.4 < x \leq 0.503$, the transformation is between a ferromagnetic orthorhombic phase [O(I)/FM] and a paramagnetic monoclinic phase [M/PM]. Temperature, magnetic field, and/or pressure have been identified as triggers of these transformations [1,4].

Different from $\text{Gd}_5(\text{Si}_x\text{Ge}_{1-x})_4$, the magnetic and crystallographic phase transformations of $\text{Tb}_5(\text{Si}_x\text{Ge}_{1-x})_4$ between O(I)/FM and M/PM are decoupled by ~ 10 K and less than 5 K when $x = 0.5$ and 0.55, respectively [5–7]. These independent magnetic and crystallographic phase transformations can be recoupled by applying moderate hydrostatic pressures and/or magnetic fields as has been demonstrated for a polycrystalline sample with $x = 0.5$ and a single

crystal with $x = 0.55$ [6,8]. The recoupling results in a 40% enhancement of the GMCE in polycrystalline $\text{Tb}_5\text{Si}_2\text{Ge}_2$ ($x = 0.5$) [8]. It is worth noting that in a single crystal of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ ($x = 0.55$), the GMCE only occurs when the magnetic field is applied parallel to the *a*- and *c*-axes [6]. Interplay between decoupling and recoupling of the magnetic and structural transformations indicates a complex energy landscape separating different magnetic and crystallographic phases, and the complexity is enhanced by the single ion anisotropy of Tb^{3+} when compared to $\text{R} = \text{Gd}^{3+}$ [6].

The SGV has been observed in both polycrystalline and single crystalline $\text{Gd}_5(\text{Si}_x\text{Ge}_{1-x})_4$ in the vicinity of the Curie temperature (T_C) when either temperature was varied at constant field or when magnetic field was changed isothermally [2,3]. The origin of SGV in these compounds is believed to be thermoelectric power, i.e., Seebeck effect [2,3]. Because a small compositional difference is always present between the two ends of a sample and because small temperature gradients are always present across a sample when its temperature is actively controlled, phase transformation typically starts at one end of the specimen and then propagates to the other. The heat release or absorption during this process gives rise to measurable temperature gradients necessary for the generation of the thermoelectric signal.

The study of SGV in $\text{Tb}_5(\text{Si}_x\text{Ge}_{1-x})_4$ compounds is a continuation of previous studies of $\text{Gd}_5(\text{Si}_x\text{Ge}_{1-x})_4$ [2,3]. To gain a better understanding of the role that different factors play in the appearance of the SGV, a single crystal of Gd metal has also been examined with respect to both temperature and magnetic field-induced spontaneous voltage. Among the materials undergoing second order magnetic order–disorder transformations, elemental Gd has one

* Corresponding author at: Ames Laboratory of the US DOE, Iowa State University, Ames, IA 50011–3020, USA.

E-mail addresses: zoumin@iastate.edu (M. Zou), vtkp@ameslab.gov (V.K. Pecharsky).

Fig. 1. The SGV of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ as a function of temperature measured along the a -, b -, and c -axes upon heating and cooling at various rates in a zero magnetic field.

of the highest MCE's around room temperature, which is about half that observed in $\text{Gd}_5(\text{Si}_x\text{Ge}_{1-x})_4$ [9]. A small anisotropy due to dipolar and spin–orbit couplings results in the c -axis of Gd being the magnetic easy axis immediately below $T_C = 293$ K [10,11].

2. Experimental

Two $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ single crystals were grown by the tri-arc method [12] from high purity Tb, Si and Ge mixed in the appropriate stoichiometry. The two Tb stocks [99.67 at.% (99.97 wt.%) and 99.89 at.% (99.99 wt.%) pure with respect to all other elements in the periodic table] were prepared by the Materials Preparation Center (MPC) of the Ames Laboratory [13]. The Si and Ge were purchased from commercial vendors, and were better than 99.999 wt.% pure. The as-grown crystals were oriented by using backscatter Laue X-ray diffraction.

Three rectangular parallelepiped samples were cut by spark erosion. They were $5.03 \text{ mm} \times 0.98 \text{ mm} \times 0.44 \text{ mm}$, $3.38 \text{ mm} \times 0.94 \text{ mm} \times 0.57 \text{ mm}$, and $4.66 \text{ mm} \times 1.02 \text{ mm} \times 0.82 \text{ mm}$ with the longest dimensions of each along the a -, b -, and c -axes, respectively. The a - and b -axes samples came from the single crystal prepared using 99.67 at.% pure Tb metal, and the c -axis sample came from the 99.89 at.% pure Tb. Four thin platinum wires were attached to each sample with H20E Epotek silver epoxy manufactured by Epoxy Technology. The samples were also used for an electrical resistivity study, results of which will be published elsewhere. The distances between the voltage contacts were 1.20, 1.14, and 3.03 mm for the a -, b -, and c -axes samples, respectively. Typical contact resistances of the freshly prepared samples were between 1 and 2 Ω .

The single crystal Gd was prepared using the strain-anneal method from polycrystalline Gd metal also prepared by the MPC. The metal was 99.89 at.% (99.98 wt.%) pure with respect to all other elements in the periodic table. A rectangular parallelepiped sample was cut using the spark erosion technique from a large grain. Its dimensions were $9.12 \text{ mm} \times 3.02 \text{ mm} \times 1.21 \text{ mm}$ with the longest side along the c -axis. Four thin platinum wires were attached to the sample by using a spot welding technique. The distance between the voltage contacts was 7.60 mm. Contact resistance of the freshly prepared samples was below 1 Ω . The SGV mea-

suring method, instrument set up, and experiment errors were described elsewhere [3].

3. Results and discussion

As shown in Fig. 1, temperature-induced SGV appears along all three major crystal axes of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ between 110 and 118 K, where the crystallographic and magnetic phase transformations occur [6,7]. The SGV starting temperatures are different upon heating and cooling by ~ 5 K. This separation is nearly the same as the extent of thermal hysteresis of the crystallographic phase transformation [6]. Therefore, one can associate the SGV with the crystallographic transformation. Fig. 1 also shows that the SGV increases with the increased rate of temperature change, which is similar to that observed in $\text{Gd}_5\text{Si}_2\text{Ge}_2$ [3]. On the other hand, a magnetic field of 40 kOe and lower can trigger the SGV only when the field vector is parallel to the a -axis. A representative result at 120 K is displayed in Fig. 2. This observation is different from $\text{Gd}_5\text{Si}_2\text{Ge}_2$, where the SGV occurs when a magnetic field is isothermally applied along any of the three major crystallographic directions in the vicinity of T_C [3].

Both neutron and X-ray powder diffraction studies of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ illustrate a temperature-induced first-order crystallographic phase transformation involving a large unit cell volume change of $\sim 1\%$ [6,7]. By rearranging the Clausius–Clapeyron equation [14] $(dP/dT) = (\Delta S/\Delta V) = (\Delta E/T \Delta V) \rightarrow \Delta E = T(dP/dT)\Delta V$, where P , T , S , V , and E are the pressure, temperature, entropy, volume, and enthalpy, respectively, it is obvious that the enthalpy change,

Fig. 2. The SGV of $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ as a function of magnetic field applied along the a -, b -, and c -axes at 120 K. The field change rate is ~ 40 kOe/min. The arrows mark the directions of the magnetic field changes.

i.e., latent heat, is proportional to the unit cell volume change. The latent heat in turn determines the temperature gradient across the sample when its crystallographic phase transformation starts from one end of the specimen and then propagates to another. Since temperature is a scalar, the appearance of SGV does not depend on the orientations of the samples. Therefore, temperature-induced SGV appears along all three major crystal axes, and depends on the latent heat of the first-order phase transformation.

The anisotropy of the magnetic field-induced SGV in $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ is in line with its highly anisotropic metamagnetism and magnetocaloric effect (MCE) [6]. Both the $\text{PM} \leftrightarrow \text{FM}$ metamagnetism and GMCE occur only with $\mathbf{H} \parallel \mathbf{a}$ when $H \leq 40$ kOe [6]. The absence of SGV with $\mathbf{H} \parallel \mathbf{b}$ and $\mathbf{H} \parallel \mathbf{c}$ when $H \leq 40$ kOe (Fig. 2) confirms that it is the magnetocaloric effect that is responsible

for the temperature gradients necessary for the observation of the field-induced SGV.

The roles played by latent heat and MCE in SGV were further studied by using a single crystal of Gd metal. No SGV occurs in the vicinity of $T_C = 293$ K as long as the magnetic field remains constant. Since the phase transition at T_C is a pure second order magnetic one, no latent heat is involved here. The absence of SGV in the elemental Gd near T_C supports the notion that the temperature-induced SGV depends on the latent heat of the first-order phase transformation.

The SGV in Gd can be triggered by applying a magnetic field isothermally in the vicinity of T_C . Fig. 3 exhibits the SGV of Gd as a function of magnetic field applied along the c -axis between 278 and 304 K with a field increasing at the rate of ~ 40 kOe/min. The largest magnitude of SGV, which is taken as the voltage difference between the positive and negative peaks, is ~ 2 μV . It is observed at 294 K, i.e., in the immediate vicinity of the maximum MCE, which occurs at 293 K. This is much smaller than the SGV of $\text{Gd}_5\text{Si}_2\text{Ge}_2$ [3] and $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ single crystals (see Fig. 2). Consistent with the behavior of the MCE in Gd, which decreases gradually as the temperature is further and further away from T_C , (see Ref. [15]), the magnitude of the SGV signal exhibits a similar reduction with temperature as is clearly seen in Fig. 3. Furthermore, since the thermoelectric signal is proportional to the temperature difference (ΔT) between two ends of a specimen, and $\text{Gd}_5\text{Si}_2\text{Ge}_2$ and $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ have a greater MCE compared to that of Gd, one concludes that the MCE determines ΔT , and therefore, determines the magnitude of the magnetic field-induced SGV.

4. Conclusions

Temperature-induced SGV has been observed in $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ along three major crystallographic axes near T_C , but not in a Gd single crystal. This suggests that a phase transformation involving a large volume change, i.e., a large latent heat, is necessary for the temperature-induced SGV. The magnetic field-induced SGV has been observed in $\text{Tb}_5\text{Si}_{2.2}\text{Ge}_{1.8}$ near T_C only with $\mathbf{H} \parallel \mathbf{a}$, but not with $\mathbf{H} \parallel \mathbf{b}$ and $\mathbf{H} \parallel \mathbf{c}$ when $H \leq 40$ kOe. The field-induced SGV has also been observed in Gd near T_C . These observations indicate that a first-order magnetostructural phase transformation is not a necessary condition for SGV to occur. But a large MCE for the magnetic field-induced SGV is necessary for the latter in order to be observed.

Acknowledgements

This work was supported by the US Department of Energy, Office of Basic Energy Sciences, Office of Science. The Ames Laboratory is operated for the US DOE by Iowa State University under Contract No. DE-AC02-07CH11358.

References

- [1] V.K. Pecharsky, K.A. Gschneidner Jr., *Pure Appl. Chem.* 79 (2007) 1383, and references therein.
- [2] E.M. Levin, V.K. Pecharsky, K.A. Gschneidner Jr., *Phys. Rev. B* 63 (2001) 174110.
- [3] M. Zou, H. Tang, D.L. Schlager, T.A. Lograsso, K.A. Gschneidner Jr., V.K. Pecharsky, *J. Appl. Phys.* 99 (2006) 08B304.
- [4] Ya. Mudryk, Y. Lee, T. Vogt, K.A. Gschneidner Jr., V.K. Pecharsky, *Phys. Rev. B* 71 (2005) 174104.
- [5] L. Morellon, C. Ritter, C. Magen, P.A. Algarabel, M.R. Ibarra, *Phys. Rev. B* 68 (2003) 024417.
- [6] M. Zou, Ya. Mudryk, V.K. Pecharsky, K.A. Gschneidner Jr., D.L. Schlager, T.A. Lograsso, *Phys. Rev. B* 75 (2007) 024418.
- [7] V.O. Garlea, J.L. Zarestky, C.Y. Jones, L.-L. Lin, D.L. Schlager, T.A. Lograsso, A.O. Pecharsky, V.K. Pecharsky, K.A. Gschneidner Jr., C. Stassis, *Phys. Rev. B* 72 (2005) 104431.
- [8] L. Morellon, Z. Arnold, C. Magen, C. Ritter, O. Prokhnenko, Y. Skorokhod, P.A. Algarabel, M.R. Ibarra, J. Kamarad, *Phys. Rev. Lett.* 93 (2004) 137201.
- [9] A.M. Tishin, Y.I. Spichkin, *The Magnetocaloric Effect and its Applications*, Institute of Physics, Bristol/Philadelphia, 2003.

Fig. 3. The SGV of Gd as a function of magnetic field applied along the c -axis at constant temperatures between 278 and 304 K. The measurements were carried out with field increasing at a rate of ~ 40 kOe/min.

- [10] J. Jensen, A.R. Mackintosh, *Rare Earth Magnetism—Structures and Excitations*, Oxford Science Publications, Oxford, UK, 1991.
- [11] Y.I. Spichkin, A.V. Derkach, A.M. Tishin, M.D. Kuz'min, A.S. Chernyshov, K.A. Gschneidner Jr., V.K. Pecharsky, *J. Magn. Magn. Mater.* 316 (2007) e555.
- [12] D.L. Schlager, T.A. Lograsso, A.O. Pecharsky, J.A. Sampaio, in: H. Kvande (Ed.), *Light Metals 2005*, The Minerals Metals and Materials Society, TMS, Warrendale, PA, 2005, p. 1177.
- [13] Materials Preparation Center, Ames Laboratory of US DOE, Ames, IA, U.S.A., www.mpc.ameslab.gov.
- [14] M.W. Zemansky, R.H. Dittman, *Heat and Thermodynamics*, 7th ed., McGraw-Hill, New York, 1997.
- [15] S.Yu. Dan'kov, A.M. Tishin, V.K. Pecharsky, K.A. Gschneidner Jr., *Phys. Rev. B* 57 (1998) 3478.

Possible two-band superconductivity in PuRhGa₅ and CeRhIn₅E.D. Bauer^{a,*}, Tuson Park^{a,b}, R.D. McDonald^a, M.J. Graf^a, L.N. Boulaevskii^a, J.N. Mitchell^a, J.D. Thompson^a, J.L. Sarrao^a^a Los Alamos National Laboratory, Los Alamos, New Mexico 87545, USA^b Department of Physics, Sungkyunkwan University, Suwon 440-746, Republic of Korea

ARTICLE INFO

Article history:

Received 16 July 2008

Accepted 6 October 2008

Available online 12 December 2008

Keywords:

Actinide alloys and materials

Superconductors

Heavy fermions

Lanthanide alloys and materials

ABSTRACT

Measurements of the upper critical field H_{c2} of the Pu-based heavy-fermion superconductor PuRhGa₅ have been made using a torque magnetometer at temperatures down to 0.6 K and magnetic fields up to 17 T along the principal axes of the tetragonal structure. A linear temperature dependence of H_{c2} down to $T_c/10$ for $H||c$ and to $T_c/2$ for $H||ab$ is observed. While the data appear to be inconsistent with both purely Pauli limiting or orbital effects governing the upper critical field, the linear T -dependence of H_{c2} is well described by a two-band model of superconductivity involving coupled bands of heavy and light electrons. A close similarity between PuRhGa₅ and the pressure-induced antiferromagnetic isostructural superconductor CeRhIn₅ is also found.

Published by Elsevier B.V.

1. Introduction

A class of lanthanide- or actinide bearing intermetallic compounds in which the f -electrons are close to a valence instability and hybridize strongly with conduction electrons of neighboring ligands, giving rise to an enhanced effective mass often 1000 times larger than simple metals such as copper, have generated considerable interest for the last 25 years [1,2]. In a few of these heavy-fermion materials, superconductivity is found to intimately involve a dense array of magnetic f -electrons and, in many cases, to coexist with long-range magnetic order, providing a rich playground to investigate the interplay of magnetism and superconductivity. The CeMIn₅ family of heavy-fermion superconductors are the most recent prototypical example of this playground [3]. In these compounds, the coexistence of antiferromagnetism and superconductivity under pressure in CeRhIn₅ [4,5] or with chemical substitution (e.g., CeRh_{1-x}Ir_xIn₅ [6], CeRh_{1-x}Co_xIn₅ [7]), and a new magnetic phase deep within the superconducting state near the upper critical field in CeCoIn₅ [8,9], are just some of the emergent phenomena indicating that the superconductivity is unconventional, involving electrons paired in finite angular momentum and spin states through magnetic fluctuations, and is strongly coupled to the magnetism. While no direct evidence for the coexistence of magnetic order and superconductivity has been found in the isostructural PuMGa₅ (M = Co, Rh) materials, which have transition

temperatures of $T_c = 18.5$ [10] and $T_c = 8.7$ K [11], respectively, a number of similarities with their CeMIn₅ counterparts, including the powerlaw behavior of the superconducting specific heat and spin-lattice relaxation rate and the linear variation of the ratio of the tetragonal lattice parameters with the superconducting transition temperature T_c [12,13], indicate that the superconductivity may also be unconventional in these PuMGa₅ materials. In the following, we report the similarity of the upper critical field in PuRhGa₅ and CeRhIn₅ at a pressure where CeRhIn₅ exhibits the coexistence of antiferromagnetic order and superconductivity [5], suggesting proximity to magnetism in PuRhGa₅.

2. Experimental details

Single crystals of PuRhGa₅ and CeRhIn₅ were grown by Ga and In flux, respectively. Magnetization measurements were performed on PuRhGa₅ using a capacitive torque magnetometer in magnetic fields up to 17 T at temperatures between 0.5 K and 300 K in a cryostat equipped with a HEPA-filtered gas handling system. The magnetometer was immersed in ³He liquid/gas to ensure good thermalization of the sample and minimize the effects of self-heating due to the radioactive decay of ²³⁹Pu. The orientation of the magnetic field along the a - and c -crystallographic directions was achieved by alignment perpendicular to the natural faces of a rectangular PuRhGa₅ single crystal and confirmed by the observed anisotropy of the upper critical field. The superconducting upper critical field was determined as the inflection of the step in torque, and was unambiguously identified as being associated with superconductivity by performing set of zero-field cooled sweeps, which exhibited strong hysteresis associated with the trapping of flux as the field is reduced below H_{c2} , and subsequent thermal cycling in low field (< 0.1 T), where the magnetic hysteresis was observed to collapse at temperatures exceeding T_c as the trapped flux was released. The maximum relative deflection of the magnetometer, and hence the sample alignment, as a function of magnetic field and temperature is less than 1°. The actual angle of the magnetic field with respect to the crystallographic axes was determined to be $\sim 20^\circ$ from the c -axis by scaling the observed upper critical field

* Corresponding author. Tel.: +1 505 665 0942.

E-mail address: edbauer@lanl.gov (E.D. Bauer).

Fig. 1. Change in capacitance ΔC (torque) vs. magnetic field H of PuRhGa₅ at 1.6 K (red triangles) and 0.62 K (blue stars), with $H \parallel \theta \sim 20^\circ$ from the c -axis. The upper critical field H_{c2} is determined by the sharp drop in ΔC at 15.5 T at 1.6 K. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

H_{c2} to that of Haga et al. [14], and is consistent with previous measurements of the angular dependence of H_{c2} [14].

3. Results

Fig. 1 shows the torque ($\propto$ magnetization), plotted as the difference in capacitance ΔC , vs. magnetic field up to 17 T of PuRhGa₅ at temperatures of 0.62 K and 1.6 K for $H \parallel c$. At 1.6 K, a clear signature of the upper critical field, denoted by the large change in ΔC and subsequent hysteresis between the zero-field-cooled (ZFC) and field-cooled curves. The lack of a similar anomaly and hysteresis in the ZFC/FC curves up to 17 T at 0.62 K indicates that the upper critical field is above 17 T at 0.62 K.

The upper critical field $H_{c2}(T)$ of PuRhGa₅ is displayed in Fig. 2 (scaled to account for the misalignment) for $H \parallel c$ and $H \parallel ab$, along with the results of Haga et al. [14]. For both field directions, H_{c2} is linear in temperature, and extends down to $\sim T_c/10$ for $H \parallel c$. Extrapolating the upper critical field linearly to zero temperature yields the values $H_{c2}^{ab} = 31.1$ T and $H_{c2}^c = 17.3$ T. This anisotropy of $H_{c2}^{ab}/H_{c2}^c = \beta = 1.8$ in PuRhGa₅ is comparable to the anisotropy of the upper critical field of the pressure-induced superconductor CeRhIn₅ at 14.7 kbar ($\beta = 1.7$) and of CeCoIn₅ ($\beta = 2.4$) and presumably reflects cylindrical (two-dimensional) nature of the Fermi surface in these “115” materials [15–17]. It should be noted that the anisotropy of H_{c2} of PuCoGa₅ near T_c is considerably smaller ($\sim 10\%$); further measurements at higher magnetic fields are required to determine whether this smaller H_{c2} anisotropy persists to lower temperature.

Fig. 2. Upper critical field $H_{c2}(T)$ of PuRhGa₅ for $H \parallel c$ (open blue circles) and $H \parallel ab$ (open red squares) in the present study and data from Ref. [14] for $H \parallel c$ (filled blue circles) and $H \parallel ab$ (filled red squares). The solid lines are the theoretical predictions for a purely orbital critical field [18] using the initial slopes of $dH^c/dT|_{T_c} = -2.0$ T/K and $dH^{ab}/dT|_{T_c} = -3.6$ T/K. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

4. Discussion

A magnetic field may suppress superconductivity in two main ways. The orbital supercurrents surrounding the flux lines produced by the external field in the mixed state will break the Cooper pairs when the kinetic energy of the orbital currents exceeds the superconducting condensation energy, leading to a suppression of superconductivity and the upper critical field. The applied field will also interact with the spins of the superconducting electron pair via the Zeeman effect. The upper critical field data of PuRhGa₅ are compared to the limiting case of these two effects within a single-band model, to coupled superconducting order parameters in a two-band model, and also to those of the pressure-induced antiferromagnetic superconductor CeRhIn₅ in the following sections.

4.1. Single-band superconductivity

In the presence of a Zeeman term it is well known that for the case of a single conduction band with isotropic gapped superconductivity, the normal state is favored over the superconducting state when the magnetic energy exceeds the condensation energy $(1/2)\chi_P H^2 > (1/2)N_f \Delta_0^2$, where χ_P is the Pauli susceptibility, Δ_0 is the zero-temperature superconducting gap, and N_f is the density of states per spin. The Pauli limiting critical field is then given by $H_P = \Delta_0 / \sqrt{2} \mu_B$ (assuming a g -factor of 2), where μ_B is the Bohr magneton. In this fully gapped case with $T_c = 8.7$ K, the Pauli limiting field is $H_P = 1.84 T_c = 16.0$ T for PuRhGa₅. This value is slightly modified for an order parameter with nodes (i.e., d -wave), as indicated by NMR measurements on PuRhGa₅ [19], the Pauli field is $H_P = 1.77 T_c = 15.2$ T [20]. As illustrated in Fig. 2, H_P agrees with $H_{c2}^c(0)$ for PuRhGa₅, but $H_{c2}^{ab}(0)$ exceeds this value and cannot be reconciled with a purely Pauli limiting field without an unlikely g -factor anisotropy. This fact, along with the linear T -dependence of H_{c2} , would suggest that PuRhGa₅ is not Pauli limited. In addition, $H_{c2}^c(0)$ is larger than expected for pure orbital contribution to the upper critical field [18], $H_{c2}^c(0) = -0.7 T_c dH/dT|_{T_c} = 12.4$ T, which is predicted to have a nearly quadratic temperature dependence close to zero temperature, as shown in Fig. 2. Spin-orbit coupling could, in principle, lead to better agreement with the experimental $H_{c2}^c(0)$, but would not yield the T -linear dependence of the upper

critical field down to $T_c/10$ in PuRhGa₅. An alternative explanation for the upper critical fields may be a two-band model as discussed below.

4.2. Two-band superconductivity

The observed anomalous linear temperature dependence of H_{c2} in Fig. 2 may be understood in terms of a two-band model of superconductivity. Assuming that the superconducting order parameter of a heavy f -electron band is coupled to an order parameter of a light d -electron band, the response to a magnetic field may be gradually tuned between the heavy and light band to obtain a nearly linear temperature dependence. Near T_c and $H \approx 0$ the heavy band will dominate, while at low temperatures and high fields the light band will dominate the magnetic response. To this end, a Ginzburg–Landau (GL) two-band model is constructed to capture the essential behavior of the upper critical field yielding a qualitative explanation of the H – T phase diagram with a small set of parameters. The GL functional of the coupled heavy (1) and light (2) bands are written as $F = F_1 + F_2 + F_{12}$, with $F_i = a_i(T)|\psi_i|^2 + (1/2)b_i|\psi_i|^4 + \kappa_i[(\nabla - i(e/\hbar c)\mathbf{A})\psi_i]^2$, and coupling term $F_{12} = \eta(\psi_1\psi_2^* + \psi_1^*\psi_2 - |\psi_1|^2 - |\psi_2|^2)$. The GL parameters are $a_i(T) = \alpha_i[T - T_i(1 - v_i H^2)]$ and $b_i = \alpha_i\beta$. Here T_i is the critical transition temperature in the absence of coupling, $v = 0$, while $\mathbf{H} = \nabla \times \mathbf{A}$ is the magnetic field inside the superconductor. The factor $(1 - v_i H^2)$ accounts for the Zeeman effect and the spin-split conduction bands with $v_i = \frac{7\zeta(3)}{4\pi^2}((g/2)\mu_B/T_i)^2$.

Minimization of the free energy results in the coupled GL equations. The transition temperature is obtained by solving the linearized GL equations at $\mathbf{H}=0$ for a uniform superconductor, which gives $T_c = [T_1 + T_2 + \gamma_1 + \gamma_2 \pm T_0]/2$, with $\gamma_i = \eta/\alpha_i$ and $T_0 = \sqrt{(T_1 - T_2)^2 + 4\gamma_1\gamma_2}$.

Next, in order to calculate the upper critical magnetic field, we solve the coupled linearized GL equations in a magnetic field assuming the Abrikosov vortex lattice solution. After some lengthy calculations, and neglecting the Zeeman term, the upper critical field is found to be

$$H_{c2}(T) = \frac{h_1 h_2}{2} \left[t_1 + t_2 \pm \sqrt{(t_2 - t_1)^2 + 4\gamma_1\gamma_2/(h_1 h_2)} \right] \quad (1)$$

where $t_1 = (T_1 + \gamma_1 - T)/h_2$ and $t_2 = (T_2 + \gamma_2 - T)/h_1$, and h_i are the slopes of the upper critical fields. When including the Zeeman term, it is easier to solve for $T_c(H)$, which is given by

$$T_c(H) = \frac{1}{2} \left[T_0(H) \pm \sqrt{T_0(H)^2 + 4D(H)} \right] \quad (2)$$

where $D(H) = \gamma_1\gamma_2 + \tilde{T}_1\tilde{T}_2 + H((\tilde{T}_1/h_2) + (\tilde{T}_2/h_1)) - (H^2/h_1 h_2)$, $T_0(H) = \tilde{T}_1 + \tilde{T}_2 + (H/h_1) + (H/h_2)$, and $\tilde{T}_i = T_i(1 - v_i H^2) + \gamma_i$. Fig. 3 shows the upper critical fields for a specific choice of GL parameters with a small coupling term $\eta = 0.06$ K and $\alpha_1 = 10\alpha_2 = 10$ K (density of states $N_f^i \propto \alpha_i$). By including the Zeeman term, which leads to significantly Pauli-limited upper critical fields, good agreement to the observed measurements is obtained (Fig. 3). However, the results at temperatures below $T_c/2$ should be considered with care, because at such low temperatures and high magnetic fields (i) the GL expansion is no longer valid and (ii) the coefficients β_i and κ_i may change sign leading to a first-order phase transition or new phases, such as a Fulde–Ferrell–Larkin–Ovchinnikov state, observed in the isostructural compound CeCoIn₅ [21].

4.3. Isostructural compound CeRhIn₅

The linear temperature dependence of the upper critical field has also been observed in the isostructural compound CeRhIn₅

Fig. 3. Upper critical field within two-band Ginzburg–Landau model with bare transition temperatures $T_1 = 8.55$ K, $T_2 = 7.3$ K and slopes $h_1 = -1.8$ T/K, $h_2 = -4.5$ T/K for $H||c$ and $h_1 = -4.0$ T/K, $h_2 = -70$ T/K for $H||ab$. The solid (dashed) lines are with (without) the Zeeman effect. The dotted curves are bare phase transition lines in the two-band model. The symbols are measurements of PuRhGa₅ for $H||c$ (blue circles) and $H||ab$ (filled red squares). (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

at $P = 14.7$ kbar where unconventional superconductivity coexists with long-range antiferromagnetic order. As shown in the inset of Fig. 4, the upper critical field of CeRhIn₅ is linear in temperature down to the lowest temperature measured for both field directions, with an anisotropy similar to that of PuRhGa₅. As we have shown [22], H_{c2} can qualitatively be described within a two-band model of superconductivity in CeRhIn₅ at $P = 14.7$ kbar, in which a band of light, weakly hybridized electrons that dominate the antiferromagnetic state, is (weakly) coupled to one composed of heavy, strongly hybridized superconducting electrons. The remarkable similarity between H_{c2} of both compounds is more clearly illustrated in Fig. 4 where it is scaled by the zero-temperature value $H/H_{c2}(0)$ vs. T/T_{c0} . While PuRhGa₅ is not in an ordered state at low temperature, it does appear to be closer to magnetic order than PuCoGa₅ [13], for which

Fig. 4. Upper critical field, scaled by the zero-temperature value $H/H_{c2}(0)$ vs. T/T_{c0} of PuRhGa₅ for $H||c$ (blue circles) and $H||ab$ (red squares) [data (closed symbols) from Ref. [14]] and CeRhIn₅ at $P = 14.7$ kbar for $H||c$ (blue triangles) and $H||ab$ (red triangles). Inset: Anisotropic upper critical field of CeRhIn₅ at $P = 14.7$ kbar for $H||c$ (blue triangles) and $H||ab$ (red triangles). (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

there is evidence for an itinerant and localized “dual-nature” of the $5f$ -electrons [23]; perhaps these more localized f -electrons in PuRhGa_5 comprise the heavy band, while the itinerant f -electrons contribute to the light within this two-band model of superconductivity; further work is underway to test this two-band scenario in these PuMGa_5 superconductors and to fully characterize the nature of their $5f$ -electrons.

5. Conclusions

The upper critical field H_{c2} of PuRhGa_5 has been determined by means of torque magnetometer measurements at temperatures down to 0.6 K and magnetic fields up to 17 T. A linear temperature dependence of H_{c2} are inconsistent with both purely Pauli limiting or orbital effects dominating the upper critical field within a single-band model, but is well-described by a two-band model of superconductivity involving coupled bands of heavy and light electrons. A close similarity between PuRhGa_5 and the pressure-induced superconductor CeRhIn_5 suggests that PuRhGa_5 may be more localized than its isostructural counterpart PuCoGa_5 .

Acknowledgment

Work at Los Alamos was performed under the auspices of the U.S. DOE.

References

- [1] Z. Fisk, H.R. Ott, T.M. Rice, J.L. Smith, *Nature* 320 (1986) 124–129.
- [2] G.R. Stewart, *Rev. Mod. Phys.* 56 (1984) 755–787.
- [3] J.D. Thompson, M. Nicklas, A. Bianchi, R. Movshovich, A. Llobet, W. Bao, A. Malinowski, M.F. Hundley, N.O. Moreno, P.G. Pagliuso, J.L. Sarrao, S. Nakatsuki, Z. Fisk, R. Borth, E. Lengyel, N. Oeschler, G. Sparn, F. Steglich, *Physica B* 329 (2003) 446.
- [4] H. Hegger, C. Petrovic, E.G. Moshopoulou, M.F. Hundley, J.L. Sarrao, Z. Fisk, J.D. Thompson, *Phys. Rev. Lett.* 84 (2000) 4986.
- [5] T. Park, F. Ronning, H.Q. Yuan, M.B. Salamon, R. Movshovich, J.L. Sarrao, J.D. Thompson, *Nature* 440 (2006) 65.
- [6] P.G. Pagliuso, C. Petrovic, R. Movshovich, D. Hall, M.F. Hundley, J.L. Sarrao, J.D. Thompson, Z. Fisk, *Phys. Rev. B* 64 (2001) 100503.
- [7] V.S. Zapf, E.J. Freeman, E.D. Bauer, J. Petricka, C. Sirvent, N.A. Frederick, R.P. Dickey, M.B. Maple, *Phys. Rev. B* 65 (2001) 014506.
- [8] B.-L. Young, R.R. Urbano, N.J. Curro, J.D. Thompson, J.L. Sarrao, A.B. Vorontsov, M.J. Graf, *Phys. Rev. Lett.* 98 (2007) 036402.
- [9] V.F. Mitrović, M. Horvatić, C. Berthier, G. Knebel, G. Lapertot, J. Flouquet, *Phys. Rev. Lett.* 97 (11) (2006) 117002.
- [10] J.L. Sarrao, L.A. Morales, J.D. Thompson, B.L. Scott, G.R. Stewart, F. Wastin, J. Rebizant, P. Boulet, E. Colineau, G.H. Lander, *Nature* 420 (2002) 297.
- [11] F. Wastin, P. Boulet, J. Rebizant, E. Colineau, G.H. Lander, *J. Phys.: Condens. Matter* 15 (2003) S2279.
- [12] E.D. Bauer, J.D. Thompson, J.L. Sarrao, L.A. Morales, F. Wastin, J. Rebizant, J.C. Griveau, P. Javorsky, P. Boulet, E. Colineau, G.H. Lander, G.R. Stewart, *Phys. Rev. Lett.* 93 (2004) 147005.
- [13] J.D. Thompson, M. Nicklas, V.A. Sidorov, E.D. Bauer, R. Movshovich, N.J. Curro, J.L. Sarrao, *J. Alloys and Compounds* 408–412 (2006) 16–20.
- [14] Y. Haga, D. Aoki, T.D. Matsuda, K. Nakajima, Y. Arai, E. Yamamoto, A. Nakamura, Y. Homma, Y. Shiokawa, Y. Onuki, *J. Phys. Soc. Jpn.* 74 (2005) 1698.
- [15] H. Shishido, R. Settai, D. Aoki, S. Ikeda, H. Nakawaki, N. Nakamura, T. Iizuka, Y. Inada, K. Sugiyama, T. Takeuchi, K. Kindo, T.C. Kobayashi, Y. Haga, H. Harima, Y. Aoki, T. Namiki, H. Sato, Y. Onuki, *J. Phys. Soc. Jpn.* 71 (2002) 162.
- [16] T. Maehira, T. Hotta, K. Ueda, A. Hasegawa, *Phys. Rev. Lett.* 90 (2003) 207007.
- [17] I. Opahle, P.M. Oppeneer, *Phys. Rev. Lett.* 90 (2003) 157001.
- [18] E. Helfand, N.R. Werthamer, *Phys. Rev.* 147 (1) (1966) 288–294.
- [19] H. Sakai, Y. Tokunaga, T. Fujimoto, S. Kambe, R.E. Walstedt, H. Yasuoka, D. Aoki, Y. Homma, E. Yamamoto, A. Nakamura, Y. Shiokawa, K. Nakajima, Y. Arai, T.D. Matsuda, Y. Haga, Y. Onuki, *J. Phys. Soc. Jpn.* 74 (2005) 1710.
- [20] A.B. Vorontsov, J.A. Sauls, M.J. Graf, *Phys. Rev. B* 72 (18) (2005) 184501.
- [21] A. Bianchi, R. Movshovich, N. Oeschler, P. Gegenwart, F. Steglich, J.D. Thompson, P.G. Pagliuso, J.L. Sarrao, *Phys. Rev. Lett.* 89 (13) (2002) 137002.
- [22] M. J. Graf et al., unpublished.
- [23] J.J. Joyce, J.M. Wills, T. Durakiewicz, M.T. Butterfield, E. Guziewicz, J.L. Sarrao, L.A. Morales, A.J. Arko, O. Eriksson, *Phys. Rev. Lett.* 91 (17) (2003) 176401.

Extended short-range ferromagnetic order with cluster-glass behavior in Dy_2AuSi_3

D.X. Li^{a,*}, S. Nimori^b, T. Yamamura^c, K. Yubuta^c, K. Shirazaki^c, X. Zhao^a

^a Key Laboratory for Anisotropy and Texture of Materials (Ministry of Education), Northeastern University, Shenyang 110004, P.R. China

^b Tsukuba Magnet Laboratory, National Research Institute for Metals, Tsukuba 305-0003 Japan

^c Institute for Materials Research, Tohoku University, Oarai, Ibaraki 311-1313 Japan

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 17 October 2008

Accepted 3 November 2008

Available online 17 November 2008

Keywords:

Intermetallics

X-ray diffraction

Magnetic measurements

ABSTRACT

We present the results of ac and dc susceptibilities, high-field magnetization, magnetic relaxation and electrical resistivity measurements for a ternary intermetallic compound Dy_2AuSi_3 with a hexagonal phase dominant crystal structure derived from the AlB_2 -type. Both the ac and dc susceptibilities show a field and frequency dependent peak around $T_C \sim 12.5$ K, while evident irreversible magnetism and long-time magnetic relaxation behavior can be observed below T_C . These metastable magnetic properties suggest that an extended short-range ferromagnetic order occurs near T_C , i.e. the formation of ferromagnetic cluster state. This is further confirmed by the magnetization and electrical resistivity measurements and by a dynamic analysis of the ac susceptibility data. According to the extended short-range ferromagnetic order model, ferromagnetic clusters in Dy_2AuSi_3 could exist with larger geometric dimensions, interact magnetically with each other and result in the observed cluster-glass behavior at low temperatures.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

The ternary intermetallic compounds with the general formula R_2MX_3 (R = rare earth or uranium, M = transition metal, X = Si, Ge, Ga, In) form a large family of compounds, and have been a focus of interest for over 15 years [1,2]. Many of the R_2TX_3 compounds crystallize in an AlB_2 -derived hexagonal structure (space group $P6/mmm$), which consist of R and M-X layers alternating along the c -axis, and the possible crystallographic disorder within M-X positions. These intermetallics exhibit a variety of interesting magnetic properties such as ferromagnetic (FM) ordering in Nd_2PdSi_3 [3], antiferromagnetic (AFM) ordering in Tb_2RhSi_3 [4], spin-glass (SG) behavior in U_2PdSi_3 [5] and Ce_2AgIn_3 [6], and coexistence of SG state and long-range magnetic order in Dy_2PdSi_3 [7], Tb_2PdSi_3 [3,7] and Tb_2CuIn_3 [8]. A common feature observed for these compounds is the presence of metastable magnetic ground state even for the long-range FM or AFM ordering systems characterized predominantly with the evident difference between field cooling (FC) and zero-field cooling (ZFC) dc susceptibility and long time magnetic relaxation behavior. The formation of SG state in some R_2TX_3 compounds was attributed to the statistical distribution of the non-magnetic atoms and the latent geometric frustration. Thus these

compounds are also called non-magnetic atom disorder (NMAD) spin glasses.

As a continuation of our studies on the 2:1:3 compounds, we have prepared a polycrystalline Dy_2AuSi_3 sample and undertaken a systemic measurement on its magnetic properties. In this paper, we present the detailed experimental results including ac susceptibility $\chi_{ac}(T)$ at different frequencies (ω), high-field magnetization $M(H)$ up to 110 kOe, FC and ZFC dc susceptibility $\chi (=M(T)/H)$ in different applied fields H , magnetic relaxation $M(t)$ at different temperatures, and electrical resistivity $\rho(T)$ down to 1.6 K on a well-annealed Dy_2AuSi_3 sample. To the best of our knowledge, research works on compounds of the R_2AuSi_3 family with respect to their physical properties were reported only for U_2AuSi_3 [9] and Ce_2AuSi_3 [10] up to date.

2. Experimental

The polycrystalline sample of Dy_2AuSi_3 was prepared by melting stoichiometric amounts of the constituent materials in an electric arc furnace under argon atmosphere using four tungsten electrodes and a water-cooled copper hearth. The purities of the materials are Dy: 3N, Au: 4N and Si: 6N. To ensure homogeneity the ingot was remelted several times and annealed at 800 °C for one week in an evacuated quartz tube. X-ray-diffraction measurement was carried out at room temperature with $\text{Cu K}\alpha$ radiation to check the purity of the sample. The diffraction patterns reveal that the annealed sample seems to crystallize in a hexagonal phase dominant structure derived from AlB_2 -type with a small amount of a tetragonal impurity phase similar to the compound Ce_2AuSi_3 after annealing at high temperature [10]. Detailed structural analysis is in progress and will be published elsewhere. The ac susceptibility, dc magnetization and magnetic relaxation were measured using a Quantum Design

* Corresponding author.

E-mail address: dxli@imr.tohoku.ac.jp (D.X. Li).

superconducting quantum interference device (SQUID) magnetometer. High-field magnetization experiments at 5 K were carried out using an Oxford Instruments VSM 12 T magnetometer in magnetic fields up to 110 kOe, and the absolute value of the magnetization was calibrated using the data measured by a SQUID. Electrical resistivity measurement was performed over temperature range 1.6–280 K using a standard four-terminal method.

3. Results and discussion

Fig. 1 shows the temperature dependence of the ZFC dc susceptibility ($\chi = M/H$) and inverse susceptibility of Dy_2AuSi_3 measured in an applied field of 100 Oe and in the temperature range 2–300 K. It is clear that the data above 25 K could be nicely fitted using a Curie-Weiss law $\chi = C/(T - \theta p)$ (dashed line in Fig. 1, right-hand scale), where C is the Curie constant and θp is the paramagnetic Curie temperature. The best fitting result yields the values of parameter $C = 4.66 \times 10^{-2}$ emuK/g and $\theta p = -3.6$ K. From the C value, an effective magnetic moment $\mu_{\text{eff}} = 10.63 \mu_B/\text{Dy}$ is obtained, which is very close to the theoretical value expected for a free Dy^{3+} ion in the Hund's rule ground state ($\mu_{\text{eff}} = g\mu_B[J(J+1)]^{1/2} = 10.65 \mu_B$) indicating the 4f electrons are almost localized within the Dy atoms. The small negative value of θp indicates the existence of AFM interactions in the sample. This feature is usually observed in typical AFM system and in some magnetic compounds with competitive FM and AFM exchange interactions such as in SG or cluster-glass system. At low temperatures, the susceptibility curve shows a steep rise near $T_C = 12.5$ K followed by a sharp peak with the peak temperature $T_m = 11$ K indicating the occurrence of some kind of magnetic phase transition in the Dy_2AuSi_3 sample.

In order to get more physical information on the nature of the observed magnetic phase transition around the dc susceptibility peak, ZFC susceptibility is further measured in various applied fields around the transition temperature. As illustrated in Fig. 2, in field strengths up to $H = 300$ Oe the maximum of the $\chi_{\text{ZFC}}(T)$ curve increases with rising H , while the peak position T_m remains almost unchanged in this field range. With a further increase of applied field the peak of the $\chi_{\text{ZFC}}(T)$ curve becomes broader and its height decreases, while the T_m shifts towards lower temperatures. At $H = 10$ kOe no peak can be observed down to 2 K. These behaviors are characteristic for ferromagnet with domain wall pinning effect [11] or for SG system. Note that although increase of the field strength has an evident influence on the peak position T_m in fields $H > 300$ Oe, the kink point T_C ($=12.5$ K) of the χ_{ZFC} curve

Fig. 1. Temperature dependence of the zero-field cooling dc magnetic susceptibility of Dy_2AuSi_3 in a field of 100 Oe, and reciprocal magnetic susceptibility where the solid line represents the fitting result using the Curie-Weiss law in the temperature range between 25 and 300 K.

Fig. 2. Temperature dependence of the zero-field cooling dc magnetic susceptibility of Dy_2AuSi_3 measured in various applied magnetic fields. The inset shows the difference between the field cooling and zero-field cooling magnetic susceptibilities measured in magnetic field of 100 Oe around the transition temperature.

determined by the minimum of the derivative $d\chi_{\text{ZFC}}/dT$, is almost unchanged even rising H up to 10 kOe. It is interesting to note that the low field (<10 Oe) χ_{ZFC} curve reveals negative magnetic moment at low temperatures. This is because the sample is cooled under a small negative residual field in the superconducting solenoid of the SQUID. This phenomenon can be usually observed for a ferromagnet with high anisotropy and large coercive field [11].

In the inset of Fig. 2, we compare the temperature dependences of FC and ZFC susceptibility measured in a field of 100 Oe for the Dy_2AuSi_3 sample. It is clear from this figure that there is no difference between the FC and ZFC curves in the paramagnetic state. With decreasing temperature the magnetic transition peak can be observed only in the $\chi_{\text{ZFC}}(T)$ curve, while $\chi_{\text{FC}}(T)$ shows a more rapid rise near the inflection point T_C and saturation at lower temperatures. This leads to the evident irreversible magnetism manifesting as the bifurcation between the FC and ZFC curves. Note that the irreversibility temperature T_{ir} (defined as the temperature below which the $\chi_{\text{FC}}(T)$ and $\chi_{\text{ZFC}}(T)$ curve separate from each other) determined at $H = 100$ Oe is clearly larger than the peak temperature T_m in $\chi_{\text{ZFC}}(T)$ curve. This phenomenon is different from that observed for standard SG materials, and can be considered as a characteristic feature for ferromagnet with high magnetic anisotropy or short-range FM order (FM cluster) system. In fact, thermomagnetic irreversibility is a common feature of all magnetic systems with metastable magnetic ground state such as SG, cluster glass and FM materials. In a low field, however, such irreversible magnetism can be observed usually beginning at the peak point T_m for standard SG and beginning at the inflection temperature T_C ($>T_m$) for FM cluster or long-range FM ordering system.

Thermodynamically, the observed irreversible magnetism can be directly related to nonequilibrium characters of the low temperature magnetic states, and thus a remanence in hysteresis loop and long time magnetic relaxation effect are also expected at low temperatures for the Dy_2AuSi_3 sample. Fig. 3 shows the $M-H$ curve measured at 5 K ($<T_C$) up to 110 kOe for Dy_2AuSi_3 . Though $M(H)$ shows a tendency to attain the full moment value at high fields, the complete saturation is not achieved in the field range of the measurement. This may be due to the existence of magnetic anisotropy as usually observed in some ferromagnets. With increasing H , M reaches a value of 128.8 emu/g ($=6.99 \mu_B/\text{Dy}$) at 110 kOe and when H is returned from 115 kOe to zero a remanent magnetization of

Fig. 3. Magnetization vs. external magnetic field up to 110 kOe for Dy_2AuSi_3 . The inset displays the low field part in an expanded scale.

about $0.8 \mu_B/\text{Dy}$ is detected for the Dy_2AuSi_3 sample. From the hysteresis loop we determine the coercive field H_C of Dy_2AuSi_3 to be 760 Oe at 5 K. Moreover, the hysteresis loop shows rapid increase at low fields, this feature is also characteristic for a short-range FM order system.

Fig. 4(a) shows remanent magnetization $M(t)$ as a function of time t at several temperatures below T_C . First, we cooled the sample in zero-field from 50 K (far above T_C) to the desired temperature, then a magnetic field of 5 kOe was applied for 5 min and switched off at $t = 0$. The main finding is that the decay of $M(t)$ is remarkably slow. After waiting for two hours, $M(t)$ drops from the initial zero-field value by about 11, 13 and 16% for $T = 5, 7$ and 9 K, respectively. The long time magnetic relaxation behavior is also observed for the Dy_2AuSi_3 sample under applied field at temperatures below T_C (see Fig. 4(b)). Note that the long time magnetic relaxation effect is evident even in a field ($H = 1.5$ kOe) much larger than the coercive field ($H_C = 760$ Oe). This observation is very significant because the long time magnetic relaxation effect in a field H larger than H_C is usually considered to originate from the SG state. Thus the present results suggest the possibility of formation of SG (or cluster glass) state

Fig. 4. Decay of magnetization measured at 5, 7 and 9 K in zero field (a), and at 5 K in magnetic fields of 0.1, 0.5, 1.5 and 5 kOe (b) for Dy_2AuSi_3 , plotted as $M(t)/M(0)$ vs. t .

Fig. 5. Temperature dependences of real (χ'_{ac}) and imaginary (χ''_{ac}) components of the ac susceptibility of Dy_2AuSi_3 measured at various frequencies with an oscillating field of 5 Oe.

in the Dy_2AuSi_3 sample at low temperatures. Using a logarithmic function, $M(t) = M_0 - S \ln(t + t_0)$, the obtained relaxation behaviors shown in Fig. 4(a) and (b) can be fitted very well over the full time range studied with three H - and T -dependent fitting parameters: initial zero-field magnetization M_0 , magnetic viscosity S and characteristic time t_0 .

It is worth emphasizing that the irreversible magnetism and long time magnetic relaxation effect described above are also characteristic of SG materials. In order to get a better insight into the magnetic properties of this compound and to explore the possible SG effect, we have measured the frequency dependence of the real and imaginary parts of the ac susceptibility around the transition temperature. The results at frequency range $0.1 \text{ Hz} \leq \omega/2\pi \leq 1000 \text{ Hz}$ are illustrated in Fig. 5. It is clear from this figure that the in-phase component of the ac susceptibility, χ'_{ac} , exhibits a pronounced maximum at a frequency dependent temperature $T_C(\omega)$ very close to the inflection point of $\chi_{ZFC}(T)$ curve shown in Fig. 2. The T_C value is determined to be 12.36 K at $\omega/2\pi = 0.1$ Hz (in good agreement with the T_C values shown in Fig. 2), which shifts to 12.62 K at $\omega/2\pi = 1000$ Hz. The upward-shift of the peak position in $\chi'_{ac}(T)$ curve with rising frequency is a typical feature of SG material, which can be considered as an important evidence for the existence of random spin freezing effect in our Dy_2AuSi_3 sample. However, using expression $\delta T_C = \Delta T_C / (T_C \Delta \log \omega)$, the frequency shift rate of T_C is estimated to be $\delta T_C = 0.005$. This value is much smaller than the δT_f values (frequency shift rate of freezing temperature) reported for the typical 2:1:3 NMAD SG systems (for examples, $\delta T_f = 0.022$ for Ce_2AgIn_3 [6], 0.016 for U_2PdSi_3 [12], 0.015 for Nd_2AgIn_3 [13], and 0.016 for Ce_2CuGe_3 [14]), but evidently larger than the δT_m values (frequency shift rate of peak temperature in $\chi'_{ac}(T)$ curve) reported for the “almost long range ferromagnetic ordering” compound Nd_2PtSi_3 ($\delta T_f = 0.002$) [15]. In this sense, the Dy_2AuSi_3 sample could be considered as a FM cluster-glass system, which reveals both FM-like characters (due to the relatively large cluster size) and SG-like behaviors (due to the magnetic exchange interactions between the clusters). The presence of FM cluster-glass effect in Dy_2AuSi_3 is further confirmed by a dynamic analysis of the obtained $T_C(\omega)$ data. We have fitted the $T_C(\omega)$ data to the standard expression (critical slowing down) [16], $\tau_{\max} = \tau_0 [(T_f - T_s)/T_s]^{-z\nu}$, and to the Vogel-Fulcher law [17], $\omega = \omega_0 \exp[-E_a/k_B(T_f - T_v)]$, respectively. Following Tholence [18], $\tau_0 = 1/\omega_0 = 10^{-13}$ s was kept

Fig. 6. Temperature dependence of the electrical resistivity of Dy_2AuSi_3 . The inset shows the data around the transition temperature in an expanded scale.

fixed, the following parameters are obtained from the best fitting results: a static freezing temperature $T_S = 12.3$ K, a critical (dynamical) exponent $z\nu = 6.6$, a Vogel-Fulcher temperature $T_0 = 11.7$ K and an average activation energy $E_a \approx 1.75k_B T_S$. Note that $z\nu$ is determined around 2 for conventional phase transitions of long-range magnetic ordering systems [19], and around 10 for SG transitions of typical 2:1:3 NMAD SG systems. The $z\nu$ value obtained for Dy_2AuSi_3 in this work is also situated between them. In addition, a characteristic cusp in the imaginary part $\chi''_{ac}(T)$ and both the peak strength and peak position change significantly with rising frequency are also the indications for cluster glasses or FM systems reflecting different energy losses depending on frequency in the process of phase transition.

On the other hand, another evidence of the presence of large FM cluster in the Dy_2AuSi_3 sample is given by the temperature dependence of electrical resistivity measurement. The experimental result is illustrated in Fig. 6. It is seen that the resistivity $\rho(T)$ reveals metallic conductivity with some negative curvature between 50 and 150 K, which may be resulted from crystal field interaction and/or s-d interband scattering of conduction electrons [20]. As clearly shown in the inset of Fig. 6 in an expanded scale, $\rho(T)$ curve manifests a sudden bent at $T_C (=12.5)$. The rapid decrease of ρ below T_C is resulted from the decrease of spin disorder scattering due to FM ordering within the large magnetic clusters. Note that for typical SG systems, no larger anomaly in $\rho(T)$ curves can be detected.

To summarize, magnetic properties of ternary intermetallic compound Dy_2AuSi_3 have been studied by means of ac and dc susceptibility, high-field magnetization, magnetic relaxation, and electrical resistivity measurements. This compound shows a sharp peak in ac and dc susceptibility curves near a transition tempera-

ture $T_C = 12.5$ K. The upward-shift of the ac susceptibility peak with increasing frequency, the downward-shift of the dc susceptibility peak with increasing magnetic field, the long-time magnetic relaxation behavior and the clear irreversible magnetism below T_C are observed. In addition, the magnetization measurement measured at 5 K shows a sharp increase at low fields, and electrical resistivity measurement reveals a sudden decrease at T_C . These features suggest the metastable properties of the magnetic ground state for the Dy_2AuSi_3 sample, and can be explained by using an extended short-range FM order model. According to this model, larger FM clusters could exist in the Dy_2AuSi_3 sample and magnetic exchange interactions between the clusters occur at low temperature, which leads to the observed FM-like and SG-like features, i.e. FM cluster-glass behaviors. This consequence is further confirmed by a dynamic analysis of the ac susceptibility data, which yields the values of frequency shift rate δT_C and dynamical critical exponent $z\nu$ being typical for a magnetic cluster system.

References

- [1] P.A. Kotsanidis, J.K. Yakinthos, E. Gamari-Seale, J. Magn. Magn. Mater. 87 (1990) 199.
- [2] R. Pöttgen, D. Kaczorowski, J. Alloys Compd. 201 (1993) 157.
- [3] A. Szytula, M. Hofmann, B. Penc, M. Slaski, S. Majumdar, E.V. Samarthkumaran, A. Zygmunt, J. Magn. Magn. Mater. 202 (1999) 365.
- [4] A. Szytula, J. Leciejewicz, K. Maletka, J. Magn. Magn. Mater. 118 (1993) 302.
- [5] D.X. Li, Y. Shiokawa, Y. Homma, A. Uesawa, A. Dönni, T. Suzuki, Y. Haga, E. Yamamoto, T. Homma, Y. Onuki, Phys. Rev. B 57 (1998) 7434.
- [6] T. Nishioka, Y. Tabata, T. Taniguchi, Y. Miyako, J. Phys. Soc. Jpn. 69 (2000) 1012.
- [7] D.X. Li, S. Nimori, Y. Shiokawa, Y. Haga, E. Yamamoto, Y. Onuki, Phys. Rev. B 68 (2003) 012413.
- [8] I.M. Siouris, I.P. Semitelou, J.K. Yakinthos, W. Schäfer, R.R. Arons, J. Alloys Compd. 314 (2001) 1.
- [9] D.X. Li, A. Kimura, Y. Homma, Y. Shiokawa, A. Uesawa, T. Suzuki, Solid State Commun. 108 (1998) 863; B. Chevalier, R. Pöttgen, B. Darriet, P. Gravereau, J. Etourneau, J. Alloys Compd. 233 (1996) 150.
- [10] R.A. Gordon, C.J. Warren, M.G. Alexander, F.J. DiSalvo, R. Pöttgen, J. Alloys Compd. 248 (1997) 24; Subham Majumdar, E.V. Samarthkumaran, Phys. Rev. B 62 (2000) 8959.
- [11] T.V. Chandrasekhar Rao, P. Raj, Sk. Mohammad Yusur, L. Madhav Rao, A. Sathyamoorthy, V.C. Sahni, Philos. Mag. B 74 (1996) 275.
- [12] D.X. Li, Y. Shiokawa, Y. Haga, E. Yamamoto, Y. Onuki, J. Phys. Soc. Jpn. 71 (2002) 418.
- [13] D.X. Li, S. Nimori, Y. Shiokawa, A. Tobo, H. Onodera, Y. Haga, E. Yamamoto, Y. Onuki, Appl. Phys. Lett. 79 (2001) 4183.
- [14] C. Tien, C.H. Feng, C. Shui, J.J. Lu, Phys. Rev. B 61 (2000) 12151.
- [15] D.X. Li, S. Nimori, Y. Shiokawa, Y. Haga, E. Yamamoto, Y. Onuki, Solid State Commun. 120 (2001) 227.
- [16] P.C. Hohenberg, B.I. Halperin, Rev. Mod. Phys. 49 (1977) 435; K. Gunnarsson, P. Svedlindh, P. Nordblad, L. Lundgren, H. Aruga, A. Ito, Phys. Rev. Lett. 61 (1988) 754.
- [17] H. Vogel, Phys. Z 22 (1921) 645; G.S. Fulcher, J. Am. Ceram. Soc. 8 (1925) 339.
- [18] J.L. Tholence, Solid State Commun. 35 (1980) 113; J.J. Prejean, J. Phys. 39 (1978) C6-907; J. Dho, W.S. Kim, N.H. Hur, Phys. Rev. Lett. 89 (2002) 27202.
- [19] J.A. Mydosh, Spin Glass: An Experimental Introduction, Taylor & Francis, London, 1993.
- [20] D. Kaczorowski, A. Czopnik, W. Suski, V.N. Nikiforov, A.V. Gribanov, Solid State Commun. 117 (2001) 373.

Internal friction of polycrystalline $\text{Zr}_{0.8}\text{R}_{0.2}\text{O}_{1.9}$ (R = Nd, Y)

Masakuni Ozawa*, Kenji Tsuchiya, Yoshitoyo Nishio

CRL, Nagoya Institute of Technology, Tajimi, Gifu 5070071, Japan

ARTICLE INFO

Article history:

Received 7 June 2008

Received in revised form 5 May 2009

Accepted 7 October 2009

Available online 17 October 2009

Keywords:

Zirconia

Nd

Internal friction

Relaxation

Mechanical loss

ABSTRACT

The oxygen relaxation in two cubic zirconias, $\text{Zr}_{0.8}\text{R}_{0.2}\text{O}_{1.9}$ where R = Nd and Y, was compared with internal friction in the temperature range of 300–685 K using forced torsion pendulum method. The internal friction of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ was shown as a single peak at around 350–450 K at frequencies of 0.32–9 Hz. The activation enthalpy of relaxation in $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ was determined to be 1.12 ± 0.1 eV. The amplitude of the high-temperature peak in Y-doped zirconia was not observed for $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$. The result suggests that the relatively lower mobility of oxygen is due to the doping of larger Nd cation to ZrO_2 lattice.

© 2009 Published by Elsevier B.V.

1. Introduction

Rare earth stabilized cubic zirconia has found widespread application as a solid electrolyte including fuel cells and sensors. Zirconia can be stabilized in its cubic phase by forming complexes of dopant cations with lower valence in the range of about 10 mol% as oxide R_2O_3 . The relaxation, i.e. local jump of oxygen around the cations should be observed as internal friction and dielectric loss peaks. Since ionic conduction occurs by migration of oxygen in the fluorite structure, this process is important to examine in details the basic process of conduction. Long-range migration of the charged oxygen leads ionic conduction under the electric field, so that the internal friction measurement provides the basic information of diffusion process in the local structure and dynamics [1–7]. The internal friction method as well as the mechanical evaluation is useful if applied with the frequency-dependent data at various temperatures to a sample. It is known that ionic radius affects the conduction and mobility in zirconia-based ionics, however the local process or jumping phenomenon itself has been less investigated. In this work, we provide the internal friction of Nd-doped zirconia ($\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$), compared to ordinal $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ ceramics, at ordinary temperature region. The effect of a large cation of Nd is examined by a series of low frequency internal friction measurements.

2. Experimental

The raw powder was synthesized by coprecipitation method of aqueous metal nitrates with ammonia solution for compositions of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ and $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$. The precipitate was filtered, washed with distilled water, and heat-treated at 1173 K for 3 h in air, and ground after cooling. The ceramic piece was prepared by the sintering of the pressed bodies at 1873 K for 3 h in air. Specimens with dimensions of 40 mm × 4 mm × 0.5 mm were cut from them. The internal friction and modulus measurements in the temperature range of 300–685 K were carried out with a forced torsion pendulum method at the frequencies of 0.32–9 Hz using a lab-made apparatus. The internal friction was obtained from the phase shift of strain to stress for each frequency and temperature. X-ray powder diffractometer (Rigaku rint 2000, Japan) was used for identifying the phases in samples.

3. Results and discussion

The internal friction of polycrystalline $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ ceramic is shown in Fig. 1, where three frequencies of 0.32, 3.2 and 9 Hz were applied at 310–720 K. The data show almost the single peaks. Fig. 2 demonstrates the comparison of internal friction of cubic $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ and $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ at 3.2 Hz. The spectrum of $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ is clear double peaks, however that of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ shows a single IF (internal friction) peak. X-ray powder diffractometer has indicated that both cubic $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ and $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ are in cubic phase, thus have the same amount of oxygen defects in a fluorite-structured crystal. Weller [3,4] reported that the height of internal friction in Y-doped zirconia increases with dopant content reaching a maximum value for 12 mol% Y_2O_3 ($\text{Zr}_{0.76}\text{Y}_{0.24}\text{O}_{1.9}$), where the second maximum at higher temperature become larger than the maximum at lower temperature. In this work, the Nd-doped zirconia, $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ has the internal friction amplitude, the same as the first peak of $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ at the same temperature. Lacking of the other peak as a feature of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ is clear

* Corresponding author.

E-mail address: ozawa@nitech.ac.jp (M. Ozawa).

Fig. 1. Internal friction of polycrystalline $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ at 0.32 Hz ($\square$), 3.2 Hz ($\circ$), and 9 Hz ($\triangle$). The apparatus background is not reduced.

Fig. 2. Internal friction of polycrystalline $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ ($\square$) and $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ ($\circ$) at 3.2 Hz. The apparatus background is not reduced.

when we superimpose it with peaks of $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$ as in Fig. 2, which was measured by the same condition and apparatus as well as the same preparation process. These data suggest the mechanical relaxation or jump of oxygen in the local structure is critically different between two zirconias. Table 1 lists the parameters of peak temperature and amplitude at each frequency. The activation enthalpy H of maximum was determined from the frequency shift as in Fig. 3. For $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$, in our previous and this work, the activation enthalpies H were 1.24 ± 0.1 eV for a low-temperature peak, and 2.28 ± 0.2 eV for a high-temperature peak. This time, newly, we determined $H = 1.12 \pm 0.1$ eV for $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ from a single peak. Nd- or Y-doped zirconia has the same relaxation process at low temperature around 400 K at 0.3–9 Hz, regarding the activation enthalpy within experimental error. However, there is

Table 1

Parameters for internal friction peaks of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$.

Frequency (Hz)	Peak temperature (K)	Amplitude ^a
0.32	376	0.03
3.2	402	0.03
9.0	416	0.03

^aThe amplitude was obtained after apparatus background was reduced.

Fig. 3. A plot of log-angular frequency versus reciprocal temperature for $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$.

a clear difference about the second relaxation at higher temperature. They suggest the difference of defect-complexes, which are assumed between $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ and $\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{1.9}$. In the temperature range at this work, the mechanical relaxation is induced by oxygen relaxation, which is not due to diffusion of cations, grain boundary and/or dislocations.

Defect formation can be described by the following reactions in classical Kroger–Vink notation.

Actually, the defect complex $(\text{Nd}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\times}$ and $(2\text{Nd}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\times}$ should form in Nd-doped zirconia crystal. Weller [4] has also discussed on Y-doped zirconia that the trigonal symmetry of the defects causing maximum directly to their assignment to simple $(\text{Y}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\bullet\bullet}$ complexes like according to Eq. (1). This defect model for the fluorite lattice of zirconia is valid for present $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ too, however lacking of the second peaks cannot be explained. The oxygen vacancies can essentially jump (reoriented) on the eight $[1\bar{1}1]$ -oriented, nearest neighboring site. Although the second peak probably requires the other relaxation pass in the lattice, it is practically difficult to realize the different route of oxygen movement with one nearest pass around cations. Possibility is of a few atoms due to its higher activation enthalpy of 2 eV or a simple relaxation with high potential barrier for hopping. The former means that a dominating high-temperature peak in Y_2O_3 – ZrO_2 for higher Y dopant levels is assigned to relaxation of oxygen vacancies within a cluster of two or more Y ions. The latter is assumed when the simplest defect may consist of two Y ions and an oxygen vacancy forming a large complex such as $(2\text{Nd}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\times}$. The local structure inducing anelastic relaxation of zirconia has been discussed elsewhere by several workers [2–4,7]. If a large complex defect, e.g. $(2\text{Y}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\times}$ and its relaxation, gives the anelastic relaxation peak, the doping of larger cation of Nd is not preferred to form a complex, because the two large cations are closing each other. With the cation sizes (the ionic size, $\text{Nd}^{3+}(0.10\text{ nm}) > \text{Y}^{3+}(0.09\text{ nm}) > \text{Zr}^{4+}(0.08\text{ nm})$), a large complex $(2\text{Y}'_{\text{Zr}}\text{V}_{\text{O}}^{\bullet\bullet})^{\times}$ has much strain and stabilized as a local structure without relaxation of oxygen. Actually, the mobility of oxygen has been partially lost by the local structural character in Nd-doped ZrO_2 . The relaxation is a phenomenon of oxygen movement under elastic field, however it affects the essential property of transport of oxygen under electric field. The lower ionic conductivity

of $\text{Nd}_2\text{O}_3\text{--ZrO}_2$, compared to $\text{Y}_2\text{O}_3\text{--ZrO}_2$ ceramics, must be closely related with the defect complex structure [8]. A tentative figure for the effect of doping larger Nd cation on oxygen relaxation was discussed in this work. More work is required for comparison with other techniques to investigate the local structure.

4. Summary

The oxygen relaxation in two cubic zirconias, $\text{Zr}_{0.8}\text{R}_{0.2}\text{O}_{1.9}$ where R = Nd and Y, was compared with internal friction in the temperature range of 300–685 K using forced torsion pendulum method. The internal friction of $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ was shown as a single peak at around 350–450 K at frequencies of 0.32–9 Hz. The activation energy of relaxation in $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$ was 1.12 ± 0.1 eV with dif-

ferent peak temperatures. The amplitude of the high-temperature peak in Y-doped zirconia was not observed for $\text{Zr}_{0.8}\text{Nd}_{0.2}\text{O}_{1.9}$, lacking a large complex in zirconia lattice.

References

- [1] A.S. Nowick, in: J.H. Crawford Jr., L.M. Slifkin (Eds.), *Point Defects In Solids*, Plenum Press, New York, NY, 1972, pp. 151–198.
- [2] M. Weller, H. Schubert, *J. Am. Ceram. Soc.* 69 (1986) 573.
- [3] M. Weller, *J. Alloys Compd.* 211–212 (1994) 66.
- [4] M. Weller, *J. Alloy Compd.* 310 (2000) 47.
- [5] M. Ozawa, T. Hatanaka, H. Hasegawa, *J. Ceram. Soc. Jpn.* 99 (1991) 643.
- [6] M. Ozawa, H. Hasegawa, *J. Mater. Sci.* 29 (1994) 380.
- [7] M. Ozawa, T. Itoh, E. Suda, *J. Alloys Compd.* 374 (2004) 120.
- [8] R. Gerhardt-Anderson, F. Zamani-Noor, A.S. Nowick, C.R.A. Catlow, A.N. Cormack, *Solid State Ionics* 9–10 (1983) 931.

Moisture and surface area measurements of plutonium-bearing oxides

Mark L. Crowder*, Jonathan M. Duffey, Ronald R. Livingston, John H. Scogin, Glen F. Kessinger, Philip M. Almond

Savannah River National Laboratory, Aiken, SC, USA

ARTICLE INFO

Article history:

Received 5 September 2008

Received in revised form

24 September 2009

Accepted 25 September 2009

Available online 17 October 2009

Keywords:

Actinide alloys and compounds

Plutonium oxide

Thermal analysis

Mass spectrometry

Moisture

ABSTRACT

To ensure safe storage, plutonium-bearing oxides are stabilized at 950 °C for at least two hours in an oxidizing atmosphere. Stabilization conditions are expected to decompose organic impurities, convert metals to oxides, and result in moisture content below 0.5 wt%. During stabilization, the specific surface area is reduced, which minimizes readsorption of water onto the oxide surface. Plutonium oxides stabilized according to these criteria were sampled and analyzed to determine moisture content and surface area. In addition, samples were leached in water to identify water-soluble chloride impurity content. Results of these analyses for seven samples showed that the stabilization process produced low moisture materials (<0.2 wt%) with low surface area ($\leq 1 \text{ m}^2/\text{g}$). For relatively pure materials, the amount of water per unit surface area corresponded to 1.7–3.4 molecular layers of water. For materials with chloride content >360 ppm, the calculated amount of water per unit surface area increased with chloride content, indicating hydration of hygroscopic salts present in the impure PuO_2 -containing materials. The low moisture, low surface area materials in this study did not generate detectable hydrogen during storage of four or more years.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

In the past two decades, significant quantities of plutonium (Pu) have been stabilized as the dioxide for storage at Department of Energy facilities. Prior to long-term storage in sealed containers, research [1,2] was performed to determine the stabilization conditions necessary to ensure safe storage. Generally, plutonium-bearing materials were heated in air at 950 °C for at least two hours, resulting in moisture content below 0.5 wt% [3]. (Some salt-bearing species, including Sample 6 in this study, were stabilized at 750 °C.) The low moisture level minimizes concerns about corrosion of storage vessels by halide-containing materials, and also reduces the potential for radiolytic hydrogen generation and subsequent pressurization of sealed vessels. Stored plutonium-bearing oxides have a wide range of plutonium contents and contain various impurities, including uranium oxides and chloride salts. Some chloride (Cl^-) phases, such as MgCl_2 , are known to be quite hygroscopic. Past investigation has shown that the specific surface area of pure and impure Pu-bearing oxides is reduced as the calcination temperature is increased [4,5]. Calcination at 950 °C effectively reduces the specific surface area (SSA), which limits the amount of moisture

that is re-adsorbed by the surface. Because of the expected low surface area and low moisture of these materials, this study did not investigate the presence of PuO_{2+x} , which has been reported in high surface area plutonium oxides in the presence of water [6]. The results presented demonstrate the effectiveness of the plutonium stabilization process through the characterization of materials that have been stored in sealed containers for more than four years, after being packaged at the Department of Energy's Rocky Flats site.

2. Experimental

Sealed containers of plutonium-bearing oxide were opened and sampled immediately. These samples were analyzed by Thermogravimetric Analysis–Mass Spectroscopy (TGA–MS) using a Netzsch STA 409 Luxx model TGA connected to a Pfeiffer ThermoStar MS. The permanent gases pass from the TGA portion of the instrument through a heated transfer tube maintained at $\geq 150^\circ\text{C}$ to the MS. During analyses, samples were heated from ambient to 1000 °C (at $15^\circ\text{C}/\text{min}$) under a flowing argon gas stream which was analyzed by the MS. Gypsum standards were used to develop an MS moisture calibration curve, as described elsewhere [7,8]. Additional samples from the same parent container were analyzed for surface area with a Micromeritics Gemini 2360 analyzer using the Brunauer–Emmett–Teller (BET) method with nitrogen adsorbate. All analyses were performed in duplicate unless otherwise indicated. Soluble chloride salt content was determined by leaching 0.5-g samples in water at 90 °C for one hour. After cooling, aliquots were analyzed to determine selected anions (by ion chromatography) and selected cations (by inductively coupled plasma–emission spectroscopy). In addition to the oxide sample characterization, gas samples from the headspace of the cans (collected during storage vessel opening) were analyzed by gas chromatography.

* Corresponding author at: Savannah River National Laboratory, Aiken, SC 29808, USA.

E-mail address: mark.crowder@srnl.doe.gov (M.L. Crowder).

Table 1
Characterization data for plutonium-bearing oxide samples.

#	% Pu	% U	Soluble Cl ⁻ μg/g	SSA m ² /g	TGA mass loss wt%	MS moisture wt%	Water/surface area mg H ₂ O/m ²	Molecular layers 0.21 mg ea
1	87.5	–	BDL	0.47	0.03	0.04	0.63	3.0
2	85.0	1.32	BDL	0.82	0.03	0.05	0.37	1.7
3	86.5	–	120	0.94	0.04	0.05	0.42	2.0
4	85.8	–	320	0.99	0.07	0.10	0.71	3.4
5	84.1	0.22	360	0.58	0.16	0.05	0.86	4.1
6	67.9	–	110,000	0.58	0.44	0.14	2.4	11 ^b
7	51.4	–	170,000	0.58	4.1	0.19 ^a	3.3	16 ^b

BDL = Below Detection Limit.

^a Value based on single value of MS replicate. Initial analysis had an MS error.

^b Values provided for comparison, since moisture tends to hydrate Cl⁻ salts, not form additional layers.

Fig. 1. Thermogravimetric analysis of chloride-bearing sample #5.

3. Results

Typical TGA and combined TGA-MS curves are shown in Figs. 1 and 2, which have the same temperature versus time profile. Detailed analytical results are shown in Table 1 with samples listed in order of increasing Cl⁻ content. Note that pure Pu oxide has an assay of 88.2% Pu for common isotopic mixtures. Uncertainties in the values reported in Table 1 are $\pm 5\%$ for TGA mass loss, $\pm 10\%$ for soluble Cl⁻ and SSA, and an estimated $\pm 30\%$ for MS moisture content. Table 1 also contains the number of molecular layers of water present on each material, based on the value of 0.21 mg/m², an average estimate for the molecular coverage on plutonium dioxide [1]. Results for water-soluble cation contents are shown in Table 2. Finally, analysis of the gas inside the sealed Pu storage vessels did not detect appreciable hydrogen for the seven samples in this study [9].

Fig. 2. TGA-MS of sample #7 containing 17 wt% chloride.

Table 2
Water-soluble cation contents.

#	Ca (μg/g)	K (μg/g)	Mg (μg/g)	Na μg/g
6	30	61,000	5,200	37,000
7	430	76,000	7,200	47,000

4. Discussion

As shown in Table 1, the four samples with the highest purity exhibited a total mass loss of 0.03–0.07 wt%. During development of the moisture calibration curve, the linear relation between MS peak area for Mass 18 versus mass of moisture was assigned an intercept of (0, 0). Using a zero intercept gave the reported MS results a small positive bias for low moisture materials; however, TGA and MS moisture results agree within the uncertainties of the measurement methods.

For the relatively pure Samples 1–4, the amount of water per unit surface area corresponded to 1.7–3.4 molecular layers of water. Pure materials have been shown to contain nominally two molecular layers of moisture [1].

For Samples 5–7, the chloride contributes significantly to the total mass loss, especially above 750 °C, the temperature at which chlorides salts begin to volatilize. For all samples, the majority of moisture release, which occurred by the time the sample reached 400 °C, is generally ascribed to physisorbed moisture. For Samples 1–3 and 5–7, moisture release from 750 to 1000 °C was ≤ 0.015 wt%. However, Sample 4, which had the highest surface area of the samples tested and contained modest Cl⁻, showed moisture release of 0.03 wt% between 750 and 1000 °C, an indication of some strongly chemisorbed moisture.

Generally, the surface areas for these samples were quite low, ranging from 0.47 to 0.99 m²/g. Reduced surface area tends to minimize rehydration of the oxide. Thus, the materials in this study compare favorably with the thirteen samples reported by Leasure et al. [4] that had been calcined at 950 °C and had surface areas ranging from 0.20 to 3.16 m²/g with a median value of 1.21 m²/g. Similarly, Machuron-Mandard and Madic [5] calcined PuO₂ at 750, 850, and 950 °C and found specific surface areas of 2.0, 2.6, and 2.1 m²/g, respectively. For samples in this study containing chloride salts, particularly Sample 6 stabilized at 750 °C, the low specific surface areas may be due in part to the presence of the salt.

The absence of hydrogen in the headspace above the plutonium-bearing materials in this study indicates minimal generation of hydrogen by either radiolysis of water or by chemical reaction of water and PuO₂. It is unlikely that H₂ was generated and later consumed. Thus, the low moisture, low surface area materials in this study were stable during storage in terms of hydrogen generation.

5. Conclusions

Seven samples which represent a portion of the types of plutonium-bearing oxides stabilized for long-term storage were tested. Characterization of these samples provides an initial indication that the stabilization process effectively produces materials with low surface area, $\leq 1 \text{ m}^2/\text{g}$, and moisture content $< 0.2 \text{ wt}\%$ for the materials in this study. The relatively pure samples tested in this study contained 2–3 molecular layers of water, which is consistent with earlier studies on pure Pu oxides. Materials containing appreciable chloride exhibited increased mass loss when heated to 1000°C , and these samples exhibited increased water content.

Acknowledgments

The authors acknowledge the assistance of Thomas L. White for performing ion chromatography analyses, Mark A. Jones for ICP-ES analyses, and a supportive actinide research team.

References

- [1] J.M. Haschke, T.E. Ricketts, J. Alloys Compd. 252 (1997) 148–156.
- [2] D.M. Smith, M.P. Neu, E. Garcia, L.A. Morales, Waste Manage. 20 (2000) 479–490.
- [3] Stabilization, Packaging, and Storage of Plutonium-Bearing Materials, Department of Energy Standard DOE-STD-3013-2004, April 2004.
- [4] C.S. Leasure, D.R. Horrell, R.E. Mason, Conditions and results from thermal stabilization of pure and impure plutonium oxides for long-term storage at Department of Energy Sites, US DOE Report LA-UR-98-3526, Los Alamos National Laboratory, September 1998.
- [5] X. Machuron-Mandard, C. Madic, J. Alloys Compd. 235 (1996) 216–224.
- [6] J.M. Haschke, T.H. Allen, L.A. Morales, Science 287 (2000) 285–287.
- [7] L. Morales, U. Gallegos, L. Bustos, S. Lemarchand, E. Post, A. Schraner, K. Imrich, A. Jurgensen, Y. Mazza, M. Brugh, S. Barney, Certification of thermal gravimetric analysis with moisture detection systems for water determinations on 3013 materials, US DOE Report LA-UR-02-2233, Los Alamos National Laboratory, Los Alamos, NM, April 2002.
- [8] A.R. Jurgensen, D.M. Missimer, R.L. Rutherford, Surface Area (BET) and TGA-MS analysis of calcined neptunium oxide, US DOE Report WSRC-TR-2003-00378, Savannah River National Laboratory, Aiken, SC, December 2005.
- [9] P.M. Almond, R.R. Livingston, L.E. Traver, M.J. Arnold, N.J. Bridges, G.F. Kessinger, Gas analyses from headspace of plutonium-bearing materials packages, J. Nucl. Mater. Manage., in press.

Lanthanide charge transfer energies and related luminescence, charge carrier trapping, and redox phenomena

P. Dorenbos

Delft University of Technology, Faculty of Applied Sciences, Mekelweg 15, 2629 JB Delft, The Netherlands

ARTICLE INFO

Article history:

Received 27 May 2008

Received in revised form 15 July 2008

Accepted 1 September 2008

Available online 31 October 2008

Keywords:

Phosphors

Point defects

Crystals and ligand fields

Electronic states (localized)

Luminescence

ABSTRACT

The energy of electron transfer from the valence band to a trivalent lanthanide ion provides information on the location of the ground state energy of the corresponding divalent lanthanide ion relative to the top of the valence band. It turns out that the 14 divalent lanthanides show a highly predictive pattern of the lowest 4f state energy location in compounds with the number n of electrons in the 4f shell. The lowest 4f state location controls important aspects like luminescence quantum efficiency, valence stability, and charge carrier trapping. An overview of our present state of knowledge is presented.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

The excitation spectrum of the red ≈ 610 nm Eu^{3+} emission in oxide compounds usually shows an intense and broad (0.6–0.8 eV) band around 250 nm. The band is due to electron transfer from an oxygen ligand to Eu^{3+} . The presence of this charge transfer (CT) excitation band makes Eu^{3+} ideally suited to sensitize the 254 nm emission of Hg in the tri-color fluorescence tube. For that reason numerous compounds with Eu^{3+} have been studied since the first use of lanthanides for lighting and display applications almost 50 years ago. Other lanthanides like Sm^{3+} , Yb^{3+} , and Tm^{3+} also show charge transfer excitation bands, yet at higher energy than for Eu^{3+} . It was realized soon that in the same compound the energy $E^{\text{CT}}(\text{Sm})$ of CT to Sm^{3+} always appears at about 1.1 eV higher energy than $E^{\text{CT}}(\text{Eu})$ [1–3].

In 2003 an analysis [4] on CT energies of all trivalent lanthanides in all types of compounds was performed with the aim to establish the values for the constant energy difference $\Delta E^{\text{CT}}(\text{Ln})$ between the energy $E^{\text{CT}}(\text{Ln})$ of CT to one specific lanthanide and $E^{\text{CT}}(\text{Eu})$ for Eu^{3+} . In that work it was proposed that $E^{\text{CT}}(\text{Ln})$ is a measure for the location of the ground state energy of the divalent lanthanide ion relative to the top of the valence band. Therefore the experimental value for $E^{\text{CT}}(\text{Eu})$ in a compound together with the tabulated values for $\Delta E^{\text{CT}}(\text{Ln})$ provide us with the location of the lowest 4f state $E_{\text{Vf}}(\text{Ln}^{2+})$ for each divalent lanthanide ion relative to the top

of the valence band in that compound. In later work a tabulation of $E^{\text{CT}}(\text{Eu})$ in about 200 different compounds was presented, and the relationship between $E^{\text{CT}}(\text{Eu})$ and the structure and chemical properties of compounds was addressed [5].

The location of the lowest energy lanthanide 4f^{*n*} state relative to host lattice bands determine important properties like; luminescence quantum efficiency, charge carrier trapping phenomena, and lanthanide valence stability. An intimate relationship exists between charge transfer energies, 4f electron binding energies, ionization potentials of the free lanthanide ions, and thermodynamic properties of the pure lanthanide metals. By combining information from those different fields of rare earth science, better estimates for the parameter values needed to predict the ground state energy locations for the divalent and the trivalent lanthanides in compounds can be obtained. In this work we will review the relationship between charge transfer energies, charge carrier trapping, valence stability, free ion ionization values and properties of lanthanide metals. We will present refined values for the parameters needed to construct energy level diagrams for lanthanide in compounds.

2. Experimental data on CT energies

The energy of the CT band can be extracted from published excitation spectra of trivalent lanthanide luminescence. Fig. 1 shows data for $E^{\text{CT}}(\text{Eu})$, $E^{\text{CT}}(\text{Yb})$, and $E^{\text{CT}}(\text{Sm})$ all in the same compound against $E^{\text{CT}}(\text{Eu})$ in that same compound. The data for Eu^{3+} then fall on a line with unit slope. The data for Yb^{3+} and Sm^{3+} show a constant

E-mail address: p.dorenbos@tudelft.nl.

Table 1

Average energy differences ΔE^{CT} between CT to Ln^{3+} and CT to Eu^{3+} . The number between brackets in column 3 and column 5 is the number of compounds used in averaging. n is the number of electrons in the $4f^n$ configuration of Ln^{3+} . $\Delta E_{\text{VF}}(\text{Ln}^{2+})$ is the proposed energy difference between the lowest Eu^{2+} 4f state and that of another Ln^{2+} . The 'old values' are from Ref. [4] and the new ones from this work. $\Delta E_{\text{VF}}(\text{Ln}^{3+})$ are the energy differences between the Ce^{3+} ground state and that of another Ln^{3+} . All energies are in eV.

Ln^{3+}	n	ΔE^{CT} (old)	$\Delta E_{\text{VF}}(\text{Ln}^{2+})$ (old)	ΔE^{CT} (new)	$\Delta E_{\text{VF}}(\text{Ln}^{2+})$ (new)	$\Delta E_{\text{VF}}(\text{Ln}^{3+})$ (new)
La	0	–	5.19	–	5.69	–
Ce	1	–	3.87	–	4.07	0
Pr	2	2.44 (1)	2.65	2.72 (1)	2.83	–1.94
Nd	3	2.29 (1)	2.27	2.2 (1)	2.50	–3.29
Pm	4	–	2.24	–	2.32	–3.63
Sm	5	1.16 (29)	1.21	1.13 (38)	1.24	–3.74
Eu	6	0	0	0	0	–4.92
Gd	7	–	4.32	–	4.67	–6.17
Tb	8	–	3.12	–	3.23	–0.88
Dy	9	2.04 (4)	2.28	2.06 (6)	2.30	–2.53
Ho	10	2.42 (1)	2.23	2.42 (1)	2.44	–3.55
Er	11	2.26 (3)	2.43	2.34 (7)	2.62	–3.41
Tm	12	1.67 (8)	1.67	1.77 (11)	1.77	–3.18
Yb	13	0.44 (20)	0.47	0.47 (32)	0.49	–4.15
Lu	14	–	–	–	–	–5.64

energy difference with that for Eu^{3+} . Some data points may deviate considerable, but one has to realize that, for example, Sm^{3+} data stem often from an entirely different source than Eu^{3+} data. Samples do not contain the same lanthanide concentration and often are also prepared differently which may affect the energy of CT. In column 3 of Table 1 the average values for $\Delta E^{\text{CT}}(\text{Ln})$, as were presented in Table 4 of Ref. [4], are reproduced. The numbers between brackets are the number of compounds involved in the averaging. Since 2003 new data became available and in column 5 we present revised values for $\Delta E^{\text{CT}}(\text{Ln})$.

The old values and the new values from Table 1 are displayed in Fig. 2. Data on Pm^{3+} are not available because of its radioactivity, and data on La^{3+} , Ce^{3+} , Gd^{3+} , and Tb^{3+} are not available because the energies of CT are at too high energy. Besides for La^{2+} , Ce^{2+} and Gd^{2+} the first 5d state is at lower energy than the lowest 4f state.

Actually $E^{\text{CT}}(\text{Ln})$ is the energy required to remove an electron from an anion ligand minus the energy released when placing it in the 4f orbital of Ln^{3+} to create the ground state of Ln^{2+} in the host lattice. Therefore the CT energies as function of the number of electrons in 4f reflect the binding energy of the added electron in the 4f orbital. For example, the binding is strong for the half filled 4f orbital of Eu^{2+} and the completely filled 4f orbital of Yb^{2+} leading to

low values for CT. The observation that the systematic variation is independent on the type of compound is linked with the shielded nature of the 4f orbital. The crystal field has then minor effect on that systematic.

Although the systematic in CT energies is almost independent on the type of compound, the absolute value $E^{\text{CT}}(\text{Ln})$ depends strongly on it. Fig. 3 compiles data available on $E^{\text{CT}}(\text{Eu})$ in about 300 different compounds. Data are grouped depending on the type of anions in the compound. The main variation with anion type is directly related with the binding strength of electrons in the anions and it can in first approximation be described by Jørgensen's empirical formula [6]

$$E^{\text{CT}} = 3.72(\chi_{\text{opt}}(x) - \chi_{\text{opt}}(m)) \text{ eV} \quad (1)$$

where $\chi_{\text{opt}}(x)$ is the optical electronegativity of the anion x from where the electron is transferred and $\chi_{\text{opt}}(m)$ is the optical electronegativity of the metal m where the electron is transferred to. $\chi_{\text{opt}}(x)$ is the same as the Pauling electronegativity, and the corrected values by Allred can be used [7]. $\chi_{\text{opt}}(m)$ is a value that must be determined empirically from observed CT energies.

Fig. 1. Energy of charge transfer to Eu^{3+} , Yb^{3+} , and Sm^{3+} against the energy of charge transfer to Eu^{3+} in compounds. Each Eu^{3+} data point represents a different compound. The location of CT-data for various compounds is indicated by the vertical lines.

Fig. 2. The average difference in CT to Ln^{3+} with that to Eu^{3+} in compounds. Solid squares are the revised values from this work, and solid triangles are the old values from Ref. [4] (displaced by +2 eV for illustration purposes). The solid curves connect the proposed values in this work (curve a) in and the old values from Ref. [4] (curve b) (displaced by +2 eV for illustration purposes).

Fig. 3. The available data on energy of charge transfer to Eu^{3+} in halide, chalcogenide, and pnictide compounds. The curve through the data is obtained from Jörgensen's optical electronegativity model. Solid symbols are Eu^{3+} CT energies estimated from CT energies of lanthanides other than Eu^{3+} .

Blasse [8] argued that for CT energies smaller than the horizontal line at 2.5 eV in Fig. 3 the oxidizing power of the anions becomes too small for Eu^{3+} to be a stable valence. In those compounds Eu will adopt the divalent state spontaneously. Indeed almost all Eu^{3+} CT-data in Fig. 3 pertain to CT energies larger than 2.5 eV. However, other lanthanides like Sm^{3+} often can still be oxidized in compounds where Eu^{3+} is not stable anymore, and from CT energies to those lanthanides one may estimate $E^{\text{CT}}(\text{Eu})$. Those estimated data are also shown in Fig. 3. Eq. (1) using $\chi_{\text{opt}}(\text{Eu}) = 2.0$ reproduces the general trend in CT energy with type of anion, but clearly a wide spread of CT values can be found within, for example, the oxide family of compounds. The binding strength of the oxygen ligands, the distance between ligands and lanthanide, the coordination number, the site size and Madelung potential, i.e., crystal structure and crystal chemistry, all affect the value for CT [5].

In excitation spectra of the red emission of Eu^{3+} in oxides the CT-band can be observed as a typically 0.6–0.8 eV wide and strong band at energies between 4 and 6 eV, see Fig. 3. After the charge transfer the transferred electron instantaneously returns to the hole left on the oxygen ligands, leaving Eu^{3+} in one of its excited $4f^6$ levels that eventually results in the intense red Eu^{3+} emission around 610 nm. There is also substantial lattice relaxation because Eu^{2+} is about 18 pm larger than Eu^{3+} . In other words there is a large Frank–Condon offset in the configuration coordinate diagram which causes that the CT bands are relatively broad. It also introduces a possible quenching route for Eu^{3+} luminescence. It was demonstrated by Struck and Fonger that the excited ^5D states of Eu^{3+} can be quenched by the CT-state especially when the CT state is at low energy [9]. In Fig. 4, data have been collected on the energy of CT to Eu^{3+} and the quenching temperature of Eu^{3+} emission. A clear more or less linear relationship can be observed. $\text{Y}_2\text{O}_3:\text{Eu}^{3+}$ has the CT band at energy close to the 254 nm (4.9 eV) emission of mercury and in addition it shows high quenching temperature of Eu^{3+} emission. This phosphor is widely applied in the tri-color fluorescence tube. Recently, we proposed that the quenching of Eu^{3+} emission in $\text{Al}_x\text{Ga}_{1-x}\text{N}$ near or below room temperature is also related with the small value for the CT energy [10]. Fig. 4 shows that the quenching temperature and the CT energy scale with the composition param-

eter x . It agrees with the observed linear relationship between CT energy and quenching temperature.

3. Charge transfer energies and absolute lanthanide level location

Since the final state in the charge transfer to Eu^{3+} is the ground state of Eu^{2+} , $E^{\text{CT}}(\text{Eu})$ should indicate the energy E_{VF} of the Eu^{2+} $4f^7$ ground state relative to the valence band. This idea was previously suggested by Wong et al. [11] and later used by Happek et al. [12,13]. In Ref. [4] an elaborate study of such relationship was made and the assumption that the energy E^{CT} can be used for the energy E_{VF} of the lowest $4f$ state above the top of the valence band was further motivated. In that work also estimates for the CT energy difference with the 'missing lanthanides' La^{3+} , Ce^{3+} , Pm^{3+} , Gd^{3+} , and Tb^{3+} were

Fig. 4. The quenching temperature of Eu^{3+} emission, defined as the temperature $T_{0.5}$ at which the luminescence has dropped to 50% of the low temperature value, as function of the energy of CT to Eu^{3+} .

Fig. 5. The 4f ground state level location of lanthanides in YPO₄. Horizontal bars are observed energies for charge transfer to trivalent lanthanides with n electrons in 4f. Curve (a) connects the 4f ground state energies of the divalent and curve (b) of the trivalent lanthanides as function of the number n of electrons in 4f of Ln³⁺.

provided. Column 4 in Table 1 compiles the average energy difference $\Delta E^{\text{CT}}(\text{Ln}) \equiv \Delta E_{\text{Vf}}(\text{Ln}^{2+})$ between $E^{\text{CT}}(\text{Ln})$ and $E^{\text{CT}}(\text{Eu})$ as were proposed in Ref. [4]. The solid curve (b) in Fig. 2 connects the same data values graphically. Since publication of Ref. [4] new data on CT energies to Ln³⁺ ions became available, and also further studies were made. The revised values for $\Delta E_{\text{Vf}}(\text{Ln}^{2+})$ are compiled in column 6 of Table 1. Curve (a) in Fig. 2 connects those data graphically. Most noteworthy differences with the 'old' values are the larger values for La, Ce, Gd, and Tb and the smaller value for Dy. Details on those studies and how the revised values were obtained will be published elsewhere.

Identifying $E^{\text{CT}}(\text{Ln})$ with $E_{\text{Vf}}(\text{Ln}^{2+})$ is an assumption that can be disputed. In an attempt to experimentally verify our assumption we decided to perform thermo-luminescence (TL) studies on YPO₄ doped with Ce³⁺ and co-doped with a second trivalent lanthanide. YPO₄ was selected because it contains only one crystallographic yttrium site that the trivalent lanthanide ion may occupy. Furthermore values for $E^{\text{CT}}(\text{Ln})$ are well documented for YPO₄. Fig. 5 shows the level scheme constructed for YPO₄. The energy of the top of the valence band is set at zero. The horizontal bars for $n = 3, 5, 6, 9, 11, 12, 13$ represent $E^{\text{CT}}(\text{Ln})$ values observed for Nd³⁺, Sm³⁺, Eu³⁺, Dy³⁺, Er³⁺, Tm³⁺, and Yb³⁺. Within our model they also mark the energies of the lowest energy 4f state of the respective divalent lanthanides. The double seated curve through the data is the same as curve (a) in Fig. 2 but displaced to run best through the CT data bars. At 8.6 eV the excitation of the PO₄³⁻ group takes place and this marks the energy of the first exciton band. The bottom of the conduction band or mobility edge is estimated at around 9.3 eV [5]. The difference is the estimated electron and hole binding energy of the exciton. In the same scheme the estimated location of the ground state energy of Ce³⁺ is shown together with the location of its first 5d state [4].

One should not interpret the energy levels as single electron states but as total energy states. For example, the location of the ground state 4f level of Ce³⁺ at 4 eV above the top of the valence band means that it requires 4 eV less energy to remove an electron from the 4f shell of Ce³⁺ than from the top of the valence band. It also means that a hole in the valence band will be trapped by Ce³⁺ with 4 eV binding energy. Or that Ce⁴⁺ is 4 eV more stable than a free hole at the top of the valence band. When Sm³⁺ is doped in YPO₄ this means that the Sm²⁺ ground state is not occupied with an

Fig. 6. Normalized thermoluminescence glow curves of YPO₄:Ce³⁺:Ln³⁺ after β -irradiation monitoring Ce³⁺ emission (from Ref. [14]).

electron. Its location at 2.6 eV below the bottom of the conduction band implies that when Sm³⁺ traps an electron from the conduction band it will be trapped with 2.6 eV binding energy. Eu³⁺ and Yb³⁺ provide even deeper electron traps.

Recently, we performed thermo-luminescence (TL) studies on YPO₄ with Ce³⁺ and co-doped with either Pr³⁺, Nd³⁺, Sm³⁺, Dy³⁺, Ho³⁺, Er³⁺, or Tm³⁺ [14]. Under β -irradiation holes are created in the valence band and electrons in the conduction band. We anticipated that Ce³⁺ will be the dominant hole trap and that the other trivalent lanthanides form electron traps. The scheme of Fig. 5 predicts that the deepest one is by Sm³⁺, followed by Tm³⁺, Dy³⁺, Ho³⁺, Nd³⁺, Er³⁺, and finally Pr³⁺. Fig. 6 shows the thermo-luminescence glow curves recorded after β -irradiation with an optical filter placed on the Ce³⁺ 5d–4f emission. The sequence in the temperature for the maximum of the glow peaks follows very nicely the predicted sequence from Fig. 5. The glow curve for Pr³⁺ as a co-dopant could not be measured because it occurs below room temperature which was not accessible to our TL-reader. The glow curves for Eu³⁺ and Yb³⁺ are expected at very high temperature also outside reach of our TL-reader.

Fig. 7. Curve (a) shows the anticipated electron trapping depths provided by trivalent lanthanides in YPO₄ assuming that the bottom of the conduction band is at 9.3 eV. Curve (b) the depth of electron trapping relative to the exciton state at 8.6 eV. ∇ , trapping depths derived from glow curve analysis. Δ , trapping depths derived from the varying heating rate method (see Ref. [14] for further details).

Fig. 8. The ionization energies of the free divalent and the free trivalent lanthanides from Johansson in Ref. [18].

Fig. 7 shows results from glow curve analysis performed in Ref. [14]. Electron trapping depths derived from two different analysis methods are shown together with the trapping depths predicted from Fig. 5 as illustrated by curve (a). On average, the trapping depths from TL analysis is about 0.5 eV smaller than those predicted from Fig. 5. Actually, considering possible errors in TL analysis and a possible error in the location of the bottom of the conduction band, we regard this as a very good agreement. It is also not excluded that recombination of a trapped electron with the hole on Ce⁴⁺ may proceed via tail states below the bottom of the conduction band. For comparison we have also drawn (curve b) the trapping depths relative to the exciton energy of 8.6 eV. The initial assumption that the energy of charge transfer from an anion to a trivalent lanthanide provides direct information on the absolute location of the 4f ground state above the top of the valence band is therefore nicely confirmed by the TL results of Ref. [14].

4. Lanthanide-doped systems, the free lanthanide ions, and pure lanthanide metals

The previous two sections dealt with $E^{\text{CT}}(\text{Ln})$ in inorganic compounds. It was mentioned that the variation in the energy for CT with the number of electrons in the 4f orbital relates to the variation in the binding energy of 4f electrons. These results and findings emerged from luminescence spectroscopy studies of lanthanide impurities in compounds. There are two other areas of rare earth science that provide complementary information that appears of much relevance to the lanthanide doped systems. These are the ionization energies of the free divalent and the free trivalent lanthanide ions and the properties of pure lanthanide metals.

For most of the free lanthanide ions the values for their second and third ionization potentials were not determined experimentally but are estimations that are based on experimentally known 4f–5d and 4f–6s transition energies. Fig. 8 shows the binding energies, i.e. ionization potentials, of the 4f electron in the free lanthanide ions based on such work [15–17]. The shape of curve (a) for the divalent lanthanide ions is very similar to the $\Delta E^{\text{CT}} \equiv \Delta E_{\text{Vf}}(\text{Ln}^{2+})$ curve in Fig. 2 curve (a). There are however slight but important differences. The 4f electron binding energy in the free ion Yb²⁺ is few tenths of an eV larger than that in the free ion Eu²⁺. However, curve (a) in Fig. 2 shows that the Yb²⁺ 4f ground state energy in inorganic compounds is at about 0.5 eV

Fig. 9. The location of the 4f ground states of curve (a) divalent and curve (b) trivalent lanthanides in the pure lanthanide metals relative to the Fermi energy as obtained from XPS and BIS data. Reproduced from Ref. [20].

higher energy than that of Eu²⁺ which implies 0.5 eV less binding energy.

Another topic that has attracted considerable attention is the chemistry and physics of the pure lanthanide metals. From XPS (X-ray photoelectron spectroscopy) and BIS (Bremsstrahlung isochromat spectroscopy) the location of the 4f levels in pure lanthanide metals is known. Fig. 9 shows those locations for the 4f states of divalent and trivalent lanthanides [20]. Apart from Eu and Yb all the lanthanide metals have the trivalent electron configuration. The three 5d6s² electrons form the conduction band. We observe the same patterns as for the ionization energies of the free ions and for the ΔE^{CT} energies in lanthanide doped compounds. Note that the Yb²⁺ ground state is located at few tenths of eV above the Eu²⁺ ground state in the pure lanthanide metals. This resembles what we have observed for the $\Delta E^{\text{CT}}(\text{Yb})$ value.

Johansson determined the energy differences $\Delta E_{\text{II,III}}$ between the heat of formation of hypothetical divalent metals with that of trivalent metals. These values were then used as a basis to estimate the $\Delta E_{\text{III,IV}}$ between trivalent metals and hypothetical four valence metals also. These ΔE values are practically the same as the energy differences between 4f states and the Fermi level in metals [18]. Fig. 10 compiles the two sets of ΔE values and indeed it is almost similar as in Fig. 9. The heat of formation of the lanthanide metals is known with reasonable accuracy and we regard the double seated curves in Fig. 10 as more accurate than the ones based on XPS and BIS data in Fig. 9.

Based on the $\Delta E_{\text{III,IV}}$ values Johansson [18] made also better estimates for the fourth ionization potentials of the lanthanides. Those estimated values are shown in Fig. 8. N.B. later also Thiel et al. [19] provide estimates for the fourth ionization energy of the lanthanides that agree well with those of Johansson.

Comparing the so-called double-seated curves for the free lanthanide ions in Fig. 8 with that for the pure lanthanide metals in Fig. 10 there is much similarity but also important differences. Most striking is the energy difference between the 4f ground state of the divalent with that of the trivalent lanthanides. It is about 20 eV for free ions but about 7 eV for the pure lanthanide metal. This reduction by a factor of three is attributed to an almost perfect screening of the lanthanide ion by the conduction band electrons [21]. In addition the double seated curves for the metals are tilted with respect to those for the free ions. With increase of the number of electrons

Fig. 10. The location of the 4f ground state of curve (a) divalent and curve (b) trivalent lanthanides in the pure lanthanide metals as determined from the heat of formation by Johansson in Ref. [18].

in 4f the 4f ground state energy is lifted slightly further. For example, the ground state energy of free Yb²⁺ is at few tenths of an eV lower energy than that of free Eu²⁺ but for the metals it is at about 0.5 eV higher energy. This is precisely the same as the value for ΔE^{CT} for Yb³⁺, see Fig. 2 and Table 1.

The following equation has been proposed to relate the ground state 4f energy E_{4f} of lanthanides in compounds with the ionization energy I_f of the free lanthanide ions [22,19]

$$E_{4f} = I_f - E_L + \alpha_R(R - R_0) \quad (2)$$

where E_L is a constant energy shift closely related with the Madelung potential pertaining to all lanthanides similarly. The last term in Eq. (2) is a correction due to the lanthanide contraction leading to additional lattice relaxation and changing Madelung potential. In fact E_L creates a vertical energy shift of the free ion curves in Fig. 8 and the last term creates a tilting of the free ion curves, i.e., the double seated curve is lifted further with increase of n .

It turns out that with Eq. (2) the free ionization curves in Fig. 8 can be mapped almost perfectly onto the pure lanthanide metal curves of Fig. 10. By combining now the ΔE^{CT} data with the free ion ionization data and the pure lanthanide metal data, a set of values can be established that provide us with the most appropriate double seated curves for the divalent lanthanides and for the trivalent ones in compounds. By requiring self-consistency one may also refine the estimates for the third and fourth ionization potentials. Details on obtaining those refined estimates will be published elsewhere. In this work we have listed the obtained values for $\Delta E_{\text{Vf}}(\text{Ln})$ for the divalent and the trivalent lanthanides in column 6 and column 7 of Table 1, respectively.

It is most convenient to use the energy $E^{\text{CT}}(\text{Eu})$ of CT to Eu³⁺ as an anchor point to position the double seated curve for the divalent lanthanides in a compound as has been done in Fig. 5. This is the reason that we have specified the $\Delta E_{\text{Vf}}(\text{Ln}^{2+})$ values relative to Eu²⁺ in Table 1. One also likes to place the double seated curve for the trivalent lanthanides in the same scheme, and for that a suitable anchor point needs to be used also. This is not as easily and abundantly available as for the divalent ions. Quenching of the 5d–4f emission of Ce³⁺ due to thermally activated ionization of the 5d electron may provide us with the activation energy for ionization, and from that the absolute location of the 5d state (and then also the 4f ground state) below the conduction band can be deduced. Pho-

toconductivity studies on Ce³⁺ doped compounds occasionally can also provide the necessary information. Presently we are exploring a new technique based on thermoluminescence studies on double doped compounds. However instead of exciting with β -irradiation, photon excitation will be used. By scanning the excitation wavelength the threshold for trap filling can be determined which in turn may provide us with the location of the Ce³⁺ 4f ground state relative to the conduction band. In Table 1 the proposed $\Delta E_{\text{Vf}}(\text{Ln}^{3+})$ values are specified relative to Ce³⁺.

In Fig. 5 the double seated curve has been drawn based on the anchor point for the Ce³⁺ ground state at 4 eV above the valence band [4]. Note that the energy difference between the ground state of Eu²⁺ and the ground state of Eu³⁺ is 6.4 eV which is much smaller than for the free Eu ions (18 eV) but larger than for the pure Eu metal (5.4 eV). Apparently the screening effects in ionic crystals are close to, but somewhat smaller than, in the pure lanthanide metals. We have strong indications that the energy difference between the Eu²⁺ and Eu³⁺ ground states in compounds varies from above 7 eV in poorly polarizable compounds like the fluorides to below 6 eV in strongly polarizable compounds like bromides and sulfides. It may well be that the energy difference between the Eu²⁺ ground state and the Eu³⁺ can be predicted well beforehand from the refractive index of the compound. Note that the free lanthanides and the pure lanthanide metals form the extreme ends on the 'polarizability scale', i.e. zero polarizability and zero screening for the free lanthanides and infinity polarizability and perfect screening for the lanthanide metals.

5. Conclusions

Spectroscopic information on charge transfer bands of trivalent lanthanides in compounds provides us with the location of the divalent lanthanide ground state above the valence band. Those locations are consistent with the depth of electron trapping by trivalent lanthanides that were derived from thermoluminescence studies on YPO₄:Ce³⁺:Ln³⁺ double doped phosphors. A close relationship between lanthanide level location in impurity doped compounds with the free lanthanide ions and the lanthanide metals has been demonstrated. By exploiting information from free ion levels and pure lanthanide metals more accurate parameter values were derived to construct lanthanide level schemes in compounds.

References

- [1] C.K. Jørgensen, *Mol. Phys.* 5 (1962) 271.
- [2] J.C. Barnes, H. Pincott, *J. Chem. Soc. (a)* (1966) 842.
- [3] G. Blasse, A. Bril, *Phys. Lett.* 23 (1966) 440.
- [4] P. Dorenbos, *J. Phys.: Condens. Matter* 15 (2003) 8417.
- [5] P. Dorenbos, *J. Lumin.* 111 (2005) 89.
- [6] C.K. Jørgensen, *Modern Aspects of Ligand Field Theory*, North-Holland Publishing Company, Amsterdam, 1971.
- [7] A.L. Allred, *J. Inorg. Nucl. Chem.* 17 (1961) 215.
- [8] G. Blasse, N. Sabbatini, *Mater. Chem. Phys.* 16 (1987) 237.
- [9] C.W. Struck, W.H. Fonger, *J. Lumin.* 1 (2) (1970) 456.
- [10] P. Dorenbos, E. van der Kolk, *Opt. Mater.* 30 (2008) 1052.
- [11] W.C. Wong, D.S. McClure, S.A. Basun, M.R. Kokta, *Phys. Rev. B* 51 (1995) 5682.
- [12] U. Happek, S.A. Basun, J. Choi, J.K. Krebs, M. Raukas, *J. Alloys Compd.* 303 (2000) 198.
- [13] U. Happek, J. Choi, A.M. Srivastava, *J. Lumin.* 94–95 (2001) 7.
- [14] A.J.J. Bos, P. Dorenbos, A. Bessiere, B. Viana, *Radiat. Measure.* 43 (2008) 222.
- [15] J. Sugar, J. Reader, *J. Chem. Phys.* 59 (1973) 2083.
- [16] L.R. Morss, *Chem. Rev.* 76 (1976) 829.
- [17] L. Brewer, in: S.P. Sinha, D. Reidel (Eds.), *Systematics and the Properties of the Lanthanides*, Publishing Company, Dordrecht, The Netherlands, 1983, p. 17.
- [18] B. Johansson, *Phys. Rev. B* 20 (1979) 1315.
- [19] C.W. Thiel, Y. Sun, R.L. Cone, *J. Modern Opt.* 49 (2002) 2399.
- [20] J.K. Lang, Y. Baer, P.A. Cox, *J. Phys. F: Metal Phys.* 11 (1981) 121.
- [21] J.F. Herbst, D.N. Lowy, R.E. Watson, *Phys. Rev. B* 6 (1972) 1913.
- [22] C. Pedrini, D.S. McClure, C.H. Anderson, *J. Chem. Phys.* 70 (1979) 4959.

Optical studies of sub-3 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals

Sameer V. Mahajan^{a,c}, James H. Dickerson^{b,c,*}

^a Interdisciplinary Program in Materials Science, Vanderbilt University, Nashville, TN 37235, United States

^b Department of Physics and Astronomy, Vanderbilt University, Nashville, TN 37235, United States

^c Vanderbilt Institute of Nanoscale Science and Engineering, Vanderbilt University, Nashville, TN 37235, United States

ARTICLE INFO

Article history:

Received 3 June 2008

Received in revised form

27 September 2008

Accepted 18 December 2008

Available online 30 December 2008

Keywords:

Nanostructured materials

Rare earth alloys compounds

Phosphors

Optical spectroscopy

Luminescence

ABSTRACT

Colloidally stable sub-3 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals have been synthesized via a hot solution phase technique. Optical properties of the nanocrystals are studied as a function of size. Both nanocrystal compositions exhibit a new optical signature, an emission peak at 620 nm. Intensity modulation of this peak has been observed for all nanocrystal sizes, suggesting surface-dependent or crystal-field dependent effect. Photoluminescence intensity of smaller Eu_2O_3 nanocrystals was comparable to that of the $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

Recent progress in the development of rare earth (RE) nanocrystalline materials has focused on new techniques to synthesize these materials to optimize their robust optical and magnetic characteristics [1–11]. Many of their physical traits, such as their small feature size and millisecond luminescence lifetimes, have facilitated the excitement over these materials, making them attractive candidates for a variety of applications, such as high resolution video displays and luminescent probes in bio-imaging applications [12,13]. Thus, the synthesis of monodisperse, colloidally stable, rare earth based nanocrystals and their optical properties are perforce sought for their implementation in bio-imaging applications and for the fabrication of nanocrystalline thin film devices [14,15]. For such biological applications, nanocrystals typically are suspended in fluid environments for which colloidal stability is of prime importance. Colloidal stability suppresses nanocrystal agglomeration and facilitates the manipulation of the surface of individual nanocrystals for bio-conjugation.

Rare earth sesquioxide nanocrystals, such as europium sesquioxide (Eu_2O_3) and RE-doped gadolinium or yttrium sesquioxide ($\text{Gd}_2\text{O}_3:\text{RE}^{3+}$, $\text{Y}_2\text{O}_3:\text{RE}^{3+}$; RE = Eu, Tb, Er), have been synthesized in a size-range of 5–100 nm through a number of meth-

ods, including gas-phase condensation [1], sol-lyophilization [4], flame pyrolysis [9] and colloidal synthesis [2,3,5,6,10]. The optical properties of RE^{3+} ion based materials originate from 4f–4f electron transitions within RE^{3+} ions [11]. Electrons are excited into the charge-transfer state of the Eu–O bond of sesquioxides (Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$) when excited with ultraviolet radiation ($\lambda = 254$ nm from a xenon lamp, for this study), and subsequently radiative decay of these electrons from ^5D energy levels into ^7F energy levels provide luminescence. Since the core electronic energy levels within Eu^{3+} ions do not change for different particle sizes, the electron transition energies are relatively unaffected by the size of nanocrystals.

The characteristic emission peak, corresponding to $^5\text{D}_0 \rightarrow ^7\text{F}_2$ electron transition in Eu^{3+} ions, resides near 612 nm (red) in body-centered-cubic sesquioxides. The energy levels of Eu^{3+} ions change when the ions experience different crystal field environments. The crystal field may change when the atomic arrangement varies from its equilibrium position. Considering the very large surface-to-volume ratio for very small nanocrystals, these materials may experience some lattice distortion, which would lead to a variation in the crystal field. Thus, the optical signature of the nanocrystal may depend on the size of the nanocrystal. To date, there is no report of a study of the optical properties of nanocrystals when their size approaches that of a single lattice constant ($a_0 = 10.86$ Å for Eu_2O_3 and $a_0 = 10.81$ Å for Gd_2O_3).

Here, we report synthesis and optical properties of sub-3 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals as a function of size. The nanocrystal size is controlled via addition of oleic acid (OA)

* Corresponding author at: Department of Physics and Astronomy, Vanderbilt University, Nashville, TN 37235, United States.

E-mail address: james.h.dickerson@vanderbilt.edu (J.H. Dickerson).

Table 1
Comparison of synthesis reaction mixture and nanocrystal size.

RE precursor (mM)	Oleic acid (mM)	Tri- <i>n</i> -octylamine (mM)	Nanocrystal size (nm)
0.50	0.00	16.0	~1.8
0.50	0.25	16.0	~2.4
0.50	1.00	16.0	~3.0

during the synthesis. Photoluminescence (PL) measurements of the sub-3 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals reveal a new luminescence peak near 620 nm that is not observed in larger nanocrystals or in the bulk. For different nanocrystal sizes, we observed intensity modulations of a new emission peak at 620 nm. Also, photoluminescence intensity of Eu_2O_3 nanocrystals is comparable to $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals for smaller nanocrystals sizes.

2. Experimental

Europium(III) chloride hexahydrate ($\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$, 99.99%), gadolinium(III) chloride hexahydrate ($\text{GdCl}_3 \cdot 6\text{H}_2\text{O}$, 99.99%), tri-*n*-octylamine (90.0%), sodium oleate (95%), and oleic acid (90%) were employed for nanocrystal synthesis. The nanocrystals were prepared in a two-stage synthesis as described earlier [8]. First, europium oleate was prepared by heating a mixture of europium chloride hexahydrate and sodium oleate at 60 °C in a water–ethanol–hexane mixture for 4 h. Second, a mixture of europium oleate, oleic acid, and tri-*n*-octylamine (refer to Table 1) was heated to ~350 °C at the rate of 5 °C min⁻¹ in an Ar environment and was refluxed for 1 h.

Fig. 1. Nanocrystals of Eu_2O_3 (a) and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ (b) of ~2.4 nm diameter. Scale bar: 12 nm.

During this period, the nucleation and growth of the Eu_2O_3 nanocrystals occurred. For the synthesis of $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ (10%) nanocrystals, 0.45 mM gadolinium oleate and 0.05 mM europium oleate were employed, while keeping all other synthesis parameters the same. The size of the nanocrystals was tuned by addition of different amount of oleic acid. The amount of precursors used in the reaction mixture and corresponding nanocrystal size is reported in Table 1. X-ray diffraction measurements were conducted using a Scintag X1 system with a $\text{Cu K}\alpha$ X-ray source. Nanocrystal imaging was performed on a Philips CM 20 transmission electron microscope (TEM) operating at 200 kV. Photoluminescence measurements were performed on nanocrystal dispersions in hexane using a Fluorolog-3 spectrophoto-fluorometer, equipped with a 450 W xenon lamp set at its 254 nm line.

Fig. 2. PL spectra of Eu_2O_3 (a) and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ (b) nanocrystals synthesized with varying amount of OA. The spectra are normalized to the peak at 612 nm and shifted vertically for clarity. (c) The intensity variation of the new peak (620 nm) with respect to the 612 nm peak determined from the above PL spectra.

3. Results and discussion

Synthesis of monodisperse, small size nanocrystals rely on controlled nucleation and growth of oxide nuclei via appropriate precursor and synthesis temperature selection. The pathway for any hot solution phase metal oxide nanocrystal synthesis involving oleic acid includes formation of metal-oleate as a transition stage [16,17]. Therefore, it is advantageous to use Eu/Gd-oleate as $\text{Eu}^{3+}/\text{Gd}^{3+}$ -precursor for controlled nucleation. In addition, the synthesis temperature ($\sim 350^\circ\text{C}$) slightly below the decomposition temperature of Eu/Gd-oleate ($\sim 370^\circ\text{C}$) facilitates slow nucleation and growth of $\text{Eu}_2\text{O}_3/\text{Gd}_2\text{O}_3$ nanocrystals leading to very small size nanocrystals. The size of nanocrystals can also be controlled with addition of oleic acid. The addition of oleic acid facilitated partial redissolution of oxide nuclei and thus, conserving RE-oleate for the nanocrystals growth. Thus, within a small size regime, increased amount of oleic acid produced larger nanocrystals. Amount of oleic acid used in the reaction mixture and corresponding nanocrystal size is reported in Table 1. Fig. 1 shows Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals of 2.4 nm diameter in size.

The optical properties of the Eu^{3+} -based materials derive from 4f–4f electron transitions within the Eu^{3+} ions. Upon excitation of these materials with UV light, the excited electrons decay radiatively from $^5\text{D}_0 \rightarrow ^7\text{F}_j$ ($j=0, 1, 2, 3$, and 4) energy levels. The characteristic red emission for Eu^{3+} -based materials originates from the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ electric dipole transition, which is the most sensitive of the $^7\text{F}_j$ transitions to the position and local environment of Eu^{3+} ions within the crystal lattice. Thus, any changes in the local crystal field surrounding the Eu^{3+} ions will directly result in modification of the peaks arising from $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition.

In Fig. 2a and b, we plot the size-dependent photoluminescence spectra for the Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. Of substantial interest to us was the emergence of a new luminescence peak at 620 nm, a characteristic which has not been reported in other Eu^{3+} -based rare earth sesquioxide nanostructures. The photoluminescence spectra were recorded for the Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals of different sizes. We attribute the peaks at 612 nm, 620 nm, and 625 nm to the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition of Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. The observed peak broadening for our nanocrystals is consistent with that observed for the other nanocrystalline Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ materials [2,4,5,8,18,19]. Comparing the spectra of our nanocrystals with the spectra reported for nanocrystalline and bulk Eu_2O_3 materials, we easily identify the conventional peak for cubic Eu_2O_3 at 612 nm. The peak at 625 nm has been reported for cubic Eu_2O_3 nanodisks, which the authors explained as due to the occupation of Eu^{3+} ions in a unique site due to ultrathin thickness (1.6 nm) of nanodisks [20]. The presence of this spectral feature suggests a similar size-dependent effect on the $^7\text{F}_j$ states in our nanocrystals.

In addition to these luminescence characteristics, we observe a peak at 620 nm, which is a new luminescence peak observed for Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanomaterials. In observing this peak for the various nanocrystal sizes, we noticed a variation in the intensity of the peak (620 nm) juxtaposed with the stronger primary peak (612 nm). We monitored the intensity for both nanocrystal types as a function of the nanocrystal size. To simplify the comparison, all the spectra were normalized to the peak at 612 nm. The ratio of intensities of the two peaks ($R = I_{620\text{ nm}}/I_{612\text{ nm}}$) is plotted as a function of nanocrystal size in Fig. 2c. For Eu_2O_3 nanocrystals, the ratio R decreases from 0.88 to 0.70 as nanocrystal size increases. The intensity variation of the peak as a function of nanocrystal size is expected in $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. However, the trend is different to that for the Eu_2O_3 nanocrystals. Intensity modulation of the peak with nanocrystal size could likely be due to occupation of Eu^{3+} ion in a unique surface site, or exposure to an anisotropic

Fig. 3. (a) Integrated PL intensity of (a) ~ 1.8 nm (no OA) and (b) ~ 2.4 nm (0.25 mM OA) Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. The X and Y error bars for the data are within the data point. The solid lines represent linear fit to each dataset.

crystal field induced because of strain on the surface of very small nanocrystals.

To continue exploring the effect of nanocrystal size on the photoluminescence intensity of rare earth sesquioxide nanocrystals, we investigated the relationship between the integrated PL intensity and the absorbance of the Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. The integrated PL intensity of nanocrystals was determined by integrating PL spectra over 525–725 nm wavelength range and is plotted as a function of nanocrystal absorbance, which is shown in Fig. 3a and b for ~ 1.8 nm and ~ 2.4 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. Low absorbance values (or low nanocrystal concentration) are considered to avoid self-quenching effects of nanocrystal suspension. For a given absorbance, 1.8 nm and 2.4 nm Eu_2O_3 nanocrystals have same integrated luminescence intensity. However, the integrated luminescence intensity is lower for 1.8 nm $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals than that of 2.4 nm $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals. This suggests that luminescence intensities of Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals are comparable for smaller nanocrystal sizes.

4. Conclusion

Sub-3 nm Eu_2O_3 and $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals were synthesized by varying the amount of oleic acid during the synthesis. Photolu-

minescence measurements reveal a new optical signature for these nanocrystals, a new luminescence peak at 620 nm. Intensity modulation of the new peak was observed for different nanocrystal size, which could be due to an anisotropic crystal field environment within the nanocrystal or to the occupation of Eu^{3+} ions in unique lattice sites. As the size of the Eu_2O_3 nanocrystals decreased, their associated photoluminescence intensity became comparable to that of the $\text{Gd}_2\text{O}_3:\text{Eu}^{3+}$ nanocrystals.

Acknowledgment

This research is supported in part by Vanderbilt Institute for Nanoscale Science and Engineering (VINSE).

References

- [1] H. Eilers, B.M. Tissue, *Mater. Lett.* 24 (1995) 261–265.
- [2] G. Wakefield, H.A. Keron, P.J. Dobson, J.L. Hutchison, *J. Colloid Interface Sci.* 215 (1999) 179–182.
- [3] G. Wakefield, H.A. Keron, P.J. Dobson, J.L. Hutchison, *J. Phys. Chem. Solids* 60 (1999) 503–508.
- [4] C. Louis, R. Bazzi, M.A. Flores, W. Zheng, K. Lebbou, O. Tillement, B. Mercier, C. Dujardin, P. Perriat, *J. Solid State Chem.* 173 (2003) 335–341.
- [5] R. Bazzi, M.A. Flores, C. Louis, K. Lebbou, W. Zhang, C. Dujardin, S. Roux, B. Mercier, G. Ledoux, E. Bernstein, *J. Colloid Interface Sci.* 273 (2004) 191–197.
- [6] R. Bazzi, M.A. Flores-Gonzalez, C. Louis, K. Lebbou, C. Dujardin, A. Brenier, W. Zhang, O. Tillement, E. Bernstein, P. Perriat, *J. Lumin.* 102 (2003) 445–450.
- [7] Y.C. Cao, *J. Am. Chem. Soc.* 126 (2004) 7456–7457.
- [8] S.V. Mahajan, J.H. Dickerson, *Nanotechnology* 18 (2007) 325605.
- [9] D. Dosev, B. Guo, I.M. Kennedy, *J. Aerosol Sci.* 37 (2006) 402–412.
- [10] F. Soderlind, H. Pedersen, J.R.M. Petoral, P.-O. Kall, K. Uvdal, *J. Colloid Interface Sci.* 288 (2005) 140–148.
- [11] S. Shionoya, W.M. Yen, *Phosphor Handbook*, CRC Press, Boca Raton, 1999.
- [12] J. Feng, G. Shan, A. Maquieira, M.E. Koivunen, B. Guo, B.D. Hammock, I.M. Kennedy, *Anal. Chem.* 75 (2003) 5282–5286.
- [13] M. Nickkova, D. Dosev, S.J. Gee, B.D. Hammock, I.M. Kennedy, *Anal. Chem.* 77 (2005) 6864–6873.
- [14] M.A. Islam, Y.Q. Xia, D.A. Telesca, M.L. Steigerwald, I.P. Herman, *Chem. Mater.* 16 (2004) 49–54.
- [15] S.V. Mahajan, D.W. Kavich, M.L. Redigolo, J.H. Dickerson, *J. Mater. Sci.* 41 (2006) 8160–8165.
- [16] J. Park, K.J. An, Y.S. Hwang, J.G. Park, H.J. Noh, J.Y. Kim, J.H. Park, N.M. Hwang, T. Hyeon, *Nat. Mater.* 3 (2004) 891–895.
- [17] T. Hyeon, S.S. Lee, J. Park, Y. Chung, H.B. Na, *J. Am. Chem. Soc.* 123 (2001) 12798–12801.
- [18] B. Bihari, H. Eilers, B.M. Tissue, *J. Lumin.* 75 (1997) 1–10.
- [19] H.S. Yang, H. Lee, P.H. Holloway, *Nanotechnology* 16 (2005) 2794–2798.
- [20] R. Si, Y.W. Zhang, H.P. Zhou, L.D. Sun, C.H. Yan, *Chem. Mater.* 19 (2007) 18–27.

Absorption cross-section control of Eu(III) complexes for increase of amplified spontaneous emission excited by third harmonic of nanosecond Nd:YAG laser

Yasuchika Hasegawa^{a,*}, Kazuki Nakamura^b, Hideki Kawai^c, Naoki Yasuda^b,
Yasunori Tsukahara^d, Yuji Wada^e

^a Graduate School of Materials Science, Nara Institute of Science and Technology, 8916-5 Takayama-cho, Ikoma, Nara 630-0192, Japan

^b Advanced Technology R&D Center, MITSUBISHI Electric Corporation, 8-1-1 Tsukaguchi-Honmachi, Amagasaki, Hyogo 661-8661, Japan

^c Research Institute of Electronics, Shizuoka University, 3-5-1 Johoku, Hamamatsu, Shizuoka 432-8011, Japan

^d Graduate School of Engineering, Osaka University, 2-1 Yamada-oka, Suita, Osaka 565-0871, Japan

^e Graduate School of Science and Engineering, Tokyo Institute of Technology, 2-12-1 Ookayama, Meguro-Ku, Tokyo 152-8552, Japan

ARTICLE INFO

Article history:

Received 2 June 2008

Received in revised form 1 August 2008

Accepted 1 September 2008

Available online 31 October 2008

Keywords:

Luminescence

Thin-films

Polymers

ABSTRACT

The amplified spontaneous emission (ASE) properties of polymer thin-films containing Eu(III) complexes were demonstrated by observing emissions from the edge of excited polymer thin-films. The amplification of the ASE components of Eu(III) complexes was increased in proportion to the absorption cross-sections. In particular, the amplitude percentages of the ASE component of Eu(III) complexes having naphthyl groups (absorption cross-section at 355 nm: $850 \times 10^{-19} \text{ cm}^2$) were estimated to be over 60% under 10 mJ excitation.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Lanthanide(III)-doped luminescent materials are expected to open up the development of some optical devices such as laser and photo-amplifier systems because of their f–f electric transition which is ideal for the formation of population inversion [1–3]. In particular, luminescent polymer incorporating europium(III) complexes have been regarded as attractive for use as luminescent materials. Koike has introduced the possibility of organic fiber laser systems using Eu(III) complexes incorporated organic optical fibers of polymethylmethacrylate (PMMA) [4]. We have also reported that strong luminescent Eu(III) complexes showed amplified spontaneous emission (ASE) from Eu(III) complexes in polymer thin-film micro-cavities by using a polyphenylsilsequioxane (PPSQ) [5,6]. Furthermore, Kido has studied that dielectric sphere systems containing Eu(III) complexes performed efficient ASE by using smaller excitation energy for laser oscillation [7]. Luminescent polymer systems containing Eu(III) complexes are promising materials for novel polymer-based optical devices.

We have reported on the molecular design of luminescent Eu(III) complexes for the enhancement of ASE properties. The

enhancement of ASE properties from luminescent polymer systems containing Eu(III) complexes is realized by increasing the stimulated emission cross-section (SEC) and the absorption cross-section [8]. The stimulated emission cross-sections of the luminescent Eu(III) complexes are closely related to full width at half maximums (FWHMs) of the emission spectra, which is dominated by the geometrical structure of the Eu(III) complexes. Previously, we have observed that the narrow FWHMs of anti-symmetrical Eu(III) complexes lead to the increase of stimulated emission cross-sections and enhanced ASE properties [9,10]. The control of the geometrical structures in Eu(III) complexes is a key contributing factor in the increase of stimulated emission cross-sections.

Here, we focus on the effect of the absorption cross-section on the ASE properties of luminescent polymers including Eu(III) complexes. In order to control the absorption cross-section, luminescent Eu(III) complexes with various absorption coefficients at the excitation wavelength (excitation wavelength: 355 nm, third harmonic of nanosecond Nd:YAG laser) were prepared. The absorption coefficients of the Eu(III) complexes were manipulated by organic β -diketonato ligands having methyl, trifluoromethyl, phenyl and naphthyl groups (Fig. 1). According to the polymer matrix for the preparation of polymer thin-films, we selected polyphenylsilsequioxane. PPSQ is a ladder-type polymer with siloxane bonds as a main chain, and has high transparency in the

* Corresponding author.

E-mail address: hasegawa@ms.naist.jp (Y. Hasegawa).

Fig. 1. Chemical structures of Eu(III) complexes.

visible and ultraviolet region [11]. The optical micro-cavity was constructed by forming a high refractive index film of PPSQ (refractive index: 1.558) on the glass substrate. Polymer thin-films containing Eu(III) complexes were excited by the third harmonic (355 nm) of nanosecond Nd:YAG laser. The ASE properties of the polymer thin-films containing Eu(III) complexes were demonstrated by observing the emissions from the edge of excited polymer thin-films as we reported previously. In this present work, we report that the increased absorption cross-section of Eu(III) complexes at 355 nm is directly linked to the enhancement of ASE properties by using a Nd:YAG laser.

2. Experimental

2.1. Apparatus

¹H NMR and ¹⁹F NMR data were obtained with a JEOL EX-270 spectrometer. ¹⁹F NMR chemical shifts were determined using hexafluorobenzene as an external standard ($\delta = -162.0$ (s, Ar-F) ppm). Elemental analyses were performed using a Perkin-Elmer 240 C.

2.2. Materials

Europium acetate tetrahydrate (99.9%), 1,1,1,5,5,5-hexafluoro-2,4-pentanedione (hfa-H₂), 4,4,4-trifluoro-butane-1,3-dione, 4,4,4-trifluoro-1-(phenyl)butane-1,3-dione, 4,4,4-trifluoro-1-(1-naphthyl)butane-1,3-dione, and triphenylphosphine oxide (TPPO) were purchased from Wako Pure Chemical Industries Ltd. and ACT-Chem Ltd. Methanol-*d*₄ and acetone-*d*₆ were obtained from Aldrich Chemical Co. Inc. PPSQ was obtained by MITSUBISHI Electric Corporation. Tris(hexafluoroacetylacetonato)europium(III)bis(triphenylphosphine oxide): **2** was prepared by the reaction of tris(hexafluoroacetylacetonato)europium(III)dihydrate and triphenylphosphine oxide in methanol following a procedure described in the previous literature [6]. The Eu(III) complexes **1**, **3** and **4** were also prepared by the same method as for **2**. Those compounds were identified by ¹H NMR, ¹⁹F NMR and elemental analyses. All other chemicals were of reagent grade and were used as received.

Deuterated Eu(III) complexes were obtained by the exchange reaction via keto-enol tautomerism **1–4** CD₃OD for 6 h under vacuum. Obtained Eu(III) complexes were then added to anisole solution containing PPSQ. An Eu(III) thin-film was prepared on a glass substrate from the anisole solution via spin-coating method. The film thickness was found to be 2.0 nm, using a surface profiler (Veeco Instruments Inc., DEK-TAK3).

2.3. Optical measurements

Emission spectra were measured at room temperature using a Spex Fluorolog- τ 3 (Jobin Yvon) system. The samples were excited at 465 nm (⁷F₀ → ⁵D₂). The emission lifetimes were determined by using a Q-switched Nd:YAG laser (Spectra Physics INDI-50, FWHM = 5 ns, $I = 1064$ nm) and a photomultiplier (Hamamatsu Photonics R7400U-03, response time ≤ 0.78 ns). Samples were excited by the third harmonic (355 nm) of the fundamental nanosecond pulse. Emission from the sample was guided to the photomultiplier through a monochromator (Jobin Yvon, Triax320). Emission decays were monitored with a digital oscilloscope (Sony Tektronix, TDS3052, 500 MHz) synchronized to single-pulse excitation. The emission quantum yields were determined by standard procedures with an integrating sphere (diameter 6 cm) mounted on a spectrofluorometer (HITACHI F-4500) [12].

2.4. ASE measurements

Eu(III) thin-film was excited by the third harmonic (355 nm) of a nanosecond Nd:YAG laser (B.M. industries 502DNS, 10 Hz, FWHM 9 ns, beam spot 5 mm). The optical waveguide on the film was excited using a combination of a cylindrical lens ($f = 200$ mm) and a concave lens ($f = 100$ mm). Emission from the edge of the thin-film was filtered by a low-cut optical filter (Toshiba Glass L-39, $I > 365$ nm) and a monochromator (Jobin Yvon H-20 Vis) placed in front of the detector (Photomultiplier: Hamamatsu Photonics R928). The response of the photomultiplier was monitored using a digital oscilloscope (SONY Tektronics TDS540) synchronized to the excitation pulse. The emission decays containing two components (normal spontaneous emission lifetimes; and faster emission lifetimes) were analyzed by a least-square fitting of the double exponential function. The emission intensity is given by

$$I = a \exp(-bt) + c \exp(-dt) \quad (1)$$

where a and c are branching ratio functions. The faster components and normal components of the emission lifetimes were $-1/b$ and $-1/d$, respectively. The percentages of the ASE components were determined by

$$\text{ASE (\%)} = \frac{a}{a+c} \times 100 \quad (2)$$

The emission spectra from the edge were measured by a photonic multichannel analyzer system (Ocean Optics USB2000) under different excitation energy. The energy of the beam spot (excitation energies of the samples) was measured by a thermo-power meter.

3. Results and discussion

3.1. Absorption and emission properties of Eu(III) complexes

The absorption spectra of the Eu(III) complexes **1–4** in methanol are shown in Fig. 2. The broad absorption band in the Eu(III) complexes were assigned to π - π^* transitions of the β -diketonato ligands. The wavelengths of absorption maxima ($\lambda_{\text{abs, max}}$) were shifted from 298 to 337 nm. The red shift of the absorption maxima of Eu(III) complexes was owing to the expansion of delocalized π -conjugation systems of the ligands. The molecular absorption coefficients and absorption cross-sections at 355 nm (optically pumping wavelength) of the Eu(III) complexes are summarized in Table 1. The absorption cross-sections at 355 nm of complexes **1** and **2** were found to be 2.0 and 6.0×10^{-19} cm², respectively. In contrast, those of complexes **3** and **4** were much larger than those of complexes **1** and **2** (330 and 850×10^{-19} cm²).

The emission spectra of the deuterated Eu(III) complexes in acetone-*d*₆ are shown in Fig. 3. We observed five emission peaks, 580, 590, 615, 650, and 700 nm, which were attributed to the f - f transitions ⁵D₀–⁷F_{*j*} ($j = 0–4$, respectively). The strongest emission at 615 nm (⁵D₀–⁷F₂) is due to the electronic dipole transition. The

Fig. 2. UV-vis absorption spectra of the Eu(III) complexes (triangle: complex **1**; cross: complex **2**; square: complex **3**; circle: complex **4**).

Table 1

Absorption properties and photophysical properties of Eu(III) complexes. Wavelength of the absorption maxima ($\lambda_{\text{abs. max}}$) and absorption cross-sections^a (σ_{abs}) at 355 nm of the Eu(III) complexes in acetone. Emission lifetimes^b (τ_{obs}), emission quantum yields^c (Φ_{In}), radiative rates^d (k_r), and stimulated emission cross-sections^e (σ_{ρ}) in acetone- d_6 .

Complex	$\lambda_{\text{abs. max}}$ (nm)	σ_{abs} ($\times 10^{-19}$ cm ²) (355 nm)	τ_{obs} (ms)	Φ_{In}	k_r ($\times 10^2$ s ⁻¹)	σ_{ρ} ($\times 10^{-20}$ cm ²)
1	298	2.0	0.72	0.70	9.7	1.41
2	303	6.0	0.93	0.90	9.7	1.42
3	320	330	0.77	0.72	9.4	1.37
4	337	850	0.75	0.80	10.7	1.56

^a Absorption cross-sections were determined using $\sigma_{\text{abs}} = \epsilon / (2.6 \times 10^{20})$.

^b Emission lifetimes of the Eu(III) complexes were measured by the excitation at 355 nm (Nd:YAG 3 ω).

^c Emission quantum yields of the Eu(III) complexes were measured using standard procedures with an integrating sphere (diameter 6 cm) by the excitation at 465 nm (⁷F₀–⁵D₂) in acetone- d_6 . Concentrations of the Eu(III) complexes were 0.05 M.

^d Radiative rates were determined using $k_r = 1/\tau_R = \Phi_{\text{In}}/\tau_{\text{obs}}$.

^e Stimulated emission cross-sections were determined according to the reported method.

emission peaks of ⁵D₀–⁷F₂ transitions of the Eu(III) complexes were split into five Stark levels (610, 612, 616, 618 and 620 nm). The shapes of emission spectra of Eu(III) complexes **1**, **3** and **4** were similar to that of previously reported Eu(III) complex **2**. The spectral shapes of Eu(III) complexes are dependent on symmetry of the geometrical structures in Eu(III) complexes [13,14]. These results suggest that geometrical structures of Eu(III) complexes **1**, **3** and **4** are similar to that of Eu(III) complex **2**. The emission lifetimes (τ_{obs}), emission quantum yields (Φ_{In}), radiative rates (k_r) and stimulated emission cross-section (σ_{ρ}) of the Eu(III) complexes in acetone- d_6 are also summarized in Table 1. The complexes **1**–**4** showed long emission lifetimes and high emission quantum yields.

Those high emission quantum yields were achieved by the prevention of radiationless transition via vibrational excitation. The prevention of radiationless transition is due to three deuterated hexafluoroacetylacetonato ligands which have only low-vibrational C–F or C–D bonds [6]. On the other hand, radiative rates and stimulated emission cross-sections of the Eu(III) complex **2** were similar to those of corresponding Eu(III) complexes **1**, **3** and **4**. Generally, the radiative rates (transition probabilities) of the f–f transitions depend on the geometrical structures of Eu(III) complexes [15]. We conclude that the geometrical structures of Eu(III) complexes **1**, **3** and **4** are similar to that of Eu(III) complex **2** in acetone- d_6 .

Fig. 3. Emission spectra of (a) Eu(III) complexes **1**; (b) complex **2**; (c) complex **3**; and (d) complex **4**.

Fig. 4. The relation between the excitation energy and percentages of the ASE components of the Eu(III) complexes (triangle: complex 1; cross: complex 2; square: complex 3; circle: complex 4). The percentages of the ASE components were determined by lifetime analysis.

3.2. ASE properties of Eu(III) complexes

The emission lifetimes were measured at the weakest excitation power (0.01 mJ) consisting of single components, (1: 0.59 ms, 2: 0.65 ms, 3: 0.61 ms, and 4: 0.60 ms), which agreed well with the spontaneous emission lifetimes of Eu(III) complexes in PPSQ films. The emission decays under the stronger excitation energy (>1 mJ) consisted of normal components (lifetimes of the spontaneous emission) and fast components (1: 0.075 ms, 2: 0.088 ms, 3: 0.080 ms, and 4: 0.078 ms). These observations suggest that the faster components are attributable to the ASE from the Eu(III) complexes in the polymer thin-films micro-cavity [5]. The ASE components in the whole emission were determined by a least-squares fitting of the double exponential function. The percentages of the ASE component of the Eu(III) complexes as a function of excitation energy are shown in Fig. 4. They increased along with the increase of excitation energy, and the threshold energies of 1 and 2 were found to be 0.1 mJ. In contrast, the threshold energy of the 3 and 4 was 0.05 mJ and less than 0.05 mJ, respectively. We also found that the amplification of the ASE components of the Eu(III) complexes were increased in proportion to the absorption cross-sections at 355 nm. In particular, the amplitude percentage of the

ASE component of complex 4 was estimated to be over 60% under 10 mJ excitation. This large amplification of the ASE of 4 should be ascribed to the large absorption cross-section value of 4. The large absorption cross-section of complex 4 would promote the formation of population inversion leading to effective stimulated emission under optical pumping.

4. Conclusion

We have demonstrated that the ASE properties of Eu(III) complexes excited by the third harmonic of Nd:YAG laser depend on not only the emission cross-sections, but also the absorption cross-sections at 355 nm. The optimum manipulation of the photo-physical properties of luminescent Eu(III) complexes by molecular design is an essential factor in creating superlative optical materials. Eu(III) complex 4 would be desirable for developing application in novel polymer materials such as plastic optical fibers [4]. Conceptual molecular design of Eu(III) complexes and fabrication of luminescent polymer are expected to open up pioneering fields in opto-material science.

References

- [1] F. Gan, *Laser Materials*, World Scientific, Singapore, 1995.
- [2] G. Blasse, B.C. Grabmaier, *Luminescent Materials*, Springer, New York, 1994.
- [3] A. Lempicki, H. Samelson, *Phys. Lett.* 4 (1963) 133.
- [4] T. Kobayashi, S. Nakatsuka, T. Iwafuji, K. Kuriki, N. Imai, T. Nakamoto, C.D. Claude, K. Sasaki, Y. Koike, Y. Okamoto, *Appl. Phys. Lett.* 71 (1997) 2421–2423.
- [5] Y. Hasegawa, Y. Wada, S. Yanagida, H. Kawai, N. Yasuda, T. Nagamura, *Appl. Phys. Lett.* 83 (2003) 3599.
- [6] Y. Hasegawa, M. Yamamuro, Y. Wada, N. Kanehisa, Y. Kai, S. Yanagida, *J. Phys. Chem. A* 107 (2003) 1697.
- [7] H. Taniguchi, H. Tomisawa, J. Kido, *Appl. Phys. Lett.* 66 (1995) 1578.
- [8] M. Sargent III, M.O. Scully, E. Willis, J. Lamb, *Laser Physics*, Addison-Wesley, Advanced Book Program, 1974.
- [9] N. Nakamura, Y. Hasegawa, Y. Wada, S. Yanagida, *Chem. Phys. Lett.* 398 (2004) 500.
- [10] K. Nakamura, Y. Hasegawa, H. Kawai, N. Yasuda, N. Kanehisa, Y. Kai, T. Nagamura, S. Yanagida, Y. Wada, *J. Phys. Chem. A* 111 (2007) 3029.
- [11] N. Yasuda, S. Yamamoto, Y. Hasegawa, H. Nobutoki, Y. Wada, S. Yanagida, *Chem. Lett.* (2002) 244.
- [12] Y. Hasegawa, T. Ohkubo, K. Sogabe, Y. Kawamura, Y. Wada, N. Nakashima, S. Yanagida, *Angew. Chem. Int. Ed.* 39 (2000) 357.
- [13] J.H. Forsberg, *Coord. Chem. Rev.* 10 (1973) 195.
- [14] G. Vicentini, L.B. Zinner, J. Zukerman-Schpector, K. Zinner, *Coord. Chem. Rev.* 196 (2000) 353.
- [15] G.F. de Sa, O.L. Malta, C.D. Donega, A.M. Simas, R.L. Longo, P.A. Santa-Cruz, E.F. da Silva, *Coord. Chem. Rev.* 196 (2000) 165.

The energy transfer from Eu^{2+} to Tb^{3+} in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ and its application in green light emitting diode

Jing Wang^{a,b,*}, Zhiyang Zhang^a, Mei Zhang^a, Qihong Zhang^a, Qiang Su^a, Jinke Tang^b

^a Ministry of Education Laboratory of Bioinorganic and Synthetic Chemistry, State Key Laboratory of Optoelectronic Materials and Technologies, School of Chemistry and Chemical Engineering, Sun Yat-sen University, Guangzhou, Guangdong 510275, PR China

^b Department of Physics & Astronomy, University of Wyoming, Laramie, WY 82071, USA

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 24 July 2008

Accepted 1 September 2008

Available online 1 November 2008

Keywords:

Europium

Terbium

Phosphate

Energy transfer

Light emitting diode

ABSTRACT

A novel green phosphor, $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$, is synthesized by high temperature solid-state reaction. The photoluminescence properties show that there is an efficient energy transfer from Eu^{2+} to Tb^{3+} where Eu^{2+} ions exhibit a strong excitation band between 350 and 420 nm, matching well with the dominant emission band of (n)-UV (390–420 nm) LED, and Tb^{3+} ions give an intense green emitting light. A green LED with CIE chromaticity coordinates ($x=0.283, y=0.383$) were fabricated by coating the $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$ phosphor onto (n)-UV chip emitting at 398 nm. These results demonstrate that Tb^{3+} ion with low 4f–4f absorption efficiency in (n)-UV region can play a role of activator in narrow green emitting phosphor potentially useful in (n)-UV GaN-based LED through efficient energy feeding by allowed 4f–5d absorption of Eu^{2+} with high oscillator strength.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

It is well known that the invention of white light emitting diodes (LEDs) has brought another revolution to the illumination technology of this century to supersede conventional incandescent or fluorescent lamps because of its excellent properties such as high brightness, reliability, lower power consumption and long life [1,2]. At the present, there are several ways to make the white LEDs [3,4]. One significant scheme is phosphor-converted white LED (pc-wLED) that is further classified into two approaches: blue (440–470 nm) and near (n)-UV (390–410 nm) InGaN chip combined with phosphors. For the blue InGaN chip, the commonly used phosphor is yellow YAG:Ce³⁺. However, such white LEDs encounter low color-rendering index ($R_a < 80$) due to the scarcity of red emission. Besides, the white LED based on blue InGaN chip encounter low color reproducibility on mass manufacturing scale. The n-UV LED is considered more stable and efficient with higher output [5]. It generally emits at wavelength shorter than 400 nm. Therefore the n-UV

LED has little effect on the chromaticity coordinate of pc-wLED, which is generally determined by the visible radiation distribution of phosphor between 380 and 730 nm [6]. In addition, any desirable color LED emitting red, green, blue, etc., can be controlled by choosing different phosphor. The phosphor converted color LED shows some advantages for example, the widely tunable color range from blue to red region, the stable color quality under different operating conditions, especially under different forward-bias currents and during the industrial mass production [7]. Thus, the n-UV pc-LEDs are expected to have great application potential in the field of solid-state lighting.

Nowadays, rare earth ions, especially Ce³⁺ and Eu²⁺ involved with inter-configurational 4f–5d transition, have been widely investigated in many compounds including orthosilicates, akermanites, aluminates, sulfides and oxynitrides/nitrides, etc. [8–12]. However, little is done on trivalent rare earth ions involving with intra-configurational 4f–4f transitions. Recently, Eu³⁺-doped phosphors have been studied for near UV InGaN-based LEDs. For example, oxysulfide ($\text{Y}_2\text{O}_2\text{S}:\text{Eu}^{3+}$) [13], molybdates ($\text{Na}_5\text{La}(\text{MoO}_4)_4:\text{Eu}^{3+}$, $\text{Na}_5\text{Eu}(\text{MoO}_4)_4$ and $\text{NaEu}(\text{MoO}_4)_2$) [14] and europium organic complex ($\text{Eu}(\text{TPBDTFA})_2(\text{TPATFA})\text{Phen}$) [15] were developed and the red LEDs were successfully fabricated.

In this paper, our aim is to investigate whether Tb^{3+} ions with low 4f–4f absorption efficiency in (n)-UV region can play a role of activator in a narrow green emitting phosphor potentially useful in (n)-UV GaN-based LEDs. The phenomena of energy transfer

* Corresponding author at: Ministry of Education Laboratory of Bioinorganic and Synthetic Chemistry, State Key Laboratory of Optoelectronic Materials and Technologies, School of Chemistry and Chemical Engineering, Sun Yat-sen University, Guangzhou, Guangdong 510275, PR China. Tel.: +86 20 84111038; fax: +86 20 84111038.

E-mail address: ceswj@mail.sysu.edu.cn (J. Wang).

Fig. 1. PL and PLE spectra of $\text{Ca}_{8.4}\text{K}(\text{PO}_4)_7:0.8\text{Tb}^{3+},0.8\text{K}^+$ (A), $\text{Ca}_{9.9}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+}$ (B) and $\text{Ca}_{8.3}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},0.2\text{Tb}^{3+},0.2\text{K}^+$ (C).

in phosphors were extensively observed [16–18], especially, those from Ce^{3+} to Tb^{3+} . However, energy transfer from Eu^{2+} to Tb^{3+} is rarely seen except in $\text{KLn}_3\text{F}_{10}$ ($\text{Ln}=\text{Y}, \text{Lu}$) [19]. In this paper, the energy transfer from Eu^{2+} to Tb^{3+} in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ was systematically investigated and a green emitting $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$ phosphor was developed for the first time. The phosphor-converted green LED was also successfully fabricated by combining ultraviolet GaInN chip and $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$.

2. Experimental

2.1. Syntheses

Eu^{2+} or Tb^{3+} singly doped and $\text{Eu}^{2+}-\text{Tb}^{3+}$ co-activated $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ phosphors were prepared by conventional solid-state reaction technique. The starting materials were CaCO_3 (A.R.), CaHPO_4 (A.R.), anhydrous CaCl_2 (A.R.), Eu_2O_3 (99.99%), Tb_4O_7 (99.99%) and K_2CO_3 (A.R.). When the trivalent Tb^{3+} ions are doped in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$, additional K_2CO_3 serves as a charge compensation reagent. Stoichiometric amounts of the raw materials were thoroughly mixed in an agate mortar by grinding and then sintered at 873 K for 3 h, followed by regrinding. Finally, they were fired at 1573 K in a reducing atmosphere (10% H_2 /90% N_2) for 4 h.

2.2. Characterizations

The phase purity of the as-prepared phosphors was investigated by X-ray powder diffraction spectroscopy (XRD) with a Rigaku D/max 2200 vpc X-ray diffractometer with $\text{Cu K}\alpha$ radiation at 40 kV and 30 mA. The XRD patterns were collected in the range $10^\circ \leq 2\theta \leq 80^\circ$. The XRD patterns of Eu^{2+} or Tb^{3+} singly doped and $\text{Eu}^{2+}-\text{Tb}^{3+}$ co-activated $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ phosphors confirm of a single phase of $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ (JCPDS 45-0138).

The decay curves were recorded by a FLS920-Combined Fluorescence Lifetime and Steady State Spectrometer (Edinburgh Instruments). The room temperature photoluminescence (PL), photoluminescence excitation (PLE) spectra were measured by a Fluorolog-3 spectrofluorometer (Jobin Yvon Inc/specx) equipped with a 450 W Xe lamp and double excitation monochromators.

2.3. Characterization of green LED

The green LEDs were fabricated by combining InGaN-based ultraviolet LEDs (Cree Inc., C395-MB290, 12 mW, $\lambda_{\text{em}} = 395$ nm) and as-synthesized phosphors. Their optical properties were evaluated by a LED-1100 Spectral/Goniometric Analyzer (Labsphere Inc.) under a direct current of 20 mA at room temperature.

3. Results and discussion

Fig. 1 shows PL and PLE spectra of singly doped Eu^{2+} or Tb^{3+} and $\text{Eu}^{2+}-\text{Tb}^{3+}$ co-activated $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ phosphors. For

$\text{Ca}_{8.4}\text{K}(\text{PO}_4)_7:0.8\text{Tb}^{3+},0.8\text{K}^+$, the emission spectrum monitoring at 379 nm shows a characteristic optical transitions of Tb^{3+} ion, which are situated at about 486, 542, 587, 619 nm, due to $\text{D}_4 \rightarrow {}^7\text{F}_J$ ($J=6, 5, 4, 3$). The weak emissions ${}^5\text{D}_3 \rightarrow {}^7\text{F}_J$ ($J=5, 6$) of Tb^{3+} at 416 and 432 nm, respectively, are also observed in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ with 8 mol% of Tb^{3+} ions, which may be due to the lower ν_{max} of phonon in this host. Monitoring at 542 nm, The PLE spectrum consists of many sharp peaks in the wavelength range from 280 to 380 nm, due to the forbidden 4f–4f transitions of Tb^{3+} ions. For $\text{Ca}_{9.9}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+}$, the PL spectra consist of two emission bands at 410 and 470 nm, both attributed to $5\text{d} \rightarrow 4\text{f}$ transitions of Eu^{2+} . The emission spectra of Eu^{2+} shows the distinct features when monitored at different excitation wavelength: the dominating emission is at about 410 nm when monitored at 275 nm while that at around 474 nm when monitored at 365 nm. The PLE spectra of Eu^{2+} , monitored at different emission at 410 and 474 nm, also present the distinguishable behavior. Therefore, it can be concluded Eu^{2+} ions occupy at least two different cation sites in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$, denoted as Eu_1 (410 nm) and Eu_2 (474 nm). It is reasonable because there are four different crystallographically independent Ca^{2+} sites with different coordination numbers (CN = 6, 8 and 9) [20].

Nowadays, the commercial n-UV LEDs show a ultraviolet light at around 390–410 nm. As shown in Fig. 1A, it can be seen that Tb^{3+} shows no absorption beyond 380 nm, meaning that Tb^{3+} singly doped phosphate is not suitable for the application of n-UV LED. Contrarily, the PLE spectra of Eu^{2+} ion (Fig. 1B) matches well with the emission of n-UV LEDs, suggesting that Eu^{2+} singly doped phosphate has potential application in the field of n-UV LEDs. However, the comparison of the PL spectrum of $\text{Ca}_{9.9}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+}$ and PLE spectrum of $\text{Ca}_{8.4}\text{K}(\text{PO}_4)_7:0.8\text{Tb}^{3+},0.8\text{K}^+$ reveals spectral overlap between the emission band of Eu^{2+} at longer wavelength (at about 474 nm) and the absorption transition of Tb^{3+} (${}^7\text{F}_6 \rightarrow {}^5\text{D}_4$ located at 486 nm). Therefore, the effective resonance energy transfer from Eu^{2+} to Tb^{3+} in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ is expected. Fig. 1C shows the PL and PLE spectra of $\text{Eu}^{2+}-\text{Tb}^{3+}$ co-activated $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$ phosphors. Monitoring at 400 nm excitation, both the broad emission band of Eu^{2+} and the sharp emission peaks of Tb^{3+} (${}^5\text{D}_4 \rightarrow {}^7\text{F}_J$ ($J=6, 5, 4, 3$)) are observed. The shapes of PLE spectra of $\text{Ca}_{8.3}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},0.2\text{Tb}^{3+},0.2\text{K}^+$, monitored at 474 and

Fig. 2. The emission spectra ($\lambda_{\text{ex}} = 400$ nm) of $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$ ($y=0, 0.05, 0.1, 0.2, 0.4, 0.6, 0.8, 1.0$); inset is the dependence of the peak intensity of Tb^{3+} (${}^5\text{D}_4 \rightarrow {}^7\text{F}_5$ located at 544 nm) and the maximum intensity of the emission band of Eu^{2+} (located 474 nm) on Tb^{3+} concentration (y) in $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$.

Fig. 3. The concentration effects of Tb^{3+} ions on the lifetime of Eu^{2+} ion in $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$ ($y=0, 0.1, 0.2, 0.4, 0.6, 0.8$) ($\lambda_{\text{ex}}=365\text{ nm}$, $\lambda_{\text{em}}=474\text{ nm}$).

544 nm (curve 2 and curve 3 in Fig. 1C), are almost the same as that of $\text{Ca}_{9.9}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+}$ (curve 4 in Fig. 1B), indicating that the energy transfer from Eu^{2+} at Eu_2 site to Tb^{3+} appears. It is therefore expected that Tb^{3+} ions can serve as activator of green-emitting phosphor by energy feeding of Eu^{2+} ions that can be directly excited by 400 nm emission of UV LED.

In order to optimize the green-emitting performance of the as-synthesized phosphors so that they can be potentially applied in n-UV LED with dominating emission at around 400 nm, a series of $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$ ($0 \leq y \leq 1.0$) phosphors were prepared and their luminescent properties were systematically investigated. The emission spectra ($\lambda_{\text{ex}}=400\text{ nm}$) of $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$ are shown in Fig. 2. It can be seen that the characteristic sharp emission of Tb^{3+} ($^5\text{D}_4 \rightarrow ^7\text{F}_j$ ($j=6,$

Fig. 4. The schematic diagram of energy transfer in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$.

5, 4, 3)) becomes stronger and stronger when the concentration of Tb^{3+} ions increases and the broad emission band of Eu^{2+} ions located around 474 nm decreases gradually. As shown in the inset of Fig. 2, the optimal concentration of Tb^{3+} ions is about 8 mol%, and excess Tb^{3+} ions will lead to its concentration quenching.

Fig. 3 shows the concentration effects of Tb^{3+} ions on the lifetime of Eu^{2+} in $\text{Ca}_{9.9-2y}\text{K}(\text{PO}_4)_7:0.1\text{Eu}^{2+},y\text{Tb}^{3+},y\text{K}^+$ ($y=0, 0.1, 0.2, 0.4, 0.6$). It can be seen that the decay curves of Eu^{2+} ion are well fitted with a second order exponential equation: $I(t)=I_0+A\exp(-t/\tau_1)+B\exp(-t/\tau_2)$ where I and I_0 are the luminescence intensity initially and at t , A and B are constants, and τ_1 and τ_2 are lifetimes). It is obvious that with the increasing amount of Tb^{3+} ions, the lifetime of Eu^{2+} ions gradually decreases. In the absence of Tb^{3+} , the lifetimes of Eu^{2+} ion are 0.16 and 1.12 μs . When the amount of codopant Tb^{3+} is up to 0.8 mol%, the lifetimes of Eu^{2+} ion are 0.06 and 0.76 μs . Such behavior indicates that the excitation energy of these Eu^{2+} ions is transferred to Tb^{3+} ions.

Fig. 4 shows schematic diagram of energy transfer in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$. As shown in Fig. 1, the broad-band emission of Eu^{2+} at 474 nm (Eu_2 site) covers with the excitation peak of Tb^{3+} at 486 nm. The overlap indicates that there is likely to be

Fig. 5. The PL spectra of $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ phosphor (A), the electroluminescence spectra of naked UV LED (B) and the fabricated green pc-LED (C) by combining with $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ phosphor and UV LED under 20 mA forward-bias current, and the 1931 CIE chromaticity diagram (D) of the as-fabricated green pc-LED under $I_f=20\text{ mA}$.

the radiative or non-radiative resonant energy transfer. However, it seems impossible for the resonant radiative transfer because the absorption transition of ${}^7F_6 \rightarrow {}^5D_4$ located at 486 nm has very weak oscillator strength. In addition, it is reasonable that the lifetime of the donor will remain constant in the presence of the acceptor if the resonant radiative transfer is involved [21]. In present case, the lifetime of Eu^{2+} ion as donor decreases with the increasing amount of Tb^{3+} ion as acceptor. It is therefore concluded that the energy transfer mechanism is likely to be ascribed to resonant non-radiative transfer from the lowest excited level of Eu^{2+} to the excited 5D_4 level of Tb^{3+} as shown in Fig. 4.

The emission spectrum of green emitting LED that was fabricated by combining $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ phosphor with the 398-nm InGaN chip under 20 mA forward-bias current (I_F), is shown in Fig. 5. The characteristic emission peaks of Tb^{3+} (486, 542, 587, 619 nm) can be clearly observed in the emission spectrum of the green pc-LED, which is consistent with the PL spectra of $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ phosphor. From the comparison of the emission intensity of near-UV-LED chip at 395 nm as shown in Fig. 5B and C, it is seen that its intensity decreases from 3700 (Fig. 5B) to 2300 mW/sr/nm (Fig. 5C), indicating that $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ phosphor has efficient absorption to the 395-nm InGaN chip. The remaining UV light can be used to excited blue and red phosphor for the white LEDs that combine with n-UV chip and RGB phosphors. As illustrated in Fig. 5D, the color coordinate of as-fabricated pc-LED is ($x=0.283, y=0.383$) under $I_F=20$ mA, which is located in green area and very close to the white light ellipse. The properties of the as-fabricated green LED also demonstrate that the pc-LEDs are alternatives to the semiconductor green LEDs for applications in lighting, signal and indicator, etc.

4. Conclusions

A novel green-emitting phosphate $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$ was reported for the first time. There are at least two luminescent centers, Eu_1 at 410 nm and Eu_2 at 474 nm and the efficient energy transfer from Eu^{2+} (Eu_2 site) to Tb^{3+} exists in $\text{Ca}_{10}\text{K}(\text{PO}_4)_7$. The $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+},\text{K}^+$ phosphor exhibit the efficient broad absorption band of Eu^{2+} and an intense green emission of Tb^{3+} . The green LED with the color coordinate of ($x=0.2835, y=0.3855$) was successfully fabricated based on $\text{Ca}_{10}\text{K}(\text{PO}_4)_7:\text{Eu}^{2+},\text{Tb}^{3+}$ and n-UV

chip. It demonstrates that Tb^{3+} ion with low 4f–4f absorption efficiency in (n)-UV region can play the role of activator in narrow green emitting phosphor potentially useful in (n)-UV GaN-based LED through efficient energy feeding by allowed 4f–5d absorption of Eu^{2+} with high oscillator strength.

Acknowledgments

We acknowledge the financial supports from the National Nature Science Foundation of China (20501023), the Nature Science Foundation of Guangdong Province (5300527) and the Science and Technology Project of Guangzhou (2005Z2-D0061).

References

- [1] S. Nakamura, M. Senoh, T. Mukai, Appl. Phys. Lett. 62 (1993) 2390.
- [2] Y. Uchina, T. Taguchi, Opt. Eng. 44 (2005) 124003.
- [3] J.K. Sheu, S.J. Chang, C.H. Ku, Y.K. Su, L.W. Wu, Y.C. Lin, W.C. Lai, J.M. Tsai, G.C. Chi, R.K. Wu, IEEE Photonics Technol. Lett. 15 (2003) 18.
- [4] J.K. Park, C.H. Kim, S.H. Park, H.D. Park, Appl. Phys. Lett. 84 (2004) 1647.
- [5] E. Radkov, R. Bompiedi, A.M. Srivastava, A.A. Setlur, C. Becker, Proc. SPIE 5187 (2004) 171.
- [6] M. Zhang, J. Wang, W.J. Ding, Q.H. Zhang, Q. Su, Appl. Phys. B 86 (2007) 647.
- [7] M. Zhang, J. Wang, Q.H. Zhang, W.J. Ding, Q. Su, Mater. Res. Bull. 42 (2007) 33.
- [8] Y.Q. Li, G. de With, H.T. Hintzen, J. Mater. Chem. 15 (2005) 4492.
- [9] W.J. Ding, J. Wang, M. Zhang, Q.H. Zhang, Q. Su, Chem. Phys. Lett. 435 (2007) 301.
- [10] W.J. Ding, J. Wang, Z.M. Liu, M. Zhang, Q. Su, J.K. Tang, J. Electrochem. Soc. 155 (2008) J122.
- [11] R.J. Yu, J. Wang, M. Zhang, J.H. Zhang, H.B. Yuan, Q. Su, Chem. Phys. Lett. 453 (2008) 197.
- [12] K. Uheda, N. Hirotsaki, Y. Yamamoto, A. Naito, T. Nakajima, H. Yamamoto, Electrochem. Solid-State Lett. 9 (2006) H22.
- [13] S.X. Yan, J.H. Zhang, X. Zhang, S.Z. Lu, X.R. Ren, Z.G. Nie, X.J. Wang, J. Phys. Chem. C 111 (2007) 13256.
- [14] Z.L. Wang, H.B. Liang, J. Wang, M.L. Gong, Q. Su, Appl. Phys. Lett. 89 (2006) 071921.
- [15] N.J. Xiang, L.M. Leung, S.K. So, J. Wang, Q. Su, M.L. Gong, Mater. Lett. 60 (2006) 2909.
- [16] G. Blasse, Chem. Mater. 1 (1989) 294.
- [17] J.S. Kim, K.T. Lim, Y.S. Jeong, P.E. Jeon, J.C. Choi, H.L. Park, Solid State Commun. 135 (2005) 21.
- [18] A. Nag, T.R.N. Kutty, Mater. Chem. Phys. 91 (2005) 524.
- [19] D. Trottier, J.C. Cousseins, J.P. Denis, B. Blanzat, J. Solid State Chem. 62 (1985) 386.
- [20] M.H. Sandstrom, D. Bostrom, Acta Crystallogr. Sect. E: Struct. Rep. Online 62 (2006) I253.
- [21] G.K. Liu, B. Jacquier, Spectroscopic Properties of Rare Earths in Optical Materials, Springer, Beijing, 2005.

$f \leftrightarrow f$ electric dipole transitions; old problems in a new light

Lidia Smentek*, A. Kędziorowski

Department of Physics, Nicolaus Copernicus University, ul. Grudziadzka 5, 87-100 Toruń, Poland

ARTICLE INFO

Article history:

Received 4 June 2008

Received in revised form 9 July 2008

Accepted 5 November 2008

Available online 18 November 2008

In memory of Brian G. Wybourne
(1935–2003).

Keywords:

Spectroscopy of lanthanides

Judd–Ofelt theory

Forbidden transitions

Parametrization of f -spectra

ABSTRACT

Very well known difficulties of the theoretical description of the $f \leftrightarrow f$ electric dipole transitions of lanthanides are addressed in the old language of the standard Judd–Ofelt (J–O) theory, which has been widely applied for more than 45 years. New light is shed on a competitive physical mechanism of these transitions, which is presented to complement the existing J–O model. Possible new solutions are given for the old problems of the negative intensity parameters obtained from the adjusting procedure. An alternative scheme for the reproduction of the hypersensitive transitions is discussed and a theoretical description of highly forbidden transitions 0–0 and 0–1 observed for Eu^{3+} and Sm^{2+} ions is presented.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

The problems of the reproduction of the hypersensitive $f \leftrightarrow f$ transitions and of the theoretical description of highly forbidden transitions 0–0 and 0–1 observed for Eu^{3+} and Sm^{2+} ions are strong motivation for the search for a reliable parametrization of f -spectra. At the same time, these particular transitions are the best examples of the important application of the spectroscopy of the lanthanide ions doped in various materials as diagnostic and therapeutic tools.

DOTA, EDTA, EDTMP, CDTMP, DTPA, DOTP are the organic chelates that, when coordinated with the Gd ion, are contrast agents used in clinical medicine to enhance NMR signals enabling the diagnosis of pathological changes in various organs of human body. When these systems are chelated with the other members of the lanthanide family, they act as markers of cancerous changes in different tissues. The signals monitoring the presence of a tumor originate from the sensitized luminescence of the lanthanide ion imbedded into the chelate built like a cage. The architecture of the cage is correlated with the kind of the targeted tissue. Although it is possible to verify, using the radiative isotopes of the lanthanides, where a certain system is absorbed the most, still the mechanisms of the energy transfer and of subsequent luminescence are not well understood. Not much is also known about the geometry of various cages. Only recently, due to

the results of the DFT calculations, several aspects of the structure of various conformers of the chelates are becoming clearer. This knowledge is crucial for designing new systems that would be characterized by more efficient energy transfer and stronger luminescence enhanced by attaching to the main cage of the chelate the so-called antenna, which harvests the energy from the external beam. Special attention is also directed to the synthesis of such chelates that absorb visible light and emit infra-red radiation, the optimal one due to its penetration depth through biological samples.

The best benchmark for the theoretical investigations devoted to the structural properties of the potential probes are the highly forbidden by the standard selection rules $f \leftrightarrow f$ electric dipole transitions 0 $\leftrightarrow$ 0 and 0 $\leftrightarrow$ 1 of Eu^{3+} . Indeed, in the case of several chelates coordinated with the Eu ion there were two lines observed in the emission spectrum assigned to the $^5D_0 \rightarrow ^7F_0$ transition! This was obvious evidence that at least two conformers of a given cage exist in equilibrium. This expectation based on the spectroscopic properties of a system was only recently confirmed by the numerical analysis of the optimal geometries of DOTA [1], EDTMP [2], CDTMP [3] and DOTP [4].

Thus, not only for the sake of the pure knowledge about the possible theoretical description of the transitions forbidden by the standard Judd–Ofelt selection rules, but also because of their important applications, the old problems of the theory of f -spectra are presented here in a new light shed by the results of the recent investigations.

* Corresponding author. Tel.: +48 56 6113268.

E-mail address: lidia.smentek@vanderbilt.edu (L. Smentek).

2. Standard Judd–Ofelt theory

The standard Judd–Ofelt theory [5,6] of $f \leftrightarrow f$ electric dipole transitions is based on the Rayleigh–Schrödinger perturbation theory applied for the following Hamiltonian,

$$H = H_0 + \lambda(PV_{CF}Q + QV_{CF}P) \quad (1)$$

where H_0 describes the system within the single configuration approximation and free ionic system approximation. Thus, P is spanned by the eigenfunctions Ψ_i^0 of H_0 of the ground electron configuration $4f^N$ of the lanthanide ion. Its orthogonal complement $Q = 1 - P$ is built of the projection operators originating from the singly excited configurations $4f^{N-1}n'\ell'$ (all the operators regarded here are single particle objects, and therefore the doubly excited configurations do not contribute). In this approach the electric dipole transitions are regarded as forced by the perturbing influence of the inter-shell interactions via the crystal field potential V_{CF} defined as

$$V_{CF} = \sum_{tp} B_p^t \sum_i r_i^t C_p^{(t)}(\vartheta_i \varphi_i) \quad (2)$$

with structural parameters (crystal field parameters) B_p^t .

The transition amplitude is defined by the matrix element of the radiation operator $D_\rho^{(1)}$ of the form

$$D_\rho^{(1)} = \sum_i r_i C_\rho^{(1)}(\vartheta_i \varphi_i) \quad (3)$$

Due to the parity considerations the electric dipole transition amplitude vanishes when evaluated with the eigenfunctions of H_0 (all states are of the same parity). The first non-vanishing contributions to the transition amplitude are of the second order, and they are determined by the matrix elements of $D^{(1)}$ with the functions expanded up to the first order corrections

$$\Phi_i = \Psi_i^0 + \lambda \Psi_i^1 \quad (4)$$

where

$$\Psi_i^{(1)} = \sum_k \frac{\langle \Psi_k^0 | QV_{CF}P | \Psi_i^0 \rangle}{E_i^0 - E_k^0} \Psi_k^0 \quad (5)$$

From the whole expansion of the crystal field potential in Eq. (2), only the interactions via its odd part are effective in forcing the electric dipole transitions (parity considerations). Following Judd and Ofelt it is assumed that the energy levels of distinct configurations might be regarded as degenerate in relation to the large energy distance between the ground configuration $4f^N$ and all the excited ones. Therefore it is possible to perform the partial closure and derive the transition amplitude in its effective operator form

$$\Gamma_{J-O}^\rho = 2(-1)^\rho \sum_t \sum_p \text{odd} B_p^t \sum_\lambda \sum_{\ell'} \text{even even} (-1)^p [\lambda]^{1/2} \begin{pmatrix} 1 & t & \lambda \\ \rho & p & -(\rho+p) \end{pmatrix} A_t^\lambda(\ell') R_{JO}^t(\ell') \langle 4f^N \Psi_f^0 | U_{\rho+p}^{(\lambda)} | 4f^N \Psi_i^0 \rangle \quad (6)$$

where the angular term is defined as

$$A_t^\lambda(\ell') = [\lambda]^{1/2} \left\{ \begin{matrix} t & \lambda & 1 \\ f & \ell' & f \end{matrix} \right\} < f \| C^{(1)} \| \ell' \rangle \langle \ell' \| C^{(t)} \| f \rangle \quad (7)$$

and, as a factor, it has the same value for all the lanthanide ions.

The radial integrals of the original Judd–Ofelt theory have the form

$$R_{JO}^t(\ell') = \sum_{n'} \frac{\langle 4f | r | n' \ell' \rangle \langle n' \ell' | r^t | 4f \rangle}{(\epsilon_{4f} - \epsilon_{n' \ell'})}$$

and when expressed in the terms of the perturbed functions [7], they are represented by a single integral, namely

$$R_{JO}^t(\ell') = \langle Q^t(4f \rightarrow \ell') | r | 4f \rangle \quad (8)$$

where $|4f\rangle \equiv P_{4f}$. The perturbed functions $Q^t(4f \rightarrow \ell') \equiv Q^t(r; 4f \rightarrow \ell')$ contain all the first-order corrections caused by the single excitations from the $4f$ shell to one-electron state of $n'\ell'$ symmetry taken into account via the crystal field potential. Indeed, each $Q^t(4f \rightarrow \ell')$ is a linear combination of the terms

$$Q^t(4f \rightarrow \ell') = \sum_{n'} \frac{\langle 4f | r^t | n' \ell' \rangle}{(\epsilon_{4f} - \epsilon_{n' \ell'})} P_{n' \ell'}(r)$$

Note that due to the perturbed function approach the sum of the original Judd–Ofelt radial integrals over the complete radial basis sets of one electron excited functions of ℓ' symmetry is replaced by a single integral with new functions that contain this very troublesome summation inside their definition (see Ref. [7]).

The expression for the transition amplitude derived by Judd and Ofelt is the basic one in the theory of f -spectra. In order to evaluate its applicability and usefulness, to discuss its weak and strong points, some questions are answered below.

- Is it possible to perform *ab initio* calculations using the expression in Eq. (6)?

- * There is no problem with the evaluation of the angular parts of the effective operators defined in Eq. (6);

- * All the problems with the evaluation of the radial integrals are solved by using the perturbed function approach, and their values for all lanthanide ions, evaluated for the complete radial basis sets of one electron functions are published in Ref. [8];

- * Unfortunately still it is impossible to perform direct calculations using the effective operators in Eq. (6) because the odd rank crystal field parameters B_p^t are not known, and there is no reliable source of their values available.

- Would the results of such calculations be reliable, if the odd rank crystal field parameters were known?

- * As mentioned, the standard Judd–Ofelt theory is based on the single configuration approximation and therefore the impact of electron correlation is completely ignored. In order to improve this theoretical model the approach has to be based on the double perturbation theory applied for the Hamiltonian

$$H = H_0 + \lambda(PV_{CF}Q + QV_{CF}P) + \mu(PV_{corr}Q + QV_{corr}P) \quad (9)$$

where the second perturbation is the non-central part of the Coulomb interaction and represents correlation effects. As a consequence instead of Eq. (6) the effective operators defined up to the third order have to be included. The numerical analysis of the relative importance of various contributions to the transition amplitude has demonstrated that electron correlation contributions, although of the third order, very often and usually for the heavier ions across the lanthanide series are dominant in comparison to the values of the Judd–Ofelt terms of the second order [9].

3. Semiempirical approach

The problems with the direct evaluation of the amplitude of $f \leftrightarrow f$ transitions are the reason that the semi-empirical realization of the Judd–Ofelt theory is the most known and commonly used in practice. In this model the transitions are reproduced within the

one particle parametrization

$$S_{f \leftarrow i}^{J-O} = \sum_{\lambda=2,4,6} \Omega_{\lambda} |\langle \Psi_f || U^{(\lambda)} || \Psi_i \rangle|^2 \quad (10)$$

This means that the intensity of all the transitions in a given system are determined by at most three intensity parameters modulated by the square of the reduced matrix elements of the unit tensor operators between the states involved in the process.

In fact it should be pointed out that there is not much in common with the original Judd–Ofelt theory and the parametrization scheme defined in Eq. (10). Indeed, the expression in Eq. (10) means only that the parametrization of the f -spectra is one particle (the Judd–Ofelt effective operators are one particle), that there are three parameters common for all transitions in a given system (without the physical meaning or interpretation), and finally that the parametrization is non-relativistic (as unit tensor operators of the original formulation of the Judd–Ofelt theory). There is neither a physical model nor a physical mechanisms involved in the expression (10), nor any evidence of the approximations of the physical model discussed in the previous section in connection with the original Judd–Ofelt theory. Even there is no any evidence in Eq. (10) that the crystal field potential is the forcing mechanism of the electric dipole $f \leftrightarrow f$ transitions. Just the opposite, the intensity parameters, traditionally called the Judd–Ofelt parameters, represent the perturbing influence of ALL physical mechanisms, which are theoretically described by one particle tensor operators acting within the orbital space. In addition, there is no *a priori* requirement that the intensity parameters HAVE to be positive! Ω_{λ} is not a square of the coefficient of the tensor operator U in Eq. (6). Each Ω_{λ} does not represent the second order terms derived from the perturbation approach; Ω_{λ} 's are freely varying parameters without physical interpretation. There is only one case in which the value of Ω_2 is expected to be positive and that is when it determines by itself the intensity of a hypersensitive transition. However, very often in such cases the fitting procedure based on the scheme in (10) gives reasonable reproduction only when the hypersensitive transition is excluded from the adjusted set. The latter problem is solved by the extended parametrization scheme presented below.

4. Electric dipole hyperfine interactions

- Does any other forcing mechanism of $f \leftrightarrow f$ transitions, except the crystal field potential, exist?

When the perturbing operator V_{cryst} in Eq. (1) is replaced by the multipole hyperfine interactions V_{EM} , the wave functions of H_0 are modified by the corrections of parity opposite to the parity of the $4f^N$ [10]. This parity condition is satisfied only for the odd part of V_{EM} . As a result, there are non-zero second-order contributions that are of a new origin, and which compete at the second order with the standard Judd–Ofelt terms. Thus, the interactions via V_{EM} represent new mechanism, which forces the electric dipole $f \leftrightarrow f$ transitions.

The distortion from the spherical symmetry of a nucleus with the spin $I > 0$ is described by the electrostatic interactions between the electron and nucleon charge densities, which, in the terms of the multipole expansion, have the following tensorial form,

$$V_{EM} = \sum_k \frac{r_n^k}{r_e^{k+1}} (\mathbf{C}_e^{(k)} \cdot \mathbf{C}_n^{(k)}) \quad (11)$$

When the energy is evaluated within the single configuration approximation, k in the expansion above is even, and the remaining contributions for k odd vanish. If the inter-shell electric multipole hyperfine interactions are analyzed, there are non-zero contributions to the transition amplitude for k odd in Eq. (11).

It is straightforward to find within the framework of the basic assumptions and approximations of the standard Judd–Ofelt theory that these new second-order one-particle effective operators have the following form,

$${}^2\Gamma_{EM}^{\rho} = 2(-1)^{\rho} \sum_{\text{odd } k} \sum_{\text{even } q} M_q^k \sum_{\ell'} \sum_{\lambda} [\lambda]^{1/2} \begin{pmatrix} 1 & k & \lambda \\ \rho & q & -(\rho+q) \end{pmatrix} A_k^{\lambda}(\ell') R_{JO}^{k-1}(\ell') (4f^N \Psi_f^0 | U_{\rho+q}^{(\lambda)} | 4f^N \Psi_i^0) \quad (12)$$

where the angular factors are defined by Eq. (7), the radial integral is presented in Eq. (8) and M_q^k is the matrix element of the nuclear multipole moment.

The tensorial structure of these effective operators is almost the same as those of the standard Judd–Ofelt effective operators from Eq. (7). Note that λ in Eq. (12) is also even, and the selection rules for the non-vanishing contributions are the same; only the odd rank crystal field parameters B_p^t of Eq. (7) are replaced in Eq. (12) by M_q^1 , and the physical origin in both cases is different. At the same time, since the transition amplitude is not determined any more by the odd rank crystal field parameters, it is possible to perform direct calculations.

The second order Judd–Ofelt effective operators represent the electrostatic interactions caused by the distortion of the spherical symmetry of a free ion by its environment represented by the crystal field potential. The new second order terms originate from the electrostatic interactions that are the consequence of the distortion of a spherical symmetry of a nucleus caused by its closest environment created by the surrounding electrons.

- Is the parametrization scheme of the f -spectra changed when the hyperfine interactions are taken into account?

The tensorial structure of the hyperfine originated terms contributing to the transition amplitude indicates that all these contributions are also included within the standard parametrization scheme of Judd and Ofelt

$$S_{f \leftarrow i} = \sum_{\lambda=2,4,6} \Omega_{\lambda}' |\langle \Psi_f || U^{(\lambda)} || \Psi_i \rangle|^2$$

where the intensity parameters are only formally distinguished from those in expression (10). Indeed, when the values of Ω_{λ} 's are evaluated from the fitting procedure, as mentioned above, they as freely adjusted parameters represent ALL physical mechanisms taken into account at all orders of the perturbation expansion.

Thus, the intensity parameters represent the interplay between two forcing mechanism of the $f \leftrightarrow f$ electric dipole transitions: the crystal field potential and electric dipole hyperfine interaction. In the particular case of $\lambda = 2$, the term which determines the intensity of the hypersensitive transition Ω_2 contains the contributions from Eq. (6) for $t = 1$, and from Eq. (12) for $k = 1$. However, there are also such examples for which the hypersensitive transitions are observed in spite of the fact that there are no terms for $t = 1$ in the expansion of the crystal field potential. Since the hyperfine mechanism is independent of the crystallographic symmetry of the system, it is concluded that for such systems the electric dipole hyperfine interactions are the sole mechanism which is responsible for the hypersensitivity of some electric dipole transitions.

5. Relativistic parametrization of f -spectra

- Is it possible to reproduce ALL electric dipole $f \leftrightarrow f$ transitions using the one particle non-relativistic parametrization scheme of Eq. (10)?

When $\Psi_f \equiv {}^7F_0$ in Eq. (10), only the transitions to the levels assigned by $J = 2, 4, 6$ are allowed by the selection rules of the standard Judd–Ofelt parametrization scheme. This means that in the particular case of *Eu* ion, all the transitions $J = 0 \leftrightarrow J' = 0, 1, 3, \dots$, odd are forbidden, although they are observed and indeed very important, as mentioned in the Introduction. There is also a problem with the reproduction of the hypersensitive transitions using the scheme in Eq. (10). In fact, very often the fitting procedure performed for the set of the allowed transitions which includes the hypersensitive ones (for example ${}^5D_0 \rightarrow {}^7F_2$ for *Eu* ion) gives rather poor reproduction of the measurements. In all these cases the Judd–Ofelt parametrization scheme is not adequate.

It is a common belief that in order to improve the quality of the reproduction of the spectra it is enough to enlarge the number of the intensity parameters. The results of the numerical analysis [11,12], supported by earlier work of Auzel [13], demonstrated however that this is not the case when the semi-empirical procedure is applied for *f*-electron spectra. The extension of the scheme in Eq. (10) by the odd-rank intensity parameters, while alleviating the selection rules for the transitions from $J = 0$ to the levels with $J = \text{odd}$, still does not lead to better reproduction. This means that not only the number of the adjusted parameters is crucial but the physical model from which the parametrization scheme originates.

The Judd–Ofelt parametrization scheme is non-relativistic as demonstrated by the fact that the unit tensor operators U in the matrix elements modulating the intensity parameters act only within the orbital space. In this way, even if the fitting procedure is applied, from all possible physical mechanisms contributing to the transition amplitude those of a relativistic nature are excluded. Indeed, the intensity parameters Ω_λ do not contain the impact of spin–orbit and hyperfine magnetic interactions, for example [14–17]. The relativistic formulation of the intensity theory of the $f \leftrightarrow f$ transitions [18,19] led to the conclusion that the original operators $U^{(\lambda)}$ in the parametrization scheme should be replaced by the double tensor operators that act within the spin–orbital space. This is why, instead of Eq. (10), a new extended and physically enriched scheme has been proposed [11,12]

$$S_{f \leftarrow i}^{\text{rel}} = \sum_{\lambda} \sum_{\kappa k} \Omega_{\lambda}^{\kappa k} |\langle \Psi_f | W^{(\kappa k) \lambda} | \Psi_i \rangle|^2. \quad (13)$$

The number of the parameters is simultaneously enlarged, and therefore the fitting procedure now requires richer experimental data. In fact the number of parameters is limited by the condition that the sum of the ranks $\kappa + k + \lambda$ has to be *even* to preserve the hermiticity of the effective operators determining the intensity.

- Is the new parametrization scheme applicable for ALL $f \leftrightarrow f$ transitions?

The relativistic parametrization scheme allows one to perform the fitting procedure for *all* $f \leftrightarrow f$ transitions, including those forbidden by the non-relativistic approach. Even the transition $0 \leftrightarrow 0$ observed in *Eu*, which is not tractable theoretically by all the previous parameterizations, is very well reproduced by the expression in Eq. (13). Indeed, when $J_f = J_i = 0$ the only consequence is that $\lambda = 0$, which means that $\kappa = k$, and the parameter $\Omega_0^{(11)}$ determines the intensity of this transition. In addition, the fitting procedure performed in accordance with the relativistic scheme gives much better reproduction of other transitions, including those allowed by the Judd–Ofelt selection rules, the hypersensitive ones, and also transitions determined by the effective operators with rank $\lambda = \text{odd}$.

Fig. 1. Relative errors of reproduction of the intensity of $f \leftrightarrow f$ transitions observed in the Eu^{3+} ion in an acetate crystal [11,20].

6. Summary

The summary of this discussion is illustrated in Fig. 1, where the quality of the results of numerical calculations are presented for various transitions observed in the Eu^{3+} ion in an acetate crystal [20]. In the figure not the actual values of the intensities of the appropriate transitions are presented, but rather the errors of reproduction defined as follows,

$$\eta = \frac{|P_{\text{exp}} - P_{\text{calc}}|}{P_{\text{exp}}} \times 100\%$$

where P_{calc} denotes the value of the intensity of a particular transition evaluated within the Judd–Ofelt scheme ($S_{f \leftarrow i}^{\text{JO}}$, Eq. (10)), within non-relativistic scheme which is the Judd–Ofelt approach extended by the odd rank intensity parameters, $S_{f \leftarrow i}^{\text{n-rel}}$, and finally within the relativistic scheme ($S_{f \leftarrow i}^{\text{rel}}$, Eq. (13)).

The arrows below the horizontal axis point out the perfect reproduction of the measured intensity ($\eta = 0$). The white bars represent the quality of the standard Judd–Ofelt scheme, the gray color describes the values of η obtained for the non-relativistic scheme in which the odd rank intensity parameters are included, and finally, the black bars show the accuracy of the reproduction when the relativistic scheme is applied. The other bars in the Fig. 1. denote the transitions which are forbidden by the Judd–Ofelt and non-relativistic schemes (error of reproduction of 100%). One of these forbidden transitions, ${}^7F_0 \rightarrow {}^5D_3$, becomes allowed by the selection rules of the non-relativistic scheme, while ${}^7F_0 \rightarrow {}^5D_0$ is still forbidden; it becomes allowed only within the relativistic scheme.

The results of the fitting procedure of the standard Judd–Ofelt scheme are improved when the extended model is applied, however still there is a rather large discrepancy between the calculated and measured intensities. In the case of all transitions included in the semi-empirical procedure there is visible improvement of the quality of the reproduction based on the relativistic scheme. Note that for the first time the intensity of the unusual and highly forbidden transition ${}^7F_0 \rightarrow {}^5D_0$ is reproduced via the fitting procedure, and this is achieved by applying the relativistic scheme of parametrization. In fact this is the only parametrization scheme in which all transitions of a given system are described by the very same semi-empirical approach.

In addition, it should be pointed out that the parameter $\Omega_0^{(11)}$, which is responsible for the $0 \rightarrow 0$ transition, represents the impact due to the $J - J$ mixing and the spin–orbit interaction (indeed, the spin–orbit interaction is represented by the unit double ten-

sor operator $w^{(11)0}$). These are the contributions, which have been evaluated by Downer and Burdick [15,16], Tanaka and Kushida [21] in their direct calculations of the intensity of ${}^7F_0 \rightarrow {}^5D_0$ transition enhanced by the intensity of the transition ${}^7F_0 \rightarrow {}^5D_2$ by means of the “borrowing of intensity” mechanism suggested by Wybourne in 1967 ([8], page 213 and references there); all these contributions are disregarded by the Judd–Ofelt and also non-relativistic parametrization schemes as a result of the limitation of the unit tensor operators U , which act only within the orbital space. This means that extension of the effective operators to the spin-orbital space gives a unique possibility to account for all the interactions, which have been included previously in *ab initio*-type calculations mentioned above. These pioneering calculations and their results are a strong motivation for extension of the parametrization scheme of *f*-spectra by all those interactions, which are represented by double tensor operators.

Although Fig. 1 shows remarkable improvement of the results of the fitting procedure based on the relativistic scheme applied for the particular example of the Eu^{3+} in an acetate crystal, more general conclusions about the effectiveness and accuracy of the relativistic scheme require further numerical analysis. At this point of the discussion the main achievement of this preliminary investigations is the fact that all the transitions, those allowed and also

forbidden by the standard scheme, are reproduced by the same semi-empirical approach.

References

- [1] L. Smentek, B.A. Hess, J.P. Cross, H.C. Manning, D.J. Bornhop Jr., J. Chem. Phys. 123 (24) (2005), 244302 (9).
- [2] L. Smentek, B.A. Hess, Jr., Collect. Czech. Chem. Commun. 73 (2008) 1437.
- [3] B.A. Hess, Jr., Smentek, L., J. Alloys Compd., in preparation.
- [4] L. Smentek, B.A. Hess, Jr., A. Kędziorowski, in preparation.
- [5] B.R. Judd, Phys. Rev. 127 (3) (1962) 750.
- [6] G.S. Ofelt, J. Chem. Phys. 37 (3) (1962) 511.
- [7] K. Jankowski, L. Smentek-Mielczarek, A. Sokołowski, Mol. Phys. 59 (6) (1986) 1165.
- [8] B.G. Wybourne, L. Smentek, Optical Spectroscopy of Lanthanides; Magnetic and Hyperfine Interactions, CRC/Taylor & Francis, 2007.
- [9] L. Smentek, Phys. Rep. 297 (4) (1998) 155.
- [10] L. Smentek, A. Kędziorowski, Spectr. Lett. 40 (2007) 293.
- [11] A. Kędziorowski, L. Smentek, J. Lumin. 127 (2007) 552.
- [12] A. Kędziorowski, L. Smentek, J. Alloys Compd. 451 (2008) 686.
- [13] F. Auzel, J. Alloys Compd. 380 (2004) 9.
- [14] B.R. Judd, D.R. Pooler, J. Phys. C 15 (3) (1982) 591.
- [15] M.C. Downer, G.W. Burdick, D.K. Sardar, J. Chem. Phys. 89 (4) (1988) 1787.
- [16] G.W. Burdick, M.C. Downer, D.K. Sardar, J. Chem. Phys. 91 (3) (1989) 1511.
- [17] L. Smentek, B.A. Hess Jr., Mol. Phys. 88 (3) (1996) 783.
- [18] L. Smentek, B.G. Wybourne, J. Phys. B 33 (18) (2000) 3647.
- [19] L. Smentek, B.G. Wybourne, J. Phys. B 34 (4) (2001) 625.
- [20] K. Bukietyńska, A. Mondry, J. Alloys Compd. 323–324 (2001) 150.
- [21] M. Tanaka, T. Kushida, Phys. Rev. B53 (1996) 588.

Crystal-field parameters from ab initio calculations

Michael F. Reid^{a,b,*}, Chang-Kui Duan^{b,c}, Hongwei Zhou^d

^a Department of Physics and Astronomy and MacDiarmid Institute for Advanced Materials and Nanotechnology University of Canterbury, Christchurch, New Zealand

^b Department of Biology and Chemistry, City University of Hong Kong, Tat Chee Avenue, Kowloon, Hong Kong SAR, China

^c Institute of Modern Physics, Chongqing University of Post and Telecommunications, Chongqing 400065, China

^d Department of Physics, Sichuan College of Education, Chengdu 610041, China

ARTICLE INFO

Article history:

Received 9 September 2008

Received in revised form 1 December 2008

Accepted 8 December 2008

Available online 24 December 2008

PACS:

71.70ch

71.15. – m

31.15. A –

71.23.An

Keywords:

Crystal-field, Ab initio, Lanthanide,
Rare-earth

ABSTRACT

We give a method for extracting an effective Hamiltonian from ab initio calculations that requires only the calculated energies for the model space and the part of the calculated eigenvectors that correspond to the model space. This method simplifies the extraction of phenomenological parameters that can be compared with experiment. We demonstrate the method with an ab initio calculation for d states, which is relevant to examining the $4f^{N-1}5d$ configurations of lanthanide and actinide ions.

© 2009 Published by Elsevier B.V.

1. Introduction

The spectra of rare-earth ions in crystals are commonly analysed using *crystal-field* models. In these models an *effective Hamiltonian* is constructed within a *model space* for an isolate rare-earth ion (in a crystal). The model space most commonly consists of the $4f^N$ configuration but other configurations, such as $4f^{N-1}5d$, may also be considered. Parameters representing the various terms in the Hamiltonian, the Coulomb interaction between the electrons, spin–orbit interaction, crystal–field interaction, etc., are determined by fitting to observed energy levels, with ab initio calculations sometimes guiding the starting point [1].

Accurate ab initio calculations for the $4f^N$ and $4f^{N-1}5d$ configurations of rare-earth ion impurities in crystals are now becoming available [2,3]. There are several reasons why it would be useful to extract the commonly used effective Hamiltonian parameters from such calculations. The parameters give valuable insight into the interactions in these systems. For some purposes minor changes in the parameters would give better agreement with experiment, which could be crucial for calculating other properties of interest such as radiative or non-radiative transition rates. For many systems

it will be more practical to use ab initio calculations to determine crystal-field parameters for simple ions such as Ce^{3+} , and use those as input for effective Hamiltonian calculations in more complex systems.

In cases of high site symmetry, such as octahedral, only one crystal-field parameter is required to parameterize the crystal-field splitting of the 5d configuration of Ce^{3+} and in that case it is a simple matter to determine the parameter ($10Dq$ or B_0^4 depending on the convention used) from the calculated energies. However, for most site symmetries the number of crystal-field parameters is greater than or equal to the number of 5d energy levels, so fitting the parameters to the ab initio energy levels, as was done in Ref. [4], is not practical.

A better alternative is to construct a full effective Hamiltonian from the ab initio calculation, and then solve for the parameters. We show that the effective Hamiltonian that we require can be constructed from an ab initio calculation as long as we know the energies and the eigenvector components of the states within our model space in the ab initio wave-functions. An important point is that the full wave-function is not needed, only the components corresponding to the model space. We demonstrate the method with a simple example of a d-electron calculation.

2. Effective Hamiltonians

In this section we show how to construct an effective Hamiltonian using the eigenvalues and eigenvectors obtained from ab initio

* Corresponding author at: Department of Physics and Astronomy and MacDiarmid Institute for Advanced Materials and Nanotechnology University of Canterbury, Christchurch, New Zealand. Tel.: +64 3 364 2548; fax: +64 3 364 2469.
E-mail address: mike.reid@canterbury.ac.nz (M.F. Reid).

calculations. The theory of effective Hamiltonians has been extensively discussed by Hurtubise and Freed [5] and we have made use of some of these concepts in earlier papers [6,7].

The eigenstates of a quantum mechanical system may be written as

$$H\psi_i = E_i\psi_i \quad (i = 1, 2, \dots, \infty), \quad (1)$$

where E_i and ψ_i are the eigenvalues and eigenvectors, respectively. Usually, we are interested in a limited number of eigenvalues and their corresponding eigenvectors. This smaller space, of dimension M , is called the *model space*. Within this space we can construct an *effective Hamiltonian* H_{eff} which has eigenstates in the model space ϕ_i that yield energies identical to those for full Hamiltonian:

$$H_{\text{eff}}\phi_i = E_i\phi_i \quad (i = 1, 2, \dots, M). \quad (2)$$

It is important to note that the ϕ_i are not the same as the ψ_i , which may contain large admixtures of other functions. Furthermore, the choice of the ϕ_i is not unique. For example, we may use a model space consisting of $4f^N$ and $4f^{N-1}5d$ configurations of a trivalent lanthanide ion, but the “true” states contain mixtures of other orbitals on the ion and its ligands’.

The eigenstates ψ_i and ϕ_i may be expanded by a set of bases. We denote the complete set of bases as $|j\rangle$ ($j = 1, 2, \dots, \infty$). For convenience we may arrange our bases in such a way that, the first M bases are chosen to be the bases of the model space and the first M states are chosen to be those states whose major component bases may be written as

$$\psi_i = \sum_{j=1}^{\infty} |j\rangle V_{ji} \quad (3)$$

and its projection into the model space as

$$(\psi_P)_i = \sum_{j=1}^M |j\rangle V_{ji}. \quad (4)$$

Here $V = \{V_{ji}\}$ ($j, i = 1, 2, \dots, \infty$) is the matrix formed by all eigenvectors and $V_P = \{V_{ji}\}$ ($j, i = 1, 2, \dots, M$) the projection of the first M states into the model space. Note that the $(\psi_P)_i$ are generally not normalized or orthogonal and so are usually not the best choice for the model-space wave-functions, ϕ_i . It is not guaranteed that V_P is non-singular but for any practical systems we assume V_P is non-singular so that its inverse V_P^{-1} exists.

The set of original eigen-equations (Eq. (1)) can be written in matrix form as

$$HV = VE. \quad (5)$$

Here $E = \text{diag}(E_1, E_2, \dots, E_{\infty})$ is a matrix where the diagonal elements are the eigenvalues and all other elements are zero. We also define $E_P = \text{diag}(E_1, E_2, \dots, E_M)$ for later use.

A straightforward definition of a (non-Hermitian) effective Hamiltonian $H_{\text{eff}}^{\text{NH}}$ is

$$H_{\text{eff}}^{\text{NH}} = V_P E_P V_P^{-1}. \quad (6)$$

The eigen-equation

$$H_{\text{eff}}^{\text{NH}} V_P = V_P E_P \quad (7)$$

gives exactly the same eigenvalues as Eq. (5) for the first M states and the model-space eigenvectors are the columns of V_P . However, those eigenvectors are neither normalized nor orthogonal, and the effective Hamiltonian $H_{\text{eff}}^{\text{NH}}$ is not Hermitian, so this is not a suitable choice for comparison with a crystal-field Hamiltonian, which is explicitly constructed to be Hermitian.

Instead of using H_{eff} , a Hermitian effective Hamiltonian H_{eff} may be constructed (e.g. Ref. [5] Eq. 2.11). Here we show that the construction requires only the energies and the part of the eigenvectors

that fall within the model space (V_P). We begin by constructing the orthonormal eigenvectors V_K :

$$V_K = ((V_P V_P^\dagger)^{-1})^{1/2} V_P. \quad (8)$$

It is noted that since V_P^{-1} is assumed to be non-singular, $(V_P V_P^\dagger)^{-1}$ exists and is positive-defined hermitian matrix, which is diagonalizable, and hence the square root of $(V_P V_P^\dagger)^{-1}$ is then well-defined (though there are, of course, arbitrary phases involved in solving for eigenvectors). Standard numerical methods may be used to calculate $(V_P V_P^\dagger)^{-1/2}$ directly.

The Hermitian effective Hamiltonian is therefore:

$$H_{\text{eff}} = V_K E_P V_K^{-1}. \quad (9)$$

We now have the effective eigenvalue equation (see Eq. (2)):

$$H_{\text{eff}} V_K = V_K E_P, \quad (10)$$

with a Hermitian effective Hamiltonian H_{eff} and orthonormal eigenstates:

$$V_K^\dagger V_K = 1_P. \quad (11)$$

Hence, with the M eigenvalues E_P and the components of their eigenvectors in the designated model space, V_P , we can use Eqs. (8) and (9) to construct a Hermitian effective Hamiltonian H_{eff} , whose eigenvectors are given by V_K . Extraction of the complete eigenstates is not required, which drastically simplifies the process.

Other properties of the system, such as dipole moments, may also be calculated using equations analogous to Eq. (9).

3. Solving for the effective Hamiltonian parameters

The “crystal-field” approach is to write a parameterized model-space Hamiltonian in terms of N_p parameters and operators:

$$H_{\text{eff}} = \sum_{\alpha=1}^{N_p} P_{\alpha} \mathbf{T}_{\alpha}. \quad (12)$$

Here the P_{α} are the parameters. The $\mathbf{T}_{\alpha}$ are the matrices of operators which represent the various interactions, such as the Coulomb interaction between the electrons, spin-orbit interaction, crystal-field interaction and so on.

If the operators span the model space we can expand the effective Hamiltonian exactly using elementary linear algebra. This is particularly simple if the operators are orthogonal, but if not, as long as they are linearly independent it is possible to construct a set of N_p equations

$$H_{\beta} = \text{tr}(\mathbf{T}_{\beta}^\dagger H_{\text{eff}}) \quad (13)$$

$$= \sum_{\alpha=1}^{N_p} A_{\beta\alpha} P_{\alpha}, \quad (14)$$

where

$$A_{\beta\alpha} = \text{tr}(\mathbf{T}_{\beta}^\dagger \mathbf{T}_{\alpha}). \quad (15)$$

Since A is non-singular when the set of N_p operators $\mathbf{T}_{\alpha}$ are linearly independent, we can solve for the parameters

$$P_{\alpha} = \sum_{\beta=1}^{N_p} (A^{-1})_{\alpha\beta} H_{\beta} = \sum_{\beta=1}^{N_p} (A^{-1})_{\alpha\beta} \text{tr}(\mathbf{T}_{\beta}^\dagger H_{\text{eff}}). \quad (16)$$

In most cases the crystal-field Hamiltonian will include only the operators representing the most important interactions in the expansion Eq. (12). If those operators do not form a complete set we

can still use Eq. (16) to calculate the strength parameters. However, there will be a residue since the expansion Eq. (12) will not give an exact fit.

4. Example

The methods described in the previous section could be applied to ab initio calculations for a range of physical systems. For simplicity we shall focus on an example relevant to systems with dilute transition metal or lanthanide ions, where the model space is composed of d or f orbitals on a particular ion. However, it would also be possible to apply the methods to concentrated systems, where magnetic anisotropy is of great concern. However, in such systems the transformation to the model space would be rather complex, since the calculation involves states that are not localized.

As an example we present the results from a density-functional calculation of the 3d orbital energies and wave-functions in VF_4^+ molecule. It is noted that this molecule itself is not of particular interest but is a simple example to demonstrate the method. This system is similar to the $5d^1$ problem for dilute Ce^{3+} ions in crystals. The calculations were done with the program Gaussian 2003 [8] and made use of density functionals. For illustrative purposes we have chosen a calculation with empty 3d orbitals merely to avoid the complication of dealing with partially occupied orbitals.

Since we want to illustrate our method for low symmetries we did not restrict the geometry to be tetrahedral. In the final optimized calculation there is a threefold symmetry axis approximately along the X-axis. However, the final geometry is close to tetrahedral, which is clear from the approximate two- and threefold degeneracies of the energies of the 3d states.

Energies for the 3d states are given in Table 1. The spin-orbit interaction was not included so there are five states of interest. The coefficients associated with the first two sets of Gaussian functions of d nature in the eigenvectors are also given. The eigenvector coefficients for these two sets differ by a factor of approximately 2, but the ratio depends on the energies of the states. In a crystal-field calculation the radial function are usually considered to be constant, but this restriction does not apply to the ab initio calculation. Consequently, we will obtain a slightly different effective Hamiltonian from the coefficients of each of the two sets of eigenvector components. However, in either case the calculated energies will be exactly reproduced.

Table 1

Calculated 3d energies and wave-functions for VF_4^+ from Gaussian 03 [8]. Energies are given in cm^{-1} relative to the configuration average. Note that there are 6 Gaussian orbitals rather than the 5 linearly independent orbitals expected for the 3d configuration. It is straightforward to transform each column of the wave-functions into a fivefold bases in terms of the spherical harmonic functions Y_m^2 . “d set 1” and “d set 2” contain the largest eigenvector coefficients of the five 3d states.

Energies	−3999	−3992	2650	2661	2680
d set 1					
5XX	−0.01697	0.03591	0.70002	−0.02945	−0.02230
5YY	−0.30254	−0.19785	−0.35082	−0.31824	0.37644
5ZZ	0.31950	0.16195	−0.34936	0.34768	−0.35414
5XY	0.43534	0.38356	−0.01154	−0.28186	0.28972
5XZ	−0.36104	0.45825	−0.05186	−0.24985	−0.30787
5YZ	−0.23534	0.32092	0.00906	0.45033	0.36917
d set 2					
6XX	−0.00813	0.01724	0.30897	−0.01291	−0.00979
6YY	−0.14544	−0.09515	−0.15443	−0.14010	0.16573
6ZZ	0.15368	0.07784	−0.15379	0.15307	−0.15591
6XY	0.20919	0.18432	−0.00509	−0.12382	0.12731
6XZ	−0.17349	0.22020	−0.02286	−0.10976	−0.13526
6YZ	−0.11317	0.15434	0.00402	0.19826	0.16254

Table 2

Crystal-field parameters for 3d states of VF_4^+ . Units are cm^{-1} .

Parameter	d set 1	d set 2
B_0^2	409	464
B_1^2	69	72
B_2^2	−514	−541
B_0^4	5748	5792
B_1^4	2615	2605
B_2^4	−6738	−6717
B_3^4	844	842
B_4^4	8321	8380

Since spin is ignored the effective crystal-field Hamiltonian may be written as

$$H_{\text{eff}} = \sum_{k=2,4} \sum_{q=-k}^k B_q^k C_q^{(k)}, \quad (17)$$

where the $C_q^{(k)}$ are spherical tensors [9]. The angular functions in Table 1 may be easily transformed into spherical tensors and we can use the eigenvector coefficients from either set of Gaussian functions to do the calculation.

In Table 2 we give crystal field parameters derived from the energies and eigenfunction of Table 1. Each column of Table 2 uses the eigenvector components from the corresponding section of Table 1.

The calculation was set up to restrict the geometry to C_{3v} and there is a threefold axis approximately along X. However, the expected twofold degeneracies are not exact due to rounding errors. The functions (or parameters) may be rotated to make the Z-axis the unique axis, so that to a good approximation we only have the three parameters B_0^2 , B_0^4 , and B_3^4 , that we would expect for C_{3v} symmetry. Note that even these three parameters could not be determined from the energies (since there are only two energy differences) let alone the parameter set given in Table 2.

More sophisticated calculations, such as those in Ref. [3], optimize separately for each energy level. The method described here could still be used in those cases. There is no requirement for the original eigenvectors V to be orthonormal, so eigenvector components from different calculations may be combined to derive an effective Hamiltonian.

5. Conclusions

In this paper we have derived and demonstrated a simple method for extracting effective Hamiltonian parameters such as “crystal-field” parameters from ab initio calculations. Only the ab initio energies and eigenvector components corresponding to the states of interest are required. Details of the eigenvector components outside of the model space are not required. This method should be applicable to the analysis of a variety of ab initio calculations.

Acknowledgements

M.F.R. acknowledges support from City University of Hong Kong in the form of a Visiting Fellowship.

C.-K.D. acknowledges support of this work by the City University of Hong Kong Research Grant 9360123.

C.-K.D. and H.W.Z. acknowledge the National Science Foundation of China Grant No. 10874173 for financial support.

References

- [1] G.K. Liu, B. Jacquier, in: *Spectroscopic Properties of Rare Earths in Optical Materials*, Springer, 2005.
- [2] K. Ogasawara, S. Watanabe, H. Toyoshima, M.G. Brik, *Handbook on the Physics and Chemistry of Rare Earths*, vol. 37, Elsevier, 2007, Chapter 231.
- [3] F. Ruiperez, A. Barandiaran, L. Seijo, *J. Chem. Phys.* 123 (2005) 244703.
- [4] C.K. Duan, M.F. Reid, S. Xia, *J. Lumin.* 122 (2007) 939.
- [5] V. Hurtubise, K.F. Freed, *Adv. Chem. Phys.* 83 (1993) 465.
- [6] A.R. Bryson, M.F. Reid, *J. Alloys Compd.* 275–277 (1998) 284.
- [7] M.J. Lee, M.F. Reid, M.D. Faucher, G.W. Burdick, *J. Alloys Compd.* 323–324 (2001) 636.
- [8] M.J. Frisch, *Gaussian 03, Revision B.03*, Gaussian, Inc., Pittsburgh PA, 2003.
- [9] B.G. Wybourne, *Spectroscopic Properties of Rare Earths*, Wiley, 1965.

Langmuir–Blodgett films incorporating an ionic europium complex

R.D. Adati, S.A.M. Lima¹, M.R. Davolos*, M. Jafelici Jr.

Unesp - São Paulo State University, Unesp, Instituto de Química, 14800-900 Araraquara, São Paulo, Brazil

ARTICLE INFO

Article history:

Received 2 June 2008

Received in revised form 3 February 2009

Accepted 24 August 2009

Available online 31 August 2009

Keywords:

Phosphor

Chemical synthesis

Electronic states

Light absorption

Luminescence

ABSTRACT

Langmuir–Blodgett (LB) technique is a powerful tool to fabricate ultrathin films with highly ordered structures and controllable molecular array for efficient energy and electron transfer, allowing the construction of devices at molecular level. One method to obtain LB films consists in the mixture of classical film-forming molecules, for example Stearic Acid (SA) and functional metal complex. In this work $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$, where the organic ligand *bmdm* is (butyl methoxy-dibenzoyl-methane) or (1-(4-methoxyphenyl)-3-(4-tert-butylphenyl)propane-1,3-dione) was used to build up Langmuir and LB films. Langmuir isotherms were obtained from (i) $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ complex and (ii) $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1). Results indicated that (i) form multilayer structure; however the surface pressure was insufficient to obtain LB films, and (ii) can easily reproduce and build LB films. The dependence of number of layers in the UV absorption spectra suggest that the complex did not hydrolyze or show decomposition, UV spectral differences observed between the solution and the LB film indicate that the complex has a highly ordered arrangement in the film and the complex has an interaction with SA. Excitation spectra confirm a ligand-europium energy transfer mechanism. The transition lines of Eu^{3+} ion were observed in emission spectra of all films, the photoluminescence spectra indicate a fluorescence enhanced effect with the number of LB layers.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

More and more attention has been paid to rare-earth β -diketone complex Langmuir–Blodgett (LB) films in recent years for their significance both in theoretical and practical areas [1]. In particular LB films based on strong luminescence have attracted interest with respect to the correlation of film-formation and fluorescence behaviors of $\text{Eu}(\text{III})$ complexes with molecular and film structures, and the fabrication of advanced optoelectronic devices [2].

Three classes of amphiphilic $\text{Eu}(\text{III})$ complexes have been reported for LB films; (i) many workers have employed metal salts in the aqueous subphase to incorporate groups into LB films that are absorbed onto the fatty acid film from the subphase by a stochastic process [3,4]; (ii) chemical modification is used to obtain amphiphilic functional molecules to build up LB films [5,6] and (iii) the mixture of classical film-forming molecules (for example: Stearic Acid or Arachidic Acid) and functional metal complexes can be used to obtain LB films [7,8].

Effects of synergetic ligands of the europium complexes $\text{Eu}(\text{tta})_3\text{nL}$ were tta denotes α -thenoyltrifluoroacetone and L denotes the synergetic ligands triphenylphosphine oxide (tppo),

1,10-phenanthroline (phen), 2,2'-bipy (bipy) and H_2O were studied by Wu et al. Experiments on the Langmuir trough showed that different supermolecular structures were formed for each complex with different synergetic ligands. By using Arachidic Acid (AA) good miscibility with this complex, controllable nanometer-scale thickness and vertical uniformity which allow it to be used as high quality ultrathin optical devices was observed [9]. The fabrication of $\text{Eu}(\text{dpm})_3$ (dpm) = 2,2,6,6-tetramethyl-3,5-heptanedionate mixed LB films coexisting with (AA) with different molar percentages can be deposited successfully and enhanced luminescence was observed [10].

Previously, other groups studied the ternary complex $\text{Eu}(\text{tta})_3\text{phen}$ and presented it as an efficient luminophor, however it is difficult to form organized molecular films [6]. In order to demonstrate the conditions required to fabricate good quality thin films, its surface behavior on various subphases has been exhaustively studied [5,6]. With distinct influences on the monolayer behaviors, the components of the subphase are very important to the fabrication of good quality of Langmuir and LB films; organized molecular films of $\text{Eu}(\text{tta})_3\text{phen}/\text{AA}$ (1:1) and $\text{Sm}(\text{tta})_3\text{phen}/\text{AA}$ (1:1) were then transferred onto solid substrates using the LB technique and investigated, results indicate that the two LB films can emit strong fluorescence, and that all the LB films are vertically uniform [6].

Zhang and co-workers mentioned that some problems arising from very loose packing of the europium complex in the film, and poor film-forming properties remain to be solved [11]. Although

* Corresponding author. Tel.: +55 1633016634; fax: +55 1633227932.

E-mail address: davolos@iq.unesp.br (M.R. Davolos).

¹ Current address: DFQB - Unesp. CP 467, 19060-900 Presidente Prudente, SP Brazil.

the addition of auxiliary film-forming materials such as Stearic Acid (SA) could improve film-forming property of the materials, this had potential phase separation difficulties and had a negative effect on fluorescent characteristics. Also, interestingly, complexes without a long alkyl chain may be used in electronic devices because of the presence of alkyl layers in LB films usually have poor vertical conduction [12].

A tetrakis complex, using a 4:1 ligand-to-metal ratio, where a single positively charged counter ion is needed to assure the electrical neutrality of the complex can be used to obtain LB films. In our previous work the synthesis and characterization of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ was described [13]. Melby et al. [14] described tetrakis diketonates as potassium and sodium salts. Another example that illustrates the use of an ionic complex is europium dibenzoylmethane (hdbm), which shows that the base used should be of sufficient strength to allow an adequate ionization of the diketone for tetrakis formation [15].

Following these strategies, in the present paper, LB film made of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ coexisting with stearic acid was investigated and its optical properties are reported.

2. Experimental

2.1. Materials

$\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ complex was synthesized and purified according to Ref. [13], the purity and structure of the complex was confirmed by elemental analyses and spectroscopic characterizations. The molecular structure *bmdm* ligand (1-(4-methoxyphenyl)-3-(4-tert-butylphenyl)propane-1,3-dione) was shown in Fig. 1. Stearic Acid and chloroform were of reagent grade and used without purification.

2.2. Procedures and apparatus

Surface pressure–area π -A isotherms and LB films were obtained by means of KSV 3000. A Milli-Q system was used to produce pure water with an average resistivity of $18.2 \text{ M}\Omega\cdot\text{cm}$. The monolayers were formed by spreading a volume of complex solution in chloroform on the liquid surface. The solvent was allowed to evaporate 15 min prior compressing, then π -A isotherms (surface pressure versus area per molecule) were recorded. Hydrophilic glass substrates were used for fabricating LB films by the vertical deposition method in Y-type. The experiments were performed under the surface pressure of $15 \text{ mN}\cdot\text{m}^{-1}$ at a speed of $10 \text{ mm}\cdot\text{min}^{-1}$ and at room temperature ($25 \pm 1^\circ\text{C}$).

The UV–vis absorption spectra of LB films were collected on a PerkinElmer UV–vis Lambda 14P instrument with a blank plate as reference. The photoluminescence spectra were obtained on a FLUOROLOG SPEX 212L with a 450 W xenon continuous lamp equipped with a Hammamatsu R928 photomultiplier.

3. Results and discussion

3.1. Monolayer behaviors and LB film fabrication

Fig. 2 shows the Surface pressure–area π -A isotherm of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ on the aqueous subphase, a minimum area per molecule for the liquid condensed to solid phase transition is around $20 \text{ \AA}^2 \text{ molecule}^{-1}$; the presence of charged species NH_4^+ contributed to arrangement of Langmuir film, however, the transfer from the monolayers to the solid substrates is not satisfactory.

Thus an appropriate amount of Stearic Acid (SA) was also separated mixed with complex solution to improve their transfer

Fig. 1. Molecular structure of the *bmdm* (1-(4-methoxyphenyl)-3-(4-tert-butylphenyl)propane-1,3-dione) ligand.

Fig. 2. Surface pressure–area isotherm for $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ on the aqueous subphase.

properties. Monolayers of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) are stable and easy to transfer onto solid substrates; on the other hand, unstable mixed monolayers were obtained by using concentration higher than the equimolecular one, as observed at π -A isotherm of the $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:2). The π -A isotherm of the mixed monolayer was shown in Fig. 3, liquid-condensed (LC) and liquid-expanded (LE) phases were assigned. A limiting molecular area was derived to be $80 \text{ \AA}^2 \text{ molecule}^{-1}$ in the condensed solid region of isotherm by extrapolation to zero value of area per molecule. The result indicated that β -diketonate complexes molecule must form multilayer condensed structure at high surface pressure at air–water interface due to the poor amphiphilic properties of rare earth β -diketonate complex. It also indicated that SA molecules should remain in monolayer structure in the mixed film.

UV–vis spectroscopy of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) LB films in different number of layers was shown in Fig. 4. The wavelength of the absorption peaks of LB films kept unchanged, while the intensities of the absorption peaks increased. The inset Fig. 4 shows a plotter absorbance at 294 nm against number of layers deposited, the linear dependence of the absorbance on the number of layers can be obtained for 11, 21 and 31 layers LB films; considering that the intensity of absorption is determined by the amount of the complex a deviation from linearity was observed just for one

Fig. 3. Surface pressure–area isotherm for $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) monolayer on the aqueous subphase.

Fig. 4. UV-vis spectra of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) LB film in different number of layers: (a) 11 layers, (b) 21 layers and (c) 31 layers. The inset is the plot of the absorbance at 294 nm versus the number of layers.

layer LB deposited, it could be explained by the sensitivity of UV-vis measurements [16,17].

Fig. 5 shows ultraviolet absorption spectra of *bmdm* ligand, $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ and LB film. A wide UV absorption band is observed with $\lambda_{\text{max}} = 358 \text{ nm}$ assigned to $\pi-\pi^*$ transitions of β -diketone in both free ligand and complex spectra. In the free ligand spectrum we also observe another two bands at 265 nm and 287 nm assigned to $\pi-\pi^*$ transitions of the benzene ring and keto-enol tautomerism respectively. In the complex spectrum the band at 287 nm disappears, which is likely due to vibronic component. The LB film exhibited maximum absorption peaks at 294 nm and 363 nm which are red-shifted compared with the complex. The UV spectral differences observed between the solution and the LB film indicate that the complex has a highly ordered arrangement in the film and the complex has an interaction with SA [18].

Fig. 6 shows the excitation spectrum of a 21 and 31 layer LB films on glass substrate. It gives two bands at 254 nm and 318 nm, assigned to the ligand centered $\pi-\pi^*$ transition of the *bmdm* ligand. The lanthanide complex and LB films absorb energy by the *bmdm* ligand, the absorption process of lanthanide usually depends on the

Fig. 5. UV-vis spectra of 11 layers of LB film of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1), (*bmdm*) ligand and $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ complex in ethanol solution.

Fig. 6. Excitation spectra of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) LB films in different number of layers: (a) 21 layers and (b) 31 layers.

Fig. 7. Emission spectra of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) LB films in different number of layers: (a) 1 layer, (b) 11 layers, (c) 21 layers and (d) 31 layers.

anion ligand, besides this the efficiency of a lanthanide complex is very sensitive to the triplet state energy as well as singlet state energy of the anion ligand; triplet state energy of ligand controls

Fig. 8. Dependence of the emission intensities on the number of deposited layers.

the energy transfer between the *bmdm* ligand and central metal ion.

Fig. 7 shows the emission spectrum of LB films, it gives three characteristic peaks at 579 nm, 591 nm and 614 nm and assignable to $^5D_0 \rightarrow ^7F_J$ ($J=0, 1$ and 2). A linearity dependence on the emission intensities versus number of layers deposited was observed in Fig. 8; this result indicates that the film transfers were reproducible and uniform, the correlation factor calculated was 0.9957.

4. Conclusions

In this work, we reported the fabrication of the mixed LB films of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]$ coexisting with stearic acid. Preliminary studies of surface pressure-area isotherm and optical properties on the Langmuir–Blodgett films of $\text{NH}_4[\text{Eu}(\text{bmdm})_4]/\text{SA}$ (1:1) showed that the complex has a good Langmuir and Langmuir–Blodgett films formation properties. UV–vis absorption band in the film was red-shifted in comparison with that in methanol solution, suggesting orientation of the transferred molecules. Y-type LB films can be deposited successfully. The luminescence intensity indicates that the film transfers were reproducible and uniform.

Acknowledgements

FAPESP and RENAMI are gratefully acknowledged. R.D.A. thanks FAPESP for scholarship.

References

- [1] R.J. Zhang, K.Z. Yang, A.C. Yu, X.S. Zhao, *Thin Solid Films* 363 (2000) 275.
- [2] A. Ulman, *An Introduction to Ultrathin Organic Films: From Langmuir–Blodgett to Self-assembly*, first ed., Harcourt Brace Jovanovich, Boston, MA, 1991.
- [3] G.B. Khomutov, I.V. Beresneva, Yu.A. Koksharov, I.L. Radchenko, I.V. Bykov, R.V. Gainutdinov, S.N. Polyakov, A.L. Tolstikhina, *Colloids Surf. A* 198–200 (2002) 509.
- [4] B.F. Abrahams, B.F. Hoskins, J. Liu, R. Robson, *J. Am. Chem. Soc.* 113 (1991) 3045.
- [5] X.M. Xiang, D.J. Qian, F.Y. Liu, H.T. Chen, H.G. Liu, W. Huang, X.S. Feng, *Colloids Surf. A* 273 (2006) 29.
- [6] R.J. Zhang, H.G. Liu, C.R. Zhang, K.Z. Yang, G.Y. Zhu, H.W. Zhang, *Thin Solid Films* 302 (1997) 223.
- [7] V. Erokhin, L. Feigin, G. Ivakin, V. Klechkovskaya, Yu. Lvov, N. Stiopina, *Macromol. Chem. Symp.* 46 (1991) 359.
- [8] W.Z. Lan, H.G. Liu, K.Z. Yang, *Colloids Surf. A* 139 (1998) 7.
- [9] S. Wu, P. He, J. Guan, B. Chen, Y. Luo, Q. Yan, Q. Zhang, *J. Photochem. Photobiol. A: Chem.* 188 (2007) 218.
- [10] Z. Gang, Z. Yanze, H. Pingsheng, *Thin Solid Films* 468 (2004) 268.
- [11] R.J. Zhang, K.Z. Yang, *Colloids Surf. A* 178 (2001) 177.
- [12] M. Era, T. Tsutsui, K. Takehara, K. Isomura, H. Taniguchi, *Thin Solid Films* 363 (2000) 229.
- [13] R.D. Adati, S.A.M. Lima, M.R. Davolos, M. Jafelicci Jr., *J. Alloys Compd.* 418 (2006) 222.
- [14] L.R. Melby, N.J. Rose, E. Abramson, J.C. Caris, *J. Am. Chem. Soc.* 86 (1964) 5117.
- [15] R.E. Whan, G.A. Crosby, *J. Mol. Spectros.* 8 (1962) 315.
- [16] C.L. Medeiros, O.A. Serra, M.E.D. Zaniquelli, *Thin Solid Films* 248 (1994) 115.
- [17] C. Huang, K. Wang, G. Xu, X. Zhao, X. Xie, Y. Xu, Y. Liu, L. Xu, T. Li, *J. Phys. Chem.* 99 (1995) 14397.
- [18] G. Zou, K. Fang, P.S. He, *J. Colloid Interf. Sci.* 261 (2003) 411.

Circularly polarized luminescence from chiral Eu(III) Complex with high emission quantum yield

Takashi Harada^a, Yasuchika Hasegawa^{a,*}, Yoko Nakano^a, Michiya Fujiki^a, Masanobu Naito^a, Takehiko Wada^b, Yoshihisa Inoue^c, Tsuyoshi Kawai^a

^a Graduate School of Materials Science, Nara Institute of Science and Technology, 8916-5, Takayama-cho, Ikoma, Nara 630-0192, Japan

^b Division of Materials Design, Institute of Multidisciplinary Research for Advanced Materials, Tohoku University, 2-1-1, Katahira, Aoba-ku, Sendai 980-8577, Japan

^c Department of Applied Chemistry, Osaka University, Yamada-oka, Suita, Osaka 565-0871, Japan

ARTICLE INFO

Article history:

Received 2 June 2008

Received in revised form 4 July 2008

Accepted 1 September 2008

Available online 6 December 2008

Keywords:

Rare earth alloys and compounds

Luminescence

Optical spectroscopy

ABSTRACT

Luminescent Eu(III) complex with axis-chiral ligand, [Eu((*R*)-BINAPO)(hfa)₃] ((*R*)-BINAPO: (*R*)-2,2'-bis(diphenylphosphoryl)-1,1'-binaphthyl, hfa: 1,1,1,5,5,5-hexa-fluoropentanedione) was synthesized. Its emission quantum yield and the emission lifetime in acetone-*d*₆ were found to be 0.53 and 2.1 ms, respectively. The circularly polarized luminescence (CPL) of the Eu(III) complex was also measured. The dissymmetry factor at the magnetic dipole transition (*g*_{lum}) of [Eu((*R*)-BINAPO)(hfa)₃] was found to be 0.03.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Lanthanide(III) complexes with narrow emission bands, ideal four level transitions and long emission lifetimes have been regarded as attractive luminescent molecules for optical devices, laser materials, EL displays, and bio-sensing engineering [1]. Luminescent lanthanide(III) complexes having chiral ligands show the strong circularly polarized luminescence (CPL) [2]. Especially, the CPL properties of the magnetic dipole transition in Eu(III) complexes ($\lambda_{em} = 595$ nm) have been extensively studied because of their large dissymmetry factors (*g*_{lum}) [3]. In the previous literatures, Parker and Riehl have reported the CPL properties of the lanthanide(III) complexes with chiral tetraazacyclododecane (DOTA) derivatives [4]. Furthermore, Petoud has successfully synthesized Eu(III) complexes having four chiral points [5]. Previous chiral ligands in Eu(III) complexes contained the high-frequency vibrational coordination sites (at around 1600 cm⁻¹) linked with numerous C–H chemical bonds (C–H: 2950 cm⁻¹). Their chemical components might lead to increase in the radiationless transitions via vibrational relaxations of the chiral Eu(III) complexes [6]. In order to enhance the emission quantum yields of the chiral Eu(III) complexes, the chiral ligands should be composed of the low-frequency vibrational coordination sites, phosphine oxides

(P=O: 1125 cm⁻¹) [7a]. Phosphine oxides with chiral structures are expected to be promising ligands for chiral Eu(III) complexes having high emission quantum yields.

Here, we report on a novel Eu(III) complex having axis-chiral phosphine oxide ligand, [Eu((*R*)-BINAPO)(hfa)₃] bearing (*R*)-2,2'-bis(diphenylphosphoryl)-1,1'-bi-naphthyl ((*R*)-BINAPO) and 1,1,1,5,5,5-hexafluoropentane-2,4-dione (hfa) ligands (Fig. 1). The introduction of chiral (*R*)-BINAPO ligand provides the chiral coordination structure around the Eu(III) ion center. The coordination sites of (*R*)-BINAPO are composed of the low-frequency vibrational P=O bonds which lead to increased emission quantum yield [7]. The low-frequency vibrational hfa ligand which contains C–F bonds also contributes to the suppression of the nonradiative transitions [6]. Furthermore, Eu(III) complex coordinated with three hfa ligands and one bidentate phosphine oxide ligand, [Eu((*R*)-BINAPO)(hfa)₃], is expected to form square antiprism (SAP) structures with no inversion center, and to show increased intensity of the electric dipole transitions related to change of odd parity [7]. A highly luminescent Eu(III) complex with achiral bidentate phosphine oxide ligand, [Eu(BIPHEPO)(hfa)₃] (BIPHEPO: 2,2'-bis(diphenylphosphoryl)-1,1'-biphenyl) is also prepared for the comparison of the emission and CPL properties of [Eu((*R*)-BINAPO)(hfa)₃]. Emission spectra, emission quantum yields, emission lifetimes and CPL spectra of the chiral [Eu((*R*)-BINAPO)(hfa)₃] and achiral [Eu(BIPHEPO)(hfa)₃] are studied. We also estimated the dissymmetry factors of the chiral Eu(III) complex by using the CPL spectrum. In present paper, chiral Eu(III) complex

* Corresponding author.

E-mail address: hasegawa@ms.naist.jp (Y. Hasegawa).

Fig. 1. Chemical structures of $[\text{Eu}((R)\text{-BINAPO})(\text{hfa})_3]$ and $[\text{Eu}(\text{BIPHEPO})(\text{hfa})_3]$.

having the high emission quantum yield is demonstrated for the first time.

2. Experimental

2.1. Apparatus

^1H NMR spectra were obtained with JEOL AL-300 spectrometers. Infrared spectra were recorded with a JASCO FT/IR-4200 spectrometer. Elemental analyses were performed with a Perkin Elmer, 2400 II.

2.2. Materials

(*R*)-BINAP and BIPHEP were purchased from Tokyo Chemical Industry Co., Ltd. Europium(III) acetate tetrahydrate (99.9%) and acetone- d_6 (99.9%) were obtained from Wako Pure Chemical Industries, Ltd. TPPO and hfa were purchased from Aldrich Chemical Co. Inc. All other organic compounds were reagent grade and used as received. (*R*)-BINAPO and BIPHEPO were prepared by oxidation of (*R*)-BINAP and BIPHEP, according to the literature procedure [8]. $[\text{Eu}(\text{BIPHEPO})(\text{hfa})_3]$ was prepared according to the previous procedure [7b].

2.3. Preparation of tris(hexafluoroacetylacetonato)Europium(III)((*R*)-2,2'-bis(diphenylphosphoryl)-1,1'-naphthyl) ($[\text{Eu}((R)\text{-BINAPO})(\text{hfa})_3]$)

$[\text{Eu}(\text{hfa})_3(\text{H}_2\text{O})_2]$ was prepared to the procedure described in our previous reports [7]. $[\text{Eu}(\text{hfa})_3(\text{H}_2\text{O})_2]$ (1.3 g, 1.5 mmol) and (*R*)-BINAPO (1.0 g, 1.5 mmol) were dissolved in methanol (80 mL) and refluxed under stirring for 12 h. The solvent was removed using rotary evaporator from the reaction mixture. Obtained powder was then dissolved in toluene and insoluble residue was removed by the filtration. Powder was obtained after removal of solvent. Obtained powder was dried under vacuum and recrystallized from hot chloroform/n-hexane and gave white solids. Yield: 40%. ^1H NMR (acetone- d_6 , 300 MHz, 298 K) δ : 8.4–6.4 (m, Aromatic), 5.9–5.7 (s) ppm. IR (ATR): 3800–3550 (w, O–H), 3060 (w, C–H), 1650 (s, C=O), 1600–1460 (m, br), 1440 (s), 1250–1050 (s, C–F), 1200 (s, P=O), 690 (s, Aromatic) cm^{-1} . Anal. Found: C, 51.08; H, 2.51%. Calcd. for $\text{EuC}_{59}\text{H}_{35}\text{O}_8\text{F}_{18}\text{P}_2$ 0.25 toluene: C, 51.11; H, 2.61%.

2.4. Optical measurements

Acetone- d_6 solutions (1.0 mM) of the Eu(III) complexes in quartz cells were treated with N_2 bubbling for emission spectra, emission quantum yields, emission lifetimes and CPL spectra measurements. The emission spectra were measured at room temperature using JASCO FP-6500 and ACTON Research Corporation SpectraPro 2300i system with a cooled CCD detector (Roper PIXIS 100). The spectra were

corrected for detector sensitivity and lamp intensity variations. The emission quantum yield of $[\text{Eu}((R)\text{-BINAPO})(\text{hfa})_3]$ excited at 465 nm was evaluated using JASCO V-660 and HITACHI F-4500. The value was corrected with $[\text{Eu}(\text{BIPHEPO})(\text{hfa})_3]$ solution dissolved in acetone- d_6 ($\Phi = 0.60$) as a reference [9]. In the emission lifetime measurements, the samples were excited by a N_2 laser (Usho KEC-160, wavelength: 337 nm, pulse width: 600 ps, 10 Hz). The emission profile was recorded using a streak camera (Hamamatsu, picosecond fluorescence measurement system, C4780). The CPL spectra were measured with a JASCO CPL-200 spectrometer. Obtained emission quantum yields and emission lifetimes have uncertainty with approximately $\pm 5.0\%$ and ± 0.02 ms, respectively.

3. Results and discussion

3.1. Emission properties

The emission spectra of $[\text{Eu}((R)\text{-BINAPO})(\text{hfa})_3]$ and $[\text{Eu}(\text{BIPHEPO})(\text{hfa})_3]$ under excitation at 365 nm (excited at $\pi\text{-}\pi^*$ transitions of hfa ligands) are shown in Fig. 2. The emission bands were observed at 578 nm, 593 nm, 611 nm, 650 nm and 700 nm. These bands were attributed to the $f\text{-}f$ transitions,

Fig. 2. Normalized emission spectra of $[\text{Eu}((R)\text{-BINAPO})(\text{hfa})_3]$ (solid line) and $[\text{Eu}(\text{BIPHEPO})(\text{hfa})_3]$ (dashed line) (excited at 365 nm, optical path: 10 mm).

$^5D_0 \rightarrow ^7F_0$ (forbidden transition), $^5D_0 \rightarrow ^7F_1$ (the magnetic dipole transition) and $^5D_0 \rightarrow ^7F_J$ ($J=2,3,4$, the electric dipole transitions), respectively. The emission spectra were normalized with respect to the magnetic dipole ($^5D_0 \rightarrow ^7F_1$) transition. The strongest emission bands of those Eu(III) complexes, the $^5D_0 \rightarrow ^7F_2$ transition corresponds to the electric dipole transitions. The probability of the electric dipole transition markedly depends on the symmetry of the coordination structure around Eu(III) ion [10]. In order to estimate the effects of the coordination structures, we calculated the relative integrated emission intensity of the $^5D_0 \rightarrow ^7F_2$ transitions ($A_{rel} = A_{611}/A_{593}$). The A_{rel} values of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] were found to be 8.1 and 16.0, respectively. It is well known that the ligand fields with low symmetry in Eu(III) complexes enhance the probability of the electric dipole transitions and increase the A_{rel} values [11]. Relatively large A_{rel} values of these Eu(III) complexes would be associated with the low-symmetrical coordination structures and their electric dipole transitions would be sufficiently allowed. The A_{rel} value of [Eu((R)-BINAPO)(hfa)₃] was smaller than that of [Eu(BIPHEPO)(hfa)₃]. The smaller A_{rel} of [Eu((R)-BINAPO)(hfa)₃] might be caused by the relatively high symmetrical structure.

The emission quantum yields of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] were found to be 0.53 and 0.60, respectively. These high emission quantum yields of these Eu(III) complexes are due to the suppression of vibrational relaxations by using low-frequency vibrational hfa ligands. In our previous paper, lanthanide(III) complexes covered with low-frequency vibrational ligands ([Nd(hfa)₃] and [Nd(pos)₃]) showed strong luminescent properties [7a]. Low-frequency vibrational C–F bonds (1200 cm⁻¹) result in small Franck–Condon factors related to vibrational relaxations. In non-deuterated acetone, the emission quantum yields of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] were found to be 0.38 and 0.44, respectively. The emission decays of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] were measured, and the single-exponential decay profiles were observed. From logarithmic plots of decay profiles, the emission lifetimes of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] in acetone-d₆ were found to be 2.1 ms and 1.1 ms, respectively.

Here, we estimated the radiative and nonradiative rate constants (k_r and k_{nr}) of [Eu((R)-BINAPO)(hfa)₃] and [Eu(BIPHEPO)(hfa)₃] based on the emission quantum yields and the emission lifetimes. The k_r and k_{nr} of [Eu((R)-BINAPO)(hfa)₃] were found to be 4.8×10^2 s⁻¹ and 4.2×10^2 s⁻¹, respectively. These values of [Eu((R)-BINAPO)(hfa)₃] were smaller than those of [Eu(BIPHEPO)(hfa)₃] ($k_r = 9.1 \times 10^2$ s⁻¹, $k_{nr} = 6.1 \times 10^2$ s⁻¹). The relatively smaller k_r value of [Eu((R)-BINAPO)(hfa)₃] might be linked to the geometrical structure of this Eu(III) complex. The geometrical structure of Eu(III) complex with achiral bidentate phosphine oxide ligand, [Eu(BIPHEPO)(hfa)₃] has been determined to be a square antiprism structure (The symmetrical group: C₁) [7b]. According to the estimations of the radiative rates, the geometrical structure of [Eu((R)-BINAPO)(hfa)₃] might be more symmetric than that of [Eu(BIPHEPO)(hfa)₃]. We propose that the smaller A_{rel} of [Eu((R)-BINAPO)(hfa)₃] is due to the symmetrical coordination structures related to odd parity.

3.2. Circularly polarized luminescence (CPL) properties

The circularly polarized luminescence (CPL) spectrum of [Eu((R)-BINAPO)(hfa)₃] was also measured as shown in Fig. 3. CPL intensity (ΔI) is expressed by the difference between left- and right-circularly polarized luminescent intensities, I_L and I_R . We found the distinct CPL signals in the $^5D_0 \rightarrow ^7F_1$ and $^5D_0 \rightarrow ^7F_2$ transitions. On the other hand, the CPL signals of Eu(III) complex with achiral ligands, [Eu(BIPHEPO)(hfa)₃] were not observed.

Fig. 3. Normalized emission (under) and CPL (upper) spectra of [Eu((R)-BINAPO)(hfa)₃] (excited at 350 nm, optical path: 10 mm).

We estimated the dissymmetry factor (g_{lum}) based on the CPL spectrum [12]. The g_{lum} values are given by,

$$g_{lum} = \frac{\Delta I}{1/2(I)} = \frac{I_L - I_R}{1/2(I_L + I_R)} \quad (1)$$

The g_{lum} values of [Eu((R)-BINAPO)(hfa)₃] at the magnetic and electric dipole transitions were estimated to be 0.03 and -0.003, respectively. The g_{lum} value at the magnetic dipole transition of [Eu((R)-BINAPO)(hfa)₃] was similar to that of reported Eu(III) complex with chiral 1,1'-binaphthyl-2,2'-diyl phosphate ligands ($g_{lum} = \text{ca. } 0.04$) [13]. CPL properties of [Eu((R)-BINAPO)(hfa)₃] seem to be induced by the coordination of the axis-chiral bidentate ligand.

4. Conclusion

We successfully synthesized a novel strong luminescent Eu(III) complex with chiral (R)-BINAPO and low-frequency vibrational hfa ligands. The high emission quantum yield and the CPL property of Eu(III) complex were achieved by the coordination of the axis-chiral phosphine oxide. The chiral Eu(III) complex with effectively luminescent properties would open up the novel photo-functional materials.

Acknowledgement

This work was partly supported by a Giant-in-Aid for Scientific Research No. 20900127 and No. 19510104 from the Ministry of Education, Culture, Sports, Science and Technology (MEXT), Japan.

References

- [1] (a) K. Kuriki, Y. Koike, Chem. Rev. 102 (2002) 2347–2356;
(b) J. Kido, H. Hayase, K. Honagawa, K. Nagai, K. Okuyama, Appl. Phys. Lett. 65 (1994) 2124–2126;
(c) N. Weibel, L.J. Charbonnière, M. Guardigli, A. Roda, R. Ziessel, J. Am. Chem. Soc. 126 (2004) 4888–4896;
(d) H. Tsukube, S. Shinoda, Chem. Rev. 102 (2002) 2389–2403;
(e) N.S. Baek, Y.H. Kim, S.-G. Roh, B.K. Kwak, H.K. Kim, Adv. Funct. Mater. 16 (2006) 1873–1882;
(f) R.S. Dickins, T. Gunnlaugsson, D. Parker, R.D. Peacock, Chem. Commun. 16 (1998) 1643–1644.
- [2] (a) O. Mamula, M. Lama, S.G. Telfer, A. Nakamura, R. Kuroda, H. Stoeckli-Evans, R. Scopelitti, Angew. Chem. Int. Ed. 44 (2005) 2527–2531;
(b) G. Muller, J.-C.G. Bünzli, J.P. Riehl, D. Suhr, A. von Zelewsky, H. Mürner, Chem. Commun. 14 (2002) 1522–1523;
(c) J. Yu, D. Parker, R. Pal, R.A. Poole, M.J. Cann, J. Am. Chem. Soc. 128 (2006) 2294–2299.

- [3] J.P. Riehl, G. Muller, Circularly polarized luminescence spectroscopy from lanthanide systems, in: K.A. Gschneidner, J.-C.G. Bünzli, V.K. Pecharsky (Eds.), *Handbook on the Physics and Chemistry of Rare Earths*, 34, North-Holland Publishing Company, Amsterdam, 2005, pp. 289–357.
- [4] D. Parker, R.S. Dickins, H. Puschmann, C. Crossland, J.A.K. Howard, *Chem. Rev.* 102 (2002) 1977–2010.
- [5] S. Petoud, G. Muller, E.G. Moore, J. Xu, J. Sokolnicki, J.P. Riehl, U.N. Le, S.M. Cohen, K.N. Raymond, *J. Am. Chem. Soc.* 129 (2007) 77–83.
- [6] Y. Hasegawa, T. Ohkubo, K. Sogabe, Y. Kawamura, Y. Wada, N. Nakashima, S. Yanagida, *Angew. Chem. Int. Ed.* 39 (2000) 357–360.
- [7] (a) Y. Hasegawa, M. Yamamuro, Y. Wada, N. Kanehisa, Y. Kai, S. Yanagida, *J. Phys. Chem. A* 107 (2003) 1697–1702;
(b) K. Nakamura, Y. Hasegawa, H. Kawai, N. Yasuda, N. Kanehisa, Y. Kai, T. Nagamura, S. Yanagida, Y. Wada, *J. Phys. Chem. A* 111 (2007) 3029–3037.
- [8] M. Berthod, C. Saluzzo, G. Mignani, M. Lemaire, *Tetra. Asymm.* 15 (2004) 639–645.
- [9] K. Nakamura, Y. Hasegawa, H. Kawai, N. Yasuda, Y. Tsukahara, Y. Wada, *Thin Solid Films* 516 (2008) 2376–2381.
- [10] K. Lunstroot, K. Driesen, P. Nockemann, C. Gorller-Warland, K. Binnemans, S. Bellayer, J.L. Bideau, A. Vioux, *Chem. Mater.* 18 (2006) 5711–5715.
- [11] (a) B.R. Judd, *Phys. Rev.* 127 (1962) 750–761;
(b) G.S. Ofelt, *J. Phys. Chem.* 37 (1962) 511–520;
(c) E.M. Stephens, M.F. Reid, F.S. Richardson, *Inorg. Chem.* 23 (1984) 4611–4618.
- [12] F.S. Richardson, *Inorg. Chem.* 19 (1980) 2806–2812.
- [13] M. Pedziwiatr, N.M. Kosareff, G. Muller, A.Y. Kopsav, V.N. Nemykin, J.P. Riehl, J. Legendziewicz, *J. Alloys Compd.* 451 (2008) 251–253.

In situ generation of fluorescent macrocyclic europium(II) complexes via zinc reduction

Satoshi Shinoda*, Miho Nishioka, Hiroshi Tsukube

Department of Chemistry, Graduate School of Science, Osaka City University, 3-3-138 Sugimoto, Sumiyoshi-ku, Osaka 558-8585, Japan

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 8 September 2008

Accepted 6 October 2008

Available online 22 November 2008

Keywords:

Rare earth alloys and compounds

Optical properties

Luminescence

ABSTRACT

We report *in situ* generation of macrocyclic Eu(II) complexes upon zinc reduction which readily emitted visible light via $5d \rightarrow 4f$ transitions. The nature of a co-existing anion significantly controlled the reduction rate of the Eu(III) complex and the fluorescence intensity of the generated Eu(II) complex. Among the examined anions, Cl^- , Br^- , and I^- effectively offered intense Eu(II) fluorescence, while OAc^- and NO_3^- elongated the time for completion of reduction and weakened the fluorescence. Since the generated macrocyclic Eu(II) complexes were stable under N_2 atmosphere, this *in situ* reduction is a useful method to prepare fluorescent Eu(II) complexes.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Although divalent europium ion shows optically allowed transitions between $4f$ and $5d$ orbitals to give a broad emission band in the visible region, a limited number of Eu(II) complexes were reported to emit intense fluorescence. Due to the vulnerability to molecular oxygen and the strong reducing power of the Eu(II) species, preparation and utilization of Eu(II) complexes in solution have been restricted. Adachi and coworkers had combined a series of macrocyclic ligands with EuCl_2 prepared from Eu_2O_3 and revealed that the complexation with macrocyclic ligands drastically enhanced the fluorescence intensities in MeOH [1]. Typically, 18-crown-6 formed 1:1 Eu(II) complex which showed the 160-times enhanced fluorescence comparing with EuCl_2 itself [1]. Starynowicz et al. [2] reduced Eu(III) complex with 18-crown-6 by electrolysis and obtained the crystal structure of its Eu(II) complex. Since the Eu(II) has large ionic radius and adopts high coordination number, its macrocyclic complexes still have available coordination sites for incoming anions and solvent molecules. A similar fluorescence enhancement was reported with Sm(II)–18-crown-6 and Sm(II)–(15-crown-5) $_2$ complexes [3].

In this paper, we report *in situ* preparation of macrocyclic Eu(II) complexes in MeOH and significant effects of anions on the generation and fluorescence properties of Eu(II) complexes. As a convenient synthetic method of Eu(II) complexes, we

applied zinc reduction of $\text{Eu}(\text{OTf})_3$ complexes with 18-crown-6 and cryptand[2.2.2]. When several tetrabutylammonium salts were added prior to reduction to the MeOH solution, some additional anions offered ternary Eu(II) complexes with different fluorescent properties.

2. Experimental

2.1. Chemicals and reagents

$\text{Eu}(\text{OTf})_3$, 18-crown-6, and cryptand[2.2.2] were respectively purchased from Sigma–Aldrich Japan K. K., Tokyo Chemical Industry Co. Ltd, and Merck Ltd. Japan, and used as received. The employed tetrabutylammonium salts were also commercially available from Sigma–Aldrich Japan K. K. (Br^- , I^- , OAc^- , and NO_3^-), Tokyo Chemical Industry Co. Ltd. (Cl^- and SCN^-), and Wako Pure Chemicals Industries Ltd. (F^- as trihydrate). Spectroscopic grade MeOH was purchased from Nacalai Tesque Inc. and used without further purification for all the measurements.

2.2. *In situ* generation of macrocyclic Eu(II) complexes in MeOH

2.2.1. Eu(II)–18-crown-6 complex

A 2-ml MeOH solution containing $\text{Eu}(\text{OTf})_3$ (5.0×10^{-4} M), 18-crown-6 (5.0×10^{-3} M), and $n\text{Bu}_4\text{NX}$ (2.5×10^{-3} M) was prepared. This solution was transferred to 1-cm quartz cell where excess amount of zinc powder (ca. 100 mg) and a stirring bar were added. The cell was then capped with a rubber septum. The solution was vigorously stirred for longer than 20 min with N_2 gas bubbling. The N_2 gas for de-aeration was passed through the methanol before introducing in the cell to avoid vaporization of the solvent. The zinc reduction was monitored by following the absorption bands of Eu(II) species around 250 and 330 nm.

2.2.2. Eu(II)–cryptand[2.2.2] complex

An equimolar mixture of $\text{Eu}(\text{OTf})_3$ and cryptand[2.2.2] was stirred at room temperature for longer than 8 h, and then the zinc reduction was similarly carried out.

* Corresponding author. Tel.: +81 6 6605 3139; fax: +81 6 6605 2560.

E-mail address: shinodas@sci.osaka-cu.ac.jp (S. Shinoda).

The final concentrations were $[\text{Eu}(\text{OTf})_3] = 5.0 \times 10^{-4} \text{ M}$, $[\text{cryptand}] = 5.0 \times 10^{-4} \text{ M}$, and $[n\text{Bu}_4\text{N}^+\text{X}^-] = 2.5 \times 10^{-3} \text{ M}$.

2.3. UV-vis and fluorescence measurements

UV-vis absorption spectra were recorded on a Hitachi U-4500 or a Scinco S-3100 spectrometer. Fluorescence spectra were recorded on a PerkinElmer LS-55 spectrometer. The Eu(II) complexes were excited at 330 nm where the absorbance of the Eu(II) absorption band was ca. 0.2. Excitation and emission slits were set to 5.0 and 2.5 nm, respectively. The obtained fluorescence spectra were not corrected.

2.4. Cyclic voltammetry

Cyclic voltammograms for macrocycle-Eu complexes were measured in MeOH with a Hokuto Denko HSV-100 electrochemical analyzer. The working electrode was a glassy carbon electrode and the counter electrode was a platinum wire. The reference electrode was a Ag^+/Ag electrode. The scan rate was 50 mV s^{-1} .

3. Results and discussion

3.1. Macrocyclic complexation

Thermodynamic and structural studies on macrocyclic Eu(II) complexes are limited due to the facile oxidation of Eu(II) species with molecular oxygen. Starynowicz et al. reported the crystal structure of bisperchlorato(18-crown-6)europium(II) by electrochemical reduction [2]. In the complex, the 18-crown-6 located in the equatorial plane and the two perchlorate anions coordinated to the Eu(II) from the opposite sides. Tóth and coworkers [4] reported $\text{Sr}(\text{II})$ -cryptand[2.2.2] $(\text{H}_2\text{O})(\text{OTf})_2$. This is an effective reference, because the ionic radius of $\text{Sr}(\text{II})$ ($r = 1.26 \text{ \AA}$) is similar to that of $\text{Eu}(\text{II})$ ($r = 1.25 \text{ \AA}$). The $\text{Sr}(\text{II})$ ion was completely wrapped in the cryptand cavity and further coordinated by one water and one OTf^- anion to give a 10-coordinated complex. Stability constants of the Eu(II) complexes with 18-crown-6 and cryptand[2.2.2] were not determined in MeOH, but those of the corresponding of SrCl_2 complexes were determined: 18-crown-6 complex, $\log K = 3.76$; cryptand[2.2.2] complex, $\log K = 4.89$ [5]. We employed $5 \times 10^{-4} \text{ M}$ $\text{Eu}(\text{OTf})_3$ solution containing 10 equiv. of 18-crown-6 or 1 equiv. of cryptand[2.2.2] in the following experiments. Under the employed conditions, considerable amounts of Eu(II)-macrocycle complexes are expected to be generated (Fig. 1).

$\text{X}^- = \text{F}^-, \text{Cl}^-, \text{Br}^-, \text{I}^-, \text{SCN}^-, \text{NO}_3^-, \text{or OAc}^-$

18-crown-6

cryptand[2.2.2]

Fig. 1. *In situ* preparation of Eu(II) complex in MeOH.

3.2. In situ preparation of Eu(II) complexes in MeOH

Reduction of Eu(III) complex by zinc was monitored by following the broad absorption bands of $4f \rightarrow 5d$ transitions of Eu(II) center. When a MeOH solution of Eu(III) salt and macrocyclic ligand was mixed with zinc powder, characteristic absorption bands of the Eu(II) species appeared around 250 and 330 nm, indicating that zinc reduction of Eu(III) complex occurred (see Fig. 2a and b). The reduction rate of each Eu(III) complex was dependent on a combination of macrocycle and co-existing anion. The reduction of $\text{Eu}(\text{OTf})_3$ -18-crown-6 complex completed after 40 min, while the addition of 5 equivalents of Cl^- or SCN^- to the solution effectively accelerated the reduction and 15 min were enough to obtain the Eu(II) complex quantitatively. OAc^- and NO_3^- anions gave no influence on the reduction rates, but the observed UV signals were somewhat broader than other Eu(II) complexes. When cryptand[2.2.2] was employed, the absorption spectral changes were similarly observed, but the reduction rates were more strongly dependent on the natures of the added anions. When an equimolar mixture of $\text{Eu}(\text{OTf})_3$ and cryptand[2.2.2] was treated by zinc powder, the absorbance increase at 250 nm continued for longer than 120 min. Addition of Cl^- , Br^- , I^- , SCN^- , or OAc^- anion shortened the required time to 30 min for completing the reaction, while 80 min was required for the reduction in the presence of NO_3^- anion. In the presence of F^- anion, however, no Eu(II) absorption band appeared at all in both complexes.

As shown in Fig. 2a and b, 18-crown-6 and cryptand[2.2.2] gave different absorption maxima of the Eu(II) species, but the added anions gave only slight changes. The molar extinction coefficients and the wavelength of the absorption maxima observed here were consistent with the values reported by Adachi and coworkers [1], where pure EuCl_2 was first prepared and then used for complexation with macrocyclic ligands under inert atmosphere: λ_{max} (nm) (ϵ ($\text{mol}^{-1} \text{ cm}^{-1}$)) of *in situ* generated 18-crown-6-EuBr₂ complex were 256 (1.7×10^3) and 326 (4.6×10^2) [6]. Literature values were 256 (1723) and 325 (477). Both macrocyclic complexes showed quasi-reversible cyclic voltammograms of $\text{Eu}^{3+}/\text{Eu}^{2+}$ in MeOH containing 0.1 M $n\text{Bu}_4\text{N}(\text{OTf})$ [7]. The cathodic peak potential (E_{pc}) was -0.70 V (vs Ag^+/Ag) for 18-crown-6-Eu(OTf)₃ complex. The addition of SCN^- , OAc^- , or NO_3^- anion gave more negative E_{pc} values: -0.73 (SCN^-), -0.84 (NO_3^-), and -1.12 V (OAc^-). Cryptand[2.2.2]-Eu(OTf)₃ complex showed much broader peaks and addition of Cl^- , Br^- , or SCN^- gave the similar voltammogram, while OAc^- and NO_3^- anion gave two reduction peaks (-1.13 and -0.74 V for OAc^- ; -0.98 and -0.62 V for NO_3^-). When F^- anion was added, both macrocyclic complexes showed no signal in the employed scan range (0 to -1.6 V). Since the F^- anion is known to bind strongly with Eu(III) ion, zinc may not have enough power to reduce its F^- complex. Since Eu(II) absorption bands appeared and the voltammograms were observable, the employed other anions did not prevent the zinc reduction of the Eu(III) complexes.

3.3. Eu(II) fluorescence

Fluorescence spectra of *in situ* generated Eu(II) complexes were measured by exciting Eu(II) absorption band at 330 nm (Fig. 2c and d). The cryptand[2.2.2] complexes showed fluorescence at longer wavelength than the 18-crown-6 complexes. The natures of the added anions gave no influences on the fluorescence wavelengths, but greatly affected the fluorescence intensities. Addition of Cl^- , Br^- , and I^- gave intense fluorescence signals, while SCN^- , OAc^- , and NO_3^- anions decreased the fluorescence intensities. The fluorescence measurements were repeated several times within 10 min, but no decrease in intensity was observed unless the solution was exposed to the air. The Eu(II) fluorescence disappeared within a

Fig. 2. UV-vis absorption spectra of (a) Eu(II)-18-crown-6 and (b) Eu(II)-cryptand[2.2.2] complexes and fluorescence spectra of (c) Eu(II)-18-crown-6 and (d) Eu(II)-cryptand[2.2.2] complexes after zinc reduction. Markers were put on every 15 points to distinguish the lines. $[\text{Eu}(\text{OTf})_3] = 5.0 \times 10^{-4} \text{ M}$, $[\text{18-crown-6}] = 5.0 \times 10^{-3} \text{ M}$ or $[\text{cryptand}[2.2.2]] = 5.0 \times 10^{-4} \text{ M}$, $[\text{nBu}_4\text{NX}] = 0$ (none) or $2.5 \times 10^{-3} \text{ M}$; $d = 1 \text{ cm}$; MeOH; room temperature; excitation at 330 nm.

minute after contact with air even when the excess amount of zinc remained in the quartz cell.

4. Conclusion

Fluorescent Eu(II) complexes with 18-crown-6 and cryptand[2.2.2] ligands were *in situ* prepared by zinc reduction of the mixture containing ligand, $\text{Eu}(\text{OTf})_3$ and external anion. Cl^- , Br^- , and I^- promoted the efficient generation of the fluorescent Eu(II) complexes with both macrocycles. Thus, the appropriate combination of macrocyclic ligand and coordinating anion enabled *in situ* preparation of fluorescent Eu(II) complex.

Acknowledgments

The authors are grateful to Professor A. Ichimura and Dr. H. Sugimoto of Osaka City University for their kind supports in the

electrochemical experiments. This work was in part supported by the Ministry of Education, Culture, Sports, Science and Technology, Japan (a Grant-in-Aid of Science Research, Nos. 20900138 and 20245014).

References

- [1] J. Jiang, N. Higashiyama, K. Machida, G. Adachi, *Coord. Chem. Rev.* 170 (1998) 1.
- [2] P. Starynowicz, *Polyhedron* 22 (2003) 337; P. Starynowicz, K. Bukietyńska, S. Gołąb, W. Ryba-Romanowski, J. Sokolnicki, *Eur. J. Inorg. Chem.* (2002) 2344.
- [3] J.A. Teprovich Jr., E. Prasad, R.A. Flowers II., *Angew. Chem. Int. Ed.* 46 (2007) 1145.
- [4] L. Burai, R. Scopelliti, É. Tóth, *Chem. Commun.* (2002) 2366.
- [5] G. Adachi, N. Higashiyama, *Nippon Kagakukaishi* (1993) 418.
- [6] The absorbance value contained a small contribution from a rise of baseline due to the weak light scattering by zinc dust in the solution.
- [7] P.H. Smith, Z.E. Reyes, C.W. Lee, K.N. Raymond, *Inorg. Chem.* 27 (1988) 4154.

Optical properties of Nd³⁺ and Er³⁺ ions in fluoro-phosphate glasses: Effects of P₂O₅ concentration and laser applications

A. Flórez*, E.M. Ulloa, R. Cabanzo

Universidad Industrial de Santander, Escuela de Física, Laboratorio de Materiales Fotónicos, A. A. 678, Bucaramanga, Colombia

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 2 September 2009

Accepted 10 September 2009

Available online 18 November 2009

Keywords:

Inorganic, amorphous and optical materials

Solid state reaction

Optical properties

ABSTRACT

Materials based on fluoride glasses have been recognized as potential hosts for trivalent rare earth ions for different applications, such as fiber lasers. A broad range of stability, an appropriate refractive index and the optimization of the optical and mechanical properties are important characteristics that need to be improved in these new materials. In this work, we made a systematic study of the effect of substituting BaF₂ for P₂O₅ in the matrix: 35InF₃–20ZnF₂–(16–x)BaF₂–xP₂O₅–20SrF₂–6GaF₃–2NaF–1.0REF₃, where RE = Nd³⁺, Er³⁺, with x = 4.0; 8.0; 12.0 and 16.0 molar concentration. In order to evaluate the material's thermal evolution, we obtained differential scanning calorimeter (DSC) measurements, noting the variations in the stability range. Measurements of the refractive index, absorption and luminescence at room temperature in the spectral range from 300 to 3200 nm were also obtained. An increase in refractive index with increasing P₂O₅ concentrations was observed. The behavior of phonons in the samples was observed through of the absorption intensity and the narrowing of the bands in the visible part of the spectrum; the width of the bands in the infrared region did not change. From the areas of the absorption bands, we calculated the oscillator strengths for the all of the samples, and using the Judd–Ofelt intensity model, we calculated the characteristic spectroscopic parameters. Furthermore, we analyzed the intensity parameter in Nd³⁺ and Er³⁺ doped glasses to determine the material's suitability for laser applications.

Published by Elsevier B.V.

1. Introduction

There have been numerous studies on fluoride glasses as host materials for trivalent rare earth ions in order to find potential applications in telecommunications, lasers, sensors, amplifiers, wave guides, and other photonic devices [1–5]. The wide range of transparency (up to ~10 μm) and low phonon energy make these materials important for new technologies [6].

Due to the prevalence of fluorine, these materials have a strong ionic character; thus, the weak ionic bonding in these materials and the heavy metallic ions explain the low resonance frequency characteristic of these glasses. As a result of the low resonance frequencies, these materials have low non-radiative losses that increase up-conversion efficiencies [7]. These characteristics make these materials good candidates for applications in laser technology [8]. At the moment, for the use of glasses in laser applications, phosphates have the best properties [9]. Fluoride glasses also have potential for applications in lasers, but further research is necessary to optimize their properties.

Of all lanthanide rare earths ions, Nd³⁺ has been extensively studied for lasers; therefore, almost all solid state lasers use Nd³⁺ as the active ion at present [10–12]. Except for Pm and Gd, all of the lanthanide ions has transitions that are useful for laser devices. Aside from Nd³⁺, the Er³⁺ ion presents the best optical properties for photonic applications. However; aside from the well known problems related to the Ω₂ intensity parameter of Pr³⁺, when transitions are described by the Judd–Ofelt theory [13–15], Pr³⁺ presents attractive properties such as low phonon energy. In fluoride glasses, its emission at 1.3 μm corresponds to the ¹G₄ → ³F₄ transition, which is suitable for optical amplification in the second telecommunication window [16].

The refractive indices in fluoroindate glasses doped with trivalent rare earth ions are typically around 1.49 ± 0.02. The thermal stability range of this family in glasses can vary depending on the concentration of their components. It is useful to study these parameters, as well as mechanical and spectroscopic characteristics, to optimize these materials for photonic applications. Also, it is useful to examine the effect of rare earth ions on these properties. In this work, we analyze the changes to the refractive index, thermal stability range and any potential laser transitions induced by substituting Ba for P in fluoroindate glasses doped with Nd³⁺ and Er³⁺ ions. We use absorption and luminescence spectroscopy and dif-

* Corresponding author. Tel.: +57 76 343495; fax: +57 76 343495.
E-mail address: aflorez@uis.edu.co (A. Flórez).

ferential scanning calorimeter (DSC) measurements in samples of good optical quality. It is important to characterize the fluorindate sample doped with Nd^{3+} , and as by adjusting the concentration of P in our samples, Ω_2 can change from a negative to a positive value.

2. Experimental analysis

2.1. Sample preparation

In this work, the goal is to analyze the effect of substituting BaF_2 for P_2O_5 in a fluorindate glass (FI): $35\text{InF}_3-20\text{ZnF}_2-(16-x)\text{BaF}_2-x\text{P}_2\text{O}_5-20\text{SrF}_2-6\text{GaF}_3-2\text{NaF}-\text{REF}_3$; $x=4.0(\text{FIP4})$; $8.0(\text{FIP8})$; $12.0(\text{FIP12})$; $16.0(\text{FIP16})$; and $\text{RE}=\text{Er}$, Nd ; 1.0 mol% concentration. The samples were prepared by using powders of oxides and fluorides of the highest available purity. Given the hygroscopic characteristics of fluorides and the strong instability of P_2O_5 in a moist environment, the samples were prepared in a chamber under a dry argon atmosphere. The transformation of the oxide into fluoride was accomplished by mixing the lanthanide, indium, gallium and phosphorus oxides with an excess ($2\times$ the stoichiometric amount) of ammonium bifluoride (NH_4HF_2), and then heating the mixture in a platinum crucible at 400°C for 3 h and 450°C for 1 h for refining [17]. Then, the fluoride compounds were mixed and melted in a platinum crucible in a tubular furnace at 750 and 850°C to refine and homogenise the liquid. The melt was then cast into a brass mould pre-heated to $\approx 260^\circ\text{C}$ and cooled at room temperature. The samples obtained showed good optical quality after cutting and polishing.

Density measurements were carried out using the Archimedes method in distilled water; the results varied between $5.02\text{--}4.76$ and $4.98\text{--}4.67\text{ g cm}^{-3} \pm 0.2$ for Nd^{3+} and Er^{3+} , respectively. The refractive indices were measured using an Abbe refractometer; the contact liquid we used was 1-bromonaphthalin ($\text{C}_{10}\text{H}_7\text{Br}$). The results varied from 1.49 for FI to 1.56 for FIP16 doped with Nd^{3+} and 1.57 for FIP16 doped with Er^{3+} .

2.2. Absorption and luminescence spectra

Absorption spectra were recorded for all samples at room temperature on a double-beam UV-vis-NIR spectrophotometer (Jasco V-7200) in the spectral range of $300\text{--}3300\text{ nm}$ for the samples doped with Nd^{3+} , and a range of $300\text{--}2000\text{ nm}$ for samples doped with Er^{3+} . Given that the absorption path length changes from 0.16 to 0.31 cm in Nd^{3+} doped samples and from 0.13 to 0.24 cm in the Er^{3+} doped samples, the spectra for all samples, after subtracting the base line, were normalized in the optical density by their path length. Figs. 1 and 2 show the spectra for the three samples Er^{3+} and Nd^{3+} doped samples (FI, FIP4, and FIP8).

The oscillator strength was obtained from the area under the absorption band with the wavelength (λ) corresponding to the band baricenter using:

$$f = \frac{4.318 \times 10^{-9}}{C l^2} \int K(\lambda) d\lambda \quad (1)$$

where $K(k)$ is the spectral absorption coefficient, $C[\text{mol/l}]$ is the concentration of the rare earth ion, and $l[\text{cm}]$ is the path length.

The luminescence spectrum was obtained using a 150-W Xenon lamp and an appropriate filter. The emission from the sample was focused with an optical fiber on the entrance slit of a $490 \pm 5\text{ nm}$ (DK480 of 0.5-m Spectral Products) monochromator. The emission was detected with a photomultiplier tube (Hamamatsu H5783-04) in the spectral range from 185 to 850 nm at room temperature, and recorded by a

Fig. 1. Normalized absorption spectra at room temperature in the spectral range from 300 to 900 nm from ground state $^4\text{I}_{15/2}$ for all the samples doped with 1.0 mol% of Er^{3+} ions.

Fig. 2. Normalized absorption spectra at room temperature in the spectral range from 300 to 1000 nm from ground state $^4\text{I}_{9/2}$ for all the samples doped with 1.0 mol% of Nd^{3+} ions.

computerized data acquisition system. Fig. 3 shows the recorded spectrum for all the Er^{3+} doped samples.

2.3. DSC measurements

The DSC measurements were recorded for the Nd^{3+} doped samples using a Differential Scanning Calorimeter (Q10 V8.1) from TA instruments at temperature range, from 30 to 600°C , under an inert atmosphere of N_2 . The mass of the samples was 9.0 mg , and the heating rate was $10^\circ\text{C min}^{-1}$. Fig. 3 shows the DSC curves for all samples.

3. Theoretical background

For trivalent lanthanide rare earth ions, the bands observed from absorption spectra correspond to intraconfigurational f-f transitions; the majority of these are induced electric dipole, and only a few of magnetic dipole transitions have been reported in these ions [15,18]. According to the Judd-Ofelt theory [13,14], the oscillator strength of a transition between two multiplets is given by:

$$f = \frac{8\pi^2 m c \sigma}{3 h (2J+1)} \chi \sum_{\lambda=2,4,6} \Omega_{\lambda} (f^N \Psi' J' || U^{(\lambda)} || f^N \Psi J)^2 \quad (2)$$

where m is the mass of the electron, c is the velocity of light, h is Planck's constant, σ is the mean energy (in cm^{-1}) for the tran-

Fig. 3. Normalized luminescence spectra at room temperature in the spectral range from 500 to 800 nm for all the samples doped with 1.0 mol% of Er^{3+} ions. Excitation of the $^4\text{F}_{7/2}$ state is centered at 490 nm .

sition, and the factor $\chi = (n^2 + 2)^2/9n$ takes into account that the lanthanide ion is not in vacuum, but in a dielectric medium of refractive index n . $U^{(\lambda)}$ represents the squared reduced matrix elements $(f^N \psi' J' || U^{(\lambda)} || f^N \psi J)^2$ of rank λ . Given that the matrix elements are virtually host independent, in this work we use the values reported by Carnall and co-workers for the trivalent lanthanide ions Er^{3+} and Nd^{3+} in LaF_3 [19].

The intensity parameters Ω_λ can be determined by a standard-least-square fitting method from the measured oscillator strengths by using Eq. (1). The quality of the fit is given by the magnitude of the root-mean-square ($\delta_{\text{r.m.s.}}$) deviation, as defined by:

$$\delta_{\text{r.m.s.}} = \left[\frac{\sum (f_{\text{Cal}} - f_{\text{Exp.}})^2}{(q - p)} \right]^{1/2} \quad (3)$$

where q is the equation number and p the parameter number.

Although the Judd–Ofelt model has been successful for the majority of lanthanide rare earths ions, there are ions for which the model does not work: Pr, Sm and Tb [20,21]. The model's fundamental assumptions about energy differences cause the most difficulty; in particular, the theory assumes that the difference in energy between $4f^N$ and $4f^{N-1}5d$ in all ions is large. Noting the energy differences (in cm^{-1}) in lanthanides: Pr (45,600), Nd (55,900), Sm (59,500), Eu (68,500), Tb (46,500), Dy (58,900), Ho (64,100), Er (64,200) and Tm (64,000) [22]; shows the inconsistency of the model, because Pr and Tb have similar values. This problem is reflected in the negative values taken by Ω_2 reported for Pr, Sm and Tb; these results are in contradiction with the definition of the Ω_λ parameters.

From the Judd–Ofelt intensity parameters Ω_λ , several radiative properties of the lanthanide ions can be calculated, such as the spontaneous emission coefficient, $A(\psi J, \psi' J') = A_{J J'}$. This coefficient is given by the expression

$$A_{J J'} = \frac{64\pi^4 \sigma^3}{3h(2J + 1)} \chi S_{\text{ed}} \quad \text{with} \quad (4)$$

$$S_{\text{ed}} = e^2 \sum_{\lambda=2,4,6} \Omega_\lambda (f^N \psi J' || U^\lambda || f^N \psi J)^2$$

where $\chi = n(n^2 + 2)^2/9$ is the effective field correction at a well-localized center in a medium of isotropic refractive index n , and S_{ed} is the electric dipole line strength. Here, we do not take into account the magnetic dipole transitions. Once all emission probabilities that depopulate an initial level $2S+1L_J$ have been calculated, they can be used to determine the rate at which that level is depopulated. This rate is given by the radiative lifetime $\tau_R(\psi J)$ defined as:

$$\tau_R(\psi J) = \frac{1}{\sum_{\psi' J'} A_{J J'}} \quad (5)$$

4. Results and discussion

4.1. Absorption spectra

Figs. 1 and 2 show the normalized absorption spectra for samples doped with Er^{3+} and Nd^{3+} . The bands shown correspond to intraconfigurational f–f transitions that occur from the ground state $^4I_{15/2}$ for Er^{3+} and $^4I_{9/2}$ for Nd^{3+} . In the trivalent lanthanides, the free ion is only slightly perturbed by the crystal-field of the host. Each free-ion level, characterized by the total angular momentum J , is split by this field into a manifold of the more than $(2J + 1)$ components. The splitting is usually not larger than 300 cm^{-1} . When we deal with ions in glasses, we neglect the site symmetry of the individual ions, such that the 41 electronic states that correspond to the configuration $4f^{11}$ of Er and the 41 states for the configuration $4f^3$

of Nd are reduced to 13 for Er and 19 for Nd. In order to label transitions that correspond to bands found from recorded absorption spectra, twelve bands for both ions in the ranges 300–1700 nm for Er^{3+} and 300–2600 nm for Nd^{3+} , we take the values reported by Carnall for these ions [23]. In the range shown in Figs. 1 and 2, the effect of the crystal field is larger in Er^{3+} than in Nd^{3+} . In that range, in Er^{3+} there is an overlapping of two components ($^4F_{5/2, 3/2}$), whereas in Nd^{3+} for the same range there are five overlapping bands, four of which having two components: $^4F_{5/2}^*$ and $^2H_{9/2}$; $^4F_{7/2}$ and $^4S_{3/2}^*$; $^2K_{13/2}$ and $^4G_{7/2}^*$; the hypersensitive transition, $^4G_{5/2}^*$ and $^2G_{7/2}$; and the four single components $^2K_{15/2}$, $^2G_{9/2}^*$, $^2D_{3/2}$ and $^4G_{11/2}$. The overlap corresponding to the $^4G_{5/2}^*$ (hypersensitive) and $^2G_{7/2}$ bands centered at 571 and 573 nm, respectively, is very difficult to resolve even in crystal hosts. The effect on the absorption spectra by exchanging BaF_2 with P_2O_5 is not significant. Given this, the nominal concentration of doping was the same (1.0 mol%) for all glasses. The hypersensitive transitions in Er^{3+} ($^4I_{15/2} \rightarrow ^2H_{11/2}$; $^4I_{11/2} \rightarrow ^4G_{11/2}$) and Nd^{3+} ($^4I_{9/2} \rightarrow ^4F_{5/2}^*$, $^2H_{9/2}$) are clearly identified by their strong intensity, and these transitions indicate that in these hosts the Er^{3+} and Nd^{3+} ions are not located at symmetric centers [15].

4.2. Oscillator strength and intensity parameters

A complicated problem with rare earth spectroscopy is the measurement and interpretation of the intensities of absorption bands. This problem is even more prevalent when ion hosts are glass materials. Given that the bands in glasses do not have a Gaussian shape, they exhibit inhomogeneous broadening associated with a variation of the crystal field from site to site, and the intensities must be measured using the area of the absorption bands. The intensity of spectral lines is measured using the oscillator strength given by Eq. (1). According to the Judd–Ofelt theory, the oscillator strength is a function of three phenomenological parameters Ω_λ , with $\lambda = 2, 4, 6$, and can be represented as a linear combination of these parameters. These parameters were determined by the method of least-square fitting using Eq. (2). The parameters are a function of the even and odd crystal field parameters, intraconfigurational radial integral and energy separation of the $4f^N$ states, and the opposite parity configurations. Hence, Ω_λ are dependent on the oscillator strength and are found to vary from site to site. In order to evaluate the validity of the intensity parameters Ω_λ obtained by the fitting, we calculate the root-mean-square values, $\delta_{\text{r.m.s.}}$, using Eq. (3). Tables 1–3 include the results of these calculations for all samples. From Table 1, the best fits are obtained in the Er^{3+} doped samples FIP12 and FIP16, (0.21).

From Table 1, the biggest difference between calculated and experimental oscillator strengths for all Er^{3+} doped samples was obtained in the transition corresponding to $^4I_{15/2} \rightarrow ^4I_{13/2}$ centered at 1519 nm; this difference is not shown in Fig. 1, but decreases with an increasing concentration of P from 0.84 in FI to 0.39 in FIP16. Similarly, the deviation Δ of the hypersensitive transitions varied from 0.14 and 0.25 for FI to 0.10 and 0.16 for FIP16. These changes appear to be associated with the increasing number of F–P bonds around of the Er^{3+} ions [5].

An important aspect of Table 2 is that the $^4I_{9/2} \rightarrow ^4D_{3/2}$ transition is not included in the calculation of the oscillator strength, because with it, $\Omega_2 < 0$ in the FI sample, as is shown in Table 3. Although, until now, there has not been a report of negative values for Ω_2 in Nd^{3+} in any host, this phenomenon can be understood given the ions' proximity to Pr^{3+} in the lanthanide series. Also, the problem has been associated with the small energy difference between the $4f^N$ and $4f^{N-1}5d$ configurations relative to the other ions in which Judd–Ofelt theory is successful [15]. Now, to avoid negative values for the Ω_2 parameter, various authors [16,24–26] often omit

Table 1

Calculated and experimental oscillator strength, $(f_{\text{Cal.}}, f_{\text{Exp.}}) \times 10^{-6}$, deviation, $(f_{\text{Cal.}} - f_{\text{Exp.}} = \Delta) \times 10^{-6}$ and root-mean-square deviation $\delta_{\text{r.m.s.}} \times 10^{-6}$, for all samples doped with Er^{3+} .

σ (nm)	FI			FIP4			FIP8			FIP12			FIP16		
	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ
356	0.28	0.19	0.09	0.28	0.03	0.25	0.26	0.08	0.18	0.24	0.06	0.18	0.24	0.03	0.21
364	0.74	0.63	0.11	0.66	0.41	0.25	0.71	0.48	0.23	0.71	0.51	0.20	0.81	0.53	0.28
378*	3.36	3.50	0.14	3.29	3.36	0.07	3.62	3.68	0.06	3.75	3.83	0.08	4.36	4.46	0.10
406	0.47	0.30	0.17	0.47	0.26	0.21	0.43	0.28	0.15	0.39	0.31	0.08	0.40	0.37	0.03
449	0.63	0.39	0.24	0.65	0.36	0.29	0.57	0.47	0.10	0.52	0.43	0.09	0.52	0.43	0.09
487	1.14	0.86	0.28	1.13	0.82	0.31	1.05	0.93	0.12	0.99	0.84	0.15	1.04	0.93	0.11
521*	1.90	1.65	0.25	1.86	1.74	0.12	2.04	1.95	0.09	2.11	1.96	0.15	2.46	2.30	0.16
542	0.33	0.21	0.12	0.34	0.18	0.16	0.30	0.19	0.11	0.27	0.17	0.10	0.27	0.15	0.12
653	0.85	0.98	0.13	0.75	0.98	0.23	0.80	1.01	0.21	0.80	1.00	0.20	0.91	1.16	0.25
798	0.08	0.10	0.02	0.05	0.10	0.05	0.08	0.09	0.01	0.09	0.08	0.01	0.12	0.10	0.02
974	0.36	0.14	0.22	0.37	0.26	0.11	0.33	0.23	0.10	0.31	0.25	0.06	0.31	0.21	0.10
1519	0.80	1.64	0.84	0.82	1.70	0.88	0.74	1.22	0.48	0.68	1.12	0.44	0.69	1.08	0.39
$\delta_{\text{r.m.s.}}$	0.34			0.37			0.22			0.21			0.21		

* Hypersensitive transitions.

Table 2

Calculated and experimental oscillator strength, $(f_{\text{Cal.}}, f_{\text{Exp.}}) \times 10^{-6}$, deviation, $(f_{\text{Cal.}} - f_{\text{Exp.}} = \Delta) \times 10^{-6}$ and root-mean-square deviation $\delta_{\text{r.m.s.}} \times 10^{-6}$, for all samples doped with Nd^{3+} .

σ (nm)	FI			FIP4			FIP8			FIP12			FIP16		
	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ	$f_{\text{Cal.}}$	$f_{\text{Exp.}}$	Δ
353	–	3.23		2.36	2.79	0.43	1.43	1.06	0.37	2.27	2.23	0.04	1.80	1.32	0.48
426.5	0.32	0.23	0.09	0.34	0.16	0.18	0.19	0.11	0.08	0.32	0.17	0.15	0.25	0.30	0.05
466	0.66	0.77	0.11	0.73	0.58	0.15	0.53	0.58	0.05	0.69	0.80	0.11	0.60	0.74	0.14
518	2.62	3.06	0.44	2.66	2.84	0.18	2.15	2.82	0.67	2.82	3.40	0.58	2.50	3.14	0.64
576.5*	5.30	5.27	0.03	5.51	5.50	0.01	5.65	5.60	0.05	6.70	6.66	0.04	6.61	6.56	0.05
628	0.08	0.05	0.03	0.08	0.04	0.04	0.07	0.03	0.04	0.09	0.07	0.02	0.08	0.05	0.03
679	0.29	0.28	0.01	0.29	0.28	0.01	0.28	0.25	0.03	0.32	0.29	0.03	0.30	0.29	0.01
740.5	3.76	3.68	0.08	3.62	3.53	0.09	3.75	3.50	0.25	4.16	4.02	0.14	3.99	3.72	0.27
797.5	3.70	3.73	0.03	3.65	3.54	0.11	3.31	3.48	0.17	3.99	4.15	0.16	3.65	3.75	0.10
865.5	1.24	0.66	0.58	1.28	0.38	0.90	0.85	0.66	0.19	1.26	0.49	0.77	1.03	1.09	0.06
1711.5	0.10	0.01	0.09	0.10	0.01	0.09	0.10	0.01	0.09	0.11	0.01	0.10	0.11	0.01	0.10
2458	0.76	0.68	0.08	0.73	1.61	0.88	0.76	0.74	0.02	0.84	0.54	0.30	0.81	1.06	0.25
$\delta_{\text{r.m.s.}}$	0.27; 0.34*; 0.34**			0.46			0.28			0.35			0.30		

0.27, 0.34*, and 0.34** correspond to the exclusion of the $^4\text{I}_{9/2} \rightarrow ^4\text{D}_{3/2}$; $^4\text{I}_{9/2} \rightarrow ^4\text{G}_{5/2}$; $^2\text{G}_{7/2}$ and $^4\text{I}_{9/2} \rightarrow ^2\text{K}_{13/2}$, $^4\text{G}_{7/2}$ transitions, respectively; (*) denotes a hypersensitive transition.

in the least-squares fitting in the Judd–Ofelt treatment of the $^3\text{P}_2$ state of Pr^{3+} , which corresponds to one transition. In this work, from the identified transitions, we omit several transitions, one at a time, and for Nd^{3+} doped samples, the results are shown in Table 4. Table 4 shows that there are several bands that give positive values of Ω_2 when different transitions are omitted; the exclusion of the hypersensitive transition, as suggested by most authors, is only one option. Additionally, in all cases treated in this work, the quality of fit as measured by the deviation $\delta_{\text{r.m.s.}}$ was similar for both bands calculated for all transitions and when calculated with some transitions omitted. Also, from Table 2, it is important to note that the fit corresponding to the hypersensitive transition is very good, and for all samples the deviation Δ changes from 0.01 to 0.05. The best fit ($\delta_{\text{r.m.s.}} = 0.27$) was obtained when we omitted the $^4\text{I}_{9/2} \rightarrow ^4\text{D}_{3/2}$ transition in the FI sample; this value is similar to that of the FIP8 sample ($\delta_{\text{r.m.s.}} = 0.28$).

Table 3 gives the intensity parameters $\Omega_{2,4,6}$ for all samples doped with Er^{3+} and Nd^{3+} . For the Er^{3+} doped samples it is impor-

tant to note that the values of Ω_2 in all of glasses are larger than $\Omega_{4,6}$. This behavior is not normal according to reports in the literature, as shown in the left part of Table 3. The values of which $\Omega_2 < 2.0$, in Er^{3+} and in Nd^{3+} , show strong covalent bonding, reflecting a high symmetry around the ions in all of the samples [15]. For Nd^{3+} , the right part of Table 3 shows that $\Omega_2 < \Omega_{4,6}$, which are the values normally observed for these parameters; also, the table shows that $\Omega_4 < \Omega_6$, as expected.

Table 4 shows the effect of progressively excluding the following transitions one at a time for a least-square fitting of the conventional Judd–Ofelt calculations: $^4\text{I}_{9/2} \rightarrow ^4\text{I}_{11/2}$; $^4\text{I}_{9/2} \rightarrow ^4\text{F}_{5/2}$; $^2\text{H}_{9/2}$; $^4\text{I}_{9/2} \rightarrow ^4\text{F}_{7/2}$, $^4\text{S}_{3/2}$; $^4\text{I}_{9/2} \rightarrow (^4\text{G}_{5/2}, ^2\text{G}_{7/2})^*$; and $^4\text{I}_{9/2} \rightarrow ^4\text{D}_{3/2}$; $^4\text{I}_{9/2} \rightarrow ^2\text{K}_{13/2}$, $^4\text{G}_{7/2}$. It is observed that the $\Omega_{2,4,6}$ parameters take exactly the same values with or without the $^4\text{I}_{9/2} \rightarrow ^4\text{I}_{11/2}$ or $^4\text{I}_{9/2} \rightarrow ^4\text{F}_{5/2}$, $^2\text{H}_{9/2}$ transitions. Also, it is clear that besides the hypersensitive transition there are other transitions which help in avoiding the negative values of Ω_2 .

Table 3

Intensity parameters Ω_λ for all samples doped with Er^{3+} and Nd^{3+} , including all transitions identified from absorption spectra.

$\Omega_\lambda \times 10^{-20} \text{ cm}^2$	Er^{3+}					Nd^{3+}				
	FI	FIP4	FIP8	FIP12	FIP16	FI	FIP4	FIP8	FIP12	FIP16
Ω_2	1.2048	1.2545	1.3002	1.2905	1.4673	−0.0360	0.4171	1.1554	0.9222	1.2299
Ω_4	0.3755	0.2098	0.3761	0.4181	0.5556	3.3238	2.7038	1.5148	2.4404	1.8851
Ω_6	0.8997	0.9172	0.8013	0.7106	0.7044	2.5647	2.6157	2.7524	2.9074	2.8186

Table 4Intensity parameters for the all Nd³⁺ doped samples, and transitions identified from absorption spectra that were excluded of the calculations of Ω_λ .

Transitions excluded of the calculates	$\Omega_\lambda \times 10^{-20} \text{ cm}^2$	FI	FIP4	FIP8	FIP12	FIP16
$^4\text{I}_{9/2} \rightarrow ^4\text{I}_{11/2}$	Ω_2	−0.0574	0.3963	1.1854	0.9493	1.2465
	Ω_4	3.3520	2.7311	1.4752	2.4047	1.8631
	Ω_6	2.6161	2.6657	2.6802	2.8422	2.7786
$^4\text{I}_{9/2} \rightarrow ^4\text{F}_{5/2}^*, ^2\text{H}_{9/2}$	Ω_2	−0.0574	0.3963	1.1854	0.9493	1.2465
	Ω_4	3.3520	2.7311	1.4752	2.4047	1.8631
	Ω_6	2.6161	2.6657	2.6802	2.8422	2.7786
$^4\text{I}_{9/2} \rightarrow ^4\text{F}_{7/2}, ^4\text{S}_{3/2}^*$	Ω_2	−0.0734	0.4557	1.2562	0.9784	1.3354
	Ω_4	3.4046	2.6204	1.2968	2.3190	1.6569
	Ω_6	2.4034	2.7819	3.1872	3.1497	3.2738
$^4\text{I}_{9/2} \rightarrow (^4\text{G}_{5/2}^*, ^2\text{G}_{7/2}^*)$	Ω_2	0.9280	1.5917	5.9601	4.9646	5.6948
	Ω_4	3.2555	2.6205	1.1744	2.1540	1.5687
	Ω_6	2.5563	2.6054	2.7104	2.8721	2.7796
$^4\text{I}_{9/2} \rightarrow ^4\text{D}_{3/2}$	Ω_2	0.4056	0.8951	0.7402	0.5237	0.8504
	Ω_4	2.5944	1.9144	2.2004	3.0995	2.4859
	Ω_6	2.7505	2.8167	2.5777	2.7315	2.8559
$^4\text{I}_{9/2} \rightarrow ^2\text{K}_{13/2}, ^4\text{G}_{7/2}^*$	Ω_2	0.0011	0.4628	1.3244	1.0637	1.3882
	Ω_4	3.2559	2.6203	1.2062	2.1820	1.5960
	Ω_6	2.5622	2.6126	2.7263	2.8979	2.8079

(·)* Hypersensitive transition.

Table 5 shows for all Er³⁺ doped samples the values of the spectroscopic parameters for the $^4\text{F}_{7/2}$ state and its low-lying relaxation states up to the ground state $^4\text{I}_{15/2}$, obtained from absorption spectra intensity parameters $\Omega_{2,4,6}$ and Eqs. (4) and (5). The table gives the values of all probabilities for only the FI sample. For the other samples, we include only the most significant probability values. From these values we note only a small effect of exchanging Ba for P. For FI and FIP4 samples, there is practically no change in $A_{J'}$ and τ_R .

4.3. Luminescence of the $^4\text{F}_{7/2}$ state excitation

Fig. 3 shows the luminescence spectra of Er³⁺ doped samples excited in the $^4\text{F}_{7/2}$ state centered in around 490 nm. Given that the spectra is normalized by the path length, and that the concentration

Table 5Transitions, energy, σ , transition probability, $A_{J'}$ and radiative lifetime τ_R for all Er³⁺ doped samples.

Simple doped Er ³⁺	Transition	$\sigma \text{ (cm}^{-1}\text{)}$	$A_{J'}$	$\tau_R \text{ (ms)}$
FI	$^4\text{F}_{7/2} \rightarrow ^2\text{H}_{11/2}$	1340	0.40	0.46
	$^4\text{F}_{7/2} \rightarrow ^4\text{S}_{4/2}$	2084	1.49	
	$^4\text{F}_{7/2} \rightarrow ^4\text{F}_{9/2}$	5220	23.49	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{9/2}$	8003	84.65	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{11/2}$	10267	178.74	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{13/2}$	13951	448.44	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{15/2}$	20534	1429.95	
FIP4	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{9/2}$	8003	84.56	0.46
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{11/2}$	10267	178.56	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{13/2}$	13951	447.97	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{15/2}$	20534	1428.46	
FIP8	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{9/2}$	8003	81.13	0.48
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{11/2}$	10267	171.31	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{13/2}$	13951	429.78	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{15/2}$	20534	1370.04	
FIP12	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{9/2}$	8003	78.03	0.50
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{11/2}$	10267	164.76	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{13/2}$	13951	413.17	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{15/2}$	20534	1318.11	
FIP16	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{9/2}$	8003	84.37	0.46
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{11/2}$	10267	178.15	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{13/2}$	13951	446.96	
	$^4\text{F}_{7/2} \rightarrow ^4\text{I}_{15/2}$	20534	1425.22	

of doping is the same in all samples (1.0 mol%), we note that the effect of exchanging BaF₂ for P₂O₅ in the $^4\text{S}_{3/2}$ transition is largest for the FI sample, smaller for the FIP4 sample, and smallest for the FIP8 sample; we also note quenching in the intensity luminescence in the FIP12 and FIP16 samples. Even for FIP8 the luminescence has an important value. Also, for FIP4 the transition from $^4\text{F}_{9/2}$ gives a nontrivial luminescence.

4.4. DSC measurements

Fig. 4 shows the differential scanning calorimeter graphs for the Nd³⁺ doped glasses. We have assumed that only minimal changes might appear in the results analyzing the graphs for only one ion. From the graphs we obtained T_g , T_x and ΔT . It is observed that in the temperature range scanned, there is little tendency to form crystalline phases in the FIP16 sample. The stability range obtained for the samples was: 121.7 °C (FI); 155.37 °C (FIP4); 167 °C (FIP8); 114.11 °C (FIP12) and 177.17 °C (FIP16) all with ± 5.0 °C. From the results we observe that the sample with the largest content of P (FIP16) presents the largest stability range. Only the analysis of FIP4 can take into account the results of the previous samples; we find that 155.37 ± 5.0 °C, ($T_g = 310.36$ °C and $T_x = 465.73$ °C).

Fig. 4. DSC measurements in the temperature range from 30 to 600 °C for all of the samples doped with 1.0 mol% of Nd³⁺.

5. Conclusions

This study shows that fluoroindate glasses modified and optimized with lanthanide ions have potential for laser applications. Concentrations larger than 8.0 mol% have a strong tendency to produce quenching in the fluoroindate glasses. The presence of P in the fluoride glasses can contribute to increasing the thermal stability. In that sense, of the glasses analyzed in this work, the sample with 4.0 mol% of P_2O_5 showed the best properties. The Ω_2 of Nd^{3+} ion in fluoroindate glasses shows the tendency towards negative Ω_2 values. Since the values are normally take $\Omega_2 \leq 2$ in these glasses, we conclude that there is high symmetry and covalence around the rare earth ions. Finally, in the Er^{3+} doped samples is noted that, $\Omega_2 > \Omega_{4,6}$, which is unusual in these host materials.

Acknowledgements

This work was partially supported by The Excellence Center for Novel Materials – ECNM, under Contract No. 043-2005 subscribed with Colciencias; and the Foundation for the Promotion of Research and Technology of the Bank of the Republic.

References

- [1] Marcel Poulain, J. Non-Cryst. Solids 184 (1995) 103–108.
- [2] F. Auzel, J. Alloys Compd. 275–277 (1998) 692–696.
- [3] M. Mortier, P. Goldner, P. Féron, G.M. Stephan, H. Xu, Z. Cai, J. Non-Cryst. Solids 326 and 327 (2003) 505–509.
- [4] Jean-Luc Adam, J. Fluorine Chem. 107 (2001) 265–270.
- [5] Joanna Pisarska, Bozena Kaczmarczyk, Zbigniew Mazurak, Micha Zelechower, Tomasz Goryczka, Wojciech A. Pisarski, Physica B 388 (2007) 331–336.
- [6] Fluoride Glass for Optical Fibers, P.W. France–Blackie, London, 1990.
- [7] J. Schneider, C. Carbonnier, U.B. Unrau, Appl. Opt. 36 (1997) 8595.
- [8] R. Reisfeld, C.K. Jorgensen, Excited State Phenomena in Vitreous Materials, Handbook on the Physics and Chemistry of Rare Earths, Elsevier Science Publishers, 1987 (Chapte.58).
- [9] J.H. Campbell, T.I. Suratwala, J. Non-Cryst. Solids 263&264 (2000) 318–341.
- [10] J.H. Campbell, 25 years of laser glass development leading to a 1.8 MJ, 500 TW laser for fusion ignition, Lawrence Livermore National Laboratory Report, UCRL-JC-129507, 1998, p. 1.
- [11] C.K. Jayasankar, R. Balakrishnaiah, V. Venkatramu, A.S. Joshi, A. Speghini b, M. Bettinelli, J. Alloys Compd. 451 (2008) 697–701.
- [12] J. Pisarska, W. Ryba-Romanowski, G. Dominiak-Dzik, T. Goryczka, W.A. Pisarski, J. Alloys Compd. 451 (2008) 223–225.
- [13] B.R. Judd, Phys. Rev. B 127 (1962) 750.
- [14] G.S. Ofelt, J. Chem. Phys. 37 (1962) 511.
- [15] R.D. Peacock, Struct. Bond. 22 (1975) 83.
- [16] R.S. Quimby, W.J. Miniscalco, J. Appl. Phys. 75 (1) (1994) 613–615.
- [17] M. Poulain, G. Mazé, Chemtronics 3 (1998) 77.
- [18] C. Görller-Walrand, K. Binnemans, Spectral intensities of f–f transitions, in: K.A. Gschneidner Jr., L. Eyring (Eds.), Handbook on the Physics and Chemistry of Rare Earths, vol. 25, 1998, p. 101 (ch. 167, North-Holland, Amsterdam).
- [19] W.T. Carnall, P.R. Fields, K. Rajnak, J. Chem. Phys. 49 (10) (1968) 4424–4442.
- [20] A. Flórez, A. Herrera, M. Flórez, Phys. Stat. Sol. (c) 4 (11) (2007) 4156–4164.
- [21] A. Florez, M. Brik, O. Plata, J. Mater. Sci.: Mater. Electron. 20 (2009) S230–S234.
- [22] R. Reisfeld, C.K. Jorgensen, Laser and Excited States of Rare Earth, Springer Verlag, Berlin, 1977.
- [23] W.T. Carnall, H. Crosswhite, H.M. Crosswhite, Energy level structure and transitions probabilities of the trivalent lanthanides in LaF_3 , Argonne National Laboratory, Special Report, 1977.
- [24] M. Eyal, E. Greemberg, R. Reisfield, N. Spector, Chem. Phys. Lett. 117 (2) (1985) 108.
- [25] W. Seeber, E.A. Downing, L. Hesselink, M.M. Fejer, D. Ehr, J. Non-Cryst. Solids 189 (1995) 218–226.
- [26] H. Inoue, K. Soga, A. Makishima, J. Non-Cryst. Solids 325 (2003) 282–294.

Emission properties of Sm(III) complexes having remarkably deep-red emission band

Hideki Kawai^{a,*}, Chen Zhao^a, Shin-ichi Tsuruoka^b, Takahiko Yoshida^b,
Yasuchika Hasegawa^c, Tsuyoshi Kawai^c

^a Research Institute of Electronics, Shizuoka University, 3-5-1 Johoku, Naka-ku, Hamamatsu, Shizuoka 432-8011, Japan

^b USHIO Chemix Co. Ltd., 2252-1 Goudo, Omaezaki, Shizuoka 437-1613, Japan

^c Graduate School of Materials Science, Nara Institute of Science and Technology, 8916-5 Takayama, Ikoma, Nara 630-0192, Japan

ARTICLE INFO

Article history:

Received 1 June 2008

Received in revised form 12 August 2008

Accepted 1 September 2008

Available online 18 November 2008

Keywords:

Sm(III) complexes

Coordination structure

Quantum yield

ABSTRACT

Novel Sm(III) complexes were synthesized by the reaction of hexafluoroacetylacetonato (hfa) and triphenylphosphine oxide (TPPO), 2,2'-bipyridine (bpy), 1,10-phenanthroline (phen). Emission bands were observed at "deep-red" region and were attributed to f–f transitions. The branching ratio (electric-dipole transitions 644 nm vs. magnetic dipole transition 598 nm) of the Sm(hfa)₃(TPPO)₂ was much larger than that of Sm(hfa)₃(bpy)₂, Sm(hfa)₃(phen)₂. Those emission properties are due to coordination number and asymmetrical structures of novel Sm(III) complexes.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

White light-emitting diodes (LEDs) attract considerable attention for new illumination, because of high luminance and low power consumption. However those LED devices are unnatural tone, since red light intensity is very weak. The strong red fluorescence is required to achieve a natural tone LED devices. Lanthanide(III) ions have been extensively studied as the attractive luminescent center for display devices [1–4]. The monochromatic emission of lanthanide(III) ion mainly comes from the f–f transition with no Stokes shift [2]. The emission wavelength of lanthanide(III) is in principle independent of the crystal or ligand field because of characteristic feature of the f–f transition. It is difficult to tune to the "deep-red" emission wavelength (around 650 nm) using Eu(III) ions having the red emission (615 nm). Luminescent materials having narrow deep-red emission are strongly desired for high-quality devices [5–8].

According to these photophysical properties, we focused on Sm(III) ions as a luminescent center and reported the emission properties of Sm(III) complexes having nine and ten coordination structures [9,10]. The Sm(III) complexes with characteristic asymmetric structures are expected to have increased radiation

probability and emission quantum yields. In the present study, we report the Sm(III) complexes having remarkably deep-red emission for developing luminescent materials. Sm(III) complexes were synthesized by the reaction of hexafluoroacetylacetonato (hfa) and triphenylphosphine oxide (TPPO), 2,2'-bipyridine (bpy), 1,10-phenanthroline (phen) (Fig. 1). The relationship between ligands structures and emission properties is demonstrated in organic solutions.

2. Experimental

2.1. Materials

Samarium(III) acetate tetrahydrate (99.9%), triphenylphosphine oxide and polystyrene beads were purchased from Wako Pure Chemical Industries Ltd. Hexafluoroacetylacetonato, 2,2'-bipyridine, 1,10-phenanthroline, were obtained from Tokyo Kasei Organic Chemicals. All other chemicals were reagent grade and were used as received.

2.2. Preparation of samarium(III) complexes

Tris(hexafluoroacetylacetonato) samarium(III) bis(triphenylphosphine oxide): Sm(hfa)₃(TPPO)₂ was prepared by the reaction of between Sm(hfa)₃(H₂O)₂ and the triphenylphosphine oxide (TPPO) in methanol under reflux for 6 h. The reaction mixture was concentrated using a rotary evaporator. Recrystallization by addition of excess hexane solution produced crude crystals, which were washed in toluene several times. Recrystallization from hot methanol gave white crystals in 45%.

Tris(hexafluoroacetylacetonato) samarium(III) bis(2,2'-bipyridine): Sm(hfa)₃(bpy)₂ and tris(hexafluoroacetylacetonato) samarium(III) bis(1,10-phenanthroline): Sm(hfa)₃(phen)₂ were also prepared by the reaction of Sm(hfa)₃(H₂O)₂ and 2,2'-bipyridine, 1,10-phenanthroline. Sm(hfa)₃(H₂O)₂ was dissolved of acetonitrile

* Corresponding author. Tel.: +81 53 478 1653; fax: +81 53 478 1653.
E-mail address: rohkawa@ipc.shizuoka.ac.jp (H. Kawai).

Fig. 1. Chemical structures of Sm(III) complexes.

solutions by stirring at 0 °C. 2,2'-Bipyridine and 1,10-phenanthroline in acetonitrile solutions were added dropwise to the above solutions and reacted at 0 °C for 2 h, respectively. The reaction mixtures were concentrated using a rotary evaporator. Reprecipitation by addition of excess hexane solution produced crude crystals, which were washed in toluene several times. Recrystallization from hot methanol/distilled water gave white crystals in 30% ($\text{Sm(hfa)}_3(\text{bpy})_2$) and 56% ($\text{Sm(hfa)}_3(\text{phen})_2$).

2.3. Characterization

Infrared spectra used to identify synthesized materials were obtained with a JASCO FT/IR-410 spectrometer. ^1H NMR data were obtained with a Varian Mercury plus 400 MHz spectrometer and determined using tetramethylsilane (TMS) as an internal standard.

Samples were excited by the third harmonic (355 nm) of a Q-switched Nd:YAG laser (B.M. industries 502DNS, 10 Hz, FWHM 9 ns). The emission spectra were measured using a photo multichannel analyzer system with a CCD detector (Hamamatsu, PMA-11) at room temperature. The emission lifetimes were measured by a nanosecond Nd:YAG laser and a photomultiplier (Hamamatsu, R928). Emission from the sample was guided to the photomultiplier through a monochromator (Jobin-Yvon, H20-VIS). Emission decays were monitored with a digital oscilloscope (Sony Tektronix, TDS540). The emission quantum yields were determined by absolute PL quantum yields measurement system (Hamamatsu, C9930-02).

3. Results and discussion

3.1. Emission spectra

The emission spectra of the Sm(III) complexes in acetone were measured for the excitation at 355 nm ($\pi\text{--}\pi^*$ transition of the hexafluoroacetylaceto ligands). The emission spectra were shown in Fig. 2. The emission bands of $\text{Sm(hfa)}_3(\text{TPPO})_2$ were observed at 562, 598, 644 and 706 nm and are attributed to f–f transition $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{5/2}$ (forbidden transition), $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{7/2}$ (magnetic dipole transition), $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{9/2}$ (electric-dipole transition), $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{11/2}$ (forbidden transition), respectively. The emission spectra in Fig. 2 were normalized with respect to the

Fig. 2. Normalized emission spectra of Sm(III) complexes in acetone solutions (0.01 M) excited at 355 nm.

magnetic dipole transition (598 nm). The emission intensities of electric-dipole transition (644 nm) were extremely enhanced as compared with those of corresponding Sm(III) ions in inorganic glass matrices.

The full width at half maximum (FWHM) of emission peak (644 nm) and the relative intensities of the electric-dipole transition (644 nm) to the magnetic dipole transition (598 nm) are summarized in Table 1. The FWHM and the relative emission intensity of the $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{9/2}$ transition (644 nm) of $\text{Sm(hfa)}_3(\text{TPPO})_2$ was larger than those of $\text{Sm(hfa)}_3(\text{bpy})_2$ and $\text{Sm(hfa)}_3(\text{phen})_2$. The electric-dipole transition is directly linked to the coordination structures related to odd parity. The geometrical structure of $\text{Sm(hfa)}_3(\text{phen})_2$ complex shows ten-coordination square antiprism without inverted center in the crystal field [10]. On the other hand, the $\text{Sm(hfa)}_3(\text{TPPO})_2$ have the eight-coordination structure due to the three hexafluoroacetylaceto (hfa) ligands and two TPPO ligands. The degree of enhanced emission intensities and widths of the Sm(III) complexes should be caused by the coordination structures.

3.2. Emission lifetimes and quantum yields

The emission lifetimes of the Sm(III) complexes in acetone were measured for the excitation at 355 nm. The emission decays were shown in Fig. 3. Single exponential decays indicated the presence of a single luminescent element in acetone. The emission lifetimes were determined from the slope of logarithmic plot of the decay profiles. The emission lifetimes of the $\text{Sm(hfa)}_3(\text{bpy})_2$ and $\text{Sm(hfa)}_3(\text{phen})_2$ complexes were found to be 31 and 37 μs , respectively. However, those of $\text{Sm(hfa)}_3(\text{TPPO})_2$ complex are about three

Table 1

Photophysical properties of Sm(III) complexes in acetone solutions.

	FWHM ^a (nm)	I_{644}/I_{598} ^b	Φ ^c	τ^d (μs)	k_r^e ($\times 10^{-2} \text{ s}^{-1}$)	k_n^e ($\times 10^{-2} \text{ s}^{-1}$)
$\text{Sm(hfa)}_3(\text{TPPO})_2$	10.0	4.2	0.041	97	4.2	99
$\text{Sm(hfa)}_3(\text{bpy})_2$	7.0	3.6	0.016	31	5.2	320
$\text{Sm(hfa)}_3(\text{phen})_2$	8.1	3.2	0.019	37	5.1	270

^a Full width at half maximum of emission peak (644 nm).

^b Relative intensities of the $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{9/2}$ (electric-dipole transition: 644 nm) to the $^4\text{G}_{5/2} \rightarrow ^6\text{H}_{7/2}$ (magnetic dipole transition: 598 nm).

^c Emission quantum yields were measured by the excitation at 480 nm (f–f transition).

^d Emission lifetime.

^e Radiative rates (k_r) and non-radiative rates (k_n) were determined using emission lifetimes and emission quantum yields ($\Phi = k_r/(k_r + k_n)$, $\tau = 1/(k_r + k_n)$).

Fig. 3. Emission decays of Sm(III) complexes in acetone solutions (0.01 M) excited at 355 nm.

times the value of other complexes. The emission quantum yields, the emission lifetimes and calculated emission rate constants are summarized Table 1. There is no significant difference in the radiative rate constant (k_r) of the Sm(III) complexes. In contrast, the non-radiative rate constant (k_{nr}) of the $\text{Sm(hfa)}_3(\text{TPPO})_2$ complex is much smaller than those of $\text{Sm(hfa)}_3(\text{bpy})_2$ and $\text{Sm(hfa)}_3(\text{phen})_2$ complexes. These results suggested that the vibrational relaxation process was inhibited by the coordination structure. Consequently, the emission quantum yield (Φ) of the $\text{Sm(hfa)}_3(\text{TPPO})_2$ (0.041) is two times larger than those of the $\text{Sm(hfa)}_3(\text{bpy})_2$ (0.016) and $\text{Sm(hfa)}_3(\text{phen})_2$ (0.019). The luminescence quantum yield of Pr(III) β -diketonate chelate which excited at ligand absorption band was observed to 0.006% at 605–645 nm [11]. We have already reported that energy transfer efficiency from hfa ligand to Sm(III) ion was found to be 26% in acetone solution [9]. The emission quantum yields of ligand excitation for $\text{Sm(hfa)}_3(\text{TPPO})_2$ complex was estimated to about 1%. The effective emission quantum yield of the Sm(III) complexes would be due to characteristic coordination

structures which lead to radiationless transition via vibrational relaxation.

4. Conclusion

We have successfully designed novel Sm(III) complexes having remarkably deep-red emission, high branching ratio, high emission quantum yields by controlling the symmetry of the complexes with various ligands. Those emission properties are due to coordination number and asymmetrical structures of the Sm(III) complexes. Furthermore, we successfully fabricated the polymer thin films containing the Sm(III) complexes. Luminescent Sm(III) complexes appear to be the suitable candidate for enhancing color rendition of LED devices.

Acknowledgments

The authors would like to thank Dr. Kengo Suzuki (Hamamatsu Photonics K.K.) for quantum yields measurements. This work was supported partly by a Grant-in-Aid for Science Research in a Priority Area “Super-Hierarchical Structures” from the Ministry of Education, Culture, Sports, Science and Technology, Japan.

References

- [1] G. Blasse, B.C. Grabmaier, *Luminescent Materials*, Springer-Verlag, New York, 1994.
- [2] F. Gan, *Laser Materials*, World Scientific, Singapore, 1995, p. 70.
- [3] M.P.O. Wolbers, F.C.J.M. van Veggel, B.H.M. Snellink-Ruel, J.W. Hofdtraat, F.A.J. Geurts, D.N. Reinhoudt, *J. Chem. Soc., Perkin Trans. 2* (1998) 2141.
- [4] J. Fang, C. Choy, D. Ma, E. Ou, *Thin Solid Films* 515 (4) (2006) 2419.
- [5] B. Chu, W.L. Li, Z.R. Hong, F.X. Zang, H.Z. Wei, D.Y. Wang, M.T. Li, C.S. Lee, S.T. Lee, *J. Phys. D: Appl. Phys.* 7 (2006) 4549.
- [6] R. Reyes, M. Cremona, E.E.S. Teotonio, H.F. Brito, O.L. Malta, *Thin Solid Films* 469 (2004) 59.
- [7] R. Reyes, M. Cremona, E.E.S. Teotonio, H.F. Brito, O.L. Malta, *Chem. Phys. Lett.* 396 (2004) 54.
- [8] Y.X. Zheng, L.S. Fu, Y.H. Zhou, J.B. Yu, Y.N. Yu, S.B. Wang, H.J. Zhang, *J. Mater. Chem.* 12 (2002) 919.
- [9] Y. Hasegawa, S. Tsuruoka, T. Yoshida, H. Kawai, T. Kawai, *J. Phys. Chem. A* 112 (2008) 803.
- [10] Y. Hasegawa, S. Tsuruoka, T. Yoshida, H. Kawai, T. Kawai, *Thin Solid Films* 516 (2008) 2704.
- [11] A.I. Voloshin, N.M. Shavaleev, V.P. Kazakov, *J. Lumin.* 93 (2001) 199.

Tb³⁺ and Eu³⁺ luminescence in imidazolium ionic liquids

Todd Hopkins*, Matt Goldey

Department of Chemistry, Butler University, 4600 Sunset Avenue, Indianapolis, IN 46208, United States

ARTICLE INFO

Article history:

Received 30 May 2008

Received in revised form 12 August 2008

Accepted 18 December 2008

Available online 30 December 2008

Keywords:

Luminescence

Rare earth compounds

ABSTRACT

The luminescence properties of Tb³⁺ and Eu³⁺ dissolved in ionic liquids are studied. Solutes in this study include simple lanthanide compounds (e.g., EuBr₃, TbCl₃) and lanthanide complexes (e.g., Eu(dpa)₃³⁻ where dpa = 2,6 pyridine dicarboxylate dianion) dissolved in a 1-butyl-3-methylimidazolium bromide (BMIBr)/water mixture. Emission, excitation, and time-resolved emission measurements are utilized to characterize the spectroscopic properties. It is well established in the literature that the solubility and spectroscopic properties of lanthanides in ionic liquids are highly dependent upon environmental factors including purity, and water content [K. Binnemans, Chemical Reviews (2007); I. Billard, S. Mekki, C. Gaillard, P. Hesemann, C. Mariet, G. Moutiers, A. Labet, J.-C.G. Bünzli, European Journal of Inorganic Chemistry 6 (2004) 1190–1197; S. Samikhanu, K. Mellem, M. Berry, P.S. May, Inorganic Chemistry 46 (2007) 7121–7128]. The water in this ionic liquid system acts as a co-solvent to facilitate solubility of Tb³⁺ and Eu³⁺ compounds. The observed spectroscopic properties of Eu³⁺ and Tb³⁺ salts are expectedly impacted by the high water content, but unexpectedly impacted by the BMIBr ionic liquid. However, the spectroscopy of Eu(dpa)₃³⁻ is unaffected by the presence of BMIBr.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

There have been a number of studies of the solubility, separations and luminescent properties of lanthanide and actinide compounds in ionic liquids [1,4–10]. Many of these studies use ionic liquids based upon alkylmethylimidazolium (RMI⁺) cations with the anion chosen based upon its properties ((e.g., water miscibility, coordination ability) [11]. Because even the hydrophobic (immiscible with water) ionic liquids are somewhat hygroscopic [2], the purity and water content of the ionic liquid play a large role in the properties ((e.g., coordination and spectroscopic) demonstrated by the dissolved metal ions [12]. Because lanthanide ions are particularly sensitive to the presence of water [13], any effort to study lanthanide luminescence in ionic liquids must account for the role of water.

In a study by Billard, et al. [2] of a hydrophobic ionic liquid, 1-butyl-3-methylimidazolium bis(trifluoromethanesulfon)imide (BMITf₂N), the presence of water seems to cause Eu³⁺ to dissolve within aggregates of water in the ionic liquid. However, in a water miscible ionic liquid, 1-butyl-3-methylimidazolium chloride (BMICl), the Eu³⁺ coordination environment and luminescence properties are unaffected by the presence of water up to a 1:1 water to ionic liquid mole ratio [3]. This shows that the coordinating

ability of the anion is more important than water miscibility of the imidazolium ionic liquid for Eu³⁺ luminescence.

In this study, the authors report a spectroscopic study of Eu³⁺ and Tb³⁺ compounds dissolved in a 1-butyl-3-methylimidazolium bromide (BMIBr)/water mixture. The lanthanide compounds studied include some simple salts, EuBr₃·6H₂O, EuCl₃·6H₂O, TbCl₃·6H₂O, and the complex Eu(dpa)₃³⁻ (where dpa = 2,6-pyridinedicarboxylate). These studies were conducted in the binary solvent (BMIBr/water), where the water acts as a co-solvent to facilitate the solubility of the compounds. Excitation, emission and time-resolved emission spectroscopic measurements were used to examine the impact of this binary solvent environment on the Eu³⁺ and Tb³⁺ luminescence. Spectroscopic measurements of the simple chloride and bromide salts were conducted to provide a comparison of BMIBr/water with similar lanthanide salts dissolved in imidazolium ionic liquid systems in the literature [3,4,14]. Spectroscopic measurements of the Eu(dpa)₃³⁻ complexes were conducted to investigate the stability of these complexes in BMIBr/water, because of their potential use as probes of intermolecular interactions (particularly for chiral recognition studies) [15] in ionic liquid solvent systems.

2. Experimental

2.1. Preparation of BMIBr

The BMIBr ionic liquid was prepared by stirring equimolar mixture of methylimidazole and bromobutane under nitrogen at 70 °C for 48 h. The resulting yellow solid was washed with ethyl acetate and stored in a vacuum desiccator. It was found that

* Corresponding author.

E-mail address: tahopkin@butler.edu (T. Hopkins).

the BMIBr solid is so hygroscopic that it picks up enough water when exposed to air to become a liquid at room temperature. Attempts to remove all of the water by degassing were unsuccessful. Therefore, the liquids were prepared by leaving some of the solid out of the dessicator for >24 h. Attempts to remove the yellow color (e.g., mixing with carbon black, using an alumina column) yielded little change [12], and did not affect the behavior (i.e. solute solubility, or spectroscopic interference) of the ionic liquids observed in this study. All of the ionic liquid used in this study is a mixture of BMIBr and water. The water content was 5 wt.% as determined by Karl Fischer titration (Metrohm, Titrino Plus 870) prior to addition of the lanthanide samples.

2.2. Sample preparation

The $\text{EuBr}_3 \cdot 6\text{H}_2\text{O}$, $\text{EuCl}_3 \cdot 6\text{H}_2\text{O}$, and $\text{TbCl}_3 \cdot 6\text{H}_2\text{O}$ were purchased from Aldrich and used as received. The lanthanide salts were dissolved in the BMIBr/water mixture by stirring for ~24 h. Except where otherwise stated, all sample concentrations are ca. 100×10^{-3} molal europium or terbium. In some instances samples were degassed at room temperature to increase solubility. Aqueous samples of EuBr_3 (10×10^{-3} M) were prepared by dissolving the lanthanide salt in water. An aqueous solution of 50×10^{-3} M $\text{Eu}(\text{dpa})_3^{3-}$ was prepared following a standard procedure [15]. The sample of ca. 15×10^{-3} molal $\text{Eu}(\text{dpa})_3^{3-}$ in BMIBr/water was prepared by mixing the appropriate volumes of aqueous $\text{Eu}(\text{dpa})_3^{3-}$ with BMIBr/water. The final water content of this sample was not measured by Karl Fischer titration.

2.3. Spectroscopic measurements

The emission and excitation spectra were recorded using a LS-55 (PerkinElmer) luminescence spectrometer. In order to remove interference by the intrinsic ionic liquid fluorescence, emission and excitation spectra were recorded in phosphorescence mode with a 50 μs delay. Absorption measurements of BMIBr/water were recorded in a Cary 50 spectrophotometer. Luminescence decay measurements were recorded on custom-built instrumentation. The excitation source was a mercury arc lamp passed through a 0.1 M monochromator (Jobin-Yvon) to select the wavelength, and this excitation light was chopped by a variable-speed chopper (Stanford Research Systems, SR540) operating in the frequency range of 60–100 Hz. For excitation light at 580 nm, a N_2 pumped dye laser (Laser Photonics models LN1000/LN107) was used with laser dye, R590 (Exciton). The emission was collected at 90° to the excitation and focused on a 0.32 M monochromator (Jobin-Yvon, iHR320). The emission intensity was detected by a photomultiplier tube (Hamamatsu, R928) and recorded using a digitizing oscilloscope (Tektronix, TDS220) interfaced to a PC. For the emission spectra of Eu^{3+} samples, the asymmetry factor, R , has been determined. The asymmetry factor is the ratio of integrated intensities of the $^5\text{D}_0 \rightarrow ^7\text{F}_2$ transition to the $^5\text{D}_0 \rightarrow ^7\text{F}_1$ transition. The uncertainty in the R value is ca. $\pm 10\%$.

3. Results and discussion

3.1. Eu^{3+} in BMIBr/water

Both EuCl_3 and EuBr_3 salts are soluble in the BMIBr/water. Both of the samples did seem to form solutions, because they are clear and show no evidence of a solid suspension or an emulsion. The typical strategy for lanthanide salt solubility in ionic liquids is to match the anions of the salt and IL (e.g., EuBr_3 in BMIBr) [14]. Therefore, the solubility of EuCl_3 in BMIBr/water in this study is likely due to the presence of water as a co-solvent with the ionic liquid.

Fig. 1 shows a comparison of the emission spectra in the $^5\text{D}_0 \rightarrow ^7\text{F}_{0-2}$ transition region of EuBr_3 salt in water, EuBr_3 in BMIBr/water, and EuCl_3 in BMIBr/water. The asymmetry factor for aqueous EuBr_3 is $R = 0.6$, which is not atypical for highly hydrated and highly symmetrical Eu^{3+} coordination environment. The asymmetry factors for each of the Eu^{3+} in the BMIBr/water show slightly larger values, $R = 1.6$ and 1.3 , than the aqueous sample. Previous studies of EuCl_3 dissolved in BMIBr/water [3] only show R values <2 for the octa- and nonahydrate europium species, which occur at water:BMIBr mole to mole ratios above 2. The water:BMIBr ratio for the EuBr_3 and EuCl_3 samples in this study are closer to 1. Comparing the spectra of EuBr_3 and EuCl_3 in BMIBr/water in Fig. 1, there is an observable peak at 580 nm, $^5\text{D}_0 \rightarrow ^7\text{F}_0$, in the EuCl_3 sample but not in the EuBr_3 sample. The observation of a $^5\text{D}_0 \rightarrow ^7\text{F}_0$ transition may indicate a more complex coordination environment in the EuCl_3 sample (e.g., Cl^- and Br^- exchange), but it is difficult to make that determination without detailed low-temperature spectroscopic data [3,16].

Fig. 1. Comparison of the emission spectra in the $^5\text{D}_0 \rightarrow ^7\text{F}_{0-2}$ transition region of EuBr_3 in water (dotted line), EuBr_3 in BMIBr/water (solid line) and EuCl_3 in BMIBr/water (dashed-dotted line). The emission was recorded after a 50 μs delay to avoid interference from the intrinsic BMIBr fluorescence. The intensity scale is different for each spectrum to aid in comparison of the location and structures of the emission peaks. The asymmetry factors, R , are shown for each of the samples. The uncertainty in R is ca. 10%.

Due to the low luminescence signal and interference by luminescence from the ionic liquid, attempts to precisely determine the observed $^5\text{D}_0$ luminescence decay rate constant of EuBr_3 in BMIBr/water were unsuccessful. However, estimates based on luminescence decay measurements show that $k_{\text{obs}} > 10000 \text{ s}^{-1}$ for EuBr_3 in BMIBr/water, which is larger than the decay constant measured for aqueous EuBr_3 (presumably europium octa- or nonahydrate [17]), $k_{\text{obs}} = 6700 \text{ s}^{-1}$. Luminescence decay measurements exciting into this $^5\text{D}_0 \rightarrow ^7\text{F}_0$ transition of EuCl_3 in BMIBr/water yield $k_{\text{obs}} = 10600 \text{ s}^{-1}$, which is consistent with the estimated decay constant for EuBr_3 in BMIBr/water. The highest k_{obs} shown in the study of EuCl_3 in BMIBr/water is $<9000 \text{ s}^{-1}$ [3] for water:BMIBr mole ratios >4. Therefore, the R values and k_{obs} for Eu^{3+} seem to be more sensitive to water concentration in our BMIBr samples than in published BMIBr samples [3].

Fig. 2 shows the excitation spectra for EuBr_3 and EuCl_3 in BMIBr/water. There is a surprising difference in the two spectra. Both spectra have broad excitation bands that seem to show sensitization of Eu^{3+} luminescence by the BMIBr. Previous studies on imidazolium ionic liquids have also shown sensitization

Fig. 2. Comparison of the excitation spectra of EuBr_3 (solid line) and EuCl_3 (dotted line) in BMIBr/water over the 300–550 nm wavelength range. The emission was monitored at 616 nm after a 50 μs delay to avoid interference from the intrinsic BMIBr fluorescence.

Fig. 3. Comparison of the emission spectra in the $^5D_4 \rightarrow ^7F_{6-3}$ transition region of $TbCl_3$ in water (dotted line) and BMIBr/water (solid line). The emission was recorded after a 50 μs delay to avoid interference from the intrinsic BMIBr fluorescence. The intensity scale is different for each spectrum to aid in comparison of the location and structures of the emission peaks.

of Eu^{3+} luminescence [18]. However, the $EuBr_3$ sample shows a much broader excitation (300–450 nm) than the $EuCl_3$ sample (350–450 nm excitation). There is also a stark contrast in the observation of sharp 4f–4f Eu^{3+} transitions, where the excitation peaks at 396 and 465 nm are almost completely suppressed in the $EuBr_3$ sample. These differences could be due to a different solvent environment for $EuCl_3$ vs. $EuBr_3$ in BMIBr, or may just reflect different coordination environments.

3.2. Tb^{3+} in BMIBr/water

Similar to $EuCl_3$, $TbCl_3$ salts are soluble in the BMIBr/water mixture. The samples appeared (by visible inspection) to form a solution, and there was no evidence of a suspension or emulsion. Fig. 3 shows the emission spectra of $TbCl_3$ dissolved in water and in BMIBr/water over the $^5D_4 \rightarrow ^7F_{6-3}$ transition region of Tb^{3+} . A comparison of the two spectra shows that the locations of all of the transitions are identical in aqueous vs. BMIBr/water, but the relative intensities show subtle differences. However, the density of Stark levels in the $^5D_4 \rightarrow ^7F_{6-3}$ transitions make interpretation of the spectra with respect to Tb^{3+} coordination environment extremely difficult without low-temperature, high-resolution spectroscopy [16]. Fig. 4 shows the excitation spectrum of $TbCl_3$ in BMIBr/water.

Fig. 4. The excitation spectrum of $TbCl_3$ in BMIBr/water over the 250–450 nm wavelength range. The emission was monitored at 545 nm after a 50 μs delay to avoid interference from the intrinsic BMIBr fluorescence.

Fig. 5. The emission spectrum in the $^5D_0 \rightarrow ^7F_{0-4}$ transition region of $Eu(dpa)_3^{3-}$ in BMIBr/water. The emission was recorded after a 50 μs delay to avoid interference from the intrinsic BMIBr fluorescence.

Similar to the excitation spectra of Eu^{3+} samples in BMIBr/water, the spectrum shows a broad excitation band indicating sensitization of Tb^{3+} emission by the BMIBr. This spectrum also shows Tb^{3+} 4f–4f excitation lines at ca. 350 ($^7F_6 \rightarrow ^5D_2$, 5G_5 , 5L_9) and 375 nm ($^7F_6 \rightarrow ^5D_3$).

3.3. $Eu(dpa)_3^{3-}$ in BMIBr/water

Fig. 5 shows the emission spectrum of $Eu(dpa)_3^{3-}$ in BMIBr/ H_2O over the $^5D_0 \rightarrow ^7F_{0-2}$ transition regions. The overall structure and relative intensities of the peaks are identical to the spectra of aqueous $Eu(dpa)_3^{3-}$ [15]. This indicates that the coordination environment of Eu^{3+} is unchanged in the ionic liquid mixture. Luminescence decay measurements give a 5D_0 decay rate constant for Eu^{3+} , $k_{obs} = 580 \pm 10 s^{-1}$, which is also similar to that measured in aqueous solution. It appears that the presence of BMIBr shows no impact upon the spectroscopic properties of $Eu(dpa)_3^{3-}$. The sample through visible inspection appears to be a solution, and shows no evidence of an emulsion or suspension.

4. Conclusions

This study shows the results from excitation and emission spectra of a Tb^{3+} , and several Eu^{3+} compounds dissolved in BMIBr/water solutions. The excitation spectra show that the BMIBr ionic liquid does sensitize Eu^{3+} and Tb^{3+} luminescence. However, the Eu^{3+} and Tb^{3+} luminescence spectra are quenched by the ionic liquid, as evidenced by the large decay constants in Eu^{3+} (relative to aqueous and BMICl samples). It is also important to note that the emission spectra of the europium chloride and bromide salts dissolved in BMIBr/water were only observable after eliminating interference from ionic liquid fluorescence (time-delayed spectra). Additional studies (e.g., EXAFS) are required to identify the exact Eu^{3+} and Tb^{3+} species present in the BMIBr/water. Many of the issues (i.e. large decay constants, small luminescence signals) could be due to the fact that the BMIBr ionic liquid used in this study is yellow, and clearly the spectroscopic properties of simple Eu^{3+} and Tb^{3+} salts are highly sensitive. In order to completely characterize the coordination and spectroscopic properties of lanthanide ions in BMIBr studies need to be conducted in colorless, anhydrous ionic liquids. However, the spectroscopic properties of $Eu(dpa)_3^{3-}$ complexes were insensitive to the presence of BMIBr, which indicates that they are plausible as intermolecular interaction probes even in binary solvent systems (BMIBr/water).

Acknowledgements

The authors would like to thank K. Cox and L. Heckman for the preparation of the $\text{Eu}(\text{dpa})_3^{3-}$ solutions. M. Goldey would like to thank the Butler Summer Institute and the Lilly Foundation for financial support. The authors would also like to thank J. Ciszewski for the initial BMIBr liquid.

References

- [1] K. Binnemans, *Chemical Reviews* (2007).
- [2] I. Billard, S. Mekki, C. Gaillard, P. Hesemann, C. Mariet, G. Moutiers, A. Labet, J.-C.G. Bünzli, *European Journal of Inorganic Chemistry* 6 (2004) 1190–1197.
- [3] S. Samikkanu, K. Mellem, M. Berry, P.S. May, *Inorganic Chemistry* 46 (2007) 7121–7128.
- [4] A.-V. Mudring, A. Babai, S. Arenz, R. Giernoth, K. Binnemans, K. Driesen, P. Nockemann, *Journal of Alloys and Compounds* 418 (2006) 204–208.
- [5] M.P. Jensen, J. Neuefeind, J.V. Beitz, S. Skanthakumar, L. Soderholm, *Journal of the American Chemical Society* 125 (2003) 15466–15473.
- [6] P. Nockemann, E. Beurer, K. Driesen, R.V. Deun, K.V. Hecke, L.V. Meervelt, K. Binnemans, *Chemical Communications* (2005).
- [7] Y.-F. Yuan, T. Carinaels, K. Lunstroot, K.V. Hecke, L.V. Meervelt, C. Gorller-Walrand, K. Binnemans, P. Nockemann, *Inorganic Chemistry* 46 (2007) 5302–5309.
- [8] I. Billard, G. Moutiers, A. Labet, A.E. Azzi, C. Gaillard, C. Mariet, K. Lutzenkirchen, *Inorganic Chemistry* 42 (2003) 1726–1733.
- [9] a.A.-V.M. Arash Babai, *Chemistry of Materials* 17 (2005) 6230–6238.
- [10] I.M. Anand Bhatt, A. Vladimir, Volkovich, David Collison, Madeleine Helliwell, B. Ilya, Polovov, G. Robert, Lewin, *Inorganic Chemistry* 44 (2005) 4934–4940.
- [11] P. Bonhote, A.-P. Dias, N. Papageorgiou, K. Kalyanasundaram, M. Gratzel, *Inorganic Chemistry* 35 (1996) 1168–1178.
- [12] P. Nockemann, K. Binnemans, K. Driesen, *Chemical Physics Letters* 415 (2005) 131–136.
- [13] J.-C.G. Bünzli, *Accounts of Chemical Research* 39 (2006) 53–61.
- [14] C. Gaillard, I. Billard, A. Chaumont, S.M. Ouadi, M.A. Denecke, G. Moutiers, G. Wipff, *Inorganic Chemistry* 44 (2005) 8355–8367.
- [15] J.P. Bolender, F.S. Richardson, *Biophysical Chemistry* 105 (2003) 293–322.
- [16] C.S. McCaw, K. Murdoch, R.G. Denning, *Molecular Physics* 101 (2003) 427–438.
- [17] L. Tilkens, K. Randall, J. Sun, M.T. Berry, P.S. May, T. Yamase, *Journal of Physical Chemistry A* 108 (2004) 6624–6628.
- [18] E. Guillet, D. Imbert, R. Scopelliti, J.-C.G. Bünzli, *Chemistry of Materials* 16 (2004) 4063–4070.

Structural and optical properties of $\text{GdAlO}_3:\text{RE}^{3+}$ (RE = Eu or Tb) prepared by the Pechini method for application as X-ray phosphors

H.H.S. Oliveira, M.A. Cebim, A.A. Da Silva, M.R. Davolos*

Unesp - São Paulo State University, Instituto de Química, 14800-900, Araraquara, São Paulo, Brazil

ARTICLE INFO

Article history:

Received 5 June 2008

Received in revised form 17 April 2009

Accepted 17 April 2009

Available online 24 April 2009

Keywords:

Rare earth alloys and compounds

Chemical synthesis

Optical properties

Luminescence

Optical spectroscopy

ABSTRACT

In this work, $\text{GdAlO}_3:\text{RE}^{3+}$ (RE = Eu or Tb) was successfully prepared by the Pechini method at lower temperatures when compared to others methods as solid-state synthesis and sol–gel process. In accordance to the XRD data, the fully crystalline single-phase GdAlO_3 could be obtained at 900 °C. The differential thermal analysis (DTA) shows a crystallization peak at 850 °C. The samples are composed by monocrySTALLINE particles (50–120 nm) exhibiting the formation of aggregates among them, which indicates the beginning of the sinterization process. This feature indicates a strong tendency to the formation of aggregates, which is a suitable ability for the close-packing of particles, and hence a potential application in X-ray intensifying screens. Luminescence measurements indicate $\text{Gd}^{3+} \rightarrow \text{RE}^{3+}$ energy transfer. The Eu^{3+} emission spectra exhibit all the characteristics $^5\text{D}_0 \rightarrow ^7\text{F}_j$ transitions and the observed profile suggests that RE^{3+} ions occupy at least one site without center of symmetry. For terbium-doped samples, the $^5\text{D}_3 \rightarrow ^7\text{F}_j$ (blue emission) and $^5\text{D}_4 \rightarrow ^7\text{F}_j$ (green emission) transitions were observed and the ratio between them may depend on the Tb^{3+} content due to cross-relaxation processes.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

X-ray phosphors are compounds that can efficiently convert high-energy photons (X-ray photons) in UV–visible radiations. This property allows such materials to be applied in industrial inspection, dosimetry, high-energy physics, nuclear medicine and medical diagnostics [1]. All medical imaging modalities that require the detection of energetic photons use these materials for their detection [2,3].

Each application requests a material with certain optical and structural properties. In general, no phosphor fulfills the requirements for all applications. Thus, improvements in one or more properties are desirable in the quest for efficient X-ray phosphors [4], which must have properties that include high density, chemical stability, radiation hardness, high luminescent yield and in some cases short lifetime. Besides, they must be easily obtained and have low cost [5,6].

Perovskite rare-earth aluminates are compounds endowed with high density and chemical stability, being promising hosts for X-ray phosphors [7,8]. These aluminates present general formula REAlO_3 (where RE represent rare-earth ions), where each RE ion is surrounded by 12 O^{2-} anions and each Al^{3+} ion by 6 O^{2-} anions (AlO_6 octahedral group). The structures of most REAlO_3 compounds,

named orthorhombic perovskites, belong to the space group $Pbnm$ due to distortions in the AlO_6 octahedra, and are derived from the ideal cubic perovskites ($Pm3m$).

Among these inorganic materials, the rare earth doped gadolinium aluminates, $\text{GdAlO}_3:\text{RE}^{3+}$ (RE = Eu or Tb), are promising for application as X-ray phosphors because it presents high density, chemical stability and important electronic and spectroscopic properties [9] as color purity, high luminous yield, lifetime of ms and $\text{Gd}^{3+} \rightarrow \text{RE}^{3+}$ energy transfer.

The Eu^{3+} ions exhibit intense red emission with lifetime of milliseconds. Moreover, Eu^{3+} ions are used as spectroscopy probe in the structural characterization of materials. The Tb^{3+} ions exhibit intense green or blue emission and they also present lifetime of milliseconds and high quantum yield values. Actually, the material utilized in planar X-ray imaging is doped with Tb^{3+} ions, $\text{Gd}_2\text{O}_2\text{S}:\text{Tb}^{3+}$.

The $\text{REAlO}_3:\text{RE}^{3+}$ has been obtained by solid-state synthesis in elevated temperatures (above 1400 °C). Wet chemical routes can be more advantageous because they make possible the preparations of phases in low temperatures and with effective doping. For example, the fully crystalline single-phase GdAlO_3 was obtained at 900–1000 °C via sol–gel method by Cizauskaite et al. [7]. Hai et al. obtained $\text{Lu}_2\text{O}_3:\text{Eu}^{3+}$ films by Pechini method and observed crystalline phase starting from 400 °C [10]. In this way, we propose a systematic study of the evolution of structural and optical properties of Eu^{3+} - and Tb^{3+} -doped GdAlO_3 powders prepared by the Pechini method with the firing temperature.

* Corresponding author. Tel.: +55 1633016634; fax: +55 1633227932.
E-mail address: davolos@iq.unesp.br (M.R. Davolos).

Fig. 1. Flow scheme of synthesis procedure of $\text{GdAlO}_3:\text{RE}^{3+}$.

2. Experimental

Rare-earth oxides (Aldrich 99.999%) and aluminum nitrate (Merk 99.5%) were used as start materials. Other chemicals used were grade reagents. Approximately 0.3 g of $\text{GdAlO}_3:\text{RE}^{3+}$ (where $\text{RE}=\text{Eu}$ or Tb) samples were prepared using a wet chemical route, i.e., the Pechini method [10,11], with 1.0, 3.0 and 5.0 at% dopant concentration. Solutions of $\text{Gd}(\text{NO}_3)_3$, $\text{Al}(\text{NO}_3)_3$ and $\text{RE}(\text{NO}_3)_3$ were mixed in stoichiometric amounts with citric acid (CA) and ethylene glycol (EG), obeying the molar proportion 1:3:16 metal:CA:EG. Initially, citric acid was added to the aqueous solution of Gd^{3+} , Al^{3+} and TR^{3+} metals. The pH was adjusted for 5.5 with NH_4OH 0.1 mol L^{-1} and the mixture was stirred for 1 h. Afterwards, ethylene glycol was added and the solution stayed under continuous stirring and heating ($\sim 100^\circ\text{C}$) for solvent evaporation. The obtained polymeric resin was fired in air atmosphere at 700, 900 and 1100°C in a tubular oven for 4 h. Fig. 1 shows the flow scheme for the process of preparing $\text{GdAlO}_3:\text{RE}^{3+}$. Thermogravimetric and differential thermal analysis of

Fig. 2. TGA and DTA curves of the polymeric resin obtained by Pechini method.

polymeric resins were carried out using a SDT 2960 simultaneous TGA–DTA in the temperature range $25\text{--}1180^\circ\text{C}$ at a heating rate of $10^\circ\text{C min}^{-1}$ under an air flux. The powders samples were characterized by X-ray diffractometry (XRD) using $\text{Cu K}\alpha$ radiation ($\lambda = 1.5442 \text{ \AA}$) in a Siemens D5000 diffractometer. Infrared spectra (FT-IR) were obtained using a spectrophotometer Perkin Elmer FT-IR Spectrum 2000. The samples also were characterized by transmission electronic microscopy (TEM) and energy dispersive X-ray spectroscopy (EDS) using a Philips CM 200 microscope. The photoluminescence measurements (PL) were recorded in a Fluorog SPEX F2121 fluorescence spectrophotometer equipped with R928 Hamamatsu photomultiplier. The excitation and emission spectra were measured at room temperature.

3. Results and discussion

Fig. 2 presents the thermogravimetric analysis (TGA) and the differential thermal analysis (DTA) of the polymeric resin obtained by Pechini method. The TGA curve shows continuous weight loss, i.e., there is no formation of stable products during precursor decomposition, which is finished around 650°C , as observed in DTA curve (exothermic peak at 530°C). The exothermic peak approximately at 850°C is due to the crystallization of GdAlO_3 phase. The crystallization temperature is low when compared to others methods, like sol–gel ($900\text{--}1200^\circ\text{C}$) and solid-state reactions (1450°C) [7,12,13].

The X-ray diffraction patterns of $\text{GdAlO}_3:\text{Eu}^{3+}$ are shown in Fig. 3. According to XRD analysis (Fig. 3a), the fully crystalline single-phase GdAlO_3 could be obtained at 900°C . The XRD patterns of samples obtained at 700°C are characteristic of non-crystalline

Fig. 3. X-ray diffraction patterns of $\text{GdAlO}_3:\text{Eu}^{3+}$ (a) temperature variation and (b) doping concentration variation.

Fig. 4. FT-IR spectra of GdAlO₃:Eu³⁺ (a) temperature variation and (b) doping concentration variation.

Fig. 5. (a) TEM image and (b) HRTEM image of GdAlO₃:Eu³⁺ 5 at%. *EDS spectrum is shown in Fig. 6.

solids. These results are consistent with crystallization temperature observed by TGA/DTA analysis. Fig. 3b shows that the doping concentration does not influence in the crystalline phase formation. All diffraction peaks in these XRD patterns could be attributed to the orthorhombic perovskite crystal structure of GdAlO₃ (JCPDF no. 46-395). The terbium-doped samples also exhibit the same behavior of the europium-doped samples in the XRD measurements.

The FT-IR spectra of GdAlO₃:Eu³⁺ samples obtained at different temperatures are shown in Fig. 4a. Only the sample obtained at 700°C exhibits strong bands related to the residual organic matter probably originated from the incomplete decomposition of precursor polymeric resin at this temperature. Fig. 5b presents FT-IR spectra of the samples containing different doping concentrations obtained at 1100°C. The spectral profiles are almost identical and exhibit strong bands between 400 cm⁻¹ and 800 cm⁻¹ which are typical metal–oxygen (Gd–O and Al–O) vibrations for the perovskite structure compounds. All spectra show a broadband around 3450 cm⁻¹ and a narrow band at 1635 cm⁻¹ assigned to the stretching and bending modes of adsorbed water, respectively. The spectra are representative of the Tb-doped samples. All characteristic absorption bands are summarized in Table 1.

The samples are composed by monocrystalline nanoparticles (mean diameter of 50–120 nm) and exhibit the formation of aggregates among them, showing a suitable ability for the sinterization (Fig. 5a). As can be seen in high resolution TEM images (Fig. 5b), the samples are highly crystalline. The TEM images showed in Fig. 5 are referent to GdAlO₃:Eu³⁺ 5% treated at 1100°C. The lattice spacing corresponding to (004) and the distance is 1.86 Å. It is possible to

observe peaks attributed to Al³⁺ and Gd³⁺ in the energy dispersive X-ray spectrum (EDS, Fig. 6). The peaks at 5.85 and 6.45 keV can be assigned to Eu³⁺ ions. Moreover, the absence of adjacent phases in XRD is evidence that Eu³⁺ is fully integrated into the GdAlO₃ host, forming solid solutions.

The excitation spectra of GdAlO₃:Eu³⁺ and GdAlO₃:Tb³⁺ samples were recorded fixing emission wavelength in 614 nm (Eu³⁺ ⁵D₀ → ⁷F₂) and 542 nm (Tb³⁺ ⁵D₄ → ⁷F₅), respectively. The spectra are shown in Fig. 7. Excitation spectra of GdAlO₃:Eu³⁺ samples (Fig. 7a) present a broadband at 265 nm attributed to O²⁻ → Eu³⁺ charger transfer. The CT band energy of Eu³⁺ depends on the type of anion, the strength of binding of valence band electrons and on the size of the site occupied by Eu³⁺ ions. Following Dorenbo [14], in the rare earth aluminates, when the rare earth site occupied by the Eu³⁺ ions becomes smaller, the energy of the CT band tends to increase (shorter wavelength). Therefore, the energy of the Eu³⁺ CT band in YAlO₃ (ionic radius of Y³⁺ = 116 pm), GdAlO₃

Table 1
Characteristic absorption frequencies of the GdAlO₃:RE³⁺.

Attribution	Frequency (cm ⁻¹)	Attribution	Frequency (cm ⁻¹)
δ Al–O (AlO ₆)	455, 467, 495	ν _s (CO ₂)	1384
Gd–O	555	ν _{ass} (CO ₂)	1404, 1508
ν Al–O (AlO ₆)	675	δ (H ₂ O)	1635
ν Al–O (AlO ₄)	720, 772	ν _{ass} (CO ₂)	2340
δ (CO ₂)	788	ν _s (CH ₂)	2364, 2856
δ _{ass} (CO ₃)	840	ν _{ass} (CH ₂)	2924
ν (CO)	1078	ν (OH)	3450

Fig. 6. EDS spectrum of $\text{GdAlO}_3:\text{Eu}^{3+}$ 5 at%.

($\text{Gd}^{3+} = 119$ pm), and LaAlO_3 ($\text{La}^{3+} = 130$ pm) are observed at 250 nm, 265 nm, and 314 nm, respectively. The results obtained in this work agree with Dorenbois [14] and Li et al. [15].

The sharp lines observed at the range 350–475 nm are assigned to $f-f$ transitions of Eu^{3+} ions. The characteristics $f-f$ transitions of Tb^{3+} ions are shown in Fig. 7b. The sharp lines observed in both spectra in 275 nm ($\text{Gd}^{3+} \ 8S_{7/2} \rightarrow 6I_{3/2}$), 312 nm and 318 nm ($\text{Gd}^{3+} \ 8S_{7/2} \rightarrow 6P_j$) appear due to energy transfer from Gd^{3+} ions to RE^{3+} ions, $\text{Gd}^{3+} \rightarrow \text{Eu}^{3+}$, which occur from $6I_{3/2}$ and $6P_j$ Gd^{3+} level to the highest energy levels of RE^{3+} ions ($4f^7 5d$ or $4f^8$ configuration of Tb^{3+} and $4f^6$ configuration of Eu^{3+}) [16–18].

The emission spectra of Eu^{3+} and Tb^{3+} -doped samples obtained at different temperatures are shown in Fig. 8. The characteristics transitions of Eu^{3+} ions, $5D_0 \rightarrow 7F_j$, are observed in all emission spectra (Fig. 8a). The $5D_0 \rightarrow 7F_0$ transition around 579 nm suggests that the Eu^{3+} ions occupy at least one site without center of symmetry. Characteristics transitions of Tb^{3+} ions were also observed in all spectra. The assignments of blue and green emission of Tb^{3+} ions are showed in Fig. 8b.

Emission spectra of Eu^{3+} and Tb^{3+} -doped samples obtained at 700°C present broad peaks, typical emission profile of non-crystalline compounds or highly disordered systems. The emission profile is similar when samples are excited at 275 nm or 399 nm (Eu^{3+} -samples) and 369 nm (Tb^{3+} -samples).

Fig. 7. Excitation spectra of (a) $\text{GdAlO}_3:\text{Eu}^{3+}$ sample, $\lambda_{\text{emission}} = 614$ nm and (b) $\text{GdAlO}_3:\text{Tb}^{3+}$ sample, $\lambda_{\text{emission}} = 542$ nm.

Fig. 9 presents the emission spectra of Eu^{3+} and Tb^{3+} -doped samples obtained at different doping concentrations. Fig. 9a shows that emission of $\text{GdAlO}_3:\text{Eu}^{3+}$ at 1% presents low intensity and the sample containing Eu^{3+} at 3% exhibit the most intense emission. In the Eu^{3+} -samples at 5%, the luminescence is vanished because, in this concentration, the distance among dopant ions is short enough to

Fig. 8. (a) Emission spectra of $\text{GdAlO}_3:\text{Eu}^{3+}$ samples. Excitation was fixed at 275 nm (continuous line) and 399 nm (dashed lines). (b) Emission spectra of $\text{GdAlO}_3:\text{Tb}^{3+}$ samples. Excitation was fixed at 275 nm (continuous line) and 369 nm (dashed lines).

Fig. 9. Emission spectra of $\text{GdAlO}_3:\text{Eu}^{3+}$ samples, $\lambda_{\text{excitation}} = 399 \text{ nm}$ and (b) emission spectra of $\text{GdAlO}_3:\text{Tb}^{3+}$ samples, $\lambda_{\text{excitation}} = 369 \text{ nm}$, obtained at different doping concentrations.

allow energy transfer, decreasing the emission intensity. The inclination observed in spectra of samples is due emission of Xe lamp utilized in spectrophotometer.

The emission spectra of $\text{GdAlO}_3:\text{Tb}^{3+}$ are shown in Fig. 9b. At low Tb^{3+} concentrations, the blue emission from $^5\text{D}_3 \rightarrow ^7\text{F}_j$ prevails. For higher Tb^{3+} concentrations, the blue emission decreases, followed by an increase in the green emission ($^5\text{D}_4 \rightarrow ^7\text{F}_j$). This occurs because the well-known cross-relaxation process [18], where Tb^{3+} ion (donor) decay non-radioactively, $^5\text{D}_3 \rightarrow ^5\text{D}_4$, and transfer energy to other Tb^{3+} ion (receptor). Thus, the emission occurs from $^5\text{D}_4$ (green emission). The process can be written as

Therefore, the activator amount in the host determines the blue-green emission composition color. In the case of scintillators, more specifically for X-ray intensifying screens, the possibility of tuning $\text{GdAlO}_3:\text{Tb}^{3+}$ emission defines the sensitivity of the photographic film used in the screen [18,19].

4. Conclusions

We reported the successful obtaining of $\text{GdAlO}_3:\text{RE}^{3+}$ perovskites by the Pechini method at 700, 900 and 1100 °C. According to TGA/DTA analysis and XRD patterns, only samples fired at 900 and 1100 °C are crystalline. The FT-IR analysis showed that heat treatment at 700 °C is not sufficient for the complete precursor decomposition. TEM images show that particles are highly crystalline and present suitable ability for close-packing. The energy transfer $\text{Gd}^{3+} \rightarrow \text{RE}^{3+}$ was observed in excitation spectra. The RE^{3+}

ions occupy at least one site without center of symmetry. The characteristic red emission of Eu^{3+} and the blue/green emission of Tb^{3+} was observed in photoluminescence measurements and the blue-green emission composition color of Tb^{3+} -samples can be tuned by amount doping.

Acknowledgements

The authors acknowledge support from the FAPESP, CNPq and RENAMI. H.H.S.O thanks FAPESP for scholarship.

References

- [1] C. Greskovich, S. Duclos, Annual Review of Materials Science 27 (1997) 69.
- [2] C.W.E. van Eijk, Nuclear Instruments and Methods in Physics Research A 392 (1997) 285.
- [3] C.W.E. van Eijk, Nuclear Instruments and Methods in Physics Research A 460 (2001) 1.
- [4] M.J. Weber, Journal of Luminescence 100 (2002) 35.
- [5] G. Blasse, Journal of Alloys and Compounds 225 (1995) 529.
- [6] S.E. Derenzo, et al., Nuclear Instruments and Methods in Physics Research A 505 (2003) 111.
- [7] S. Cizauskaite, et al., Materials Chemistry and Physics 102 (2007) 105.
- [8] C.R. Stanek, et al., Journal of Applied Physics 99 (2006) 113518.
- [9] S.A. Smirnova, et al., Journal of Luminescence 60 and 61 (1994) 960.
- [10] G. Hai, et al., Applied Surface Science 243 (2005) 245.
- [11] United State Patent Office, M.P. Pechini. US 3330697 (11th July 1967).
- [12] J.W.M. Verweij, et al., Chemical Physics Letters 239 (1995) 51.
- [13] S. Chaudhury, et al., Journal of Solid State Chemistry 180 (2007) 2393.
- [14] P. Dorenbos, Journal of Luminescence 111 (2005) 89–104.
- [15] Y. Wang, et al., Journal of Solid State Chemistry 177 (2004) 2242–2248.
- [16] Y.C. Li, et al., Materials Science and Engineering B 146 (2008) 225.
- [17] H. Gao, Y. Wang, Journal of Luminescence 122 and 123 (2007) 997.
- [18] A.A. da Silva, et al., Journal of Luminescence 128 (2008) 1165.
- [19] L.H. Brixner, Materials Chemistry and Physics 16 (1987) 253.

Spectroscopic studies of the 1.5 μm ($^4\text{I}_{15/2} \rightarrow ^4\text{I}_{13/2}$) emission from polycrystalline ceramic Er:YAG and Er:KPb₂Cl₅

U. Hömmerich^{a,*}, C. Hanley^a, E. Brown^a, S.B. Trivedi^b, J.M. Zavada^c

^a Department of Physics, Hampton University, Hampton, VA 23668, United States

^b Brimrose Corporation of America, 19 Loveton Circle, Baltimore, MD 21152, United States

^c Department of Electrical Engineering, North Carolina State University, Raleigh, NC 27695, United States

ARTICLE INFO

Article history:

Received 9 June 2008

Received in revised form 26 June 2008

Accepted 1 September 2008

Available online 8 November 2008

Keywords:

Insulators

Light absorption and reflection

Luminescence

ABSTRACT

The 1.5 μm emission from Er³⁺ ions continues to be of current interest for applications in optical communications and eye-safe solid-state lasers. Recently, significant attention has been focused on the development of 1.5–1.6 μm Er³⁺ solid-state lasers with resonant pumping of the $^4\text{I}_{13/2} \leftrightarrow ^4\text{I}_{15/2}$ transition. The motivation for resonantly pumped Er³⁺ lasers lies in the reduced thermal load, which is critical for high power laser application. In this work we present results of the infrared optical properties of polycrystalline ceramic Er:YAG and Er:KPb₂Cl₅ including absorption and emission studies, lifetime measurements, and calculations of 1.5 μm emission cross-sections using the reciprocity and Fuchtbauer–Ladenburg methods.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

The development of solid-state gain media for the ~1.5–1.6 μm region continues to be of significant current interest for applications in optical communications and eye-safe laser applications [1–3]. Significant advances were recently reported in the development of ~1.6 μm Er³⁺ lasers (e.g. Er:YAG), which are resonantly pumped between Stark levels of the $^4\text{I}_{15/2} \leftrightarrow ^4\text{I}_{13/2}$ transition [4–10]. The interest in resonantly pumped Er³⁺ lasers has been stimulated by the availability of new long-wavelength pump sources including Er³⁺ fiber lasers and ~1.5 μm diode-laser arrays. In contrast to pumping into the $^4\text{I}_{9/2}$ excited state of Er³⁺ at ~980 nm, resonant pumping of the $^4\text{I}_{13/2}$ level provides the advantage of a smaller heat load due to a reduced quantum defect.

The development of high quality ceramic Y₃Al₅O₁₂ (YAG) doped with trivalent rare earth ions has made an enormous impact on the field of solid-state lasers and is envisioned to replace single-crystal YAG laser rods used in current applications [11–13]. Transparent ceramics offer several important advantages over single crystals including ease of fabrication at reduced cost, higher rare earth homogeneity and concentration, the possibility of multi-layer structures, and fabrication of larger sizes [11–13]. Many studies on ceramic YAG have been concentrated on the material fabrication, characterization, and laser performance of Nd:YAG and Yb:YAG

ceramics for ~1 μm laser applications. Only a few studies were reported so far on the spectroscopic properties of Er:YAG ceramics for solid-state laser applications [14–17]. In most cases, the investigated Er:YAG ceramics had a 50 at.% Er³⁺ concentration, which is too high for 1.5 μm eye-safe laser applications [16,17]. The emission quantum efficiency of the 1.5 μm emission was determined to be only ~26.4% for highly doped Er:YAG ceramics, which was attributed to upconversion and cross-relaxation processes [16]. For quasi-three level laser operation of the $^4\text{I}_{13/2} \leftrightarrow ^4\text{I}_{15/2}$ transition it is important to keep the Er³⁺ concentration low (1 at.% or less) in order to minimize re-absorption losses at the laser wavelength and to reduce upconversion losses that depopulate the pump and upper laser levels [1–10].

Compared to oxide and fluoride laser hosts, Er-doped crystals with small maximum phonon energies provide the advantage of reduced non-radiative relaxation rates leading to high emission quantum efficiencies. Ternary lead halides such as KPb₂Cl₅ and KPb₂Br₅ were recently identified as a novel class of low-phonon energy laser hosts [18–26]. Efficient emission at near and mid-IR wavelengths have been reported from several rare earth-doped KPb₂Cl₅ and KPb₂Br₅ crystals [18–24]. Moreover, several laser demonstrations from rare earth-doped KPb₂Cl₅ crystals have been reported including Er:KPb₂Cl₅ (Er:KPC) at 1.7 μm and 4.5 μm [22]. Recently, it was also shown that energy-transfer upconversion processes in Er:KPC are orders of magnitude lower compared to common oxide and fluoride laser hosts, which further reduces heat loading in resonantly pumped 1.5 μm Er³⁺ lasers [23].

* Corresponding author.

E-mail address: uwe.hommerich@hamptonu.edu (U. Hömmerich).

In this paper we report spectroscopic results of the 1.5 μm absorption and emission properties in polycrystalline Er:YAG and Er:KPC. A commercial Er:YAG ceramic was used in these studies, whereas Er:KPC crystals were grown using in-house facilities. The emission cross-sections were determined for low concentration samples (~ 0.5 at.%) using a combination of the reciprocity and Fuchtbauer–Ladenburg (FL) methods.

2. Experimental considerations

A sample of a polycrystalline ceramic Er:YAG was purchased from Baikowski International Corporation (Charlotte, North Carolina) with the dimension 5 mm $\times$ 5 mm $\times$ 3 mm. The Er concentration as provided by the manufacturer was 0.5 at.%. The investigated Er:KPC crystals were grown using in-house crystal growth facilities as described previously [21,24]. The synthesized KPC material was purified through a combination of directional solidification, zone-refinement, and chlorination of the melt using research grade HCl gas. The Er:KPC crystals were subsequently grown using a modified Bridgman growth technique.

Absorption spectra were measured using a Cary 5000 spectrophotometer with a fixed spectral bandwidth of 0.5 nm. The near-IR emission was excited using a modulated (70 Hz) 972 nm diode-laser and dispersed with a 0.5-m spectrometer. The spectrometer was equipped with a 600 grooves/mm reflecting grating blazed at 1 μm . The spectral resolution in all emission measurements was ~ 0.5 nm. A long pass filter with a cut-on wavelength of 1100 nm was placed in front of the entrance slit of the spectrometer to block laser scattering. The emission signal was recorded using a thermoelectrically cooled InGaAs detector in conjunction with a lockin amplifier. All recorded emission spectra were carefully calibrated for the spectral response of the experimental setup. For emission lifetime studies the 965 nm output of a pulsed (5 ns) Nd:YAG pumped Optical Parametric Oscillator was employed as the pumped source. The entire emission from the $^4I_{15/2} \rightarrow ^4I_{13/2}$ transition was monitored using a 1.5 μm bandpass filter placed directly in front of the detector. The decay transients were averaged and recorded using a digital oscilloscope.

3. Optical characterization

3.1. Polycrystalline ceramic Er:YAG

The room-temperature absorption spectrum of the $^4I_{13/2} \rightarrow ^4I_{15/2}$ transition of ceramic Er:YAG is shown in Fig. 1. The spectral position and stark-splittings of the observed absorp-

Fig. 1. Absorption and emission cross-section spectra for the $^4I_{15/2} \leftrightarrow ^4I_{13/2}$ transition of ceramic Er:YAG at room-temperature.

tion lines for ceramic Er:YAG closely matched reported data for single-crystal Er:YAG [1,2,10]. The absorption cross-section was calculated using an Er concentration of $6.9 \times 10^{19} \text{ cm}^{-3}$ as determined by inductively coupled plasma optical emission spectroscopy (ICP-OES). The measured Er concentration agreed well with the nominal concentration of 0.5 at.% provided by the manufacturer.

The absorption cross-section for ceramic Er:YAG at the most common pump wavelengths of 1475 nm and 1532 nm were determined to be $1.8 \times 10^{-20} \text{ cm}^2$ and $2.3 \times 10^{-20} \text{ cm}^2$, respectively. At the common Er:YAG laser wavelengths of 1617 nm and 1645 nm, the absorption cross-sections determining ground-state absorption losses were $0.12 \times 10^{-20} \text{ cm}^2$ and $0.06 \times 10^{-20} \text{ cm}^2$, respectively. These numbers are in good agreement with recent spectroscopic results reported for single-crystal Er:YAG (0.5 at.%) [9,10]. It was noticed, however, that the absorption cross-section data reported in the literature vary slightly for single-crystal Er:YAG depending on the Er concentration and spectral resolution employed in the absorption measurements [1–10].

The emission cross-section (σ_{emis}) for ceramic Er:YAG was calculated using the reciprocity method, which relates absorption and emission cross-section [1]:

$$\sigma_{\text{emis}}^{\text{recip}}(\lambda) = \sigma_{\text{abs}}(\lambda) \frac{Z_l}{Z_u} \exp\left(\frac{E_{Zl} - hc/\lambda}{kT}\right) \quad (1)$$

where σ_{abs} is the absorption cross-section, Z_l and Z_u are the partition functions of the lower and upper states, and E_{Zl} is the zero-line energy. E_{Zl} is defined as the energy difference between the lowest stark component in the upper and lower levels. The partition function ratio Z_l/Z_u was calculated from published data on the energy level structure of ceramic Er:YAG and yielded a value of 1.055 [17]. The wavelength used for the zero-line (E_{Zl}) was 1526 nm [17]. The obtained emission cross-section spectrum is shown in Fig. 1 and yielded values of $0.67 \times 10^{-20} \text{ cm}^2$ and $0.59 \times 10^{-20} \text{ cm}^2$ at the common laser wavelengths of 1617 nm and 1645 nm, respectively. These cross-sections are similar to reported values for single-crystal Er:YAG [1–10], which further underlines that ceramic Er:YAG has comparable optical properties to its crystalline counterpart. The emission cross-section spectrum was also determined from the well-known FL equation [20]:

$$\sigma_{\text{emis}}^{\text{FL}}(\lambda) = \frac{\beta \lambda^5 I(\lambda)}{8\pi n^2 c \tau_{\text{rad}} \int \lambda I(\lambda) d\lambda} \quad (2)$$

where β is the branching ratio, n is the refractive index, c is the speed of light, $I(\lambda)$ is the intensity of the corrected emission spectrum, and τ_{rad} is the radiative lifetime of the $^4I_{13/2}$ multiplet. τ_{rad} was calculated to be 6.2 ms from the condition that the integrated emission cross-sections derived from the reciprocity and FL methods should be equal. The room-temperature lifetime for ceramic Er:YAG powder was measured to be 5.9 ms (see Fig. 2), which supports the internal consistency of the emission cross-section calculations. It was noticed thus, that the measured emission spectrum was slightly impacted by re-absorption losses at wavelengths lower than ~ 1550 nm, which led to reduced emission cross-sections values compared to those obtained from the reciprocity method. Based on the cross-section analysis, the emission quantum efficiency of the investigated ceramic Er:YAG (0.5 at.%) sample was estimated to be $\sim 95\%$, which compares well with the 92.5% emission efficiency reported for single-crystal Er:YAG [10].

3.2. Er:KPCl₅

The 1.5 μm absorption and emission cross-section spectra ($^4I_{13/2} \rightarrow ^4I_{15/2}$) for Er:KPC are shown in Fig. 3. In contrast to ceramic Er:YAG, the IR spectra for Er:KPC are relatively broad with only a

Fig. 2. Emission decay transients for ceramic Er:YAG and Er:KPC excited at 965 nm.

few structures indicating Stark-level splittings. A detailed Stark-level analysis was recently performed on Er:KPC [25,26] indicating a ground-state splitting of $\sim 240\text{ cm}^{-1}$ compared to $\sim 575\text{ cm}^{-1}$ reported for ceramic Er:YAG [17]. The reciprocity method was applied to determine the emission cross-section spectrum for Er:KPC (Fig. 3). The partition functions were calculated from the energy level structure of Er:KPC and the ratio Z_l/Z_u yielded a value of ~ 1.1 [19,25]. The wavelength used for the zero-line (E_{ZL}) was 1535.4 nm [25]. The resulting peak emission cross-section at 1536 nm was determined to be $1.1 \times 10^{-20}\text{ cm}^2$. The cross-sections at the longer wavelength peaks of 1552 nm and 1582 nm were reduced to values of $0.89 \times 10^{-20}\text{ cm}^2$ and $0.29 \times 10^{-20}\text{ cm}^2$, respectively. For consistency check, the emission cross-section was also calculated using the FL-method as shown in Fig. 3 using a radiative lifetime of 4.3 ms. This lifetime is in good agreement with the radiative lifetime of 4.2 ms derived from a Judd–Ofelt analysis [19].

Fig. 3. Absorption and emission cross-section spectra for Er:KPC at room-temperature.

Fig. 4. Gain cross-section spectra for the 1.5 μm transition in ceramic Er:YAG and Er:KPC for different population inversion ratios ($\beta = 0.25, 0.5$, and 0.75).

The experimental lifetime from a low concentration Er:KPC powder was determined to be 5.7 ms (Fig. 2), which suggests some residual effect of radiation trapping [19]. The initial rise-time in the 1.5 μm lifetime transient can be attributed to radiative feeding from the $^4I_{11/2}$ excited state.

3.3. Gain cross-sections for ceramic Er:YAG and Er:KPC

Using the obtained absorption and emission cross-sections for ceramic Er:YAG and Er:KPC the gain cross-sections were calculated according to [2]:

$$g(\lambda) = \beta \sigma_{\text{emis}}(\lambda) - (1 - \beta) \sigma_{\text{abs}}(\lambda) \quad (3)$$

where $\beta = N_{\text{exc}}/N_{\text{tot}}$ is the inversion ratio with N_{exc} and N_{tot} being the Er^{3+} excited state and total Er^{3+} populations, respectively. Examples of the gain cross-section spectra for $\beta = 0.25, 0.5$, and 0.75 are shown in Fig. 4. The peak gain cross-section in Er:KPC for $\beta = 0.75$ is only half the value determined for ceramic Er:YAG, which would lead to a significantly higher laser threshold. Furthermore, it can be noticed that higher population inversion ratios are required for Er:KPC than for ceramic Er:YAG to achieve a positive gain cross-section at longer wavelengths. For example, for ceramic Er:YAG already 25% population inversion leads to a gain cross-section of $\sim 0.1 \times 10^{-20}\text{ cm}^2$ at the common laser wavelength of 1647 nm. On the contrary, nearly 50% population inversion is needed for Er:KPC to achieve a positive gain of $\sim 0.1 \times 10^{-20}\text{ cm}^2$ at the long-wavelength peak at 1582 nm. This can be explained by the larger Stark-level splittings in ceramic Er:YAG compared to Er:KPC, which leads to reduced re-absorption losses at longer wavelengths. However, the significant spectral overlap between the $^4I_{13/2} \rightarrow ^4I_{15/2}$ emission and $^4I_{13/2} \rightarrow ^4I_{9/2}$ excited state absorption in Er:YAG leads to a larger energy-transfer upconversion coefficient and higher heat loading compared to Er:KPC [23].

4. Conclusions

Spectroscopic results of the 1.5 μm ($^4I_{15/2} \leftrightarrow ^4I_{13/2}$) absorption and emission properties of ceramic Er:YAG and Er:KPC were presented. It was observed that the spectral properties and cross-sections of ceramic Er:YAG are very similar to results reported for single crystals of Er:YAG. Therefore, it can be predicted that 1.5–1.6 μm lasers using ceramic Er:YAG will have comparable laser properties to their crystalline counterparts, with the added advantages intrinsic to ceramic gain media. Compared to ceramic Er:YAG, Er:KPC has significantly broader spectral features providing the possibility for modest wavelength tunability in the 1.5 μm region.

The smaller ground-state splitting for Er:KPC compared to Er:YAG, however, leads to significant ground-state re-absorption due to higher thermal populations in the Stark levels of the $^4I_{15/2}$ multiplet. In addition, further improvement in the material purification and crystal growth are necessary to produce laser quality Er:KPC crystals for the 1.5 μm spectral region.

Acknowledgements

The authors at Hampton University acknowledge financial support by the Army Research Office through grant W911NF-04-1-0302 and the National Science Foundation through grants HRD-0630372 and HRD-0734635.

References

- [1] S.A. Payne, L.L. Chase, K.K. Smith, W.L. Kway, W.F. Krupke, *IEEE J. Quant. Electron.* 28 (1992) 2619.
- [2] T. Schweitzer, T. Jensen, E. Heumann, G. Huber, *Opt. Commun.* 118 (1995) 557.
- [3] P. Le Boulanger, J.L. Doualan, S. Girard, J. Margerie, R. Moncorge, *Phys. Rev. B* 60 (1999) 11380.
- [4] Y.E. Young, S.D. Seltzer, K.J. Snell, P.A. Budni, T.M. Pollak, E.P. Chicklis, *Opt. Lett.* 29 (2004) 1075.
- [5] S.D. Setzler, M.P. Francis, Y.E. Young, J.R. Konves, E.P. Chicklis, *IEEE J. Sel. Topics Quant. Electron.* 11 (2005) 645.
- [6] D. Garbuzov, I. Kurryashov, M. Dubinskii, *Appl. Phys. Lett.* 87 (2005) 121101.
- [7] D.Y. Shen, J.K. Sahu, W.A. Clarkson, *Opt. Lett.* 31 (2006) 754.
- [8] K. Spariosu, V. Leyva, R.A. Reeder, M. Klotz, *IEEE J. Quant. Electron.* 42 (2006) 182.
- [9] J.O. White, M. Dubinskii, L.D. Merkle, I. Kuryashov, D. Garbuzov, *J. Opt. Soc. Am. B* 24 (2007) 2454.
- [10] M. Eichhorn, S.T. Fredrich-Thornton, E. Heumann, G. Huber, *Appl. Phys. B* 91 (2008) 249.
- [11] A. Ikesue, Y.L. Aung, T. Taira, T. Kamimura, K. Yoshida, G.L. Messing, *Annu. Rev. Mater. Res.* 36 (2006) 397.
- [12] J. Lu, K. Ueda, H. Yagi, T. Yanagitani, Y. Akiyama, A. Kaminskii, *J. Alloys Compd.* 341 (2002) 220.
- [13] J. Dong, A. Shirakawa, K. Ueda, H. Yagi, T. Yanagitani, A.A. Kaminskii, *Opt. Lett.* 32 (2007) 1890.
- [14] M. Sekita, H. Haneda, S. Shirasaki, *J. Appl. Phys.* 69 (1991) 3709.
- [15] G. Qin, J. Lu, J.F. Bisson, Y. Feng, K. Ueda, H. Yagi, T. Yanagitani, *Solid State Commun.* 132 (2004) 103–106.
- [16] D. Sardar, C.C. Russell, J.B. Gruber, T. Allik, *J. Appl. Phys.* 97 (2005) 123501.
- [17] J.B. Gruber, A.S. Nijjar, D.K. Sardar, R.M. Yow, C.C. Russell III, T.H. Allik, B. Zandi, *J. Appl. Phys.* 97 (2005) 063519.
- [18] M.C. Nostrand, R.H. Page, S.A. Payne, L.I. Isaenko, A.P. Yeliseyev, *J. Opt. Soc. Am. B* 18 (2001) 264.
- [19] N.W. Jenkins, S.R. Bowman, S. O'Connor, S.K. Searles, J. Ganem, *Opt. Mater.* 22 (2003) 311.
- [20] K. Rademaker, W.F. Krupke, R.H. Page, S.A. Payne, K. Petermann, G. Huber, L. Isaenko, U.N. Roy, A. Burger, K. Nitsch, *J. Opt. Soc. Am. B* 21 (2004) 2117.
- [21] U. Hümmerich, E.E. Nyein, S.B. Trivedi, *J. Lumin.* 113 (2005) 100.
- [22] S.R. Bowman, S.K. Searles, N.W. Jenkins, S.B. Qadri, E.F. Skelton, in: C. Marshall (Ed.), *Trends in Optics and Photonics*, vol. 50, Optical Society of America, 2001.
- [23] R.S. Quimby, N.J. Condon, S.P. O'Connor, S. Biswal, S.R. Bowman, *Opt. Mater.* 30 (2008) 827.
- [24] P. Amedzake, E. Brown, U. Hümmerich, S.B. Trivedi, J.M. Zavada, *J. Cryst. Growth* 310 (2008) 2015.
- [25] J.B. Gruber, R.M. Yow, A.S. Nijjar, C.C. Russell III, D.K. Sardar, B. Zandi, A. Burger, U.N. Roy, *J. Appl. Phys.* 100 (2006) 043108.
- [26] A. Ferrier, M. Velazquez, J.L. Doualan, R. Moncorge, *J. Opt. Soc. Am. B* 24 (2007) 2526.

Spectroscopic characterization of Praseodymium doped Gallium Nitride powder prepared by a Na flux method

E. Brown^{a,*}, U. Hömmerich^a, T. Yamada^b, H. Yamane^b, J.M. Zavada^c

^a Department of Physics, Hampton University, Hampton, VA 23668, United States

^b Institute of Multidisciplinary Research for Advanced Materials, Tohoku University, 2-1-1 Katahira, Aoba-Ku, Sendai 980-8577, Japan

^c Department of Electrical Engineering, North Carolina State University, Raleigh, NC 27695, United States

ARTICLE INFO

Article history:

Received 16 June 2008

Received in revised form

13 September 2008

Accepted 5 November 2008

Available online 14 November 2008

Keywords:

Semiconductors

Light absorption and reflection

Luminescence

ABSTRACT

The photoluminescence (PL) properties of Pr³⁺ doped GaN powders prepared by a Na flux method were investigated. Under above- and below-gap excitation, GaN:Pr powders exhibited intense red emission lines centered at ~650 nm corresponding to the intra-4f transition $^3P_0 \rightarrow ^3F_2$ of Pr³⁺. In addition, weak infrared PL bands were observed from lower excited states of Pr³⁺ at ~960, ~1300, and ~1500–1700 nm. A temperature dependent study of the red emission showed that the integrated PL intensity decreased by a factor of two under above-gap excitation for the temperature range 10–300 K. No significant thermal quenching of the red Pr³⁺ PL was observed under below-gap excitation. Time-resolved emission studies revealed that the decay transient of the red PL was characterized by a fast non-exponential decay followed by a slower decaying exponential component. The non-exponential decay can be attributed to cross-relaxation processes among Pr³⁺ ions, whereas the exponential component suggests the existence of isolated Pr³⁺ centers not affected by emission quenching through cross-relaxations.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Over the last decade, light emission from rare-earth (RE) doped wide band gap III-nitride semiconductors has been intensively studied for applications in display technology, solid-state light sources, and optical communications [1–5]. Since the RE emission intensity is not significantly affected by thermal quenching in wide band-gap semiconductors, III-nitride alloys have proven to be promising host materials for RE doping [6]. Results have been reported on *in situ* doping and ion-implantation of RE ions into GaN, AlN, and AlGaIn thin-films [1–4,7–9]. Among the III-nitrides, GaN is an excellent host because it has a direct band gap and it allows the incorporation of high RE concentrations [5]. Light emission in the UV, visible, and IR spectral region has been reported from several RE doped GaN systems prepared by different growth techniques [2–4,7–10].

Pr³⁺ doping of GaN has been of interest for photonic applications due to the strong red emission at ~650 nm and IR emission at ~1300 nm [11–13]. There are several reports regarding photoluminescence (PL), electroluminescence (EL), and cathodoluminescence (CL) in the red spectral region from Pr³⁺ doped GaN films grown by ion implantation, solid source MBE, and metal-organic chemical vapor deposition (MOCVD) [11–19]. Although considerable

research has been done on RE doped GaN, questions concerning the RE incorporation, excitation mechanisms, and local crystal-field symmetry still remain. Wahl et al. studied the lattice location of Pr³⁺ implanted GaN using emission channeling technique and reported that substitutional Ga sites are thermally stable lattice positions for Pr³⁺ ions in GaN [15]. Gruber et al. calculated the crystal-field splitting of Pr³⁺ energy levels in Pr implanted GaN films grown by MOCVD [16]. Effects of the oxygen incorporation and thermal annealing on the red PL intensity of Pr implanted GaN samples were investigated by Zavada et al. [13] and others [17,19].

Recently, RE doped GaN powders have been prepared for potential applications as phosphors in displays and solid-state lighting using different methods including flux techniques and combustion synthesis [20–25]. Wu et al. [21,22] reported green and red emissions from Er and Eu doped GaN powders, respectively. The visible PL and CL properties of Eu and Tb doped GaN nano-crystallites were investigated by Nyk et al. [25]. To our knowledge, there has been no report on the PL properties of Pr³⁺ doped GaN powder. In this work results of the emission properties of Pr³⁺ doped GaN powders prepared by a Na flux method are presented. Steady-state and time-resolved PL studies were performed as a function of excitation wavelength and temperature.

2. Experimental details

GaN crystallites and powders were prepared from a Na–Ga melt heated at temperatures of 600–800 °C and N₂ pressures of approximately 5 MPa. Pr metal (1.2 at.%) was added into the Na–Ga melt. After heating for 200 h, the sample was cooled down

* Corresponding author. Tel.: +1 757 218 8819; fax: +1 757 728 6910.
E-mail address: eiyei.nyein@hamptonu.edu (E. Brown).

Fig. 1. Room temperature visible (a) and infrared (b) PL spectra from Pr doped GaN powder under above-gap UV excitation. (c) Schematic energy level diagram of the intra-4f levels of Pr^{3+} ions in GaN. The observed visible and near-IR emission lines of Pr^{3+} are indicated in the diagram.

to room temperature. The solidified Na–Ga melt was removed from the GaN crystals by adding ethanol first and then using a nitrohydrochloric acid solution to dissolve the remaining Na–Ga intermetallic compounds. More details of the sample preparation were described elsewhere [23]. Fragments of the Pr doped GaN crusts were powdered with an agate pestle and a mortar. The powder was pressed into pellets (~ 2 – 3 mm diameter) for the emission measurements.

PL characterization was performed using either a He–Cd laser (325 nm) or a UV argon laser (333.6–363.8 nm) for above-gap excitation. A diode-pumped solid-state (DPSS) laser operating at 473 nm was used for below-gap excitation. The visible PL was analyzed by a 0.5 m monochromator in conjunction with a photomultiplier tube. The IR PL was dispersed by a 1 m monochromator and detected with an InGaAs detector. The spectral resolution in visible PL studies was ~ 1 nm, whereas IR PL spectra were recorded with lower resolution (~ 10 nm) due to weaker signal intensities. For PL decay time measurements, the third harmonic output of a pulsed Nd:YAG laser (355 nm) was used for above-gap excitation. A Nd:YAG pumped optical parametric oscillator (OPO) system (10 ns pulses, 10 Hz) was employed for resonant pumping at ~ 473 nm. The decay signals were recorded by averaging the detector signal on a

digital oscilloscope. Temperature dependent PL studies (10–300 K) were carried out using a two-stage closed-cycle helium refrigerator.

3. Results and discussion

Fig. 1(a) and (b) shows the overview PL spectra of GaN:Pr powder in the visible and near-IR spectral regions at room temperature. Under above-gap excitation the sample exhibited GaN bandedge emission at ~ 365 nm, a defect-related background emission centered at ~ 550 nm, and strong red emission lines centered at ~ 650 nm which corresponds to the $^3\text{P}_0 \rightarrow ^3\text{F}_2$ transition of Pr^{3+} ions (Fig. 1(a)). The full width at half maximum (FWHM) of the ~ 650 nm PL line was ~ 3 nm at 300 K. A few weaker emission lines were observed at ~ 671 nm ($^3\text{P}_1 \rightarrow ^3\text{F}_3$) and ~ 750 – 800 nm ($^3\text{P}_0 \rightarrow ^3\text{F}_4$,

Fig. 2. High-resolution PL spectra of the red emission line of $^3\text{P}_0 \rightarrow ^3\text{F}_2$ at 10 and 300 K from GaN:Pr powder under (a) above-gap excitation and (b) below-gap excitation. (c) Temperature dependence of the integrated Pr^{3+} PL intensities for above-gap and below-gap excitations.

Fig. 3. Decay transients of the red PL ($^3P_0 \rightarrow ^3F_2$) from GaN:Pr following pulsed excitation for (a) above-gap pumping and (b) below-gap pumping. The emission was monitored at ~ 652 nm.

$^1D_2 \rightarrow ^3H_6$) [13,14]. Besides the visible PL, near-IR emission lines from Pr^{3+} were observed at ~ 0.91 – 1.0 , ~ 1.3 , and ~ 1.5 – 1.7 μm corresponding to the $^1D_2 \rightarrow ^3F_3$, $^1G_4 \rightarrow ^3H_5$, and 3F_3 , $^3F_4 \rightarrow ^3H_4$ transitions (Fig. 1(b)). Additional emission lines were noted at 1108, 1145, and 1185 nm, but the origin of these lines has not yet been identified [11–13]. A schematic energy level diagram of Pr^{3+} depicting all identified PL lines is shown in Fig. 1(c) along with the GaN energy gap. The visible and IR PL spectra of Pr doped GaN powder agree well with previous reports on Pr implanted GaN and MBE grown Pr doped GaN thin-films [11–13]. For the remainder of this paper, attention is focused on the red emission properties of Pr doped GaN powder.

The high-resolution emission spectra of GaN:Pr powder at 10 and 300 K under above-gap (325 nm) and below-gap (473 nm) excitations are shown in Fig. 2. No significant spectral differences were observed for both excitation wavelengths, which suggest that similar Pr^{3+} centers are excited. At low-temperature, several PL lines were resolved with peaks at 650.8, 652.9, 654.8, 658.2, 660.8, and 670.5 nm. Many authors have discussed that RE ions predominantly enter the substitutional Ga^{3+} lattice sites in GaN with trigonal C_{3v} symmetry [14–16,18]. Assuming that Pr^{3+} ions are located in C_{3v} symmetry for the investigated GaN:Pr powder, the dominant lines at 650.8 and 652.9 nm (including a weak shoulder at 654.8 nm) are assigned to the expected crystal-field components of the $^3P_0 \rightarrow ^3F_2$ transition. The weaker visible emission lines at longer wavelengths are most likely due to other $^3P_J \rightarrow ^3F_J$ transitions of Pr^{3+} [14].

The temperature dependence of the integrated Pr^{3+} PL intensity of the dominant red emission lines at ~ 650 nm under above and below-gap excitations is shown in Fig. 2(c). The integrated PL intensity was reduced by a factor 2 between 10 and 300 K for above-gap pumping. Under below-gap excitation, no significant thermal quenching of the red PL intensity was observed for the same temperature range. The Pr^{3+} PL quenching under above-gap excitation is tentatively attributed to a slight reduction in excitation efficiency with increasing temperature [26].

The decay transients of the red PL ($^3P_0 \rightarrow ^3F_2$) at 10 and 300 K for above- and below-gap excitation are shown in Fig. 3. The PL was monitored at 652 nm. In both cases, the observed decay transients had two distinguishable components, a fast non-exponential component and a slower decaying exponential

component. The non-exponential decay component can be due to several processes including multiple RE^{3+} centers, energy transfer, and cross-relaxation processes [27,28]. Since no significant spectral differences were observed for different excitation wavelengths, the contribution of multiple Pr^{3+} centers to the non-exponential decay component is considered to be small. As discussed by Lozykowski et al. for Pr implanted GaN films, the dominant contribution to the non-exponential decay is due to cross-relaxation between Pr^{3+} ions [14]. On the other hand, the exponential decay component suggests the existence of isolated Pr^{3+} centers not affected by emission quenching through cross-relaxation processes [14,29]. At low temperature, the slower decay component was determined to be ~ 38 μs for above-gap pumping and ~ 30 μs for below-gap excitation. A similar radiative decay rate of 38.9 μs was reported for Pr implanted GaN at 12 K under UV excitation [14]. An extrapolation of the exponential component to $t = 0$ shows that the ratio of the slow decay component to the total decay transient is $\sim 35\%$ for above-gap excitation. This value is significantly larger than the $\sim 12\%$ reported for Pr implanted GaN under UV excitation. This observation suggests that for the investigated GaN:Pr powder, Pr^{3+} ions are less affected by emission quenching through cross-relaxation than reported for Pr implanted GaN films. At room temperature, the exponential decay component decreased slightly to values of ~ 26 μs and ~ 20 μs for above- and below-gap pumping, respectively. The slight temperature dependence of the exponential decay component can be explained by the onset of weak non-radiative decay through multi-phonon emission and/or energy transfer to defects [30]. Further studies on the red PL quenching mechanisms in GaN:Pr powders are still in progress.

4. Summary

The PL emission properties of Pr doped GaN powder prepared by a Na flux method were investigated. Under above- and below-gap pumping, the sample exhibited bright red emission at 652 nm, which is of interest for applications in displays and solid-state lighting. The observation of near-IR emission lines at 0.96, 1.3 and ~ 1.5 – 1.7 μm indicates that GaN:Pr powder is also of interest for IR light source development and optical communications. Under UV excitation the integrated PL intensity at ~ 652 nm ($^3P_0 \rightarrow ^3F_2$)

decreased by a factor of two between 10 and 300 K, whereas no significant PL quenching was observed for resonant intra-4f excitation using below-gap pumping. Emission decay time studies revealed that the majority of Pr^{3+} ions are impacted by cross-relaxation processes quenching the red emission from the ${}^3\text{P}_0 \rightarrow {}^3\text{F}_2$ transition. At the same time, the observation of a slower and exponential decay component suggests the existence of isolated Pr^{3+} centers not influenced by cross-relaxation emission quenching. Further time-resolved emission studies and decay time modeling are planned in the future to gain a better understanding of non-radiative quenching processes in Pr doped GaN powders.

Acknowledgements

The work at Hampton University was supported by the Army Research Office through grant W911NF-04-1-0302 and the National Science Foundation through grants HRD-0734635 and HRD-0630372. The work at Tohoku University was partially supported by the Ministry of Education, Culture, Sports, Science and Technology (MEXT) through Grand-in-Aid for Young Scientists (B): KAKENHI (17760536).

References

- [1] A.J. Steckl, J.M. Zavada, *MRS Bull.* 24 (1999) 33.
- [2] H.J. Lozykowski, W.M. Jadwisieniczak, I. Brown, *Appl. Phys. Lett.* 74 (1999) 1129.
- [3] A.J. Steckl, J. Heikenfeld, D.S. Lee, M. Garter, *Mater. Sci. Eng. B* 81 (2001) 97.
- [4] R.G. Wilson, R.N. Schwartz, C.R. Abernathy, S.J. Pearton, N. Newman, M. Rubin, T. Fu, J.M. Zavada, *Appl. Phys. Lett.* 65 (1994) 992.
- [5] A.J. Steckl, J. Heikenfeld, D.S. Lee, M.J. Garter, C.C. Baker, Y. Wang, R. Jones, *IEEE J. Sel. Top. Quantum Electron* 8 (2002) 749.
- [6] P.N. Favennec, H. L'Haridon, M. Salvi, D. Moutonnet, Y. Le Guillou, *Electron. Lett.* 25 (1989) 718.
- [7] U. Hömmerich, E.E. Nyein, D.S. Lee, J. Helkenfeld, A.J. Steckl, J.M. Zavada, *Mater. Sci. Eng. B* 105 (2003) 91.
- [8] U. Hömmerich, E.E. Nyein, D.S. Lee, A.J. Steckl, J.M. Zavada, *Appl. Phys. Lett.* 83 (2003) 4556.
- [9] J.M. Zavada, N. Nepal, J.Y. Lin, H.X. Jiang, E. Brown, U. Hömmerich, J. Hite, C.T. Thaler, C.R. Abernathy, S.J. Pearton, *Appl. Phys. Lett.* 89 (2006) 152107.
- [10] S. Morishima, T. Maruyama, K. Akimoto, *J. Cryst. Growth* 209 (2000) 378.
- [11] R. Birkhahn, M. Garter, A.J. Steckl, *Appl. Phys. Lett.* 74 (1999) 2161.
- [12] L.C. Chao, A.J. Steckl, *Appl. Phys. Lett.* 74 (1999) 2364.
- [13] J.M. Zavada, R.A. Mair, C.J. Ellis, J.Y. Lin, H.X. Jiang, R.G. Wilson, P.A. Grudowski, R.D. Dupuis, *Appl. Phys. Lett.* 75 (1999) 790.
- [14] H.J. Lozykowski, W.M. Jadwisieniczak, I. Brown, *J. Appl. Phys.* 88 (2000) 210.
- [15] U. Wahl, A. Vantomme, G. Langouche, J.P. Araujo, L. Peralta, J.G. Correia, *J. Appl. Phys.* 88 (2000) 1319.
- [16] J.B. Gruber, B. Zandi, H.J. Lozykowski, W.M. Jadwisieniczak, I. Brown, *J. Appl. Phys.* 89 (2001) 7973.
- [17] C.J. Ellis, R.M. Mair, J. Li, J.Y. Lin, H.X. Jiang, J.M. Zavada, R.G. Wilson, *Mater. Sci. Eng. B* 81 (2001) 167.
- [18] T. Monteiro, C. Boemare, M.J. Soares, R.A. Sa Ferreira, L.D. Carlos, K. Lorenz, R. Vianden, E. Alves, *Physica B* 308–310 (2001) 22.
- [19] S.F. Song, W.D. Chen, F. Su, J. Zhu, K. Ding, C.C. Hsu, *J. Cryst. Growth* 267 (2004) 400.
- [20] G.A. Hirata, F. Ramos, R. Garcia, E.J. Bosze, J. Mckittrick, O. Contreras, O. Contreras, *Phys. Status Solidi A* 188 (2001) 179.
- [21] H. Wu, C.B. Poitras, M. Lipson, M. Spencer, J. Hunting, F. DiSalvo, *Appl. Phys. Lett.* 86 (2005) 191918.
- [22] H. Wu, C.B. Poitras, M. Lipson, M. Spencer, J. Hunting, F. DiSalvo, *Appl. Phys. Lett.* 88 (2006) 011921.
- [23] T. Yamada, H. Nanbu, H. Yamane, K. Kohiro, Y. Tsuchida, *Jpn. J. Appl. Phys.* 45 (2006) L194.
- [24] A. El-Himri, D. Perez-Coll, P. Nunez, I.R. Martin, V. Lavin, V.D. Rodriguez, *J. Solid State Chem.* 177 (2004) 4213.
- [25] M. Nyk, R. Kudrawiec, W. Strek, J. Misiewicz, *Opt. Mater.* 28 (2006) 767.
- [26] U. Hömmerich, J.T. Seo, M. Thaik, J.D. Mackenzie, C.R. Abernathy, S.J. Pearton, R.G. Wilson, J.M. Zavada, *MRS Internet J. Nitride Semicond. Res.* 4S1 (1999) G11.6.
- [27] C.W. Lee, H.O. Everitt, D.S. Lee, A.J. Steckl, *J. Appl. Phys.* 95 (2004) 7717.
- [28] J. Hegarty, D.L. Huber, W.M. Yen, *Phys. Rev. B* 25 (1982) 5638.
- [29] M.J. Weber, *Phys. Rev.* 156 (1967) 231.
- [30] E. Nyein, U. Hömmerich, D.S. Lee, A.J. Steckl, J.M. Zavada, *Phys. Status Solidi C* 2 (2005) 2796.

Intensity parametrizations for electric-dipole transitions between Stark components in $\text{Er}^{3+}:\text{Y}_3\text{Al}_5\text{O}_{12}$

Gary W. Burdick^{a,*}, John B. Gruber^b, Kelly L. Nash^b, Sreerenjini Chandra^b, Dhiraj K. Sardar^b

^a Department of Physics, Andrews University, Berrien Springs, MI 49104, United States of America

^b Department of Physics and Astronomy, The University of Texas at San Antonio, San Antonio, TX 78249, United States of America

ARTICLE INFO

Article history:

Received 18 June 2008

Received in revised form 1 August 2008

Accepted 5 November 2008

Available online 14 November 2008

Keywords:

Er:YAG

Absorption spectroscopy

f-Electron parametrization

ABSTRACT

Trivalent erbium Er^{3+} ($4f^{11}$), as a dopant in the laser host material $\text{Y}_3\text{Al}_5\text{O}_{12}$ (YAG), is a well-known and popular activator ion in a medium having optical, thermal, and mechanical properties suitable for numerous photonic applications. Despite its technological importance, a detailed intensity analysis of transitions between individual Stark components has not previously been attempted. This work presents an intensity analysis for Er:YAG, achieving good agreement between measured and calculated Stark-component transition intensities. Ambiguities in the parametrization due to different possible orientations of the quantization axes are addressed. Use of the “vector crystal field” parametrization resolves additional ambiguities that arise in the transition intensity parameters for low symmetry systems, and allows for a new definition for polarization-resolved Judd-Ofelt parameters, which can have wide-ranging applicability for polarized multiplet-to-multiplet intensity calculations.

© 2008 Elsevier B.V. All rights reserved.

1. Introduction

Recently there has been a renewed interest in the examination of crystal-field parametrizations for lanthanide systems having low symmetry. This arises from a need to characterize trivalent lanthanide ions in low symmetry hosts having technological importance [1–4]. One concern for the rationalization of low symmetry crystal-field parameters is that different orientations of the quantization axes may be used, yielding seemingly disparate parameter sets that give identical calculations of theoretical energy levels [5–7].

An issue that has received less attention is the ambiguity this produces in the determination of intensity parameters for calculating transitions between energy levels in these systems. So long as the standard isotropic Judd-Ofelt parametrization for multiplet-to-multiplet transitions is used, the intensity parameters will be independent of the selection choice made for crystal-field quantization direction [8]. However, for the characterization of transitions between Stark-component energy levels, an extended set of intensity parameters must be used that are sensitive to the orientation of the quantization axes.

The analysis of Stark-component transition intensities for low symmetry systems is far scarcer in the literature [9] than are the crystal-field energy level analyses, even though both must be

understood to completely rationalize the observed data for technologically important materials. One prominent exception has been the analysis of intensities in D_2 symmetry for Nd:YAG [10]. However, that work neglected to consider parameter ambiguities that arise from multiple local minima [11] and from the multiplicity of identical solutions that arise due to having independent polarization directions [12].

In the present study, we analyze the crystal-field energy level and (Stark) transitions of Er^{3+} ($4f^{11}$) in YAG. Parameter ambiguities potentially arising from different sources are examined. First, we examine the multiple solutions due to alternate choices for the quantization axes. Then we examine the potential for multiple local minima and the multiplicity of identical solutions arising from the independent polarization directions. By redefining the standard Judd-Ofelt parameters as rotationally invariant intensity parameter strengths, we develop the idea of polarization-separated subsets of the Judd-Ofelt parameters.

2. Energy level analysis

The 125 experimental energy levels analyzed in this study span $29\ 2S+1L_J$ multiplet manifolds up to $44,000\text{ cm}^{-1}$. Each energy level in the D_2 site symmetry of the Er^{3+} ion is a Kramer's doublet, the states of each doublet having irrep labels $\Gamma_{1/2}$ and $\Gamma_{3/2}$. The Er:YAG crystals used in the present study are the same samples that were used in the previously reported crystal-field splitting structure study of Gruber et al. [13] but their analysis did not include an intensity analysis of the individual transitions between Stark levels.

* Corresponding author. Tel.: +1 269 471 3501; fax: +1 269 471 3509.
E-mail address: gburdick@andrews.edu (G.W. Burdick).

Table 1

Crystal-field energy parameters (in cm^{-1}) for the six different D_2 symmetry orientations of Er:YAG.

Crystal-field parameter	Value Set 1	Value Set 2	Value Set 3
B_0^2	−443(14)	102(17)	341(15)
B_2^2	±97(12)	±320(10)	±223(11)
B_0^4	−1687(47)	678(58)	−173(51)
B_2^4	±538(39)	±958(31)	±1496(28)
B_4^4	847(33)	−1132(33)	−420(41)
B_0^6	623(46)	±628(52)	−1178(41)
B_2^6	±152(46)	±422(40)	±323(32)
B_4^6	1010(24)	676(31)	529(28)
B_6^6	±187(32)	±664(30)	±441(46)
D_0^4	15.4(1.7)	−6.2(0.7)	1.6 (0.2)
D_2^4	[±4.9]	[±8.8]	[±13.7]
D_4^4	[−7.8]	[10.4]	[3.9]
D_0^6	3.7(0.9)	−3.8(1.0)	−7.0(1.8)
D_2^6	[±0.9]	[±2.5]	[±1.9]
D_4^6	[6.0]	[4.0]	[3.2]
D_6^6	[±1.1]	[±4.0]	[±2.6]

The present analysis also has allowed identification of additional energy levels not reported in the previous study.

The electronic energy level structure of Er:YAG is analyzed by means of a model Hamiltonian defined to operate within the $4f^{11}$ electronic configuration of Er^{3+} . All parts of the Hamiltonian that depend upon 4f-electron radial coordinates or describe intermixing from excited configurations are represented as variable parameters [14,15]. Wavefunctions defined within the model Hamiltonian may then be used for evaluation of transition intensities between $4f^{11}$ states.

It is well understood that for lanthanide systems having low site symmetry, different possible orientations of the crystal-field quantization axes will result in different parameter sets that yield identical calculated energy levels. For D_2 symmetry, such as the Er:YAG system examined here, there are three different orientations of the quantization z-axis for which only the nine crystal-field parameters B_q^k listed in the first column of Table 1 are non-zero. For each of these three z-axis orientations, there exist two orientations of the x-axis, resulting in six alternative sets of crystal-field parameters.

Sets of crystal-field parameters corresponding to the six orientations of the quantization axes are presented in the three numerical columns of Table 1, identified as Sets #1–3 in Morrison and Leavitt [16] notation. Each column presents two possible sets of parameter values, indicated by the top and bottom symbols of the $\pm$ ($\mp$) signs on the $q=2, 6$ parameters. Set 1a (upper sign) parameters represent the “standardized” parameter set as defined by Rudowicz [17]. Set 3b (lower sign) parameters presented in Table 1 are similar to those previously reported by Gruber et al. [13]. Converted from unit-tensor to spherical-tensor (Wybourne) notation [8], Gruber’s crystal-field parameters become: $B_0^2 = 326$, $B_2^2 = 227$, $B_0^4 = -199$, $B_2^4 = -1590$, $B_4^4 = -449$, $B_0^6 = -1164$, $B_2^6 = -283$, $B_4^6 = 496$, and $B_6^6 = -402 \text{ cm}^{-1}$.

Values of the correlation-crystal-field delta-function [18,19] parameters D_q^k and D_q^6 are also presented in the three numerical columns of Table 1. The relationship between the orthogonal correlation-crystal-field parameters [20,21] and the delta-function-restricted parameters are given elsewhere [22]. Rather than directly fitting all nine correlation-crystal-field delta-function parameters, a simplifying assumption has been made that the q -dependence of the D_q^k scales with respect to the B_q^k . That is, the ratios D_q^k/D_0^k are fixed to the respective B_q^k/B_0^k ratios, reducing the number of freely

fit correlation-crystal-field parameters to three: D_0^2 , D_0^4 , and D_0^6 . The rank-two parameters D_q^2 do not have a statistically significant influence on the energy level fitting for Er^{3+} , and have therefore been omitted from the fitting presented in Table 1.

The standard deviation of the fitted energy levels with respect to experimentally determined values is 12.66 cm^{-1} (rms error of 11.21 cm^{-1}), compared to the rms deviation of 13.20 cm^{-1} reported by Gruber et al. [13]. This fitting improvement is predominately due to two factors: improved correlation-crystal-field parametrization from using the delta-function model rather than the previous arbitrary choice of a single parameter (G_{10A}^4), and corrected values for the atomic operators $\mathbf{m}_j$ and $\mathbf{p}_k$. [23] Details of the experimental and calculated energy levels will be presented elsewhere [24].

3. Intensity analysis

Following the notation of Reid and Richardson [25,26] transition linestrengths are calculated by evaluating:

$$S_{i \rightarrow f} = e^2 \left| \sum_{\lambda \ell p} A_{\ell p}^{\lambda} \sum_{\ell q} (\lambda \ell, 1(-q) | tp) (-1)^q \langle \psi_i | \mathbf{U}_{\ell}^{\lambda} | \psi_f \rangle \right|^2 + |\langle \psi_i | \mathbf{m} | \psi_f \rangle|^2 \quad (1)$$

where $q=0, \pm 1$, $\ell = p + q$, and p is restricted by the D_2 site symmetry to even integers with $|p| \leq t$. The first term, giving the electric-dipole contribution, is modeled by the $A_{\ell p}^{\lambda}$ parameters and uses calculated $U_{\ell}^{(\lambda)}$ matrix elements. The second term gives the magnetic-dipole contribution and is calculated directly. For ground-state transitions of Er^{3+} , only the $^4I_{15/2} \rightarrow ^4I_{13/2}$, $^2K_{15/2}$ and $^2K_{13/2}$ transitions have a magnetic dipole contribution greater than 2% of the observed intensity.

For D_2 site symmetry, there are 18 independent $A_{\ell p}^{\lambda}$ parameters, nine which are allowed under the “superposition model” approximation: $A_{32}^2, A_{32}^4, A_{52}^4, A_{52}^6, A_{54}^6, A_{52}^6, A_{72}^6, A_{74}^6$, and A_{76}^6 ; and an additional nine parameters which arise through non-cylindrically symmetric ligand/ion interactions: [27] $A_{20}^2, A_{22}^2, A_{40}^4, A_{42}^4, A_{44}^4, A_{60}^6, A_{62}^6, A_{64}^6$, and A_{66}^6 . Non-independent $p = \text{negative}$ parameters are related to these by the relationship $(A_{\ell p}^{\lambda})^* = (-1)^{t+p+1} A_{\ell, -p}^{\lambda}$. Previous work has shown that the additional “non-superposition model” parameters, which incorporate non-cylindrically symmetric interactions due to the “second-nearest” neighboring ligands, are necessary to adequately rationalize transition line strengths in the YAG system [10].

As was the case for the crystal-field and correlation-crystal-field energy level parameters, calculated intensity parameter values for transitions between Stark levels are dependent upon the orientation of the quantization axes. As well, it is now known that once the quantization axes are selected, there are additional ambiguities in the intensity parameters that yield multiple sets of parameter values which give identical calculated intensities.

In order to rationalize these multiple sets of parameters, we use an alternative, “vector crystal field” parametrization $B_{\ell q}^{\lambda}$ [12] which yields the following expansion for transition linestrengths:

$$S_{i \rightarrow f} = e^2 \left| \sum_{\lambda \ell q} B_{\ell q}^{\lambda} \langle \psi_i | U_{\ell}^{(\lambda)} | \psi_f \rangle \right|^2 + |\langle \psi_i | \mathbf{m} | \psi_f \rangle|^2 \quad (2)$$

Comparing Eq. (1) with Eq. (2), we see there is a direct linear transformation between the $B_{\ell q}^{\lambda}$ and $A_{\ell p}^{\lambda}$ parametrizations, given by

$$B_{(p+q)q}^{\lambda} = \sum_t A_{\ell p}^{\lambda} (-1)^q (\lambda(p+q), 1-q | tp) \quad (3)$$

Table 2Transformations between the A_{tp}^λ and $B_{\ell i}^\lambda$ parameter sets in D_2 symmetry.

	A_{20}^2			A_{22}^2			A_{32}^2		
B_{1x}^2	-1/2			$-1/\sqrt{6}$			$1/\sqrt{3}$		
B_{1y}^2	1/2			$-1/\sqrt{6}$			$1/\sqrt{3}$		
B_{2z}^2	0			$\sqrt{2/3}$			$1/\sqrt{3}$		
	A_{32}^4	A_{40}^4	A_{42}^4	A_{44}^4	A_{52}^4	A_{54}^4			
B_{1x}^4	$1/\sqrt{24}$	-1/2	$-3\sqrt{40}$	0	$\sqrt{7/30}$	0			
B_{1y}^4	$1/\sqrt{24}$	1/2	$-3\sqrt{40}$	0	$\sqrt{7/30}$	0			
B_{2z}^4	$-1/\sqrt{3}$	0	$1/\sqrt{5}$	0	$\sqrt{7/15}$	0			
B_{3x}^4	$-7\sqrt{24}$	0	$-\sqrt{7/40}$	$-1/\sqrt{10}$	$-1/\sqrt{30}$	$\sqrt{2/5}$			
B_{3y}^4	$7/\sqrt{24}$	0	$\sqrt{7/40}$	$-1/\sqrt{10}$	$1/\sqrt{30}$	$\sqrt{2/5}$			
B_{4z}^4	0	0	0	$2/\sqrt{5}$	0	$1/\sqrt{5}$			
	A_{52}^6	A_{54}^6	A_{60}^6	A_{62}^6	A_{64}^6	A_{66}^6	A_{72}^6	A_{74}^6	A_{76}^6
B_{1x}^6	$\sqrt{5/78}$	0	-1/2	$-\sqrt{5/21}$	0	0	$\sqrt{18/91}$	0	0
B_{1y}^6	$\sqrt{5/78}$	0	1/2	$-\sqrt{5/21}$	0	0	$\sqrt{18/91}$	0	0
B_{2z}^6	$-4\sqrt{39}$	0	0	$\sqrt{2/21}$	0	0	$\sqrt{45/91}$	0	0
B_{3x}^6	$-3\sqrt{13}$	$1\sqrt{52}$	0	$-\sqrt{3/14}$	$-\sqrt{5/28}$	0	$-\sqrt{5/91}$	$\sqrt{55/182}$	0
B_{3y}^6	$3\sqrt{13}$	$1\sqrt{52}$	0	$\sqrt{3/14}$	$-\sqrt{5/28}$	0	$\sqrt{5/91}$	$\sqrt{55/182}$	0
B_{4z}^6	0	$-\sqrt{10/39}$	0	0	$\sqrt{8/21}$	0	0	$\sqrt{33/91}$	0
B_{5x}^6	0	$-\sqrt{55/156}$	0	0	$-\sqrt{11/84}$	$-1/\sqrt{14}$	0	$-\sqrt{3/182}$	$\sqrt{3/7}$
B_{5y}^6	0	$\sqrt{55/156}$	0	0	$\sqrt{11/84}$	$-1/\sqrt{14}$	0	$\sqrt{3/182}$	$\sqrt{3/7}$
B_{6z}^6	0	0	0	0	0	$\sqrt{6/7}$	0	0	$1/\sqrt{7}$

where the $q = 0, \pm 1$ represent the spherical polarization bases. Converted to Cartesian bases via the following identification:

$$B_{\ell x}^\lambda = \frac{-B_{\ell 1}^\lambda + B_{\ell -1}^\lambda}{\sqrt{2}}, \quad B_{\ell y}^\lambda = \frac{i(B_{\ell 1}^\lambda + B_{\ell -1}^\lambda)}{\sqrt{2}}, \quad B_{\ell z}^\lambda = B_{\ell 0}^\lambda \quad (4)$$

there are six x-polarization $B_{\ell x}^\lambda$ parameters, six y-polarization $B_{\ell y}^\lambda$ parameters, and six z-polarization $B_{\ell z}^\lambda$ parameters in D_2 symmetry. Table 2 presents the transformation matrices between the A_{tp}^λ and $B_{\ell i}^\lambda$ ($i = x, y, z$) parametrizations.

In this vector-crystal-field parametrization, the multiplicity of parameter sets is resolved as independent overall signs on each separated-polarization subset of parameters. That is, for each independent polarization direction, the overall sign on the subset of intensity parameters for that polarization is indeterminate. Thus, for D_2 symmetry the three independent polarization directions result in $(2)^3 = 8$ parameter sets that yield identical line strengths.

Table 3 presents the $B_{\ell i}^\lambda$ ($i = x, y, z$) parameters fitted to 88 ground-state transitions by minimizing the standard deviation:

$$\sigma = \sqrt{\sum_i \frac{[(E_i - C_i)/E_i]^2}{N - P}} \quad (5)$$

where E_i and C_i are the experimental and calculated values, respectively, $N = 88$ data points and $P = 18$ parameters. The fitting standard deviation is $\sigma = 0.280$ (rms error = 0.250), representing a 25% overall deviation between experimental and calculated values. Using a method of random starting parameter values [28] we found that this is an extremely robust solution, with the eightfold solution being the only minimum found from all reasonable ranges of starting parameters. This is in marked contrast to previous calculations of Nd:YAG [11] and oxydiacetate systems [29] where dozens of local

minima were found. This provides us with some degree of confidence that the measured intensities are self-consistent and that the calculated parameter values are reliable.

The six numerical columns of Table 3 present parameter values for each of the six crystal-field quantization orientations given in Table 1. Sets “a” correspond to the top signs for the $p = 2, 6$ parameters given in Table 1, while sets “b” correspond to the bottom signs. Each set of parameter values presented in Table 3 represents an eightfold solution. The other seven solutions can be derived from the one presented in Table 3 by independently changing the sign on all $B_{\ell x}^\lambda$ parameters, changing the sign on all $B_{\ell y}^\lambda$ parameters, and/or changing the sign on all $B_{\ell z}^\lambda$ parameters.

The three panels of Table 4 present the same parameter solutions in standard A_{tp}^λ notation. The first column presents the solutions of Table 3, with the top sign on the $p = 2, 6$ parameters corresponding to sets “a” and the bottom sign corresponding to sets “b”. The second, third, and fourth numerical columns of Table 4 present solutions from Table 3 with the sign on the $B_{\ell z}^\lambda$ parameters reversed (“-z” column), the sign on the $B_{\ell x}^\lambda$ ($B_{\ell y}^\lambda$ for set “b”) parameters reversed (“-x/-y” column), and the sign on $B_{\ell y}^\lambda$ ($B_{\ell x}^\lambda$ for set “b”) parameters reversed (“-y/-x” column). The other four solutions may be derived from these four solutions by reversing the sign on all parameters.

It is possible to relate the A_{tp}^λ intensity parameters to the Judd-Ofelt parameters for multiplet-to-multiplet transitions by the following expression:

$$\Omega_\lambda = \frac{1}{2\lambda + 1} \sum_{tp} |A_{tp}^\lambda|^2 = \frac{1}{2\lambda + 1} \sum_t \left[(A_{t0}^\lambda)^2 + 2 \sum_{p>0} |A_{tp}^\lambda|^2 \right] \quad (6)$$

Table 3

Intensity parameters in *vector crystal-field* notation corresponding to the six different D_2 symmetry orientations given in Table 1. Sets “a” (“b”) correspond to the top (bottom) signs for the $p = 2$, 6 parameters given in Table 1. The $B_{\ell x}^\lambda$ and $B_{\ell z}^\lambda$ parameters have units $i \times 10^{-12}$ cm; $B_{\ell y}^\lambda$ parameters have units 1×10^{-12} cm. The Ω_λ parameters have units 10^{-20} cm².

Parameter	Set 1a	Set 1b	Set 2a	Set 2b	Set 3a	Set 3b
B_{1x}^2	40(15)	−192(13)	192(13)	−88(15)	88(15)	−40(15)
B_{1y}^2	192(13)	−40(15)	88(15)	−192(13)	40(15)	−88(15)
B_{2z}^2	88(15)	−88(15)	40(15)	−40(15)	192(13)	−192(13)
B_{1x}^4	6(13)	−114(12)	−31(16)	−18(15)	−27(14)	−182(15)
B_{1y}^4	114(12)	−6(13)	18(15)	31(16)	182(15)	27(14)
B_{2z}^4	12(17)	−12(17)	−266(11)	266(11)	−117(15)	117(15)
B_{3x}^4	−282(13)	82(16)	−137(12)	−20(16)	3(17)	215(10)
B_{3y}^4	82(16)	−282(13)	−20(16)	−137(12)	215(10)	3(17)
B_{4z}^4	24(14)	24(14)	94(14)	94(14)	77(14)	77(14)
B_{1x}^6	−220(11)	−112(9)	35(8)	6(6)	−88(8)	66(12)
B_{1y}^6	112(9)	220(11)	−6(6)	−35(8)	−66(12)	88(8)
B_{2z}^6	60(7)	−60(7)	−56(9)	56(9)	−110(10)	110(10)
B_{3x}^6	84(11)	−52(8)	173(9)	130(8)	0(7)	160(10)
B_{3y}^6	−52(8)	84(11)	130(8)	173(9)	160(10)	0(7)
B_{4z}^6	−95(8)	−95(8)	−178(12)	−178(12)	−88(9)	−88(9)
B_{5x}^6	43(10)	129(10)	−25(10)	15(8)	97(6)	166(10)
B_{5y}^6	−129(10)	−43(10)	−15(8)	25(10)	−166(10)	−97(6)
B_{6z}^6	−67(7)	67(7)	−150(12)	150(12)	109(8)	−109(8)
Ω_2	1.85	1.85	1.85	1.85	1.85	1.85
Ω_4	2.22	2.22	2.22	2.22	2.22	2.22
Ω_6	1.63	1.63	1.63	1.63	1.63	1.63
Ω_{2x}	0.06	1.48	1.48	0.31	0.31	0.06
Ω_{2y}	1.48	0.06	0.31	1.48	0.06	0.31
Ω_{2z}	0.31	0.31	0.06	0.06	1.48	1.48
Ω_{4x}	1.76	0.44	0.44	0.02	0.02	1.76
Ω_{4y}	0.44	1.76	0.02	0.44	1.76	0.02
Ω_{4z}	0.02	0.02	1.76	1.76	0.44	0.44
Ω_{6x}	0.88	0.49	0.49	0.26	0.26	0.88
Ω_{6y}	0.49	0.88	0.26	0.49	0.88	0.26
Ω_{6z}	0.26	0.26	0.88	0.88	0.49	0.49

That is, under the specific conditions that individual Stark splittings within the initial and final multiplets can be neglected, each Stark level of the initial multiplet can be considered to be essentially equally populated, and the initial and final multiplet states have well-defined J character, summing the electric-dipole contribution of Eq. (1) over all Stark levels gives:

$$S_{\psi J \rightarrow \psi' J'}^{\text{ED}} = e^2 \sum_{\lambda t p} \frac{1}{2\lambda + 1} |A_{tp}^\lambda|^2 \langle \psi J || \mathbf{U}^{(\lambda)} || \psi' J' \rangle^2$$

$$= e^2 \sum_{\lambda} \Omega_\lambda \langle \psi J || \mathbf{U}^{(\lambda)} || \psi' J' \rangle^2 \quad (7)$$

where the second line reproduces the famous Judd–Ofelt equation. As the specific conditions requiring the absence of crystal-field mixings of different J -multiplets and the absence of crystal-field splittings within the multiplets are not well-met in real systems, one would not expect the Ω_λ parameters calculated from the A_{tp}^λ to equal published Ω_λ parameters from multiplet-to-multiplet fittings. However, treated as interaction-strength parameters, they provide rotationally invariant values that may be used for comparison purposes.

The bottom part of each section of Table 4 presents Ω_λ parameters calculated from Eq. (6). As can be seen from this table, the Ω_λ parameters are invariant with respect to both coordinate direction and multiple parameter solutions within a particular coordinate orientation. These values are $\Omega_2 = 1.85 \times 10^{-20}$ cm², $\Omega_4 = 2.22 \times 10^{-20}$ cm², and $\Omega_6 = 1.63 \times 10^{-20}$ cm².

For comparison, literature values of the Judd–Ofelt parameters are, $\Omega_2 = 0.740$, $\Omega_4 = 0.330$, and $\Omega_6 = 1.020 \times 10^{-20}$ cm², from Kaminskii [30] and $\Omega_2 = 0.724$, $\Omega_4 = 0.327$, and $\Omega_6 = 0.790 \times 10^{-20}$ cm², from Sardar et al. [31]. These values

are the same order of magnitude, but somewhat smaller than our calculated values, a phenomenon that has been observed previously for Nd:YAG [10].

When the summation in Eq. (5) is restricted to $t = \text{odd}$ terms, only the nine superposition-model allowed parameters are included in the calculated Ω_λ parameters. These values are presented as $\Omega_{\lambda}^{\text{super}}$ in Table 4, along with the percentage of the complete Ω_λ parameter represented. As can be seen from Table 4, these superposition-restricted Ω_λ parameters are not invariant with respect to the different identical parameter solutions. That is, different solutions intermix the $t = \text{even}$ with $t = \text{odd}$ parameter values differently. Thus, care should be taken with interpreting fitted A_{tp}^λ parameters to determine whether the superposition model might be valid in a particular system.

However, it should be noted that for each set of $\Omega_{\lambda}^{\text{super}}$ parameter values listed in Table 4, there is an identical set for each orientation of the crystal-field. This occurs because a rotation of the crystallographic parametrization axis will not intermix A_{tp}^λ parameters with different t (or λ), but will only intermix different values of p .

Alternatively, we can use the vector crystal-field $B_{\ell q}^\lambda$ parameters to define the Ω_λ parameters. Rewriting Eq. (6) in terms of the $B_{\ell q}^\lambda$ gives:

$$\Omega_\lambda = \frac{1}{2\lambda + 1} \sum_{\ell q} |B_{\ell q}^\lambda|^2 = \frac{2}{2\lambda + 1} \sum_{\ell > 0} (|B_{\ell x}^\lambda|^2 + |B_{\ell y}^\lambda|^2 + |B_{\ell z}^\lambda|^2) \quad (8)$$

where the 2 on the right hand side comes from the $\ell = \text{negative}$ contributions to the summation. As can be seen from the right hand side of Eq. (8), the contributions from each of the three polarizations are separable, allowing one to define polarization-dependent Judd–

Table 4
Intensity parameters in Reid-Richardson notation corresponding to the six different D_2 symmetry orientations given in Table 1. The $\pm$ ($\mp$) signs correspond to the respective signs for $p = 2, 6$ parameters in Table 1. Parameters have units $i \times 10^{-12}$ cm. The Ω_λ parameters have units 10^{-20} cm².

Set 1 parameter	Value	–z value	–x/–y value	–y/–x value
A_{20}^2	152(19)	152(19)	232(21)	232(21)
A_{22}^2	$\mp 23(17)$	$\mp 167(11)$	$\pm 10(15)$	$\pm 134(14)$
A_{32}^2	$\pm 185(11)$	$\pm 83(17)$	$\pm 139(13)$	$\mp 37(14)$
A_{32}^4	$\pm 214(14)$	$\pm 228(13)$	$\mp 93(18)$	$\pm 79(13)$
A_{40}^4	108(18)	108(18)	120(17)	–120(17)
A_{42}^4	$\pm 101(16)$	$\pm 90(14)$	$\mp 129(17)$	$\pm 140(18)$
A_{44}^4	85(13)	41(16)	–93(14)	137(14)
A_{52}^4	$\pm 133(13)$	$\pm 116(15)$	$\pm 24(13)$	$\mp 7(16)$
A_{54}^4	–115(17)	–137(14)	241(13)	–219(13)
A_{52}^6	$\mp 131(10)$	$\mp 54(9)$	$\pm 61(9)$	$\mp 138(8)$
A_{54}^6	–49(9)	–145(8)	–22(10)	118(9)
A_{60}^6	332(14)	332(14)	108(15)	108(15)
A_{62}^6	$\pm 8(10)$	$\mp 29(9)$	$\mp 129(10)$	$\pm 166(9)$
A_{64}^6	–134(9)	–17(9)	–32(10)	–85(10)
A_{66}^6	$\mp 39(7)$	$\pm 85(8)$	$\mp 16(7)$	$\mp 108(7)$
A_{72}^6	$\mp 38(8)$	$\mp 122(10)$	$\pm 198(8)$	$\mp 113(9)$
A_{74}^6	–61(8)	53(9)	–143(9)	29(10)
A_{76}^6	$\mp 81(10)$	$\mp 31(10)$	$\mp 138(9)$	$\pm 87(9)$
Ω_2	1.85	1.85	1.85	1.85
Ω_4	2.22	2.22	2.22	2.22
Ω_6	1.63	1.63	1.63	1.63
Ω_2 super	1.37(74%)	0.28(15%)	0.77(42%)	0.05(3%)
Ω_4 super	1.70(77%)	1.87(84%)	1.49(67%)	1.21(54%)
Ω_6 super	0.48(30%)	0.66(40%)	1.27(78%)	0.83(51%)
Set 2 parameter	Value	–y/–x value	–z value	–x/–y value
A_{20}^2	–104(23)	–280(15)	–104(23)	280(15)
A_{22}^2	$\mp 82(15)$	$\mp 10(14)$	$\mp 147(13)$	$\pm 75(17)$
A_{32}^2	$\pm 185(11)$	$\pm 83(17)$	$\pm 139(13)$	$\mp 37(14)$
A_{32}^4	$\pm 214(14)$	$\pm 228(13)$	$\mp 93(18)$	$\pm 79(13)$
A_{40}^4	49(20)	13(24)	49(20)	–13(24)
A_{42}^4	$\mp 64(14)$	$\mp 30(12)$	$\pm 174(13)$	$\mp 207(11)$
A_{44}^4	134(13)	121(13)	–34(14)	47(16)
A_{52}^4	$\mp 166(17)$	$\mp 177(12)$	$\pm 197(14)$	$\mp 186(14)$
A_{54}^4	–57(13)	–32(17)	–141(12)	116(14)
A_{52}^6	$\pm 23(9)$	$\mp 99(8)$	$\mp 49(9)$	$\pm 171(8)$
A_{54}^6	138(10)	120(9)	–42(10)	61(9)
A_{60}^6	–41(9)	–30(11)	–41(9)	30(11)
A_{62}^6	$\mp 52(9)$	$\mp 178(7)$	$\mp 17(8)$	$\pm 143(7)$
A_{64}^6	–234(9)	114(10)	–14(11)	–106(10)
A_{66}^6	$\mp 128(11)$	$\mp 136(11)$	$\pm 150(11)$	$\mp 142(12)$
A_{72}^6	$\mp 37(8)$	$\mp 92(8)$	$\pm 43(9)$	$\pm 13(8)$
A_{74}^6	61(10)	–78(10)	275(8)	–136(10)
A_{76}^6	$\mp 83(8)$	$\mp 64(10)$	$\pm 31(9)$	$\mp 50(10)$
Ω_2	1.85	1.85	1.85	1.85
Ω_4	2.22	2.22	2.22	2.22
Ω_6	1.63	1.63	1.63	1.63
Ω_2 super	1.37(74%)	0.28(15%)	0.77(42%)	0.05(3%)
Ω_4 super	1.70(77%)	1.87(84%)	1.49(67%)	1.21(54%)
Ω_6 super	0.48(30%)	0.66(40%)	1.27(78%)	0.83(51%)
Set 3 parameter	Value	–x/–y value	–y/–x value	–z value
A_{20}^2	–48(24)	128(18)	–128(18)	–48(24)
A_{22}^2	$\pm 105(14)$	$\pm 177(12)$	$\pm 137(16)$	$\mp 209(11)$
A_{32}^2	$\pm 185(11)$	$\pm 83(17)$	$\pm 139(13)$	$\mp 37(14)$
A_{32}^4	$\pm 214(14)$	$\pm 228(13)$	$\mp 93(18)$	$\pm 79(13)$
A_{40}^4	209(20)	155(21)	–155(21)	209(20)
A_{42}^4	$\mp 37(13)$	$\mp 60(14)$	$\mp 45(13)$	$\pm 68(16)$
A_{44}^4	0(15)	2(15)	136(14)	–138(15)
A_{52}^4	$\pm 34(16)$	$\pm 61(17)$	$\mp 221(13)$	$\pm 194(13)$
A_{54}^4	173(15)	169(12)	–100(13)	103(15)
A_{52}^6	$\pm 108(9)$	$\pm 153(9)$	$\mp 116(11)$	$\mp 33(9)$
A_{54}^6	–89(9)	26(8)	64(8)	–178(8)
A_{60}^6	22(14)	–154(14)	154(7)	22(14)
A_{62}^6	$\pm 115(9)$	$\pm 29(10)$	$\mp 97(9)$	$\pm 183(8)$
A_{64}^6	–217(8)	–147(8)	38(10)	–108(10)
A_{66}^6	$\pm 119(8)$	$\pm 171(8)$	$\pm 30(8)$	$\mp 82(8)$
A_{72}^6	$\mp 109(9)$	$\mp 30(10)$	$\mp 125(10)$	$\pm 47(10)$
A_{74}^6	1(9)	26(9)	–132(7)	107(9)
A_{76}^6	$\mp 4(8)$	$\mp 131(9)$	$\pm 212(8)$	$\mp 86(9)$
Ω_2	1.85	1.85	1.85	1.85
Ω_4	2.22	2.22	2.22	2.22

Table 4 (Continued)

Set 1 parameter	Value	–z value	–x/–y value	–y/–x value
Ω_6	1.63	1.63	1.63	1.63
Ω_2 super	1.37(74%)	0.28(15%)	0.77(42%)	0.05(3%)
Ω_4 super	1.70(77%)	1.87(84%)	1.49(67%)	1.21(54%)
Ω_6 super	0.48(30%)	0.66(40%)	1.27(78%)	0.83(51%)

Ofelt parameters:

$$\Omega_{\lambda x} = \frac{2}{2\lambda + 1} \sum_{\ell > 0} |B_{\ell x}^{\lambda}|^2, \quad \Omega_{\lambda y} = \frac{2}{2\lambda + 1} \sum_{\ell > 0} |B_{\ell y}^{\lambda}|^2, \quad (9)$$

$$\Omega_{\lambda z} = \frac{2}{2\lambda + 1} \sum_{\ell > 0} |B_{\ell z}^{\lambda}|^2$$

where

$$\Omega_{\lambda} = \Omega_{\lambda x} + \Omega_{\lambda y} + \Omega_{\lambda z} \quad (10)$$

The bottom part of Table 3 presents the complete Judd–Ofelt parameters Ω_{λ} along with the separated-polarization $\Omega_{\lambda x}$, $\Omega_{\lambda y}$, and $\Omega_{\lambda z}$ terms. As we have already noted, the Ω_{λ} parameters are invariant with respect to coordinate rotations. But more than this, each of the six sets of $B_{\ell i}^{\lambda}$ ($i = x, y, z$) parameters yields identical $\Omega_{\lambda i}$ parameter values, but with the x, y , and z subscripts permuted in all six possible ways. This means the $\Omega_{\lambda i}$ may be identified with the crystallographic a, b , and c axis directions, independent of the choice of quantization axes.

This provides justification for the idea of formally separating polarization-dependent parts of the Judd–Ofelt parameters. Presentation of separated polarization-dependent parts of the Judd–Ofelt parameters may be able to provide greater information than the current practice of presenting only one set of (isotropic) Judd–Ofelt parameters. See, for example, Ref. [32], where polarization-dependent measurements were taken, but only isotropic Judd–Ofelt parameters were reported.

4. Conclusion

In this study, we analyzed the energy (Stark) levels of Er^{3+} ($4f^{11}$) in YAG and the intensity of absorption transitions from the ground-state Stark level to individual excited Stark levels having an energy up to $50,000 \text{ cm}^{-1}$. Within this energy range, 88 experimental transition line strengths were analyzed in detail with a weighted $(E_i - C_i)/E_i$ standard deviation of 0.28 (rms deviation of 0.25), indicating a 25% overall deviation between calculated and experimental values.

We have presented the six sets of crystal-field parameters arising from the six alternative choices for parametrization axes in D_2 symmetry, and calculated intensity parameters based upon each of these parametrizations. The eightfold sets of intensity parameters arising from each parametrization have been resolved as three arbitrary sign choices for each polarization subset of vector crystal-field parameters. The vector crystal-field parametrization also leads to a new definition for polarization-resolved Judd–Ofelt parameters, which has the potential to have wide-ranging applicability for polarized Judd–Ofelt-type intensity calculations.

Acknowledgements

This research was supported in part by the American Chemical Society Grant No. PRF 43862-B6 and the National Science Foundation Grant No. DMR-0602649.

References

- [1] W. Koechner, *Solid State Laser Engineering*, Springer, New York, 1996.
- [2] A.A. Kaminskii, *Crystalline Lasers: Physical Processes and Operating Schemes*, CRC, New York, 1996.
- [3] R.M. Ranin, *Erbium-Doped Fiber Lasers*, Springer, New York, 1997.
- [4] E. Lippert, G. Rustnad, K. Sternerson, *OSA Trends in Optics and Photonics Series, Advanced Solid-State Photonics*, vol. 83, Optical Society of America, Washington, DC, 2003, p. 266.
- [5] C. Rudowicz, J. Qin, *J. Lumin.* 110 (2004) 39.
- [6] G.W. Burdick, M.F. Reid, *Mol. Phys.* 102 (2004) 1141.
- [7] J. Mulak, M. Mulak, *J. Phys. A: Math. Gen.* 38 (2005) 6081.
- [8] C. Görller-Walrand, K. Binnemans, in: K.A. Gschneidner Jr., L.R. Eyring (Eds.), *Handbook on the Physics and Chemistry of Rare Earths*, vol. 23, North Holland, Amsterdam, 1996, p. 121.
- [9] C. Görller-Walrand, K. Binnemans, in: K.A. Gschneidner Jr., L.R. Eyring (Eds.), *Handbook on the Physics and Chemistry of the Rare Earths*, vol. 25, North Holland, Amsterdam, 1998, p. 101.
- [10] G.W. Burdick, C.K. Jayasankar, F.S. Richardson, M.F. Reid, *Phys. Rev. B* 50 (1994) 16309.
- [11] S.M. Crooks, M.F. Reid, G.W. Burdick, *J. Alloys Compd.* 303 (2000) 383.
- [12] G.W. Burdick, S.M. Crooks, M.F. Reid, *Phys. Rev. B* 59 (1999) R7789.
- [13] J.B. Gruber, J.R. Quagliano, M.F. Reid, F.S. Richardson, M.E. Hills, M.D. Seltzer, S.B. Stevens, C.A. Morrison, T.H. Allik, *Phys. Rev. B* 48 (1993) 15561.
- [14] W.T. Carnall, G.L. Goodman, K. Rajnak, R.S. Rana, *J. Chem. Phys.* 90 (1989) 3443.
- [15] C.A. Morrison, *Angular Momentum Theory Applied to Interactions in Solids*, Springer, New York, 1988.
- [16] C.A. Morrison, R.P. Leavitt, in: K.A. Gschneidner, L. Eyring (Eds.), *Handbook on the Physics and Chemistry of the Rare Earths*, North-Holland, Amsterdam, 1982, p. 632.
- [17] C. Rudowicz, M. Chua, M.F. Reid, *Physica B* 291 (2000) 327.
- [18] B.R. Judd, in: P. Kramer, A. Rieckers (Eds.), *Lecture Notes in Physics*, Springer, Berlin, 1978, p. 417.
- [19] G.W. Burdick, F.S. Richardson, *Chem. Phys.* 228 (1998) 81.
- [20] B.R. Judd, *J. Chem. Phys.* 66 (1977) 3163.
- [21] M.F. Reid, *J. Chem. Phys.* 87 (1987) 2875.
- [22] L.F. McAvien, M.F. Reid, P.H. Butler, *J. Phys. B: At. Mol. Opt. Phys.* 29 (1996) 1421, erratum, 4319.
- [23] X. Chen, G. Liu, J. Margerie, M.F. Reid, *J. Lumin.* 128 (2008) 421.
- [24] G.W. Burdick, J.B. Gruber, K.L. Nash, S. Chandra, D.K. Sardar, manuscript in preparation.
- [25] M.F. Reid, F.S. Richardson, *J. Chem. Phys.* 79 (1983) 5735.
- [26] M.F. Reid, F.S. Richardson, *J. Phys. Chem.* 88 (1984) 3579.
- [27] D.J. Newman, G. Balasubramanian, *J. Phys. C: Solid State Phys.* 8 (1975) 37.
- [28] G.W. Burdick, R.L. Summerscales, S.M. Crooks, M.F. Reid, F.S. Richardson, *J. Alloys Compd.* 303 (2000) 376.
- [29] G.W. Burdick, R.D. Robertson, R.L. Summerscales, *J. Alloys Compd.* 323 (2001) 778.
- [30] A.A. Kaminskii, *Laser Crystals*, Springer, Berlin, 1981.
- [31] D.K. Sardar, C.C. Russell III, J.B. Gruber, T.H. Allik, *J. Appl. Phys.* 97 (2005) 123501.
- [32] D.K. Sardar, P.D. Bella, *J. Appl. Phys.* 76 (1994) 5900.

Correlation between structure variation and luminescence red shift in YAG:Ce

Y.X. Pan^a, W. Wang^a, G.K. Liu^{a,*}, S. Skanthakumar^a, R.A. Rosenberg^b, X.Z. Guo^c, Kewen K. Li^c

^a Chemical Sciences and Engineering Division, Argonne National Laboratory, Argonne, IL 60439, United States

^b Experimental Facilities Division, APS, Argonne National Laboratory, Argonne, IL 60439, United States

^c Boston Applied Technologies Ins., 6F Gill St, Woburn, MA 01801, United States

ARTICLE INFO

Article history:

Received 22 June 2008

Received in revised form 3 February 2009

Accepted 16 April 2009

Available online 23 April 2009

Keywords:

YAG:Ce phosphor

5d–4f transition

Lattice expansion

Crystal-field splitting

ABSTRACT

Red shift of Ce³⁺ luminescence in Y₃Al₅O₁₂ (YAG) co-doped with Gd³⁺ is investigated with X-ray diffraction (XRD) based structural analysis and crystal-field modeling of electronic energy levels. It shows a linear relationship between the lattice expansion induced by substituting Gd³⁺ for Y³⁺ and the red shift in the Ce³⁺ luminescence. A crystal-field analysis of the Ce³⁺ 5d energy levels is conducted to establish the correlation between the YAG lattice expansion and the Ce³⁺ energy level shifts.

© 2009 Elsevier B.V. All rights reserved.

1. Introduction

Phosphor conversion of the UV/blue light emitting diode (pc-LED) radiation into white light emission has been identified as one of promising technologies of solid-state lighting (SSL) for future energy efficient light sources. In comparison with conventional lighting technologies such as fluorescent lamps, white LEDs have advantages of energy saving, long lifetime, while being mercury-free. The current commercial white pc-LEDs are made with a phosphor of Ce³⁺ doped Y₃Al₅O₁₂ (YAG:Ce). As a result of the 4f¹–5d¹ electronic transition, Ce³⁺ in YAG can efficiently absorb blue light from 450 nm to 470 nm and emits a broad band of luminescence in the range of 510 nm to over 600 nm. These spectroscopic properties make YAG:Ce a good phosphor for converting the blue radiation of a LED to white light [1–3]. In pc-LED, white light is created by combination of a part of the blue light from the LED chip and the yellow-red luminescence from the YAG:Ce phosphor. For general application particularly for room lighting, an ideal white light device should accurately simulate the sunlight spectrum in the visible region. However, the color rendering index (CRI) of the current commercial white LED products is not high enough to simulate the sun light because of the lack of red components in the emission spectra of the YAG:Ce phosphor. A practical method to solve this problem is to expand the YAG:Ce emission band or induce a red shift through modifications of the phosphor composition. There are

many studies of red shift of the YAG:Ce luminescence induced by modification of the YAG composition with substitution of Y³⁺ in the YAG lattice with Gd³⁺ or other trivalent ions with an ionic size larger than that of the Y³⁺. With such a modification, the Ce³⁺ emission spectrum can be shifted by more than 30 nm toward the red region [4–7]. In the present work, we report experimental results of the structure characterization and spectroscopic measurements on YAG:Ce modified by Gd³⁺. Based on these results, we attempt to provide a detailed understanding of the consequences of co-doping Gd³⁺ with Ce³⁺ into the lattice of YAG by crystal-field modeling of the correlation between the co-doping induced lattice expansion and the variation of the crystal-field energy levels of Ce³⁺ in Y(Gd)AG.

2. Experimental

Nanosized Y(Gd)AG:Ce crystals with a general composition of (Y_{1-x}Gd_x)₃Al₅O₁₂:Ce were synthesized by a citrate–nitrate gel combustion method as described elsewhere [8]. Briefly, soluble metal citrates and citric acid monohydrate were dissolved and mixed in a mixture of de-ionized water and ethanol. The mixture became viscous and self-propagation combustion was initiated with continuous heating on a hot plate. Phosphor precursors were formed after combustion in a short time. Crystallized phosphors were obtained after sintering the precursors at 850 °C for 4 h under CO atmosphere. A single crystal of YAG:Ce was synthesized at Boston Applied Technologies Ins. XRD measurements were performed with an X-ray diffractometer operating with a Cu K α radiation Ni filter. The powder phosphors were diluted in a layer of optical epoxy and pasted on a piece of glass. The luminescence spectra and efficiency of the powder phosphors were measured with a photon counting spectrometer connected with a light integrating sphere at room temperature, while the low temperature measurements were carried out using an optical cryostat and a spectrometer connected with a photomultiplier.

* Corresponding author.

E-mail address: gkliu@anl.gov (G.K. Liu).

Fig. 1. XRD spectra of $(Y_{1-x}Gd_x)_2.97Al_5O_{12}:Ce_{0.03}$ powder phosphors crystallized at $1200^\circ C$ for 2 h. $x = 0, 0.03, 0.06$, and 0.1 , respectively, for samples (a), (b), (c), and (d). Peaks marked by “*” do not belong to the intrinsic YAG structure.

3. Results and discussion

The powder samples of YAG:Ce co-doped with Gd have high quality of crystalline structure. Fig. 1 shows the XRD spectra of $(Y_{1-x}Gd_x)_2.97Al_5O_{12}:1\%Ce$ with x varying from 0 to 0.1. No intermediate phase has been observed after the heat-treatment at temperature higher than $850^\circ C$. Based on the XRD data, we have derived the lattice parameters and cell volume (listed in Table 1) of the samples of different Gd concentration. In comparison with the sample without Gd, the peaks shift toward smaller angles with increasing Gd concentration, which is consistent with the observed lattice expansion [4–7]. In addition, minor peaks representing impure phases appear in the samples with a higher Gd concentration. As shown in Fig. 1, $GdAlO_3$ can be identified as an impurity phase in the samples we studied. It is known that the absorption and emission energies of $GdAlO_3:Ce$ are much higher respectively than those of YAG:Ce, therefore have no contribution to the luminescence spectrum between 500 nm and 600 nm [9].

The photoluminescence properties of YAG:Ce series powders were investigated to reveal the effects of composition changes on the emission wavelength and the luminescence efficacy. Replacing Y by Gd induces a red shift in the Ce^{3+} emission band as shown in Fig. 2. The normalized emission spectra of the YAG:Ce powders samples with different Gd concentration cover a broad spectral range from 480 nm to 700 nm. The broad Ce^{3+} emission band originates from the $4f-5d$ electronic transition with intensive side bands due to vibronic coupling to the lattice and local vibration modes in the YAG lattice [10]. As the Gd concentration increasing, the center of the emission band shifts from 529 nm to 564 nm. Such a shift is primarily due to the variation of the lowest crystal-field energy level (emitting state) of the $5d^1$ state which depends strongly on the local electrostatic field determined by the crystalline structure of the YAG lattice.

Because the ionic size of Gd^{3+} and Ce^{3+} is larger than that of the host ion Y^{3+} , substituting Gd^{3+} and Ce^{3+} results in a lattice expansion. When the concentration of Ce^{3+} is low and fixed at a constant, the lattice expansion will depend on the concentration of Gd^{3+} . Measured from the XRD spectra, and shown in Fig. 3, the dependence of the lattice constant value on the Gd^{3+} concentration varied from zero to 10% of Y^{3+} is approximately a linear function. It is also interesting to see that the red shift of the Ce^{3+} emission correlates very well with the lattice expansion (Fig. 3). Based on these

Fig. 2. Red shift and intensity of luminescence from $(Y_{1-x}Gd_x)_2.97Al_5O_{12}:Ce_{0.03}$ phosphor with composition changes: (a) $x = 0$, (b) $x = 0.03$, (c) $x = 0.06$, and (d) $x = 0.1$. The spectra for the four samples were obtained with a blue LED with peak at 475 nm excitation and normalized to the peak intensity indicated the legend.

observations, we can conclude that within the range of Gd^{3+} concentration less than 10%, the red shift of the YAG:Ce luminescence is predominantly originated from the lattice expansion.

In the framework of crystal-field theory, the electronic energy levels of Ce^{3+} in YAG and their shifts observed in the emission and absorption spectra can be evaluated as a function of spin–orbit coupling and crystal-field interaction expressed in terms of Hamiltonian parameters [11]. Other mechanisms such as electrostatic interaction is absent in the $4f^1$ and $5d^1$ configurations. Whereas the lattice expansion induced energy level shifts should be independent of the spin–orbit coupling, the observed red shifts can be calculated as a function of crystal-field parameters. In the lattice of YAG, Ce^{3+} ions occupy the site of Y^{3+} at a tetragonal symmetry of approximately D_2 . Considering the doping induced site distortion, the actual site symmetry of Ce^{3+} may be even lower than D_2 . However, the five crystal-field energy levels of $6d^1$ is not sufficient to determine the free-ion and crystal-field parameters for D_2 symmetry especially for B_2^2 and B_2^4 . In our calculations, an approximation of D_{2d} is considered. Accordingly, the crystal-field splittings for a

Fig. 3. Comparison of the lattice expansion and the red shift of Ce^{3+} luminescence as function of Gd^{3+} concentration in $(Y_{1-x}Gd_x)_2.97Al_5O_{12}:Ce_{0.03}$.

Table 1

Lattice expansion, energy level of the 5d emitting state, and 5d crystal-field strength according to Eq. (2) for $(Y_{1-x}Gd_x)_{2.97}Al_5O_{12}:Ce_{0.03}$ are evaluated as a function of Gd concentration (x).

X	Lattice (Å)	Cell volume (Å ³)	Emitting state energy (cm ⁻¹)	Crystal-field strength (cm ⁻¹)
0	12.00888	1731.8369	20,450	1892
0.03	12.04047	1745.5421	19,963	2217
0.06	12.06151	1754.7109	19,597	2462
0.1	12.09289	1768.4383	19,277	2677

5d state are determined by [12]:

$$H(5d) = \zeta_{SO}(d)A_{SO}(d) + B_0^2(d)C_0^{(2)} + B_0^4(d)C_0^{(4)} + B_4^4(d)(C_4^{(4)} + C_{-4}^{(4)}) \quad (1)$$

where the first term is the spin–orbit interaction and $B_q^k(d)$ are the crystal-field parameters for the 5d states and $C_q^{(k)}$ are operators of spherical harmonic functions. Because the 4f states have much weaker crystal-field interaction, one can assume that the observed red shift in the Ce^{3+} 5d–4f transition is dominantly contributed by the energy level shift in the excited 5d emitting state.

In the present work, Eq. (1) is used for evaluating a systematic trend of the changes in the Ce^{3+} energy levels expressed in terms of the crystal-field parameters. In order to establish such a correlation, the observed electronic energy levels must be obtained from absorption and emission spectra of a single crystal of YAG:Ce. In fact, vibronic features dominate the emission and absorption spectra of the 5d–4f transitions. Ion-phonon coupling and structure defects induced inhomogeneous line broadening often obscure the lines of zero-phonon electronic transitions. Only with Ce^{3+} diluted in a single crystal cooled to liquid helium temperature, one may observe the zero-phonon lines. As shown in Fig. 4, two sharp lines with a line width of approximately 20 cm⁻¹ located at 489 nm and 546 nm are assigned to the zero-phonon lines from the emitting 5d state to the ground configuration 4f states of $^2F_{5/2}$ and $^2F_{7/2}$, respectively. This result is consistent with the previously reported work by Robbins [13], who clearly resolved the zero-phonon-line (ZPL) of emission spectrum (at 4 K) at 20,441 cm⁻¹, and that of the absorption spectrum at 20,443 cm⁻¹. An intensity profile of mirror symmetry between the emission and absorption suggests the same vibronic coupling in emission and absorption. The band center (or intensity peak) is about 1400 cm⁻¹ from the ZPLs. At higher temperature or due to disordering, the first 4f–5d absorption appears

at 460 nm, while the emission band centers at 520 nm. However, we should keep in mind that the electronic energy level of the lowest 5d¹ state should be assigned to 489 nm and the same vibronic shift should be subtracted from the other absorption bands when assigning energy levels for other 5d¹ states.

Apparently, the energy levels of 5d¹ states of Ce^{3+} in YAG are not clearly understood, even though in the literature there are a number of reports on both experimental investigations and theoretical modeling of the 5d¹ energy level structure for Ce^{3+} :YAG [13–16]. The experimental results from different groups are not quite consistent. The primary difficulty is presumably that the energy span of the 6d¹ states is on the same order or even larger than the energy gap between the valence and conduction bands. It was observed that the ground 4f photoconduction occurs at 30,650 cm⁻¹ (3.8 eV) [14], where the energy levels of the upper three 5d¹ states are located in a region from 38,300 cm⁻¹ to 48,880 cm⁻¹. Our crystal-field analysis relied on the experimental results from the optical absorption spectra reported by Hamilton et al. [14] and by Tomiki et al. [15]. The band peaks reported by these two groups are consistent where as the upper three bands are resolved more clearly in Ref. [14]. A recent review of experimental results and crystal-field analysis by Tanner et al. [16] proposed three different assignments of the 5d¹ energy level structure. The energy levels in these three assignments are different only for the upper three levels. The values of crystal-field parameters vary significantly for these assignments. In view of energy levels, only the third assignment is more consistent with the experimental results of Refs. [14,15]. This work provided a general insight to the crystal-field splitting of the excited 5d¹ states of Ce^{3+} :YAG. However, the authors apparently assigned the band peaks instead of the ZPLs to the 5d¹ states based on which the crystal-field analysis was performed.

The present work reinvestigated the previous discrepancies in assigning the upper 5d¹ energy levels. Our crystal-field analysis is based on the results from Refs. [14,15] and our own experiment as shown in Fig. 4. Only ZPLs are used in energy level assignment. The ZPL for the lowest level is clearly seen in the emission spectrum (Fig. 4) and in a high resolution absorption spectrum [13] of single crystal samples. The energy difference between the ZPL and the band peak is 1400 cm⁻¹. Therefore, ZPL positions for the upper four levels are determined by subtracting the 1400 cm⁻¹ vibronic shift from the energies of the band peaks.

In order to understand the underlying reasons for the luminescence red shift, it is necessary to examine how each of the crystal-field terms in Eq. (1) contributes to the energy level shift. First, the calculated energy levels were fit to the experimentally observed values of ZPLs for the five crystal-field levels of the 5d¹ configuration. The crystal-field and spin–orbit Hamiltonian was diagonalized for the 5d¹ configuration of Ce^{3+} in D_{2d} symmetry. The eigenfunctions in terms of $|J,M\rangle$ and calculated energies of the five crystal-field states of the 5d¹ configuration of Ce^{3+} in YAG have been evaluated and are listed in Table 2. In comparison with crystal-field parameters for Scenario III in the work of Tanner et al. [16], the energy level structure calculated using D_{2d} symmetry is approximately the same as that obtained using D_2 symmetry. This is not surprising because of the small contribution from $B_0^2(d)$ and $B_0^4(d)$. Our calculation also agrees with that of Tanner et al. in which

Fig. 4. Emission spectrum of single crystal of YAG:1% Ce^{3+} at 4 K excited by a 475 nm laser beam. The two sharp peaks marked in the spectrum are due to Ce^{3+} 5d¹ zero-phonon transition to the state of 4f¹ $^2F_{7/2}$ and $^2F_{5/2}$, respectively, while the broad band following the zero-phonon lines are vibronic transitions.

Table 2Crystal-field energy, eigenfunction and Hamiltonian parameters for 5d¹ states of Ce³⁺ in YAG.

Exp. energy (cm ⁻¹) ^a	Cal. energy (cm ⁻¹)	Eigenfunction ($ JM_J\rangle$)
20,445	20,461	$-0.6763 3/2, 3/2\rangle + 0.6770 5/2, -5/2\rangle - 0.2905 5/2, 3/2\rangle$
28,039	27,679	$-0.7313 3/2, 1/2\rangle + 0.6820 5/2, 1/2\rangle$
36,912	36,785	$0.6820 3/2, 1/2\rangle + 0.7313 5/2, 1/2\rangle$
42,961	37,589	$0.4686 3/2, 3/2\rangle - 0.8787 5/2, 1/2\rangle$
47,478	45,594	$-0.5684 3/2, 3/2\rangle - 0.7304 5/2, -5/2\rangle - 0.3788 5/2, 3/2\rangle$
Parameters (cm ⁻¹)		$\zeta = 996$, $B_0^2 = -1066$, $B_0^4 = -19$, 150 , $B_4^4 = 31$, 351

^a The first level is obtained from emission spectrum (Fig. 4) and other four are from Refs. [14,15].

the third and fourth levels are close with a separation only about 800 cm⁻¹. However, values of the crystal-field parameters, particularly B_0^4 , vary significantly, in order to reduce the third level from above 40,500 cm⁻¹ down to 36,900 cm⁻¹ to fit the experimental data [14,15].

Rediagonalization of the Hamiltonian was conducted while the value of one of the three crystal-field parameters was allowed to vary. As shown in Fig. 5, the energy level of the Ce³⁺ emitting state exhibits a line dependence respectively on the three crystal-field parameters varied up to 50% from the values for the YAG:Ce without Gd doping. This behavior is understood based on the eigenfunctions and energy splittings list in Table 2 while the energy shift is small in comparison with the gaps to the upper crystal-field states of the 5d¹ configuration.

The increases in B_q^k indicate an enhancement on the local crystal-field strength for Ce³⁺ in the Y(Gd)AG lattice. This result is consistent with a compress of local lattice surrounding the Ce³⁺ ions when Gd³⁺ ions are added to replace Y³⁺ in the YAG lattice. In addition to the variation of the individual crystal-field parameters, such an effect may be described as a function of crystal-field strength defined as

$$N_V = \left[\frac{1}{4\pi} \sum \frac{(B_q^k)^2}{2k+1} \right]^{1/2}. \quad (2)$$

The crystal-field strength is evaluated for Ce³⁺ in YAG with different Gd³⁺ concentrations and list in Table 1. The leading contribution is from the axial crystal-field term of B_0^4 , while the contributions from the other two terms are also included according to the same ratios between the values of the parameters for the system with-

Fig. 5. Dependence of the energy level of the 5d¹ emitting state on the model crystal-field parameters for Ce³⁺ in YAG:Ce modified by Gd³⁺. $B_q^k(x=0)$ are the 5d crystal-field parameters of Ce³⁺ in YAG without Gd doping. Their values are listed in Table 2.

out Gd³⁺ ions. Such a restriction is based on the assumption that the intrinsic symmetry is preserved even though the actual site for Ce³⁺ in YAG:Ce added with Gd³⁺ may have a certain degree of distortion. This assumption is supported by the XRD spectra as shown in Fig. 1 and the linear variation of the parameters shown in Fig. 5. In fact, this behavior is expected because the number of Gd³⁺ ions substituting for Y³⁺ is small and does not change the site symmetry of Ce³⁺ and the related crystalline properties.

It is previously reported and also observed in our experiments that increase in Gd³⁺ concentration leads to a decrease of the YAG:Ce luminescence intensity or quantum efficiency [17]. Several mechanisms may be involved for leading to such a decrease, while two of them are obvious and may be dominant. First, lattice expansion from the unperturbed structure of the pure YAG lattice induces a much larger energy shift on the 5d states than on the 4f states. As a result, the 5d–4f electronic transitions become less efficient, or the zero-phonon lines become weaker. This effect is evident in the emission spectrum of YAG:Ce added with a higher concentration of Gd³⁺, in which the intensity in the short wavelength side dropped significantly but not in the red region. Secondly, as we indicated in the previous section that, when the Gd concentration increases, impurity phases such as GdAlO₃:Ce appears in the phosphor. These impurity phases do not contribute to the light emission in the 500–600 nm region, but may absorb and scatter the blue pumping light. A more detailed analysis of the co-doping induced luminescence efficiency decrease is needed in future studies.

4. Conclusions

We have investigated the consequences of composition changes in YAG:Ce by substituting Y with Gd, which induces lattice expansion and changes in the local crystal-field interaction of Ce³⁺. Both the increase in the YAG crystal lattice and the red shift of the Ce³⁺ emission band depend linearly on the Gd³⁺ concentration within a range of 10% of the host lattice ion Y³⁺. The red shift in luminescence band is dominantly due to the energy level decrease of the 5d emitting state. A crystal-field analysis of the 5d¹ energy levels of Ce³⁺ in Y(Gd)AG shows that the red shift in luminescence band corresponds to an enhancement on the crystal-field interaction of Ce³⁺ in the YAG lattice. The expansion in the YAG lattice leads to an increase in the crystal-field interaction of Ce³⁺. The crystal-field modeling of the Gd³⁺ induced red shift in the Ce³⁺ luminescence band also provides a basis for understanding the efficiency decrease in the Gd³⁺ doped YAG:Ce phosphor.

Acknowledgements

Work performed at ANL was supported by the U.S. Department of Energy, Office of Basic Energy Sciences, Division of Chemical Sciences, Geosciences, and Biosciences, under contract DE-AC02-06CH11357.

References

- [1] P. Schlotter, J. Baur, Ch. Hielscher, M. Kunzer, H. Obloh, R. Schmidt, J. Schneider, *Mater. Sci. Eng. B* 59 (1999) 390.
- [2] J. Baur, P. Schlotter, J. Schneider, *Adv. Solid-State Phys.* 37 (1998) 67.
- [3] K. Höhn, A. Debray, P. Schlotter, R. Schmidt, J. Schneider, United States Patent (2003) 6,613,247.
- [4] C.C. Chiang, M.S. Tsai, M.H. Hon, J. Electrochem. Soc. 154 (2007) J326–J329.
- [5] M. Kottaisamy, P. Thiyagarajan, J. Mishra, M.S.R. Rao, *Mater. Res. Bull.* 43 (2008) 1657.
- [6] K. Zhan, H.Z. Liu, Y.T. Wu, W.B. Hu, J. Mater. Sci. 42 (2007) 9200.
- [7] Y.X. Pan, M.M. Wu, Q. Su, J. Phys. Chem. Solid 65 (2004) 845.
- [8] X.Z. Guo, P.S. Devi, B.G. Ravi, J.B. Parise, S. Sampath, J.C. Hanson, J. Mater. Chem. 14 (2004) 1288.
- [9] J.W.M. Verweij, M.Th. Cohen-Adad, D. Bouttet, H. Lautesse, B. Moine, C. Pédrini, *Chem. Phys. Lett.* 239 (1995) 51.
- [10] M. Grinberg, A. Sikorska, S. Kaczmarek, J. Alloy. Compd. 300–301 (2000) 158.
- [11] G.K. Liu, in: G.K. Liu, B. Jacquier (Eds.), *Spectroscopic Properties of Rare Earths in Optical Materials*, Springer-Verlag, 2005, pp. 1–89, Ch. 1.
- [12] L. Van Pieterse, R.T. Weigh, Meijerink, M.F. Reid, J. Chem. Phys. 115 (2001) 9382.
- [13] D.J. Robbins, J. Electrochem. Soc.: Solid-State Sci. Technol. 126 (1979) 1550.
- [14] D.S. Hamilton, S.K. Gayen, G.J. Pogatschnik, R.D. Ghen, W.J. Miniscalco, *Phys. Rev. B* 39 (1989) 8807.
- [15] T. Tomiki, T. Kohatsu, H. Shimabukuro, Y. Ganaha, J. Phys. Soc. Jpn. 61 (1992).
- [16] P.A. Tanner, L. Fu, L. Ning, B. Cheng, M.G. Brik, J. Phys.: Condens. Matter 19 (2007) 216213.
- [17] K. Zhang, W. Hu, Y. Wu, H. Liu, *Physica B* 403 (2008) 1678.