~~SECRET~~

UNCLASSIFIED

Report No. BMI-1194

C-84 Reactors -- Special Features
of Aircraft Reactors
(M-3679, 19th Ed.)

This document consists of 48 pages,
No. 111 of 144 copies, Series A.

Contract No. W-7405-eng-92

A TRACER STUDY OF THE TRANSPORT OF CHROMIUM
IN FLUORIDE FUEL SYSTEMS

by

Robert B. Price
Duane N. Sunderman
Meyer Pobereskin
George D. Calkins

Classification cancelled (or changed to) **UNCLASSIFIED**
Extr From Declassification
by authority of *Branch, dated 5-13-60*
by *J.C. Ridenour* **TLSOR**, date *5-19-60*

June 18, 1957

~~RESTRICTED DATA~~

This document contains restricted data as defined in the Atomic
Energy Act of 1954. Its transmittal or disclosure of its contents
in any manner to an unauthorized person is prohibited.

BATTELLE MEMORIAL INSTITUTE
505 King Avenue
Columbus 1, Ohio

~~SECRET~~

UNCLASSIFIED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

SECRET

3 and 4

Report No. BMI-1194
C-84 Reactors — Special Features
of Aircraft Reactors
(M-3679, 19th Ed.)

<u>Copy No.</u>	<u>Distribution</u>
1	Aerojet-General Corporation
2	AF Plant Representative, Baltimore
3	AF Plant Representative, Burbank
4	AF Plant Representative, Clifton
5	AF Plant Representative, Long Beach
6-7	AF Plant Representative, Marietta
8-10	AF Plant Representative, Santa Monica
11-12	AF Plant Representative, Seattle
13	AF Plant Representative, Wichita
14	Air Materiel Command
15	Air Research and Development Command (RDGN)
16	Air Technical Intelligence Center
17-19	ANP Project Office, Fort Worth
20	Albuquerque Operations Office
21	Argonne National Laboratory
22	Armed Forces Special Weapons Project, Sandia
23	Armed Forces Special Weapons Project, Washington
24	Assistant AF Plant Representative, Downey
25	Assistant Secretary of the Air Force, R & D
26-31	Atomic Energy Commission, Washington
32	Atomics International
33-34	Bettis Plant (WAPD)
35	Bureau of Aeronautics
36	Bureau of Aeronautics (Code 24)
37	Bureau of Aeronautics General Representative
38	Chicago Operations Office
39	Chicago Patent Group
40	Chief of Naval Research
41	Convair-General Dynamics Corporation
42	Curtiss-Wright Corporation
43	Engineer Research and Development Laboratories
44-47	General Electric Company (ANPD)
48	General Nuclear Engineering Corporation
49	Glenn L. Martin Company
50	Hartford Area Office
51-52	Headquarters, Air Force Special Weapons Center
53	Idaho Operations Office
54	Knolls Atomic Power Laboratory
55	Lockland Area Office
56	Los Alamos Scientific Laboratory
57	Marquardt Aircraft Company
58	National Advisory Committee for Aeronautics, Cleveland
59	National Advisory Committee for Aeronautics, Washington
60-62	Naval Air Development and Material Center
63	Naval Research Laboratory
64	New York Operations Office
65	North American Aviation, Inc. (Missile Development Division)
66	Nuclear Development Corporation of America
67	Office of the Chief of Naval Operations (OP-361)
68	Patent Branch, Washington
69	Patterson-Moos
70-73	Pratt and Whitney Aircraft Division (Fox Project)
74	San Francisco Operations Office
75	Sandia Corporation
76	School of Aviation Medicine
77	Sylvania Electric Products, Inc.
78	Technical Research Group
79-88	Union Carbide Nuclear Company (ORNL)
89	USAF Headquarters
90	USAF Project RAND
91	U. S. Naval Radiological Defense Laboratory
92	University of California Radiation Laboratory, Livermore
93-110	Wright Air Development Center (WCOSI-3)
111-135	Technical Information Service Extension, Oak Ridge
136-144	Battelle Memorial Institute

SECRET

SECRET

5 and 6

TABLE OF CONTENTS

	<u>Page</u>
ABSTRACT	7
INTRODUCTION	7
Inconel-Fluoride Corrosion Reactions	7
Mechanism of Corrosion	8
Use of Chromium-51 to Study Inconel-Fluoride Corrosion	9
EXPERIMENTAL WORK	11
Isothermal Studies	12
Randomization Experiments	12
Diffusion Experiments	13
Polythermal Studies	20
Tilting-Capsule Experiments	20
Thermal-Convection-Loop Experiments	29
Pumping-Loop Experiments	36
DISCUSSION	37
Isothermal Studies	37
Randomization Experiments	37
Diffusion Experiments	40
Polythermal Studies	41
Tilting-Capsule Experiments	41
Thermal-Convection-Loop Experiments	42
Pumping-Loop Experiments	44
CONCLUSIONS	45
REFERENCES	48

SECRET

SECRET

7

A TRACER STUDY OF THE TRANSPORT OF CHROMIUM IN FLUORIDE FUEL SYSTEMS

Robert B. Price, Duane N. Sunderman, Meyer Pobereskin,
and George D. Calkins

An experimental study was made of the mass transport of chromium in polythermal Inconel-fluoride fuel systems. The transport of chromium was followed by the technique of adding radioactive chromium-51 to the system as either CrF_2 in the salt or as elemental chromium in the solid phase.

Isothermal experiments at 600, 700, 800, and 900 C showed that the Inconel-No. 30 salt system was typical of a liquid-solid heterogeneous exchange system in that the long-term rate of exchange was controlled by the rate of diffusion of chromium into the Inconel. There was no effect on the rate of exchange attributable to variation in chromium concentration in the salt in the absence of uranium. In the presence of equilibrium chromium concentrations in the salt, the presence or absence of uranium had no effect on the rate of exchange.

The rates of diffusion of chromium in Inconel at 600, 700, 800, and 900 C were determined by an electropolishing technique.

Polythermal studies were carried out by three methods, tilting capsules, thermal-convection loops, and pumping loops. Tilting-capsule experiments indicated that the preferred location for chromium deposition on the wall was in the region of maximum temperature but the conclusions were not clear cut. Thermal convection loops operated for 125 and 288 hr showed radioactivity profile which could be attributed to simple exchange, with some distortion in the 288 hr case. The duration of these experiments was evidently insufficient to allow equilibrium to be reached in the salt. A thermal-convection loop operated for 400 hr showed distortion in the exchange radioactivity profile which indicated a favorable position for chromium deposition at a point about 100 F below the maximum wall temperature, and on the upstream side of the flow.

A pumping loop of Inconel and No. 30 salt mix gave an activity profile which was very similar to that of the 400-hr thermal-convection loop, indicating a favorable deposition point 100 F below maximum temperature on the upstream side.

One hypothesis advanced is that the long-term corrosion rate of chromium in the Inconel-No. 30 salt system is controlled by the rate of diffusion of chromium into the wall at a temperature about 100 F below the maximum temperature on the upstream side.

INTRODUCTION

Inconel-Fluoride Corrosion Reactions

In the corrosion of dynamic polythermal systems of Inconel containing fluoride fuels, chromium is removed from the metal wall by a number of oxidative mechanisms. The equations describing these reactions, presented below, are generally applicable to fluoride fuel materials contained in chromium-bearing metals. This investigation was

SECRET

SECRET

8

concerned particularly, however, with No. 30 and No. 31 salt mixes in Inconel. No. 31 salt is an equimolar mixture of NaF and ZrF₄. No. 30 salt mix contains 50 mole per cent NaF, 46 mole per cent ZrF₄, and 4 mole per cent UF₄.

followed by

The first three of these reactions go to completion rapidly and are the result of reactions with impurities in the salt and on the surface of the metal. The fourth reaction, which is the basic corrosion reaction in this system, proceeds at a rapid rate initially and then at a constant slower rate for the duration of any operation. During the initial period of rapid reaction, chromium is removed from the wall and the concentration of CrF₂ in the salt is increased to a constant value. Subsequently, as the corrosion progresses by its long-term rate, this concentration in the salt remains constant but chromium removal from the metal continues.

Generally, in such a case, the corroded material is transported to and deposited grossly in the low temperature part of the system. In a similar fuel system Inconel-No. 108 salt mix (56.3 mole per cent NaF—37.2 mole per cent ZrF₄—6.5 mole per cent UF₄) metallic chromium is deposited in relatively pure form in the low-temperature zone; however, in Inconel-No. 30 salt systems, under usual operating conditions, such deposits are not generally observed.

Mechanism of Corrosion

A theory embracing the existing experimental work on this system was formulated by Grimes in 1956.⁽¹⁾ He postulated that leaching of chromium from the Inconel during the initial operation of the system was true corrosion. However, when the CrF₂ concentration in the salt reached its constant value, the chromium could be dissolved from the metal in the hot zone only as rapidly as it was being removed from the salt in some cooler zone. The following equilibrium constant based on the reversibility of Reaction (4) was defined:

$$k = \frac{[\text{CrF}_2] [\text{UF}_3]^2}{[\text{Cr}] [\text{UF}_4]^2} ,$$

with the activity of elemental chromium being taken as its molar concentration in Inconel.

(1) References at end of report.

SECRET

SECRET

9

By determining equilibrium constants of both the Inconel-No. 30 salt mix and the pure chromium-No. 30 salt systems, Grimes showed that the equilibrium concentration of chromium in the salt of an Inconel-No. 30 salt system at 800 C is not high enough to exceed the equilibrium concentration of chromium in the salt of a pure chromium-No. 30 salt system at 600 C. It would not be expected, therefore, that pure chromium deposits would occur at the lower temperature in a polythermal Inconel-No. 30 salt system with a maximum temperature at 800 C and a minimum at 600 C. Grimes theorized further that chromium is removed from the salt by the reverse of Reaction (4) in a cooler zone at such a rate as to maintain the surface chromium activity only slightly above that in the Inconel. The rate at which chromium is deposited would then be the same as the rate at which it diffused into the metal to maintain its equilibrium activity on the surface. Thus, the rate of diffusion of chromium in Inconel at some lower temperature in a given polythermal system would control the rate of corrosion in the hot zone. The temperature at which this deposition would attain its maximum rate was not known.

Use of Chromium-51 to Study Inconel-Fluoride Corrosion

Previous attempts by chemical analysis to determine the location of chromium transported in polythermal Inconel-No. 30 salt systems have been inconclusive. It was suggested that the use of a radioactive chromium tracer would increase the sensitivity of measurement to a point where very small quantities of transported chromium could be detected. The applicability of a radioactive tracer in a study of this type depends upon the degree to which the actions of the radioactive atoms are typical of the actions of the macro quantities of chromium in the system. The method of incorporation of the tracer in the system determines the degree of correspondence. In a heterogeneous system of the type under study there are several ways in which the addition of tracer may be accomplished. In one case, radioactive chromium is added to the salt in the same chemical form in which the nonradioactive chromium exists in the salt. In the second case, radioactive chromium is added to the system as a component of the Inconel or other metal used as an integral part of the structure. In either of these cases, the radioactive chromium will tend to distribute itself uniformly in the salt-metal system, finally reaching a concentration in the components which is proportional to the concentration of chromium in these components. This randomization will result in a movement of radioactive chromium which is not associated with net changes in chromium concentration. It is therefore necessary to consider the effect of this randomization, or exchange, on the study of the corrosion and diffusion reactions.

The reactions investigated are listed below, including the randomization reaction for the case where the radioactive chromium originates in the salt.

- (1) Chromium diffusion through Inconel to the salt-metal interface.
- (2) Chromium dissolution by corrosion:

- (3) Transport of chromous fluoride through the salt system by mechanical flow or liquid diffusion.

SECRET

SECRET

10

- (4) Deposition of metallic chromium in another portion of the system by the reverse of the corrosion reaction:

- (5) Diffusion of the deposited chromium into the metal.
- (6) Randomization of the radioactive chromium* by exchange between the chromium in the wall and that in the salt:

In the case where an equilibrium concentration of CrF_2 , tagged with Cr^*F_2 , is added to the salt, the following equilibrium will exist in the system: $\text{Cr} + 2\text{UF}_4 \rightleftharpoons 2\text{UF}_3 + \text{CrF}_2$. Transport of chromium in a system where this equilibrium is established will receive its driving force from the polythermal nature of the system which results in a different equilibrium constant for the above reaction for regions at different temperatures. For systems operated at 600 to 800 C, at any particular point on the metal surface the chromium can be deposited only to replace chromium which has diffused into the metal and lowered the surface activity of chromium. Likewise, chromium can be removed from the surface only when diffusion of chromium to the surface has raised the chromium activity to a point where the equilibrium concentration is exceeded. There is reason to believe that the corrosion and deposition reactions are very rapid and, therefore, infinitesimal changes in the concentration of chromium on the metal surface will be adjusted for immediately in the equilibrium system. In the absence of a polythermal driving force, the randomization reaction, $\text{Cr}^*\text{F}_2 + \text{Cr} \rightleftharpoons \text{Cr}^* + \text{CrF}_2$, is dependent upon the rate at which radioactive chromium, Cr^* , diffuses into the metal to lower its concentration on the surface. In a polythermal system with a tracer present initially in the salt, the mechanism for incorporation of the tracer in the wall will be either the reverse of the corrosion reaction, or the randomization reaction, whichever is faster. In several heterogeneous metal-fluid systems, it has been shown that the randomization reaction is very rapid and reaches equilibrium in a few minutes, involving only a few atomic layers of metal surface. Thus, this initial exchange would not be expected to influence appreciably the long-term transport experiments. Once the randomization reaction has reached equilibrium, the rate of incorporation of tracer in the metal is dependent upon the same mechanism of depletion of the surface by diffusion as when no tracer is present. Thus, the tracer becomes a true indicator of the rate and position of transport of chromium in the system.

A similar argument may be developed for the case in which the radioactive chromium originates in the metal phase. In the systems in which metallic chromium deposits in the pure form in cold zones the tracer is again a true indicator of the action of macro chromium. The tracer and the natural chromium are at equilibrium on the wall where diffusion is the rate-controlling step as in the case previously described. The pure chromium is deposited with the same specific activity as the chromium in the salt since this is its origin, and thus no randomization correction is necessary to account for the radioactivity of the deposit.

* In reactions listed in this report, Cr^* = chromium-51.

SECRET

SECRET

11

In cases where no chromium other than tracer chromium is added to the salt at the beginning of the experiment, no deposition or transport will occur until the equilibrium concentration of chromium has been reached. Prior to this time the only mechanism for the transfer of radioactive chromium to the wall is that of exchange or randomization. This randomization may transfer tracer chromium to the wall for a relatively long period of time before transport begins. For example, equilibrium may not be reached in thermal loops for 250 to 300 hr and in pumping loops for 50 hr. In these cases, in order to interpret the results of a tracer experiment it is necessary to determine the effect of the randomization reaction and to correct for it before mass transport can be determined.

EXPERIMENTAL WORK

There are two major reactions of interest in the study of the mass-transfer phenomenon by the use of radioactive chromium. These are

Reaction (4) is a reversible one resulting in corrosion in the forward direction and deposition in the reverse. This reaction will occur regardless of the presence or absence of the radioactive tracer. Reaction (5) is also reversible and is in true equilibrium only when radioactive chromium, Cr^* , is uniformly distributed throughout the system in the same relative proportions as the natural chromium. This reaction which transfers radioactive chromium to the wall is dependent only upon the temperature and composition of the wall and will proceed in the forward direction until randomization is achieved in either isothermal or polythermal systems in either the presence or absence of corrosion and mass transport.

The first series of experiments was conducted to determine the effect of temperature and concentration variables on this randomization reaction under conditions of no corrosion. Effects were sought for temperature variations, presence or absence of uranium, and concentration of chromium in the absence of uranium (No. 31 salt).

The second step in the investigation of mass transport was the determination of the diffusion rate of chromium in the Inconel and how this was affected by the temperature and the structure of the metal. These two steps of the experimental program established the parameters of the exchange reaction as a function of time, temperature, and concentration, in the absence of mass transport of chromium.

The second phase of the experimental program consisted of the study of polythermal systems in which corrosion and mass transport were superimposed on the randomization. The first polythermal efforts were directed toward tilting-capsule experiments. With the experience obtained in these experiments, thermal-convection loops were designed and operated with the chromium tracer present. The final experiments consisted of the addition of chromium tracer to the salt phase in two pumping loops.

SECRET

SECRET

12

The experimental details of the isothermal and polythermal phases of the program are described below.

Isothermal Studies

Randomization Experiments

Twelve series of randomization experiments were conducted, six with No. 30 salt mix in Inconel and six with No. 31 salt mix in Inconel. Equilibration periods ranged from 1 to 1500 hr and temperatures from 600 to 900 C. Experimental conditions are listed in Table 1.

TABLE 1. LIST OF RANDOMIZATION EXPERIMENTS

Experiment	Equilibration Temperature, C	Fluoride Fuel	CrF ₂ (a) Additive, ppm Cr	Chromium Analysis, ppm	
				Initial	Final
1	600	30	635	1355	1440
2	800	30	810	1220	1610
3	600	30	1100	1310	1750
3A	600	31	1100	1050	1280
4	700	30	1250	2030	2540
4A	700	31	1250	1320	1340
5	800	30	1400	1285	1660
5A	800	31	400	750	700
5B	800	31	1000	980	1080
5C	800	31	1400	1270	1380
5D	800	31	170	810	980
6	900	30	1550	--	--

(a) Chromium-51 tracer material. Prepared from neutron-activated chromium metal of 99.99 per cent purity.

Each randomization experiment was prepared by loading Inconel capsules (0.50 in. in OD by 0.40 in. in ID by 1.50 in. long) with 2.00 ± 0.01 g of salt from a master batch. The master batches were prepared by dissolving, with agitation, a predetermined amount of chromium 51-labeled chromous fluoride in the fluoride fuel in an Inconel container. A uniform distribution of chromium-51 was assured by radioassaying representative samples of each master batch.

The chromium 51-labeled chromous fluoride was produced by adapting a synthesis developed by B. J. Sturm of ORNL. This method consisted of dissolving neutron-activated chromium metal (99.99 per cent pure) in aqueous HCl, precipitating $\text{CrF}_3 \cdot 3\text{-}1/3\text{H}_2\text{O}$ with HF, fusing with NH_4HF_2 to produce the complex $(\text{NH}_4)_3\text{CrF}_6$, thermally decomposing in a hydrogen atmosphere to anhydrous CrF_3 , and reducing with hydrogen to anhydrous CrF_2 . The composition and purity of the $\text{CrF}_3 \cdot 3\text{-}1/3\text{H}_2\text{O}$ and the anhydrous CrF_2 end product were determined by X-ray diffraction and petrographic examination. The specific activity of the chromous fluoride was determined by dissolving in

SECRET

SECRET

13

hot concentrated HCl and radioassaying. Specific activities ranged from 1 to 10 millicuries per g depending on the neutron-activation dosage and the decay period. Chromium-51 decays by K-electron capture, a portion of these captures resulting in the emission of a 0.32-mev gamma ray. Its half life is 27 days.

In order to attain as uniform experimental conditions as possible, all capsules were prepared and loaded in a similar manner. Uniform lengths were cut from Inconel tubing received from ORNL. This tubing had been cold drawn and annealed. The sections were cleaned with detergent and acetone, and a disk of 18-gage Inconel sheet was Heliarc-welded on one end of each tube length. These capsules were hydrogen-fired for 4 hr at 1850 F, primarily to remove oxides formed in welding. The capsules were then loaded with $2.00 \pm .01$ g of fluoride mixture in a helium-atmosphere dry box, and the Inconel-sheet top disks were Heliarc-welded in place.

For equilibration, capsules were suspended vertically, in the same plane, in a furnace at the desired temperature. At intervals, the capsules were inverted, allowed to drain for 1 min at temperature, and then removed from the furnace and hung upright to cool, so that the salt solidified in the end opposite to the equilibration end. After cooling, the salt was removed, ground, dissolved in a mixture of boric, nitric, and sulfuric acids and radioassayed. Representative samples of salt from each series were examined petrographically and it was found that there was little or no free ZrF_4 , reduction products, opaque material, or oxides. Samples from each series were analyzed for chromium content.

Figures 1 through 5 show the effects of time, temperature, concentration of chromium, and presence or absence of uranium on the percentage of chromium removed from the salt.

Photomicrographs, taken of samples of Inconel from the wall and the bottom of a randomization capsule (4 hr at 900 C), are shown in Figures 6b and 6c. The larger grain size in the surface layer of the bottom disk (about 40 times the grain size in the first 0.5-mil layer of the tube wall) results in a correspondingly greater grain volume-to-grain boundary ratio. The deduced lowered diffusion rate correlates with the decreased specific activity of the bottom disk found by radioassay. These data are presented in Table 2.

Diffusion Experiments

An electropolishing radioassay technique was developed to determine the rate of diffusion of chromium-51 into the Inconel capsule walls. The capsules from the randomization study were used as the anode and a steel rod, 3/32 in. in OD was used as the cathode in the electropolishing apparatus. The electrolyte was 85 parts by volume, H_3PO_4 and 15 parts H_2SO_4 . A lathe chuck was used to obtain alignment of the capsule and the cathode.

A 5/64-in. spacing between the capsule bottom and the steel-rod cathode was determined to be necessary to obtain uniform polishing in respect to capsule geometry. An adapted ball-point micrometer reading to 0.0001 in. and a positioning jig were used to determine the uniformity of polishing. Using a uniform volume of electrolyte and maintaining a constant current flow of 100 ma (~ 100 ma per in.²) removed 6.0 mg or a

SECRET

FIGURE 1. RANDOMIZATION OF CHROMIUM-51 IN INCONEL-NO. 30 SALT SYSTEMS

FIGURE 2. RANDOMIZATION OF CHROMIUM-51 IN INCONEL-NO. 31 SALT SYSTEMS

FIGURE 3. CONCENTRATION EFFECT ON RANDOMIZATION

FIGURE 4. TEMPERATURE EFFECT ON RANDOMIZATION

FIGURE 5. COMPARISON OF EXPERIMENTAL AND THEORETICAL EXCHANGE CURVES

- a. Inconel Tubing, 0.50 in. in OD by 0.40 in. in ID, in As-Received Condition

Thin layer of fine grains can be seen on the ID.

100X

N31613

- b. Wall of Randomization Capsule 6-2 Equilibrated 4 Hr at 900 C

Thin layer of fine grains can be seen on the ID. The wall is cold-drawn Inconel tubing, 0.50 in. in OD by 0.40 in. in ID.

250X

N40491

- c. Bottom of Randomization Capsule 6-2

No fine grain layer is seen. The bottom is hot-rolled 18-gage Inconel sheet.

250X

N40492

FIGURE 6. PHOTOMICROGRAPHS SHOWING GRAIN SIZE OF CAPSULE BOTTOM AND WALL

SECRET

20

1- μ -thick layer in 5 min. The electrolyte from several successive runs was analyzed for nickel, chromium, and iron content, and it was found that the constituents were removed each time in the ratio existent in Inconel. The cathode was tested for any increase in weight and for radioactivity, but no change was found.

TABLE 2. TRANSFER OF CHROMIUM-51 INTO INCONEL SHEET
AND INCONEL TUBING

Capsule Section	Activity of Capsule Section After Heating Indicated					
	Capsule 2-7		Capsule 6-1		Capsule 6-2	
	388 Hr at 800 C		2 Hr at 900 C		4 Hr at 900 C	
	Counts/ (Min) (G)	Per Cent of Maximum	Counts/ (Min) (G)	Per Cent of Maximum	Counts/ (Min) (G)	Per Cent of Maximum
Bottom	75,800	52	107,500	80	99,600	41
Wall, 1	146,600	100	135,000	100	242,000	99
Wall, 2	131,100	90	123,500	91	245,000	100
Wall, 3	136,700	93	121,000	90	190,000	78

Several capsules from the 600, 700, 800, and 900 C randomization studies were electropolished using the above technique. The specific activity of the electrolyte from successive electropolishings was determined by radioassay. Radioassay data are plotted in Figures 7 through 12. Approximate diffusion rates were determined from the relation⁽²⁾

$$\log C = (-0.1086/Dt)X^2 + \text{a constant.}$$

Boundary-diffusion effects were separated from volume-diffusion effects by the convenient but not rigorous technique of extrapolating the tail of the curve to the ordinate and subtracting these values from the initial part of the curve. The shallow penetration of chromium-51 was primarily due to volume diffusion and the deep penetration to boundary diffusion. This is similar to the pattern found by Kishkin and Bokstein⁽³⁾. The high specific activity of the first few layers (to about a 7- μ depth) coincides with the surface roughness of the tubing, 5 to 10 μ deep. Diffusion rates and the alloy compositions are given in Tables 3 and 4, respectively, along with comparative values from the literature⁽⁴⁾. Diffusion rates and transfer rates are plotted as a function of temperature in Figure 13.

Polythermal Studies

Tilting-Capsule Experiments

Four transport experiments in tilting capsules were completed. Inconel capsules containing No. 30 salt mix were seesawed for periods of 100 to 1000 hr while 800 and 600 C temperatures were maintained at opposite ends of the capsules. A tilting cycle was completed in 80 sec. The experiments are listed in Table 5.

SECRET

FIGURE 7. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 1510 HR AT 600 C

FIGURE 8. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 739 HR AT 700 C

FIGURE 9. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 644 HR AT 800 C

FIGURE 10. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 768 HR AT 800 C

FIGURE 11. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 11 HR AT 900 C

FIGURE 12. DIFFUSION OF CHROMIUM-51 INTO INCONEL
AFTER 48 HR AT 900 C

TABLE 3. COMPARISON OF DIFFUSION RATES OF CHROMIUM IN VARIOUS NICKEL-BASE ALLOYS AS REPORTED BY GRUZIN AND FEDEROV⁽⁴⁾

Material	Diffusion Rate at Indicated Temperature, cm ² per sec				
	600 C	700 C	800 C	900 C	1000 C
Inconel boundary ^(a)	6×10^{-15}	5×10^{-13}	4.4×10^{-12}	2.0×10^{-11}	--
Inconel volume ^(a)	--	1×10^{-13}	4.4×10^{-13}	3.0×10^{-12}	--
Nickel	--	7×10^{-14}	7×10^{-13}	5.0×10^{-12}	2.5×10^{-11}
Alloy 1	--	9×10^{-15}	1.5×10^{-13}	1.6×10^{-12}	1.1×10^{-11}
Alloy 2	--	--	--	1.0×10^{-12}	9.0×10^{-12}
Alloy 3	--	2×10^{-16}	1×10^{-14}	3.0×10^{-13}	4.0×10^{-12}

(a) Battelle data.

TABLE 4. COMPOSITION OF NICKEL-BASE ALLOYS USED FOR EXPERIMENTS LISTED IN TABLE 3.

Alloy	Composition (Balance Nickel), w/o								
	Cr	Ti	Al	Fe	C	Si	Mn	S	P
Inconel	16	--	--	8	0.15	0.5	1.0	0.015	--
Nickel	Trace	--	--	Trace	0.015	0.13	Trace	0.003	Trace
1	19.8	--	0.66	0.46	0.015	0.17	Trace	0.004	Trace
2	20.35	2.55	0.82	0.66	0.08	1.04	0.31	0.002	0.005
3	19.73	1.85	0.18	1.30	0.02	0.79	Trace	0.004	0.004

FIGURE 13. COMPARISON OF DIFFUSION RATE AND TRANSFER RATE AS A FUNCTION OF TEMPERATURE

SECRET

29

TABLE 5. LIST OF TILTING-CAPSULE EXPERIMENTS

Experiment	Temperature, C		Test Period, hr	Chromium Analysis, ppm	Activity of salt, counts/(min)(mg)
	Activated End	Nonactivated End			
1	800	600	113	1770	307
2	800	600	499	1830	323
3	800	600	1026	1780	334
4	600	800	1026	1630	40

Tilting capsules were composed of a 3.0-in.-long section of neutron-activated Inconel tubing Heliarc welded to a section of nonactivated Inconel tubing. The completed capsules were 0.50 in. in OD by 0.40 in. in ID by 11.0 in. long. Each capsule was hydrogen fired and loaded with 15.00 ± 0.04 g of No. 30 salt in a helium-atmosphere dry box, and an end disk Heliarc-welded in place. Maximum- and minimum-temperature-controlling thermocouples were attached to the opposite ends of the capsules and the equilibration performed as listed in Table 5. Furnace-temperature profiles were determined separately.

At the completion of the tilting periods, the capsules were opened, the salt removed, and the tubing sectioned. Radioassays were made of the sections and of the salt. Samples of the salt and the tubing were analyzed in a gamma-ray spectrometer, and it was determined that the radioactivity was due entirely to chromium-51. The radioactivity of the sections was normalized with respect to time and area of contact between the salt and the tubing by comparison with the radioactivity profile of a capsule equilibrated isothermally in the tilting furnace. Temperature and radioassay data are plotted in Figure 14.

Thermal-Convection-Loop Experiments

Thermal-convection-loop experiments are listed in Table 6. Four Inconel loops containing No. 30 salt mix were operated with maximum temperatures of about 1450 F and ΔT 's of about 200 F for periods of 125 to 400 hr. Chromium 51-labeled chromous fluoride was used as a tracer in each loop. In the first two loops chromous fluoride was added to the salt while in the last two loops chromous fluoride was produced in the salt by pre-equilibrating in contact with neutron-activated Inconel. The tubing in Loop 4 was made radioactive by pre-equilibrating in contact with the test salt for a period of 50 hr at 1652 F with a ± 4 F variation throughout the loop.

Loops 1 and 2 were fabricated by welding Inconel tubing 0.50 in. in OD by 0.40 in. in ID into a parallelogram with 5.0-in. vertical legs and 3.0-in. crossarms. Loops 3 and 4 were fabricated by bending hot Inconel tubing to shape and welding the top crossarm in place to form a parallelogram with 9.0-in. vertical legs and 4.5-in. crossarms. The internal angles of all the loops were about 75 and 105 deg. All four loops had a reservoir above the cycle section to allow for salt drainage after the tests were completed.

SECRET

FIGURE 14. GROSS TRANSPORT OF CHROMIUM-51 IN TILTING CAPSULES 1, 2, 3, AND 4

SECRET

31

TABLE 6. LIST OF THERMAL-CONVECTION-LOOP EXPERIMENTS

Inconel-No. 30 Salt Mix Flow Rate, ~1 fpm Tracer, Chromium-51				
	<u>Loop 1</u>	<u>Loop 2</u>	<u>Loop 3</u>	<u>Loop 4</u>
Maximum Wall Temperature, F	1475	1446	1455	1450
ΔT , F	239	210	205	210
Source of Chromium-51	Additive, 100 ppm CrF_2 (58 ppm Cr)	Additive, 100 ppm CrF_2 (58 ppm Cr)	Pre-equilibration with neutron-activated Inconel	Pre-equilibration with neutron-activated Inconel
Pre-equilibration Conditions				
Salt	--	--	192 hr at 1475 F	144 hr at 1650 F
Wall	--	--	--	50 hr at 1650 F
Duration of Test, hr	125	400	288	288

The amount of salt required to fill the loops to a level above the crossarms was determined by calculation and by experimental measurement to be 96.5 g each for Loops 1 and 2 and 167 g each for Loops 3 and 4. The loops were helium-leak checked, hydrogen fired for 4 hr at 1850 F, and then loaded with No. 30 salt mix containing chromium 51-labeled chromous fluoride. Loops 1, 2, 3, and 4 were loaded with 98.3, 99.3, 171.7, and 178.5 g of salt, respectively, in a helium-atmosphere dry box.

Heat-loss calculations indicated that a 1500-w heater would maintain a 200 F ΔT . Calculations indicated that a flow rate of the order of 1 fpm would be established with a 200 F ΔT . The heaters were constructed by winding coils of 30-ft lengths of 16-gage Chromel A wire. One heater coil per loop was wound on Alundum tubing on the hot leg and on the crossarms. Fourteen thermocouples were spot welded to the four legs. The loops were set, singly, in a pot furnace and the temperature raised slowly above the liquidus temperature of the salt, 968 F. After the salt had melted, furnace temperature, heater-coil temperature, and voltage-control settings were adjusted to establish the desired maximum temperature and temperature differential.

After operating for the test period, the loops were inverted so that the molten salt drained into the reservoirs. The loops were sectioned and radioassayed. The gamma-ray spectrum of the salt was determined. The activity was due entirely to chromium-51. Temperature and radioassay data are plotted in Figures 15 through 18.

SECRET

FIGURE 15. GROSS TRANSPORT OF CHROMIUM-51 IN THERMAL-CONVECTION LOOP 1

FIGURE 16. GROSS TRANSPORT OF CHROMIUM-51 IN THERMAL-CONVECTION LOOP 2

FIGURE 17. GROSS TRANSPORT OF CHROMIUM-51 IN THERMAL-CONVECTION LOOP 3

SECRET

35

SECRET

FIGURE 18. GROSS TRANSPORT OF CHROMIUM-51 IN THERMAL-CONVECTION LOOP 4

Pumping-Loop Experiments

Pumping-loop experiments are listed in Table 7. Two experiments were completed, Pumping Loop 1 (4500) with No. 108 salt mix in Inconel at a maximum temperature of 1500 F, and Pumping Loop 2 (4900) with No. 30 salt mix in Inconel at a maximum temperature of 1650 F. Temperature drops of approximately 200 F were established using water cooling in Loop 1 and air cooling in Loop 2. A salt-flow velocity of 4 fps was used in both tests. These experiments were conducted by including a chromium-51 tracer study in previously planned corrosion tests Numbers 4500 and 4900 in which the usual metallurgical techniques were used in determining the corrosion pattern.

TABLE 7. LIST OF PUMPING-LOOP EXPERIMENTS

	<u>Loop 1 (4500)</u>	<u>Loop 2 (4900)</u>
Fluoride Fuel	108	30
Tubing	Inconel	Inconel
Loop Temperature, F		
Inlet	1500	1650
Outlet	1300	1470
Cooling	Water	Air
Velocity, fps	4	4
Duration, hr	500	240
Reason for Termination	Scheduled	Power failure
Tracer Additive		
Source of Chromium-51	CrF ₂	CrF ₂
Amount Added, ppm Cr	81	43

In addition to determining the corrosion-deposition pattern, the first pumping loop was used to observe the interaction of silver and the Inconel-No. 108 salt system. Short sections of silver wire (1/16 in. in diameter in the hot zone and 3/32 in. in diameter in the cold zone) and silver-plated tubing were welded in place in both the hot and cold zones.

Chromium 51-labeled chromous fluoride was added to the systems in the following manner. The filler pot was loaded by transferring the desired amount of salt, 2560 g for Loop 1 and 3255 g for Loop 2, under helium pressure. After the salt had solidified and cooled to room temperature, radioactive chromous fluoride, 358 mg for Loop 1 and 242 mg for Loop 2, was added through a liquid-level-indicator plug. The final chromium concentration was 81 ppm in Loop 1 and 43 ppm in Loop 2. The filler pot was connected to the loop system in parallel with a flush pot. The system was evacuated to 1 μ , and purged and pressurized with helium to 3 to 6 psig. The salt in the flush pot was melted, transferred, and circulated through the loop system. Then the flush salt was drained and the system loaded from the filler pot.

Loop 1 was operated the scheduled 500 hr. Loop 2 was terminated prematurely at 240 hr due to power failure. The loops were drained, sectioned, and radioassayed, in addition to being examined metallurgically.

SECRET

37

Temperature and radioassay data are plotted in Figures 19 and 20.

DISCUSSION

Isothermal Studies

Randomization Experiments

In Figure 1, the randomization data for No. 30 salt mix in Inconel at 600, 700, 800, and 900 C are plotted. Two effects are readily evident: first the randomization rate increases rapidly with temperature, and, secondly, the curves can be separated into an early fast exchange rate and a slower long-term rate. Both of these effects are typical of a diffusion-controlled isotopic exchange reaction in a heterogeneous system.⁽⁵⁾ The two curves at 800 C have the same long-term rate but different short-term rates, apparently due to some differences in starting conditions such as oxide or other impurities in the salt or oxides on the surface of the tubing. Randomization data for No. 31 salt mix in Inconel at 600, 700, and 800 C, Figure 2, are quite similar to those for the No. 30 salt mix. The apparently more rapid exchange rate with No. 31 salt mix is thought to be due to the fact that more corrosion occurred in the No. 30 salt randomization than in the No. 31 salt randomization. Concentration data, listed in Table 1, indicate that corrosion occurred during the randomizations, even though attempts were made to prepare equilibrium mixtures for starting material. Equal rates of exchange for No. 30 and No. 31 salt mixes would be expected for the diffusion-controlled reactions under identical experimental conditions.

Effect of the chromium concentration on the randomization of No. 31 salt mix in Inconel at 800 C is shown in Figure 3. Again, identical rates of exchange were expected. The long-term rates of exchange are equal, but differences can be seen in the early portions of the curves which appear to be inversely in order of the initial chromous fluoride concentration. However, a more reasonable direct correlation can be seen between the observed early exchange rates and the change in chromium concentration in the series of experiments. Apparently, differences in starting conditions caused increasing corrosion in the starting period of the experiments in the increasing order 5A, 5B, 5C, and 5D. This would necessitate subtracting, in that order, from each apparent exchange rate to normalize the values. This could account for the apparent inverse concentration effect being observed, rather than the expected lack of effect of concentration on the exchange rates. If the curves were normalized as indicated above, however, one would expect them all to fall on the same line.

The temperature effect is shown plotted separately in Figure 3. A rapid, nearly linear increase with temperature is seen in the curve which is a plot of the 100-hr data from each randomization of mix No. 30 in Inconel.

Figure 5 illustrates graphically the fact that the exchange rate is diffusion controlled^(5,6,7). One factor which gives evidence of the diffusion control can be seen in the 900 C curve in Figure 1. A capsule equilibrated 265 hr in a horizontal position had an associated transfer value of 59.0 per cent compared with values of 48.5 and

SECRET

SECRET

FIGURE 19. GROSS TRANSPORT OF CHROMIUM-51 IN PUMPING LOOP 1 (4500)

SECRET

SECRET

FIGURE 20. GROSS TRANSPORT OF CHROMIUM-51 IN PUMPING LOOP 2 (4900)

SECRET

SECRET

40

49.5 per cent for two other capsules equilibrated for the same time and temperature in a vertical position. The surface area-to-salt volume ratio of the horizontally equilibrated capsule was about 140 per cent of that ratio for the vertically equilibrated capsule. If diffusion was controlling the rate of transfer, more surface area in contact with the salt would allow more chromium to transfer and diffuse into the tubing. In addition the surface of the tubing was composed of finer grained material than the end plates (Figures 6b and 6c), which allows more chromium-51 to diffuse into the tubing.

More experimental evidence of the diffusion control can be seen in Table 2 and in Figures 6b and 6c. The specific activity of the wall of a randomization capsule, equilibrated 4 hr at 900 C, is about 240 per cent of the specific activity of the bottom of the same capsule. This greater specific activity is associated with 0.5-mil layer of fine-grain Inconel in the capsule wall which has about 1/40 the grain size of the Inconel (sheet material) in the capsule bottom (Figures 6b and 6c). The finer grain material and accompanying increase in relative amount of grain boundary provides a larger boundary-to-volume diffusion ratio than the larger grain material and consequently, a greater over-all diffusion rate. The ratio of the specific activities of two other capsules examined, listed in Table 2, shows the same effect, although not to the same degree. This 0.5-mil-deep layer of fine-grained Inconel may be associated with surface roughness, commonly found to be a depth of 5 to 10 μ in Inconel tubing.

Diffusion Experiments

In Figures 7 through 12, the results of the electropolishing radioassay procedure are plotted as the logarithm of the concentration [counts/(min)(mg)] as a function of the square of the average depth of penetration of the chromium-51. In all except the 600 C plot, in which almost negligible penetration occurred, a smooth curve resulted which can be resolved into two distinct sections. Resolution was accomplished by extrapolating the tail of the curve to the ordinate and subtracting these values from the early portion. This is similar to the findings and procedures of Kishkin and Bokstein.⁽³⁾

The method used for calculating the grain-boundary-diffusion and volume-diffusion rates is not rigorous. As was shown in the Russian studies^(3,4), the grain-boundary- and volume-diffusion rates are not independent and can be separated experimentally only by work with both single crystals and polycrystalline materials. The effective grain-boundary area must be known even for an application of the theoretical method of Fisher⁽⁸⁾, which is itself only an approximation for an idealized situation.

The basis for the approximations used in this report are the concentration-depth penetration curves obtained from the electropolishing technique coupled with the metallographic examination of the grain size and orientation in the specimens. The initial surface layer consisted of polycrystalline material where the grain size was very small compared with that of the bulk metal phase. Immediately beneath this surface layer were grains whose diameters were large compared with the maximum penetration of the radioactive tracer. For example, some of these grains have diameters of up to 6 mils compared with a maximum tracer penetration of from 3 to 4 mils. Work by other investigators indicates that the grain-boundary-diffusion rate is generally higher than the volume-diffusion rate. The predominant rate will depend upon the relative grain

SECRET

SECRET

41

size and boundary area of the portion of the specimen being considered. In the specimens studied in this work the first 0.5 mil, consisting of small grains, supported primarily grain-boundary diffusion. The major portion of the volume electropolished from the specimen consisted of large grains with a high volume-to-surface area ratio. The predominant rate in this region would be expected to be that of volume diffusion. The tail of the curve of the log-concentration versus the square of the depth came from the portion of the specimen where grain-boundary diffusion again becomes important, since it was one or more grain diameters from the surface in most cases. Analysis of the curves on this basis yields values for diffusion rates which are only approximations of the true rates. However, the rates determined in this manner have been found to check within experimental error with the work of other investigators, as shown in Table 3.

As expected, both volume and boundary diffusion increased rapidly with temperature, and boundary diffusion was more rapid than volume diffusion. The effect of small additions of other elements to nickel-base alloys containing chromium in reducing the diffusion rate is seen in Tables 3 and 4. Figure 13 illustrates the direct relation between diffusion rate and transfer rate as a function of temperature. These data indicate the effect of the metallurgical condition of the surface and the initial layers (e.g., the first 5 mils, and especially the first 0.5 mil) of the tubing on the diffusion rate and, consequently, on the transfer rate.

The most valuable information obtained from the isothermal studies was the temperature function of the rate of exchange in systems where no corrosion occurred. With the temperature dependence known, the data from polythermal studies could be resolved into two contributions, one from simple exchange and the other from mass transport. The method in which this information was applied is described in the discussion of the polythermal studies.

Other valuable information consisted of the observations that the exchange reaction was a simple heterogeneous type in which the long-term rate was controlled by the rate of diffusion in the solid phase. In such a system, the natural corollaries are lack of dependence upon chromium concentration in the salt phase, and no influence of the presence or absence of uranium on the rate of exchange. These effects were observed experimentally. Heterogeneous exchange reactions are dependent initially upon the condition of the surface of the solid phase and this was also observed in the Inconel-No. 30 salt mix system. Long-term exchange rates must be proportional to the rate of diffusion in the metal, as is shown in Figure 3, and not a function of surface conditions or chromium concentration in the salt.

Polythermal Studies

Tilting-Capsule Experiments

Figure 14 shows the activity profile obtained in the tilting-capsule experiments. Conditions of the tilting experiments made the data very difficult to interpret. Corrections had to be made for time of contact and area of contact, as well as a distorted temperature profile. As a result, the indications of a mass transport pattern are not clearly defined. There appears to be no single temperature where the transport was

SECRET

SECRET

42

maximized by a favorable diffusion rate. The activity of the wall increased steadily from 600 to 800 C. The equilibrium concentration of chromium was reached in 100 hr but the pattern for mass transport which was shown by later thermal-convection and pumping loops is apparently obscured by the nature of the corrections made on the data and the difficulty of interpretation.

The fact that in Capsule 4 the low-temperature end was neutron activated resulted in a lower rate of supply of chromium tracer to the salt. In fact, the specific activity of the salt in this case was only one-eighth of that of Capsules 1 through 3.

Thermal-Convection-Loop Experiments

In the hypothetical situation where No. 30 salt is flowing in a polythermal system but no corrosion is taking place, the distributions in the wall of chromium tracer added to the salt would be as shown in Figure 21. Distribution around the point of maximum temperature would be determined by the rate of diffusion of the chromium into the metal. The experimentally determined diffusion rates form the basis for this plot. Corrosion is also a function of temperature and could be expected to distort the theoretical exchange-diffusion picture of Figure 21 in a manner which is symmetrical around the maximum temperature. However, when the equilibrium concentration of chromium has been reached in the salt and chromium is being deposited with the specific activity of the chromium in the salt, the activity profile will be distorted, giving a second maximum at the favorable temperature for deposition.

Several of these conditions are shown by the thermal-convection-loop experiments. In thermal-convection Loop 2, operated 400 hr, a pattern of transport developed (Figure 16). The usual increase in gross chromium-51 activity with increasing temperature, due to randomization effects, can be seen. However, superimposed on this curve is an increased specific activity caused by actual chromium transport. This occurs in a zone of optimum deposition conditions and results in a plateau in the gross-transport curve. As shown in the inset curve, this peak occurred at 1335 F, which was about 110 F below the maximum wall temperature, and on the "upstream" side of the maximum wall temperature.

In this region, the bulk-salt temperature was lower than both the maximum bulk-salt temperature and the associated interface or wall temperature. This condition affords the combination of a chemical driving force toward chromium deposition from the chromous fluoride-laden salt, with fast exchange-diffusion rates at the high interface temperature. Deposition probably occurred throughout the system, with the possible exception of regions of maximum temperatures. However, as shown in Figure 16, the major deposition occurred in this optimum transport zone.

This transport pattern was not developed in thermal-convection-Loops 1 and 3 (Figures 15 and 17). The gross activity of the wall increased with temperature in accordance with the randomization results. However, these loops were operated for only 125 and 288 hr, respectively, which is less than the 250 to 300 hr required to reach equilibrium in thermal-convection loops. The salt in Loop 3 was pre-equilibrated 192 hr in Inconel prior to being loaded into the loop. This may indicate that a 300-hr period is required to establish equilibrium in a thermal-convection-loop system, regardless of previous equilibration.

SECRET

SECRET

43

SECRET

FIGURE 21. DIFFUSION RATE AS A FUNCTION OF TEMPERATURE

SECRET

44

In thermal-convection-Loop 4, a maximum specific activity occurred at about 40 F below the maximum temperature, but the profile is poorly defined. This may be the result of two complicating factors. One of these was the pre-equilibration of the salt with irradiated Inconel to achieve an equilibrium salt solution containing chromium tracer. This was then contacted with fresh Inconel in the loop under isothermal conditions at 1650 F, which caused movement of a large amount of chromium tracer into the wall by exchange. When a polythermal situation was established, the chromium tracer in the wall was transferred to the salt at a rate which was a combination of corrosion, which removed macro amounts of chromium from the wall, and diffusion, which transferred chromium tracer into the metal. This more complicated situation is probably the reason for the distorted profile, and makes interpretation of the results difficult. In a broad sense, however, there is a similarity to the transport curve of Figure 16.

Pumping-Loop Experiments

A transport pattern similar to that in thermal-convection Loop 2 was found in pumping Loop 2 (No. 30 salt mix in Inconel), which operated for 240 hr at a maximum temperature of 1650 F. A 180 F temperature drop was established by using air cooling. No deposits were observed in this loop. An increased specific activity occurred again in a region, upstream of the maximum wall temperature, where the wall temperature was approximately 100 F below the maximum. Only approximate temperature values can be given, since experimental measurements were not obtained at the sections analyzed.

This transport pattern was not developed in pumping Loop 1. However, the usual increase in gross activity with increasing temperature due to randomization can be seen. Pumping Loop 1, with No. 108 salt mix in Inconel, operated for 500 hr at a maximum temperature of 1450 F and a temperature drop of 200 F established by water cooling. Massive crystalline deposits of chromium were found in the coolers. With undoubtedly different equilibrium concentrations for chromous fluoride in No. 108 salt mix and with drastic cooling by the water coolers, the chromous fluoride concentration required for deposition of chromium in the cold zone was exceeded. This removal of chromium from the system by deposition covered up the possibility of observing any removal by diffusion. Also, of general interest, the interaction of silver with the No. 108 salt mix-Inconel system can be seen in pumping Loop 1. Silver-plated Inconel sections in both the hot and cold zones were similar to adjacent Inconel sections in gross activity. This indicated that the plating was ineffective, possibly due to porosity. Subsequently, porosity of the silver plating was established by metallographic analysis. Gross activity of a silver-wire section in the hot zone was about 4 per cent of the activity of adjacent Inconel sections (compared by counts/min/in.² of surface). This indicated a greatly reduced randomization effect due to a low rate of removal of chromium-51 from the surface. In the cold zone, the activity of a silver-wire section was about 50 per cent of the activity of adjacent Inconel sections. This relative increase in activity of the silver wire can be accounted for by the presence of a grayish-black film of deposits, probably containing chromium, on the wire.

SECRET

SECRET

45

CONCLUSIONS

Listed below are the significant facts established in this investigation:

- (1) The over-all exchange rate of chromium in the CrF_2 -No. 30 salt-Inconel system increases rapidly with temperature.
- (2) The over-all exchange rate of chromium in the CrF_2 -No. 31 salt-Inconel system is equivalent to the exchange rate of the No. 30 salt mix system.
- (3) There is no chromium concentration effect on the exchange rate in the No. 31 salt mix system.
- (4) Exchange-rate curves can be separated into a high early exchange rate and a low long-term rate.
- (5) The exchange rate is diffusion controlled at all temperatures investigated. That is, the exchange rate observed is the over-all rate as limited by the diffusion rate.
- (6) An increase in exchange rate, in certain cases, was correlated directly with a 0.50-mil-thick surface layer of fine-grained Inconel on the ID of the Inconel tubing.
- (7) An increase in exchange rate was associated also with an increase in the ratio of surface area of contact to salt volume.
- (8) The diffusion rate of chromium in Inconel increases rapidly with temperature.
- (9) Two separate diffusion rates are observed — grain boundary and grain volume, with grain-boundary diffusion being more rapid.
- (10) The direct relation between diffusion and exchange rate is illustrated when the logarithms of the rates are plotted versus the reciprocal absolute temperature.
- (11) Considerable reduction in the diffusion rate can be attained with small additions to nickel-base alloys.(4)
- (12) Similar patterns of chromium transport were obtained with No. 30 salt mix in Inconel in a thermal-convection loop and in a pumping loop.
- (13) No transport pattern developed in thermal loops equilibrated less than 300 hr.

SECRET

SECRET

46

- (14) No diffusion transport pattern developed in an Inconel-No. 108 salt mix pumping loop in which massive crystalline deposits of chromium were found. Also, in this system, it was found that an extremely small amount of chromium diffuses into silver.
- (15) Optimum conditions for transfer of chromium from salt to metal exist about 100 F below and upstream of the maximum wall temperature.
- (16) Chromium will not deposit in the cold zone in the Inconel-No. 30 salt mix system unless the equilibrium concentration of chromous fluoride in the hot zone exceeds the equilibrium concentration of chromous fluoride supportable by pure chromium deposits in the cold zone.⁽¹⁾

The facts established by the experimental study point to a situation which is very similar to that hypothesized by Grimes.⁽¹⁾ The situation may be summarized in the following manner. There are two steps involved in the mass-transport process of supplying chromium to and removing chromium from the salt. There is a chemical driving force to maintain an equilibrium amount of chromous fluoride in the salt by the reaction $2\text{UF}_4 + \text{Cr} \rightleftharpoons 2\text{UF}_3 + \text{CrF}_2$. The second step is the diffusion of chromium to or away from the wall surface. In supplying chromium to the salt, both these steps are favored by higher temperature. Maximum corrosion occurs, as might be expected, then, in the highest temperature zones. The chemical drive to maintain an equilibrium amount of chromous fluoride by removing chromium from the salt would normally be dominant at lower temperatures. However, in Inconel-No. 30 salt, chromium normally cannot be removed by deposition in the cold zone since the equilibrium concentration of chromous fluoride in the salt at the high temperature is less than the equilibrium concentration which could be supported by pure chromium deposits at the low temperature. Since corrosion continues in this system after the equilibrium concentration of chromous fluoride has been developed in the salt, the chromium must be removed from the salt by diffusion into the wall. This study indicated the existence of an optimum zone for removal of chromium from the salt at a temperature about 100 F below and upstream of the maximum wall temperature. In this optimum zone, the chemical drive of the chromous fluoride-laden salt is in balance with the fast exchange-diffusion rate of a high interface temperature. Since the exchange rate is diffusion controlled, and since the diffusion rate increases with temperature, the over-all corrosion process is controlled by the diffusion rate at the intermediate temperature of this optimum chromium removal zone. This process should result in a depletion of chromium in the highest temperature zone of the metal and an increase in concentration in the intermediate temperature zones. This would continue until ultimately (perhaps years) this process would result in a chromium concentration gradient in the metal with a minimum in the hot zone and a maximum in a colder zone. In other words, the system is tending to develop a chromium concentration gradient in the metal such that its activity at all temperatures satisfies the conditions for equilibrium with the salt at that temperature.

In similar systems, but systems in which the equilibrium concentration for pure metal is exceeded in the salt of the cold zone, the over-all process is controlled by either the deposition rate in the cold zone (chromium removal) or the diffusion rate in the hot zone (chromium supply), whichever is slower.

SECRET

SECRET

47

With the hypothesis of the intermediate-temperature zone diffusion control in mind, results of experimental work performed by other investigators^(9,10) are understandable. Several effects are listed below:

- (1) Continued corrosion without deposition after the equilibrium concentration of chromous fluoride in the salt had been attained. This is the result of chromium transport and deposition in the intermediate-temperature zone.
- (2) Lack of effect of flow rate on corrosion after equilibrium chromous fluoride concentrations were established (thermal loops versus pumping loops). The rate-determining step was the diffusion of the chromium into the wall and this is not affected by flow rate.
- (3) Decided effect of maximum wall temperatures on corrosion. The maximum temperature controls the chromium supply and also the point at which the chromium is deposited, thus the diffusion and corrosion rate.
- (4) Minor effect of maximum salt temperature on corrosion, the wall temperature being the important one.
- (5) No effect of area-to-volume ratio in the cold zone on corrosion, since the intermediate-temperature zone is controlling.
- (6) No effect of ratio of hot-leg surface to total loop volume ratio on corrosion. [About Items (5) and (6), if the ratio of the surface area of contact to the volume of salt contacted were changed significantly in the optimum removal zone, a visible effect may be realized. In the experiment where the area to volume ratio was increased to 140 per cent, the exchange increased from 49 to 59 per cent, or by 20 per cent. However, also associated with this increase was an increased proportion of finer grained surface material contacted, which may have accounted for a large share of the 20 per cent increase.]
- (7) Inconsistent effect of temperature differential on corrosion as a result of the dependence of the corrosion and deposition primarily upon the maximum temperature.
- (8) Lack of effect of UF_3 additions to the fluoride mixture.
- (9) Significant reduction in attack with the addition of UF_3 to KF-LiF -base mix, in which deposition can occur. [Regarding Items (8) and (9) it should be remembered that, since diffusion in the intermediate temperature zone is controlling the reaction $2\text{UF}_4 + \text{Cr} \rightleftharpoons 2\text{UF}_3 + \text{CrF}_3$ in the Inconel-No. 30 salt system, shifting of the equilibrium condition by additives would not be effective. However, when deposition occurs, additives may be effective in reducing the corrosion rate if the exchange rate in the cold zone is

SECRET

SECRET

48

slower than the diffusion rate in the hot zone (and thus controlling).
This appears to be the case in the KF-LiF-base mix.]

REFERENCES

- (1) Grimes, W. R., "Some Observations on Mass Transfer of Chromium by Molten Salts", ORNL-2106, p 96 (June 10, 1956).
- (2) Wahl, A. C., and Bonner, N. A., Radioactivity Applied to Chemistry, John Wiley and Sons, Inc., New York (1951), p 71.
- (3) Kishkin, S. T., and Bokstein, S. Z., "Distribution and Diffusion of Components in Metal Alloys Studied by the Autoradiographic Method", Peaceful Uses of Atomic Energy, Proceedings of the International Conference in Geneva, 15, 87-98 (August 1955).
- (4) Gruzin, P. L., and Federov, G. B., "Chromium Diffusion in Nickel-Base Solid Solutions", Doklady Akademii Nauk SSSR, 105 (2), 264-267 (1955).
- (5) Reference (2), pp 7-11 and pp 34-43.
- (6) Friedlander, G., and Kennedy, J. W., Introduction to Radiochemistry, John Wiley and Sons, Inc., New York (1949), pp 285-288.
- (7) Zimen, K. E., "Isotope Exchange With Solids as a Method for Self-Diffusion Measurements", Proceedings of the International Symposium on the Reactivity of Solids, Gothenburg, pp 85-92 (1952).
- (8) Fisher, J. C., "Calculation of Diffusion Penetration Curves for Surface and Grain Boundary Diffusion", Journal of Applied Physics, 22, 74 (1951).
- (9) De Van, J. H., and Kovacevich, E. A., ORNL-2080, p 53 (April 10, 1956).
- (10) De Van, J. H., and Kovacevich, E. A., ORNL-2217, p 45 (October 10, 1956).

RBP:DNS:MP:GDC/mln

SECRET