Written: January 26, 1970
Distributed: March 16, 1970

LA-4367
UC-4, CHEMISTRY
TID-4500

LOS ALAMOS SCIENTIFIC LABORATORY
of the
University of California
LOS ALAMOS • NEW MEXICO

**Unit Cell of the Zeta Phase of the
Plutonium-Zirconium and the
Plutonium-Hafnium Systems**

by

**W. H. Zachariasen
F. H. Ellinger**

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission nor any person acting on behalf of the Commission

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that dissemination of the information is required by any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

UNIT CELL OF THE ZETA PHASE OF THE PLUTONIUM-ZIRCONIUM AND THE PLUTONIUM-HAFNIUM SYSTEMS

by

W. H. Zachariasen and F. H. Ellinger

ABSTRACT

The unit cell of the isostructural Pu-Zr and Pu-Hf zeta phases (~3 at. % Zr or Hf) was found to be body-centered tetragonal with $a = 18.19 \pm 0.01 \text{ \AA}$ and $c = 7.851 \pm 0.003 \text{ \AA}$.

INTRODUCTION

The existence of the Pu-Zr zeta phase has been reported by Ellinger¹ and confirmed by Kutaitsev et al.² and Taylor.³ The isostructural Pu-Hf zeta phase has been observed by Kutaitsev et al.² and by Ellinger et al.⁴ These zeta phases are stable below about 270°C at atmospheric pressure. Their equilibrium concentration of zirconium or hafnium is about 3 at. %, however, the metastable zeta phase containing as little as 2 at. % Zr or Hf is readily prepared. Since attempts to isolate single crystals from polycrystalline alloys were unsuccessful, the unit cell of the zeta phase was determined from x-ray diffraction powder data.

EXPERIMENTAL

Powder data were obtained both with a Norelco diffractometer and with 114.59-mm-diam powder cameras. The diffractometer traces were all made with $\text{CuK}\alpha$ radiation, but the most satisfactory photographic patterns were taken with $\text{CrK}\alpha$ radiation. Alloy buttons about 1 cm in diameter that had been mounted in epoxy resin and polished for microscopic examination served as diffractometer samples. Alloy filings sealed in evacuated, clear sili-

ca capillary tubes were used in the powder cameras.

RESULTS

By the method of searching out relationships in $\sin^2 \theta$ values, the x-ray powder data of the zeta phase have been indexed on the basis of a body-centered tetragonal unit cell. Table I lists the low-angle reflections taken from the diffractometer trace of a Pu-2 at. % Hf alloy. The calculated $\sin^2 \theta$ values are based on the lattice parameters

$$\begin{aligned} a &= 18.167 \pm 0.003 \text{ \AA} \\ c &= 7.856 \pm 0.001 \text{ \AA} \end{aligned}$$

The good agreement between the calculated and observed values, and the small number of missing reflections, support the correctness of the indexing.

Precision unit-cell dimensions were determined by least-squares extrapolation of the measurable high-angle lines on powder patterns taken with $\text{CrK}\alpha$ radiation. The computer program of Vogel and Kempter⁵ as modified by Roof⁶ was used. A typical set of data of a Pu-3 at. % Zr alloy is shown in Table II, which yielded the following lattice parameters

TABLE I

Pu-2 at. % Hf ZETA PHASE DIFFRACTOMETER DATA (CuK α)BODY-CENTERED TETRAGONAL, $a = 13.167 \pm 0.003 \text{ \AA}$ $c = 7.956 \pm 0.001 \text{ \AA}$

<u>hkl</u>	<u>$10^5 \sin^2 \theta (\text{calc.})$</u>	<u>Peak Intensity</u>	<u>$10^5 \sin^2 \theta (\text{obs.})$</u>	<u>$d, \text{\AA} (\text{obs.})$</u>
600	6471	4	6478	3.029
402	6731			
332	7091			
620	7190	5	7205	2.872
422	7441	15	7450	2.824
611	7612			
541	8331	5	8335	2.670
512	8519	83	8529	2.640
103	8833	10	8863	2.589
710,550	8998			
631	9050	90	9058	2.561
640	9347	37	9350	2.521
213	9552	76	9585	2.490
442	9498			
701	9768	59	9776	2.466
532	9958	3	9963	2.442
303	10270	7	10290	2.403
602	10317			
730	10426			
721	10488	45	10498	2.379
323	10990	16	11016	2.323
622	11036			
800	11504	12	11503	2.273
413	11709			
651	11926	10	11940	2.231
820	12223	7	12225	2.205
811,741	12645	3	12639	2.168
712,552	12835			
660	12942			
503,433	13147	19	13183	2.123
642	13193			

TABLE II

Pb-3 at. % Zr ZETA PHASE, HIGH-ANGLE DIFFRACTION DATA (CrKa)

BCT $a = 13.1959 \pm 0.0016$, $c = 7.3511 \pm 0.0003$ Å

HKL	$10^4 \sin^2 \theta (\text{calc.})$	$10^4 \sin^2 \theta (\text{obs.})$	Intensity
10·9·3 α_1	9078	9084	S
606 α_1	9079		
12·8·2 α_1	9084		
10·9·3 α_2	9109	9124	S
606 α_2	9110		
12·8·2 α_2	9115		
15·0·1 α_1 , 12·9·1 α_1	9119	9156	MI
15·0·1 α_2 , 12·9·1 α_2	9150		
945 α_1	9155		
13·4·3 α_1 , 11·8·3 α_1	9237	9244	S-
626 α_1	9238		
14·4·2 α_1	9242		
13·8·1 α_1	9436	9442	W
12·7·3 α_1	9553	9556	W
10·3·5 α_1	9630	9634	MI
716 α_1 , 556 α_1	9634		
12·10·0 α_1	9658		
10·3·5 α_2	9663	9667	WI
716 α_2 , 556 α_2	9667		
14·1·3 α_1	9712		
646 α_1	9713	9714	S
12·4·4 α_1	9735		
14·1·3 α_2	9745		
646 α_2	9746	9741	S-
875 α_1	9788		
15·1·2 α_1	9796		
875 α_2	9821	9826	W
15·1·2 α_2	9829		

$$a = 18.1959 \pm 0.0016 \text{ \AA}$$

$$c = 7.8511 \pm 0.0008 \text{ \AA}.$$

We found that the lattice parameters varied in a random manner from film to film evidently owing to the overlapping reflections and the consequent difficulty in accurately measuring their positions. The mean values as determined from eight separate samples of both Pu-Zr and Pu-Hf alloys are

$$a = 18.19 \pm 0.01 \text{ \AA}$$

$$c = 7.851 \pm 0.003 \text{ \AA}.$$

On the basis of these lattice parameters and a measured density of 17.5 g/cm^3 for the 3 at. % Hf zeta phase, the number of atoms in the unit cell is calculated to be 115.4, hence 116 so as to conform to the equivalent positions of a tetragonal space group. Thus, the ideal composition of zeta is probably Pu_{28}M (3.4 at. % Zr or Hf). With four formula weights per unit cell, the calculated density for Pu_{28}Zr is $17.44 \pm 0.04 \text{ g/cm}^3$ and for Pu_{28}Hf $17.57 \pm 0.04 \text{ g/cm}^3$.

ACKNOWLEDGMENTS

We wish to thank M. Gibbs, C. C. Land, V. G. Shadden, V. O. Struebing, and P. Vigil for their assistance.

REFERENCES

1. F. H. Ellinger, "Discussion of Plutonium-Zirconium Alloys," in *Plutonium 1960*, E. Grison, W. B. H. Lord, and R. D. Fowler (Eds.), (Cleaver-Hume Press, Ltd., London, 1961), pp. 318-319.
2. V. I. Kutaitsev, N. T. Chebotarev, I. G. Lebedev, M. A. Andrianov, V. N. Konev, and T. S. Menshikova, "Phase Diagrams of Plutonium with the Metals of Groups II A, IV A, VIII A and IB," in *Plutonium 1965*, A. E. Kay and M. B. Waldron (Eds.), (Chapman and Hall, London, 1967), pp. 420-449.
3. J. M. Taylor, "The Plutonium-Zirconium Equilibrium Diagram from 0 to 10 at. % Zr.," *J. Nucl. Mater.* **30**, 346-350 (1969).
4. F. H. Ellinger and C. C. Land, "The Constitution of Plutonium-Rich Plutonium-Hafnium Alloys," *J. Nucl. Mater.* **28**, 291-296 (1968).
5. R. E. Vogel and C. P. Kempter, "A Mathematical Technique for the Precision Determination of Lattice Constants," *Acta Cryst.* **14**, 1130-1134 (1961).
6. R. B. Roof, Jr., unpublished work (1968).