204 c
11.23
DWR- 1630

MASTER

ORNL-4600

UC-25 - Metals, Ceramics, and Materials

FUELS AND MATERIALS DEVELOPMENT PROGRAM

QUARTERLY PROGRESS REPORT

FOR PERIOD ENDING JUNE 30, 1970

THIS DOCUMENT CONFIRMED AS
UNCLASSIFIED
DIVISION OF CLASSIFICATION
BY 9 H Kahn / amh
DATE 12/1/70

OAK RIDGE NATIONAL LABORATORY

operated by

UNION CARBIDE CORPORATION

for the

U.S. ATOMIC ENERGY COMMISSION

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

P7566

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

8. ~~X~~ SHIELDED METAL-ARC WELDING FOR IMFBR COMPONENTS

W. O. Harms G. M. Slaughter

The objective of this program is to evaluate the shielded metal-arc (stick electrode) welding process for fabricating and repairing certain stainless steel components for liquid-metal fast breeder reactors (IMFBR). We very slightly modified the flux coatings of electrodes and are determining the influence of minor elements on the mechanical properties of the weld metal at elevated temperature. Flux coatings traditionally have been evaluated and selected by the relative ease with which weld metal can be deposited, and bead contour, arc stability, and deposition efficiency are usually prime considerations. The effect of the coating on the properties at elevated temperatures has not been seriously considered.

As part of this effort, we are also providing weld specimens to Battelle Memorial Institute Pacific Northwest Laboratory (BNWL) for a program of irradiations for the Fast Flux Test Facility (FFTF) Reactor.

Effect of Variations in Flux Coating

Preparation and Creep-Rupture Testing of Weldments (N. C. Binkley, G. M. Goodwin, D. G. Harman)

We reported¹ that the shielded metal-arc weldments display decreasing creep elongations with increasing time to rupture at 650°C (1200°F). We showed that, for the standard lime-TiO₂ coating, the ductility loss was associated with a metallurgical instability at the phase boundary. We suspect that the ferrite that is concentrated in these locations is perhaps transforming to the brittle sigma phase at the test temperature and that this is responsible for the loss of creep ductility for the welds of other compositions as well.

Sigma phase forms most readily at 650°C (1200°F) but has been reported for service temperatures ranging from about 500 to 760°C. We expected that the embrittlement that would occur at temperatures below 650°C would be more sluggish and, consequently, more difficult to demonstrate at testing times commensurate with the laboratory facilities committed to this program.

Creep-rupture tests of specimens from welds made with electrodes with the standard lime-TiO₂ coating at 593°C (1100°F) did show the embrittlement to be sensitive to temperature in the direction expected. The relationship of rupture time with stress and elongation is shown in Fig. 8.1 for both test temperatures for this weld. We were quite surprised that the creep

Fig. 8.1. Creep-Rupture Properties of Shielded Metal-Arc Weldment from Standard Lime-Titania Coated Electrode Tested in the As-Welded Condition.

ductility at 593°C decreased as rapidly as is shown here. Values of less than 5% can be expected for times greater than 1000 hr, even at the lower temperature. Since embrittlement due to formation of carbides at grain boundaries has generally been found to be most serious between 550 and 600°C for wrought austenitic alloys, the role of carbides in the instability of phase boundaries in weld metal is being investigated.

We recently included three experimental lime-base coatings in our studies of compositional variations. These were formulated by Combustion Engineering personnel at Chattanooga, Tennessee, and their tests show them to have improved ductility as compared with welds made with the standard lime-coated electrode. The new formulations contain a

ferro-titanium addition, ferro-titanium plus B, and ferro-titanium plus B and P. Figure 8.2 shows their test results along with ours for the weld from standard lime-coated electrode. We are preparing test specimens from the welds made at Combustion Engineering and have also obtained electrodes so as to prepare welds using equipment and personnel common to the rest of our program.

Fig. 8.2. Effect of Compositioned Variations on the Creep-Rupture Properties of Weldments from Lime-Base Coated Electrodes Tested at 650°C in the As-Welded Condition.

The status of our tests at 650°C and 18,000 psi of the welds made with the controlled lime-titania coatings is shown in Table 8.1. We previously showed C to be only moderately effective in increasing the rupture time.¹ Close examination of the creep curve from the high-C weld

Table 8.1. Effect of Compositional Variables on Creep Properties of Shielded Metal-Arc Welds in Stainless Steel at 650°C and 18000 psi

Coating	Rupture Life (hr)	Total Elongation (%)	Minimum Creep Rate (%/hr)
Commercial lime-TiO ₂ , 0.044C-0.47Si-0.012P- 0.016S-0.001 B	576	0.50	1.9×10^{-4}
Low (0.035%) C	490	4.5	1.0×10^{-3}
High (0.074%) C	6000 ^a	0.46	$< 5.0 \times 10^{-5}$
Low (0.29%) Si	592	3.2	1.0×10^{-3}
High (0.73%) Si	710	0.2	2.0×10^{-4}
Low (0.009%) P	To be tested		
Medium (0.023%) P	To be tested		
High (0.034%) P	1655	0.97	2.5×10^{-4}
Low (0.006%) S	526	0.75	8.3×10^{-4}
High (0.027%) S	548	0.67	3.9×10^{-4}
Medium (0.004%) B	2670	1.0	1.1×10^{-5}
High (0.006%) B	To be tested		

^aTemperature drift caused specimen to rupture early. Rupture time extrapolated from tests of higher stress.

showed a slight increase in creep rate midway in the test due to a temperature drift caused by a faulty component in our temperature standard. Since the total creep strain is limited to very small values, a slight change in minimum creep rate severely affects the rupture time. Tests at two other stress levels substantiated this. These results show that additions of C increase strength but decrease ductility, while additions of B and P increase strength more and offer some promise in indicating solutions to the problem of loss of ductility.

Tensile properties of the standard lime-TiO₂ weld are compared with those of a submerged-arc weld elsewhere.²

Notes

1. N. C. Binkley, G. M. Goodwin, and D. G. Harman, Fuels and Materials Development Program Quart. Progr. Rept. March 31, 1970, ORNL-4560, pp. 119-126.
2. D. G. Harman and G. M. Goodwin, "Investigations of Mechanical Properties," pp. 131-136, this report.