135
4-26

Fast reactor A & B formal

GEAP-10028-37
AEC RESEARCH AND
DEVELOPMENT REPORT
MARCH 1971

MASTER

CHH

**SODIUM-COOLED REACTORS
FAST CERAMIC REACTOR
DEVELOPMENT PROGRAM
THIRTY-SEVENTH QUARTERLY REPORT
NOVEMBER 1970-JANUARY 1971**

U.S. ATOMIC ENERGY COMMISSION
CONTRACT AT (04-3)-189
PROJECT AGREEMENT 10

GENERAL ELECTRIC

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

**SODIUM-COOLED REACTORS
FAST CERAMIC REACTOR DEVELOPMENT PROGRAM**

Thirty-Seventh Quarterly Report

November 1970 – January 1971

Approved:

J. H. Field, Principal Project Engineer
Fast Ceramic Reactor Development Program

Approved:

E. L. Zebroski, Manager
Development Engineering

Prepared for the
United States Atomic Energy Commission
Under Contract No. AT(04-3)-189
Project Agreement No. 10

*Printed in U.S.A. Available from the
Clearing House for Federal Scientific and Technical Information
National Bureau of Standards, U. S. Department of Commerce
Springfield, Virginia
Price: \$3.00 per copy*

BREEDER REACTOR DEVELOPMENT OPERATION • GENERAL ELECTRIC COMPANY
SUNNYVALE, CALIFORNIA 94086

GENERAL ELECTRIC

6239—Dev. Eng.—(110)
(300)—MS—3/71

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

leg

LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

TABLE OF CONTENTS

1. INTRODUCTION	1
2. SUMMARY	1
2.1 Task B – Defected Fuel Testing	1
2.2 Task C-1 – Safety Experimentation (Transient Overpower)	1
2.3 Task C-2 – Safety Experimentation (Loss of Flow)	7
2.4 Task E – Fuel Materials Properties and Performance Evaluation	7
2.5 Task F – Fast Flux Tests and Support	7
2.6 Task G-6 – Core Design Analysis	7
2.7 Task G-10 – Kinetic Analysis	7
2.8 Task G-12 – ANL Safety/Core Design Guidance	7
2.9 Task L – Cladding Development	7
2.10 Task N – Core Physics Analysis	13
2.11 Task P – Fuel Element Design Analysis	13
3. TASK B – DEFECTED FUEL BEHAVIOR	13
3.1 General	16
3.2 Defected Fuel Testing	16
3.3 Fission Product Distribution	19
4. TASK C-1 – SAFETY EXPERIMENTATION (TRANSIENT OVERPOWER)	20
4.1 General	20
4.2 High Burnup Fuel Experiments	20
4.3 Comparative Tests	21
4.4 Mark II Loop Tests	21
5. TASK C-2 – SAFETY EXPERIMENTATION (LOSS OF FLOW)	21
5.1 General	22
5.2 Mockup 1B	22
5.3 Capsule C10X	22
5.4 Capsule C10A	23
6. TASK E – FUEL MATERIALS PROPERTIES AND PERFORMANCE EVALUATION	23
6.1 General	24
6.2 Material Properties Studies	24
6.3 Center Temperature Limits and Fuel Behavior	24
6.4 Fuel-Fission Product-Cladding Reactions	24
6.5 Electron Microprobe Examination of Irradiated Specimens	25
7. TASK F – FAST FLUX TESTS AND SUPPORT	40
7.1 General	40
7.2 Medium Power Long-Term Irradiations	41
7.3 High Power Intermediate Burnup Irradiations	41
7.4 Elevated Cladding Temperature Tests	43
7.5 Unencapsulated Fuel Pin Irradiations	46

TABLE OF CONTENTS (Continued)

7. CONTINUED	
7.6	Capsules F12P and F12Q (Effect of Radial Restraint on Fuel Swelling) 49
7.7	Experimental Tests in EBR-II 51
7.8	Fuel Burnup 51
8. TASK G-6 — CORE DESIGN ANALYSES	52
8.1	General 52
8.2	FFTF Grid-Spaced Driver Fuel Assembly 52
8.3	F9E Grid Spacer Irradiation Test 53
8.4	Out-of-Pile Grid Spacer Mechanical Tests 53
8.5	Steady-State and Defected Fuel Irradiation Testing Needs 55
8.6	Fuel Element Failure, Coolant Boiling and Operating Safety Limits 55
9. TASK G-10 — KINETIC ANALYSIS	55
9.1	General 55
9.2	Model Development 55
10. TASK G-12 — ANL SAFETY/CORE DESIGN GUIDANCE	67
10.1	General 67
11. TASK L — CLADDING DEVELOPMENT	68
11.1	General 68
11.2	Materials Irradiation Performance 68
11.3	Cladding Alloy Swelling 69
11.4	Cladding Alloy Mechanical Properties 75
11.5	Materials Management 81
12. TASK N — CORE PHYSICS ANALYSIS	83
12.1	General 83
12.2	Compilation and Distribution of Evaluated Data 83
12.3	Supplementary Analytical Interpretation of Integral Data 83
12.4	Improvement of Fuel Cycle and Management Schemes 85
12.5	Improvements of Existing Methods for Generating Group Constants 85
12.6	Computers, Computer Language, and Code Center 85
13. TASK P — FUEL ELEMENT DESIGN ANALYSIS	86
13.1	General 86
13.2	Fuel Performance Simulation 86
13.3	Fuel Behavior Studies 87
APPENDIX A — PRIOR REPORTS	89
APPENDIX B — LIST OF ABBREVIATIONS, SYMBOLS, AND ACRONYMS	97
DISTRIBUTION	101

LIST OF ILLUSTRATIONS

Figure No	Title	Page No
3-1	Test Apparatus For The Determination Of The Failure Detection System Line Plugging Susceptibility	18
6-1	Microprobe Analysis Of Xenon In Irradiated Mixed Oxide Fuel Pins F2C and F0K	26
6-2	Radial Concentrations Of Pu/(Pu+U), Oxygen, And Corresponding Microstructure In Specimen F2C-8A	27
6-3	Radial Concentrations Of Pu/(Pu+U), Oxygen, And Corresponding Microstructure In Specimen F2C-11B (Reduced 90% for reproduction purposes)	28
6-4	Radial Concentrations Of Pu/(Pu+U), Oxygen, And Corresponding Microstructure In Specimen F0K-H2 (Reduced 90% for reproduction purposes)	29
6-5	Specimen Current And X-Ray Images Showing The Distribution Of Te, Cs and Cl In The Crack Observed In Section F2H-5	31
6-6	Specimen Current And X-Ray Images Of Cs, Te And Pd In Cladding Crack of Section F2H-5	32
6-7	X-Ray Images Of Si, Fe, Cr And Ni In The Crack In Section F2H-5	33
6-8	Optical, Specimen Current And X-Ray Images Showing The Distribution Of Fuel In The Center Void Region Of F2G	34
6-9	X-Ray Images Showing The Distribution Of The Primary Species Of The Center Void Phase Region Of Specimen F2G	35
6-10	Specimen Current And X-Ray Images Showing Distribution Of Fuel, Silicon And Aluminum In The Banded Phase Of Specimen F2G	36
6-11	Photomicrograph Of Specimen F2G-G And Corresponding Radial Distributions Of Pu/(Pu+U) Oxygen And Xenon	37
6-12	Computer Oxygen Distribution In A Pin Operating At 16.7 kW/ft In EBR-11 At Start Of Life	39
7-1	Fission Product Material In Fuel-Cladding Gap Of Fuel Pin F2G	42
7-2	Group F3B Capsule Tube Profiles (E1H-23)	45
7-3	F3A Cladding Microstructures Showing Intergranular Penetration	47
7-4	Length Increase As A Function Of Fluence For Unencapsulated Group F9A and F9C Fuel Pins	48
7-5	Diameter Increase As A Function Of Smeared Density For Unencapsulated Group F9A And F9C Fuel Pins	50
9-1	Fuel Movement	56
9-2	Plot Of Fuel Rod Pressure And Fuel Gas Bubble-Pressure Versus Time	58
9-3	Upper And Lower Sodium Slug Velocities	59
9-4	Displacement Of Upper And Lower Sodium Slugs	60
9-5	Pressure Rise Due To Instantaneous Stoppage Of Sodium Flow At 1000°F	62
9-6	Void Pattern (First Bubble) For 3 Different Superheats	63
9-7	Void Pattern For 2 Different Superheats	64
9-8	Power And Reactivity For Sample FREADM-MARS	66
11-1	Effect Of Fuel Density On Peak Cladding Strain	72
11-2	Cladding $\Delta D/D$ Versus Local Burnup For 347 Cladding Pins Of Similar Smear Density (F2A F2T and F2G)	73
11-3	Clad Swelling In F-2 Series Fuel Pins	74
11-4	Swelling Of Type 304 SS - Measured By Profilometry Of F2 Capsule Tubes Data Normalized To $\phi t = 5 \times 10^{22} \text{ n/cm}^2$, $>0.1 \text{ MeV} - \text{GE}$	76
11-5	Biaxial Creep Strain Time Curves For 304 Stainless Steel Irradiated in EBR II Test Temperature 593°C (1100°F)	79
11-6	Effect Of Irradiation In The Creep Rate Of 304 Stainless Steel	80
13-1	Formation Of The Strong Unbroken Ring (SUR) Of Fuel	88

LIST OF TABLES

Table	Title	Page
2-1	Task B – Summary of Current Mixed Oxide Capsule Irradiations	2
2-2	Task C – Current Experimental Test Series	4
2-3	Task E – Summary of Current Mixed Oxide Capsule Irradiations	8
2-4	Summary of Task F Fast Flux Testing Program in EBR-II	10
2-5	Summary of Task F Thermal Flux Irradiations	12
2-6	Summary of Task L Capsules in EBR-II	14
6-1	Test Parameters of Thermal Gradient Experiments	25
7-1	Summary of Fission Gas Release for Pins F2D, F2G, F2V, and F2X	43
7-2	Fabrication Parameters and Diameter Change Data for Group F3B Capsules	44
7-3	Burnup Values for Group F2 Pins	51
8-1	Local Contact Load Test Results	54
11-1	Immersion Density Measurements on F2G, F2V, F2X Cladding Materials	70
11-2	Comparison of Swelling Data from 316 Cladding Fuel Rods	71
11-3	Immersion Density Data from F-2 Capsule Tubes	75
11-4	Biaxial Creep Tests: Test Conditions and Strain Rate Measurements After 1486 Hours Testing	77
12-1	Results of Fast Reactor Benchmark Calculations Using ENDF/B, Version II Data	84

HIGHLIGHTS

- An EBR-II specimen, irradiated to $\sim 60,000$ MWd/Te, was re-encapsulated and transferred to TREAT for overpower transient testing.

Using completely remote operations the C4H capsule was successfully filled with sodium and assembled into its TREAT pressure vessel. This is the first high-burnup specimen from EBR-II to be re-encapsulated for TREAT irradiation.

- Fuel pins with cladding made of types 316 and 321 stainless steels exhibit one-half to one-third as much swelling as pins clad in 304, after a burnup of $\sim 50,000$ MWd/Te in EBR-II.

Interim examinations of 52 unencapsulated fuel pins irradiated in EBR-II to burnups of 50,000 MWd/Te (nvt 0.4×10^{23} , $E > 0.1$ MeV) indicated one-half to one-third as much swelling in the axial and radial direction for 316 and 321 clad fuel pins compared to 304 clad pins.

- A reference design was selected for the fuel grid assembly of the FFTF driver.

A comparative analysis of three basic grid concepts in FFTF was completed to provide a basis for further development. Design of the F9E irradiation test assembly, which includes diagnostic capability for grid spacers, was completed.

- Volume increases of up to 10% have been measured for highly irradiated fuel cladding.

Immersion density measurements on fuel pin cladding irradiated to a fluence of 0.7×10^{23} ($E > 0.1$ MeV) indicate volume increases of 10% for 347 and 8.7% for 316. The 10% increase is the highest reported value to date for stainless steel irradiated in EBR-II.

- New code development standards have been developed which will aid code exchange between LMFBR development organizations.

This has been accomplished through participation in the *de facto* Committee on Computer Code Coordination.

- Radial distribution of retained xenon was measured in irradiated mixed-oxide fuel.

Fuel cross sections irradiated in EBR-II were examined by the electron microprobe to establish radial distributions of xenon. This analysis indicated that the radial distribution is a function of the peak operating temperature of the fuel element.

- Post-irradiation examination of five pins from the void deployment experiment (F3B) was initiated.

Destructive examination of six pins irradiated to a burnup of 85,000 MWd/Te indicated that the containment capsules increased in diameter between 6 to 8 mils. One of the pins being examined in this series is clad with 316 cold-worked stainless steel. This pin represents the highest burnup cold-worked specimen in the U.S. program.

- Destructive examination of unencapsulated pins from subassembly X040 indicated intergranular attack of the inside surface of the clad.

Observations in both 316 and 304 clad fuel pins irradiated to a burnup of 50,000 MWd/Te at clad temperatures in excess of 1100°F indicate intergranular attack of up to 9 mils in depth.

2

3

4

5

6

7

8

9

10

11

12

1. INTRODUCTION

The Fast Ceramic Reactor Development Program is an integrated analytical and experimental program directed toward the development of fast reactors employing ceramic fuels, with particular attention to mixed plutonium-uranium oxide. Its major objectives follow:

- Development of selected portions of a reliable, high performance fast reactors having nuclear characteristics which provide stable and safe operation.
- Demonstration of low fuel cycle cost potential for such reactors, primarily through achieving high burnup of ceramic fuels operating at high specific power.

Progress during the period of November 1970 through January 1971 on the currently active tasks of this program is described in subsequent sections.

This is the thirty-seventh in a series of quarterly progress reports written in partial fulfillment of Contract AT(04-3)-189, Project Agreement No. 10, between the United States Atomic Energy Commission and the General Electric Company. Prior progress reports to the Commission are listed in the Appendix.

2. SUMMARY

2.1 TASK B -- DEFECTED FUEL TESTING

Redesign of Capsule B9D was completed. Major changes were made to the binary gas control system. In addition, the capsule cold trap was replaced with an uranium metal getter to maintain sodium purity during irradiation. Preparation of 21 key documents that describe capsule fabrication, quality control, and quality assurance for transmittal to AEC-RDT was 71% complete. Qualification of welding and brazing processes, and of welders and brazers was continued.

Preliminary analysis has indicated the desirability of incorporating a thermal "switch" in the fluted liner of Capsule B9B to prevent overheating of the fuel pin in the event of failure of the helical induction pump for the capsule. A test program was initiated to evaluate the performance of radial heat pipes for this application.

The niobium and vanadium wires exposed to the loop sodium during the filling of Capsule B9C were removed and forwarded to ANL for oxygen analysis. Comparison of these analyses with those obtained from the loop sodium will provide information on the feasibility of using niobium and/or vanadium wire to measure the final oxygen level of the sodium in forced convection capsules at the conclusion of the experiment.

Alternative courses of action for Capsule B9C were identified and are being evaluated.

Nuclear analysis for the design of the B10A flux filter was initiated.

Analysis of leach samples from the miniloop was completed.

The status of Task B, capsule irradiations, is shown in Table 2-1.

2.2 TASK C-1 -- SAFETY EXPERIMENTATION (TRANSIENT OVERPOWER)

The C4X fuel specimen was subjected to a transient irradiation that resulted in a calculated $\geq 85\%$ molten fuel volume with cladding temperatures $>2000^{\circ}\text{F}$ ($>1090^{\circ}\text{C}$). There was apparent sodium boiling for ~ 0.8 second. Despite the adverse transient conditions, post-test neutron radiographs and capsule instrumentation indicate that the C4X fuel specimen did not fail.

The C4H fuel specimen, previously irradiated in EBR-II to $\sim 60,000$ MWd/Te burnup, was successfully encapsulated and sodium-filled by remote operations. The capsule was shipped to TREAT and irradiated for calibration purposes.

Preliminary results indicate that it will be possible to test fully enriched fuel specimens in multipin capsules with thermal flux filters.

Thermal hydraulic calculations to evaluate Mark II loop design parameters for TREAT tests were initiated.

The status of the current in-pile test program for Task C-1 is shown in Table 2-2.

Table 2-1
TASK B – SUMMARY OF MIXED-OXIDE CAPSULE IRRADIATIONS

Capsule Designation		Design Parameters							Operating Conditions					Status
		Fuel												
		Diameter (inch)	Length (inch)	Fuel-Cladding Gap (in.-diam)	Composition			Cladding Material Stainless Steel Type	Irradiation Facility	Cladding Surface Temp (°F)	Peak Rating (kW/ft)	Peak Burnup (MWd/Te)		
					Density (Smear) (% TD)	PuO ₂ (%)	O/M							
Purpose and Major Parameters														
B3D	Vented Fuel. Power profile simulates fuel in central core position. Natural convection cooling design.	0.217	20	0.006	85	25	1.97	316	V-Raft GETR	1100	18	700	Examination Completed	
B3E	Vented Fuel. Power profile simulates fuel in peripheral core position. Natural convection cooling design.	0.213	23	0.008	83	25	1.98	316	V-Raft GETR	1100	18	8,700	Examination Completed	
B3F	Vented Fuel. Power profile simulates fuel in peripheral core position. Natural convection cooling design.	0.212	23	0.008	84	25	1.98	316	V-Raft GETR	1100	15	23,500	Examination completed	
B4D	Vented Fuel. Power profile simulates fuel in central core position. Natural convection cooling design.	0.217	20	0.007	84	25	1.98	316	V-Raft GETR	1100	15	47,500	Examination completed	
B8B (2 pins)	Fuel-sodium compatibility. sodium-bonded fuel central temperature measured versus exposure time.	0.216	2	0.010	80	25	2.00	347	V-Raft	800	14	14,500	Examination completed	
		0.216	2	0.010	83	25	1.93		GETR					
B8C (2 pins)	Fuel-sodium compatibility versus burnup. Fission gas release versus burnup. Fuel-sodium-clad compatibility.	0.144	2.2	0.006	86	25	1.97	316	V-Raft	1100	21	113,500	Examination Completed	
		0.204	2.25	0.017*	84	25	1.97		GETR			57,000		

GEAP-10028-37

Table 2-1 (Continued)

		Design Parameters							Operating Conditions					
		Fuel												
Capsule Designation	Purpose and Major Parameters	Diameter (inch)	Length (inch)	Fuel-Cladding Gap (in.-diam)	Composition			Cladding Material Stainless Steel Type	Irradiation Facility	Cladding Surface Temp (°F)	Peak Rating (kW/ft)	Peak Burnup (MWd/Te)	Status	
					Density (Smear) (% TD)	PuO ₂ (%)	O/M							
B8D (3 pins)	Fuel-sodium compatibility versus density and stoichiometry and Pu content of fuel	0.214	1.75	0.0065	80-88	40	1.97	316	V-Raft	950	17.5	41,000	Examination	
		0.214	1.75	0.0065	80-88	25	1.97		GETR			43,500	completed	
		0.214	1.75	0.0065	80-88	25	1.94					41,400		
B9A (2 pins axially aligned)	Defected fuel pin. Fuel swelling versus stoichiometry in flowing sodium.	0.216	5	0.005	89	25	1.99	316	Special	1019	23.4	8,600	Examination	
		0.216	5	0.005	89	25	1.95		V-Raft GETR	971	23.4	8,600	completed	
E1J-B1	Test thermal expansion clad defect mechanism	0.221	5	0.0007	94	25	2.00	316	Trail Cable	835	17.5	50	Examination completed	
E1J-B2	Test thermal expansion clad defect mechanism	0.221	5	0.0007	92	25	2.00	316	Trail Cable	860	19.0	300	Examination completed	
B9C (2 pins)	Swelling behavior of defected fuel pins in flowing sodium.	0.216	4.25	0.004	89.6	25	1.97	316 20% CW	Special V-raft	1015	20.0	~7300	Test eliminated	
		0.216	4.25	0.004	89.6	25	1.97	316 Annealed	GETR	1030	20.0	~7300	Test eliminated	
B9D (2 pins)	Two defected fuel pins. Fuel swelling in clean sodium (<5 ppm Oxygen)	0.215	4.25	0.005	89.5	25	1.97	316 20% CW	Special V-raft GETR	1100 1060	15.0	~5500	Fabrication hold	

GEAP-10028-37

* Large gap required to accommodate sampling device

Table 2-2

TASK C — CURRENT EXPERIMENTAL TEST SERIES

Capsule	Test Objective	Design Parameters										TREAT							Destructive Exam.
		Diameter (inch)	Fuel Length (inch)	Fuel Density (% TD)		Fuel Composition				Cladding Material	Fabrication	Pre Irradiated		Transient Irradiation		Nondestructive Exam†			
				Pellet	Smeared	%UO ₂	%PuO ₂	%U 235	O/M			Yes	No	Calibration	Test	Before Trans.	After Trans.		
C4A	Determine the transient failure threshold for zero-burnup, mixed-oxide fuel specimens as a function of fuel column axial restraint, fuel density, and fuel form (pellet vs powder)	0.2159	13.46	83.2	80.5	72	28	92.7	1.974	316SS	C	C*		P	P	C	P	P	
C4B																			
C4C																			
C4D																			
C4I																			
C4J																			
Final report has been issued -- GEAP 13562																			
C4E	Axial restraint designed to simulate the restraint of C4A after steady-state irradiation. specific test goals to be determined after nondestructive examination of pin following removal from EBR-II	0.2159	13.46	83.2	80.5	72	28	92.7	1.974	316SS	C	C*		P	P	C	P	P	
C4F	Identical to C4E (transient magnitude will be varied)	0.2160	13.51	84	80.5	72	28	92.8	1.975	316SS	C	C*		P	P	C	P	P	

Table 2-2 (Continued)

		Design Parameters										TREAT						Destruc- tive Exam.
		Diameter (inch)	Fuel Length (inch)	Fuel Density (% TD)		Fuel Composition				Cladding Material	Fabri- cation	Pre Irra- diated		Transient Irradiation		Nondestructive Exam†		
Capsule	Test Objective			Pellet	Smeared	%UO ₂	%PuO ₂	%U 235	O/M			Yes	No	Calib- ration	Test	Before Trans	After Trans	
C4G	Axial restraint similar to C4A. This test (and C4H) will be compared to C4A and B to determine the effect of burnup on failure threshold.	0.2154	13.50	94.4	90.5	72	28	89.3	1.973	316SS	C	C*		P	P	C	P	P
C4H	Identical to C4G (transient magnitude will be varied).	0.2152	13.45	94.4	90.4	72	28	89.3	1.976	316SS	C	C*		P	P	C	P	P
C4K	This test (and C4L) will be compared to C4I and J to determine effect of burnup on failure threshold of powder fuel.	0.2205	13.50	powder	84.1	72	28	93.0	1.972	316SS	C	C*		P	P	C	P	P
C4L	Identical to C4K (transient magnitude will be varied).	0.2206	13.47	powder	84.2	72	28	93.0	1.972	316SS	C	C*		P	P	C	P	P
C4M	Determination of failure threshold for low power (6-10 kW/ft), high burnup fuel.	0.215/ 0.217	13.5	84/94	80/90	70/80	30/20	~93	1.97/ 1.98	316SS	††	X		P	P	P	P	P
C4X	Checkout of the redesigned C4 TREAT capsule (remote assembly techniques and TREAT characteristics) intended for the transient irradiation of preirradiated specimens C4E, H and K, M.	0.2186	13.48	96.2	91.0	100	0	92.8	2.00	316SS	C		X	C	C	C	C	P

Table 2-2 (Continued)

Design Parameters												TREAT							Destructive Exam
Capsule	Test Objective	Diameter (inch)	Fuel Length (inch)	Fuel Density (% TD)		Fuel Composition				Cladding Material	Fabrication	Pre-Irradiated		Transient Irradiation	Nondestructive Exam†				
				Pellet	Smeared	%UO ₂	%PuO ₂	%U-235	O/M			Yes	No	Calibration	Test	Before Trans.	After Trans.		
C5A	Study mobility of transient melted fuel; investigate potential for fuel relocation under prototypical conditions of length, restraint, and fission gas.																		
C5B																			
Final report has been issued -- GEAP-13543																			
C6A, 1	Test to evaluate transient performance of defected or sodium bonded fuel, determine relative performance limits and failure mechanisms of pellet and powder fuel under transient irradiation conditions. Sodium logged powder fuel is to maximize fuel-sodium heat transfer	0.212	24	86	80	100	0	10	2.000	316SS	C		X	C	C	C		C	
-2		0.2203	24	powder	80	100	0	10	2.000	316SS									
-3		0.212	24	86	80	100	0	10	2.000	316SS									
C6B, 1	Identical to C6A (transient magnitude will be varied).	0.212	24	86	80	100	0	10	2.000	316SS	C		X	C	C	C		C	
-2		0.2203	24	powder	80	100	0	10	2.000	316SS									
-3		0.212	24	86	80	100	0	10	2.000	316SS									
P	Planned																		
I	Initiated																		
NC	Nearly completed																		
C	Completed																		
				* EBR-II Fast flux, burnup goal ≈ 50,000 MWd/Te															
				** GETR thermal flux, burnup goal ≈ 20,000 MWd/Te															
				† Consists of X-rays, neutron radiographs, deencapsulation, cladding, diametral measurements, gamma transmission scan															
				†† Actual fuel pin has yet to be chosen.															

2.3 TASK C-2 – SAFETY EXPERIMENTATION (LOSS OF FLOW)

Specifications and drawings for the Mockup 1B heaters have been issued. The QA/QC procedures for capsule C10X have been revised to conform with the intent of F2-2T. Capsule C10X fabrication and welder qualification are continuing. Writing of the capsule C10A Design Basis Specification is in progress. Checkout of the THTE Program continues with limited production usage.

2.4 TASK E – FUEL MATERIALS PROPERTIES AND PERFORMANCE EVALUATION

A compressive creep test of a (U-20 wt % Pu) $O_{1.98}$ sample for a time period of 30 hours has been completed. This test was operated at 1200°C and indicated a measured creep rate of 1.8×10^{-5} in/in/hour. The result of this test agrees well with previously reported values extrapolated to these low values of temperature and stress.

Analysis was completed to determine the relative xenon concentrations in three fuel samples irradiated in a fast flux. These analyses indicated that the retention of fission gas is a function of the temperature during irradiation. Oxygen analyses on these specimens indicated no variation in oxygen content.

The current status of the Task E Irradiation Test Capsule program is given in Table 2-3.

2.5 TASK F – FAST FLUX TESTS AND SUPPORT

Examination of six F3B capsule tubes at ~78,000 MWd/Te (8.8 at. %) showed capsule diameter increases of 6 to 8 mils. Variations in capsule diameter occurred at the spacer wire locations. Maximum diameter increases of 2.2 to 8.0 mils were found on the F3B fuel pins. A Type 316 stainless steel clad pin containing low density powder fuel had the smallest diameter increase (2.2 mils).

Metallographic examination of six unencapsulated fuel pins from Group F3A (~50,000 MWd/Te, 5.6 at. %) revealed intergranular attack of both Type 304L and 316 stainless steel to a maximum depth of 8 to 9 mils at a calculated clad inside surface temperature of ~1120°F (604°C). No intergranular attack occurred at calculated clad temperatures below 1000°F (538°C). The clad outside surface was in excellent condition.

An interim examination on unencapsulated fuel pins from Groups F9A and F9C at ~50,000 MWd/Te (5.6 at. %) showed similar fuel pin length and diameter increases for Type 316 and 321 stainless steel cladding. Pins clad in Type 304 stainless steel had length and diameter increases ~3 times as large as those of the Type 316 and 321 stainless steel clad pins.

The current status of the Task F irradiation program is summarized in Tables 2.4 and 2.5.

2.6 TASK G-6 – CORE DESIGN ANALYSIS

The design of the grid spaced diagnostic assembly F9E for irradiation testing in EBR was completed. A reference optimized grid spaced fuel assembly for the FFTF driver was selected.

A final report on "Steady-State and Defected Fuel Irradiation Testing Needs" was completed and released. Review of the draft of the report on fuel failure propagation and sodium boiling test needs continued prior to its release.

2.7 TASK G-10 – KINETIC ANALYSIS – REACTOR SAFETY

Initial results were obtained using the new fuel expulsion model.

A coupled version of FREADM and MARS was successfully run.

A sensitivity analysis was completed using the BUBBLE coolant boiling and channel voiding calculation.

2.8 TASK G-12 – ANL SAFETY/CORE DESIGN GUIDANCE

Work was initiated toward the goal of providing design guidance for development programs at Argonne National Laboratory.

2.9 TASK L – CLADDING DEVELOPMENT

Immersion density measurements have been completed on cladding from Task F fuel rods F2V (Type 316), F2G (Type 347) and F2X (Type 316). Swelling values of 10% $\Delta V/V$ in Type 347 clad and 8.7% $\Delta V/V$ in Type 316 clad were measured (fluence of 0.7×10^{23} n/cm² E > 0.1 MeV-GE). The 10% volume change measurement is the highest reported for stainless steel irradiated in a reactor.

Table 2-3
TASK E—SUMMARY OF CURRENT MIXED OXIDE CAPSULE IRRADIATIONS

Capsule	Description	Design Parameters							Operating Conditions				Status
		Diameter (inch)	Length (inch)	Fuel		Composition		Cladding Material	Irradiation Facility	Cladding Surface Temp (°F)	Peak Power (kW/ft)	Burnup (MWd/Te)	
				Density	(% TD)	PuO ₂ (%)	O/M						
E1E	Relative smeared conductivity at high burnup irradiation to high burnup and rabbit test E1F.	0.218	1.9	94.7	94.5	20	2.00	347	MTR	875	20	85,000	Report in review
E1F		0.218	1.9	94.6	94.8	20	2.00		MTR	654/875	20/28	77,000	
E1J-1	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.94	316	GETR	1100	23	2,000	Examination complete
E1J-2	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.94	316	GETR	1100	23	2,000	Examination complete
E1J-3	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.94	316	GETR	1100	23	2,000	Examination complete
E1J-4	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.97	316	GETR	1100	23	2,000	Examination complete
E1J-5	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.97	316	GETR	1100	24	2,000	Examination complete
E1J-6	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	1.97	316	GETR	1100	23	2,000	Examination complete
E1J-7	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	2.00	316	GETR	1100	24	2,000	Examination complete
E1J-8	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	2.00	316	GETR	1100	23	2,000	Examination complete

Table 2-3 (Continued)

Capsule	Description	Design Parameters							Operating Conditions					Status
		Diameter (inch)	Length (inch)	Fuel		PuO ₂ (%)	O/M	Cladding Material	Irradiation Facility	Cladding Surface Temp (°F)	Peak Power (kW/ft)	Burnup (MWd/Te)		
				Density (% TD)										
				Pellet	Smeared									
E1J-9	Effect of restructuring on smeared thermal conductivity.	0.217	5.0	92.0	90.5	25	2.00	316	GETR	1100	23	2,000	Examination complete	
E2C-1	High burnup. Reference fuel irradiated at near reference thermal conditions.	0.218	5	84.5	82.2	25	2.00	347	GETR	1060	20	121,000	Report in review	
E2C-2		0.218	5	94.3	91.4	25	2.00		GETR	1060	20	113,000		
E2E	Fuel swelling. Four separate pins at three power levels	0.100	3	98.5	95.4	25	2.00	304	MTR	785	11.6	199,000	Report in publication	
E2F		0.100	3	96.9	95.1	25	2.00		MTR	655	9.4	172,000		
E2G		0.100	3	97.0	95.2	25	2.00		MTR	560	7.9	255,000		
E2H		0.100	3	96.6	94.8	25	2.00		MTR	785	11.6	330,000		
E2J-1	High burnup. Annular versus solid pellet.	0.218	5	90.4	89.5	25	1.98	316	GETR	1100	21	124,000	Report in review	
E1J-2		0.218	5	96.0	88.5	25	1.98			1100	21	125,000		
E2R	Center void formation rate at lower burnup.	0.216	10	94.0	91.0	25	1.98	316	GETR	1000	20	0	Awaiting irradiation	
E5A-1	Powder and pellet fuel comparison at low burnup.	0.218	4.9	86.8	84.3	25	2.00	347	GETR	1100	27	2,000	Report in review	
E5A-2		0.218	4.9	84.1	84.1	25	2.00		GETR	1100	27	2,000		
E5B-1	Powder and pellet fuel comparison at low burnup.	0.218	4.9	85.8	84.1	25	2.00	347	GETR	1400	20	138,000	Report in review	
E5B-2		0.218	4.9	84.1	84.1	25	2.00		GETR	1400	20	138,000		

Table 2-4

SUMMARY OF TASK F FAST FLUX TESTING PROGRAM IN EBR-II *

Group	Purpose and Major Parameters	Total Number of Pins In Group	Date In	Projected Date Out	Actual Date Out	Number of Pins		Position	Range of Average Pin Powers ⁽¹⁾ kW/ft	Target Burnup		Ave Calc Burnup ⁽²⁾ At % MWd/T _e		Peak Calc Fluence ⁽³⁾ (nvt X 10 ⁻²³) Total E > 1 MeV		Status
						In S/A	S/A			At %	MWd/T _e	At %	MWd/T _e			
F 0	Low power swelling rate of high density fuel at various burnup levels	5	07/16/65		08/15/68	1	XG02	7A1	8 71	3 91	35,000	3 88	34,702	0 322	0 2370	Post exam complete
			07/16/65		08/08/70	2	XG03	7D1	5 39 5 83	8 95	80 000	6 88	61,510	0 592	0 4327	Interim exam
			07/16/65		08/08/70	2	XG04	7B1	5 35 6 14	11 18	100 000	7 62	68,103	0 662	0 4876	Interim exam
			09/14/70	02/15/72	—	2	XG03A	8D2	5 58 6 19	8 95	80,000	7 26	64,852	0 627	0 4570	In reactor
F 1	Short time performance and proof test	6	09/15/60	01/06/73	—	2	XG04A	8A7	5 55 6 00	11 18	100,000	8 02	71 746	0 700	0 5146	In reactor
			05/06/65		05/23/65	6	XG01	4F2	12 17 14 31	0 22	2,000	0 21	1,904	0 017	0 0149	Reported in GEAP 5570
F 2	Medium power scoping irradiation Major para meters include smear density stoichiometry cladding coolant interactions and burnup	21	09/03/65		03/06/68	9	XG05	4C2	11 28 13 74	8 39	75,000	6 69	59,800	0 569	0 5011	Report in Review
			09/03/65		02/20/67	12	XG06	4E2	8 34 14 65	5 59	50,000	5 02	44,897	0 422	0 3613	Reported in GEAP 13549
			02/23/60		05/18/70	4	X050	4C2	10 50 12 58	11 19	100,000	11 75	105,058	1 034	0 8861	Post exam in progress
F 3A	Bare pin irradiation to evaluate fuel cladding and cladding coolant interaction	16	08/15/68		06/30/69	16	X040	5B2	12 59 14 32	5 62	50,000	2 88	25 601	0 236	0 2008	Interim exam
			10/04/69		05/18/70	16	X040A	5B2	12 25 13 91	5 62	50,000	5 17	45,978	0 430	0 3658	Post exam initiated
F 3B	Density and stoichiometry effects for encapsulated fuel pins	18	11/21/67		05/18/70	18	X027	4B3	11 20 12 49	13 49	120,000	8 86	78,819	0 754	0 6459	Interim exam
F-4	Low density fuel behavior at high heat	9	05/09/66		06/28/67	9	X011	2F1	13 57 14 30	5 64	50,000	3 64	32,255	0 298	0 2562	Post exam complete
			08/15/68		12/24/68	7	X039	3C2	13 12 13 55	9 03	80,000	4 85	42,964	0 400	0 3436	Interim exam
			01/10/70		08/08/70	7	X070	3E1	12 44 13 00	9 03	80,000	8 25	73,080	0 695	0 5973	Removed from reactor
F 5	Fuel performance at peak FCR cladding temperatures	19	05/28/69		08/08/70	19	X064	4F2	12 26 13 05	11 25	100,000	5 71	50,872	0 476	0 4067	Removed from reactor
F 6	Fuel cladding interactions	4	03/24/66		04/24/69	4	X010	7F3	8 45 9 17	5 60	50,000	5 71	51,014	0 480	0 3936	Post exam complete
F 7	Pre irradiated, axially restrained fuel prior to transient test Main variable is fuel density See Task C, Capsules C-4 series	6	12/23/67		12/23/67	2	X015	4A2	—	—	—	—	—	—	—	Completed
			01/23/70		05/18/70	4	X050	4C2	—	5 48	50,000	5 86	53,400	—	—	Completed

GEAP-10028-37

Table 2-4 (Continued)

Group	Purpose and Major Parameters	Total Number of Pins In Group	Date In	Projected Date Out	Actual Date Out	Number of Pins In S/A	S/A	Position	Range of Average Pin Powers ⁽¹⁾ kW/ft	Target Burnup At. %	MWd/T _e	Peak Calc. ⁽³⁾ Fluence (nvt X 10 ⁻²³)				Status
												Ave Calc. Burnup ⁽²⁾ At. %	MWd/T _e	Total E	>.1 MeV	
F-8A	Effect of density on fuel swelling rate.	16	01/13/67		08/02/69	7	X019	6D2	8 36-8 95	.63	50,000	4.97	44,161	0 412	0.3420	Post exam complete
			01/13/67		01/31/70	9	X020	6B5	8 20-8 91	11.26	100,000	6 15	54,615	0.524	0.4377	Interim exam
			05/24/70	04/06/72	—	9	X081	7F6	7 66 9 09	11.26	100,000	7.91	70,328	0.684	0.5661	In reactor
F-8B	Effect of void deployment on fuel cladding reaction.	19	07/25/68		08/24/70	19	X036	7E1	4.59-6 45	5 63	50,000	4.73	42,030	0 400	0.3002	Interim exam
F-9A	High power, high burnup, unencapsulated fuel pin irradiations.	37	02/20/69		05/18/70	37	X043	4D2	11 78-13 03	11.26	100,000	5.57	49,501	0.464	0.3974	Interim exam
			10/27/70	06/24/72	—	37	X043A	6D3	10 69-12 66	11 26	100,000	5.92	52,644	0.494	0.4234	In reactor
F-9B	Medium power, high burnup, unencapsulated fuel pin irradiations.	37	05/23/69		—	37	X062	7F3	8 00-10 58	11 26	100,000	5.57	49,558	0.464	0.3907	In reactor
F-9C	High power, high burnup, unencapsulated fuel pin irradiations.	37	04/03/69		07/16/70	37	X056	5C2	10 26 11.27	11.24	100,000	5.67	50,455	0.472	0.4022	Interim exam
			10/27/70	07/22/72	—	37	X056A	6B2	10.03-12 08	11.24	100,000	5.99	53,263	0.500	0.4251	In reactor
F-9D	Medium power, high burnup, unencapsulated fuel pin irradiations.	37	04/24/69	03/20/73	—	37	X058	7B6	7 19-9 41	11 25	100,000	5.42	48,205	0.456	0.3522	In reactor
F-9E	High power, high burnup, unencapsulated fuel pin irradiation	37	—	—	—	37	—	—								Design in progress.
F-10A	Cladding performance at peak cladding temperatures.	19	—	—	—	19	—	—								Fabrication in progress.
F-10B	Cladding performance at peak cladding temperatures.	19	—	—	—	19	—	—								Fabrication in progress.
F-10C	Fuel pin performance at peak cladding temperatures.	19	—	—	—	19	—	—								Fabrication in progress
F-11A	Cladding performance at peak FCR cladding temperatures.	37	—	—	—	37	—	—								Fabrication in progress

* All calculated power, burnup, and fluence numbers are based on the fission rates provided in the "Guide for Irradiation Experiments in EBR-II"

1. Values are the calculated axial average powers. Ratio of peak to average power is 1.125

2. Burnup values are axial average values for the pin in the subassembly with the highest fuel burnup regardless of position in subassembly.

All values are corrected for fuel depletion. Burnup values in MWd/T_e are based on a value of 192 MeV/fission and calculated from data supplied by EBR-II.

3. Fluence values reported are calculated for the peak axial flux for the pin in the subassembly located closest to the center of reactor core based on values supplied by EBR-II.

Table 2-5

SUMMARY OF TASK F THERMAL FLUX IRRADIATIONS

Capsule		Description	Diameter (inch)	Fuel Length (inch)	Design Parameters*				Operating Conditions**			Status
New No	Former No				Fuel		Composition		Cladding Surface Temperature (°F)	Peak Power (kW/ft)	Burnup (MWd/Te)	
					Pellet	Smeared	PuO ₂ (%)	O/M				
F12A	(E5F)	Linear fuel movement versus burnup	0 214	10 0	92 0	87 1	25	1 98	850	17	44,000	Report in process
F12C	(E5C-1)	Powder, pellet, and annular fuel comparison at high burnup	0 215	16 0	87 5	82 9	25	1 95	1160	19 5	137,000	Report in process
F12D	(E5D 1)	Powder pellet, and annular fuel comparison at high burnup	Powder	16 0	81 8	81 8	25	1 97	1160	19 5	141,000	
F12E	(E5E 1)	Powder, pellet, and annular fuel comparison at high burnup	0 215 (Annular)	16 0	95 0	83 3	25	1 96	1160	19 5	130,000	
F12P	(E2P)	Effect of radial restraint on fuel swelling (15 mil tubing)	0 219	2 0	92 0	91 0	25	1 98	1160	15	~78,000	Interim exam
F12Q	(E2Q)	Effect of radial restraint on	0 229	2 0	92 0	91 0	25	1 98	1160	15	~78,000	

* In all capsules, the cladding is Type 316 stainless steel

** Listing was conducted in the GETR

Analysis of profilometry and immersion density data from all of the Task F series F2 fuel rods suggest the following:

- a) Fuel-clad mechanical interaction is a function of initial smear density; the higher the smear density, the greater the strain caused by fuel-clad interaction.
- b) Stress appears to enhance clad swelling at about 500°C (932°F), although the effect is small.

Immersion density and profilometry measurements on Type 304 stainless steel capsule tubes from the F-2 series of high burnup fuel rods ($\sim 7.4 \times 10^{22}$ n/cm², $E > 0.1$ MeV-GE) were used to establish that the assumption of isotropic swelling is valid at volume changes up to 7% $\Delta V/V$.

Irradiated Type 304 stainless steel specimens creep tested at high stress levels show reduced strain rates compared to unirradiated specimens. Decreasing the stress level reduces this effect until the trend is reversed (i.e., the creep rate of irradiated material exceeds that of the unirradiated material).

Characterization of the first order of cold worked tubing (5G430G Tubing) was completed. The results show that this material was of high quality. Stress-rupture testing of purposely defected tubing of 20% cold worked Type 316H has shown that defects as deep as 10% of the wall do not degrade or otherwise alter the mechanical properties at 1300°F, using tests at relatively high strain rates, with failures occurring in less than 2000 hours.

The status of the current Task L irradiation program is summarized in Table 2-6.

2.10 TASK N – CORE PHYSICS ANALYSIS

Benchmark calculations, carried out as part of the Cross Section Evaluation Working Group activities, have been completed and will aid in the further development of the Evaluated Nuclear Data File /B.

A procedure has been specified for determining uncertainties in computed physics quantities of power reactors from integral measurements.

The topical report describing the fuel management code FUMBLE has been submitted to the AEC for review.

Participation in the activities of the *de facto* Committee on Computer Code Coordination has resulted in code development standards which will aid code exchange between LMFBR development organizations.

2.11 TASK P – FUEL ELEMENT DESIGN ANALYSIS

The BEHAVE-I fuel element performance code is near operating status. The code calculates growth in diameter along the length of a fuel pin due to the integrated effect of behavior during the first startup, steady-state operation, and power increases following steady power operation. The steady-state phenomena of clad swelling, loss of effective clad thickness, clad creep under gas pressure, and clad strain due to fuel swelling are included. Work on the AEC-RDT Fuel Modeling Round Robin is in progress.

3. TASK B – DEFECTED FUEL BEHAVIOR

Task Leader: P.E. Novak

Major Contributors:

F.L. Bamford
P.E. Bohaboy
J.M. Bridges
J.H. Cherb
W.L. Conant
R.J. Ernst

Table 2-6

SUMMARY OF TASK-L CAPSULES IN EBR-II

Group	Purpose & Major Parameters	Total Pins In Group	Number of Specimens		Date In	Projected ⁽¹⁾ Date Out	Row-S/A	Core Position	Reactor Exposure (MWD)	Target Fluence ⁽²⁾	S/A Average Fluences ⁽³⁾		Status
										(n/cm ² x 10 ²³) Total	(n/cm ² x 10 ²³) Total	0.1MeV	
L-2'	P.I. Mech. Prop. Eval. of Type-304,-316L,-321,-347, & Incoloy-800.	5	15	80	09/03/65	02/20/67 ⁽²⁾	4-XG06	4E2	9,317	0.4	0.33	0.29	Report complete
L-4	P.I. Mech. Prop. Eval. of Type-316.	2	10	20	03/29/66	11/14/66 ⁽²⁾	4-X009	4A2	5,355	0.2	0.19	0.16	Report complete
L-4'	P.I. Mech. Prop. Eval. of Type-304,-321,-347, & Incoloy-800	5	25	50	07/17/66	04/10/67 ⁽²⁾	2-X014	2D1	3,674	0.2	0.16	0.14	Report complete
L-10	P.I. Mech. Prop. Eval. of Type-304,-316,-321,-347, & Incoloy-800	10	70	60	01/13/67	09/ /68 ⁽²⁾	4-X016	4D3 & 4F3	7,894	0.2	0.28	0.24	Report complete
L-14	P.I. Mech. Prop. Eval. of Type-304,-316,-321,-347, & Incoloy-800	19	133	114	10/10/67	12/ /68 ⁽²⁾	4-X025	4E2	8,399	0.2	0.29	0.25	Post exam complete
L-21	P.I. Mech. Prop. Eval. of Type-321	1	3	16	09/03/65 08/15/68	03/06/68 ⁽²⁾ 12/24/68 ⁽²⁾	4-X605 3-X039	4C2 3C2	12,632 2,532	0.75	0.54	0.46	Post exam in progress
L-2	P.I. Mech. Prop. Eval. of Type-304,-316,-347, and Incoloy-800	4	12	64	09/03/65 02/23/69	03/06/68 ⁽²⁾ 05/18/70 ⁽²⁾	4-X605 4-X050	4C2 4C2	12,632 11,706	0.75	0.90	0.75	Post exam in progress
MT-3 ⁽⁴⁾	P.I. Mech. Prop. Eval. of Incoloy-800, Inconel-625 & Hastelloy-X	4	None	48	12/13/65	06/26/69 ⁽²⁾	4-XA08	4F2	19,280	1.0	0.64	0.55	Exam completed
L-6	P.I. Mech. Prop. Eval. of Type -304,-316,-347 & Incoloy-800	3	63	126	12/06/66 04/23/69 10/02/69	01/02/69 ⁽²⁾ 06/26/69 ⁽²⁾ 09/10/70 ⁽²⁾	2-X018 4-X018A 4-X018B	2B1 4E2 4E2	10,687 2,334 9,851	2.0	0.78	0.67	At FEF, EBR-II
L-15	P.I. Mech. Prop. Eval. of Type -304,-316,-321,-347 &	4	None	288	08/15/68 08/24/70	12/24/68 ⁽²⁾ 06/ /71	3-X039 4-X080	3C2 6E5	2,532 2,525	0.3	0.15	0.12	In reactor
MT-4 ⁽⁴⁾	P.I. Mech. Prop. Eval. of Incoloy-800, Inconel-625, & Hastelloy-X	1	None	48	12/13/65 08/24/70	06/26/69 ⁽²⁾ 1972	4-XA08 6-X080	4F2 6E5	19,280 2,525	2.0	0.70	0.60	In reactor

Table 2-6 (Continued)

Group	Purpose & Major Parameters	Total Pins In Group	Number of Specimens		Date In	Projected ⁽¹⁾		Core Position	Reactor Exposure (MWD)	Target Fluence ⁽²⁾ (n/cm ² x 10 ²³)	S/A Average Fluences ⁽³⁾ (n/cm ² x 10 ²³)		Status
			Tubular	Flat Tensile		Date Out	Row-S/A			Total	Total	0.1 MeV	
L-16A	Meas. γ -heating rates for L-16 Type Capsule design	19			—	—	4	4C2	—	0.01			Fabrication in progress
L-16B	Meas. Swelling in Type-316 & -304 Annealed and C.W.	19	76	None			4-X098	4C2	—	0.3			In reactor
L-16C	Meas. Temp. Dependence of Swelling in Clad Alloys	7		None	—	—	—	—	—				Design in progress
L-16D	Peencapsulation of previously irradiated specimens	3	36	None	—	—	—	—	—		0.90 ⁽⁵⁾	0.75 ⁽⁵⁾	Design in progress

1. Assuming ERR-II continues to operate at 62.5MW with 50% Load Factor.

2. Actual date out.

3. Fluence calculated as described in GEAP-10028-37, pages 68-69.

4. Capsules from previous AEC program under Contract AT(04-3)-189,PA-29.

5. Fluence prior to reencapsulation.

K.E. Gregoire
R.E. Harris
E.A. Meliaka
J.H. Morgan
R.E. Murata
P.E. Novak
G.E. Payne
D.E. Plumlee
W.A. Smith
G.L. Stimmell
H.J. Stock
G.L. Tunnell
J.D. Wilson

3.1 GENERAL

The technical and economic feasibility of fast reactors depends on a thorough knowledge of defected fuel behavior and its consequences to reactor design and safety. Defective fuel elements can be expected in any reactor, despite intensive quality control and detection systems. Moreover, to reach the full economic potential of the LMFBR, high plant availability must be achieved. It must, therefore, be experimentally demonstrated that an LMFBR can continue to operate safely with a substantial number of fuel pins with breached cladding, and what operating conditions are limiting.

The specific purpose of Task B is to: (1) determine experimentally whether fuel failure under normal or near normal LMFBR operating conditions will result in propagation of the failure to adjacent pins; (2) provide experimental and analytical data to permit selection of fuel design parameters and operating conditions which limit the consequence of fuel failure; (3) provide experimental data on failure kinetics to permit modeling and prediction of fuel failure behavior for the projected range of LMFBR operating conditions; and (4) identify the fuel and fission product species distribution in the reactor coolant and cover gas as a function of the failure mode.

3.2 DEFECTED FUEL TESTING

3.2.1 Forced Convection Capsule B9C

Capsule B9C was designed to investigate the performance of defected hypostoichiometric mixed-oxide fuel at typical LMFBR conditions in flowing sodium.

It has been demonstrated by researchers at ANL that at low oxygen levels in sodium (in the range of 5 ppm or less) an equilibrium is established between oxygen in the sodium and oxygen dissolved in niobium and vanadium. Measurement of the oxygen content in these metals, can, therefore, be thermodynamically related to an oxygen level in the sodium. This method has promise as a means of measuring low oxygen levels in sodium. During the sodium filling of Capsule B9C, a fraction (<10%) of the sodium flow exiting from the capsule was bypassed to a sample holder containing niobium and vanadium wires. These wires were removed from the sample holder and forwarded to ANL for oxygen analysis. The results of this analysis will be compared to oxygen analyses performed on sodium samples obtained from the sample holder after sodium filling the capsule. This comparison should provide information on the feasibility of using niobium and/or vanadium wires to measure the oxygen level in the sodium of a forced convection capsule at the end of its irradiation.

During final checkout of Capsule B9C in June 1970, a failure in the instrumentation system was detected¹ and disassembly and repair were required.³

Alternate courses of action for final disposition of Capsule B9C have been established and are being reviewed. Five basic alternatives were identified and transmitted to AEC-RDT for evaluation.

3.2.2 Forced Convection Capsule B9D

Capsule B9D will be used to investigate the performance of defected fuel in high temperature (1050°F) flowing sodium with failure occurring after several days of full power operation. It has the same basic design as Capsule B9C.

Engineering efforts during the quarter were directed at improving quality assurance and quality control procedures and completing the capsule redesign. Emphasis was placed on simplifying the capsule design. Major design changes included:

- (1) Eliminating all electrical heaters
- (2) Standardizing weld-prep designs
- (3) Re-routing the binary gas temperature control
- (4) Replacing the cold trap with an uranium metal getter to remove oxygen from the sodium coolant during irradiation.

A stress analysis of critical joints and components during steady-state and transient conditions was also completed.

Work was continued on the preparation of a formal quality assurance and quality control system for the design, fabrication, irradiation and examination of Capsule B9D. Preparation of 21 key procedures for transmittal to AEC-RDT was continued, with 15 completed to date.

A comprehensive weld qualification program was initiated. Each of the weld designs in the capsule has been qualified to the revised and updated welding procedures. A program was also initiated to develop a reliable brazing technique for use on Capsule B9D. Torch brazing and inert gas brazing processes were evaluated. A technique which employs an infrared light heat source and a flowing inert atmosphere was found to produce brazes of acceptable quality. Qualification of this brazing technique was initiated.

A bench-scale test program was initiated to optimize the operating procedure for the Failure Detection System (FDS)². For these tests, a mockup of the system will be fabricated (Figure 3-1). The test will provide data for the development of a gas sampling procedure which will minimize the probability of plugging of the FDS gas lines or filters with sodium condensate during irradiation testing.

A summary of the basic design parameters for Capsule B9D was previously described^{2,3}. These parameters were originally established to compliment the test parameters of Capsule B9C and anticipated FFTF operating conditions. However, due to the B9C difficulties and changes in the FFTF parameters, the following revised operating conditions for B9D are being considered:

Linear power	15 KW/ft
Sodium velocity	22.5 ft/sec
Sodium inlet temperature	1050°F
Oxygen level of sodium	<5 ppm

These conditions were chosen to correspond to the peak fuel surface temperature in the hot channel at overpower in FFTF.

Figure 3-1. Test Apparatus For The Determination Of The Failure Detection System Line Plugging Susceptibility

3.2.3 Forced Convection Capsule B9B

Work continued on the design of forced convection capsule B9B. This capsule contains a single fuel pin, which will be defected after an exposure of approximately 25,000 MWd/Te.

Because of the relatively long duration of the B9B irradiation compared to previous tests of forced convection capsules, the increased possibility of pump failure before completion of the test is a prime concern. Preliminary analysis indicates the desirability of incorporating a thermal "switch" in the fluted liner of the capsule to prevent overheating of the fuel pin in the event of failure of the capsule pump.

In the event of pump failure, the reactor will be programmed to initiate a scram within ~50 milliseconds. However, decay heat and energy from delayed neutron induced fission will combine to generate approximately 12 to 15% of the full power thermal output for a few seconds after the reactor scrams. Natural circulation of the sodium in the capsule cannot be guaranteed to dissipate this amount of heat. Conduction and radiation through the liner are also inadequate. A calculation performed with the THTE computer code indicates that the upper end of the fuel pin would experience a thermal transient of approximately 500°F, which would be unacceptable because of possible effects on the experiment. A more serious situation could develop if the loss-of-flow condition persisted more than a few (~ 5) minutes. Freeze-up of part of the loop sodium would occur in that time and natural circulation would be lost. Overheating of the test pin would be approximately 700 to 1000°F in this case.

One solution to this problem is to incorporate a thermal switch into the fluted liner of the capsule. A device that appears feasible for use as a thermal "switch" is a radial heat pipe. By careful selection of the working fluid, the heat pipe can be designed to be nonfunctional during normal capsule operation. In the event of a temperature transient, the heat pipe will begin a startup regime of operation, which is characterized by rapidly increasing vaporization of the working fluid and a resulting large increase in radial heat transfer.

The selection of a working fluid for the heat pipe must be based on consideration of the following parameters:

- (1) compatibility with heat pipe structural materials at operating temperatures
- (2) vapor pressure
- (3) surface tension
- (4) wetting action
- (5) neutron economy
- (6) heat of vaporization.

The liquid metals (lithium, sodium, and potassium) appear to be suitable candidate working fluids.

A bench-scale testing program was initiated to evaluate the performance of radial heat pipes for B9B Capsule. The tests are being designed to evaluate the effects of wick design, working fluid, and the presence or absence of a noncondensable gas in the liner.

3.2.4 Forced Convection Capsule B10A

This capsule will be used to investigate short-term fuel failure propagation between adjacent pins at typical LMFBR operating conditions.

Nuclear analysis for the design of the B10A flux filter was initiated. The analysis will also provide radial power distributions and linear power estimates for multipin irradiations using a flux filter.

3.3 FISSION PRODUCT DISTRIBUTION

3.3.1 Miniloop

This experiment investigated the leaching and deposition of selected fission products from high burnup mixed-oxide fuel (out-of-pile) in a small pumped sodium loop.

Analysis of the remaining leach samples from the loop was completed, and correlation of the data is presently being initiated. Results obtained previously were presented in the 35th Quarterly Report, GEAP-10028-35.

REFERENCES

1. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report, August-October 1970*, December 1970 (GEAP-10028-36).
2. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Fourth Quarterly Report, February-April 1970*, June 1970, (GEAP-10028-34).
3. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Fifth Quarterly Report, May-July 1970*, September 1970, (GEAP-10028-35).

4. TASK C-1—SAFETY EXPERIMENTATION (TRANSIENT OVERPOWER)

Task Leader: G.R. Thomas

Major Contributors:

T. Hikido
J.L. Scofield
R.C. Thompson
R.C. Weakly
G.L. Stimmell
R.S. Tsukida
S.M. Lukezic

4.1 GENERAL

The purpose of Task C-1 is to establish the behavior of fuel and cladding under transient casualty and accident situations. Both analytical techniques and an experimental program are used to determine the response of fuel to severe transients. These investigations include a study of the transient performance of fuel and cladding as a function of axial restraint, density, condition (defected, high burnup), and fuel form (powder and pelleted fuel). Tests are continuing to determine the potential for movement of molten fuel and to observe the effect of the prototypic range of fuel and blanket lengths on movement.

4.2 HIGH BURNUP FUEL EXPERIMENTS

This subtask investigates the transient overpower failure thresholds and subsequent fuel-sodium interactions for preirradiated fuel specimens of varying fuel smeared density (80 to 90%) and fuel form (pellet and powder). The specimens have been preirradiated in EBR-II to ~60,000 MWd/Te burnup.

4.2.1 Capsule Fabrication and Assembly

The Task C-1 remote sodium fill system was used successfully to fill an instrumented dummy capsule, and then the C4H capsule. Following verification of the proper sodium fill level (using neutrography), the C4H capsule was remotely inserted into its TREAT pressure vessel, leak checked, and shipped to TREAT. The completion of these remote operations represents the first time that a high-burnup (~60,000 MWd/Te), EBR-II irradiated fuel specimen has been reencapsulated for TREAT transient irradiation.

4.2.2 TREAT Irradiation

The C4X prototype capsule (enriched UO_2 at zero burnup) was subjected to a second test transient in TREAT. This capsule was designed to proof test and calibrate the capsule design and procedures for EBR-II pin testing in TREAT. The final

test purpose was twofold: (1) induce failure of the C4X fuel specimen; and (2) determine the capabilities of the capsule flowmeter and pressure transducer for monitoring the results of the post-failure fuel-sodium interaction — in particular, the resulting sodium void history.

Post-transient neutron radiographs indicate that the C4X fuel specimen did not fail, despite a combination of fuel and cladding conditions above the expected failure threshold. Calculations indicate that the resulting fuel melt fraction was probably $\geq 85\%$, with peak cladding and sodium temperatures of $\sim 2080^\circ\text{F}$ ($\sim 1140^\circ\text{C}$) and $\sim 1800^\circ\text{F}$ ($\sim 980^\circ\text{C}$), respectively.

Consistent with the calculated peak sodium temperatures of $\sim 1800^\circ\text{F}$ (probable sodium saturation temperature of $\sim 1700^\circ\text{F}$ or $\sim 930^\circ\text{C}$), the electromagnetic flowmeter and pressure transducer outputs were characteristic of bubble growth and collapse during sodium boiling. Preliminary hydraulic calculations indicate maximum sodium velocities through the flowmeter of -2.15 to $+1.6$ ft/sec, with one or possibly two bubbles growing and collapsing for ~ 50 discernible cycles over a period of ~ 0.8 second. A quasi-steady state existed for ~ 0.2 to 0.3 second during the interval of maximum flow oscillation. During this time, the bubble growth-collapse period was 30 to 40 milliseconds with a flow reversal from -2.15 ft/sec to $+1.6$ ft/sec in ~ 2 milliseconds. The maximum bubble size was ~ 0.06 cubic inches. Each of the rapid flow reversals was accompanied by a pressure pulse of ≤ 50 psi over the static pressure, as measured at the pressure transducer location.

Since the test successfully confirmed proper operation for both the flowmeter and the pressure transducer, it has been decided to disassemble the capsule in an effort to discover the mechanism that prevented failure of the C4X specimen during the extreme transient overpower conditions. A malfunction in the data retrieval system for the TREAT fast neutron hodoscope prevented data collection during this transient.

The C4H capsule was irradiated twice for calibration purposes. The transient parameters were virtually identical to the calibration transients performed on the C4X capsule. Preliminary results indicate that the C4H power factor is $\sim 15\%$ lower than the C4X power factor.

Discussions with TREAT indicate that a calibration error of $\sim +30\%$ was included in the reported outputs for TREAT power and integrated power during the transient irradiations performed on the C4X capsule. Applying this correction results in an increase in the effective C4X power factor from 0.925×10^{-4} to $\sim 1.22 \times 10^{-4}$ w/cc fuel/TREAT watt, a value much closer to the original physics prediction of 1.54×10^{-4} w/cc fuel/TREAT watt. Calculations are continuing in an effort to determine the cause of the remaining discrepancy in power factors.

4.3 COMPARATIVE TESTS

The primary purpose of these tests is to evaluate relative fuel pin performance as a function of such parameters as burnup, fuel length, and possible differences between UO_2 and $\text{UO}_2\text{-PUO}_2$ under identical transient overpower conditions. The initial tests in this series, evaluating the transient performance of defected or sodium-filled fuel have been completed.^{1,2}

However, the feasibility of further tests is contingent upon affirmative results of a design study to determine whether multipin capsules can accommodate specimens previously irradiated in EBR-II or GETR. Preliminary results indicated that tests may be conducted with fully enriched fuel specimens if thermal flux filters were incorporated to harden the flux spectrum.

4.4 MARK II LOOP TESTS

These tests will evaluate fuel performance under flowing sodium conditions and in multiple pin configurations.

Thermal-hydraulic calculations to evaluate Mark II loop design parameters were initiated. Initial analyses are scoping calculations to determine design criteria for proposed transient irradiations.

5. TASK C-2—SAFETY EXPERIMENTATION (LOSS OF FLOW)

Task Leader: H.C. Pfefferlen

Major Contributors:

D.G. Albertson
D.L. Brown
C.A. Calkins
W.L. Conant

M.D. Dermer
 D.E. Hafer
 E.O. Ormiston
 R.C. Thompson
 G.W. Tunnell

5.1 GENERAL

A major safety-related area which is of concern to both FFTF and the LMFBR programs is the potential for rapid reduction or loss of coolant flow to localized portions of the core. Such coolant starvation might be a result of local blockages, fuel distortion, debris, or failure of the pumps. The fuel response to such starvation, the propagation of malfunctions to neighboring pins, and the time characteristics of signals (such as temperature and flow) are a primary concern in the design of the fuel bundles and instrumentation system. Firm data in these areas must be available to provide reliable input to accident analyses for licensing purposes.

Various theoretical studies have been conducted on the effects of loss-of-flow, ranging from estimates of core voiding reactivity, to the local heat transfer and dynamics of single channel boiling. However, very little experimental data are available on the local effects of transient under-cooling and boiling in a confined channel. A need exists to perform experiments in-pile, with oxide fuel and flowing coolant, to verify models based on out-of-pile experiments, and to assess secondary events produced by re-entry of the sodium and its subsequent contact with hot or molten fuel. The purpose of this task is to conduct a program of such tests, both in-pile and out-of-pile, utilizing the Forced Convection Capsule and/or the Mark II Loop as the basic in-pile vehicle.

5.2 MOCKUP 1B

Mockup 1B (formerly Mockup 1A-2) will be used to investigate the initial stages of a loss-of-flow accident in an out-of-pile loop experiment utilizing the same facility as the Mockup 1A test. This investigation includes the flow transient as well as the initial stage of void formation. The test will be performed in a concentric loop¹ which utilizes three replaceable 24-inch-long electric heaters to simulate fuel rods.

Specifications and drawings for the Mockup 1B heaters have been issued. A cost estimate for reactivation of the loop, test setup and test operation has been completed. A schedule for the performance of the test will be drawn up as soon as the heater delivery date has been established.

5.3 CAPSULE C10X

Capsule C10X is an in-pile vehicle for the study of the latter stages of the loss-of-flow accident. This is a small nonflowing capsule in which boiling will be initiated and the subsequent interaction of sodium and fuel investigated. Results from this test will have intrinsic value as well as providing vital information for the design of later loss-of-flow tests in the FCC and/or Mark II loop.

The quality control procedures for Capsule C10X have been reviewed in light of the quality assurance plan developed under Task B². This QA/QC effort has disclosed some deficiencies in the original procedures. As a result, the following steps will be taken:

- (1) All joints and parts are to be classified as to service and consequence of failure. This classification will serve as a guide in the selection and tests of these components.
- (2) Welds will receive the same attention as recommended under the Task B procedures. This includes welder qualification as well as pre- and post-weld test specimens of critical joints.

Classification of all joints has been completed. Engineering Change Notices have been written to incorporate the necessary weld quality control procedures into the capsule fabrication plan. All engineering documents have been updated to reflect the required changes.

Fabrication is continuing on Capsule C10X under the guidance of the revised quality control plan. Welder qualifications as well as pre- and post-test welds of critical joints are in progress.

This classification and qualification procedure has resulted in a significant schedule slippage but is responsive to the intent of RDT Standard F2-2T. A revised schedule estimates capsule fabrication completion in February 1971.

5.4 CAPSULE C10A

Capsule C10A is the first in a series of in-pile loss-of-flow tests utilizing the Forced Convection Capsule. The purpose of this series of tests is to investigate the complete loss-of-flow accident from the initial flow reduction, through voiding and into the area of secondary events from sodium-molten fuel interactions. In these tests every effort will be made to include the influence of fuel, blanket, and plenum as well as flow restrictions and boundary conditions.

An outline has been written for a Design Basis Specification to define the requirements for the design, operation, and examination of all future irradiation capsules. This new specification is much more detailed than the Product Specification currently in use. Rewriting of the C10A Product Specification to conform with the requirements of the new Design Basis Specification format has been initiated.

Checkout of the THTE program continues with limited production usage. The THTE program is an extended version of the THTD program with added capabilities for computation of fluid flow and pressure drop as well as multichannel transient and steady-state heat transfer. These capabilities are necessary for a rigorous analysis of loss-of-flow experiments.

REFERENCES

1. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Third Quarterly Report*, November 1969-January 1970 (GEAP-10028-33).
2. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report*, August-October 1970 (GEAP-10028-36).

6. TASK E -- FUEL MATERIALS PROPERTIES AND PERFORMANCE EVALUATION

Task Leader: B.F. Rubin

Major Contributors:

E.A. Aitken
 P.E. Bohaboy
 D.A. Cantley
 S. Cifalo
 W.L. Conant
 R.N. Duncan
 S.K. Evans
 J. Haskins
 C.L. Hilf
 T.E. Lannin
 J.E. Lewis
 T.E. Ludlow
 G.F. Melde
 C.R. Mijares
 P.E. Ray
 H.S. Rosenbaum
 R.E. Smith
 R. Wolf

6.1 GENERAL

The purpose of Task E is to establish the physical, mechanical, and thermal properties of ceramic fuels and fuel elements. These properties are obtained by in- and ex-reactor testing and are then utilized to model or predict the behavior of fuel elements under steady-state or failure conditions. The reactions of fuel and cladding with fission products and sodium are being investigated with an electron probe microanalyzer, x-ray diffractometer and by simulated out-of-pile testing. Methods of limiting these reactions are being explored. The migration of impurities, fission products, and fuel cations are being studied in irradiated samples.

6.2 MATERIAL PROPERTIES STUDIES

6.2.1 Mechanical Properties

A long-term, low temperature creep test of a mixed-oxide sample has been completed. The data agree well with previously reported numbers for creep rates extrapolated to these low values of temperature and stress. Specific parameters of the test are as follows:

Measured creep rate	1.8×10^{-5} in/in/hour
Stress	1200 psi
Temperature	1200°C
Density	93.8%
Grain Size	3.4 - 4.0 μm (estimated)
Composition	(U-20 wt % Pu)O _{1.98} prepared from coprecipitated powders
Duration	30 days

The test results are being analyzed for presentation in a topical report.

6.3 CENTER TEMPERATURE LIMITS AND FUEL BEHAVIOR

6.3.1 Capsule E2R (Rate of Center Hole Formation at Startup)

A neutron radiograph has been taken of the test pin and the neutrographic standard to calibrate this technique for measuring the center void during interim examinations. Image enhancement of the neutron radiograph is being done to improve resolution so that more accurate dimensional measurements may be obtained. The test pin is scheduled for irradiation in GETR during the next reporting period.

6.4 FUEL-FISSION PRODUCT-CLADDING REACTIONS

6.4.1 Fueled, Out-of-Pile Thermal Gradient Testing

Previous progress reports^{1,2} described this program that is intended to investigate volatile fission product migration and the combination and reaction of fission products with cladding over the temperature range of 500 to 1200°C.

The most recent test series contained six Type 316 stainless steel clad pins loaded with (U-25 wt % Pu)O_{2.00} or (U-25 wt % Pu)O_{1.97} and radioactive cesium. The cesium was added as Cs₂O or in combination with iodine or tellurium as noted in Table 6-1. Results of gamma activity counting of pins 1 through 4 were reported earlier². In pins 2 and 4, cesium and tellurium migrated down the thermal gradient depositing at the same relative positions, which corresponded to temperatures between 800 and 900°C. In pins 1 and 3, cesium and iodine concentrated primarily at the cool end (500°C). The stoichiometric sample (Pin 3) indicated less movement of the cesium and iodine down the thermal gradient.

Pin 1, containing hypostoichiometric fuel in which cesium and iodine concentrated at the cold end, was subsequently heated uniformly to 200°C. The iodine (B.P. = 183°C), previously concentrated at the cold end, was observed to vaporize and redistribute itself throughout the tube while the cesium (B.P. = 670°C) remained at the original cold end. These results suggest that cesium and iodine are capable of independent transport under these conditions.

This observation is similar to that of Castleman and Tang³, who noted that iodine released from irradiated uranium heated to 1250°C was not in chemical combination with cesium or any other fission product. Their experiment, however, was carried out in a quartz tube, which could have affected the equilibrium dissociation temperature of a CsI compound.

Table 6-1
TEST PARAMETERS OF THERMAL GRADIENT EXPERIMENTS

Pin	Fuel*	Primary Additive**		Secondary Additive**	
		Species	Amount	Species	Amount
1	(U-25 wt % Pu) 0 _{1.97}	Cs ₂ O	50 mg	I as PdI ₂	10 mg
2	(U-25 wt % Pu) 0 _{1.97}	Cs ₂ O	50 mg	Te	40 mg
3	(U-25 wt % Pu) 0 _{2.00}	Cs ₂ O	50 mg	I as PdI ₂	10 mg
4	(U-25 wt % Pu) 0 _{2.00}	Cs ₂ O	50 mg	Te	44 mg
5	(U-25 wt % Pu) 0 _{2.00}	Cs ₂ O	100 mg	—	—
6	(U-25 wt % Pu) 0 _{2.00}	Cs ₂ O	200 mg	—	—

*Fuel pins were heat treated in a thermal gradient, 500 to 1245°C for 100 hours.

**Additives are inserted at the hot end of the pin.

A yellow compound was found deposited at pellet interfaces in the cool regions of pin 5. X-ray diffraction patterns of this deposit were found to correspond to values reported for Cs₂UO₄ and Cs₂U₂O₇ by Soviet scientists⁴. The sample will be analyzed to determine the presence of plutonium, which was not included in the Soviet study.

6.5 ELECTRON MICROPROBE EXAMINATION OF IRRADIATED SPECIMENS

6.5.1 Microprobe Examination of Specimens From Pins F2C and FOK

Microprobe examination of irradiated fuel and clad specimens is being done to establish the nature and extent of clad attack and the identification and distribution of fission products and other elements.

The initial results of the examination of Incoloy 800-clad F2C (peak burnup — 6.3 at. %) were reported last quarter². Subsequent examinations indicated that cesium, tellurium, and molybdenum were present within a crack that initiated from the clad inside diameter. Two specimens from this pin and one from pin FOK were analyzed on the microprobe to establish the radial xenon and oxygen intensities and the Pu/(U+Pu) concentrations. Figure 6-1 shows these results along with the microstructure of each sample. Sample pin FOK, which operated at the lower temperature, showed the greatest xenon retention. The plotted xenon intensity values are averages of three counts at each location. The readings were reproducible and did not decrease during the application of the electron beam. The dispersive spectrometers used in this study were calibrated against a sodium xenate standard. This compound, however, was unstable in the electron beam and did not provide sufficient information to establish absolute values for the xenon concentration.

The oxygen (O-Kα) values are in counts per second and show little variation in intensity across the radial traverses shown in Figures 6-2, 6-3, and 6-4.

Virtually no radial variation in plutonium concentration was detected in pin FOK, which operated at the lowest temperature. However, the variation across the two F2C specimens was significant, with F2C-11B showing the maximum value. This sample operated at a lower temperature than F2C-8A. The extensive Pu migration observed in the F2C samples is much greater than that previously determined in sample F2H¹, which operated at comparable power and burnup. It is possible that the higher oxygen activity in F2C (F2H had an initial oxygen:metal ratio of 1.98) was responsible for the increased plutonium migration. The radial oxygen and plutonium intensities and corresponding microstructure are shown in Figures 6-2, 6-3, and 6-4.

F2C-8A

F2C-11B

50X

F0K-H2

Figure 6-1. Microprobe Analysis Of Xenon In Irradiated Mixed-Oxide Fuel Pins F2C And F0K

50X

Figure 6-2. Radial Concentrations Of Pu/(Pu+U), Oxygen And Corresponding Microstructure In Specimen F2C-8A

50X

Figure 6-3. Radial Concentrations Of $Pu/(Pu+U)$, Oxygen And Corresponding Microstructure In Specimen F2C-11B (Reduced 90% for reproduction purposes)

GEAP-10028-37

50X

GEAP-10028-37

Figure 6-4. Radial Concentrations of $Pu/(Pu+U)$, Oxygen And Corresponding Microstructure In Specimen FOK-H2 (Reduced 90% for reproduction purposes)

6.5.2 Microprobe Examination of Specimen from Pin F2H

Post-irradiation examination of pin F2H (~6.7 at. % peak burnup) indicated several large cracks from the inside part way through the wall of the cladding. Microprobe examination of this specimen indicated a phase within the fuel-clad gap which contained palladium, tellurium, cesium, silicon, and chlorine. Molybdenum and iodine were not detected. The presence of the chlorine in this phase has been tentatively attributed to residue from the etchant.* (Specific care had been previously taken to grind away the etched zone.) However, chlorine has been reported by Yates and Bramman⁵ in an electron microprobe examination of an unetched fission product inclusion within a mixed oxide specimen.

The elemental distribution within the crack and its vicinity is shown in Figures 6-5 and 6-6. Figure 6-5 shows a 500X specimen current image of the crack along with the x-ray images of cesium, tellurium and chlorine. Figure 6-6 is an approximately 1300X view of the crack tip, which includes a specimen current image (the bright dots are bubbles in the carbon coating) and x-ray images of cesium, tellurium, and palladium. This analysis indicates that palladium concentrated at the base of the crack, while cesium and tellurium were more uniformly distributed over its length. The specimen current image indicates the crack is following a boundary, in that it disappears and then reappears as the boundary leaves the plane of the polished surface.

Figure 6-7 shows x-ray images of silicon, iron, chromium, and nickel where the cladding elements are absent from the crack and silicon is concentrated at the cladding interface.

6.5.3 Microprobe Examination of a Specimen From Pin F2G

A cross section from fuel pin F2G (10.8 at. % peak burnup) which displayed a multiphase structure adjacent to the center void was examined. This region, shown in Figures 6-8, 6-9, 6-10, and 6-11, was investigated for all elements in the Periodic Table between oxygen and plutonium. The band adjacent to the fuel indicated a matrix rich in barium, zirconium, and strontium with inclusions of UO_2 - PuO_2 fuel. The inner band (adjacent to the central void) has a fine dendritic structure in which barium, zirconium, strontium, aluminum, and silicon are prominent, with lesser amounts of molybdenum and niobium present. Within both dendritic structures, large inclusions containing barium, zirconium and strontium were observed. The composition of these inclusions was the same as the matrix of the band next to the fuel. Figure 6-8 is a photomicrograph of the area showing the three structures and the dendritic character of the inner band.

Figure 6-8 includes both negative specimen current image in which high atomic number elements appear light, and a plutonium and uranium x-ray pulse image. These studies indicate: (1) an absence of fuel in the inner band, and (2) a decrease in the fuel content of the outer band and fuel-rich inclusions.

Figure 6-9 shows the elemental distributions through the use of x-ray pulse images. Barium appears throughout both bands except in the area of the fuel inclusions. Zirconium is found in higher concentrations near the fuel—second phase interface than in the region adjacent to the center hold. Strontium and silicon were observed adjacent to the center void. Figure 6-10 shows a similar structure at the center and includes a specimen current image of the area along with the x-ray pulse images for uranium, silicon, and aluminum. Both aluminum and silicon were observed adjacent to the center void in all areas examined.

The inner band contained four times more barium, five times more strontium, and 100 times more silicon than the outer band. Aluminum was in the inner band but could not be semiquantitatively analyzed because an adequate standard was not available.

Very little silicon was found in the band adjacent to the fuel matrix. It consisted predominantly of barium, strontium and zirconium and 4 wt % Pu, with 11 wt % U. The $\text{Pu}/(\text{Pu}+\text{U})$ remained relatively constant, varying between 0.22 and 0.27.

The deposit within the fuel-cladding gap was friable and contained metallic appearing particles. This phase was found to consist of molybdenum, tellurium, and palladium, combined in a thin layer adjacent to the cladding. No migration of cladding alloying elements was observed. High concentrations of cesium and silicon were found in the diametral gap.

*The chlorine identification was positive, since no molybdenum was indicated. (The Mo-L γ line does interfere with the chlorine line when molybdenum is present. With both molybdenum and chlorine present in a sample, the relative ratios of the Mo-L α : Mo-L β : Mo-L γ lines would be analyzed to qualitatively determine the presence of chlorine.)

CLADDING
REACTION ZONE
FUEL

NEGATIVE SPECIMEN CURRENT IMAGE
HIGH-ATOMIC-NUMBER ELEMENTS BRIGHTER

Te-L α X-RAY PULSE IMAGE

Cs-L α X-RAY PULSE IMAGE

500X

Cl-K α X-RAY PULSE IMAGE

(DENSITY OF IMAGE IS RELATED TO CONCENTRATION)

Figure 6-5. Specimen Current And X-Ray Images Showing The Distribution Of Te, Cs And Cl In The Crack Observed In Section F2H-5

NEGATIVE SPECIMEN CURRENT
IMAGE HIGH ATOMIC-NUMBER
ELEMENTS BRIGHTER

Cs-L α X-RAY PULSE IMAGE

Te-L α X-RAY PULSE IMAGE

Pd-L α X-RAY PULSE IMAGE

~ 1300X

(DENSITY OF IMAGE IS RELATED TO CONCENTRATION)

Figure 6-6. Specimen Current And X-Ray Images Of Cs, Te And Pd In Cladding Crack of Section F2H-5

FUEL
REACTION ZONE
CLADDING

500X

Si-X α X-RAY PULSE IMAGE

Fe-K α X-RAY PULSE IMAGE
CLADDING ONLY

~1300X

Cr-K α X-RAY PULSE IMAGE

~1300X

Ni-K α X-RAY PULSE IMAGE

~1300X

(DENSITY OF IMAGE IS RELATED TO CONCENTRATION)

Figure 6-7. X-Ray Images Of Si, Fe, Cr And Ni In The Crack In Section F2H-5

PHOTOMICROGRAPH OF THE BANDED AREA EXAMINED

U-M α X-RAY PULSE IMAGE

NEGATIVE SPECIMEN CURRENT IMAGE OF HIGH ATOMIC NUMBER ELEMENTS, FUEL

Pu-M β X-RAY PULSE IMAGE

250X

(DENSITY OF THE IMAGE IS RELATED TO THE CONCENTRATION)

Figure 6-8. Optical, Specimen Current And X-Ray Images Showing The Distribution Of Fuel in The Center Void Region Of F2G

(DENSITY OF THE IMAGE IS RELATED TO THE CONCENTRATION)

Figure 6-9. X-Ray Images Showing The Distribution Of The Primary Species Of The Center Void Phase Region Of Specimen F2G

FUEL

OUTER BAND

INNER BAND

CENTER VOID

OUTER BAND

INNER BAND

CENTER VOID

NEGATIVE SPECIMEN CURRENT IMAGE
OF HIGH ATOMIC NUMBER ELEMENTS

-36-

OUTER BAND

INNER BAND

CENTER VOID

Al-K α X-RAY PULSE IMAGE

250X

OUTER BAND

INNER BAND

CENTER VOID

Si-K α X-RAY PULSE IMAGE

(DENSITY OF THE IMAGE IS RELATED TO THE CONCENTRATION)

Figure 6-10. Specimen Current And X-Ray Images Showing Distribution Of Fuel,
Silicon And Aluminum In The Banded Phase Of Specimen F2G

50X

Figure 6-11. Photomicrograph Of Specimen F2G-G And Corresponding Radial Distributions Of Pu/(Pu+U), Oxygen And Xenon

Figure 6-11 shows the microstructure of pin F2G along a radius of which the Pu:(U+Pu) ratio, and relative oxygen and xenon concentrations were determined. The Pu:(U+Pu) ratio decreased at mid-radius and then increased near the center void, similar to that observed in pin F2C (Figure 6-2). During irradiation, the equivalent stoichiometry of this pin (F2G) increased from 1.98 to a value in excess of 2.00. This change in stoichiometry increases the UO_3 (mobil species) partial pressure, which, in turn, may be related to this concentration shift. This same explanation was previously applied to F2C.

The relative intensity of oxygen (O-K α) line over the radius is also plotted in Figure 6-11. The net intensity decreased in the equiaxed grain region of the fuel, remained relatively constant in the columnar grain region, and dramatically increased in the central area containing the two bands previously discussed. Also plotted in Figure 6-11 is the relative intensity of the Xe-L α line which was measured as a function of radius.

Calculation of Oxygen Distribution

A computer program was written to calculate the O:Pu ratio for any region of an operating fuel pin. The calculated oxygen distributions had the same shape as those determined by electron microprobe analyses.² The calculation of the O:Pu ratio is based on the equation:

$$\frac{x_2}{x_1} = \exp \left\{ \frac{Q^*}{R} \left(\frac{1}{T_2} - \frac{1}{T_1} \right) \right\}$$

where:

- Q^* = heat of transport (-Kcal)
- x = oxygen value for the deviation from stoichiometry ($\text{MO}_{2\pm x}$)
- T_1, x_1 = absolute temperature and oxygen value at the fuel surface
- T_2, x_2 = temperature and oxygen value for the center of the volume increment
- R = gas constant.

The heat of transport value Q^* is taken to be -10Kcal/mole for start of life⁶, -8 Kcal/mole for a cesium environment representing appreciable burnup, and -5.7 Kcal/mole for a sodium environment⁷, typical of a defected pin. The temperature (T_2) is calculated by standard methods for the midpoint of each volume within a fuel pin including density changes. The O/M volume average is calculated considering radial heat and mass transport only. The program plots oxygen distribution at any axial position as a function of radius for different fuel surface O/M values, using O/Pu as the ordinate. Figure 6-12 presents the output for a pin of (U-20 wt. % Pu) O_{2-x} composition operating at 16.7 kW/ft at start of life. Appropriate O/M values for this composition are also noted.

REFERENCES

1. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Fourth Quarterly Report, February-April 1970, April 1970* (GEAP-10028-34).
2. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report, August-October 1970, December 1970* (GEAP-10028-36).
3. Castleman, A.W. and Tang, I.N., "Vaporization of Fission Products From Irradiated Uranium-II," *J. Inorg. Nucl. Chem.* 32, 1057 (1970).

Figure 6-12. Computed Oxygen Distribution In A Pin Operating At 16.7 kW/ft In EBR-II At Start Of Life. O/M Values For (U-20 wt % Pu) O_{2-x} Compositions Are In Parentheses.

4. Spitsyn, V.I., Ed., "Investigations in the Field of Uranium Chemistry," ANL-TRANS-33 (1964).
5. Yates, G. and Bramman, J.I., "The Identification of an Unknown Constituent in the Electron Probe Microanalysis of Inclusions in Irradiated Oxide Fuels," J. Nucl. Mat., 27, 88-93 (1968).
6. Evans, S.K., Aitken, E.A., Craig, C.N., "Effect of a Temperature Gradient on the Stoichiometry of Urania-Plutonia Fuel," J. Nucl. Mat. 30, 57-61 (1969).
7. Aitken, E.A., Evans, S.K., *A Thermodynamic Data Program Involving Plutonia and Urania at High Temperatures, Quarterly Report No. 12*, October 1970 (GEAP-12133).

7. TASK F – FAST FLUX TESTS AND SUPPORT

Task Leader: C.N. Craig

Major Contributors:

J.W. Bennett	P.M. Magee
G.C. Berg	W.H. McCarthy
B.E. Farwell	T.R. McIntyre
W.R. Faust	G.F. Melde
C.L. Hilf	K.J. Perry
G.R. Hull	C.C. Ripley
S.K. Jain	M.L. Thompson
T.A. Lauritzen	P.D. Tullbane
C.E. Leighty	

7.1 GENERAL

The purpose of Task F is to apply the more promising results of developments in basic fuel technology to the design, fabrication, and integral testing of fuel elements in fast fluxes. Important fuel performance characteristics, such as fission gas release, fuel cladding interactions, and fuel thermal performance, are determined under conditions simulating as closely as possible those expected in a fast ceramic reactor. Testing of fuel pins in a fast flux will, in principle, permit subsequent testing of fuel bundles under a fair approximation of prototypical conditions.

The test parameters for Task F are selected by a combination of design analyses which rely on basic properties data and on the results of pertinent experiments (such as those in Tasks E and L). More recently, model analysis under Task P has been applied quantitatively to interpretation of the results, and to aid in the selection of the values of parameters for further tests. The results of prior fast flux irradiation tests are interpreted as quantitatively as possible to guide the design of future tests. The selection of test parameters is also influenced and guided by the work under: (1) Task B on defected fuel testing; (2) Task C, which focuses on the preferred range of parameters for safety considerations of LMFBR designs; (3) Task G-6, which is concerned with subassembly design and performance; and (4) Task P, involving fuel element design and analysis. Demonstration of high fuel burnup (50,000 to 100,000 MWd/Te, 6.5 to 11.2 at. %) is required over a range of power levels (4 to 24 kW/ft). Fuel parameters that are under study in a fast flux environment include density, configuration, fabrication process history, stoichiometry, diametral gap, axial gap, and external restraint. Fast flux tests are performed with both encapsulated and unencapsulated pins.

Selected irradiation tests in thermal test reactors are being performed in support of the fast flux irradiations in EBR-II. These tests include high-risk tests, instrumented capsules, capsules operated at high-power with fuel temperatures at or above melting, and capsules designed to determine mixed-oxide fuel swelling by measuring fuel pin diameters without the complications of cladding swelling.

A summary of the fast flux irradiation tests in the EBR-II is given in Table 2-4. Calculated values for total fluence greater than 0.1 MeV, and fuel burnup values in MWd/Te and at. % (taking into account fuel depletion) are incorporated into the summary table. The fluence, power, and burnup values given in Table 2-4 were calculated using the fission rates provided in revision 3 of the "Experimenters' Guide for Irradiations in EBR-II" as a basis.

Table 2-5 lists the capsules irradiation tests which are being performed under Task F in thermal spectrum test reactors and the capsule tests which were transferred from Task E to Task F.

7.2 MEDIUM POWER LONG-TERM IRRADIATIONS

7.2.1 Group F2 (Medium Power Scoping Irradiations)

Group F2 consists of 19 encapsulated fuel pins irradiated in EBR-II. The purpose of these pins was to provide scoping information on the performance of mixed-oxide fuel pins irradiated to burnups up to ~100,000 MWd/Te (11.18 at. %). Twelve of the pins were examined at average burnups of ~60,000 MWd/Te (~6.7 at. %). Four pins were irradiated to average burnups of ~105,000 MWd/Te (~11.75 at. %). These last four pins have reached the highest burnup and neutron fluence ($\sim 1.0 \times 10^{23}$ nvt total) of any pins irradiated in the EBR-II under the FCR Program. Examination and reporting of the post-irradiation examination of these pins was reported in previous quarterly reports and GEAP-13549⁽¹⁾. Current results are reported below.

Metallography, burnup analyses, and fission gas analyses of the high burnup pins (F2G, F2V, and F2X) were completed. This work completes the post-irradiation examination of these pins with the exception of microprobe examination of selected samples and detailed examination of fuel cladding morphology.

Metallography

Work to confirm the presence of material in the fuel-clad gap of pins F2G, F2V, and F2X was completed. Transverse sections from the peak flux regions were carefully prepared to retain the material in the gap. Examination of the samples showed that the gap was filled with material, most likely fission products. A typical photograph of metallic appearing particles in the gap of a section from pin F2G is shown in Figure 7-1. Gamma spectroscopy of a sample of material observed to ooze from the fuel-clad gap on pin F2G during sectioning indicated the material was greater than 99% cesium. Microprobe examination of a sample from F2G was completed and is reported under Task E. No cladding attack was observed in this specimen. Other specimens will be examined.

Burnup

Analysis of the burnup of fuel from pins F2G, F2V, and F2X was completed. The calculated** and experiment values are listed in Table 7-1. As observed with previous analysis, the variation between the calculated and measured values is of the order of 15%.

Fission Gas Release

Fission gas release fractions based on calculated and experimental burnup values are given in Table 7-1.

7.3 HIGH POWER INTERMEDIATE BURNUP IRRADIATIONS

7.3.1 Group F3B (Density and Stoichiometry Effects)

Post-irradiation examination of six encapsulated fuel pins from Group F3B is in progress. Twelve capsules remain at EBR-II for additional irradiation exposure. Average fuel burnup on these pins is ~78,000 MWd/Te (8.8 at. %).

All pins in Group F3B contain hypostoichiometric fuel with a O:M range of 1.97 to 1.98. Other significant fuel and cladding parameters for the six pins being examined are listed in Table 7-2. Neutron radiographs showed that pin E1H-33 had failed.

*Nelson, R.C., et al, "Performance of Plutonium-Uranium Mixed-Oxide Fuel Pin Irradiated in a Fast Reactor (EBR-II) to 50,000 MWd/Te," GEAP-13549 (August 1969).

**Calculated burnups are based on the fission rates published in the "Guide for Irradiation Experiments in EBR-II Revision 3" with corrections made for core changes and depletion of fuel.

Figure 7-1. Fission Product Material In Fuel-Cladding Gap Of Fuel Pin F2G

Table 7-1
SUMMARY OF FISSION GAS RELEASE FOR PINS F2D, F2G, F2V, AND F2X

Fuel Pin	Calculated Burnup ⁽¹⁾ (at. %) Peak	Measured Burnup (at. %) Peak	% Fission Gas Release ⁽²⁾	
			Based on Calculated Burnup	Based on Measured Burnup
F2D	12.78	(3)	52	59
F2G	12.71	10.84	92	102
F2V	13.05	11.14	— ⁽⁴⁾	—
F2X	11.90	10.18	92	101

(1) Calculated burnups are based on the fission rates published in the "Guide for Irradiated Experiments in EBR-II, Revision 3," with correction made for core changes and depletion of fuel.

(2) Basis: 0.246 atoms Xe + Kr per fission

(3) No burnup determination was made on failed pin F2D. Calculations assume burnup on F2D was same as F2G.

(4) A large fraction of the F2V fission gas was lost when the plenum was accidentally breached during the examination.

Profile measurements indicated that maximum diameter increases on the capsule tubes were 6 to 8 mils. These results are listed in Table 7-2. The effect of the spiral spacer wires was apparent. The wires produced periodic variations of ~1.5 mils in capsule tube diameters. A typical profile is shown in Figure 7-2. Similar variations have been found in the diameter of the Group F2 capsules (GEAP-10028-36).

Fission gas punctures were made on the capsules. The capsule of E1H-29 contained fission gas; however, neutron radiographs did not indicate pin failure.

Pins E1H-21, -23, -26, and -30 were removed from their capsules. Rust colored deposits were found on the pins above the capsule sodium level.

Diameter measurements on the fuel pins of type 304 and 316 cladding indicate peak diameter changes of 2.2 to 8.0 mils. These results are listed in Table 7-2. Pin E1H-21, which contained low density powder fuel, exhibited the smallest diameter change.

7.3.2 Group F4 (Low Density Fuel Behavior at High Heat Ratings)

The seven Group F4 encapsulated fuel pins were received from the EBR-II site and placed in storage. Plans for the nondestructive and destructive examination of the capsules and fuel pins were completed.

7.4 ELEVATED CLADDING TEMPERATURE TESTS

7.4.1 Group F5 (Fuel Performance at Peak FCR Cladding Temperatures)

The five Group F5 fuel pins scheduled for post-irradiation examination were received from the EBR-II site and are scheduled for destructive examination after the Group F3B fuel pins are completed. The fourteen remaining Group F5 capsules are at the EBR-II awaiting reconstitution into new subassembly hardware for continued irradiation toward a goal burnup of 100,000 MWd/Te (11.25 at. %).

7.4.2 Group F10A, F10B, and F10C (Cladding Performance at Peak FCR Cladding Temperatures)

The Group F10A and F10B data package was completed and transmitted to ANL/EBR-II.

Table 7-2

FABRICATION PARAMETERS AND DIAMETER CHANGE DATA FOR GROUP F3B CAPSULES

Parameter	Fuel Rod	E1H-21	E1H-23	E1H-26	E1H-29	E1H-30	E1H-33
Cladding Type		316 SS Welded and Drawn	316 SS Welded and Drawn	316 SS Welded and Drawn	304 SS Seamless 13% Cold Work	304 SS Seamless 13% Cold Work + Garafalo H.T.***	304 SS Seamless Annealed
Fuel Type		Co-ppt.	Co-ppt.	Physically Mixed	Co-ppt.	Co-ppt.	Co-ppt.
Fuel Form		Powder	Annular Pellet	Solid Pellet	Solid Pellet	Solid Pellet	Solid Pellet
Fuel Density (% Theoretical)		82.3	96.4	89.9	95.2	96.5	95.7
Smeared Density (% Theoretical)		82.3	88.5	86.9	91.8	93.2	92.7
Cold Gap Range (mils)		--	2.9-4.9	2.4-4.5	3.6-4.4	3.1-4.6	2.6-4.0
Maximum Diameter Increase (mils)		2.2	3.3	6.5****	*	8	**
Maximum Capsule Diameter Increase (mils)		6	8	7.5	7	6.5	6.5

* Fission gas (Kr-85) was detected in the capsule. The pin has not yet been removed from its capsule.

** Pin E1H-33 failed.

*** Garafalo heat treatment is 24 hours at 900°F; 216 hours at 1300°F with air quench.

**** This high value is partially attributed to the small diametrial gap (2.4 mils) in one section of the fuel pin.

Figure 7-2. Group F3B Capsule Tube Profiles (E1H - 23)

Qualification welds and testing of the welds used to attach the flow reducers to the F10A and F10B capsules were completed. The welds were qualified by consecutively making five mockup assemblies which were tested to failure under tension. The minimum load required to break the welds was 260 pounds. The flow reducers were machined and attached to the twelve capsules in each of the Group F10A and F10B tests which will occupy the peripheral positions in the subassemblies. Pre- and post-weld samples were made when the flow reducers were attached to the capsules. These samples were also tested to failure and all exceeded a load of 240 pounds before failure. Final inspection of the capsules was completed.

An addendum to the Group F10C Approval-in-Principle was prepared and transmitted to AEC-RDT. The addendum was prepared as a result of a request for further information from AEC-RDT. Preliminary drawings and specifications for the Group F10C capsules and fuel pins were completed and a design review meeting was held. Comments and suggested changes in the drawings and specifications resulting from the design review meeting are being incorporated before issuing the final specifications and drawings.

7.5 UNENCAPSULATED FUEL PIN IRRADIATIONS

7.5.1 Group F3A* (Unencapsulated Fuel Pin Irradiation to Evaluate Fuel-Cladding and Cladding-Coolant Interactions)

Metallographic Examination

Metallographic examinations of pins F3B-1, F3B-3, F3B-5, F3B-7 and F3B-10 were completed. Four to six specimens were prepared from each fuel pin, including a specimen from the peak flux region and one from the region of highest clad temperature. The significant observation from this work is the presence of intergranular attack on the inside surface of the claddings in regions where the calculated cladding temperature exceeded 1000°F (538°C).

Figure 7-3 shows typical intergranular attack which occurred in 316 and 304L cladding inter-surface at calculated temperatures of ~1080°F (582°C). Penetrations of 5 to 6 mils are visible in the polished specimens. A metallic appearing material is visible in the 316 grain boundaries which were attacked. The etched specimen of 304L, however, did not exhibit any metal in the boundaries. A loss of grain boundary integrity is possibly indicated by a loss of grains in the polished specimen.

Examination of the intergranular attack data indicates no correlation of the attack to parameters such as fuel density, oxygen:metal or cladding material. Cladding temperature, rather than axial location, appears to be the controlling factor. Maximum grain boundary attack of 8 to 9 mils was observed in the region of highest calculated cladding temperature (~1120°F, 604°C) at the top end of the hottest pin.

The cladding outside surface, which was exposed to flowing sodium, was found in excellent condition on all pins.

Fission gas and fuel burnup analysis have not been completed on these pins.

7.5.2 Groups F9A, F9B, F9C, and F9D (Unencapsulated Fuel Pin Irradiations at High and Medium Powers to High Burnups)

An interim examination was performed on lead burnup subassemblies X043 (F9A) and X056 (F9C). Each subassembly contained 37 unencapsulated mixed-oxide fuel pins. All pins were acceptable for continued irradiation, and both subassemblies were reconstituted and inserted in EBR-II for run 47.

Length and diameter measurements were made on all pins in Group F9A and on 15 pins from Group F9C. Diameter measurements were made with a continuous recording profilometer which followed a spiral path parallel to the spacer wire.

The results of these measurements are as follows:

		316 Cladding	321 Cladding	304 Cladding
ΔD , %	Mean Value	0.47	0.49	0.84
	Range	0.24–0.80	0.32–0.64	0.48–1.16
	Average Deviation	0.06	0.10	0.27
ΔL , %	Mean Value	0.076	0.101	0.398
	Range	0–0.244	0.037–0.163	0.289–0.519
	Average Deviation	0.043	0.046	0.057

*The F3A subassembly contained fuel pins F3B through F3X.

A589-04-05

POLISHED

A589-12-13

ETCHED
316 CLADDING $\sim 1080^{\circ}\text{F}$ (582°C) CLADDING i.d. TEMPERATURE

A630-23-24

POLISHED

A630-34-35

ETCHED
304L CLADDING $\sim 1080^{\circ}\text{F}$ (582°C) CLADDING i.d. TEMPERATURE

250X

Figure 7-3. F3A Cladding Microstructures Showing Intergranular Penetration

Figure 7-4. Length Increase As A Function Of Fluence For Unencapsulated Group F9A And F9C Fuel Pins

Cladding temperature and neutron fluences were similar for the two groups of pins; however, peak linear power was 10 to 15% lower in Group F9C than in F9A (~15 kW/ft for F9A; ~13 kW/ft for F9C).

Fuel pin length changes are plotted in Figure 7-4. The effect of fluence is not evident over the narrow range involved. The data on length change is summarized as follows:

- (1) $\Delta L/L$ for the Type 316 stainless steel clad pins was similar for the two groups of pins and was $< 0.14\%$ except for a single data point at 0.24% .
- (2) $\Delta L/L$ for the Type 321 stainless steel clad pins was similar to Type 316 stainless steel pins.
- (3) $\Delta L/L$ for the Type 304 stainless steel clad pins was significantly greater than Type 316 or 321 stainless steel pins (0.29 to $0.52\% \Delta L/L$).

Length measurements were made with a device which does not correct for bowing of the pins; therefore, the values measured are equal to or less than the actual ΔL .

Maximum clad diameter increases are plotted in Figure 7-5. Over the range utilized, the data indicate no dependence of ΔD or ΔL on the following variables:

- (1) Linear Power
- (2) Clad nvt
- (3) Fuel average smeared density
- (4) Physically blended versus coprecipitated fuel
- (5) Corner or edge versus central position in the subassembly.

The following are conclusions drawn from analysis of the fuel pin diameter data:

- (1) Pins containing solid or annular pellets in Type 316 or 321 stainless steel cladding had similar ΔD . This result is consistent with the ΔL results and shows similar characteristics for 316 and 321 cladding.
- (2) The effect of vipack fuel is inconclusive. Although three vipack pins did exhibit low ΔD , the majority did not.
- (3) A majority of the Type 304 stainless steel clad pins showed diameter increases which were 2 to 3 times as great as for 316 or 321 stainless steel. This is consistent with the ΔL results. Unencapsulated fuel pins from Group F3A showed a similar result.

Some pins were contaminated with RTV-30* during handling operations in the air cell at EBR-II. The majority of this material was removed from the pins by wiping with alcohol soaked swabs. After consulting the manufacturer of RTV-30, the pins were soaked in warm toluene to remove residual film material. Smears taken after the toluene soak showed silicon levels lower than uncontaminated control surfaces. All pins were reinserted in EBR-II for run 47.

7.5.3 Group F9E (High Power, High Burnup, Unencapsulated Fuel Pin Irradiation Using Grid Spacers)

The F9E flow test subassembly mockup was completed and the flow orifice size has been determined by water flow testing.

The grapple for removing fuel rods from the assembly was received and tested. All end plugs for the removable rods have been dressed for a smooth fit in the fuel rod grapple.

7.5.4 Group F11A (Cladding Performance at Peak FCR Cladding Temperatures)

Preparation of the group F11A data package continued.

7.6 CAPSULES F12P AND F12Q (EFFECT OF RADIAL RESTRAINT ON FUEL SWELLING)

Pins F12P and F12Q attained fuel burnups of ~78,000 (8.8 at %) MWd/Te and were removed from GETR for an interim examination. This examination has not been completed; however, neutron radiographs indicated that both pins are intact.

*RTV-30 is a silicone rubber product used in the EBR-II air cell to make mold impressions. This compound was inadvertently smeared on the fuel pins from the manipulators.

Figure 7-5. Diameter Increase As A Function Of Smeared Density For Unencapsulated Group F9A And F9C Fuel Pins

7.7 EXPERIMENTAL TESTS IN EBR-II

The EBR-II was shut down on November 14, 1970, as a result of an unusual noise in the intermediate heat exchanger. The shutdown was extended for an indefinite period until the cause of the noise could be determined and the necessary repairs made. As a result, no additional exposure was obtained on tests in the reactor during December and January. The tests affected are:

Group F0 — (Low Power Swelling of High Density Fuel)

Group F8A — (Effect of Fuel Density on Fuel Swelling Rate)

Group F8B — (Effect of Void Deployment on Fuel-Cladding Interactions)

Groups F9A, F9B, F9C and F9D — (Unencapsulated Fuel Pin Irradiations at High and Medium Powers to High Burnups)

The burnups accumulated on these tests through November 14, 1970 are given in Table 2-4.

7.8 FUEL BURNUP

Burnup analyses were completed on seven samples from the high burnup Group F2 pins. A sample was taken from the peak flux regions of pins F2G, F2V and F2X. An additional four samples were taken from pin F2X. These are the highest fast flux burnup specimens analyzed under the FCR program. The high fuel burnup caused a significant change in the total U-236 and Pu-240 contents. This permitted calculation of accurate capture to fission ratios (α) for EBR-II. Accurate and independent burnup values were calculated using heavy element ratios based on these α values. Burnup was also calculated from neodymium to heavy element ratios. These results are tabulated in Table 7-3, along with burnup values predicted by published EBR-II fission rates. The heavy element and neodymium results agree quite well. Burnups calculated from EBR-II fission rates are 10 to 18% higher than the measured values.

Table 7-3

BURNUP VALUES FOR GROUP F2 PINS

Pin	Fuel Burnup (at. %)			Measured ^(e)		Location, inches from bottom of fuel
	Calculated ^(a)	Measured		Alpha Values		
		Nd ^(b) ± 3%	H.E. ^(c) ± 10%	α-235	α-239	
F2G ^(d)	12.71	10.84	10.84	.184	.202	6.22
F2V ^(d)	13.05	11.14	11.17	.185	.210	6.22
F2X-C	10.04	8.50	9.53	.211	.249	0.97
F2X-F	11.50	9.67	9.99	.192	.216	3.47
F2X-I ^(d)	11.90	10.18	10.39	.189	.208	6.22
F2X-L	11.3	9.83	9.83	.184	.199	9.72
F2X-O	9.81	8.03	9.14	.216	.286	12.22

(a) Burnup calculated from EBR-II published fission rates corrected for depletion

(b) Burnup from neodymium to heavy element ratios

(c) Burnup from heavy element ratios

(d) Peak flux region

(e) Alpha values calculated using information from the EBR-II Experimenters Guide are 0.083 for Pu-239 and 0.177 for U-235.

8. TASK G-6 – CORE DESIGN ANALYSES

Task Leader: P.R. Pluta

Major Contributors:

D.B. Atcheson
J.W. Bennett
W.R. Gee
S. Kaplan
L.M. McWethy
W.G. Meinhardt
J.R. Panches
C.C. Ripley
F.W. Sclacca
D.B. Sherer
H.J. Snyder
M.I. Temme

8.1 GENERAL

The purpose of this task is to contribute to the understanding of fuel performance, core design and thermal hydraulic problem areas; and to provide guidance for effective planning and coordination of experimental programs.

The current objective of this task is to develop a grid-spaced fuel assembly for the fast breeder reactor. The spacer concept offers potential advantage over the present wire wrap fuel assembly in:

- (1) Increased accommodation of differential structural swelling
- (2) Reduced core steel volume fraction
- (3) More uniform fuel pin circumferential temperature distribution
- (4) Lower bundle pressure drop.

The engineering analyses, out-of-pile mechanical and hydraulic testing, and supporting irradiation diagnostic test assemblies in EBR-II will result in an optimized grid-spaced driver fuel assembly and an LMFBR assembly for testing in the FFTF. This program, including tests of prototypic fuel assemblies in the FFTF, will establish the technical basis for the selection of the grid spacer support system as the preferred system for the LMFBR.

8.2 FFTF GRID-SPACED DRIVER FUEL ASSEMBLY

The purpose of this subtask is to assess the performance of various 217 pin grid spacers for irradiation in FFTF, to select a reference grid design, and to qualify an optimized grid spacer fuel assembly for irradiation test in FFTF.

A comparative analysis of basic grid concepts in FFTF was conducted to provide a basis for selection of the reference grid for further development. A beginning of life pin-to-channel edge spacing of 0.040 inch was used to reduce the hot channel factor and the temperature gradient across the edge rods.

The pitch-to-diameter ratio of an optimized grid bundle using the reference FFTF channels and 217 0.230 inch o.d. fuel pins is approximately 1.26. The following areas were considered in evaluating the relative merits of the various grids.

Pin Bowing

Deflection
Internal Load
Pin Stress
Pin Creep Strain

- Pin-to-Grid Swelling
 - Contact Load
 - Pin Bending Stress
 - Grid Bending Stress
 - Grid Creep Strain
- Pin-to-Channel Longitudinal Swelling
 - Grid Axial Stress
 - Grid Axial Creep Strain
- Grid-to-Channel Axial Swelling
 - Grid Axial Stress
 - Grid Axial Creep Strain
 - End Attachment Stress
- Pin Hot Spot
- Fabricability
 - Relative Cost
 - Tolerance Requirements
- Pressure Drop

8.3 F9E GRID SPACER IRRADIATION TEST

The purpose of this subtask is to design and analyze a grid spacer LMFBR diagnostic test assembly for irradiation in EBR-II (0.25 in. o.d. fuel pins at P/D = 1.28).

A draft of the report describing the F9E design basis was completed. Additional analysis to determine the wave beam spring constant was conducted using a finite difference solution to the plate equations. This analysis, which was conducted to determine the effect of the grid welds and the grid flexibility, showed that the wave beam grid flexibility may be less than has been predicted using a more restricted analytical model. As a result of this work and the FFTF grid studies, the proposed F9E grid spacer test design has been modified. A quality control plan for the fabrication of reactor grade grids has been drafted and is being followed during the F9E grid fabrication.

8.4 OUT-OF-PILE GRID SPACER MECHANICAL TESTS

The purpose of this subtask is to perform mechanical tests directed toward the overall evaluation of the grid spacer and its interaction with the fuel rods and the channel wall.

8.4.1 Thermal Stability Test

In order to determine the thermal stability of a wave beam and straight dimpled beam grid spacer, a thermal cycling test is being conducted. Four welded grids, two of which are inserted in channel sections, and five grid beams are being thermally cycled between 1100 and 1200°F and ambient for 50 cycles. Soaking times of 10 to 15 minutes at each temperature should be sufficient to attain uniform temperature throughout the specimens. The major objective of the test will be to assess the effect of thermal cycling on the shapes and dimensions of the grid beams and welded grids. A second test will involve several grid beams and welded grids which will be soaked at 1300°F for an extended period of time in a furnace.

8.4.2 Local Contact Load Test

Significant local bending stresses can occur at local points on the cladding surface due to concentrated loadings which result from the fuel rod spacer. These stresses occur under the point of contact due to local bending of the cladding and increase as the area of contact decreases.

Roark^{1,2} has investigated these stresses and determined that they may be computed from the general expression of the form

$$\sigma = K \frac{P}{t^2}$$

where

$$\begin{aligned} \sigma &= \text{maximum local bending stress} \\ K &= \text{stress constant} \\ P &= \text{local load (lb)} \\ t &= \text{cladding thickness (in.)} \end{aligned} \quad (1)$$

In this work, Roark determined that the constant, K , ranged from a maximum of approximately two down to nearly zero, depending on the geometry of the contacting bodies. This work, however, was conducted with very thin cylinders for which the diameter-to-thickness ratio varied from approximately 50 to 430, considerably thinner than the present reference fuel pin design with a diameter-to-thickness ratio of approximately 16. For this reason, a simple experimental program was initiated to determine the approximate value of the stress constant, K , for LMFBR geometry and to compare the results to those of Roark.

Experiments were conducted on a ten-times scale model of the cladding with local loads applied with ten-times scale models of simulated grid spacer contact surface (and wire wrap for comparison). Preliminary analysis had shown that the stress constant, K , could be directly computed if the load applied was varied as the square of the scaling factor.

Small (0.062 in.) resistant strain gages were applied to the inside surface of the test piece under the loading point and at discrete points away from the load application.

Incremental loads were applied, the strains measured, and stresses computed under the loaded point. With equation (1), the stress constant, K , was then determined.

Six different loading geometries were tested. The results are shown in Table 8-1. The strain measurements taken gave only the average stress over the gage lengths, and, since the variation in stress intensity is very rapid near the point of loading, a correction factor was necessary. This was accounted for by using the results of previous work^{1,2} in the local area of contact resulting in a maximum to average stress of 1.65. As indicated, the experimental values of the stress constants obtained from this work, although larger, are quite similar to that which would be computed using Roark's thin wall formulations also shown in Table 8-1. However, since uncertainty exists in the peak-to-average ratio, it is recommended that Roark's formulation be used for design purposes.

8.4.3 Mechanical Test Preparation

0.230 in. o.d. 0.015 in. wall 20% cold-worked tubing was ordered in support of mechanical and hydraulic testing planned for the FFTF driver fuel grid assemblies.

Sections of FFTF size channels are being fabricated for the purpose of conducting mechanical tests in support of the design of the FFTF grid assemblies.

Table 8-1

LOCAL CONTACT LOAD TEST RESULTS

Configuration of Local Load (Diameter-inches)	K (Test)	P/A^{**} Ratio	K (Corrected)	K (Roark)
0.5 Cylinder*	0.961	1.65	1.59	1.34
0.75 Cylinder*	0.928	1.65	1.53	1.31
1.0 Cylinder*	0.838	1.65	1.38	1.29
1.5 Cylinder*	0.923	1.65	1.52	1.25
0.375 Ball	0.905	1.65	1.49	1.49
0.875 Ball	1.014	1.65	1.68	1.39

Note: Typical wire wrap 0.5 - 0.75 inch diameter cylinder
 Typical grid spacer 1.0 - 1.50 inch diameter cylinder
 Typical dimple 0.40 - 1.50 inch diameter ball

* Applied 90° to tube axis.

** P/A = peak/average stress correction factor.

8.5 STEADY-STATE AND DEFECTED FUEL IRRADIATION TESTING NEEDS

The purpose of this subtask is to assess the information required from tests of defected fuel in the steady state and under irradiation in order to support the design and operation of LMFBR fuel assemblies. The data requirements are being assessed on the basis of their impact on core design, safety, and fuel cycle economics. This activity was completed in September 1970. A final report was issued during this quarter.

8.6 FUEL ELEMENT FAILURE, COOLANT BOILING AND OPERATING SAFETY LIMITS

The objective of this task is to make a comprehensive assessment of the information on the effects of fuel element failure, coolant boiling, and operating safety limits needed to design LMFBR fuel assemblies. The technical work on this task was completed during the last quarter. During this quarter, a draft report on the work accomplished was completed and final review is in progress.

REFERENCES

1. Roark, R.J., "The Strength and Stiffness of Cylindrical Shells Under Concentrated Loading," ASME Trans., Appl. Mechanics, Vol. 2, 4 (December 1935).
2. Roark, R.J., "Stresses and Deflections in Thin Shells and Curved Plates Due to Concentrated and Various Distributed Loading," Technical Note No. 806, National Advisory Committee of Aeronautics (1941).

9. TASK G-10 – KINETIC ANALYSIS

Task Leader: D.D. Freeman

Major Contributors:

D.L. Brown
R.C. Thompson
R.G. Stuart
R.E. Murata
K.G. Janberg
L.M. McWethy

9.1 GENERAL

The purpose of Task G-10 is to contribute to the understanding of fast reactor safety, to develop and use analytical tools to aid in the evaluation of the safety of fast reactors, and to provide guidance for effective planning and coordination of experimental programs. The results of these studies will guide further development of analytical methods and form a basis for establishing the design and safety criteria that define the range of reactor characteristics and test parameters upon which the experimental programs must focus.

9.2 MODEL DEVELOPMENT**9.2.1 Fuel Movement**

As a sequel to the determination of the fuel pin failure thresholds (reported in the 34th and 35th quarterly reports), the motion of the molten fuel gas mixture from the failed fuel pin is being examined to determine:

- (a) the time required to empty a fuel pin of the major portion of its molten fuel.
- (b) the effect of the expelled fuel gas mixture on the flowing sodium coolant
- (c) the construction of an adequate computer model for the analysis of TREAT transient overpower experiments performed under Task C 1, ANL, PNL and others.

The development to date has concentrated on examining the motion of the fuel and sodium under the following assumptions:

- (a) Complete failure of all the fuel pins in a single subassembly, thus allowing a single fuel pin to represent the failure.
- (b) The molten fuel and fission gas mixture flows in two-phase homogeneous flow from the fuel pin.
- (c) the fuel pin failure occurs at core mid-plane.
- (d) the area through which the molten fuel gas-mixture flows is the area of the molten fuel in the fuel pins and at the core mid-plane.

Figure 9-1 diagrammatically illustrates these assumptions.

Figure 9-1. Fuel Movement

As a first step in the computer program development, heat transfer between the fuel gas and sodium is ignored, and only momentum effects are considered (experimental evidence¹ suggests that the heat transfer between the fuel and sodium in the presence of gas is nonviolent). This restriction of no heat transfer between the fuel and sodium is currently being eliminated, and a typical result is discussed below. The following initial conditions were obtained from the transient overpower fuel failure code (TOFF).

Fuel-gas internal pressure at time of pin failure	=	4470 psia
Fuel temperature at failure	=	5040°F
Fuel flow area	=	$7.67 \times 10^{-5} \text{ ft}^2$
Quantity of gas in the fuel at failure (4470 psia)	=	$.0276 \text{ in.}^3$
Fraction of molten fuel in the pin	=	30%
Weight fraction of gas	=	.000367
Sodium flow area (unit cell)	=	$.000121 \text{ ft}^2$
Sodium temperature	=	1000°F
Initial sodium velocity	=	26 ft/sec
Sodium inlet pressure to core	=	108 psia
Sodium outlet pressure from core	=	38 psia
Initial sodium pressure at burst point	=	73 psia
Active fuel length below burst point	=	1.25 ft
Active fuel length above burst point	=	1.25 ft
Upper and lower axial blanket length	=	1.25 ft
Fission gas plenum length	=	1.25 ft
Fuel flow area	=	$.0000767 \text{ ft}^2$
Fuel burnup	=	100,000 MWd/Te

Figure 9-2 shows the fall in pressure within the fuel pins and the rise and subsequent fall in pressure of the fuel gas bubble. Initially, the high pressure in the fuel pins causes a rapid rate of flow out of the pin. At the same time, the expelled fuel gas mixture is trying to overcome the inertia of the flowing sodium. This results in a rapid pressure rise. After .00045 seconds, the pressure in the bubble equals the pressure in the pin, resulting in zero flow from the pin. The bubble is still trying to overcome the inertia of the sodium; that is, it is trying to accelerate the sodium above it and decelerate the sodium below. At .0004 seconds, the lower sodium slug is brought to rest (Figure 9-3). As the sodium flow is accelerated, the pressure in the fuel-gas bubble falls rapidly, and a rapid flow rate of fuel and gas is resumed from the rod. This again raises the pressure in the bubble, a second peak occurring at .001 seconds. Since the lower slug velocity has been reversed, it is easier for the bubble to expand. An orderly fall in bubble pressure and pin pressure results, with a continued fall in flow rate of fuel and gas from the pin. This reduction in flow rate results in a deceleration of the sodium slugs, and, as time proceeds, the velocities exponentially approach the initial steady-state conditions.

Figure 9-4 shows the displacement of the sodium slugs with time, the algebraic sum of these displacements is the size of the fuel gas-bubble. It can be seen that, during the early parts of the fuel gas expulsion, the bubble is quite small. Thus, the force that acts on bundle containment, being proportional to the bubble height, will be small, even though the pressure is large.

Figure 9-2. Plot Of Fuel Rod Pressure And Fuel Gas Bubble-Pressure Versus Time

Figure 9-3. Upper and Lower Sodium Slug Velocities

Figure 9-4. Displacement of Upper and Lower Sodium Slugs

Owing to the rapidity of the initial expulsion, it is felt that the amount of heat transfer between the fuel and sodium will be negligibly small; thus, the initial two pressure peaks resulting from inertia effects dominate pressures resulting from heat transfer. It is entirely possible that the thermal inertia of the sodium will be overcome and a longer lasting thermal pressure pulse will be created, and will act over a larger bubble and hence a larger area of the bundle containment. The force acting on the containment will then be larger and could cause a breach in the channel. This aspect of the problem is currently undergoing analysis and will be the subject of a future report.

Fission Gas Release

Fission gas release has been identified as a potential mechanism for ejection of coolant from an LMFBR subassembly². Analysis based on expansion of the gas assumed an initial flow stoppage at an assumed cladding failure point.

The potential for an instantaneous flow stoppage in a subassembly must take into consideration the sodium hammer effect. The pressure rise due to the instantaneous stoppage of flow is given in Streeter and Wylie³ as

$$\Delta P = \frac{\rho a V_o}{144g} \left(1 + \frac{V_o}{a} \right)$$

where

ΔP	=	pressure change (psi)
ρ	=	density of sodium (lb/ft ³)
a	=	wave speed (fps)
g	=	acceleration due to gravity (ft/sec ²)
V_o	=	initial fluid velocity (ft/sec)

for $a \gg V_o$

$$\Delta P = \frac{\rho a V_o}{144g}$$

Figure 9-5 shows the pressure change as a function of initial fluid velocity for sodium at 1000°F. Also, it can be seen that an instantaneous flow stoppage due to fission gas release (~600 psig design plenum pressure) is not possible unless the sodium velocity is $> \sim 7$ ft/sec. Based on this analysis, slug ejection of coolant with flow reversal due to fission gas release is feasible in loss-of-flow accidents. Work is continuing to develop a fission gas release model more representative of LMFBR conditions.

9.2.2 Subtask 10.2 – Coolant Boiling and Channel Voiding

Conditions for coolant boiling can be reached in hypothetical LMFBR accident analysis through loss of flow or by interaction of sodium with molten fuel. The dynamics of sodium boiling affect the probability for propagation of the accident in three ways:

- (1) Loss of coolant from an LMFBR may lead to substantial positive reactivity effects.
- (2) Collapse of the bubble may lead to significant energy release either through conversion of potential energy in the bubble to kinetic energy or through interaction with hot core components.
- (3) The probability of fuel cladding failure depends upon the cooling capability of the boiling sodium.

Figure 9-5 Pressure Rise Due To Instantaneous Stoppage Of Sodium Flow At 1000° F

The subroutine BUBBLE was written for the VOIDUM (primary loop hydraulics) routine of the FREADM code to treat sodium boiling in a reactor subassembly, including the effects of evaporative cooling and condensation in the coolant channel. The present version of the code neglects thermal gradients in the radial direction.

Principal uncertainties in the BUBBLE treatment of sodium boiling are (1) the initial superheat, (2) the initial thickness of the sodium film, which is assumed to remain on the fuel after boiling begins, and (3) coefficients affecting rates of evaporation and condensation which govern bubble growth and collapse.

The effects of varying superheat and initial film thickness on the growth of the first bubble were evaluated for a hypothetical flow coastdown in an LMFBR fuel bundle. Results are summarized in Figure 9 6 and 9 7. With loss of 80% of flow (Figure 9 6) as superheat increases, the time to initiate boiling increases, and the axial extent of the first bubble prior to its collapse also increases. With 10 mils of initial film thickness, no dryout of the cladding was observed. No dryout of the clad was observed (Figure 9 7) with initial film thicknesses of 1 mil and 5 mils with low superheat (21°F) and 80% flow reduction. However, with reduction of flow by 90% and superheat of 53°F, cladding dryout did occur with 5 mils of initial film thickness. The temperature of the cladding in this latter case did not reach failure level due to rewetting of the cladding by residual flow. Note also the indication of a second bubble forming when the first bubble begins to collapse. Work is continuing to improve the definition of these sensitivities and to include the effects of radial condensation in the model.

9.2.3 Subtask 10.3 – Reliability Modeling

The purpose of this subtask is to refine fault free analysis in areas previously identified as potentially influencing core design under Task G 6. Areas selected for more detailed analysis include violent boiling and damage propagation due to fuel debris flow blockage. Work in this area was initiated under Task G-10 in the last month of this quarter.

Figure 9-6. Void Pattern (First Bubble) For 3 Different Superheats

Figure 9-7. Void Pattern For 2 Different Superheats

9.2.4 Subtask 10.4 – Core and Reactivity Modeling

Coupling of the FREADM multichannel accident analysis calculation to the MARS two-dimensional (R-Z) hydrodynamics (weak explosion) calculation was completed. This coupling permits accident analysis for containment design with transient initial conditions based on a sequence of postulated mechanisms and criteria for accident propagation. A demonstration calculation was performed in which a ramp insertion of reactivity of \$15.00 per second was inserted into a 1000 MWe LMFBR. The MARS calculation was triggered when the average fuel temperature exceeded the melting temperature and the net reactivity was >0.9 dollars. Power and reactivity traces are shown in Figure 9-8. The MARS calculation is called for whenever the values of variables computed in FREADM satisfy one of the following criteria:

- (1) The elapsed time reaches an input value
- (2) the reactor period is positive and less than an input value
- (3) the reactivity exceeds an input value and the temperature of an axial section of fuel exceeds an input value
- (4) the temperature of an axial section of fuel exceeds an input value
- (5) the elapsed time from fuel failure in a bundle type reaches an input value.

Work was initiated to couple the FREADM code with the VENUS two-dimensional hydrodynamics calculation. This coupling will give added capability in the analysis of accidents in which the core is only partially voided of coolant. A sample VENUS calculation was prepared using FREADM results to provide transient initial conditions to VENUS.

9.2.5 Subtask 10.5 – FREADM Update

The purpose of this subtask is to revise the FREADM accident analysis code to include recent developments in core accident modeling (TOFF and BUBBLE routines) and to enhance its utility as a calculational tool. Planning was initiated during the reporting period. Specific activities will include revising the input, output and core storage to comply with recommendations of the *de facto* Committee on Computer Code Coordination.

9.2.6 Subtask 10.6 – Parametric Analysis

The purpose of this subtask is to use core and subassembly accident modeling techniques to focus on areas of uncertainty in LMFBR accident analysis. Current plans include a study of coolant channel blockage by fuel debris and analysis of a coastdown accident using multichannel heat transfer and recent coolant boiling and fuel failure information.

REFERENCES

1. ANL-7632, October 1969.
2. "Sodium-Cooled Reactors Development Program, Thirty-Sixth Quarterly Report, August-October 1970, December 1970 (GEAP-10028-36).
3. Streeter, V.L. and Wylie, E.B., "Hydraulic Transients", McGraw-Hill, 1967.

Figure 9-8. Power And Reactivity For Sample FREADM-MARS

10. TASK G-12 – ANL SAFETY/CORE DESIGN GUIDANCE

Task Leader: D.B. Sherer

Major Contributors:

J.J. Regimbal

F.W. Sciacca

10.1 GENERAL

Task G-12 has the goal of providing design guidance for development programs at Argonne National Laboratory so that the support of the demonstration plant in safety and related areas will be strengthened.

Work on Task G-12 was initiated during the quarter. A review of the LMFBF programs being conducted by ANL is in progress. Those areas that are concerned with safety and related areas will be reviewed in detail to assess their relationship to the demonstration plant development requirements. The following ANL programs are being reviewed:

Accident Analysis and Safety Evaluation

Instrumentation System to Protect Core Integrity

Coolant Dynamics

Core Structural Safety

Fuel Element Failure Propagation

Fuel Dynamics Studies in TREAT

Fuel Coolant Interaction

Post-Accident Heat Removal

Reactor System and Containment Structural Dynamic Response

High Temperature Physical Properties and Equation-of-State of Reactor Materials

In-Reactor Creep Studies

In-Pile Stainless Steel Swelling and Mechanical Properties

Behavior of Reactor Materials

Oxide Fuel Studies

Heat Transfer and Fluid Flow

Instrumentation and Control

Liaison with ANL is being maintained to ensure a proper understanding of their programs.

11.0 TASK L – CLADDING DEVELOPMENT

Task Leader: H.J. Busboom

Major Contributors:

W.K. Appleby	D. H. Frisby	G. F. Rieger
R.R. Asamoto	W. H. Furnal	P. J. Ring
W.L. Conant	T. A. Lauritzen	D. W. Sandusky
R.N. Duncan	V. Maguire	U. E. Wolff
J.D. Eveland	A. Montes	D. L. Zimmerman
G.P. Ferguson	R. P. Rhoads	

11.1 GENERAL

The technical and economic feasibility of ceramic-fueled fast reactors depends on the attainment of high performance of core structural members and the fuel system, especially the survival of the cladding at temperatures and specific fuel rod powers of practical interest.

The objectives of the cladding materials development program are to:

- (1) Determine the performance characteristics — including mechanical properties, fracture characteristics, radiation damage, and structural stability — of the most likely cladding material candidates and core structural materials under test conditions simulating the LMFBF environment.
- (2) Investigate the rate of alloy swelling and the environmental and metallurgical factors which influence and control it in LMFBF primary alloys and those which are potential candidates.

11.2 MATERIALS IRRADIATION PERFORMANCE

The objective of this subtask is to provide and follow capsules used as vehicles for irradiating cladding alloy specimens in EBR-II, and then to characterize the irradiation history of the capsules and prepare specimens for evaluation of mechanical and physical properties. A summary of this effort is shown in Table 2-6.

11.2.1 Fluence Calculations for EBR-II Irradiations

The following method for calculating fluence has been adopted as a standard procedure for materials irradiations in EBR-II. When fluences reported in this and future reports use this method, the value will be identified as such, $(1.0 \times 10^{23} \text{ n/cm}^2, E > 0.1 \text{ MeV-GE})$.

The total fluence distribution at the flux midplane at various core radii is determined from the relative radial fission rates for U-235 in EBR-II¹. Using the radial fission rate distribution, the megawatt days in reactor is converted to fluence at a particular radial location with the aid of conversion factors provided by EBR-II Physics. Since EBR-II has operated with a variety of core configurations, and therefore different fission rates, different conversion factors are used to distinguish between the different cores used in EBR-II.

The peak total fluence at the flux midplane is then divided by 1.2 as a correction for apparent difference in the unperturbed physics calculation values and experimental dosimetry results.² Other laboratories also make use of this type of correction when reporting radiation damage data.

The peak fluence at the flux midplane greater than 0.1 MeV is then determined by multiplying the corrected peak total fluence by the proper spectral weighting factor. These factors are determined as a function of radial position from the EBR-II Guide.¹ The same determination is made for flux greater than 1 MeV.

The axial distribution of fluence (total, $>0.1 \text{ MeV}$ and $>1 \text{ MeV}$) may also be determined from the EBR-II Guide, but since the range from the midplane was limited, the dosimetry results from XG05 were used instead.³ The dosimetry data agree with the Guide as far as these curves extend. The axial flux distribution is normalized to a peak of 1.0 so that the fluence at any axial position is readily available if the peak values are known. It has been assumed that the axial profiles for XG05 are valid throughout EBR-II. This conclusion appears to be valid after comparing relative flux profiles at various radial positions as calculated by the DOT2DB computer program.⁴

All of the above features are incorporated into a computer program to simplify fluence computations. All fluence values calculated by the above method will be identified. If EBR-II values are used, they will also be identified ($1.2 \times 10^{23} \text{ n/cm}^2$, $E > 0.1 \text{ MeV}$ -EBR-II).

11.2.2 Series L-6, L-15 and MT-4 EBR-II Materials Capsules

The capsule series noted in this section are the capsules presently at the EBR-II in various stages of irradiation. The three L-6 capsules (Mark-B7 type) are in the EBR-II Fuel Evaluation Facility hot cell and will be shipped to the Vallecitos Nuclear Center during the next quarter. These capsules have accumulated a total fluence of $8.3 \times 10^{22} \text{ n/cm}^2$ -GE (S/A X018B).

The four L-15 capsules and the MT-4 capsule (Mark-A19 type) are in the EBR-II Core in row 6 (S/A X080). As of December 31, 1970, the four L-15 capsules and the MT-4 capsule have accumulated a total fluence of 1.5×10^{22} and $7.0 \times 10^{22} \text{ n/cm}^2$ -GE, respectively.

11.2.3 Series L-2 EBR-II Materials Capsules

The four L-2 series capsules irradiated in S/A X050 to a total fluence of $9.0 \times 10^{22} \text{ n/cm}^2$ -GE were disassembled and all specimens are available for evaluation. Evaluation of the L-2 series materials will be reported under other Task L subtasks.

11.2.4 Series L-16 Materials Capsules

A new group of materials capsules, designated the L-16 series, is being designed to provide quantitative data on the swelling behavior of candidate cladding alloys Type 304 and Type 316 as a function of temperature of irradiation, metallurgical condition, and fluence.

L-16A Capsules

The 19 L-16A capsules are designed to accommodate various temperature monitoring devices and flux wires to measure the temperature of irradiation and neutron flux in a typical L-16 type Mark-A19 subassembly. Assembly of the capsule inserts has been delayed until the next quarter.

L-16B Capsules

The 19 L-16B capsules were shipped to EBR-II and assembled into a row 4 S/A designated X098. The initial irradiation exposure for this S/A is scheduled for a total fluence of $3 \times 10^{22} \text{ n/cm}^2$ -GE.

L-16D Capsules (Materials Re-Irradiations)

These three capsules are being designed to accommodate highly irradiated ring specimens for continued irradiation to higher fluences. Selected cladding specimens will be taken from the high burnup Task F fuel pins and Task L materials capsules. Design of these capsules is in progress.

11.3 CLADDING ALLOY SWELLING

The objective of this program is to measure cladding alloy materials and S/A hardware volume changes in available irradiated specimens to determine the relationships between swelling, fluence, irradiation temperature, alloy microstructure, and stress history. The techniques used to measure cladding swelling are liquid immersion density measurements, dimensional measurements (profilometry), and transmission electron microscopy (TEM).

11.3.1 Immersion Density Measurements

Immersion density measurements of irradiation-induced metal swelling in alpha-cleaned cladding sections from pins F2V, F2G, and F2X have been completed. Swelling values of $10\% \Delta V/V$ in Type 347 stainless steel (F2G) and $8.7\% \Delta V/V$ in Type 316 stainless steel (F2V) were measured.

The complete data are listed in Table 11-1, where the density decreases in the cladding have been converted to volume increases and then to diameter increases assuming isotropic swelling. These increases in diameter are compared with the overall fuel pin profilometry measurements.

Table 11-1

IMMERSION DENSITY MEASUREMENTS ON F2G, F2V, F2X CLADDING MATERIALS

Sample	Cladding	Axial Location (in. above bottom of pin)	Density (g.cm ⁻³)	- $\Delta\rho/\rho$ (%)	$\Delta V/V$ (%)	$\Delta D/D^*$ Cladding	Fluence $\times 10^{22}$ >0.1MeV-GE	Temperature**		$\Delta D/D$ Profilometry (%)
						Swelling (%)		(°C)	(°F)	
F2G-D	347	3.0-4.0	7.4886	5.49	5.80	1.93	6.40	488	912	3.41
F2G-H	347	7.25-8.5	7.2007	9.12	10.02	3.34	7.00	526	980	4.81
F2G-M	347	12.0-13.0	7.5114	5.21	5.49	1.83	5.50	538	1001	2.97
F2G-P	347	16.0-17.25	7.8803	.56	.56	.19	—	—	—	.34
F2G-R	347	30.0-31.25	7.9245	(control)	0	0	—	—	—	0
F2V-C	316	1.75-3.0	7.6354	3.80	3.95	1.32	6.15	472	883	1.61
F2V-E	316	4.0-5.25	7.3834	6.96	7.48	2.50	7.03	494	921	2.7
F2V-F	316	5.25-6.5	7.3651	7.20	7.76	2.59	7.32	508	943	3.3
F2V-J	316	7.5-8.75	3.3031	7.98	8.68	2.9	7.32	522	972	3.74
F2V-M	316	10.5-11.75	7.4811	5.74	5.98	2.0	6.40	531	990	2.78
F2V-P	316	12.75-14.0	7.7077	2.89	2.98	1.0	5.28	531	990	1.41
F2V-S	316	16.0-17.25	7.9276	.10	.10	.03	—	—	—	.17
F2V-U	316	30.0-31.25	7.9369	(control)	0	0	—	—	—	0
F2X-D	316	2.0-3.25	7.7159	2.78	2.86	.95	5.58	468	873	.94
F2X-J	316	7.25-8.5	7.4964	5.54	5.86	1.95	6.56	512	953	2.12
F2X-M	316	10.75-12.0	7.6770	3.26	3.37	1.12	5.60	522	972	1.49
F2X-R	316	16.0-17.25	7.9370	0-.45	0-.45	0-.15	—	—	—	.15
F2X-T	316	30.0-31.25	7.9362	(control)	0	0	—	—	—	0

* Calculated from volume change data.

** Mean of four values calculated for different power levels.

As noted in the previous quarterly report, the data show that the extent of cladding deformation not attributable to cladding swelling is a function of the initial smear density of the fuel.⁵ The low density powder fuel pin (F2X, 83.9% TD) shows essentially no fuel-induced cladding strain; the lowest density pelleted fuel pin (F2V, 86.7% TD) shows cladding strain principally in the peak burnup region, whereas the densest pelleted fuel pin (F2G) shows significant cladding strain from fuel-cladding interaction at all locations examined. In Figure 11-1, these strains in the peak burnup regions are plotted against smear density, together with equivalent data points from pins F2H and F2T.

Comparison of data from three 347 clad pins of similar smear densities (F2A, 93.5% TD; F2T, 94.3% TD; and F2G, 92.9% TD) permits some insight into the roles of cladding swelling and fuel swelling in determining the overall cladding deformation. In Figure 11-2, $\Delta D/D$ data for these pins have been separated into the contributions of cladding swelling and fuel-cladding interaction and are plotted against local burnup. It is found for the conditions of 93 to 94% TD fuel and 347 cladding that most of the fuel-cladding interaction occurred at 5 to 7 a/o burnup. Thereafter, the increasing cladding swelling rate exceeded the overall fuel swelling rate and fuel-cladding interaction was reduced. For steady-state conditions the cladding ductility at 12 a/o burnup ($\sim 7 \times 10^{22}$ n/cm², >0.1 MeV-GE) is probably less important than the ductility at 6 a/o burnup because the cladding stress probably decreases at higher burnup. It is of interest that the failed pin F2D (347 cladding) was of higher smear density than F2G (94.4% vs 92.9%) so that fuel-cladding interaction would be greater and would presumably begin slightly earlier in life.

The immersion density data obtained from these fuel rod cladding samples are of interest as basic cladding swelling information. The volume increase of 10.0% found in 347 stainless steel is the greatest amount of swelling yet reported in any metal irradiated in-reactor. The maximum swelling of the 316 stainless steel was somewhat less at 8.7% $\Delta V/V$.

An important consideration is whether any evidence of stress-induced void growth leading to enhanced swelling can be detected in the data. The measured swelling values have been compared with those calculated using various cladding swelling correlations. No immediate conclusion is apparent, principally because the correlations are based primarily on data for solution treated (ST) 304 stainless steel, and it is becoming increasingly evident that other types of stainless steel exhibit significantly different temperature dependencies and magnitudes of swelling. In Table 11-2 selected data are compared with values calculated by the PNL September 1969 equation for (ST) type 304 and 316 stainless steel. For the current data, this equation is probably the most relevant because the higher temperature part ($T > 470^\circ\text{C}$ - 878°F) is based solely upon (ST) 316 data. Specimens irradiated at similar temperatures but different stress levels were compared (F2V-F and F2V-J contained denser fuel than F2X-J, F2X-M). It was found that the specimens likely to be subjected to the higher stresses all showed greater swelling than calculated, whereas the other specimens showed less or only slightly more swelling than calculated. These observations suggest that a stress effect does exist but is not large. Electron microscopy (TEM) will provide further information on void number, density, and size.

In Figure 11-3 the swelling data are plotted as a function of fluence together with data from pins F2H and F2T reported previously. No tendency towards any limiting swelling value (saturation) is evident. Re-encapsulation of some of these specimens, permitting additional irradiation, will provide further information in this area (L-16D capsules).

Table 11-2

COMPARISON OF SWELLING DATA FROM 316 CLADDING FUEL RODS

Specimen	Fluence n/cm ² $\times 10^{-22}$ E>0.1 MeV-GE	Temperature °C (°F)	Measured $\Delta V/V$ (%)	Calculated $\Delta V/V$ (%)	Calculated to Measured Deviation	Relative Cladding Stress
F2V-F	7.32	508 (946)	7.65	6.5	-1.15	High
F2X-J	6.57	512 (954)	5.76	5.4	-0.36	Low
F2V-J	7.32	522 (972)	8.56	6.4	-2.16	High
F2X-M	5.60	522 (972)	3.28	4.0	+0.78	Low

* DEFINED AS PEAK TOTAL $\Delta D/D$ MINUS PEAK CLADDING SWELLING

Figure 11-1. Effect Of Fuel Density On Peak Cladding Strain

Figure 11-2. Cladding $\Delta D/D$ Versus Local Burnup For 347 Cladding Pins Of Similar Smear Density (F2A, F2T and F2G)

Figure 11-3. Clad Swelling In F-2 Series Fuel Pins

11.3.4 Swelling in Type 304 Stainless Steel

Profilometry measurements of the *capsule tubes* from the high burnup ($\sim 110,000$ MWd/Te) F-2 series fuel pins (F2G, F2V and F2X) complete a unique set of data describing the swelling of Type 304 stainless steel as a function of fluence from 2 to 7.4×10^{22} n/cm², $E > 0.1$ MeV-GE, and a temperature range of 380 to 480°C (716 to 896°F).

Profilometry is an attractive technique for measuring swelling in unpressurized tubes where swelling can be assumed isotropic, since it gives point-swelling measurements so that the associated temperature and flux level of the specimen can be very precisely defined. Previous work at GE^{6,3} and ANL⁷ has compared swelling as measured by profilometry and immersion density and found good agreement. The availability of capsule tubes F2V and F2G, which exhibit the greatest swelling measured to date in Type 304 stainless steel ($\Delta V/V$ to 7%), allowed an accurate check to be made of the assumption of isotropic swelling. A total of three sections (each 1/2 in. long) were cut from the F2V and F2G capsule tubes. Immersion density measurements were made on each specimen, and the measured decreases in density were converted to volume increases and then to diameter increases assuming isotropic swelling. These increases-in-diameter were compared with those measured by profilometry and found to be in good agreement. The data are given in Table 11-3.

Table 11-3

IMMERSION DENSITY DATA FROM F-2 CAPSULE TUBES

Specimen	Material	Axial Location (in. above disassembly) cut	Profilometry		ρ g/cm ³	Density Determination		
			ΔD (mils)	$\Delta D/D$ (%)		$-\Delta\rho/\rho^*\%$	$\Delta V/V\%$	$\Delta D/D\%$
F2V-C	304	9-5/8"	8.25	2.2	7.3760	6.67	7.15	2.38
F2V-D	304	16-1/8"	2.45	0.66	7.7207	2.31	2.36	0.79
F2G-B	304	12-3/8"	6.80	1.82	7.4301	5.99	6.37	2.12

* Based upon unirradiated density of 7.9035 g/cm³.

Typical swelling data from a number of capsule tubes are shown in Figure 11-4, in which the mean $\Delta D/D$ measurements have been multiplied by 3 to give $\Delta V/V$ and plotted as a function of temperature after normalizing the swelling values to a fluence of 5×10^{22} n/cm², $E > 0.1$ MeV-GE assuming a fluence exponent of 1.81 (as obtained in a previous empirical fit⁸). It is found that the data come together and exhibit peak swelling at 460 to 470°C (860 to 878°F). Data from the capsule tubes of lower power fuel pins (e.g., F2X, powder fuel) tend to show lower peak swelling temperatures which are not yet explained. It is noteworthy that analysis (as yet, incomplete) of profilometry traces from the F-6 series capsule tubes irradiated in Row 7 of EBR-II to fluences of 3.3×10^{22} n/cm², $E > 0.1$ MeV-GE and at higher temperatures (to 580°C, 1076°F) also show peak swelling at 460°C (860°F), although this temperature occurs below the flux midplane for these tubes. For the other capsule tubes, a temperature of 460°C (860°F) occurs slightly above the flux midplane.

11.4 CLADDING ALLOY MECHANICAL PROPERTIES

The objective of this subtask is to evaluate the post-irradiation mechanical properties of available cladding alloy specimens, including pre-cut tensile specimens and tubular specimens from Task L and Task F fuel cladding and capsule tubing. Various uniaxial and biaxial techniques are being used to perform the required mechanical properties evaluations.

Figure 11-4. Swelling Of Type 304 SS - Measured By Profilometry Of F2 Capsule Tubes.
Data Normalized To $\phi t = 5 \times 10^{22} \text{ n/cm}^2, > 0.1 \text{ MeV} - \text{GE}$

Table 11-4
Biaxial Creep Tests: Test Conditions and Strain Rate Measurements After 1486 Hours Testing

Specimen Identity	Irradiation Temperature Max. °C (°F)	Fluence E>.1 MeV-GE x10 ²² n/cm ²	Test Temperature °C (°F)	Hoop Stress (Ksi)	Strain Rate (in/in/hr) $\dot{\epsilon}_{irr}$	Strain Rate of Equivalent unirradiated specimen (a) (in/in/hr) $\dot{\epsilon}_u$	Strain Rate of irr. specimen Strain Rate of equivalent unirradiated specimen $\dot{\epsilon}_{irr}/\dot{\epsilon}_u$
A3	449(840)	3.82	704(1300)	12	2x10 ⁻⁶	2x10 ⁻⁴	.01
E2	377(710)	2.48	704(1300)	12	4.7x10 ⁻⁶	2x10 ⁻⁴	.023
A5	468(875)	3.81	704(1300)	10	2x10 ⁻⁶	.54x10 ⁻⁴	.037
E3	377(710)	2.91	704(1300)	10	4.7x10 ⁻⁶	.54x10 ⁻⁴	.087
A6	482(900)	3.26	704(1300)	8	2x10 ⁻⁶	1.14x10 ⁻⁵	.175
E4	377(710)	2.91	704(1300)	8	3.5x10 ⁻⁶	1.14x10 ⁻⁵	.3
B2	427(800)	3.32	704(1300)	6	3.2x10 ⁻⁷	.15x10 ⁻⁵	.21
F2	377(710)	2.48	704(1300)	6	2.3x10 ⁻⁶	.15x10 ⁻⁵	1.5
B3	455(850)	3.9	704(1300)	4	2.1x10 ⁻⁷	.1x10 ⁻⁶	2.1
C3	452(846)	3.72	593(1100)	30	(b)	.29x10 ⁻³	—
B5	474(885)	3.9	593(1100)	25	1.1x10 ⁻⁶	.75x10 ⁻⁴	.014
G2	377(710)	2.3	593(1100)	25	1x10 ⁻⁶	.75x10 ⁻⁴	.013
C4	468(875)	3.72	593(1100)	20	(b)	.15x10 ⁻⁴	—
G3	377(710)	2.7	593(1100)	20	1.1x10 ⁻⁶	.15x10 ⁻⁴	.073
D3	455(850)	3.9	593(1100)	15	.8x10 ⁻⁶	.185x10 ⁻⁵	.44
G4	377(710)	2.7	593(1100)	15	1.1x10 ⁻⁶	.185x10 ⁻⁵	.61
D4	474(885)	3.9	593(1100)	10	2.6x10 ⁻⁷	1.1x10 ⁻⁷	2.36
H2	377(710)	2.29	593(1100)	10	2.6x10 ⁻⁷	1.1x10 ⁻⁷	2.36
A2	424(795)	3.25	482(900)	35	.7x10 ⁻⁶	.32x10 ⁻⁶	2.18
B6	484(905)	3.33	482(900)	35	1.4x10 ⁻⁶	.32x10 ⁻⁶	4.37
I2	377(710)	2.23	482(900)	35	(b)	.32x10 ⁻⁶	—
I3	377(710)	2.6	482(900)	30	(b)	.97x10 ⁻⁷	—
I4	377(710)	2.6	482(900)	25	.6x10 ⁻⁶	.25x10 ⁻⁷	24.0

(a) Calculated from $\dot{\epsilon} = (e^{49.7}) [\sinh (2.14 \times 10^{-5} \sigma)] 6.87 (e^{-47,044/T})$

(b) No measurements available due to measuring equipment malfunction.

11.4.1 Biaxial Creep Program

The biaxial creep facility previously described⁹ was designed and fabricated for creep testing highly irradiated tubing materials at elevated temperatures. The experience gained in the successful operation of this type of constant stress creep test could be applied to in-pile creep testing. The swollen and distorted tubes, together with the very low strain rates being considered, make measurement of the small diameter changes difficult; however, a mechanical profilometer is being employed for these measurements and has given consistent results. An optical scanning measurement technique¹⁰ was tested and found to be less satisfactory. The test program is designed to obtain creep, stress rupture, and ductility data on irradiated tubular specimens.

Creep Test Results

Stress levels for the tests were selected to include a range of values representative of anticipated steady-state hoop stresses in the cladding of the pin during the last half of its intended life. The lower limit of stress selected for these tests is 4KSI at 704°C (1300°F).

Strain rate measurements have been made after 1486 hours on the higher fluence (3×10^{22} n/cm², >0.1 MeV-GE) Type 304 stainless steel specimens from S/A XG05 (Table 11-4). These creep rates are determined from only two measurements per specimen. Several additional measurements will be made to confirm the present findings.

Data reported previously indicated that two sets of specimens had shown a marked reduction in strain rate compared to unirradiated specimens. This trend has continued; with decreasing stress, the difference between irradiated and unirradiated creep rates diminished. Test data at 593°C (1100°F) show the percentage strain at increasing levels of stress (Figure 11-5).

Values for secondary creep rate taken from these curves show much less variation in strain rate with increasing stress, than calculated strain rate values for unirradiated material.

The most recent measurements indicate a cross-over point; at sufficiently low stresses (for a particular temperature), the irradiated creep rate exceeds the unirradiated creep rate. Figure 11-6 is a plot of stress-versus-strain-rate ratio (the ratio of the unirradiated strain rate to the unirradiated strain rate for an equivalent stress condition). It can be seen that at high stress levels the ratio is less than one; the strain rate of the irradiated material is less than that of the unirradiated material. At low stress levels, where the ratio exceeds one, the irradiated strain rate is higher than the unirradiated. Data points for 482°C (900°F) and 593°C (1100°F) unirradiated strain rates were computed from a general 304 equation¹¹:

$$\dot{\epsilon} = (e^{49.7}) [\sinh (2.14 \times 10^{-5} \sigma)] 6.87 (e^{-47,044/T})^{(9)}$$

where

$$\begin{aligned} \dot{\epsilon} &= \text{strain rate} \\ \sigma &= \text{stress (ksi)} \\ T &= \text{Temperature (}^{\circ}\text{C)} \end{aligned}$$

Good correlation was obtained in comparing calculated strain rates at 704°C (1300°F) with strain rates measured on unirradiated control specimens at this temperature. Unirradiated control data for the lower temperatures are not yet available.

In general, the following conclusions are drawn from the recent data:

- (1) At high stress levels, the strain rate of irradiated specimens (2.6 and 3.6×10^{22} n/cm², $E > 0.1$ MeV-GE) are less than computed strain rates for comparable unirradiated specimens by more than an order of magnitude.

Figure 11-5. Biaxial Creep Strain Time Curves For 304 Stainless Steel
Irradiated in EBR-II Test Temperature 593°C(1100°F)

■	704° C (1300° F)	~3.6x10 ²² n/cm ² >0.1 MeV
▲	593° C (1100° F)	~3.6x10 ²² n/cm ² >0.1 MeV
●	482° C (900° F)	~3.6x10 ²² n/cm ² >0.1 MeV
□	704° C (1300° F)	~2.6x10 ²² n/cm ² >0.1 MeV
△	593° C (1100° F)	~2.6x10 ²² n/cm ² >0.1 MeV
○	482° C (900° F)	~2.6x10 ²² n/cm ² >0.1 MeV

Figure 11-6. Effect Of Irradiation In The Creep Rate Of 304 Stainless Steel

- (2) As the stress level decreases, the difference between the strain rates of irradiated and unirradiated specimens decreases, until at very low stress levels, a cross-over occurs; the irradiated material creeps at a faster rate than does unirradiated material. The above effects and the stress levels at which they occur are strongly dependent on fluence, irradiation temperature and test temperature.
- (3) At a test temperature of 593°C (1100°F), the effect of variations in both fluence and irradiation temperature appear to be less pronounced than for material tested at 704°C (1300°F).
- (4) Material exposed to the same fluence but at higher irradiation temperature — 485°C (905°F) — displays an annealing effect on hardening; that is, the minimum creep rate is higher for the higher irradiation temperature.

Testing of the third group of irradiated specimens¹⁰ (fluence $\sim 7 \times 10^{22}$ n/cm², E>.1 MeV-GE) is expected to start during the next quarter. The test conditions will correspond to the present batch of specimens, and the results will provide further information with regard to the effect of fluence on strain rate.

11.5 MATERIALS MANAGEMENT

The objective of this subtask is to provide high quality tubing to experimenters on all tasks of the PA-10 programs. Also included in the characterization of this tubing.

11.5.1 Characterization of Fuel Cladding Material

A comprehensive characterization study that describes the as-received condition of the 5G430G tubing was completed during the current report period. The 5G430G tubing order consists of equal quantities of Types 304H and 316H stainless steel, each produced with 10, 20, 30 and 50% of residual cold work. The tubing — all 0.250-in. outside diameter with a 0.015-in. wall, seamless tubing — was procured to provide test material for current and future fuels and materials irradiation experiments and out-of-pile cladding development studies. It was ordered to a specification that included increased control on production parameters such as tube hollow manufacture, tube reduction schedules, and physical parameters such as chemical composition.

The tests and examinations performed on the 5G430G tubing included analyses to confirm alloy grade and show conformance to vendor certifications, a comprehensive series of nondestructive tests to establish dimensions, dimensional variances, and the condition of the tube wall and, finally, a test program to evaluate the mechanical properties of the eight lots of tubing. The results of these tests and analyses showed that the material represents tubing of high quality which conforms to the ordering specifications.

Stress-Rupture Behavior of Tubing with Various Defect Levels

The experimental program designed to assess the influence of local wall defects on the biaxial stress-rupture properties of cold-worked tubing is continuing. Testing of tube samples with outside surface defects was expanded to include inside surface defects as well. Defects were impressed by electrical discharge machining and range from 10 to 20% of the tube wall in depth. Testing is currently underway at a temperature of 1300°F.

Results from the small number of tests completed to date show that outside surface defects with depths as large as 10% of the tube wall do not significantly degrade the stress-rupture strength of 20% cold-worked material tested at high strain rates (pressures producing failures in less than 2000 hours). Moreover, the behavior of tubes with defects of this magnitude is indistinguishable in all respects from defect-free material similarly tested. Tests to failure with the 10% cold-worked material and with both materials containing inside surface defects are in progress.

REFERENCES

1. Guide for Radiation Experiments in EBR-II, Rev. 2 and Rev. 3, July 1969, EBR-II Project, ANL, Illinois.
2. McElroy, W.N., et al, "EBR-II Dosimetry Test - Preliminary Results," BNWL-CL-2076, April 25, 1969.
3. Busboom, H.J. and Asamoto, R.R., *Evaluation of Physical and Mechanical Properties of Type 304 Stainless Steel After Irradiation to 3.9×10^{22} n/cm² Total Fluence*, February 1970 (GEAP-13571).
4. Protsik, R. and Leff, E.G., *Users Manual for DOT2DB*, September 1969 (GEAP-13537).
5. *Sodium-Cooled Reactors Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report, August-October 1970*, December 1970 (GEAP-10028-36).
6. *Sodium-Cooled Reactors Fast Ceramic Reactor Development Program, Twenty-Ninth Quarterly Report, November 1968-January 1969*, February 1969 (GEAP-5753).
7. "Argonne National Lab. Reactor Development Project, Progress Report," ANL-7726, July 1970.
8. Comprelli, F.A., Oldberg, T., and Sandusky, D., *Empirical Analysis of Swelling of Austenitic Stainless Steels in Fast Reactors*, September 1969 (GEAP-13517).
9. *Sodium-Cooled Reactors Fast Ceramic Reactor Development Program, Thirtieth Quarterly Report, February-April 1969*, May 1969 (GEAP-10028).
10. *Sodium-Cooled Reactors Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report, August-October 1970*, December 1970 (GEAP-10028-36).
11. Lovell, A.J., FFTF Quarterly Report September-November 1969, BNWL 1275.

12. TASK N – CORE PHYSICS ANALYSIS

Task Leader: B.A. Hutchins

Major Contributors:

P. Greebler
C.L. Cowan
D.D. Freeman
R. Protsik
J.E. Turner
S.C. Crick
M.D. Kelley
N.H. Barth

12.1 GENERAL

The purpose of Task N is to contribute to the development of improved physics computational tools for the LMFBR program. To accomplish this work, computational methods and nuclear data used in the design of LMFBRs are evaluated and the need for improved methods and data determined. Acquisition of the improved methods and data is accomplished by development efforts within Task N and by cooperative activities in the national LMFBR program. Results of the evaluation studies, together with results from associated reactor design and development activities, also provide direction for establishing current LMFBR design and safety criteria.

12.2 COMPILATION AND DISTRIBUTION OF EVALUATED DATA

Benchmark calculations which have been carried out as part of the activities of the Data Testing Subcommittee of CSEWG have been completed and transmitted to the subcommittee chairman for correlation with other results. The calculated values of k_{eff} , reaction rate ratios, and central reactivity worths will be used to test the applicability of ENDF/B, Version II data in fast reactor studies. Results of the computations for the five benchmarks assigned to General Electric are given in Table 12-1.

In performing these benchmark calculations, self-shielded, composition-dependent cross sections for each of the assemblies were generated from ENDF/B, Version II data using the ENDRUN-TDOWN rapid cross-section adjustment approach. The benchmark analysis will include a comparison of this approach with other data processing techniques, such as the ETOE-MC² procedure. The k_{eff} values and reaction rate ratios presented in Table 12-1 were determined from discrete-ordinates transport calculations, and the reactivity coefficients were calculated by perturbation theory using real and adjoint fluxes from diffusion theory calculations.

The results of the benchmark calculations are presently being analyzed to determine the sensitivity of the parameters to data modifications for U-238, Pu-239, U-235, Fe, C and Cu — the principal materials in the composite benchmark study. Emphasis in the data evaluation program will be placed on possible modification to the Pu-239 fission cross section because of the low k_{eff} values, which were calculated for the plutonium fueled assemblies, and the low fission ratios of Pu-239 to U-235, which were calculated for all of the benchmarks with the exception of VERA-11A. A preliminary study has indicated that a 5 percent higher Pu-239 fission cross section between 50 keV and 1 MeV will provide near agreement between calculated and experimental benchmark eigenvalues.

12.3 SUPPLEMENTARY ANALYTICAL INTERPRETATION OF INTEGRAL DATA

The procedure for extracting uncertainties in computed physics design quantities of power reactors from the results of integral measurements in ZPPR, ZPR-6 and SEFOR has been specified in general terms. The approach is to reduce the analysis to uncertainty differences which have been sufficiently isolated to permit computations and meaningful estimates of the differences. This is accomplished by considering differences between: (a) direct calculation and measurement of the integral quantities; (b) experimental error for the quantity measured and the actual design quantity; and (c) errors involved in the calculation of the measured quantity and the design quantity in a power reactor.

The breeding ratio serves as a good example to illustrate the approach. The measured breeding ratio in ZPPR must be based on captures in U-238 and fissions in Pu-239 and Pu-241, only. The power reactor breeding ratio includes captures in Pu-240, as well as absorptions in Pu-239 and Pu-241. Thus, the error in the computed power reactor breeding ratio will be based on: (a) the difference between the calculated and measured breeding ratio in ZPPR; (b) additional experimental error due to exclusion of Pu-240, Pu-239 and Pu-241 capture in the measured breeding ratio, and to the reaction rates being measured outside, rather than within the fuel; and (c) additional error in the design breeding ratio calculation due to inclusion of Pu-240, Pu-239 and Pu-241 capture, and less error due to a more homogeneous geometry in the power reactor.

For the analysis of ZPPR, Assembly 2, flux weighting coefficients for the inner and outer core zones have been used to generate equivalent homogeneous cross sections. The weighting coefficients which were used had been computed at Argonne National Laboratory for the single cell in the inner zone and the combined cells in the outer zone.

The Doppler coefficient in the SEFOR reactor is being computed using data from ENDF/B, Version II. While the precalculated value of the Doppler effect in SEFOR is within 10% of the measured value¹, this new calculation will provide a comparison based on a well-known and available nuclear data set.

Table 12-1

RESULTS OF FAST REACTOR BENCHMARK CALCULATIONS USING ENDF/B, VERSION II DATA

	VERA-11A ⁽¹⁾	ZPR3-48 ⁽¹⁾	ZEBRA-3 ⁽¹⁾	ZPR3-11 ⁽¹⁾	ZPR3-12 ⁽¹⁾
CORE RADIUS (cm)	13.985	46.46	23.67	31.61	28.76
FUEL					
FISSILE Material	Pu-239	Pu-239	Pu-239	U-235	U-235
Atom Density (atoms/barn-cm)	7.213-3	1.645-3	3.465-3	4.567-3	4.516-3
MEAN FISSION ENERGY (keV)	~480	~218	~508	~367	~250
k _{eff}	0.9783	0.9733	0.9540	0.9714	0.9981
REACTION RATE RATIOS (C/E) ⁽²⁾					
σ_f (U-238)	1.065	0.967	0.870	0.895	0.936
σ_f (Pu-239)	1.037	0.929	0.948	0.950	0.955
σ_c (U-238)	-	1.007	-	1.063	1.033
σ_f (Pu-240)	0.998	0.930	0.936	0.970	-
REACTIVITY COEFFICIENTS (x 10 ⁻⁵ $\Delta k/k$ per mole) ⁽³⁾					
U-235	477.6	104.5(79.3)	-	143(123)	156(157)
U-238	13.3	-7.6(-5.9)	-13.6(-9.9)	-7.82(-6.6)	-7.86(-6.7)
Pu-239	767.6	132(106)	415(318)	222(209)	241(244)
Pu-240	306.1	21.8(19.4)	110	55.4	64.7
Pu-241	909.5	190.2	487	-	-
Fe	-0.55	-0.97(-0.69)	-4.30	-1.7(-1.7)	-1.36(-1.5)
C	-4.73	-0.26(-0.05)	-3.77	-0.59(-0.85)	0.94(2.0)
B-10	-	-101(-89.1)	-121	-73.4(-72.0)	-
Ta	-	-	-34.9	-19.0(-19.6)	-29.6(-31)

(1) A description of each benchmark is given in a letter distributed to the CSEWG members by W.G. Davey and A.L. Hess in March 1969.

(2) Given as the calculated ratio of the reaction rate to U-235 fission divided by the measured ratio of the reaction rate to U-235 fission.

(3) The measured values are in parentheses, where available.

12.4 IMPROVEMENT OF FUEL CYCLE AND MANAGEMENT SCHEMES

The topical report describing the fuel management code FUMBLE² has been submitted to the AEC for review.

12.5 IMPROVEMENTS OF EXISTING METHODS FOR GENERATING GROUP CONSTANTS

Several routines in the ENDRUN-2 code have been modified to improve the accuracy and/or efficiency of the computational operations of the code and to make the calculations consistent with those described in the recent data and procedures manual for the ENDF/B neutron cross-section library³. The principal modifications are summarized as follows:

- (1) Resonance calculations are being expanded to include a more explicit formulation of the higher order angular momentum states ($\ell=1,2$) and the energy dependent phase shift is being included in the potential scattering and resonance scattering calculations.
- (2) An elastic scattering matrix calculation was developed on the basis of a simple scattering probability function, $P(U \rightarrow U')$, defined as

$$P(U \rightarrow U') = A(U \cdot U') + B$$

where U' and U are the initial lethargy and the lethargy afterscattering, respectively, and A and B are constants which can be derived from the solution of

$$\int_{U'}^{U' + \ln \frac{1}{\alpha}} P(U \rightarrow U) dU = 1.0$$

and

$$\int_{U'}^{U' + \ln \frac{1}{\alpha}} (U - U') P(U \rightarrow U) dU = \bar{\xi}$$

where $\bar{\xi}$ is the average logarithmic energy loss

The elastic scattering matrix calculation has been checked out and preliminary results indicate that the scattered neutron spectrum is harder than that obtained with the earlier matrix routine.

The TDOWN-2 code is undergoing a procedural checkout. The elastic removal iteration process appears to be working correctly but requires more iterations than expected. Comparison of the flux spectra calculated in TDOWN-2 with those calculated using the diffusion theory code DEMON show close agreement.

12.6 COMPUTERS, COMPUTER LANGUAGE, AND CODE CENTER

Activities associated with the *de facto* Committee on Computer Code Coordination continued. Acceptance by the Advisory Committee on Reactor Physics of the Committee's recommendations on code development standards marked an important milestone in improving code coordination. General Electric personnel are participating in the setting of these standards and have played a key role in determining the standards for programming practices. Continued work includes providing support in the determination of standard interfaces and standard input formats. With respect to the latter, a demonstration of the use of the standard format proposed by General Electric was performed by translating a sample input deck from Argonne National Laboratory into the proposed standard.

A routine for setting up code tapes for transmittal to the Argonne Code Center and other users has been written and checked out. This routine will automatically replace any machine language routine with an appropriate FORTRAN equivalent (if available) from a standard library plus resequence internal statement numbers of each routine by ten, and resequence the

source deck in card columns 73-80. The first four characters in columns 73-80 identify the routine and the last four are the sequence number incremented by ten. A code binary tape is then generated which has all the control cards and a standard test case necessary for execution. The program is executed for the standard case as a check against the General Electric version. Once the binary tape has been checked out, it is transliterated to a BCD, 556 BPI, IBM(code 5) compatible tape for shipment to outside users.

This procedure will be used for the SYN, FUMBLE, ENDRUN-2 and TDOWN-2 codes for shipment to the Argonne Code Center.

REFERENCES

1. Noble, L.D., et al, *Results of SEFOR Zero Power Experiments*, General Electric Company, March (1970) (GEAP-13588).
2. P. Greebler, C.L. Cowan, *FUMBLE, An Approach to Fast Power Reactor Fuel Management and Burnup Calculations*, General Electric Company, November (1970) (GEAP-13599).
3. Data Formats and Procedures for the ENDF Neutron Cross Section Library, Edited by M.K. Drake, National Neutron Cross Section Center, BNL, October (1970).

13. TASK P – FUEL ELEMENT DESIGN ANALYSIS

Task Leader: J.D. Stephens

Major Contributors:

C.F. Barrett
D.K. English
F.E. Gelhaus
D.P. Hines
N.R. McBurney
S. Oldberg

13.1 GENERAL

The objective of Task P is the development of a model which will predict fuel performance and fuel lifetime. This modeling and analysis effort relates to other portions of the FCR Development Program in the following manner:

- (1) Guidance is provided in planning for fuel and cladding irradiations.
- (2) Assistance is provided for the analysis and interpretation of experimental results from fuel and cladding irradiations.
- (3) A performance and failure model is being developed for use in parametric design studies of the sodium-cooled breeder reactor.

13.2 INTEGRAL FUEL PERFORMANCE SIMULATION

Construction of the BEHAVE-I code is nearly complete. This code is the first version of a computer tool to simulate the integral performance of a fuel element throughout its operating history, including power changes and transients. BEHAVE-I calculates diametral growth along the length of a fuel pin during three modes of operation: (1) startup with fresh fuel; (2) steady-state operation; and (3) power increase following a period of steady power operation.

The structure of the code and the subroutines which follow the fuel behavior during first startup and steady-state operation have been described earlier^{1,2,3}. During the past quarter, a model for estimating fuel-cladding interference during an increase in power level was encoded.

One of the mechanisms for producing cladding strain during an increase in power is differential thermal expansion between the fuel and cladding. To illustrate this point, postulate the formation, after some time at steady power, of a strong unbroken ring (SUR) of fuel within a pin. The ring is bounded on the inside by fuel that will flow plastically under the thermal stresses generated, and on the outside by fuel with many radial cracks running from the fuel surface to the ring (Figure 13-1). The location of this ring (i.e., bounding radii) is a function of the hot pressing characteristics of the fuel, and the temperature regime. The structural integrity of the ring is not affected by subsequent shutdowns and restarts (it may, in fact, be enhanced).

Formation of the SUR can be pictured as occurring in three steps. First, radial cracks form during the first rise to power. The cracks do not go all the way to the center because: (1) local differential thermal expansion is small towards the center, and (2) the fuel flows readily in the center under the load produced by contact with the cladding. Second, the cracks heal out to a crack radius by sintering, with an assist from the load imposed by contact with the cladding. Finally, the void from the crack radius outward begins to fill in during the subsequent steady power operation due to fuel transport. A continuous ring is thus formed in the cooler, stronger fuel.

During a power increase, cladding strain is produced by differential thermal expansion between (1) this ring and the "fingers" of fuel, and (2) the cladding.

In the Fuel Modeling Round Robin, sponsored by the AEC-RDT, problems are posed to the modelers both to account for the observed behavior of experimental pins and to predict the performance of future test and LMFBR pins. The BEHAVE-I code is currently in use on the first round of these problems.

13.3 FUEL BEHAVIOR STUDIES

A model of fuel-cladding mechanical interaction during both steady-state operation and power changes has been encoded and is currently being debugged. This model was developed from the logic of the "SS2" two-dimensional stress analysis model of behavior during steady-state operation (described in Section 12 of references 2 and 3). The code will be used to expand the detailed investigation of mechanisms that may lead to cladding strain, in terms of both the accuracy with which power history effects can be simulated and the variety of situations that can be studied.

The major concern is the cladding diameter increase in excess of cladding swelling observed in the recent high burnup irradiations in EBR-II (GE-F2D, F2G, F2V, F2X; NUMEC-D5, C11, C15). Three mechanisms that are currently believed to be important in explaining these data are: (1) the steady-state "gas bottle" effect; (2) thermal expansion interference during power increases; and (3) fission gas precipitation during power increases. The gas bottle effect occurs when vapor transport or plastic flow of the fuel creates a sealed gas container in the inner fuel region. Migration of the fission gas from that region to the plenum is restricted, leading to high pressures during long periods of steady power operation.

The mechanism for interference between the fuel and cladding due to differential thermal expansion during a power increase after a period of steady power operation is described in the discussion of the derivative model in Subsection 13.2 above. In this context, a derivative model is defined as a model which is derived from detailed investigation of the mechanism, and which accounts for the significant effects of the mechanism but suppresses unnecessary complexity.

A fraction of the fission gas atoms retained in the lattice during steady power operation will precipitate during a subsequent power increase as the fuel temperature increases. This mechanism was described in Subsection 7.13 of reference 3.

REFERENCES

1. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Fourth Quarterly Report*, June 1970 (GEAP-10028-34).
2. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Fifth Quarterly Report*, September 1970 (GEAP-10028-35).
3. *Sodium-Cooled Reactors, Fast Ceramic Reactor Development Program, Thirty-Sixth Quarterly Report*, December 1970 (GEAP-10028-36).

1. RADIAL CRACK FORMATION

2. HEALING TO CRACK RADIUS

3. CRACK FILL

4. ANALYTICAL MODEL

(CRACK SIZE IS EXAGGERATED TO ILLUSTRATE THIS CONDITION)

Figure 13-1. Formation Of The Strong Unbroken Ring (SUR) Of Fuel

APPENDIX A PRIOR REPORTS

Prior progress reports to the Commission under this contract include:

Monthly Progress Letters, Number 1-107, from July 1959 through September 1970.

The quarterly reports under the title "Sodium-Cooled Reactors Fast Ceramic Reactor Development Program" follow:

GEAP-3888
First Quarterly Report
October-December 1961.

GEAP-3957
Second Quarterly Report
January-March 1962.

GEAP-3981
Third Quarterly Report
April-June 1962.

GEAP-4080
Fourth Quarterly Report
July-September 1962.

GEAP-4158
Fifth Quarterly Report
October-December 1962.

GEAP-4214
Sixth Quarterly Report
January-March 1963.

GEAP-4300
Seventh Quarterly Report
April-June 1963.

GEAP-4382
Eighth Quarterly Report
July-September 1963.

GEAP-4480
Ninth Quarterly Report
October-December 1963.

GEAP-4601
Tenth Quarterly Report
January-March 1964.

GEAP-4640
Eleventh Quarterly Report
April-June 1964.

GEAP-4723
Twelfth Quarterly Report
July-September 1964.

GEAP-4795
Thirteenth Quarterly Report
October 1964-January 1965.

GEAP-4860
Fourteenth Quarterly Report
February-April 1965.

GEAP-4931
Fifteenth Quarterly Report
May-July 1965.

GEAP-4982
Sixteenth Quarterly Report
August-October 1965.

GEAP-5098
Seventeenth Quarterly Report
November 1965-January 1966.

GEAP-5158
Eighteenth Quarterly Report
February-April 1966.

GEAP-5198
Nineteenth Quarterly Report
May-July 1966.

GEAP-5292
Twentieth Quarterly Report
August-October 1966.

GEAP-5433

Twenty-First Quarterly Report
November 1966—January 1967.

GEAP-5491

Twenty-Second Quarterly Report
February—April 1967.

GEAP-5522

Twenty-Third Quarterly Report
May—July 1967.

GEAP-5541

Twenty-Fourth Quarterly Report
August—October 1967.

GEAP-5584

Twenty-Fifth Quarterly Report
November 1967—January 1968.

GEAP-5631

Twenty-Sixth Quarterly Report
February—April 1968.

GEAP-5677

Twenty-Seventh Quarterly Report
May—July 1968.

GEAP-5700

Twenty-Eighth Quarterly Report
August—October 1968.

GEAP-5753

Twenty-Ninth Quarterly Report
November 1968—January 1969.

GEAP-10028

Thirtieth Quarterly Report
February—April 1969.

GEAP-10028-31

Thirty-First Quarterly Report
May—July 1969.

GEAP-10028-32

Thirty-Second Quarterly Report
August—October 1969.

GEAP-10028-33

Thirty-Third Quarterly Report
November 1969—January 1970.

GEAP-10028-34

Thirty-Fourth Quarterly Report
February 1970—April 1970

GEAP-10028-35

Thirty-Fifth Quarterly
May 1970—July 1970

GEAP-10028-36

Thirty-Sixth Quarterly Report
August 1970—October 1970

Supplementary Program Letters, Nos. 1-11 from
October 1962 through April 1964.

Reports from G. D. Collins and W. J. Ozeroff on
Assignment to CEA—France.

In addition, the following topical reports have been
issued:

GEAP-3287

Fast Oxide Breeder - Reactor Physics,
Part I - Parametric Study of 3000 MWe Reactor Core;
P. Greebler, P. Aline, and J. Sueoka
(November 10, 1959).

GEAP-3347

Fast Oxide Breeder - Stress Considerations
in Fuel Rod Design;
K. M. Horst
(March 28, 1960).

GEAP-3486

Fast Oxide Breeder Project -
Fuel Fabrication

Part I - Plutonium-Uranium Dioxide Preparation
and Pelletized Fuel Fabrication;
J. M. Cleveland and W. C. Cavanaugh

Part II - Fabrication of
Plutonium-Uranium Dioxide Specimens by Swaging;
M. E. Snyder and W. C. Cowden
(August 15, 1960).

GEAP-3487

Fast Oxide Breeder -
Preliminary Sintering Studies
of Plutonium—Uranium Dioxide Pellets;
J. M. Cleveland and W. C. Cavanaugh
(August 15, 1960).

GEAP-3646

Calculation of Doppler Coefficient
and Other Safety Parameters
for a Large Fast Oxide Reactor;
P. Greebler, B. A. Hutchins, and J. R. Sueoka
(March 9, 1961).

GEAP-3721

Core Design Study for a 500 MWe
Fast Oxide Reactor;
K. M. Horst, B. A. Hutchins,
F. J. Leitz, and B. Wolfe
(December 18, 1961).

GEAP-3824

Fabrication Cost Estimate
for UO_2 and Mixed PuO_2 - UO_2 Fuel;
G. D. Collins
(January 24, 1962).

GEAP-3833

The Post-Irradiation Examination
of a PuO_2 - UO_2 Fast Reactor Fuel;
J. M. Gerhart
(November 1961).

GEAP-3856

Experimental Fast Oxide Reactor;
K. P. Cohen, M. J. McNelly and B. Wolfe
(November 27, 1961).

GEAP-3876

Plutonium Fuel Processing and Fabrication
for Fast Ceramic Reactors;
H. W. Alter, G. D. Collins, and E. L. Zebroski
(February 1, 1962).

GEAP-3880

Comparative Study of PuC - UC and PuO_2 - UO_2
as Fast Reactor Fuel,

Part I - Technical Considerations;
K. M. Horst and B. A. Hutchins
(February 15, 1962).

Part II - Economic Considerations;
G. D. Collins
(November 15, 1962).

GEAP-3885

Experimental Fast Ceramic Reactor Design,
Status Report as of October 31, 1961;
Edited by K. M. Horst
(April 24, 1962).

GEAP-3923

Resonance Integral Calculations
for Evaluation of Doppler Coefficients -
The RAPTURE Code;
J. H. Ferziger, P. Greebler, M. D. Kelly,
and J. Walton
(June 12, 1962).

GEAP-4028

A Fuel Reprocessing Plant
for Fast Ceramic Reactors;
H. W. Alter
(February 1, 1962).

GEAP-4058

Analytical Studies of Transient Effects
in Fast Reactor Fuels;
R. B. Osborn and D. B. Sherer
(August 1962).

GEAP-4090

FORE - A Computational Program
for the Analysis of Fast Reactor Excursions;
P. Greebler and D. B. Sherer
(October 1962).

GEAP-4092

Doppler Calculations for
Large Fast Ceramic Reactors,
Effects of Improved Methods
and Recent Cross Section Information;
P. Greebler and E. Goldman
(December 1962).

GEAP-4130

Experimental Studies of Transient Effects
in Fast Reactor Fuels
Series I, UO_2 Irradiations;
J. H. Field
(November 15, 1962).

GEAP-4426

Conceptual Mechanical Design
of 565 MWe Fast Ceramic Reactor;
A. G. Silvestor
(April 1963).

GEAP-4271

Measurement of Oxygen-to-Metal Ratio
in Solid Solutions of UO_2 and PuO_2 ;

W. L. Lyon
(May 31, 1963).

GEAP-4283

Experimental Studies of Sodium Logging in FCR Fuels;

G. L. O'Neill, P. E. Novak, M. L. Johnson,
and W. E. Baily
(September 1963).

GEAP-4350

Fast Reactor Meltdown Excursions-
Analysis and Computer Program FARM I;
B. C. Luci, D. R. Riley, and N. F. Friedman
(December 5, 1963).

GEAP-4410

Calculations of Doppler and
Sodium Reactivity Effects;
P. Greebler
(November 1963).

GEAP-4414

Reactor Safety and Fuel Cycle Economics;
K. P. Cohen
(November 1963).

GEAP-4418

Liquid Metal Fast Breeder Reactor Design Study,
1000 MWe PuO_2 - UO_2 Fueled Plant,
Vols. I and II;
M. J. McNelly, et al.
(January 1964).

GEAP-4420

Influence of Doppler Effect on Meltdown Accident;
N. F. Friedman
(December 1963).

GEAP-4466

Experimental Studies of
Plutonium and Fission Product Redistribution
in Fast Reactor Fuels;
T. Lauritzen, et al.
(July 1966).

GEAP-4469

Experimental Studies of Transient Effects
in Fast Reactor Fuels,
Series III,
Pre-Irradiated Mixed Oxide (PuO_2 - UO_2),
Irradiations Final Report,
Transient Irradiations;
J. E. Hanson, J. H. Field
(February 1968).

GEAP-4471

Calculated Nuclear Parameters and
Their Uncertainties in a 1000 MWe FCR;
P. Greebler, et al.
(October 1966).

GEAP-4472

User Requirements for Cross Sections
in the Energy Range from 100 eV to 100 keV;
P. Greebler and B. A. Hutchins
(1966).

GEAP-4580

FLUX-A Computer Code
for Analyzing the Reactor Response
to Small Reactivity Oscillations;
P. Greebler, B. A. Hutchins, and M. D. Kelley
(March 22, 1965).

GEAP-4630

The Effects of Resonance Overlap on
the Doppler Coefficient in a Fast Ceramic Reactor,
Computer Codes RAVE and DOPIE;
B. A. Hutchins
(August 1964).

GEAP-4675

Some Electrical Properties of
the Plutonium-Uranium Mixed Oxide System;
W. E. Baily
(July 1966).

GEAP-4770

A Technical and Economic Evaluation of
Vented Fuel for Sodium-Cooled Fast Ceramic Reactors;
G. L. O'Neill, J. Duffy, J. C. Gilbertson, F. W. Knight,
and D. B. Sherer
(May 1965).

- GEAP-4787
An Analysis of Fast Reactor Transient Response and Safety in Selected Accidents;
W. Meinhardt, Jr.
(August 1966).
- GEAP-4804
Experimental Studies of
Transient Effects in Fast Reactor Fuels,
Series II;
J. E. Hanson, J. H. Field, and S. A. Rabin
(June 1965).
- GEAP-4809
Fast Reactor Meltdown Accidents
Using Bethe-Tait Analysis;
R. Meyer and B. Wolfe
(January 1957).
- GEAP-4819
Experimental Studies of
Transient Effects in Fast Reactor Fuels,
Series III,
Pre-Irradiated Mixed Oxide ($\text{PuO}_2\text{-UO}_2$) Irradiations,
Interim Report, Steady State Irradiations;
J. E. Hanson and S. A. Rabin
(September 1965).
- GEAP-4822
Studies of Alternate Core Design Concepts
for Fast Sodium Cooled Reactors;
C. L. Cowan
(November 1966).
- GEAP-4870
Some Design and Irradiation Experience
with Capsules for Long Ceramic Fuel Elements;
F. W. Knight
(July 1966).
- GEAP-4877
Diffusion of Plutonium and Uranium
in Oxide Fuel at 2400°C ;
J. Davies and P. Novak
(August 1966).
- GEAP-4878
The Solid-Liquid Phase Diagram
for $\text{UO}_2\text{-PuO}_2$ System;
W. L. Lyon and W. E. Baily
(May 1966).
- GEAP-4879
Thermal Conductivity of
Uranium and Uranium Plutonium Oxides;
T. E. Lannin
(January 1968).
- GEAP-4897
Irradiation Behavior of
Hyper- and Hypo-Stoichiometric Plutonia-Urania Fuel
at 70,000 MWd/Te;
E. L. Zebroski, W. E. Baily, and D. P. Hines
(March 1965).
- GEAP-4922
BISYN—
A Two Dimensional Synthesis Program;
M. D. Kelley
(December 1966).
- GEAP-4939
Safety and Economic Characteristics of
a 1000 MWe Fast Sodium Cooled Reactor Design;
K. P. Cohen and G. L. O'Neill
(April 1967).
- GEAP-5271
Implications of Recent Fast Critical Experiments
on Basic Fast Reactor Design;
P. Greebler
(March 1968).
- GEAP-5272
Evaluation and Computation of
Pu-239 Cross Section Data
for the ENDF/B Files;
P. Greebler, P. Aline, B. Hutchins
(January 1967).
- GEAP-5273
FORE II, A Computational Program for
the Analysis of Steady-State and Transient
Reactor Performance;
B. E. Lawler, et al.
(September 1967).
- GEAP-5340
Neutron Spectrum Measurements in a Fast Plutonium
Assembly ZPR-III Assembly 48;
P. S. Brown and A. Weitzberg
(April 1967).

GEAP-5344

Electron Microanalysis of Radioactive Materials I,
Preliminary Experiments and Plans for a Shielded Facility;
H. Rosenbaum, et al.
(February 1968).

GEAP-5355A

Burnup: A FORTRAN IV Code for Computing U and Pu
Fuel Burnup from U, Pu, and Nd Mass Spectrometric
Measurements.
B. F. Rider
(January 1970)

GEAP-5411

Turbulent Velocity Distribution in a Rod Bundle;
D. J. Bender, D. M. Switick, J. H. Field
(January 1968)

GEAP-5493

The Effect of Density on Thermal Conductivity
of Uranium Dioxide;
R. Asamoto
(February 1968).

GEAP-5494

RAPFU—A Computer Code;
P. Greebler, C. Cowan
(November 1967).

GEAP-5556

In-Pile Comparison of Effective
Thermal Conductivity (Pu-UO₂) Mixed Oxides;
C. N. Craig, W. E. Baily
(March 1968).

GEAP-5583

The Role of Fission Products
in the Swelling of Irradiated UO₂-(U, Pu)O₂ Fuel;
F. Anselin
(January 1969).

GEAP-5633

Compatibility of LMFBR Fuel Pin Components;
T. A. Lauritzen
(June 1968).

GEAP-5635

Significance of Neutron Data Uncertainties
to Fast Reactor Economics and Power Plant Design;
B. A. Hutchins, et al.
(June 1968).

GEAP-5683

Thermodynamic Analysis
of Possible Chemical Interactions in the System,
UO₂-PuO₂ Fuel-Sodium-Stainless Steel;
E. A. Aitken
(July 1968).

GEAP-5744

Analytical Procedures and Applications
of Fluence Determinations from EBR-II Flux Wires;
A. Withop, B. A. Hutchins, G. C. Martin
(March 1968).

GEAP-5748

Fuel Cladding Heat Transfer Coefficients
for Oxide Fuel Rods;
C. N. Craig, et al.
(January 1969).

GEAP-5761

The Irradiation of Mixed Oxide Fuel
to 125,000 MWd/Te in a Thermal Flux;
B. F. Rubin and K. J. Perry
(March 1969).

GEAP-5570

Short Term Fast Flux (EBR-II) Irradiation
of PuO₂-UO₂ Fuel Pins;
S. A. Rabin, W. W. Kendall, W. E. Baily
(February 1968).

GEAP-10046

BISYN—PERT:
A Two-Dimensional Perturbation Module
for the BISYN System;
M. D. Kelley and T. R. Jones
(April 1969).

GEAP-10052

Turbulent Heat Transfer in a Rod Bundle
with Liquid Metal Coolant;
D. J. Bender and P. M. Magee
(July 1969).

GEAP-10054

Compressive Creep Characteristics
of Stoichiometric Uranium Dioxide;
P. E. Bohaboy, R. R. Asamoto, A. E. Conti
(May 1969).

GEAP-10062

Mechanical Properties of Irradiated Type-304
and Type-316 Stainless Steel in Fast Reactors;
F. A. Comprelli, H. J. Busboom, M. F. Gebhardt
(June 1969).

GEAP-10066

Mechanical Properties Evaluation of Austenitic Stainless Steels Irradiated in EBR-II;
T. Lauritzen, A. Withop, G. P. Ferguson
(July 1969).

GEAP-13553

An Evaluation of the Quality of Seamless Austenitic Stainless Steel Tubing;
T. A. Lauritzen
(December 1969).

GEAP-13515

The Melting Point of Plutonia-Urania Mixed Oxides Irradiated to High Burnup;
J. L. Krankota, C. N. Craig
(July 1969).

GEAP-13556

BICYCL - A Computer Code for Two-Dimensional Analysis of Equilibrium Fuel Cycles;
P. C. Vaughn
(December 1969).

GEAP-13517

Empirical Analysis of Swelling of Austenitic Stainless Steels in Fast Reactors;
F. A. Comprelli
(September 1969)

GEAP-13591

Pu-239 Unresolved Resonance Data for ENDF/B Version II;
J. T. Hitchcock and B. A. Hutchins
(April 1970).

GEAP-13543

Molten Fuel Movement in Transient Overpower Tests of Irradiated Oxide Fuel;
T. Hikido
(September 1969).

GEAP-13592

ENDRUN-1, A Computer Code to Generate A Generalized Multigroup Data File from ENDF/B;
B. A. Hutchins and L. N. Price
(April 1970).

GEAP-13562

Transient Overpower Irradiation of Axially-Restrained, Zero-Burnup Fast Reactor Fuel Specimens;
G. R. Thomas
J. H. Field
(September 1969)

GEAP-13599

FUMBLE: An Approach to Fast Power Reactor Fuel Management and Burnup Calculations;
P. Greebler
C. L. Cowan
(November 1970)

GEAP-13549

Performance of Plutonium-Uranium Mixed Oxide Fuel Pins in a Fast Reactor (EBR-II) to 50,000 MWd/Te;
R. C. Nelson
(August 1969)

GEAP-13608

THE FREADM CODE: A Fast Reactor Excursion and Accident Dynamic Model;
D. Freeman, et al.
(September 1970)

GEAP-13551

Effects of Nuclear Methods Approximations on LMFBR Analysis;
R. Protsik
(August 1969).

+

,

.

»

.

.

»

»

»

.

»

.

APPENDIX B

LIST OF ABBREVIATIONS, SYMBOLS, AND ACRONYMS

Å	=	angstroms
(Ann)	=	annealed
a/o	=	atom percent burnup (fission only)
at. %	=	atom percent
BCD	=	binary coded decimal
BEHAVE	=	fuel modeling code
B.P.	=	boiling point
BPI	=	bits per inch (computer tape density)
BUBBLE	=	coolant boiling and channel voiding code
cm	=	centimeters
C.W.	=	cold worked
CSEWG	=	Cross Section Evaluation Working Group
DEMON	=	diffusion theory flux solution computer code
EBR-II	=	Experimental Breeder Reactor II
ENDF/B	=	Evaluated Nuclear Data File/B
ENDRUN	=	computer code for cross section processing
ETOE-MC ²	=	computer codes for cross section processing
FFTF	=	Fast Flux Test Facility
FORTTRAN	=	standard computer programming language
FREADM	=	Fast Reactor Excursion and Accident Dynamics Model
ft/sec	=	feet per second
FUMBLE	=	fuel management computer code
h_{gap}	=	fuel-cladding gap conductivity

GETR	=	General Electric Test Reactor
gm	=	grams
i.d.	=	inside diameter
in./in./hr	=	inches per inch per hour
I.P.	=	integrated power
K	=	thermal condition
Kcal/mole	=	kilocalories per mole
k_{eff}	=	effective neutron multiplication factor
keV	=	kilo electron volts
kW/ft	=	kilowatts per foot
ℓ	=	angular momentum states
Lbf	=	pounds force
Lbm	=	pounds mass
LMFBR	=	Liquid Metal Fast Breeder Reactor
MARS	=	disassembly calculation
MeV	=	million electron volts
mg	=	milligram
μm	=	micrometers
msec	=	millisecond
mole	=	gram molecular weight
MWd/Te	=	megawatt-day per ton (metric, tonne, 2205 lb)
nvt	=	time integrated neutron flux
o.d.	=	outside diameter
$\%\Delta k$	=	percent reactivity addition
$\%\text{TD}$	=	percent of theoretical density of fuel

P_L	=	linear power
P_{max}	=	peak power
ppm	=	parts per million
psi	=	pounds per square inch
psia	=	pounds per square inch absolute
psig	=	pounds per square inch (gauge)
S/A	=	subassembly
SEFOR	=	Southwest Experimental Fast Oxide Reactor
SS or S/S	=	stainless steel
(ST)	=	solution treated
SUR	=	strong unbroken ring
σ_c	=	capture cross section
σ_f	=	fission cross section
SYN	=	combined synthesis-fuel cycle code system
TDOWN	=	computer code for cross section processing
TEM	=	transmission electron microscopy
THTD	=	transient heat transfer code (version D)
THTE	=	transient heat transfer code (version E)
TOFF	=	transient overpower fuel failure
TREAT	=	Transient Reactor Test Facility
VENUS	=	disassembly calculation code
VERA-11	=	critical assembly 11A in VERA facility
VNC	=	Vallecitos Nuclear Center
V/o	=	volume percent
$\bar{\xi}$	=	average logarithmic energy decrement

watts/cc	=	watts per cubic centimeter
wt %	=	weight percent
ZEBRA-3	=	critical assembly 3 in ZEBRA facility
ZPPR-2	=	critical assembly 2 in Zero Power Plutonium Reactor facility
ZPR3-11	=	critical assembly 11 in ZPR-3 facility
ZPR3-12	=	critical assembly 12 in ZPR-3 facility
ZPR3-48	=	critical assembly 48 in ZPR-3 facility
ZPR-6	=	Zero Power Reactor facility 6

DISTRIBUTION LIST-PA 10

Director, Contracts Division U. S. Atomic Energy Commission San Francisco Operations Office 2111 Bancroft Way Berkeley, California 94704	1	Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Reactor Engineering	2
RDT Site Office U. S. Atomic Energy Commission General Electric Company 310 DeGuigne Drive Sunnyvale, California 94086	1	Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Reactor Technology	1
Chief, California Patent Group U. S. Atomic Energy Commission San Francisco Operations Office P. O. Box 808 Livermore, California 94550	1	Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Chief, Fuels and Materials Branch	3
Manager Westinghouse Electric Corporation Advanced Reactors Division P. O. Box 158 Madison, Pennsylvania 15663	1	Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Chief, Fuel Engineering Branch	1
Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Engineering Standards	1	Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Chief, Reactor Vessels Branch	1
Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Nuclear Safety	1	Assistant Director for Pacific Northwest Programs, RDT U. S. Atomic Energy Commission P. O. Box 550 Richland, Washington 99352	1
Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Plant Engineering	1	RDT Site Office U. S. Atomic Energy Commission Argonne National Laboratory Building 2, Argonne, Illinois 60439	1
Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Program Analysis	1	RDT Site Office U. S. Atomic Energy Commission Atomics International P. O. Box 1446 Canoga Park, California 91304	1
Division of Reactor Development and Technology, Headquarters U. S. Atomic Energy Commission Washington, D. C. 20545 Attn: Assistant Director, Project Management	2	RDT Site Office U. S. Atomic Energy Commission Argonne National Laboratory P. O. Box 2108 Idaho Falls, Idaho 83401	1

RDT Senior Site Representative U. S. Atomic Energy Commission P. O. Box 2325 San Diego, California 92112	1	FFTF Fuels Department Pacific Northwest Laboratory P. O. Box 999 Richland, Washington 99352	2
Division of Naval Reactors Chief, Nuclear Materials Branch U. S. Atomic Energy Commission Washington, D. C. 20545	1	Division Leader (CMB) Chemistry and Metallurgy Division Los Alamos Scientific Laboratory P. O. Box 1663 Los Alamos, New Mexico 87544	1
Director Division of Reactor Licensing U. S. Atomic Energy Commission Washington, D. C. 20545	2	Director Metallurgy and Materials Science Division Brookhaven National Laboratory Upton, New York 11973	1
Director Metallurgy Division Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60439	2	Division Chief, M & S Division NASA - Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135	1
Manager, FFTF Project Pacific Northwest Laboratory P. O. Box 999 Richland, Washington 99352	6	General Manager Westinghouse Electric Corporation Bettis Atomic Power Laboratory P. O. Box 79 West Mifflin, Pennsylvania 15122	1
Manager Chemistry and Metallurgy Division Pacific Northwest Laboratory P. O. Box 999 Richland, Washington 99352	1	Associate Manager Materials Engineering Department Battelle Memorial Institute Columbus Laboratories 505 King Avenue Columbus, Ohio 43201	1
RDT Site Office U. S. Atomic Energy Commission Oak Ridge National Laboratory P. O. Box X Oak Ridge, Tennessee 37830	1	Manager, Nuclear Laboratories Combustion Engineering Inc. Nuclear Division Prospect Hill Road Windsor, Connecticut 06095	1
Director Division of Reactor Standards U. S. Atomic Energy Commission Washington, D. C. 20545	2	Manager, Plutonium Chemistry and Ceramics Fuels Development Nuclear Materials and Equipment Corporation Plutonium Laboratory Leechburg, Pennsylvania 15656	1
Division of Technical Information Extension U. S. Atomic Energy Commission P. O. Box 62 Oak Ridge, Tennessee 37831	135		
Director LMFBR Program Office Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60439	2	Head, Fuels and Materials Atomic Power Development Associates 1911 First Street Detroit, Michigan 48226	1
Director Chemical Engineering Division Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60439	1	Director Metals and Ceramics Division Oak Ridge National Laboratory P. O. Box X Oak Ridge, Tennessee 37830	2

Director, Liquid Metal Engineering Center Atoms International P. O. Box 1449 Canoga Park, California 91304	1	K-2 Group Leader Reactor Division Los Alamos Scientific Laboratory P. O. Box 1663 Los Alamos, New Mexico 87544	1
Manager—Advanced Development Activity General Electric Company Knolls Atomic Power Laboratory P. O. Box 1072 Schenectady, New York 12301	1	Westinghouse Electric Corporation Technical Director Advanced Reactors Division P. O. Box 158 Madison, Pennsylvania 15663	2
Director, LMFBR Technology Program Atoms International P. O. Box 309 Canoga Park, California 91304	1	Manager Liquid Metal Information Center Atoms International P. O. Box 1449 Canoga Park, California 91304	1
Director Nuclear Development Center The Babcock and Wilcox Company Atomic Energy Division Lynchburg, Virginia 24501	1	Irradiation Coordinator EBR-II Project Argonne National Laboratory P. O. Box 2528 Idaho Falls, Idaho 83401	1
Laboratory Assistant Director Gulf General Atomic Incorporated P. O. Box 608 San Diego, California 92112	1	Experiment Manager EBR-II Project Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60439	1
Manager, Research United Nuclear Corporation Research and Engineering Center Grasslands Road Elmsford, New York 10523	1	Director Reactor Analysis and Safety Division Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois, 60439	5
Director Nuclear Safety Program Oak Ridge National Laboratory P. O. Box Y Oak Ridge, Tennessee 37830	3	Technical Director, FFTF Project Hanford Engineering Development Laboratory P. O. Box 1970 Richland, Washington 99352	1