MASTER

OAK RIDGE NATIONAL LABORATORY

Operated by

UNION CARBIDE NUCLEAR COMPANY

Division of Union Carbide Corporation

Post Office Box X

Oak Ridge, Tennessee

EXTERNAL DISTRIBUTION
AUTHORIZED~~Distribution Limited to~~
~~Recipients Approved~~ORNL
CENTRAL FILES NUMBER

60-6-72

DATE: June 10, 1960

COPY NO. 31

SUBJECT: ORNL Fuel Cycle Progress Report for
Period March 15 to May 15, 1960

TO: Distribution

FROM: D. E. Ferguson

ABSTRACT

A method for the preparation of high-density ThO_2 of the correct particle size for vibratory compaction is under development. The method being developed appears easily adaptable to remote operation. Pure ThO_2 made by this method was readily compacted to 86% of theoretical density by pneumatic vibration. Preparations of high-density mixed $\text{ThO}_2\text{-UO}_2$ and UO_2 by this general method have been successfully carried out. Densification of arc-fused mixed oxide by a pneumatic vibrator compared favorably with results of tests with the same oxide using electronic vibrators at both Huntsville, Alabama, and Savannah River. In the limited tests with the electronic vibrators at the other sites, it appeared that a saw-tooth wave shape gave greater densification than a sine wave or random noise.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights, or

It assumes no liability with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" means any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or agreement with the Commission, or its employment with such contractor.

NOTICE

This document contains information of a preliminary nature and was prepared primarily for internal use at the Oak Ridge National Laboratory. It is subject to revision or correction and therefore does not represent a final report. The information is not to be abstracted, reprinted or otherwise given public dissemination without the approval of the ORNL patent branch, Legal and Information Control Department.

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

This report is the first bimonthly progress report of the ORNL Fuel Cycle Program. It covers experimental work by E. S. Bomar, P. A. Haas, O. C. Dean, J. W. Snider, W. S. Ernst, Jr., S. D. Clinton, K. H. McCorkle, and C. E. Schilling. An ORNL topical report covering this material, ORNL-2965, is in preparation.

Vibratory Compaction Studies

The most interesting observation made during this period was the behavior during vibratory loading of ThO_2 prepared by the hydrothermal process (see next section). This oxide, having a particle density greater than 99% of theoretical, vibrated to a bulk density of 8.66 g/cc, or 86% of theoretical, in a 3/8-in.-o.d. stainless steel tube. The powder used for the vibration experiment was sized and blended with a distribution which represented a variation on that blend found by Hanford to be optimum for fused UO_2 .

Preparatory to selecting electronic equipment to supply vibratory energy for powder consolidation work, cursory vibration experiments were run on electronic equipment at the U. S. Army Ballistic Missile Agency, Huntsville, Alabama, and the AEC facilities at Savannah River. The experiments at Huntsville examined the effect of vibration wave form and acceleration level on fused 96.6 wt % ThO_2 -3.4 wt % UO_2 powder. The tubes were preloaded at ORNL. Pure sine waves gave a decrease in density from the value of about 8.3 g/cc for as-loaded powder. This is at variance with Hanford's experience where sine-wave vibration is reported to yield densities greater than 90% of theoretical with fused UO_2 in Zircaloy-2 tubes. Random-noise and saw-tooth wave forms cause no significant change in density, while distorted-sine wave form resulted in a detectable density increase to a maximum value of 8.51 g/cc. These data are shown in Table 1. Acceleration values ranging from 10 to 50 G appeared to have little effect on the resulting bulk density. All of the above tubes were revibrated on the BH-1 1/4-in. pneumatic vibrator upon returning to ORNL. Increases of 2 to 5% were obtained. The tests at Savannah River were carried out by a procedure duplicating that used by Hanford. Four runs were made using sine-wave input and resulted in an average density of 8.57 g/cc. A single run with saw-tooth input yielded a density of 8.80 g/cc. The Hanford visit was made for a mutual exchange of information on experience to date with vibratory consolidation.

Moving pictures were made at a speed of 155 frames/sec to record the movement of powder contained in a 2-ft-long lucite tube. At certain locations along the length of the tube, the fine particles appeared to move rapidly. However, the coarse fractions were relatively motionless.

In the course of loading experiments, a temperature rise as a result of absorption of vibrational energy had been detected in the tubes. To obtain quantitative results, thermocouples were placed at 2-in. intervals along a 2-ft section of stainless steel tubing. A difference was found for the temperature rise of a tube loaded with oxide compared with an empty tube as

Table 1. Huntsville Electronic-Vibrator Conditions and Results
for ThO₂-UO₂ Powders

Run No.	Acceleration, G	Freq., cycles/sec	Wave Form	Loaded ^a Density, g/cc	Electronically ^b Vibrated Density, g/cc	Pneumatically ^c Vibrated Density, g/cc
2	60	2000	Sine	8.33	8.29	8.62
3	46	943	Sine	8.32	8.26	--
4	50	77	Sine	8.37	7.94	8.26
5	50	370	Saw-tooth	8.34	8.37	8.50
6	48	290	Saw-tooth	8.40	8.44	8.69
7	19	40	Saw-tooth	8.34	8.40	8.75
8	29	50-1000	Random-noise	--	8.37	--
9	10	50-1000	Random-noise	8.30	8.34	8.62
10	20	90	Distorted-sine	8.44	8.51	8.58
11	20	66	Distorted-sine	8.34	8.23	8.70

^aAll tubes 2 ft long. Vibrated for 1 min while powder was poured into the tubes.

^bVibrated for 10 min.

^cVibrated for 10 min on pneumatic unit after returning to ORNL.

follows: loaded tube 50°C warmer at the bottom, 5°C warmer at the center, 20°C warmer at three-quarters of the distance from bottom of the tube, and 10°C cooler at the top.

The Preparation of High-Density Fuel Materials

A method is being developed for the preparation of high-density thorium and thorium-uranium fuel materials which appears to be easily adaptable to operation behind shielding. Much of the procedure is carried out in water, and the maximum temperature used for densification is 1300°C, within the capability of day-to-day operation of silicon carbide globar furnace elements in air. By making adjustments in procedure, the process promises to yield the desired particle sizes, making unnecessary a grinding and screening operation.

Dense, sized thorium fragments were prepared by dispersion of low-fired thorium oxide particles in thorium nitrate or nitric acid, followed by hydrothermal denitration to a dried gel state. On calcination to 1200°C, particles whose average size was as large as 1.4 mm, and whose density was 9.97 g/cc, >99% of theoretical, were prepared. A distribution of sizes of this material had a tap density of 7.95 g/cc and a vibrated bulk density of 8.66 g/cc. Particle size control is achieved through control of temperature and nitrate content in the denitration step.

Batches up to 300 g of uranium-thorium whose U/Th atomic ratio was 5/95 were prepared by a slight modification of the procedure for pure thorium above. Particle density was 9.78 to 9.94 g/cc, 98.5% of theoretical. Control of size appears possible. The average size of the largest particle group was 2 mm. A 200-g sample was vibrated to a bulk density of 8.33 g/cc.

Uranium was prepared by a procedure similar to that used for thorium and the mixed oxide. Uranous oxalate was thermally decomposed to UO₂, then peptized with HCl solution. Under argon atmosphere three successive evaporations produced a glassy gel similar to the dried denitrated thorium gels. Calcination in a hydrogen atmosphere produced strong fragments of ~1 mm size and having a particle density of 10.2 g/cc, 93% of theoretical.

DISTRIBUTION

1. G. M. Adamson, Jr.
2. R. E. Blanco
3. E. S. Bomar
4. J. C. Bresee
5. K. B. Brown
6. F. R. Bruce
- 7-8. R. A. Charpie
9. S. D. Clinton
10. F. L. Culler
11. O. C. Dean
12. W. K. Eister
13. W. S. Ernst, Jr.
14. D. E. Ferguson
15. J. H. Frye
16. H. E. Goeller
17. A. T. Gresky
18. P. A. Haas
- 19-21. J. P. Hammond
22. A. T. Kleinsteinuber
23. K. H. McCorkle
24. W. D. Manly
25. C. E. Schilling
26. M. J. Skinner
27. J. W. Snider
28. J. A. Swartout
29. M. E. Whatley
30. C. E. Winters
- 31-40. Laboratory Records
41. Laboratory Records-RC

EXTERNAL

42. L. P. Bupp, GE, Hanford
43. J. J. Cadwell, GE, Hanford
- 44-45. D. F. Cope, AEC, Reactor Div., Oak Ridge
- 46-55. J. M. Simmons, AEC-DRD, Washington, D.C.
56. J. W. Morris, Savannah River