LEGAL NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Atomic Energy Commission, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

GEAP-13539-15
AEC Research and
Development Report
December 1970

SODIUM TECHNOLOGY DEVELOPMENT PROGRAM
MASS TRANSFER INVESTIGATIONS IN LIQUID METAL SYSTEMS

QUARTERLY PROGRESS REPORT NO. 15
SEPTEMBER 1970 - NOVEMBER 1970

Approved:

G. D. Collins, Project Engineer
Sodium Mass Transfer Program

Approved:

E. L. Zebroski, Manager
Development Engineering Section

Prepared for the
United States Atomic Energy Commission
Contract No. AT(04-3)-189
Project Agreement 15

Printed in U. S. A. Available from the
Clearing House for Federal Scientific and Technical Information
National Bureau of Standards, U. S. Department of Commerce
Springfield, Virginia
Price: \$3.00 per copy

BREEDER REACTOR DEVELOPMENT OPERATION • GENERAL ELECTRIC COMPANY
SUNNYVALE, CALIFORNIA 94086

6208-Dev. Eng.-41
175-ACG-1/71

GENERAL ELECTRIC

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or*
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.*

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

TABLE OF CONTENTS

1.	Introduction	1-1
1.1	Technical Highlights	1-1
1.2	Program Description and Background	1-1
1.3	Summary of Task Objectives	1-2
2.	Task I: Corrosion—Deposition Studies	2-1
2.1	General	2-1
2.2	Operation of Test Facilities	2-1
2.3	Task I-1: Oxygen Control Tests and Cleanup Rate Study	2-1
2.4	Task I-2: Radioisotope Transport and Measurement Scoping Tests	2-1
2.5	Task I-3: Radioactivity Buildup in Primary Coolant System	2-3
2.6	Task I-4: Effect of High Oxygen Concentration on Corrosion and Mass Transfer	2-3
2.7	Task I-5: Study of Particulates in Flowing Sodium	2-4
2.8	Task I-6: Large System Velocity Profile Effects on Local Corrosion Rate	2-4
2.9	Task I-7: Corrosion—Deposition Under Controlled Temperature Profiles	2-6
2.10	Task I-8: Analytical Predictions of Radioactivity Buildup Using Existing Data	2-6
3.	Task II: Surveillance and Analysis of Impurities in Sodium	3-1
3.1	Task II-1: Surveillance of Oxygen Level by On-Line Instruments	3-1
3.2	Task II-2: Hydrogen—Oxygen Interaction Study	3-4
3.3	Task II-3: Chemical Analysis of Surveillance Samples	3-8
3.4	Task II-4: Particulate Analysis	3-12
4.	Task IV: Effects of Sodium on Structure, Composition, and Integrity of LMFBR Cladding	4-1
5.	List of Sodium Mass Transfer Project Reports	5-1
	List of Contributors	1
	Distribution List PA-15	2

LIST OF ILLUSTRATIONS

Figure	Title	Page
3-1	FFTF Closed Loop Corrosion Mock-Up of Loop 9	3-3
3-2	Response of Loop 9 Air Reference O ₂ Meter to Oxygen Additions	3-5
3-3	Cold Trap Temperature Controller	3-6
3-4	Schematic: Cold Trap Temperature Controller	3-7
3-5	Calibration Curve for 316 SS Diffusion Membrane (0.021 in.) Hydrogen Detector at 1000° F Sodium Temperature	3-9
3-6	Temperature Dependence of Diffusion Membrane Hydrogen Detector	3-10
3-7	Theoretical Curves as a Function of Sodium Temperature for Oxygen Meter (Air Reference Electrode)	3-11
4-1	Biaxial Stress-Rupture Properties in Type 316 Stainless Steel in Sodium and Argon	4-5
4-2	Biaxial Stress-Rupture Properties of Type 304 Stainless Steel in Sodium and Argon	4-6
4-3	1300° F Biaxial Stress-Rupture Properties of Type 304 Stainless Steel in Argon	4-7
4-4	1300° F Biaxial Stress-Rupture Properties of Type 316 Stainless Steel in Argon	4-8
4-5	1300° F Biaxial Stress-Rupture Properties of Type 321 Stainless Steel in Argon	4-9
4-6	1300° F Biaxial Stress-Rupture Properties of Type 347 Stainless Steel in Argon	4-10
4-7	1300° F Biaxial Stress-Rupture Properties of Incoloy-800 in Argon	4-11

LIST OF TABLES

Table	Title	Page
2-1	Summary of Loop Operations	2-2
2-2	Stainless Steel Surface Cleanup Test - Loop 3R	2-5
3-1	Determination of Total Alkalinity Data Corrected for Hydride and Carbonate	3-2
3-2	Total Alkaline Impurities in Loop Sodium	3-2
3-3	History of Loop 1R Filters	3-13
3-4	Loop 1R Filter History	3-14
4-1	1300° F Biaxial Stress Rupture Data from Run 4R-2	4-1
4-2	1300° F Biaxial Stress Rupture Data from Run 5R-5	4-2
4-3	1150° F Biaxial Stress Rupture Data from Run 6R-4	4-2
4-4	1300° F Biaxial Stress Rupture Data in Argon	4-3
4-5	Carbon Stability in Austenitic Steels in Sodium	4-4

1. INTRODUCTION AND SUMMARY

1.1 TECHNICAL HIGHLIGHTS

- **Chemical Analysis**

An improved amalgamation method procedure for analysis of sodium determines the Na_2CO_3 and NaH impurities, separately. With the further discrimination of NaOH, an accurate and reliable method for determination of oxygen activity in sodium will be attained. (II-1)

- **Deposition and Particulates**

Particulates filtered from main stream loop flow sodium with high oxygen (20 ppm) are different in color and lower in density than particles from sodium with low oxygen. Properties and behavior of corrosion product particulates are being determined with a view to possible control of local deposition rates of corrosion products and the associated radioactivity in primary systems. (II-4)

- **Oxygen Cleanup of Fresh Stainless Steel Surfaces**

Quantitative measurements of the oxygen removed from new 316 SS surfaces were extended from 600°F to 1000°F. Additional oxygen was removed with each step increase in temperature. These data are useful for the design and programming of startup operations for purification systems for loops and capsules. (I-1)

- **Hydrogen Meter Based on Ion Gauge**

The stainless steel diffusion tube sensor for hydrogen using ion gauge readout has been calibrated at 800°F and 1000°F. Adequate sensitivity (< 1 ppm) and precision are attainable at 800°F. This simple and rugged sensor appears generally useful and reliable for hydrogen measurement in primary and secondary systems. (II-2)

- **Lifetime Test - Electrochemical Oxygen Meter**

The ceramic tube of a UNC oxygen meter cracked at normal steady state conditions after 7500 hours of operation in 600°F sodium. Visual evidence of some attack on the ceramic was observed. (II-1)

- **High Precision Cold Trap Control**

An improved control system for cold trap temperatures has demonstrated control to $\pm 2^\circ\text{F}$ during 1200 hours of on-line operation. This is expected to provide more accurate control and more constant levels of oxygen and other dissolved impurities for loop operation. (II-1)

- **Hydrogen—Oxygen Interaction**

The interaction test apparatus attained regular operation with the sodium gettered by uranium foil for the calibration of on-line meters. (II-2)

- **Long-Time Stress Rupture Test Completion**

The stress rupture data in Loop 4R have passed 14,000 hours with one specimen remaining. The operation of the loop will be terminated at the end of the present run. (IV-1)

- **Comparative Carbon Analyses**

Identical samples of sodium analyzed for carbon by WADCO, EBR-II and GE disclosed a severe discrepancy in the results. (II-3)

1.2 PROGRAM DESCRIPTION AND BACKGROUND

Corrosion of candidate structural materials, the influence of corrosion and of impurities in the sodium on engineering properties of materials, and corrosion and deposition of radioactive isotopes from the core cladding are being studied in test loops designed to simulate typical conditions of sodium cooled reactors. The program is designed to obtain out-of-pile test data that will (when used in conjunction with irradiation data) support engineering design selections and lead to the establishment of specifications for the monitoring and control of impurities in large plants.

Current work is directed to the near-term requirements for data and the development of sodium technology for application to FFTF and LMFBR demonstration plant designs. Emphasis is placed on deposition studies, design data for materials performance, the associated requirements and methods for plant chemistry control, and data on the transport and buildup of radioactive isotopes.

Work initiated during the quarter includes the preparations for experimental determination of corrosion release rates of long-lived radioactive isotopes from the core regions of FTR and LMFBR and their deposition patterns in the piping and other components in the cold leg of the primary sodium system. Emphasis is placed on development of a calculational model, based on accurate experimental data, for predicting the buildup of radioactivity in the primary coolant system of large sodium cooled reactors.

In an earlier 6-year phase of the program, ending in 1965, corrosion and mass transfer of Type 316 stainless steel and 2% Cr-1 Mo and 5 Cr- $\frac{1}{2}$ Mo- $\frac{1}{2}$ Ti ferritic steels were studied at sodium temperatures to 1200°F. Average corrosion rates were correlated by statistical analysis from which quantitative relations were derived.

In the current phase of the program, the number of materials studied has been extended to include cladding candidates for oxide fuel (Types 304, 316 and 347 stainless steels and Incoloy 800). The temperature range of testing has been increased to 1300°F, and temperature profiles, loop geometry, and sodium purity controls have been established to better represent environments of large fast reactors.

Increasing emphasis has been placed on improving sodium impurity monitoring and control. In-line devices are used to obtain rapid and, where possible, continuous indications of impurity changes. These include chromatography for cover gas, replaceable flow-through sodium samplers, electrochemical cells for oxygen activity, diffusion cells for hydrogen concentration in sodium and on-line distillation. Provisions were begun for eventual use of electrochemical cells for carbon.

Cold traps for control of sodium purity in test loops have been modified with electromagnetic stirring devices to increase cleanup rate and automatic controls have been added for continuous and unattended operation with an accuracy of $\pm 2^\circ\text{F}$.

1.3 SUMMARY OF TASK OBJECTIVES

The Sodium Mass Transfer Program is organized into five tasks* of which three are currently active. These three tasks have the following objectives:

Task I — Corrosion—Deposition Studies

The continuous improvement of empirical and rational models for the accurate prediction of corrosion and mass transport in the primary and secondary sodium systems of large plants. This task is organized in eight subtasks which include experimental determination of corrosion rates and deposition patterns of stainless steel corrosion products as a function of temperature, velocity, and the chemical composition of the sodium, as well as geometric and hydrodynamic factors. A further objective of this task is the development of calculational models to predict the release, transport, and deposition of radioactive isotopes from the core regions of FTR and LMFBR and the consequent buildup of long-lived radioactivity in primary coolant system piping and components.

Task II — Surveillance and Analysis of Impurities in Sodium

The development of improved methods for sampling of sodium systems, impurity monitoring, collection and identification of particulate material, and chemical and structural analysis. An operating objective is to provide well-controlled operation of loops and to support the development of rational models.

Task IV — Corrosion and Mass Transport Effects on Composition, Structure and Structural Integrity of Candidate Alloys for LMFBRs

The determination of the relation between mass transfer and sodium impurities and the long term stress rupture properties of specific LMFBR candidate materials, including Types 304 and 316 stainless steel tubing.

*Quarterly Report No. 11 includes a description of all five tasks.

2. TASK I: CORROSION-DEPOSITION STUDIES

2.1 GENERAL

Current work is directed toward:

- The experimental study of the corrosion rates, transport, mechanisms and deposition of corrosion products of Types 304 and 316 stainless steel in pumped sodium systems at top temperatures of 1150°F and 1300°F, and the specification of corrosion allowances appropriate for large plant design criteria.
- The experimental and analytical study of corrosion rates and transport of activated corrosion products from cladding and the prediction of radioactive buildup factors which describe their deposition in the primary system and its components (plant maintenance and shielding criteria).
- The understanding of the mechanisms of corrosion, mass transport, and deposition including boundary layer phenomena and fluid dynamic parameters typical of sodium coolant systems in large reactors.

2.2 OPERATION OF TEST FACILITIES

The experimental work is conducted in seven test loops designed to simulate corrosion conditions in the primary coolant system of a typical FTR and LMFBR. A summary of operations is shown in Table 2-1. Two loops, 1R and 8, were operated at a high oxygen level (20 ppm) controlled by a cold trap operated at 432°F and which was precharged with anhydrous Na₂O.

2.3 TASK I-1: OXYGEN CONTROL TESTS AND CLEANUP RATE STUDY (D. N. Rodgers)

Objective:

The objective of this task is to investigate the effects of low cold trap throughput rates on oxygen control and on system cleanup rates.

Technical Summary:

Earlier data have been obtained from small loops operated at relatively high cold trap throughput, from 50 to a few hundred system turnovers per day. In Run 9-2A, data will be obtained at (cold trap) throughput rates simulating large primary systems, that is on the order of one system turnover per day. Cleanup times and equilibrium sodium oxide impurity levels will be related to expected corrosion using existing corrosion data.

Operations:

Test Run 9-2A, started in October, has produced data which are currently being analyzed. Results will be reported in the next period. The tests in Loop 9 were interrupted by failure of the ceramic electrolyte tube of the air reference electrochemical oxygen cell. New ceramic tubes are being prepared for installation and tests will be resumed early in December. Results of tests to measure amounts and rates of cleanup of a new stainless steel system at high cold trap turnover rates are reported under Task I-6.

2.4 TASK I-2: RADIOISOTOPE TRANSPORT AND MEASUREMENT SCOPING TESTS (J. S. Armijo)

Objective:

This task is to establish the feasibility and sensitivity of practical techniques for measuring corrosion and deposition rates for those corrosion products which have been activated in the core and transported and deposited elsewhere in the primary coolant system of a large fast reactor. The initial test is being designed to provide a preliminary determination of ratios of in-core activated ⁶⁰Co depositing in FFTF core exit regions compared to the amounts depositing outside the reactor vessel.

Table 2-1

SUMMARY OF LOOP OPERATIONS

	Temp (°F)	ΔT (°F)	Flow (gpm)	CT* (°F)	Time (Hours)
Run 8-6	1300	400	5.0	432	2,000
Cumulative, Run 8-6					1,024
Three-Month Operation of the Loop					1,584
Total Loop Age					27,059
Run 9-2A	1300	500	5.0	425	~4,000
Cumulative, Run 9-2A					6,813
Three-Month Operation of the Loop					2,012
Total Loop Age					22,375
Run 1R-3	1300	800	2.0	432	2,000
Cumulative, Run 1R-3					2,172
Three-Month Operation of the Loop					1,900
Total Loop Age					8,498
Run 3R-1	1300	800	0.3	270	500
Cumulative, Run 3R-1					24
Three-Month Operation of the Loop					481
Total Loop Age					665
Run 4R-2	1300	500	7.0	<300	10,000
Cumulative, Run 4R-2					
Comparative Corrosion Test					15,150
Stress-Rupture Test					14,672
Three-Month Operation of the Loop					2,016
Total Loop Age					17,052
Run 5R-5	1300	500	10.0	<300	5,000
Cumulative, Run 5R-5					
Comparative Corrosion Test					6,779
Stress-Rupture Test					6,472
Three-Month Operation of the Loop					2,016
Total Loop Age					22,228
Run 6R-4	1150	400	7.0	<300	10,000
Cumulative, Run 6R-4					
Comparative Corrosion Test					8,929
Stress-Rupture Test					8,571
Three-Month Operation of the Loop					1,545
Total Loop Age					17,424

*CT – Temperature of on-line cold trap.

Technical Summary:

Prior tests at BNWL* indicated that most of the ^{60}Co released into the sodium from core cladding would deposit in the core exit regions of the fission gas plenum and axial reflector. The Sodium Mass Transfer program data on nickel (which is chemically very similar to cobalt) would predict that cobalt will deposit in the Intermediate Heat Exchanger and other components of the primary coolant system. This task has been initiated to resolve this discrepancy as well as to establish bases for the design and performance of tests to determine rates of radioactive buildup outside the reactor vessel.

In spite of the chemical similarity between nickel and cobalt, prediction of cobalt transport based on measurements of nickel movement is ultimately not adequate because the two metals are not identical. Furthermore, it is necessary to establish that the cobalt which deposits outside the reactor vessel, if any, is one or more of the radioactive isotopes rather than nonradioactive cobalt released from outside the core area by some displacement or exchange mechanism with the activated products from core cladding.

Operations:

New experiments were planned during the quarter to study the movement of cobalt using radioactive tracers of ^{60}Co . Activated specimens will be placed on a tubular heater, which may be energized to simulate corrosion product release rates from core cladding. A test section containing sample coupons following the heated zone will simulate conditions of the core fuel plenum and axial reflector.

The tests will be conducted in Loop 9 at temperatures representative of the "design" basis FTR core. Migration of the ^{60}Co will be monitored on-line by portable detectors. After completion of the first run, both corrosion and deposition samples will be removed and radioactivity levels will be measured directly. The sample modifications are now in progress.

2.5 TASK I-3. RADIOACTIVITY BUILDUP IN PRIMARY COOLANT SYSTEM (J. S. Armijo)**Objective:**

The objective of this task is to obtain quantitative data on the concentration in the sodium, the rate of corrosion and the distribution of deposition of long-lived radioactive materials. These data will provide a basis for the prediction of radioactivity levels in FTR and LMFBR primary coolant system piping and components pertinent to verification of plant maintenance design criteria. Particular emphasis is placed on ^{60}Co and ^{54}Mn in tests simulating FTR conditions. Experimental techniques to be used will be based on results from Task I-2.

Operations:

The task is in a preliminary planning stage pending results from Task I-2.

2.6 TASK I-4: EFFECT OF HIGH OXYGEN CONCENTRATION ON CORROSION AND MASS TRANSFER (P. Roy)**Objective:**

This task is to determine corrosion data and also movement of interstitials such as carbon, silicon, nitrogen, etc., at relatively high oxygen levels (~20 ppm) and to obtain additional information about the chemistry of the high oxygen system.

Status:

The experimental work is in progress in Loop 8, Run 8-6, which completed 1000 of its planned 2000 hours during the period. The oxygen level is being controlled by operating a cold trap continuously at 432°F to control oxygen concentration at a value of 20 ppm, according to the Eichelberger solubility correlations. The cold trap was initially clean and charged with anhydrous Na_2O for Run 8-6.

*W. F. Brehm, et al., Radioactive Material Transport in Flowing Sodium System, Corrosion by Liquid Metals 97, Plenum Press, New York, 1970.

Operations:

During preparations for the run an auxiliary heater was fabricated and installed ahead of the main heater to allow the loop to operate at the planned test conditions, which have been maintained since the last week of September.

Sodium chemistry is being monitored by a combination of methods; both on-line and laboratory backup. On-line instruments are plugging meter, vacuum distillation, UNC electrochemical oxygen meter, and recirculating gas chromatograph. Laboratory analyses (on flow through samples) are by amalgamation. Results of lab analyses are reported in Task II-3, and continue to show evidence of oxygen segregation during cooling.

The original UNC oxygen meter cell failed after 7500 hours of operation, but has been replaced by another cell. Further reports of oxygen meter performance and calibration are reported in Task II-1.

2.7 TASK I-5: STUDY OF PARTICULATES IN FLOWING SODIUM (P. Roy)

The objective of this task is to study the shape, composition, and distribution of particles in flowing sodium. The data will provide a basis for the prediction of local deposition and estimates of radioactivity levels to be expected in reactor components.

The work related to this task during this quarter is reported under Task II-4.

2.8 TASK I-6: LARGE SYSTEM VELOCITY PROFILE EFFECTS ON LOCAL CORROSION RATE (P. Roy)**Objective:**

To determine corrosion rates in a small loop system at the thin boundary layer conditions and turbulence which are associated with sodium coolant systems operating at high Reynolds number (such as those in a large plant), and to investigate the transition to turbulent flow which occurs at such obstacles as fuel pin spacers in the core.

Technical Summary:

Most published data on corrosion rates cite sodium velocity as a primary parameter, but the extrapolation to the design of large plants must recognize the strong relationship of corrosion rate (and deposition) to fluid boundary layer thickness. Fully developed stream-line flow such as in small diameter piping and fuel channels results in a relatively thick fluid boundary layer and is characterized by low Reynolds number. Highly turbulent flow such as in large pipes and abrupt changes in flow channel geometry, such as fuel pin and IHX tube supports, results in a thin fluid boundary layer characterized by high Reynolds number.

The meager published data on deposition include observations that deposition occurs at points of sharp increases in velocity, usually accompanied by increased turbulence and decreased boundary layer thickness. Therefore, corrosion and deposition data correlated as a function of average velocity alone, are inadequate. Detailed information on geometry, local velocities and turbulence are necessary for accurate estimates of deposition rates.

An experiment in Loop 3R (Run 3R-1), designed to measure corrosion rates over a range of controlled boundary layer conditions, was started in November. The variation in boundary layer is attained by rotating a sodium agitator to produce velocities and turbulence levels of interest (large system simulation) at the stationary specimen surfaces.

A series of tests is planned with the agitators, each test running a few hundred hours, to measure the effect of high Reynolds number on corrosion rates. The first of these tests will be run at conditions overlapping existing data from in-pipe annular samples so that a firm basis will be laid for higher Reynolds number tests to follow. In addition the loop sodium inventory has been minimized by design in the hope of eventually accomplishing precise oxygen activity additions by use of an electrochemical oxygen cell operated at reverse polarity. A second oxygen cell monitors oxygen activity. Oxygen removal is by cold trap.

Operations:

Measurements have been made to determine the amount of oxygen released into sodium from fresh 316 stainless steel surfaces during the startup of a new system. This was done during initial filling and startup by monitoring changes in the oxygen content of the sodium with an air-reference oxygen meter (uncalibrated) and a plugging meter. A second part of the test consisted of monitoring changes in the oxygen concentration as the temperature of the sodium was increased to new high levels for the first time.

The results of the first part of the test showed an average of 30 mg/M² removed from the new surfaces at ~600°F. This value compares quite well with Ivanovskii's¹ value of 50 mg/M² (see Table 2-2).

Additional oxygen was found to be removed from the loop surfaces when the temperature was raised from 825°F to 988°F and again when raised from 988°F to 1087°F. The amounts measured were 47 and 14 mg/M², respectively. The measurements were made with an air reference oxygen meter. The total oxygen removal up to 1000°F was 90 mg/M² obtained by adding the amounts from the three temperature intervals. The experimental results are presented in Table 2-2.

Run 3R-1 (corrosion) was interrupted by a leak of cover gas at 850°F from the flange which seals the agitator and drive motor to the test vessel. A flange modification successfully stopped the leakage and the seal was reestablished at 1200°F. After a change of agitator bearings, the run will be resumed.

Table 2-2

STAINLESS STEEL SURFACE CLEANUP TEST - LOOP 3R**Part I - Exposure of Fresh Surfaces at 600°F³**

Source of Oxide	Method of Measurement	Area M ²	Surface Temp. °F	Oxygen Change ppm	Equivalent Film mg/M ²
Fixture†	O ₂ meter	0.94	620	0.7	4
Fixture	PI run*	0.94	620	10.0	58
Cold Trap Mesh	O ₂ meter	1.07	570	5.5	28
Ivanovskii ¹		not reported			50

†Fresh stainless steel foil

*Eichelberger's² solubility curve used to evaluate PI run.

Part II - Increasing Sodium Temperature

Surface Temperature of Test Vessel, °F		Hours at Upper Temp.	Oxygen Change ppm	Equivalent Film mg/M ²
Initial	Final			
825	988*	3	2.2	47
988	1087	18	0.7	14

*The test was delayed at this point due to a flange leak. The loop was restarted and cold trapped before obtaining the final measurement.

1. Ivanovskii, M. N., et al., "The State and Distribution, Monitoring, and Elimination of Impurities in Circulating Alkali Metal Coolants," IAEA Symposium, Vienna, December 1966.
2. Eichelberger, R. L., AI-AEC-12685, November 1968.
3. Quarterly Report No. 14 (PA-15), GEAP-13539-14, September 1970.

2.9 TASK I-7: CORROSION-DEPOSITION UNDER CONTROLLED TEMPERATURE PROFILES (M. K. Schad)

Objectives:

- To separate the effects of hydraulic conditions and temperature gradient on the release and transport of activated corrosion products in a circulating ΔT loop with controlled temperature profiles.
- To determine the distribution patterns of alloying and interstitial elements in cold leg temperature patterns simulating FTR core and FFTF Closed Loop conditions.

Technical Summary:

Preliminary design of a loop capable of simulating a variety of proposed FTR hydraulic conditions and temperature profiles has been completed. Some modification of the design is needed for on-line monitoring of radioactive transport. After the preliminary radio-tracer scoping studies (Task I-2), the loop design will be modified.

Operations:

A preliminary design of this loop was reported in the 14th Quarterly Report. Activity in this period was confined to preliminary planning. Results from the radioactive tracer scoping tests (I-2) will provide guidance for extension of design work on Loop 2R.

2.10 TASK I-8: ANALYTICAL PREDICTIONS OF RADIOACTIVITY BUILDUP USING EXISTING DATA (J. S. Armijo)

Objective:

The objective of this task is to update and improve analyses of radioactive materials transport in LMFBR systems. Emphasis will be placed on the calculation of expected radiation levels of key plant components in service and during possible maintenance periods.

Technical Summary:

The first draft of an analysis of release and transport of radioactive isotopes from the FTR core has been completed and an estimate of deposition, distribution and the buildup of radioactivity will be made.

Existing corrosion and deposition data correlations have been used to predict radiation levels in the FTR primary coolant system and its components. The effects of oxygen level, temperature, velocity, and temperature gradient patterns from tests in the mass transfer loops were factored into models for the analytical predictions of source, transport, and deposition in FTR.

A major result of this study is that contact maintenance of the FTR primary system and its components will be seriously limited because of radioactive isotope deposition and radioactivity levels built up. Radiation levels at 3 feet from the IHX of the FFTF are estimated at 0.1 to 0.7 R/hr.

3. TASK II: SURVEILLANCE AND ANALYSIS OF IMPURITIES IN SODIUM

3.1 TASK II-1: SURVEILLANCE OF OXYGEN LEVEL BY ON-LINE INSTRUMENTS (D. Dutina)

Objective:

To monitor oxygen level in the mass transfer loops using a combination of on-line devices and techniques to achieve control of oxygen level within ± 2 ppm.

Technical Summary:

The work in this task includes oxygen monitoring by on-line electrochemical cells, on-line distillation, cold trap temperature control, vanadium wire equilibration, and chemical analysis of on-line samples by amalgamation analysis. A part of the work is the improvement of the reliability of the electrochemical oxygen cells by monitoring their performance, tabulating their behavior in operation, evaluating attempts to calibrate the cells by the combination of techniques mentioned above, and utilizing applicable new technology which may be developed. Work in Task II-2 will provide additional direction for this work.

Operations:

Laboratory effort during this quarter has involved the following items:

a. Calibration by Vanadium Wires

The Argonne National Laboratory has agreed to provide wires and to carry out a limited number of post exposure analyses. No handling problems are anticipated in the event of deposition of minor amounts of radioactivity on the samples, a possible consequence of exposure in Loop 9. Initial steps have been taken to delineate loop positions in which the wires could be inserted.

b. Calibration by Amalgamation

Initial work has been carried out modifying the amalgamation procedure for total alkalinity to correct for the presence of residual sodium hydride and sodium carbonate. The procedure will also permit analysis for hydride hydrogen and for carbonate on a single sample. The method involves (1) in-box amalgamation under vacuum; (2) removal of the vessel to a vacuum system after amalgamation is complete for determination of hydrogen; (3) addition of water followed by determination of hydrogen, i.e., that evolved from undecomposed hydride; (4) addition of dilute acid followed by analysis of gases released, i.e., those resulting from decomposition of carbonate; (5) analysis of the acidified sample for total sodium. The data from steps (2) and (3) give the amount of total hydride. The data from step (4) give the carbonate present. The data from steps (3) and (4) permit correction of the total alkalinity value (data from step 5) for undecomposed hydride and carbonate. The corrected value reflects only Na_2O and NaOH in the samples.

Initial data obtained on two loop samples are shown in Table 3-1.

The data for the new method on a typical loop sample, cold trap 270°F , is quite encouraging in that the total alkalinity obtained through the extensive steps required for species separation is in good agreement with that obtained by the standard amalgamation method. A similar comparison for the high oxygen sample has not been possible because of the large scatter in these data (see Table 3-2). Further encouragement is gained from the fact that the amounts of total hydrogen and carbon present as carbonate obtained by this technique are in the expected range based on separate analyses for these species (see Table 3-1). Some methane was also observed. A final encouragement for continued effort is that the corrected total alkalinity value is closer to the values based on cold trap temperature.

To calibrate the air reference type oxygen meter, 43 ppm of oxygen gas, as 1 percent oxygen in an argon carrier, were added to Loop 9 through a 1/4-inch-diameter tube projecting into the sodium in the cold leg surge tank* (for drawing of Loop 9, see Figure 3-1). The air-reference electrode type oxygen meter showed a linear response during the addition of the

*Isaacs, H. S., Minushkin, Salzano, ANL 7520, Part I, pp. 460-464, November 1968.

Table 3-1

DETERMINATION OF TOTAL ALKALITY*
DATA CORRECTED FOR HYDRIDE AND CARBONATE

Sample No.	4R-2-20A	1R-3-1A
Cold Trap Temperature, °F	270	430
Total Alkalinity (Standard Method), ppm	13	-- **
By Specific Technique		
(a) Alkalinity from Na ₂ CO ₃ , ppm	4.5	5
(b) Alkalinity from NaH, ppm	5.0	12
(c) Alkalinity from Na ₂ O + NaOH, ppm	4.0	***12
(d) Total Alkalinity	13.5	29

*Alkalinity in all cases is calculated as Na₂O

**Large scatter in data

(see Table 3) no comparison possible

***By difference d - (a + b)

Hydride and Carbonate Values by Amalgamation

Sample No.	4R-2-20A	1R-3-1A
Carbon as Carbonate, ppm	3.5	3.8
Hydrogen as Hydride, ppm	3.0	4.0

Table 3-2

TOTAL ALKALINE IMPURITIES IN LOOP SODIUM
(Flow-Through Samples - Amalgamation Determination)

Sample No.	Date Taken	Cold Trap Temperature °F	Total Alkalinity (ppm)
1R-3-1A	8/18/70	432	64, 45, 30
1R-3-2A	8/26/70	432	29, 23, 9, 22
8-6-16A	10/9/70	432	100, 25
8-6-17A	10/16/70	432	49
1R-3-3A	9/10/70	270	44
1R-3-4A	10/2/70	270	10
1R-3-5A	10/7/70	270	21
4R-2-18A	4/16/70	270	11
4R-2-20A	5/22/70	270	13
4R-2-21A	6/10/70	270	12
4R-2-23A	8/14/70	270	13
4R-2-24A	8/27/70	270	16
4R-2-25A	9/9/70	270	9
4R-2-26A	10/7/70	270	8
5R-5-10A	7/16/70	270	15
5R-5-11A	8/13/70	270	16
5R-5-12A	8/27/70	270	12
5R-5-13A	9/9/70	270	17
6R-14-14A	8/12/70	270	77

Figure 3-1. FFTF Closed Loop Corrosion Mock-Up of Loop 9

first 12 ppm but during the addition of the last 31 ppm the output voltage was uninterpretable (see Figure 3-2). Above 12 ppm the cell voltage varied at random between the 12 ppm value and a line extrapolated from the linear range below 12 ppm. The reason for the abrupt departure from linearity at 12 ppm is not known, and although a few points up to 35 ppm did fall in line, the majority of points between 12 and 43 ppm gave outputs within a ± 25 millivolt band. This indicates the possibility of either a saturation effect in the oxygen meter or a buffering, or storage action, for oxygen on the piping walls* or elsewhere in the cold leg of the loop.

The calibration based upon the data below 12 ppm in Figure 3-2 gave implausibly high indications of oxygen level during subsequent cold trapping cleanup runs, and was therefore considered to be inaccurate. Both stirred and unstirred cold trap operations were employed in the test, and the meter responded during the stirred mode operation, but not during standard unstirred cold trap operation. Subsequent operation at 800°F, compared to a normal 700-740°F range for the air reference cell, did not help resolve the anomaly. Finally the ceramic electrolyte tube cracked after 1500 hours of operation, without positive clues as to when the ceramic deterioration might have begun. Further calibration will be undertaken when the replacement tube is installed.

Loop 8 — UNC oxygen meter - Cu/Cu₂O reference electrode.

After 7500 hours of operation at a controlled operating temperature of 600°F, the ceramic electrolyte tube broke. During its long time in Loop 8 its operation had been characterized by good stability, but with a calibration shift during loop shutdown between runs. The break occurred during a restart operation but since several similar prior restarts had been performed without difficulty the failure is thought to have been caused by cumulative chemical attack on the ceramic as evidenced by visual inspection.

A new UNC meter has been installed and is operating satisfactorily.

New, improved cold trap temperature control systems (see Figures 3-3 and 3-4) have been placed in operation on Loops 1R and 8. The capabilities of the equipment and its description were covered in Quarterly Progress Report No. 13.

Since October 6, 1970 this new control system has been maintaining cold trap temperature at 432°F $\pm 2^\circ$ in Loop 1R for a total of ~ 1200 hours. Since October 10, 1970 the new system has maintained the cold trap temperature at 432°F $\pm 2^\circ$ in Loop 8 for a total of ~ 1225 hours.

3.2 TASK II-2: HYDROGEN—OXYGEN INTERACTION STUDY (P. Roy)

Objective:

The objectives of this task are as follows:

- Calibration of the air reference and UNC oxygen cells.
- Calibration of hydrogen detectors (diffusion type).
- Measurements of the effect of hydrogen on activity of oxygen and vice versa.
- Study of the cold trap cleanup rates of oxygen and hydrogen from sodium systems.
- Interpretation of plugging temperatures in presence and absence of hydrogen contamination in sodium.

*Isaacs, H. S., Minushkin, Salzano, ANL 7520, Part I, pp.460—464, November 1968.

Figure 3-2. Response of Loop 9 Air Reference O₂ Meter to Oxygen Additions

Figure 3-3. Cold Trap Temperature Controller

Figure 3-4. Schematic: Cold Trap Temperature Controller

Technical Summary:

To meet the above objectives, tests are being carried out at present in two test facilities, under static and dynamic conditions. The calibration of a stainless steel tube (20 mil wall thickness) for hydrogen permeation has been completed. Figure 3-5 shows the calibration curve for hydrogen as a function of the sputter pump current (at a sensor temperature of 1000°F). The hydrogen concentration in the sodium was maintained by changing the cold trap temperatures and by using APDA solubility data. A second set of calibration curves was obtained after an interval of about 1 month.

Operations:

Preliminary comparison indicates that there has been a significant change in the calibration of the meter after 1 month of operation. The temperature dependence of hydrogen permeation was also determined during this period as shown in Figure 3-6. The activation energy obtained during this experiment was found to be 13.5 K.Cal. This value is in close agreement with the values available in the literature for the activation energy for diffusion of hydrogen through stainless steel.* This observation implies that diffusion of hydrogen through the stainless steel is the rate controlling step, and that the partial pressure of hydrogen (below saturation) is independent of temperature.

Further progress in the hydrogen-oxygen interaction studies has been made with the isothermal (stirred) pot. The 13th Quarterly Report described the test equipment. During the current reporting period, the entire system has been made operational, i.e., electrical and gas systems have been connected; sodium lines and vapor traps blown out; leak checking completed; the gas chromatograph calibrated; background readings for the vac-ion pump and residual gas analyzer have been obtained; the oxygen meter cell installed; the stirring motor activated and the uranium lowering device tested.

The system has been brought to a temperature of 800°F and the oxygen was gettered by uranium foil to a constant level as indicated by the oxygen meter. The oxygen cell was fabricated by General Electric and is of the air-reference variety. The cell has been in operation about 700 hours in this quarter. The theoretical response is shown in Figure 3-7 and is based on the solubility data of Eichelberger. Oxygen activity has fallen from a start-up value of 1.690V (70 ppm) to an equilibrium value of 1.815V (1 ppm). Oxygen dissolved in liquid sodium in equilibrium with uranium metal should be below 0.1 ppm. The present data indicate that due to the short period of uranium gettering the equilibrium oxygen concentration was not attained. The other possibility is that calculation of the theoretical voltage based on solubility data may not be valid at low oxygen levels. Finally, it is very likely that electronic conductivity of the cell at very low oxygen activities may be sufficient, so that cell voltage will deviate from the theoretical calculations. The response time and reproducibility of the system were measured by the addition of a small amount of oxygen. The activity of oxygen increased immediately and in 3 minutes reached a low meter reading of 1.765 volts. After 10 hours of gettering, the oxygen meter output reattained the voltage (1.815V) prior to oxygen addition.

An unexpected observation is that equilibrium values are different in stirred and unstirred modes of operation—higher activity value for the unstirred mode. The unstirred mode indicates a slightly lower voltage (higher oxygen activity) than the stirred mode. The reason for this is being investigated but may be associated with boundary layer effects, ceramic surface enrichment by oxygen transferred electrolytically, or a buffering effect on the walls of the vessel.

Steady values have also been obtained for the hydrogen in the cover gas (2 ± 2 ppm hydrogen in argon) for the vac-ion pump current and for the residual gas analyzer readings.

3.3 TASK II-3: CHEMICAL ANALYSIS OF SURVEILLANCE SAMPLES (D. Dutina)**Objective:**

To provide surveillance at appropriate intervals on the purity of sodium and cover gas samples from the operating loops.

*Webb, R. W., *Permeation of Hydrogen Through Metals*, NAA-SR-10462, July 25, 1965.

Figure 3-5. Calibration Curve for 316 SS Diffusion Membrane (0.021 in.) Hydrogen Detector at 1000° F Sodium Temperature

Figure 3-6. Temperature Dependence of Diffusion Membrane Hydrogen Detector

Figure 3-7. Theoretical Curves as a Function of Sodium Temperature for Oxygen Meter (Air Reference Electrode)

Technical Summary:

The principal emphasis of the work of this task is on chemical analysis of flow-through on-line samples from the mass transfer loops which complement on-line plugging meters and controlled cold trap temperatures.

Operations:

1. Total Alkalinity

Table 3-2 shows the results of analyses made during the quarter on samples from loops indicated.

The data from Loops 4R, 5R, and 6R are in the usual range for loop operation at cold trap temperature of about 270°F.

Both Loop 1R and Loop 8 are being run at cold trap temperatures of 432°F. The data for these samples show low precision both among samples and within a single sample (see 1R-3-1A and 1R-3-2A where several sections of pipe from a single sample were analyzed). The possibility of oxygen segregation in samples during cooling at higher concentration levels is demonstrated by workers at APDA* and this may be one cause of the problem. Clearly, repetitive analyses are required if the true value of the alkalinity is to be assessed.

The evolution of hydrogen from the cold trap may contribute to variations among samples. The attempt to correct for hydrogen was discussed under Task II-1.

2. Determination of Carbon

Parts of the same flow-through sample (from Loop 5R) were analyzed for carbon by WADCO, EBR-II and GE with results:

WADCO	1.7 ppm
EBR-II	0.5 ± 0.1 ppm
GE	15 ± 5 ppm

The severe discrepancy in these results is being investigated; its resolution is important.

WADCO and EBR-II used a high temperature dry oxidation method while GE used a low temperature wet oxidation (Van Slyke) method. WADCO provides the additional information that by a hydrolysis technique carbon as carbonate ranged between 1.2 and 3.6 ppm, and this is in good agreement with our value of approximately 2 ppm. It does not, obviously, support a value of 1.7 ppm for total carbon.

Resolution of the discrepancy will be pursued by two routes. Further parts of the same flow-through sample will be sent to the National Bureau of Standards for photon activation analysis. In addition a low carbon sample provided by WADCO will be analyzed by GE and WADCO.

3. Cover Gas Analysis

Samples of cover gas taken in mid-November from Loop 4R showed 5 ppm hydrogen, and 1000 ppm nitrogen in the cold leg surge tank, and 1500 ppm nitrogen and no detectable hydrogen (< 2 ppm), in the hot leg.

3.4 TASK II-4: PARTICULATE ANALYSIS (D. Dutina)

This task is devoted to the chemical identification of deposits and particulate matter obtained in Tasks I-4 and I-5.

This task includes the work on characterization of deposits and particulate materials obtained from filters, traps and sample surfaces. It is performed as part of the study to predict local deposition effects and is needed to improve estimates of the radioactivity levels of reactor components.

*Sampling and Analyses for Oxygen in Sodium APDA 246, April 1970.

Three filters have been taken from Loop 1R since operation at high oxygen conditions (cold trap temperature 432°F) has been in progress. The history of this sampling is shown in Tables 3-3 and 3-4.

Filters designated IX and X have been stripped of sodium by distillation. Number IX contained 1.3 grams of particulates per element and Number X contained 0.3 grams per element. The material was different in color from the material obtained at low oxygen levels—green instead of black (see attached photos) and appeared to be less dense.

Preliminary x-ray data surprisingly reveals no great qualitative differences in the phases present despite differences in oxygen level. Alpha iron is a major phase and an austenitic phase is present at minor concentration. Traces of carbides were observed. Additional work is in progress to establish the elemental composition of the residue.

1. Particulates from Loop 8 Cooler

Particulates were examined from a section of pipe from the second cooler exit of Loop 8. Major species found were sodium chromite and chromium carbide along with minor amounts of α iron and an austenitic phase. The data is consistent with previous particulate analyses. This amount of material obtained was in the quarter gram range which is sufficient to permit further characterization (e.g., quantitative analysis for the metals) and indicates the value of sampling for deposition products in this manner.

Table 3-3

HISTORY OF LOOP 1R FILTERS

Filter Designation	Exposure History		Hours	Temp. °F	Description
	From	To			
IX Main Housing*	8-6-70	9-1-70	618	600	Ni, 5 μ
X Main Housing*	9-2-70	10-13-70	989	600	Ni, 5 μ
XI Main Housing**	10-15-70	11-2-70	432	600	Ni, 5 μ

* All filters had three elements

** This set was flattened to facilitate direct x-ray examination

Table 3-4

LOOP 1R FILTER HISTORY

Filter Change	Location	Exposure Hours At Temp.	Filter Temp. °F	Filter Material	Average Pore Size	Material Collected Gms.
I	CFH	149	750	Fe	5 μ	
II	CFH + MFH	603	MF-580 CF-560	Ni	5 μ	~3
III	CFH	1347	600	Ni	5 μ	
IV	MFH	1129	525	Ni	5 μ	~3
V	MFH	1877	540	Ni	5 μ	~3
VI	MFH	1534	520	Ni	10 μ	0
VI	MFH	175	725	Ni	5 μ	0
VIII	MFH	115	600	Ni	5 μ	
IX	MFH*	618	600	Ni	5 μ	~4
X	MFH*	989	600	Ni	5 μ	
XI	MFH*	432	600	Ni	5 μ	
XII	MFH*	not yet completed	760	Ni	5 μ	

CFH – Cleanup Filter Housing

MFH – Main Filter Housing

* 20 ppm oxygen operation. Other runs, low oxygen.

4. TASK IV: EFFECTS OF SODIUM ON STRUCTURE, COMPOSITION, AND INTEGRITY OF LMFBR CLADDING (G. P. Wozadlo)

Objective:

The objective of these tests is to measure the effects of sodium exposure on the composition, microstructure and high temperature stress rupture properties of stainless steels.

Technical Summary:

Loop 4R, Run 4R-2, 1300°F

The loop operated at test conditions during the quarter. The run reached 14,170 hours at 1300°F with the pressure applied, as of October 23. There was one failure during this quarter. Fifteen of the original sixteen samples have now failed. The results to date are shown in Table 4-1.

Table 4-1

1300°F BIAXIAL STRESS RUPTURE DATA FROM RUN 4R-2

Material	Initial Hoop Stress, psi	Time-to-Rupture, hr
304CA	7000	2188
304MA	7000	2198
304MA	7000	2237
304CA	7000	2263
316MA	8000	3822
316MA	8000	4415
316CA	8000	5162
316CA	8000	5175
304CA	5000	4500
304MA	5000	5187
304CA	5000	6228
304MA	5000	6546
316CA	6000	10,852
316MA	6000	10,883
316CA	6000	14,239

MA — Mill Annealed

CA — Carbide Agglomerated, 1650°F for 24 hours

Loop 5R, Run 5R-5, 1300°F

The loop operated at test condition during the quarter. The run reached 5979 hours at 1300°F with the pressure applied as of October 23. There were two failures during the quarter. Three of the original sixteen samples have now failed. The results to date are shown in Table 4-2.

Table 4-2

1300°F BIAXIAL STRESS RUPTURE DATA FROM RUN 5R-5

Material	Initial Hoop Stress, psi	Time-to-Rupture, hr
304MA	5500	3939
316MA	9000	4676
316CA	9000	6124

Loop 6R, Run 6R-4, 1150°F

The loop operated at test conditions until October 26, when a pump failure forced a shutdown. The run reached 8538 hours at 1150°F with the pressure applied as of October 23. There was one failure during the quarter. Ten of the original sixteen samples have now failed. The results to date are shown in Table 4-3.

Table 4-3

1150°F BIAXIAL STRESS RUPTURE DATA FROM RUN 6R-4

Material	Initial Hoop Stress, psi	Time-to-Rupture, hr
304MA	20,000	514
304MA	20,000	559
304CA	20,000	1662
304CA	20,000	4006
316MA	20,000	639
304MA	18,000	1710
304MA	18,000	1947
304CA	18,000	5391
304CA	18,000	6235
316MA	22,000	7734

Control Tests, Argon, 1300°F

Stress-rupture tests are being run at 1300°F in argon on mill-annealed and carbide-agglomerated Types 304 and 316 SS. The tests are being run for the purpose of supplying comparison (control) data for the tests in flowing sodium. The same heats of materials are being tested in both environments; by this means, the environmental effect(s) can be delineated. The results to date are shown in Table 4-4.

Table 4-4
1300°F BIAXIAL STRESS RUPTURE DATA IN ARGON

Material	Initial Hoop Stress, psi	Time-to-Rupture, hr
316CA	15,000	925
316MA	15,000	1375
316CA	13,000	1584
316MA	13,000	2415
316MA	11,000	3183
316MA	11,000	4551
316CA	11,000	4874
316CA	11,000	9279
304CA	11,000	718
304MA	11,000	829
304MA	11,000	901
304MA	9,000	2511
304CA	9,000	2727
304CA	9,000	2895
304MA	9,000	3373
304CA	9,000	3389
304MA	9,000	4374
304MA	8,000	3380
304CA	8,000	4165
304CA	8,000	5965
316MA	8,000	11,760

The results, plus those for Runs 4R-2 and 5R-5 and the previously reported data from Loop 5R,* are plotted in Figures 4-1 and 4-2. On the basis of comparison with the control tests, there is a definite decrease in long-term stress-rupture strength due to exposure in 1300°F nonisothermal flowing sodium.

The Type 304 SS tests in 1150°F sodium have been completed. Although there is no control data at 1150°F, it can be seen that the effect of 1150°F flowing sodium on the rupture strength of Type 304 SS will be minimal at best due to the very gradual slope of the curve. Previously, no difference could be seen between the mill-annealed and carbide-agglomerated structures of Types 304 and 316 SS in 1300°F sodium or argon. However, it should be noted that a significant difference in rupture strength is seen for Type 304 SS in 1150°F sodium. The carbide-agglomerated structure has better rupture strength, as was originally thought would be the case, due to the reduction in grain boundary sliding. At 1300°F, the large grain boundary carbides produced by the heat treatment do not exist after a relatively short period of time due to the decarburization. Therefore, no effect is seen. However, if the decarburization is slight or nil as indicated by the 1150°F rupture curves, the carbides remain and an effect should be seen as noted. The effect is further evidence that little carbon movement is occurring in 1150°F sodium.

Samples of Types 304, 316, 321, 347 SS, and Incoloy-800, 0.250-in. o.d. X 0.015-in. wall seamless tubing, have been exposed to 1300°F sodium for various lengths of time in the unstressed condition. The biaxial stress-rupture testing of these samples in 1300°F argon has been initiated, and the preliminary results are compared to the argon results for previously unexposed material in Figures 4-3 through 4-7.

*PA-15 "Quarterly Progress Report No. 9, GEAP-10036, June 1969.

The rupture strength of the sodium exposed Types 304 and 316 SS has been reduced. The strength reduction increases with increased sodium exposure, although it is difficult to distinguish between 500, 1000 and 1700 hours exposure. However, the stress-rupture curve for a particular sodium exposure has the same slope as the unexposed data. It has been established* that Types 304 and 316 SS undergo decarburization due to exposure in 1300°F nonisothermal flowing sodium. The above results are predictable on the basis of increasing bulk decarburization with increasing sodium exposure. In effect, the results are a series of curves for Types 304 and 316 SS with various carbon contents.

The rupture strength of the sodium exposed Types 321 and 347 SS also shows a reduction. The strength reduction appears to be more dependent on the sodium exposure time (see Figure 4-6), than previously noted for Types 304 and 316 SS. However, as shown in Table 4-5 for Type 347 SS, the stabilized grades of austenitic stainless steel do not decarburize in 1300°F nonisothermal flowing sodium. This and the fact that there is a significant effect of the carbide agglomeration heat treatment on the rupture properties at 1300°F not noted with Types 304 and 316 SS, indicate that an aging process is occurring, which is drastically reducing the rupture strength.

The statements made concerning Types 321 and 347 SS also apply to Incoloy-800 with one exception; the rupture strength appears to increase after some period of exposure to 1300°F sodium. However, it is well known** that Incoloy-800 will age harden in this temperature range, which would increase the rupture strength and tend to offset any other mechanism producing a reduction in rupture strength.

Table 4-5
CARBON STABILITY IN AUSTENITIC STEELS IN SODIUM

<u>Material</u>	<u>Total Carbon Content (wt %)</u>		
	<u>As-Received</u>	<u>Post Exposure</u>	<u>Percent Change</u>
304 SS	0.062	0.017	-73
316 SS	0.073	0.038	-48
347 SS	0.051	0.052	+2
Incoloy-800	0.088	0.098	+11

Note: Exposed in flowing sodium at 1300°F for 4838 hours (Run 5R-4).

*PA-15 "Quarterly Progress Report No. 13, GEAP-13539-13, June 1970.

**"Incoloy-800 for Nuclear Fuel Sheaths (A Monograph)," Compiled by C. N. Spalaris, GEAP-4633, July 1964.

Figure 4-1. Biaxial Stress-Rupture Properties in Type 316 Stainless Steel in Sodium and Argon

Figure 4-2. Biaxial Stress-Rupture Properties of Type 304 Stainless Steel in Sodium and Argon

Figure 4-3. 1300°F Biaxial Stress-Rupture Properties of Type 304 Stainless Steel in Argon

Figure 4-4. 1300°F Biaxial Stress-Rupture Properties of Type 316 Stainless Steel in Argon

Figure 4-5. 1300°F Biaxial Stress-Rupture Properties of Type 321 Stainless Steel in Argon

Figure 4-6. 1300°F Biaxial Stress-Rupture Properties of Type 347 Stainless Steel in Argon

4-11/4-12

GEAP-13539-15

Figure 4-7. 1300°F Biaxial Stress-Rupture Properties of Incoloy-800 in Argon

5. LIST OF SODIUM MASS TRANSFER PROJECT REPORTS

TOPICAL REPORTS

1. GEAP-3725—Lockhart, R.W., Billuris, G., and Lane, M.R., "Sodium Mass Transfer: I Test Loop Design," June 1962.
2. GEAP-3726—Lockhart, R.W., et al., "Sodium Mass Transfer: II Screening Test Data and Analysis — Mass Transfer Results," Volume I, April 1962.
3. GEAP-3726—Hetzler, F.J., and Young, R.S., "Sodium Mass Transfer: II Screening Test Data and Analysis — Metallurgy," Volume II, June 1962.
4. GEAP-3726—Lockhart, R.W., "Sodium Mass Transfer: I Screening Test Data and Analysis — 1961 Corrosion Sample Data," Volume 3, May 1962.
5. GEAP-4006—Alter, H.W., and McManus, P.A., "Sodium Mass Transfer: III The Application of Liquid Ammonia as a Leaching Agent," April 1962.
6. GEAP-4181—Pohl, L.E., "Sodium Mass Transfer: IV 1962 Corrosion Sample Data," January 1963.
7. GEAP-4182—Lockhart, R.W., "Sodium Mass Transfer: V 1962 Test Run Reports," June 1963.
8. GEAP-4183—Dunn, E.L., "Sodium Mass Transfer: VI Statistical Correlation of 1961 — 1962 Corrosion Data," February 1964.
9. GEAP-4178—Sabol, W.W., and Lockhart, R.W., "Sodium Mass Transfer: VII Methods for Determining Impurities in Sodium Samples," September 1963.
10. GEAP-4313—Mottley, J.D., "Sodium Mass Transfer: VIII Corrosion of Stainless Steel in Isothermal Regions of a Flowing Sodium System," February 1964.
11. GEAP-4436—Lockhart, R.W., et al. "Sodium Mass Transfer: IX The Effect of Carbon and Carbonate Additions in a Sodium Test Loop," December 1964.
12. GEAP-4437—Pohl, L.E., "Sodium Mass Transfer: X 1963 Corrosion Sample Data," February 1964.
13. GEAP-4438—Lockhart, R.W., "Sodium Mass Transfer: XI 1963 Test Run Reports (January - June)," February 1964.
14. GEAP-4439—Lockhart, R.W., "Sodium Mass Transfer: XII 1963 Test Run Reports (July - December), October 1964.
15. GEAP-4540—Sabol, W.W., Dutina D., Rey, D.E., and Simpson, J.L., "Sodium Mass Transfer: XIII The Determination of Total Carbon in Sodium," June 1964.
16. GEAP-4830—Dunn, F.L., Stewart, K.B., and Jaech, J.L., "Sodium Mass Transfer: XIV Statistical Analysis of 1961 - 1964 Sample Weight Change Data," February 1965.
17. GEAP-4831—Rowland, M.C., Plumlee, D.F., and Young, R.S., "Sodium Mass Transfer: XV Behavior of Selected Steels Exposed in Flowing Sodium Test Loops," March 1965.
18. GEAP-4832—Brush, E.G., "Sodium Mass Transfer: XVI The Selective Corrosion Component of Steel Exposed in Flowing Sodium," March 1965.
19. GEAP-4833—Dutina, D., and Simpson, J.L., "Sodium Mass Transfer: XVII The Determination of Hydrogen in Loop Sodium and Cover Gases," June 1965.
20. GEAP-4834—Plumlee, D.E., Lockhart, R.W., and Pohl, L.F., "Sodium Mass Transfer: XVIII Studies of Carbon Movement in Pumped Sodium Test Loops," June 1965.
21. GEAP-4835—Rowland, M.C., Plumlee, D.E., Pohl, L.E., and Lockhart, R.W., "Sodium Mass Transfer: XIX Long-Term Exposure Effects in a Bimetallic Type 316 Stainless Steel - 2-¼ Cr Test Loop," April 1965.
22. GEAP-4836—Pohl, L.E., "Sodium Mass Transfer: XX 1964 Corrosion Sample Data," May 1965.
23. GEAP-4837—Lockhart, R.W., Rowland, M.C., and Pohl, L.E., "Sodium Mass Transfer: XXI 1964 Run Reports," June 1965.
24. GEAP-3838—Rowland, M.C., and Plumlee, D.E., "Sodium Mass Transfer: XXII Metallurgical Examination of the Test Loops," October 1965.
25. GEAP-4602—Lockhart, R.W., Blair, R.C., Dutina, D., Jaech, J.L., and Sabol, W.W., "Results of the USAEC Round-Robin Analysis for Carbon Impurity in Sodium," March 1964.

26. GEAP-5020—Dutina, D., and Simpson, J.L., "Sodium Mass Transfer: XXIV Methods for Separation and Identification of Sodium Impurities," January 1967.
27. GEAP-5560—Steamer, A.G., "Refueling Cell Studies," November 1967.
28. GEAP-4881—Lockhart, R.W., and Blair, R.C., "Sodium Mass Transfer: XVIII, Model for Corrosion Mockup of Sodium Cooled Reactors," July 1967.
29. GEAP-10048—Collins, G.D., "Plugging Indicator Operation," September 1969.
30. GEAP-13545—Comprelli, F. A., Krankota, J. L., "Interpretation of the ASME Code for Low Alloy Steels in Bimetallic Sodium Systems," September 1969.
31. GEAP-13544—Wozadlo, G. P., Spalaris, C. N., "Corrosion of Stainless Steel and Deposition of Particulates in Flowing Sodium Systems," September 1969.
32. GEAP-13548—Roy, P., Gebhart, M. F., "Corrosion and Mass Transport of Stainless Steels in Sodium Systems," September 1969.

QUARTERLY REPORTS

1. GEAP-4408—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 1, March - May 1967," June 1967.
2. GEAP-5546—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 2, June - August 1967," September 1967.
3. GEAP-5582—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 3, September - November 1967," January 1968.
4. GEAP-5602—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 4, December 1967 - February 1968," May 1968.
5. GEAP-5648—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 5, March - May 1968," July 1968.
6. GEAP-5693—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 6, June - August 1968," October 1968.
7. GEAP-5719—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 7, September - November 1968," January 1969.
8. GEAP-10008—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 8, December 1968 - February 1969," April 1969.
9. GEAP-10036—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 9, March - May 1969," June 1969.
10. GEAP-13539—"Sodium Components Development Program Mass Transfer Investigations in Liquid Metal Systems, Quarterly Progress Report No. 10, June - August 1969," September 1969.
11. GEAP-13539-11—"Sodium Technology Development Program Mass Transfer Investigations In Liquid Metal Systems, Quarterly Report No. 11, September 1969—November 1969," December 1969.
12. GEAP-13539-12—"Sodium Technology Development Program Mass Transfer Investigations In Liquid Metal Systems, Quarterly Report No. 12, December 1969 - February 1970," September 1970.
13. GEAP-13539-13—"Sodium Technology Development Program Mass Transfer Investigations In Liquid Metal Systems, Quarterly Report No. 13, March 1970 - May 1970," June 1970.
14. GEAP-13539-14—"Sodium Technology Development Program Mass Transfer Investigations In Liquid Metal Systems, Quarterly Report No. 14, June - August, 1970," September 1970.

PA-15 PROGRAM CONTRIBUTORS

TASK I – CORROSION-DEPOSITION STUDIES

Contributors

J. S. Armijo	D. N. Rodgers
J. T. Cochran	P. Roy
L. A. Dixon	M. K. Schad
G. E. Orr	J. A. Whittington
L. E. Pohl	G. P. Wozadlo

TASK II – SURVEILLANCE AND ANALYSIS OF IMPURITIES IN SODIUM

Contributors

E. A. Aitken	W. D. Reynolds
L. A. Dixon	D. N. Rodgers
D. Dutina	H. S. Rosenbaum
J. E. Lewis	P. Roy
G. E. Orr	J. L. Simpson
L. E. Pohl	

TASK IV – EFFECT OF SODIUM ON STRUCTURE, COMPOSITION, AND INTEGRITY OF LMFBR CLADDING

Contributors

J. S. Armijo	L. E. Pohl
R. R. Asamoto	P. Roy
L. A. Dixon	J. A. Whittington
A. Montes	G. P. Wozadlo

GENERAL PROGRAM AND CONSULTING

Contributors

G. D. Collins	R. S. Young
C. N. Spalaris	E. L. Zebroski

DISTRIBUTION LIST-PA 15

Director, Div. of Reactor Dev. & Tech. Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	Chief, Liquid Metal Projects Branch Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1
Asst. Director for Project Management Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	Chief, Fuel Engineering Branch Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1
Asst. Director for Plant Engineering Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	LMFBR Program Manager Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1
Asst. Director for Reactor Engineering Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	Director, LMFBR Program Office Argonne National Laboratory 9700 South Cass Avenue Argonne, Illinois 60439	1
Asst. Director for Reactor Technology Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	Director, Contracts Division United States Atomic Energy Commission San Francisco Operations Office 2111 Bancroft Way Berkeley, California 94704	1
Asst. Director for Program Analysis Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	Chief, California Patent Group United States Atomic Energy Commission San Francisco Operations Office P. O. Box 808 Livermore, California 94550	1
Chief, Coolant Chemistry Branch Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	3	United States Atomic Energy Commission Division of Technical Information Extension P. O. Box 62 Oak Ridge, Tennessee 37380 Attention: T. W. Laughlin	90
Chief, Fuels & Materials Branch Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1	RDT Site Office United States Atomic Energy Commission General Electric Company 452 De Guigne Drive Sunnyvale, California 94086	2
Chief, Reactor Vessels Branch Division of Reactor Development & Technology United States Atomic Energy Commission Washington, D. C. 20545	1		