UNCLASSIFIED

(CLASSIFICATION)

GENERAL ELECTRIC

HANFORD ATOMIC PRODUCTS OPERATION - RICHLAND, WASHINGTON

DOCUMENT NO.

HW-79354

DATE

10-28-63

COPY NO.

TITLE

REDUCTION OF PLUTONIUM(VI) TO PLUTONIUM(III) AND (IV)
BY SODIUM NITRITE.

ISSUING FILE

AUTHOR

C. A. Colvin

REFERENCE COPY
RECEIVED 300 AREA
NOV 4 1963

BEST AVAILABLE COPY

DISTRIBUTION

TECHNICAL INFORMATION FILES

NAME

BUILDING AREA

NAME

BUILDING AREA

GJ Alkire	222-U	200-W
OF Beaulieu	222-S	200-W
JS Buckingham	222-S	200-W
LL Burger	325	300
RE Burns	222-S	200-W
MH Campbell	222-S	200-W
EW Christopherson	325	300
CA Colvin	222-S	200-W
JJ Courtney	234-5	200-W
OD Erlandson	202-S	200-W
WS Frank	2704-E	200-E
WJ Gartin	2704-Z	200-W
KM Harmon	325	300
MK Harmon	202-S	200-W
OF Hill	326	300
HH Hopkins, Jr.	234-5	200-W
ER Irish	329	300
RE Isaacson	202-S	200-W
JW Jordan	222-S	200-W
BF Judson	202-A	200-E
RJ Kofoed	2704-W	200-W
LM Knights	234-5	200-W
TR McKenzie	222-S	200-W
RL Moore	325	300
JR Morrey	325	300
CW Pollock	222-S	200-W
HC Rathvon	2704-W	200-W
WH Reas	326	300
JL Ryan	325	300
RA Schneider	329	300
FA Scott	325	300

RJ Sloat	2704-Z	200-W
AE Smith	2704-Z	200-W
RJ Sorenson	234-5	200-W
RE Tomlinson	2704-W	200-W
AJ Waligura	202-A	200-E
MT Walling	325	300
EJ Wheelwright	325	300
RA Yoder	202-S	200-W
300 Files	3760	300
Records Center	3760	300
Extra (10)		

RL Lerch 32480 325 SEP 4 1968

Reviewed and Approved for
Public Release by the NSAT
JD Watson PNNL ADD
12/13/2000 Date

ROUTE TO

PAYROLL NO.

LOCATION

FILES ROUTE
DATE

SIGNATURE AND DATE

300 Files

T14 J. E. Gardner

53011

713

NOV 27 63

LW C. A. Colvin

12926

1904H

DEC 9 '63

54-3000-030 (1-61)

AEC-GE RICHLAND, WASH.

UNCLASSIFIED

(CLASSIFICATION)

TO BE USED ON UNCLASSIFIED AND OFFICIAL USE ONLY DOCUMENTS.

UNCLASSIFIED

HW-79354

REDUCTION OF PLUTONIUM(VI) TO PLUTONIUM(III)
AND (IV) BY SODIUM NITRITE

by

C. A. Colvin

Separations Chemistry Laboratory
Research and Engineering
Chemical Processing Department

October 28, 1963

HANFORD ATOMIC PRODUCTS OPERATION
RICHLAND, WASHINGTON

Operated for the Atomic Energy Commission by
the General Electric Company under Contract #AT(45-1)-1350

REDUCTION OF PLUTONIUM(VI) TO PLUTONIUM(III)
AND (IV) BY SODIUM NITRITE

INTRODUCTION

The application of anion exchange for final plutonium purification⁽¹⁾ in the Redox facility requires the adjustment of plutonium(VI) to plutonium(IV). Two methods of reduction were investigated: The first method was reduction by ferrous sulfamate; the second method was the use of nitrite for reduction.

The use of ferrous sulfamate was adopted due to the rapid rate of reduction and simplicity of the process. It was recommended that 2.5 moles of ferrous sulfamate per mole of plutonium be added to the process solution. The resulting Pu(IV) - Pu(III) mixture is continuously fed to a boiling concentrator which is 7M in HNO₃. Any excess ferrous is oxidized, sulfamate ion is oxidized to sulfate, plutonium(III) is oxidized to plutonium(IV), and thus the resulting feed solution contains the required plutonium(IV) nitrate complex in 7M HNO₃. The main objection to this method is the increase in iron content in backcycle streams.

Efficient reduction by nitrite is limited to solutions below 1.4M HNO₃ with elevated temperatures (above 50 C). Rates of reduction are such that time is also a determining factor. The information gained during the investigation of reduction by nitrite is presented in this paper in hope that it may be of value in future investigations and processes.

SUMMARY AND CONCLUSIONS

The reduction of Pu(VI) by nitrite is dependent on nitrite concentration, temperature, acidity, ferric ion concentration, and time. It is interesting to note that greater than 90% reduction to plutonium(III) by sodium nitrite may be accomplished by controlling the above conditions. Three oxidation states were apparent in most of the solutions and were quantitatively determined by use of a recording spectrophotometer.

EXPERIMENTALAnalysis

Oxidation state analyses were performed spectrophotometrically⁽²⁾, using a Beckman Model DK-2 ratio-recording spectrophotometer with 1 cm rectangular silica cells.

- (1) J. L. Ryan and E. J. Wheelwright, The Recovery, Purification, and Concentration of Plutonium by Anion Exchange in Nitric Acid, HW-55893. January 2, 1959. (Confidential)
- (2) C. A. Colvin and D. A. Dodd, Quantitative Determination of Plutonium Oxidation States In Variable Nitric Acid Solutions - Spectrophotometric, HW-79195, October 14, 1963.

Effect of NaNO₂ Concentration

Solution:

Pu(VI) 0.0111M
 HNO₃ 0.55M
 Fe(III) 5 x 10⁻⁵M
 NaNO₂ Variable
 Temperature 60 C

<u>NaNO₂ conc.</u>	<u>Time (Min.)</u>	<u>% Pu(VI)</u>	<u>% Pu(IV)</u>	<u>% Pu(III)</u>
0.012M	10	63	21	16
	20	47	30	23
	30	37	37	26
	40	25	46	29
	50	20	50	30
	60	17	52	31
	70	14	55	31
0.024M	10	53	21	26
	20	30	33	37
	30	15	40	45
	40	5	47	48
	50	2	49	49
	60	1	50	49
	70	1	51	48

UNCLASSIFIED

-4-

HW-79354

<u>NaNO₂ conc.</u>	<u>Time(Min.)</u>	<u>% Pu(VI)</u>	<u>% Pu(IV)</u>	<u>% Pu(III)</u>
0.049 <u>M</u>	10	39	23	38
	20	14	34	52
	30	3	37	60
	40	1	39	60
	50	< 1	40	60
	60	< 1	41	59
	70	< 1	41	59
0.098 <u>M</u>	10	18	22	60
	20	2	27	71
	30	< 1	28	72
	40	< 1	28	72
	50	0	29	71
	60	0	30	70

Effect of HNO₃ Concentration

Solution:

Pu(VI)	0.0111 <u>M</u>
HNO ₃	Variable
Fe(III)	5 x 10 ⁻⁵ <u>M</u>
NaNO ₂	0.049 <u>M</u>
Temperature	70 C

UNCLASSIFIED

-5-

HW-79354

<u>HNO₃ Conc.</u>	<u>Time (min.)</u>	<u>% Pu(VI)</u>	<u>% Pu(IV)</u>	<u>% Pu(III)</u>
0.55 <u>M</u>	10	16	30	54
	20	2	35	63
	30	1	36	63
	40	1	37	62
	50	1	38	61
	60	1	40	59
1.00 <u>M</u>	10	23	58	19
	20	4	75	21
	30	2	78	20
	40	1	79	20
	50	1	80	19
	60	2	81	17
	70	2	82	16
1.25 <u>M</u>	10	28	60	12
	20	5	85	10
	30	2	91	7
	40	1	93	6
	50	1	94	5
	60	1	94	5
1.40 <u>M</u>	10	31	65	4
	20	7	89	4
	30	3	94	3
	40	2	96	2
	50	2	97	1
	60	1	98	1
	70	1	98	1

Effect of Ferric Ion Concentrations

The rate of reaction is dependent upon the ferric ion concentration.

Solution:

Pu(VI)	0.0111M
HNO ₃	0.55M
Fe(III)	Variable
NaNO ₂	0.049M
Temperature	70 C

<u>Fe(III)</u>	<u>Time (min.)</u>	<u>% Pu(VI)</u>	<u>% Pu(IV)</u>	<u>% Pu(III)</u>
5 x 10 ⁻⁵ M	10	16	30	54
	20	2	35	63
	30	1	36	63
	40	1	37	62
	50	1	38	61
	60	1	40	59
0.01M	10	2	33	65
	20	<1	35	65
	30	<1	36	64
	40	<1	37	63
	50	1	38	61
	60	2	39	59

Effect of Temperature

Reaction was not readily detectable at 25 C.

Solution:

Pu(VI)	0.0111M
HNO ₃	0.55M
Fe(III)	5 x 10 ⁻⁵ M
NaNO ₂	0.049M
Temperature	Variable

UNCLASSIFIED

-7-

HW-79354

<u>Temperature</u>	<u>Time (min.)</u>	<u>% Pu(VI)</u>	<u>% Pu(IV)</u>	<u>% Pu(III)</u>
48 C	10	28	3	69
	20	17	5	78
	30	12	6	82
	40	9	7	84
	50	6	8	86
	60	3	8	89
	70	1	8	91
70 C	10	16	30	54
	20	2	35	63
	30	1	36	63
	40	1	37	62
	50	1	38	61
	60	1	40	59

Gaseous NO₂

Use of gaseous NO₂ in 0.5M HNO₃ solutions at temperatures above 50 C yielded results comparable to those obtained with NaNO₂. Attempts to reduce Pu(VI) to Pu(IV) in 7M HNO₃ with gaseous NO₂ indicated that the reaction rate was too low to be of practical use. Also the nitrogen oxides dissolved in the 7M HNO₃ solution after NO₂ sparging would require considerable air sparging for removal before a suitable feed to the anion exchange unit was available.