UNCLASSIFIED

This document classified
by R. E. Burns

HW-53636
Undocumented

Distribution

NOTICE!

This report was prepared for use within General Electric Company in the course of work under Atomic Energy Commission Contract W-31-109-Eng-52, and any views or opinions expressed in the report are those of the author only. This report is subject to revision upon collection of additional data.

enter

INHIBITION OF HNO_3 - H^+ CORROSION OF TYPE 304-L STAINLESS STEEL

WITH $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$

By

W. L. Walker

Development and Corrosion Chemistry Operation

Hanford Laboratories Operation

November 18, 1957

HANFORD ATOMIC PRODUCTS OPERATION

RICHLAND, WASHINGTON

GENERAL ELECTRIC

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

TO: 300 Files

November 18, 1957

FROM: W. L. Walker

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

INHIBITION OF HNO_3 -HF CORROSION OF TYPE 304-L STAINLESS STEEL WITH $\text{Al}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$

Introduction and Summary

Part of the feed preparation for the Recuplex process involves a dissolution in a mixture of nitric and hydrofluoric acids. This solution is extremely corrosive to most of the 300-series stainless steels, and to prevent corrosion of equipment used in subsequent processing steps, aluminum nitrate nonohydrate (ANN) is added to tie up the fluoride; either as AlF_3 or a tight complex. Assuming that the fluoride is tied up as AlF_3 , a solution of HNO_3 , HF, and ANN in which the HF - ANN molar ratio was 3, should not exhibit serious corrosive attack on the 300-series stainless steels. Work performed by DuPont personnel has confirmed this.⁽¹⁾

In the Recuplex process, it is desirable to keep the salt content of the solution as low as possible. It would be advantageous if higher HF - ANN ratios could be tolerated. Also, the Recuplex process dissolution step is made at the boiling point, and no corrosion data was available for this system at that temperature; the DuPont work was performed at a maximum temperature of 40° C. In view of this situation, the Corrosion laboratory of the Development and Corrosion Chemistry Operation was requested to investigate the inhibitory effects of ANN on the corrosivity of an HNO_3 - HF mixture at the boiling point.

It was found that in a 2 M HNO_3 - 1 M HF - ANN system at the boiling point, an HF - ANN molar ratio of between 2 and 1 is necessary for drastic inhibition of the corrosion. The corrosion rate of type 304-L stainless steel in this system, without ANN, is about 1.0 inches penetration per month (ipm). In this same system, with an HF-ANN molar ratio of 2, the corrosion rate is about 0.2 ipm; and at a molar ratio of 1, the rate is about 0.003 ipm. The difference in molar ratios necessary for inhibition between our work and that of DuPont may be due to dissociation of the complex, or ionization of the AlF_3 , at the boiling point. It appears, also, that within the HF-ANN molar ratio range of 2 to 6, the corrosion rate is directly proportional to the HF-ANN ratio.

Experimental

Samples of sensitized type 304-L stainless steel were exposed to solutions of 2 M HNO_3 - 1 M HF, containing varying quantities of ANN such that the HF - ANN molar ratios had values of 1/2, 1, 2, 3, 4, 5, 6, and infinity (no ANN). The samples were immersed in these boiling solutions for three six-hour periods, with weight loss measurements and solution changes performed every six hours. The results of these exposures are shown below. The corrosion rates represent the average of the three periods:

HF - ANN Molar Ratio				Corrosion Rate (ipm)
2 M HNO_3	- 1 M HF	- 2 M ANN	1/2	.0014
2 M HNO_3	- 1 M HF	- 1 M ANN	1	.0032
2 M HNO_3	- 1 M HF	- 0.5 M ANN	2	.2257
2 M HNO_3	- 1 M HF	- 0.33 M ANN	3	.3850

(Cont'd)

							<u>HF-ANN Molar Ratio</u>	<u>Corrosion Rate (ipm)</u>	
2	<u>M</u>	<u>HNO₃</u>	- 1	<u>M</u>	<u>HF</u>	- 0.25	<u>M</u> ANN	4	.4228
2	<u>M</u>	<u>HNO₃</u>	- 1	<u>M</u>	<u>HF</u>	- 0.20	<u>M</u> ANN	5	.4995
2	<u>M</u>	<u>HNO₃</u>	- 1	<u>M</u>	<u>HF</u>	- 0.167	<u>M</u> ANN	6	.6094
2	<u>M</u>	<u>HNO₃</u>	- 1	<u>M</u>	<u>HF</u>	- 0.00	<u>M</u> ANN	infinity	1.0115

From these data, it appears that the break point is somewhere between HF-ANN molar ratios of 2 and 1. The discrepancy between our results and those of DuPont personnel is probably due to our having made our exposures at the boiling points of these solutions, while the DuPont work was done at a maximum of 40° C. There may be significant dissociation of the complex or ionization of the salt AlF_3 at this temperature.

It also appears that between the molar ratios of 2 and 6, the corrosion rate is directly proportional to the HF-ANN molar ratio; therefore, any increase in this ratio will result in a corresponding increase in corrosion rate.

Although the Recuplex dissolvers are fabricated from type 309-SCb stainless steel, type 304-L stainless steel was used in this investigation because it is a more dependable testing material. There is a much smaller variation in corrosion resistance between different heats of 304-L than between heats of 309-SCb. Had 309-SCb been used as the test material, there would be no guarantee that the corrosion rates observed in the laboratory were representative of those which would be experienced in the field. However, one sample of 309-SCb was exposed to the solution with an HF-ANN molar ratio of 4 in order to obtain some idea of the magnitude of the rates which might be encountered in operation. The corrosion rate on this sample was .006 ipm; lower by a factor of 70 as compared to type 304-L.

This represents the work performed in this investigation and, unless a more extensive program is desired, will conclude our work on this problem.

WL Walker:pc