Title: Refractory for Black Liquor Gasifiers

Type of Report: Topical Report Task 1.4

Reporting Period Start Date: January 1, 2005

Reporting Period End Date: September 31, 2005

**Principal Authors: William L. Headrick Jr., Musa Karakus
and Xiaoting Laing**

Date Report Issued: October 2005

DOE Award Number: DE-FC26-02NT41491

Name and Address of Submitting Organization:

**Curators of the University of Missouri on behalf of University
of Missouri-Rolla**

Sponsored Programs

1870 Miner Circle

215 ME Annex

Rolla, MO 65409-1330

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

ABSTRACT

The University of Missouri-Rolla will identify materials that will permit the safe, reliable and economical operation of combined cycle gasifiers by the pulp and paper industry. The primary emphasis of this project will be to resolve the material problems encountered during the operation of low-pressure high-temperature (LPHT) and low-pressure low-temperature (LPLT) gasifiers while simultaneously understanding the materials barriers to the successful demonstration of high-pressure high-temperature (HPHT) black liquor gasifiers. This study will define the chemical, thermal and physical conditions in current and proposed gasifier designs and then modify existing materials and develop new materials to successfully meet the formidable material challenges.

Resolving the material challenges of black liquor gasification combined cycle technology will provide energy, environmental, and economic benefits that include higher thermal efficiencies, up to three times greater electrical output per unit of fuel, and lower emissions. In the near term, adoption of this technology will allow the pulp and paper industry greater capital effectiveness and flexibility, as gasifiers are added to increase mill capacity. In the long term, combined-cycle gasification will lessen the industry's environmental impact while increasing its potential for energy production, allowing the production of all the mill's heat and power needs along with surplus electricity being returned to the grid. An added benefit will be the potential elimination of the possibility of smelt-water explosions, which constitute an important safety concern wherever conventional Tomlinson recovery boilers are operated.

Developing cost-effective materials with improved performance in gasifier environments may be the best answer to the material challenges presented by black liquor gasification. Refractory materials may be selected/developed that either react with the gasifier environment to form protective surfaces in-situ; are functionally-graded to give the best combination of thermal, mechanical, and physical properties and chemical stability; or are relatively inexpensive, reliable repair materials. This report covers Task 1.4, Industrial Trial of candidate materials developed by refractory producers and in the laboratory based on the results of Task 1.1, 1.2 and 1.3.

Refractories provided by in-kind sponsors to industrial installations tested by cup testing, density/porosity determinations, chemical analysis and microscopy. None of the materials produced in this program have been trialed in high temperature gasifiers, but the mortar developed Morcocoat SP-P is outperforming other mortars tested at ORNL. MORCO PhosGun M-90-O has shown in laboratory testing to be an acceptable candidate for hot and cold repairs of existing high temperature gasifiers. It may prove to be an acceptable lining material.

TABLE OF CONTENTS

DISCLAIMER	3
ABSTRACT	4
TABLE OF CONTENTS	5
LIST OF GRAPHICAL MATERIALS	6
INTRODUCTION	7
EXECUTIVE SUMMARY	10
EXPERIMENTAL	11
RESULTS AND DISCUSSION	11
CONCLUSION	13
REFERENCES	15
BIBLIOGRAPHY	17

LIST OF GRAPHICAL MATERIALS

Figure 1 Schematic construction of a typical high temperature gasifier	8
Figure 2 MORCOCOat SP-P after 100 hr. immersion in BL smelt. Showing minimal to no reaction.....	11
Figure 3 Picture of failed pulse combustor tube sheet.	12
Figure 4 Enlargement showing critical delamination failure at 5-6" in depth and accompanying transverse cracking.	13

INTRODUCTION

The Tomlinson recovery boiler is the conventional technology for recovering cooking chemicals and energy from black liquor. As a potential replacement for the Tomlinson recovery boiler, black liquor gasification (BLG) technology has garnered much interest over the last two decades in the papermaking industry. The BLG technology has higher energy efficiency and generates far more power with overall lower cost than conventional technology. It improves safety by reducing the risk associated with smelt-water explosions. It reduces the wastewater discharges and harmful emissions into the environment. BLG systems recover sodium and sulfur as separate streams that can be blended to produce a wide range of pulping liquor compositions [Stigsson (1998)]. As a technique that is still under development, it has problems including refractory failure during operation due to a combined effect of chemical reaction and thermomechanical stress [Brown and Hunter (1998), Dickinson, Verrill and Kitto (1998)]. The objective of this study is to investigate refractory materials for the lining of the gasifier.

High temperature black liquor gasifiers are generally cylindrical in shape as shown in Figure 1. The height ranges from 1.5 m to 25 m and diameter ranges from 0.5 m to 5 m. In the gasifier reactor vessels, there are usually 2-6 coaxial layers of component lining [Taber (2003)]. Refractory lining is used to protect the exterior metallic part of the gasifier vessel. A dense refractory material layer is designed to be exposed to the highest temperature environment. The second “safety” layer is usually made of a similar material. Subsequent layers are used to provide insulation and allow for expansion. The steel shell is used to provide reaction space and confinement. The gasifier generally operates at temperature ranging from 950 to 1000°C.

Figure 1 Schematic construction of a typical high temperature gasifier

The commercial high temperature black liquor gasifier was developed by Kvaerner Chemrec. A pilot plant first started running in 1994 at a pulp mill near Karlstad, Sweden [Larson, Consonni and Katofsky (2003)]. The first commercial size Chemrec system (75-100 tons of dry solids/day) was built in 1991. This air blown gasifier has performed well and been proven to be easy to operate and maintain. The first commercial Chemrec system in North America started operation in 1996 at Weyerhaeuser's New Bern, SC, USA [Brown and Hunter (1998)]. It was an atmospheric, air-blown, entrained bed gasifier operating between 950-1000 °C with a capacity of 350 ton black liquor solids per day. However, this system was shutdown in January 2000 due to failure of the stainless steel shell [Brown and Landalv (2001)].

Black liquor gasification converts the organic components into combustible fuel gas and leaves inorganic components as smelt to generate high-quality green liquor for regenerating pulping chemicals [Kelleher and Kohl (1986)]. The combustible gas contains carbon monoxide (CO), hydrogen (H₂), carbon dioxide (CO₂), methane (CH₄), nitrogen (N₂), water vapor (H₂O) and hydrogen sulfide (H₂S). The smelt drops are mainly sodium carbonate (Na₂CO₃) and sodium sulfide (Na₂S). Some of the smelt drops form a thin layer of smelt flowing along the reactor wall.

The current refractory materials for the BLG reactor vessel lining are not deemed adequate. The combination of high temperature and alkalinity produces an aggressive environment for

the reactor lining. Chemrec has used several refractory materials in the pilot units and the commercial atmospheric units. The refractories last from 1 to 18 months, with a replacement cost of up to 1 million dollars and several weeks of downtime. Severe refractory thinning occurred and several bricks were found lost from the upper part of the gasifier vessel during operation. The refractory lining is subjected to the penetration of sodium and subsequent reactions with alkali-rich molten smelt, such that the refractory undergoes significant volume change and strength degradation. Several refractory samples have been studied after immersion in molten smelt by Peascoe, Keiser, Hubbard, Brady and Gorog (2001). The results of their study are summarized below. For mullite based refractories, molten smelt first attacks mullite and forms sodium aluminum silicates. This reaction is accompanied by a volume change. A significant surface expansion occurs during immersion testing in smelt. Furthermore, a liquid phase can develop in the mullite refractory as Na_2O concentration increases. Surface expansion coupled with the loss of structural integrity lead to the spalling of the lining. MgAl_2O_4 spinel based refractories react with the smelt to form NaAlO_2 and MgO , with an associated expansion of 2.1% to 13%. For α/β -alumina refractories, expansion was accommodated partly through spalling and a significant radial expansion of the gasifier's lining. The alumina refractories show the least corrosion, the chemical expansion of alumina samples is from 0 to 0.7%. Due to this reason, fused cast alumina which is expansive and sensitive to thermal shock is being used in the most recent commercial high temperature black liquor gasifier at New Burn, SC, USA, [Brown, Leary, Gorog and Abdullah (2004)].

During Task 1.1 of this study candidate refractory materials suitable black liquor smelt containment were determined through a combination of thermodynamic calculations and phase diagrams. During Task 1.2 samples were made of the candidate materials for property measurements including density, porosity, smelt contact angles and reaction products. During Task 1.3 refractory materials developed by the in-kind cost share partners were tested in a cup test with a simulative environment to determine the resistance of refractory materials that can be produced commercially to black liquor smelt. Refractories provided by in-kind sponsors were tested by cup testing, density/porosity determinations, chemical analysis and microscopy. The best performing materials in the cup testing were fused cast materials. However, 2 castables appear to outperforming any of the previously tested materials and may perform better than the fused cast materials in operation. Additionally, A mortar was developed to bond fused cast spinel brick. ORNL found this mortar outperformed all other mortars submitted. The basis of the high performance of these materials is the low open porosity and permeability to black liquor smelt. Task 1.4 was submittal of these materials to end-users for plant trials.

EXECUTIVE SUMMARY

Black liquor gasification is a high potential technology for production of energy which allows substitution for other sources of energy. This process uses a waste of the pulp and paper industry as black liquor to produce synthetic gas and steam for production of electricity; therefore development of this technology not only recovers the waste of the paper industry but also decreases dependency on fossil fuel.

Today one of the main obstacles in the development of this technology is the development of refractory materials for protective lining of the gasifier. So far the materials used for this application have been based on alumino-silicate refractories but, thermodynamics and experience shows that these materials are not sufficiently resistant to black liquor under the harsh working conditions of Black liquor gasifiers. Consequently development of cost-effective materials with improved performance in gasifier environments to answer the material challenges presented by black liquor gasification (HTHP, HTLP) is the objective of this project. Refractories provided by in-kind sponsors were tested by cup testing, density/porosity determinations, chemical analysis and microscopy. The best performing materials in the cup testing were fused cast materials. However, MORCO PhosGun M-90-O appears to outperforming any of the previously tested materials and may perform better than the fused cast materials in operation at less than 1/3 the current cost. Additionally, a mortar was developed to bond fused cast spinel brick. ORNL found this mortar outperformed all other mortars submitted. The basis of the high performance of these materials is the low open porosity and permeability to black liquor smelt. Task 1.4 was submittal of these materials to end-users for plant trials.

EXPERIMENTAL

Samples were submitted for industrial trial. Representatives from UMR traveled to give recommendations, observe the installation and acquire post-mortem samples as appropriate.

RESULTS AND DISCUSSION

The best performing materials in the cup testing were fused cast materials. MORCO PhosGun M-90-O appears to be outperforming any of the previously tested materials.

Figure 2 MORCOCOat SP-P after 100 hr. immersion in BL smelt. Showing minimal to no reaction.

This sample, MORCOCOat SP-P was put through our immersion test for 100 hours of exposure at 1000C, shown in Figure 2. The mortar is applied in a cut made in a piece of Monofrax L. It performed very well. Most mortar materials show some swelling which is evident by the material extending beyond the bottom of the Monofrax L sample. This was minimal on this sample. Additionally, the swelling of the mortar material can be severe enough in some cases to actually break the L material. This mortar should be used as the mortar in future installations.

Refractory materials were evaluated and modeled to be used in the pulse combustors, shown in Figure 3, that are failing at Big Island and Trenton.

Figure 3 Picture of failed pulse combustor tube sheet.

An enlargement showing the critical delamination at a depth of 5-6" into the 11" thick by 5' diameter panel is shown in Figure 4. The delamination eventually would lead to blockage of the heat exchanger tubes and necessitates refractory replacement. Material properties of two possible replacement materials have been measured and a finite element model of the tube sheet was developed.

Figure 4 Enlargement showing critical delamination failure at 5-6" in depth and accompanying transverse cracking.

The AZ-10 material installed at Big Island failed in 2 pulse heaters due to improper installation and in 2 pulse heaters due to attack by gases generated by the surrounding Pligun LWI28 insulating castable. It is currently believed that the AZ10 is not strong enough for use in the pulse heater and that chemical attack from other refractory materials is leading to failure in the tube sheet. MORCO is redesigning the AZ10 to have higher strength and better flow characteristics. Optional materials for this installation are 90+ % alumina dense refractories. It is important that all refractory materials be compatible.

CONCLUSION

Samples provided by in-kind sponsors were submitted for industrial trial. MORCO PhosGun M-90-O may outperform any of the previously tested materials at approximately 1/3 the cost of current fused cast linings. Gunned materials as overlays and patches may be able to improve the lifetime of the reactor with hydration prone materials such as magnesia backing them up.

MORCOCoat SP-P performed better than any other tested mortar against BL smelt and should be used as the mortar in future installations.

A fused cast magnesia or spinel should perform better than other fused cast materials. However, during shutdowns magnesia would be prone to hydration and thus problematic.

Spinel would form a dense magnesia layer, as shown in Task 1.2, that would be prone to hydration and may slough off during shutdowns.

Low open porosity and permeability appear to be important for materials although it can not be proven by the current work. Low permeability spinel and magnesia castables should be formulated and investigated. It is also show that materials that form a viscous glass smelt refractory interface layer perform well. This has not been proven in the field and may be detrimental to green liquor quality or may be rapidly removed by scouring action of the liquid with entrained solids smelt washing down the interface layer.

Gasifier end-users are still experiencing major refractory problems. Refractories are one of many issues still slowing use of this energy saving technology. Without continued assistance from DOE black liquor gasifiers currently in use may be shut down and future work abandoned.

REFERENCES

- Stigsson, L. (1998): Chemrec™ Black Liquor Gasification. *International Chemical Recovery Conference*, pp. 663-674.
- Brown, C. A.; Hunter, W. D. (1998): Operating Experience at North America's First Commercial Black Liquor Gasification Plant. *International Chemical Recovery Conference*, pp. 655-662.
- Dickinson, J. A.; Verrill, C. L.; Kitto, J. B. (1998): Development and Evaluation of a Low-Temperature Gasification Process for Chemical Recovery from Kraft Black Liquor. *International Chemical Recovery Conference*, June 1-4.
- Taber, W. A. (2003): Refectories for Gasification. *Refectories Applications and News*, Vol. 8[4], pp. 18-22.
- Larson, E. D.; Consonni, S.; Katofsky, R. E. (2003): A Cost-Benefit Assessment of Biomass Gasification Power Generation in the Pulp and Paper Industry. *Final report, Princeton University, Navigant Consulting, Inc., and Dipartimento di Energetica*.
- Brown, C.; Landalv, I. (2001): The Chemrec Black Liquor Recovery Technology – A Status Report. *International Chemical Recovery Conference*, Whistler, B.C.
- Kelleher, E. G.; Kohl, A. L. (1986): Black Liquor Gasification Technology. *Presented at the 1986 Summer National Meeting*, American Institute of Chemical Engineers, August 24-28.
- Peascoe, R. A.; Keiser, J. R.; Hubbard, C. R.; Brady, M. P.; Gorog, J. P. (2001): Performance of Selected Materials in Molten Alkali Salts. *International Symposium on Corrosion in the Pulp & Paper Industry*, pp. 189-200.
- Brown, C. A.; Leary, R.; Gorog, J. P.; Abdullah, Z. (2004): The Chemrec Black Liquor Gasifier at New Bern – A Status Report. *2004 International Chemical Recovery Conference*, pp. 1089- 1093.
- Kachanov, L. M. (1958): Rupture Time under Creep Conditions. *Izv. Acad. Nauk USSR, OTN*, Vol. 8, pp. 26-31.
- Lemaitre, J. (1985): A Continuum Damage Mechanics Model for Ductile Fracture. *J. Engrg. Mat. and Technol.*, Vol. 107[1], pp. 83-89.
- Kachanov, L. M. (1986): Introduction to Continuum Damage Mechanics. Martinus Nijhoff Publishers, Dordrecht, the Netherlands.
- Chaboche, J. L. (1988): Continuum Damage Mechanics, Part I & II. *J. Appl. Mech.*, Vol. 55, pp. 59-72.
- Hillerborg, A.; Modeer, M.; Petersson, P. E. (1976): Analysis of Crack Formation and Crack Growth in Concrete by Means of Fracture Mechanics and Finite Elements. *Cement and Concrete Research*, Vol. 6, pp. 773-782.
- Lublimer, J.; Oliver, J.; Oller, S.; Oñate, E. (1989): A Plastic-Damage Model for Concrete. *International Journal of Solids and Structures*, Vol. 25, pp. 299-329.
- Lee, J.; Fenves, G. L. (1998): Plastic-Damage Model for Cyclic Loading of Concrete Structures. *Journal of Engineering Mechanics*, Vol. 124[8], pp. 892-900.
- Saetta, A.; Scotta, R.; Vitaliani, R. (1998): Mechanical Behavior of Concrete Under Physical-Chemical Attacks. *Journal of Engineering Mechanics*, pp. 1100-1109.
- Schacht, C. A. (1995): Refractory Linings. Marcel Dekker, Inc.
- Boisse, P.; Gasser, A.; Rousseau, J. (2002): Computations of Refractory Lining Structures Under Thermal Loadings. *Advances in Engineering Software*, Vol. 33, pp. 487-496.

Buyukozturk, O.; Tseng, T. (1982): Thermomechanical Behavior of Refractory Concrete Lining. *Journal of the American Ceramic Society*, Vol. 65[6], pp. 301-307.

Chen, E. (1990): Simulation of the Thermomechanical Behavior of Monolithic Refractory Lining in Coal Gasifier Environment. *Radex Rundschau*, Vol. 4, pp. 376-384.

Hibbitt, Karlsson & Sorensen, INC. (2002): ABAQUS/Standard User's Manual. Version 6.3.

Hemrick, J. G. (2001): Creep Behavior and Physical Characterization of Fusion-Cast Alumina Refractories. PhD Dissertation, University of Missouri-Rolla.

<http://www.matweb.com>. MatWeb.com, a division of Automation Creations, Inc.

<http://www.ceramics.nist.gov>. NIST WebSCD Database, Ceramic division, National Institute of Standards and Technology.

BIBLIOGRAPHY

"Coal Gasification for Power Generation",

http://www.dti.gov.uk/energy/developpep/chevron_texaco_part2.pdf

"Gasification of Solid and Liquid Fuels for Power Generation", Technology status report to Department of Trade and Industry, 1998,

<http://www.dti.gov.uk/energy/coal/cfft/cct/pub/tsr008.pdf>

"ABAQUS/Standard User's Manual," version 6.3, Hibbitt, Karlsson and Sorensen, Inc., 2000

"Refractories Handbook," The Technical Association of Refractories, Japan, 1998

A. R. Cooper, Jr, W. D. Kingery, "Dissolution in Ceramic Systems: I, Molecular Diffusion, Natural Convection and Forced Studies of Sapphire Dissolution in Calcium Aluminum Silicate", *J. Am. Ceram. Soc.*, 47 [1], 37- 43, 1964.

Alexander Klein, "Gasification: An Alternative Process for Energy Recovery and Disposal of Municipal Solid Wastes", Master Thesis, Columbia University, 2002,

Ayhan Demirbas, "Pyrolysis and Steam Gasification Processes of Black Liquor," *Energy Conversion and Management*, 43, 877-884, 2002

B. N. Samaddar, W. D. Kingery, A. R. Cooper, "Dissolution in Ceramic Systems: II, Dissolution of Alumina, Mullite, Anorthite, and Silica in a Calcium-Aluminum-Silicate Slag", *J. Am. Ceram. Soc.*, 47 [5] 249-254.

Barrie H. Bieler, "Corrosion of AZS, Zircon and Silica Refractories by Vapors of NaOH and of Na₂CO₃", *J. Am. Ceram. Soc. Bull.*, 61[7], 745-749, (1982).

Brown, N.R. "Alkali Vapor Attack of Alumino-Silicate refractories", *Proceedings of International Ceramic Conference: AUSTCERAM 88*, Sydney, pp.711-715, (1988).

C. A. Brown and W. D. Hunter, "Operating Experience at North America's First Commercial Black Liquor Gasification Plant", *International Chemical Recovery Conference*, 655-662, 1998

C. Brown, I. Landalv, "The Chemrec Black Liquor Recovery Technology – A Status Report," 2001 *International Chemical Recovery Conference*, Whistler, B.C., 2001

C. Wagner, "The Dissolution Rate of Sodium Chloride with Diffusion and Natural Convection as Rate-Determining Factors", *J. Phys. Colloid Chem.*, 53, 1030-33, 1949.

Craig A. Brown and W. Densmore Hunter, "Operating Experience at North America's First Commercial Black Liquor Gasification Plant", *International Chemical Recovery Conference*, 655-662, 1998

Craig A. Brown, Ray Leary, J. Peter Gorog and Zia Abdullah, "The Chemrec Black Liquor Gasifier at New Bern – A Status Report," 2004 *International Chemical Recovery Conference*, 1089- 1093, 2004

D. A. Weirauch Jr, J. E. Lazaroff and P. D. Ownby, "Wetting in an Electric Packaging Ceramic System: II, Wetting of Alumina by a Silicate Glass Melt under Controlled PO₂ conditions," *J. Am. Ceram. Soc.*, 78 [11] 2923-28 (1995).

Dave G. Newport, Lee N. Rockvam and Robert S. Rowbottom, "Leading Paper-Black Liquor Steam Reformer Start-up at Norampac," Presented at 2004 International Chemical Recovery Conference, Charleston, SC, June, 2004

Dominic Au, S. Cockcroft and D. Maijer, "Crack Defect Formation During Manufacture of Fused Cast Alumina Refractories," Metallurgical and Materials Transactions, **33A**, 2053-2065, 2002

E. G. Kelleher and A. L. Kohl, "Black Liquor Gasification Technology", Presented at the 1986 Summer National Meeting, American Institute of Chemical Engineers, August 24-28, 1986

E. Gmelin, M. Asen-Palmer, M. Reuther and R. Villar, "Thermal Boundary Resistance of Mechanical Contacts between Solids at Sub-ambient Temperatures," J. Phys. D: Appl. Phys. **32** R19-R43, 1999

E. Marotta, S. Mazzuca and J. Norley, "Thermal Joint Conductance for Graphite Materials," <http://www.electronics-cooling.com>

EnSheng Chen, "Simulation of The Thermomechanical Behavior of Monolithic Refractory Lining in Coal Gasification Environment," Radex Rundschau, 4, 376-384, 1990

Eric D. Larson and Delmar R. Rqymond, "Commercializing Black Liquor and Biomass Gasifier/Gas Turbine Technology", TAPPI Journal, 50 – 57, 1997

Eric D. Larson, Stefano Consonni, and Ryan E. Katofsky, "A Cost-Benefit Assessment of Biomass Gasification Power Generation in the Pulp and Paper Industry," Final report, Princeton University, Navigant Consulting, Inc., and Dipartimento di Energetica, 2003

Gupta Abha, Rajan Nidhi, Mathur R.M. and Kulkarni A.G., "Development of Lignin By-Products for Industrial Applications", IPPTA Convention, 13, 49-55, 2001

<http://www.ceramics.nist.gov>

<http://www.matweb.com>

J. A. Dickinson, C. L. Verrill and J. B. Kitto, "Development and Evaluation of a Low-Temperature Gasification Process for Chemical Recovery from Kraft Black Liquor," International Chemical Recovery Conference, June 1-4, 1998

J. E. Lazaroff and P. D. Ownby, "Wetting in an Electric Packaging Ceramic System: I, Wetting of Tungsten by Glass in Controlled Oxygen Partial Pressure Atmospheres," J. Am. Ceram. Soc., **78** [3] 539-44 (1995).

J. G. Hemrick, "Creep Behavior and Physical Characterization of Fusion-Cast Alumina Refractories", PhD Dissertation, University of Missouri-Rolla, 2001

J. Gullichsen, H. Paulapuro, "Chemical Pulping, Paper Making Science and Technology", Book 6B.

J. Rawers, J. Kwong, and J. Bennett, "Characterizing Coal-gasifier Slag-refractory Interactions," Materials at High Temperatures, 16[4] 219-222, 1999

J. Sweeney and M. Cross, "Analyzing the Stress Response of Commercial Refractory Structures in Service at High Temperatures, II. A Thermal Stress Model for Refractory Structures," *Trans. J. Br. Ceram. Soc.*, 81, 47-52, 1982

James Cantrell, P.E., "Simulation of Kraft Black Liquor Gasification – A Comparative Look at Performance and Economics", *Engineering/Fishing & Converting Conference & Trade Fair*, 1181-1195, 2001

K. Andreev, H. Harmuth, "FEM Simulation of The Thermo-mechanical Behaviour and Failure of Refractories - A Case Study," *Journal of Materials Processing Technology*, 143-144[1] 72-77, 2003

K. McAlister & E. Wolfe, "A Study of the Effects of Alkali Attack on Refractories Used in Incineration", *Proceedings of Incineration Conference*, Albuquerque, New Mexico, pp.631-638 (1992).

Keijo Salmenoja, "Black-Liquor Gasification: Theoretical and Experimental Studies," *Bioresource Technology*, 46, 167-171, 1993

Ken Patrick, "Gasification Edges Closer to Commercial Readily with Three N.A. Mill Startups", *PaperAge*, 30-33, 2003

Kennedy, Christopher R, "Alkali attack on mullite refractory in the grand forks energy technology center slagging gasifier", *Journal of Materials for Energy Systems*, 3[N-1, June] 27-31, (1981).

Kenneth T. Hood and Gunnar B. Henningsen, "Black Liquor Gasification...Evaluation of Past Experience in order to Define the Roadmap of the Future Pathway", *TAPPI Fall Conference & Trade Fair*, 1451-1463, 2002

Kirk J. Finchem, "Black Liquor Gasification Research Yields Recovery Options for Future", 69[11] 51-59, 1995

L. Reed, L. R. Barrett, "The Slagging of Refractories, I. The Controlling Mechanism in Refractory Corrosion", *Trans. Brit. Ceram. Soc.*, 54, 671-676, 1955.

L. Reed, L. R. Barrett, "The Slagging of Refractories, II. The Kinetics of Corrosion", *Trans. Brit. Ceram. Soc.* 63, 509-534, 1964.

Lars Stigsson, "Chemrec™ Black Liquor Gasification," *International Chemical Recovery Conference*, 663-674, 1998

LeBlanc, John R, "Brockway's Lower Checker Sulfate Test", *J. Can. Ceram. Society*, 52, 58-60, (1983).

M. L. Millard, "The Effect of Microstructure on the Liquid Corrosion of Sodium Chloride and Aluminum Oxide", Ph.D. Dissertation, Department of Ceramic Engineering, University of Missouri-Rolla, 1982.

M. M. Akiyoshi, R. Pereira, A. P. da Silva and V. C. Pandolfelli, "Thermal Conductivity of Refractories," *American Ceramic Society Bulletin*, 82 [6] 29-33, 2003

M. M. Yovanovich, "New XContact and Gap Correlations for Conforming Rough Surface," AIAA-81-1164, presented at AIAA 16th Thermophysics Conference, Palo Alto, CA., June 1981

- M. P. Borom, R. H. Arendt, "Dissolution of Oxides of Y, Al, Mg, and La by Molten Fluorides", *Ceramic Bulletin*, 60 [11], 1169-1174, 1981.
- Magnus Marklund, "Black Liquor Recovery: How Does It Work?" ETC, (Energy Technology Center, Sweden, http://www.etcpitea.se/blg/document/PBLG_or_RB.pdf)
- Mikael Ahlroth, Gunnar Svedberg, "Case Study on Simultaneous Gasification of Black Liquor and Biomass in a Pulp Mill," *International Gas Turbine & Aeroengine Congress & Exhibition*, 1998
- N. McCallum, L. R. Barrett, "Some Aspects of the Corrosion of Refractories", *Trans. Brit. Ceram. Soc.*, 51, 523-543, 1952.
- Oral Buyukozturk and Tsi-Ming Tseng, "Thermomechanical Behavior of Refractory Concrete Lining," *Journal of the American Ceramic Society*, 65[6] 301-307, 1982
- P. D. Ownby, Ke Wen K. Li, D. A. Weirauch Jr, "High Temperature Wetting of Sapphire by Aluminum," *J. Am. Ceram. Soc.*, **74** [6] 1275-81 (1991).
- R. A. McCauley, "Corrosion of Ceramics", 1994, New York, Marcel Deker.
- R. A. Peascoe, J. R. Keiser, "Performance of Selected Materials in Molten Alkali Salts", 10th International Symposium on Corrosion in the Pulp and Paper Industry (10th ISCPPI); Marina Congress Center, Helsinki, Finland, pp189-200, 2001.
- R. A. Peascoe, J. R. Keiser, C. R. Hubbard, J. P. Gorog, C. A. Brown and B. H. Nilsson, "Comparison of Refractory Performance in Black Liquor Gasifiers and A Smelt Test System," 2001 International Chemical Recovery Conference, Whistler, B.C., 2001
- R. A. Peascoe, J. R. Keiser, C. R. Hubbard, M. P. Brady and J. P. Gorog, "Performance of selected materials in molten alkali salts," *International Symposium on Corrosion in the Pulp & Paper Industry* 2001, 189-200, 2001
- R. B. Hetnarski, "Thermal Stresses I," Elsevier Science Publications B.V., 1986
- R. Sangiorgi, "Corrosion of Ceramics by Liquid Metals", *NATO ASI Ser., Ser E., Applied Sciences*, Vol. 267, pp. 261-84, 1994
- Robert A. Peascoe, James R. Keiser, Camden R. Hubbard, Michael P. Brady and J. Peter Gorog, "Performance of selected materials in molten alkali salts," *International Symposium on Corrosion in the Pulp & Paper Industry* 2001, 189-200, 2001
- S. E. Feldman, W. K. Lu, "Kinetics of the Reactions between Silica and Alumino-Silicate Refractories and Molten Iron", *Metallurgical Transactions*, 5, 249-253, 1974.
- S. L. Cockcroft, J. K. Brimacombe, D. G. Walrod and T. A. Myles, "Thermal Stress Analysis of Fused-Cast AZS Refractories during Production: Part II, Development of Thermo-elastic Stress Model," *J. Am. Ceram. Soc.*, **77** [6] 1512-1521, 1994
- S. Song, M. M. Yovanovich and F. O. Goodman, "Thermal Gap Conductance of Conforming Surface in Contact," *Journal of Heat Transfer*, **115**, 533-540, 1993
- Shigekastu Mori et. al., "Gasification Process of Organic Wastes for Electric Power Generation by Fuel Cell", http://www.cape.canterbury.ac.nz/Apcche_Proceedings/APCChE/Data/720REV.pdf

Suat Yilmaz, "Thermomechanical Modeling for Refractory Lining of a Steel Ladle Lifted by Crane," *Steel Research*, 74[8] 485-490, 2003

Tadaoki Fukui, "Corrosion of Zircon Refractories by Vapors of Sodium Compounds", *Ashi Gvasu Kenkyu Hokoku*, **17**(2), 77-98 (1967).

Terry N. Adams, "Black Liquor Properties, Crystallization, and Sodium Salt Scaling in Concentrators," TAPPI 2001 Pulp Conference, 1209-1222, 2001

Thomas, Everett A, "A Study of Soda and Potash Vapor Attack on Super Structure Refractories", *J. Can. Ceram. Soc*, **44**, 37-41 (1975).

V. G. Levich, "Physicochemical Hydrodynamics", 1962. Englewood Cliffs, NJ, USA, Prentice-Hall.

V. W. Antonetti and M. M. Yovanovich, "Thermal Contact Resistance in Microelectronic Equipment," in "Thermal Management Concepts in Microelectronic Packaging from Component to System," ISHM Technical Monograph Series 6984-003, 135-151, 1984

W. A. Taber, "Refractories for Gasification," *Refractories Applications and News*, **8**[4] 18-22, 2003

W. D. Kingery, H. K. Bowen, D. R. Uhlmann, "Introduction to Ceramics", Second ed. , John Wiley & Sons. New York, 1976.

W. E. Lee, S. Zhang, "Melt Corrosion of Oxide and Oxide-Carbon Refractories", A Review from Dept. of Engineering Materials, University of Sheffield, UK., 1999.

Xiaoting Liang, "Modeling of Thermomechanical, Cracking and Creep Behavior in Glasstank Crown," MS Thesis, University of Missouri-Rolla, 2003

Y. A. Cengel and R. H. Turner, "Fundamentals of Thermal-Fluid Sciences," McGraw-Hill Higher Education, 2001

Y. Chung, "Corrosion of Partially Stabilized Zirconia by Steelmaking Slags", M.S. Thesis, Department of Ceramic Engineering, University of Missouri-Rolla, 1993.

Y. Kuromitsu, H. Yoshida, "Interaction between Alumina and Binary Glasses", *J. Am. Ceram. Soc*, **80** [6] 1583-87, 1997.

Yamaguchi, A, "Reactions between Alkaline Vapors and Refractories for Glass Tank Furnaces", *Proceedings of International Congress on Glass*, Kyoto, Japan, pp.1-8 (1974).