JUN 26 1967

MASTER

Report No. AGN-8224
Contract AT(04-3)-368
Project Agreement No. 6

NPS

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 January through 31 March 1967

May 1967

**NUCLEAR PRODUCTS AND SERVICES GROUP
AEROJET - GENERAL CORPORATION
SAN RAMON, CALIFORNIA**

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

129

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Report No. AGN-8224
Contract AT(04-3)-368
Project Agreement No. 6

CFSTI PRICES

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

HQ \$300; MN 65

Quarterly Progress Report
1 January through 31 March 1967

Published

May 1967

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights, or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

APPROVED BY: RH Chesworth

R. H. Chesworth, Manager
Nuclear Engineering and Manufacturing
Operations

NUCLEAR PRODUCTS AND SERVICE GROUP
AEROJET-GENERAL CORPORATION
SAN RAMON, CALIFORNIA

LEGAL NOTICE

This report was prepared as an account of Government-sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or,

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

The information herein is regarded as preliminary and subject to further checking, verification, and analysis.

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

TABLE OF CONTENTS

	<u>Page</u>
1.0 <u>INTRODUCTION AND SUMMARY</u>	1
2.0 <u>TECHNICAL PROGRESS</u>	3
2.1 TASK A - OXIDATION STUDIES	3
2.1.1 <u>Task A-1, Low-Cobalt Tubing Control Specimen Evaluations</u>	3
2.1.2 <u>Task A-2, Commercial-Cobalt Specimen Evaluations</u>	28
2.1.3 <u>Task A-3, High Temperature Oxidation Studies</u>	38
2.2 TASK B - MECHANICAL PROPERTIES STUDIES	59
2.2.1 <u>Task B-2, Phase II, 1800°F Tests</u>	59
2.2.2 <u>Task B-3 - Adaptation of Centrifugal and Tensile Creep Apparatus for Inert Atmosphere Testing</u>	72
2.2.3 <u>Task B-4, 1300°F Creep Test in Argon Atmosphere</u>	72
REFERENCES	75
APPENDIX A- Derivation on the Deflection-Strain Relation for Circular Bending	A-1
APPENDIX B - Computer Program	B-1 B-1

LIST OF TABLES

<u>No.</u>		<u>Page</u>
1	Typical X-ray Pattern of Products Electrolytically Digested from Hastelloy-X Heat E9517 Aged in Air at 1450°F for 2500 and 10,000 Hours	4
2	Hastelloy X Low-Cobalt Tubing Control Specimens Analyzed by Particle Extraction (10% HCl/Methanol) and X-ray Diffraction	5
3	Typical X-ray Pattern of Hastelloy X Spallation Products Obtained through 1750°F Thermo-Gravimetric Oxidation Tests	6
4	X-ray Diffraction Standard for Hastelloy X Oxide	7
5	Results of Quantitative Analyses of Precipitates in Specimen V ₂ -5-8	12
6	Results of X-ray Diffraction Analyses Performed on Specimen E9517 Residue (HCl Extraction) Aged 10,000 Hours in Air at 1300°F Following Various Leaching Operations Using Murakamais' Reagent	14
7	Experimental Electron Diffraction Pattern Compared to Published Values for M ₆ C Carbides	24
8	Experimental Electron Diffraction Pattern Compared to Published X-ray Diffraction Patterns for Sigma Phase	25
9	Experimental Electron Diffraction Pattern Compared to Published X-ray Diffraction Pattern for Chi Phase	25
10	Experimental Electron Diffraction Pattern Compared to Published X-ray Diffraction Pattern for Sigma Phase	26
11	Hastelloy X Commercial-Cobalt Tubing Control Specimens Analyzed by Particle Extraction (10% HCl/Methanol) and X-ray diffraction	28
12	Occurrence of Sigma Phase (Ni-Cr-Mo) in Various Hastelloy X Heats Following the Indicated Aging Histories	30
13	Results of Quantitative Analysis of Precipitates in Specimen E ₃ -4-4	31
14	Results of Quantitative Analysis of Precipitates in Specimen S ₂ -2-1	36
15	Room Temperature Tensile Properties of Hastelloy X Sheet Specimens Aged in Air at 1900°F	52

LIST OF TABLES- CONTINUED

<u>No.</u>		<u>Page</u>
16	Room Temperature Tensile Properties of Hastelloy X Tubing Heats Aged at 1900 and 2000°F in Air for Various Times	54
17	Typical X-ray Pattern of Products Electrolytically Digested from Hastelloy X Sheet Heats Aged in Air for 7500 Hours at 1900 and 2000°F	57
18	Representative X-ray Patterns of Surface Oxides for Hastelloy X Sheet Specimens Aged in Air for 7500 Hours at 1900 and 2000°F	58
19	Stress-Strain Data for Hastelloy X Tested in Centrifugal Creep at 1800°F in Air	67

LIST OF FIGURES

<u>No.</u>		<u>Page</u>
1	Reproductions of Electron Microprobe (MACX) Traces for Specimen of Hastelloy X Aged 10,000 hr in Air at 1600°F	9
2	Reproductions of Electron Microprobe Point-Counting Traverses for Specimen of Hastelloy X Aged 10,000 hr in Air at 1750°F	11
3	X-ray Scanning Images for a Specimen of Hastelloy X Low-Cobalt Tubing Aged 10,000 hr in Air at 1600°F	15
4	Microstructure of Hastelloy X Tubing Aged in Air at 1300°F for 10,000 hr	18
5	Electron Scanning Micrograph of Hastelloy X Tubing Aged at 1300°F for 10,000 hr	18
6	Electron Micrograph of Hastelloy X Tubing Aged 10,000 hr in Air at 1300°F	20
7	Electron Micrograph of Hastelloy X Tubing Aged 10,000 hr in Air at 1300°F	20
8	Electron Micrograph of Specimen of Hastelloy X Low-Cobalt Tubing Aged in Air for 2500 hr at 1300°F	21
9	Electron Micrograph of Specimen of Hastelloy X Low-Cobalt Tubing Aged in Inert Gas for 2500 hr at 1300°F	21

LIST OF FIGURES - CONTINUED

<u>No.</u>		<u>Page</u>
10	Carbon Extraction Replica Showing Rods of Sigma Phase Nucleating from Large M_6C Carbide Particles	22
11	Carbon Extraction Replica Showing Clusters of Rectangular Platelets	22
12	Transmission Micrograph of Large Particles shown in Figure 10 Identified as M_6C by Selected-Area Diffraction	23
13	Transmission Micrograph of Rod-Shaped Precipitates shown in Figure 10 Identified as Sigma Phase by Selected-Area Diffraction	23
14	Carbon Extraction Replica showing Shape of Sigma Phase Particles Electrolytically Digested from Specimen of Heat E9517 Aged 10,000 hr at 1300°F and Separated from Carbide Particles by Treatment with Murakamais' Reagent	27
15	X-ray Scanning Images for a Specimen of Hastelloy X Commercial-Cobalt Tubing Aged 5820 hr in Air at 1750°F	33
16	Reproductions of Electron Microprobe MACX Traces for a Specimen of Hastelloy X Heat X14593 Specimens Aged 5820 hr in Air at 1750°F	35
17	Electron Micrograph of Hastelloy X Commercial-Cobalt Tubing Aged 10,000 hr in Air at 1600°F	37
18	Electron Micrograph of Hastelloy X Commercial-Cobalt Tubing Aged 10,000 hr in Air at 1750°F	37
19	Typical Microstructures of Heat E9517 Specimens Aged 7500 hr in Air at 1900°F	39
20	Typical Microstructures of Heat E9517 Specimens Aged 7500 hr in Air at 2000°F	40
21	Typical Microstructures of Heat X14593 Specimens Aged 7500 hr in Air at 1900°F	42
22	Typical Microstructures of Heat X14593 Specimens Aged 7500 hr in Air at 2000°F	43
23	Appearance of Duplex Oxide Observed on Specimens of Heat X14593 Aged 7500 hr in Air at 2000°F	44
24	Typical Microstructures of Heat X4762 Specimens Aged 7500 hr in Air at 1900°F	46

LIST OF FIGURES - CONTINUED

<u>No.</u>		<u>Page</u>
25	Typical Microstructures of Heat E9505 Specimens Aged 7500 hr in Air at 1900°F	46
26	Typical Microstructures of Heat X34381 Specimens Aged 7500 hr in Air at 1900°F	47
27	Typical Microstructures of Heat X4762 Specimens Aged 7500 hr in Air at 2000°F	48
28	Typical Microstructures of Heat E9505 Specimens Aged 7500 hr in Air at 2000°F	49
29	Typical Microstructures of Heat X34381 Specimens Aged 7500 hr in Air at 2000°F	50
30	Room Temperature Tensile Properties of Various Hastelloy X Sheet Heats Exposed in Air at 1900°F	53
31	Room Temperature Tensile Properties of Two Tubing Heats Aged in Air at 1900°F	55
32	Typical Centrifugal Creep Test Specimen	61
33	Centrifugal Creep Data - Strain vs. Time for Hastelloy X Heat 4902	63
34	Centrifugal Creep Data - Strain vs. Time for Hastelloy X Heat 4793	64
35	Centrifugal Creep Data - Strain vs. Time for Hastelloy X Heat 4787	65
36	Strain vs. Stress for Hastelloy X Heat 4902	69
37	Strain vs. Stress for Hastelloy X Heat 4793	70
38	Strain vs. Stress for Hastelloy X Heat 4787	71
39	Modified Centrifugal Creep Machine for Inert Atmosphere Testing	73

EVALUATION STUDY OF HASTELLOY X AS A
NUCLEAR CLADDING

Quarterly Progress Report
1 January through 31 March 1967

1.0 INTRODUCTION AND SUMMARY

This report has been prepared to summarize technical progress during the period from 1 January through 31 March 1967 under the program to evaluate Hastelloy X as a cladding material for nuclear fuels. The reported work is authorized by Project Agreement No. 6 of Contract AT(04-3)-368 between the USAEC and the Aerojet-General Corporation (AGC). The work was performed, primarily, at San Ramon, California, by personnel of the Nuclear Engineering and Manufacturing Operations of the Nuclear Products and Services Group of AGC.

Microconstituent analysis of low and commercial cobalt tubing control specimens revealed that the primary constituent present in the matrix following aging at all temperatures (including 2000°F) is M_6C . $M_{23}C_6$ is also present as a minor phase following aging at all temperatures except 1800, 1900 and 2000°F, although it was less prominent following exposure at 1750°F. Sigma phase identifications following aging at 1300 and 1450°F, presented in earlier reports, have been refined.

A duplex oxide film is formed on Hastelloy X at all exposure temperatures. The outer layer, as evaluated by electron microprobe analysis, was found to be rich in manganese and chromium ($MnCr_2O_4$); the inner layer is composed largely of chromium (Cr_2O_3). Very little nickel was identified in either layer. A standard X-ray diffraction pattern has been established for the $MnCr_2O_4$ outer oxide layer based upon data developed in this program.

The carbide particles present in exposed Hastelloy X were analyzed by point-counting techniques. The data indicate that the composition of the carbides varies between $M_{3.5}$ and $M_{15}C$, rather than the more commonly accepted M_6C .

Metallographic examination of low and commercial cobalt tubing exposed for 7500 hr at 1900 and 2000°F was completed. Major differences in oxidation effects were observed between the two types of tubing. Corrosion in the low cobalt tubing was largely by internal oxidation. A major depleted zone was detected in the commercial cobalt material. This depleted zone was also present on commercial cobalt tubing examined previously and exposed at 1750 and 1800°F. The oxidation attack in all sheet specimens was similar; internal oxidation occurred but no depleted zone was observed.

A uniform duplex oxide film formed on specimens exposed at 1900°F; this formation was characteristic of all the specimens examined. Severe oxide film spalling was observed on all specimens aged at 2000°F although the residual film was of the characteristic duplex form.

Room temperature tensile testing of sheet and tubing exposed at 1900°F revealed a general reduction in ultimate and yield strength as a function of exposure duration. Elongation properties of the sheet material varied only slightly as a function of exposure time. The ductility of tubing was reduced to a greater degree than that of the sheet material.

Data from an 1800°F, 1000 hr centrifugal creep test of four Hastelloy X heats in air was analyzed. In specimens where the total strain was less than 1%, a linear relationship existed between strain and time. The linear relationship did not exist at higher total strains. The difference has been attributed, primarily, to residual stresses present in the specimens.

The centrifugal creep machine was modified to permit testing in an inert gas environment. The computer code used to analyze the centrifugal creep test deflection data and to transform the data into uniaxial creep data was converted from FORTRAN II to FORTRAN IV. In the course of this conversion, some refinement was also made to improve accuracy; the program is included as an appendix to this report.

2.0 TECHNICAL PROGRESS

2.1 TASK A - OXIDATION STUDIES, G. W. Titus and W. L. Clarke, Jr.

2.1.1 Task A-1, Low Cobalt Tubing Control Specimen Evaluations

2.1.1.1 Microconstituent Extraction and Analyses

The completion of the microconstituent characterization of low-cobalt tubing control specimens required the evaluation of specimens aged in air at 1450°F for various times. Specimens exposed for 2500 and 10,000 hr at 1450°F were electrolytically digested in a 10% HCl/methanol solution at approximately 2 amps/in². The resultant residues were analyzed by X-ray diffraction; the patterns determined by this analysis are shown, along with the published values, in Table 1. The primary constituents identified were sigma phase (of the Ni-Cr-Mo-type discussed earlier⁽¹⁾) and M₆C carbides.

A summary of the microconstituents identified in all of the Hastelloy X low-cobalt control specimens analyzed is presented in Table 2. As indicated in this table, M₆C is the main constituent present over the range of exposures evaluated. Sigma phase occurs in specimens aged at 1300 and 1450°F for both 2500 and 10,000 hr but was not detected in specimens aged at temperatures greater than 1450°F. It appears from these results that the re-solution temperature of sigma phase in Hastelloy X is between 1450 and 1600°F, irrespective of exposure duration.

(1) Superscript numbers in paranthesis identify references listed at the end of this report.

TABLE 1- TYPICAL X-RAY PATTERN OF PRODUCTS ELECTROLYTICALLY
DIGESTED FROM HASTELLOY-X HEAT E9517 AGED IN
AIR AT 1450°F FOR 2500 AND 10,000 HOURS

Experiment (2500 hrs)		Experiment (10,000 hrs)		M_6C^*		$\sigma(Ni-Cr-Mo)^{**}$	
<u>d</u>	<u>I</u>	<u>d</u>	<u>I</u>	<u>d</u>	<u>I</u>	<u>d</u>	<u>I</u>
2.731	15	2.70	25	2.72	50		
2.508	15	2.49	25	2.50	50		
2.386	5	2.361	25			2.39	W
2.315	5					2.29	MW
2.222	35	2.211	52	2.22	80		
2.169	10	2.154	15			2.15	MS
2.092	100	2.083	100	2.099	100	2.09	M
2.055	10					2.06	M
2.003	10					1.995	MS
1.958	10	1.952	25	1.956	80	1.955	MS
1.920	20	1.912	30	1.924	80	1.915	MS
1.815	10	1.802	10			1.815	VVW
1.525	10	1.516	15	1.521	50		
1.416	5	1.411	15	1.413	50		
1.327	5	1.323	11	1.325	50		
1.278	30	1.277	30	1.280	80		
1.092	15	1.092	11	1.090	65		
1.052	10	1.049	8	1.049	50		

* ASTM Index Card #11-546

** "Relations Between Microstructure and Creep Rupture Properties of Nickel-Base Alloys as Revealed by Over-Temperature Exposures,"
University of Michigan Report NASA-TN-D-1325, Sept. 1962.

The $M_{23}C_6$ (usually Cr-rich) carbide phase was noted in specimens exposed at the lower temperatures (1600°F and less), but was less prominent in specimens aged at 1750 and 1800°F. Apparently the $M_{23}C_6$ carbide transforms into the more stable M_6C carbide at higher temperatures, particularly after longer exposure (10,000 hr).

TABLE 2- HASTELLOY X LOW-COBALT TUBING CONTROL SPECIMENS
ANALYZED BY PARTICLE EXTRACTION (10% HCl/METHANOL)
AND X-RAY DIFFRACTION

Sample No.	Exposure History			Phases Present*
	Atm.	Temp., °F	Time, Hrs	
30	Air	1300	2500	(S) M_6C ; (S) σ ; (W) $M_{23}C_6$
32	"	1450	"	(S) M_6C ; (S) σ ; (W) $M_{23}C_6$
34	"	1600	"	(S) M_6C ; (W) $M_{23}C_6$
35	"	1750	"	(S) M_6C ; (VW) $M_{23}C_6$
29	"	1300	10,000	(S) M_6C ; (S) σ ; (W) $M_{23}C_6$
37	"	1450	"	(S) M_6C ; (W) σ ; (W) $M_{23}C_6$
28	"	1600	"	(S) M_6C ; (VW) $M_{23}C_6$
39	"	1750	"	(S) M_6C
27	"	1800	"	(S) M_6C

* S = Strong pattern (positive identification)

W = Medium to weak pattern (phase probably present)

VW = Very weak pattern (possibility of phase being present)

2.1.1.2 Oxidation Characteristics

In an effort to further characterize the oxide film present on Hastelloy X after exposure in air, samples of the oxides spalled from specimens exposed for 5000 hr at 1750°F during continuous weight-change tests (performed earlier⁽²⁾) were analyzed by X-ray diffraction. A typical X-ray pattern, representative of the eight samples analyzed, is shown in Table 3; note that excellent agreement exists for two oxide species (Cr_2O_3 and $MnCr_2O_4$ -spinel). The identification of $MnCr_2O_4$, rather than the more commonly reported⁽³⁾ $NiCr_2O_4$ spinel structure, is available for direct comparison. The d-spacings listed in Table 3 are consistent with those reported by GE-FPD⁽⁴⁾ for Rene Y (lanthanum modified-Hastelloy X), where both Cr_2O_3 and $MnCr_2O_4$ compounds were identified after oxidation tests at 2000°F.

A review of the patterns of other metallic oxides and mixed oxides reveals that the spinel structure of nickel-manganese oxide, nickel chromite, and manganese oxide have face-centered cubic patterns with intensity ratios

TABLE 3 - TYPICAL X-RAY PATTERN OF HASTELLOY X SPALLATION
PRODUCTS OBTAINED THROUGH 1750°F THERMO-
GRAVIMETRIC OXIDATION TESTS

Experiment		Cr ₂ O ₃ *		MnCr ₂ O ₄ **	
d	I	d	I	d	I
4.85	W			Omitted	
3.63	M	3.63	MS		
2.96	M			2.95	VW
2.65	M	2.67	VS		
2.53	S			2.53	S
2.47	M	2.48	VS		
2.26	VW	2.26	W		
2.17	W	2.18	M	2.16	W
2.10	W			2.10	VW
1.81	W	1.82	M		
1.72	W			1.720	VW
1.67	MW	1.67	S		
1.62	MW			1.619	W
1.49	MW			1.488	M
1.46	VW	1.47	MW		
1.43	VW	1.43	M		

* ASTM Index Card #6-0504 ($a_o = 4.954\text{\AA}$)

** GE-FPD for MnCr₂O₄ ($a_o = 8.42\text{\AA}$)

which approximately match most of the peaks attributed to MnCr₂O₄ in the pattern shown in Table 3. The eight oxide samples discussed above were combined, finely ground and analyzed with a narrow, highly aligned X-ray beam at slow scan speeds to obtain the most accurate X-ray diffraction pattern possible for use as a standard for MnCr₂O₄ for future comparisons. The Phillips Norelco X-ray machine used for this work was aligned with a 1.5° takeoff angle. The 2θ angle was set to within 0.03° of the 56.12° peak yielded by a silicon standard. The peaks observed from the small sample with a copper target tube and a nickel filter at 30 kv and 20 ma were not large but were sufficient to show the major features of the structure. The X-ray

diffraction pattern generated is shown in Table 4. The ASTM index for Cr_2O_3 (Card 6-0504) matches the measured pattern very closely for the first seven prominent lines although the small sample size (the width of the powder sample was about 5mm) resulted in less intense peaks at the low angle. After

TABLE 4 - X-RAY DIFFRACTION STANDARD FOR HASTELLOY X OXIDE

<u>2 θ Angle</u>	<u>d(Å)</u>	<u>Relative Intensity</u>
22.0-22.5	~ 4.0	~ 20 (very broad)
24.53	3.630	54
30.00	2.978	20
33.65	2.662	70
35.34	2.540 ₀	70
35.70	2.515 ₀	32
36.23	2.479 ₂	80
41.55	2.173 ₂	30
50.27	1.814	30 (broad)
54.89	1.672 ₄	100
56.72	1.623 ₀	20
62.32	1.489 ₈	32
63.47	1.465 ₅	22

subtracting the Cr_2O_3 pattern, the derived pattern for the MnCr_2O_4 spinel is:

<u>d(Å)</u>	<u>Relative Intensity</u>
~ 4.0	~ 20 (very broad)
2.978	20
2.540 ₀	70
2.515 ₀	32
1.623 ₀	20
1.489 ₈	32

The line at 4.0 is really too broad and weak to speculate about its origin. However, the next low-angle peak in the face-centered cubic system is 4.8, with an hkl of (111). This would correspond to the 4.85 peaks obtained experimentally for all the eight oxide samples when analyzed separately

(Table 3), and would yield a lattice constant of $8.42\text{\AA}$, which is consistent with that determined for the standard pattern. The line at 2.515_{o} is readily attributed to the most intense peak from the face-centered cubic structure of chromic oxide (ASTM Card 6-0532), which is presumably CrO_3 ($a_{\text{o}} = 8.36\text{\AA}$).

Assuming only that the structure is face-centered cubic, the standard pattern for MnCr_2O_4 developed from the work summarized above and intended for use in future comparisons is:

<u>d(Å)</u>	<u>hkl</u>	<u>a_o</u>
4.85	111	8.42
2.978	220	8.423 ₁
2.540 _o	311	8.424 ₂
1.623 _o	511,333	8.433 ₃
1.489 ₈	440	8.427 ₆
Average a _o =		8.426 ₅ angstroms

2.1.1.3 Microprobe and Electron Microscopy Analysis

Electron microprobe analysis was conducted on a specimen (V₂-5-8) of Heat E9517 aged 10,000 hr in air at 1600°F. The objective of the analysis was threefold: a) semi-quantitative chart traces (MACX)* were recorded across the oxide-metal reaction zones to determine the concentration changes of Si, Mo, Cr, Mn, Fe, and Ni; b) quantitative analysis (point-counting) for the above elements was performed on precipitate particles distributed along the microprobe paths; and c) X-ray scanning images were obtained for the same elements within the oxide film and the residual matrix.

Reproduction of the MACX traces for Ni, Cr and Mn are shown in Figure 1. Very little change was detected in the Fe, Mo and Si concentrations in either the matrix or oxide film and these traces are omitted in Figure 1 for purposes of clarity. As shown, the nickel concentration increased from 51.5 w/o in the metal matrix to 57 w/o at the oxide-metal interface. However, no nickel was identified within the inner or outer oxide film.

*Refers to X-ray traces using Model MAC-400 electron microprobe analyzer.

AGN-8224

FIGURE 1. REPRODUCTIONS OF ELECTRON MICROPROBE (MACX) TRACES FOR SPECIMEN OF HASTELLOY X (HEAT E 9517; LOW-COBALT TUBING) AGED 10,000 hr IN AIR AT 1600°F

The chromium concentration decreased somewhat from the matrix (22.5 w/o) to the oxide-metal interface (18 w/o), and reached a maximum concentration of 63 w/o in the oxide inner layer. This concentration corresponds to a slightly chromium-deficient Cr_2O_3 (68.5 w/oCr) composition.

Significant depletion (0.7 to 0.1 w/o) of manganese from matrix to metal-oxide interface was evident. This element was not detected in the inner oxide layer, although it reached a concentration of 5.4 w/o in the outer oxide layer. The 5.4 w/o manganese in the outer oxide is too low for the anticipated MnCr_2O_4 (24.6 w/o Mn) structure, and is not consistent with the data obtained for the commercial-cobalt material exposed at 1750°F (see Section 2.1.2.2). Discussions with the microprobe analyst, resulted in the conclusion that the outer oxide on the 1600°F specimen was too narrow for accurate MACX trace analysis. This point was substantiated by microprobe traverses performed at other locations on the same specimen, where X-ray scanning images clearly revealed intense manganese layers, although very little manganese was detected by the MACX traces.

A specimen (V_2 -5-9) of low-cobalt material aged 10,000 hr at 1750°F was analyzed using point-count techniques to resolve this discrepancy. Point-counting analysis permits far more accurate elemental concentration determinations than the faster, continuous MACX traces. The results of these analyses are presented in Figure 2; the chromium reaches a concentration of 63 w/o in the inner oxide (Cr_2O_3), and drops to 48 w/o in the outer oxide. The manganese, not present in the inner oxide, reaches a concentration of about 22 w/o in the outer oxide. Excellent evidence exists, therefore, to support the predicted presence of MnCr_2O_4 -spinel structure (46.6 w/o Cr and 24.6 w/o Mn).

No nickel was identified in either the inner or outer oxide layers of specimen V_2 -5-9. This observation is important, since it refutes earlier contentions* that the oxide film on Hastelloy X consists of an inner Cr_2O_3 structure overgrown by a NiCr_2O_4 structure (rather than the now proven MnCr_2O_4 structure).

* Section 2.1.1.2

FIGURE 2. REPRODUCTIONS OF ELECTRON MICROPROBE POINT-COUNTING TRAVERSES FOR SPECIMEN OF HASTELLOY X (HEAT E 9517, LOW-COBALT TUBING) AGED 10,000hr IN AIR AT 1750°F

The results of precipitate particle point-counting for specimen (V₂-5-8) are presented in Table 5. Major variations in precipitate chemistry

TABLE 5 - RESULTS OF QUANTITATIVE ANALYSES
OF PRECIPITATES IN SPECIMEN V₂-5-8

Ppt. No.	Dist. from M-0 Interface, microns	Corrected Compositions, Wt. %						
		Si	Mo	Cr	Mn	Fe	Ni	C*
1	30	6.6	55.7	3.3	0.03	2.5	30.8	1.1
2	30	6.8	56.6	3.0	0.03	2.1	30.4	1.1
3	45	7.0	55.9	3.7	0.06	6.5	35.2	**
4	250	6.5	52.8	12.3	0.27	6.1	28.8	**
5	600	0.6	24.0	30.2	0.33	13.7	23.5	7.7

* Determined by balance

** Total of six elements analyzed is greater than 100%.

are indicated, particularly between particles located close to the oxide-metal interface ($\sim 30\mu$) and those some distance into the metal matrix ($\sim 600\mu$). The reason for the chemical variations is not fully understood but is believed to be associated, in part, with the chemical equilibrium changes which occur during aging and oxidation. Based on the compositions shown, carbide computations indicate a variation between $M_{3.5}C$ and $M_{15}C$, rather than the more commonly accepted M_6C . This is in agreement with the results reported by Russian workers, ⁽⁵⁾ who report that M_6C is more accurately a combination of M_4C and $M_{12}C$ and that these compounds differ only in the number of interstitial sites filled by carbon. However, analysis of precipitates in the same material exposed for 10,000 hr at 1750°F (performed earlier on specimen V₂-5-9) reveals an M_6C structure ($M_{6.4-6.8}C$) with a typical composition of:

Si	Cr	Mn	Fe	Co	Ni	Mo	C (Bal)
2.2	6.9	<0.1	4.1	<0.1	28.8	55.4	2.4

Using this composition, the approximate stoichiometric M_6C^* phase in Hastelloy X can be written as $(Mo_{2.9}Ni_{2.5}Cr_{0.67}Fe_{0.37})C$. In contrast to the M_6C com-

* More accurately $M_{6.44}C$

position $[(\text{NiCo}_2\text{Mo}_3)\text{C}]$ reported by other investigators,⁽⁶⁾ the present M_6C composition is unique in that virtually no cobalt was detected. The cobalt content shown above for the present M_6C is typical of 20 precipitate particles from two different (0.04 and 2.07 w/o Co) specimens analyzed during an earlier program. Based on this consistency, therefore, the present M_6C composition is that which should be expected in Hastelloy X.

The scanning images obtained are displayed in Figure 3. Figure 3-a is an optical photomicrograph (570X) showing the specimen area analyzed; the dark line perpendicular to the oxide film is the microprobe traverse path. Figures 3-b, c, d, e, f, and g are images of Si, Mo, Fe, Ni, Cr and Mn concentrations, respectively. It is apparent that the oxide consists of a Cr-rich inner layer (f) and a Mn-rich outer layer (g). No Si, Mo, Fe, or Ni compounds are revealed in the oxide film (b through e). The only significant matrix effect noted is the Si-rich particles precipitated just under the oxide-metal interface (white spots in 3-b). Based on oxygen determinations performed earlier on similar specimens, these particles (black void-appearing sites in Figure 3-a) have a composition corresponding to stoichiometric SiO_2 .

2.1.1.4 Sigma Phase Characterization

In consideration of the previously reported identification of sigma phase in specimens exposed to 1300 and 1450°F, additional studies were undertaken to more fully characterize the morphology of sigma formation in Hastelloy X. Residue samples obtained electrolytically from specimens determined by X-ray diffraction to contain sigma phase were combined (to increase the volume), and treated chemically with Murakamais' reagent, a differential etchant which selectively attacks carbide phases while leaving sigma phase relatively unaffected.⁽⁷⁾ The intent of this work was to dissolve the carbide phases, thereby concentrating the sigma phase particles so that subsequent X-ray diffraction and fluorescence analyses would provide more meaningful data. The technique employed involved obtaining an X-ray diffraction pattern for the untreated sample, followed by subsequent X-ray diffraction analyses after leaching the sample for one hour at room-temperature, ten minutes at 170°F, and, finally, for two hours at 170°F. The results of these analyses are presented in Table 6. As shown, the unleached pattern reflects

TABLE 6- RESULTS OF X-RAY DIFFRACTION ANALYSES PERFORMED ON SPECIMEN E9517
RESIDUE (HCl EXTRACTION) AGED 10,000 HOURS IN AIR AT 1300°F
FOLLOWING VARIOUS LEACHING OPERATIONS USING MURAKAMAI'S

Line	Unleached		One hour Cold		Ten Min. 170°F		Two hrs 170°F		ASTM Index Card (11-546) M ₆ C		σ Ni-Cr-Mo**	
	d	I	d	I	d	I	d	I	d	I	d	I
1	2.723	17			2.715	20			2.72	50		
2	2.494	14							2.50	50	2.47	VVW
3	2.367	11	2.343	10	2.303	25			*2.31	50	2.29	MW
4	2.216	45	2.221	30					2.22	80		
5	2.169	6										
6	2.160	8	2.150	50	2.164	90	2.159	90	*2.16	60	2.15	MS
7	2.092	100	2.078	100	2.106	60			2.099	100	2.09	M
8	2.051	7	2.038	25	2.047	40	2.042	30	*2.05	50	2.06	M
9	2.025	8									2.04	M
10	1.995	7	1.991	25	1.995	60	1.995	80	*1.993	60	1.995	S
11	1.959	8	1.955	50	1.955	100	1.955	100	*1.956	80	1.955	VS
12	1.923	25	1.908	30	1.908	50	1.912	30	1.924	80	1.91	MS
13	1.872	2							1.860	30	1.86	VVW
14	1.809	5			1.790	20			*1.810	40	1.81	VVW
15	1.522	8	1.527	10					1.521	50		
16	1.414	3			1.392	20			1.413	50		
17	1.330	7							1.325	50		
18	1.280	28	1.279	20			1.274	15	1.280	80		
19	1.255	10	1.251	15	1.251	20			1.251	5		
20	1.186	4	1.184	12	1.188	20						
21	1.098	4										
22	1.092	10	1.089	15					1.090	65		

* Indices for Sigma Phase

** See Table 1 for reference.

AGN-8224

171-67-334

(a) OPTICAL PHOTOMICROGRAPH

(b) Si - $K\alpha$ (c) Mo - $L\alpha$ (d) Fe - $K\alpha$ (e) Ni - $K\alpha$ (f) Cr - $K\alpha$ (g) Mn - $K\alpha$

FIGURE 3. X-RAY SCANNING IMAGES (25kv) FOR A SPECIMEN (V2-5-8) OF HASTELLOY X
LOW-COBALT TUBING AGED 10,000hr IN AIR AT 1600°F X570

BLANK

all of the major M_6C and σ (Ni-Cr-Mo) indices. The intensity of the major peaks shown, however, are much greater for M_6C (lines #7, 4, 12, 18) than for sigma phase (lines #11, 10, 6).

Dissolution in cold Murakamais' for one hour eliminates the weak M_6C peaks, decreases the stronger M_6C peaks and increases the sigma phase peak intensities. This pattern is followed with increasing time and temperature; after two hours at 170°F, virtually all of the M_6C phase has been removed. The remaining pattern is clearly that of sigma phase, with the major peak intensities suitably proportioned.

The work summarized above is significant for two reasons:

- The standard pattern reported by ASTM for M_6C (Index Card #11-546) also lists the indices attributed to the sigma phase (those identified by an asterisk in Table 6) that have been used in previous identifications. To support the present experimental verifications, therefore, it was necessary to establish conclusively which of the ASTM reported indices could be attributed only to sigma phase in Hastelloy X. The information gained from the chemical treatment discussed above has accomplished this task. The conclusion established by the above analysis can be generalized as follows: Hastelloy X systems can be considered to have precipitated sigma phase following aging when such systems yield an X-ray diffraction pattern containing d-spacings of (or very near) 1.955, 1.995, 2.15 and 1.91. The d-spacings found necessary for the positive identification of M_6C in Hastelloy X are: 2.09, 2.22, 1.92 and 1.28.
- The Murakamais' treatment is demonstrated as a successful technique for separating sigma from the carbide phases in Hastelloy X, thereby permitting more positive identification, particularly when the quantity of sigma phase present is quite small.

The appearance of the sigma phase observed in Hastelloy X is shown in Figures 4-9. Figure 4 is an optical photomicrograph of a specimen aged in air at 1300°F for 10,000 hr. The grain boundary precipitate and irregular-shaped particles distributed throughout the matrix are M_6C carbides. The rod-shaped formation is the sigma phase. This formation is shown more clearly in Figure 5, which is a micrograph taken at 3000 magnifications using an

FIGURE 4. MICROSTRUCTURE OF HASTELLOY X TUBING
AGED IN AIR AT 1300°F FOR 10,000 hr
(SCHANTZ ETCH)
(a) M_6C CARBIDES (b) SIGMA PHASE

FIGURE 5. ELECTRON SCANNING MICROGRAPH OF
HASTELLOY X TUBING AGED IN AIR AT
1300°F FOR 10,000 hr
(a) M_6C CARBIDES (b) SIGMA PHASE

electron scanning microscope. It can be seen that the sigma phase morphology takes the form of chunky elongated particles which appear ordered in definite crystallographic planes.

Two electron micrographs taken of a specimen aged in air at 1300°F for 10,000 hr, which were replicated with carbon and shadowed with chromium, are shown in Figure 6 and 7. Figure 6 shows an elongated sigma phase rod precipitated through a matrix of discrete carbide particles. The large particle shown in Figure 7 was identified by electron diffraction (discussed later) as M_6C , while the precipitate nucleating from this carbide was identified as sigma phase by the same technique.

Electron micrographs of specimens aged for 2500 hr at 1300°F in air and inert gas, are shown in Figures 8 and 9, respectively. The second phase precipitates appearing in both micrographs are less ordered than those observed in specimens which were aged for longer times (Figures 6 and 7) and assume a platelet morphology in contrast to the rod-shaped formation discussed previously. The reasons for these differences are unknown at present; additional evaluation is required for clarification.

Electron diffraction analyses were performed on particles removed from the matrix of a specimen aged in air for 10,000 hr at 1300°F (structure shown in Figure 7) using bromine dissolution and carbon extraction replica techniques. The general appearance of these extracted particles is shown in Figures 10 and 11. Figure 10 shows retained M_6C particles (large black particles), a void with collapsed replica material where a large M_6C particle pulled away during the replica stripping process, and the fragmented sigma phase rods which apparently nucleated from the pulled-out M_6C particle. A transmission micrograph of one of the large black particles is shown in Figure 12; the selected-area diffraction pattern obtained from this specimen is presented in Table 7. As indicated in Table 7, the electron diffraction pattern compares favorably to the M_6C identified by X-ray diffraction during the present studies, and with that verified at GE by electron diffraction for Hastelloy X aged 2000 and 5200 hr at 1050°F.⁽⁸⁾

The transmission micrograph of one of the rod-shaped precipitates (shown nucleating from M_6C particle in Figure 10) in the previously mentioned sample is shown in Figure 13. The selected-area diffraction pattern obtained for this

FIGURE 6. ELECTRON MICROGRAPH OF HASTELLOY X TUBING AGED 10,000 hr AT 1300°F (NOTE ELONGATED SIGMA PHASE PRECIPITATE THROUGH MATRIX OF CARBIDE PARTICLES)

X 4100
C-REPLICA
Cr SHADOWED

FIGURE 7. ELECTRON MICROGRAPH OF HASTELLOY X TUBING AGED 10,000 hr IN AIR AT 1300°F (NOTE SIGMA PHASE NUCLEATING FROM M₆C CARBIDE PARTICLES)

X 7700
C-REPLICA
Cr SHADOWED

17.1-67-336

FIGURE 8. ELECTRON MICROGRAPH OF SPECIMEN OF
HASTELLOY X (LOW-COBALT TUBING) AGED
IN AIR FOR 2500 hr AT 1300°F

X 5800
C-REPLICA/Pt/Pd
SHADOWED

FIGURE 9. ELECTRON MICROGRAPH OF SPECIMEN OF
HASTELLOY X (LOW-COBALT TUBING) AGED
IN INERT GAS FOR 2500 hr AT 1300°F

X 6900
C-REPLICA/Pt/Pd
SHADOWED

X 8300

FIGURE 10. CARBON EXTRACTION REPLICA SHOWING RODS OF SIGMA PHASE NUCLEATING FROM LARGE M_6C CARBIDE PARTICLES

X 8300

FIGURE 11. CARBON EXTRACTION REPLICA SHOWING CLUSTER OF RECTANGULAR PLATELETS

FIGURE 12. TRANSMISSION MICROGRAPH OF LARGE PARTICLES SHOWN IN FIGURE 10 IDENTIFIED AS M_6C BY SELECTED-AREA DIFFRACTION

FIGURE 13. TRANSMISSION MICROGRAPH OF ROD-SHAPED PRECIPITATES SHOWN IN FIGURE 10 IDENTIFIED AS SIGMA PHASE BY SELECTED-AREA DIFFRACTION

17.1-67-339

TABLE 7 - EXPERIMENTAL ELECTRON DIFFRACTION PATTERN COMPARED
TO PUBLISHED VALUES FOR M_6C CARBIDES

Exp. <u>d</u>	GE (a*) <u>d</u>	GE (b*) <u>d</u>	AGN** <u>d</u>
6.30	6.275	6.35	6.32
5.55	5.43	5.54	
3.82	3.83	3.90	3.87
3.28	3.28	3.32	3.28
3.08			3.12
2.52	2.49		2.494
2.09			2.092
1.92			1.924

* F. A. Comprelli, "Stability of High-Nickel Alloys in Superheated Steam," GEAP-4745, Nov. 1964.

(a) Electron diffraction pattern of particles identified as M_6C extracted from Hastelloy X aged 2000 hours at 1050°F.

(b) Electron diffraction pattern of particles identified as M_6C extracted from Hastelloy X aged 5200 hours at 1050°F.

** X-ray diffraction pattern of particles extracted electrolytically from Hastelloy X Heat E9517 aged 2500 hours in inert gas at 1300°F.

precipitate is presented in Table 8 which also shows the excellent agreement with X-ray diffraction patterns for sigma phase of the Ni-Cr-Mo- and/or Fe-Ni-Cr-Mo-types.

The third type of precipitate observed in the above extraction replica, shown in Figure 11, appeared as clusters of platelets randomly distributed throughout the matrix. Although the diffraction results from particles were not completely satisfactory, one selected-area pattern was obtained (Table 9) which compared favorably with that of chi phase ($Mo_5Cr_6Fe_{18}$). According to Goldschmidt,⁽⁹⁾ chi phase can act either as an intermetallic compound with high carbon solubility or as a complex carbide, and can form assemblies with sigma phase. The possibility of chi phase in Hastelloy X is not considered unusual, although, based on reported⁽¹⁰⁾ temperatures at which it occurs, such formation in the present sample is suspect. Additional analyses will be required before any conclusions regarding chi phase can be formulated.

TABLE 8 - EXPERIMENTAL ELECTRON DIFFRACTION PATTERN COMPARED
TO PUBLISHED X-RAY DIFFRACTION PATTERNS FOR SIGMA
PHASE

<u>Exp.*</u> <u>d</u>	<u>$\sigma(\text{Ni-Cr-Mo})^{**}$</u> <u>d</u>	<u>$\sigma(\text{Fe-Ni-Cr-Mo})^{***}$</u> <u>d</u>
3.70	Conflict	Conflict
2.48	2.49	2.47
2.14	2.16	2.16
1.98	1.96	1.96
1.85	1.86	1.87
1.26	1.26	1.26
1.21	1.22	1.21

* Analysis taken on rod-shaped particle illustrated in Figure 10.

** ASTM Index Card #9-284

*** ASTM Index Card #7-96

TABLE 9 - EXPERIMENTAL ELECTRON DIFFRACTION PATTERN COMPARED
TO PUBLISHED X-RAY DIFFRACTION PATTERN FOR CHI
PHASE

<u>Exp.*</u> <u>d</u>	<u>$\text{Chi}(\text{Mo}_5\text{Cr}_6\text{Fe}_{18})^{**}$</u> <u>d</u>
4.62	Not listed
3.12	Conflict
2.41	2.41
2.15	2.11
1.73	1.75
1.50	1.49
1.39	1.38
1.20	1.21
1.15	1.13
0.92	0.99

* Analysis taken on platelet illustrated in Figure 11.

** ASTM Index Card #8-200.

In addition to the analyses discussed above, a sample of Murakamais'-treated residue (also discussed previously) was analyzed by electron diffraction techniques. These particles, which are both rod and platelet-shaped as shown in Figure 14, yielded the selected-area diffraction pattern presented in Table 10. This pattern corresponds closely to the X-ray diffraction pattern for the Fe-Ni-Cr-Mo sigma phase. The chemical composition of this sample was determined by X-ray fluorescence to be 11 w/o Mo, 19 w/o Cr, 10 w/o Fe and 60 w/o Ni, further substantiating the observed precipitation of a quaternary rather than a ternary-type sigma phase. These findings are somewhat confusing as X-ray diffraction patterns indicate the formation of a Ni-Cr-Mo sigma phase, while electron diffraction and X-ray fluorescence analyses tend to verify the formation of a more complex variety (Fe-Ni-Cr-Mo). Resolution of this uncertainty is not presently possible, since it will require additional experimentation, and/or discussions with other experimenters who have performed similar investigations.

TABLE 10- EXPERIMENTAL ELECTRON DIFFRACTION PATTERN COMPARED
TO PUBLISHED X-RAY DIFFRACTION PATTERN FOR SIGMA
PHASE

<u>Exp.*</u> <u>d</u>	<u>σ(Fe-Ni-Cr-Mo)**</u> <u>d</u>
4.52	Not listed
2.58	2.53
2.17	2.16
2.42	2.41
2.32	2.32
1.97	1.96
1.78	1.79

* Sample extracted electrolytically from Hastelloy X aged 10,000 hours in air at 1300°F and leached two hours at 170°F in Murakamais reagent.

** ASTM Index Card #7-96.

X 4200

FIGURE 14. CARBON EXTRACTION REPLICA SHOWING SHAPE OF SIGMA PHASE PARTICLES ELECTROLYTICALLY DIGESTED FROM SPECIMEN OF HEAT E 9517 AGED 10,000 hr AT 1300°F, AND SEPARATED FROM CARBIDE PARTICLES BY TREATMENT WITH MURAKAMI'S REAGENT

2.1.2 Task A-2, Commercial-Cobalt Specimen Evaluations*

2.1.2.1 Microconstituent Extraction and Analysis

Microconstituent extraction and X-ray diffraction analyses were completed on specimens of Heat X14593 (commercial-cobalt tubing) aged in air at temperatures between 1300 and 1800°F, and for 5820 and 12,500 hr. The results of these analyses are summarized in Table 11. As anticipated, M_6C is the primary constituent detected in these specimens.

TABLE 11- HASTELLOY X COMMERCIAL-COBALT TUBING CONTROL
SPECIMENS ANALYZED BY PARTICLE EXTRACTION
(10% HCl/METHANOL) AND X-RAY DIFFRACTION

Sample No.	Exposure History		Time, hrs	Phases Present*
	Atm	Temp., °F		
40	Air	1300	12,500	(S) M_6C ; (S) σ ; (S) $M_{23}C_6$
41	"	1450	"	(S) M_6C ; (W) σ ; (W) $M_{23}C_6$
42	"	1600	"	(S) M_6C ; (W) $M_{23}C_6$
43	"	1750	"	(S) M_6C ; (VW) $M_{23}C_6$
44	"	1800	"	(S) M_6C ;
45	"	1300	5820	(S) M_6C ; (S) σ ; (W) $M_{23}C_6$
46	"	1450	"	(S) M_6C ; (W) σ ; (W) $M_{23}C_6$
47	"	1600	"	(S) M_6C ; (W) $M_{23}C_6$
48	"	1750	"	(S) M_6C ;
49	"	1800	"	(S) M_6C

* S = Strong pattern (positive identification)

M = Medium to weak pattern (phase probably present)

VW = Very weak pattern (possibility of phase being present)

* Note: In connection with the work performed under this task, data included in "Evaluation Study of Hastelloy X as a Nuclear Cladding, Quarterly Progress Report, 5 July through 30 September 1966," (AGN-8205) is in error. The percentage elongation for Heat X4762 aged 1000 hr in inert gas at 1300°F as shown in Figure 9 should be 21.5% rather than 40% as reported.

Sigma phase occurred in specimens aged at 1300 and at 1450°F, although the patterns obtained for these samples were not as intense as those noted for the low-cobalt specimens. A summary of all Hastelloy X heats (and the associated exposure history) in which sigma phase was identified is presented in Table 12. As indicated by the data in this Table, no sigma phase was detected in specimens aged in inert gas for times less than 2500 hr, and no sigma phase was noted in tubing specimens aged in air at temperatures greater than 1450°F. Considering the first observation, sigma phase formation in Hastelloy X is apparently somewhat analogous to the similar process in many of the stainless steel systems, where the transformation is often quite sluggish. This is especially true when sigma transforms directly from the gamma matrix rather than from systems containing appreciable quantities of ferrite, in which case its transformation rate is normally more rapid.⁽¹¹⁾ The second observation has already been discussed; i.e., the re-solution temperature of sigma phase in Hastelloy X apparently occurs somewhere between 1450 and 1600°F. This observation is important for design considerations, particularly when Hastelloy X is intended for use at temperatures above 1450°F.

The general trend of $M_{23}C_6$ precipitation is similar to that discussed for the low-cobalt material. Stronger $M_{23}C_6$ patterns were obtained for specimens aged at the lower temperatures, while much weaker patterns were generated for specimens aged at the higher temperatures.

2.1.2.2 Microprobe and Electron Microscopy Analysis

Electron microprobe analyses were completed on specimens of Heat X14593 (aged for 5820 hr in air at 1750°F) and of Heat E9505 (low-cobalt sheet material aged for 2680 hr in inert gas at 1300°F).

The specimen exposed to inert gas (E₃-4-4) was evaluated to furnish control data regarding matrix and precipitate chemical changes dependent only on thermal effects. The MACX traces and scanning images provided no significant information because of the absence of an oxide film. The results of precipitate point-counting, shown in Table 13, reveal some major differences from the low-cobalt tubing aged in air discussed previously; the molybdenum and iron contents of the carbide phase are significantly lower in the inert gas aged material, while the manganese and chromium contents are generally higher.

TABLE 12- OCCURRENCE OF SIGMA PHASE (Ni-Cr-Mo) IN VARIOUS HASTELLOY X
HEATS FOLLOWING THE INDICATED AGING HISTORIES

<u>Heat Number</u>	<u>Material Type</u>	<u>Environment</u>	<u>Temp., °F</u>	<u>Time, hrs</u>					
				<u>100</u>	<u>1000</u>	<u>2500</u>	<u>5000</u>	<u>10,000</u>	<u>12,500</u>
E9522	Sheet	Inert Gas	1300	-	o	-			
E9505	Sheet	Inert Gas	1300	o	o	++			
X4762	Sheet	Inert Gas	1300	o	o	+			
X34381	Sheet	Inert Gas	1300	o	o	+			
E9517	Tubing	Inert Gas	1300	-	o	++			
X14593	Tubing	Inert Gas	1300	-	o	+			
E9517	Tubing	Air	1300	-	-	++	-	++	-
			1450	-	-	++	-	+	-
			1600	-	-	o	-	o	-
X14593	Tubing	Air	1300	-	-	-	++	-	++
			1450	-	-	-	+	-	+
			1600	-	-	-	o	-	o

Legend: ++ = Strong pattern; positive identification
+ = Medium pattern; probably present
o = None detected
- = Was not analyzed

AGN-8224

The nickel content remains relatively unchanged. The composition of these precipitates more nearly approximates that determined for as-received Hastelloy X shown below.

<u>Cr</u>	<u>Mo</u>	<u>Fe</u>	<u>Ni</u>
16.2%	44.8%	5.8%	24.6%

TABLE 13- RESULTS OF QUANTITATIVE ANALYSIS OF PRECIPITATES
IN SPECIMEN E₃-4-4

<u>Ppt.</u> <u>No.</u>	<u>Dist. from M-0</u> <u>Interface, microns</u>	<u>Corrected Compositions, wt %</u>						
		<u>Si</u>	<u>Mo</u>	<u>Cr</u>	<u>Mn</u>	<u>Fe</u>	<u>Ni</u>	<u>C*</u>
1	75	4.9	44.5	13.9	0.12	4.6	26.2	4.8
2	150	4.9	43.5	14.1	0.11	5.1	26.4	5.9
3	530	5.2	43.9	14.0	0.13	4.3	26.6	5.9
4	740	5.1	44.2	10.1	0.24	5.3	26.9	8.2
5	810	5.1	44.1	13.8	0.12	4.9	26.6	5.4

* Determined by difference

The inert gas-aged precipitate compositions are fairly uniform, containing a high percentage of molybdenum and nickel, with medium chromium and little iron. The resulting calculated carbide compound is M_3C , which is again lower than the anticipated M_6C composition. Insufficient information is available at this time, however, to postulate details concerning these carbide compositional variations.

The scanning images obtained for the specimen of Heat X14593 aged for 5820 hr in air at 1750°F (S₂-2-1), are shown in Figure 15. It is obvious that the oxide consists of a chromium-rich inner layer (Figure 15-f) overgrown with a manganese-rich outer layer (Figure 15-g). No Si, Mo, Fe, or Ni compounds (Figures 15b, c, d and e, respectively) are apparent in the oxide film.

Reproductions of the MACX traces obtained for this specimen, showing variations of Ni, Cr, and Mn contents, are presented in Figure 16. It can be seen that nickel is absent in both the inner or outer oxide layers, while the chromium content reaches 63 w/o (corresponding to the Cr_2O_3 structure) in the inner layer. The manganese content approaches 20 w/o in the outer oxide layer, indicating a slightly manganese-deficient $MnCr_2O_4$ -spinel structure. Point-count analysis of the outer oxide layer of a commercial-cobalt specimen (V₂-8-4) exposed for 10,000 hr at 1750°F (performed earlier), detected a manganese content of 21 w/o (shown as dashed lines in Figure 16) which is

BLANK

171-67-341

(a) OPTICAL PHOTOMICROGRAPH

(b) Si - $K\alpha$ (c) Mo - $L\alpha$ (d) Fe - $K\alpha$ (e) Ni - $K\alpha$ (f) Cr - $K\alpha$ (g) Mn - $K\alpha$

FIGURE 15. X-RAY SCANNING IMAGES (25kv) FOR A SPECIMEN (S₂-2-1) OF HASTELLOY X
COMMERCIAL-COBALT TUBING AGED 5820hr IN AIR AT 1750°F X570

BLANK

FIGURE 16. REPRODUCTION OF ELECTRON MICROPROBE(MACX)TRACES FOR A SPECIMEN OF HASTELLOY X HEAT X14593 (COMMERCIAL-COBALT TUBING) SPECIMENS AGED 5820 hr IN AIR AT 1750°F
 * Mn₂ SHOWN AS DASHED LINE IS FOR SPECIMEN AGED 10,000 hr IN AIR AT 1750°F (POINT-COUNT TRAVERSE)

consistent with that discussed previously for an MnCr_2O_4 structure of the low-cobalt material.

The results of precipitate quantitative analysis performed on specimen S_2 -2-1 are listed in Table 14. The precipitate trends demonstrated here are similar to those of the as-received and inert gas-aged material, with the exception of the iron content, which is generally higher in the air-aged specimen (S_2 -2-1). Calculated carbide compositions yield compounds between M_3C to $\text{M}_{4.5}\text{C}$, once again indicating extremely carbon-rich contents compared to the M_6C structures discussed earlier in Section 2.1.1.3.

TABLE 14- RESULTS OF QUANTITATIVE ANALYSIS OF PRECIPITATES
IN SPECIMEN S_2 -2-1

Ppt. No.	Dist. from M-0 Interface, microns	Corrected Compositions, wt %						
		Si	Mo	Cr	Mn	Fe	Ni	C*
1	50	2.1	44.3	12.5	0.07	11.4	24.5	5.1
2	35	2.1	44.5	12.4	0.05	11.9	25.4	3.6
3	130	2.3	44.3	12.5	0.06	10.8	24.3	5.7
4	310	6.2	43.9	13.8	0.16	2.8	28.8	4.3
5	35	2.1	42.0	12.4	0.08	11.2	24.6	7.6

* Determined by difference

Electron microscopic examination was performed on two specimens of heat X14593 aged in air for 10,000 hr at 1600°F at 1750°F , respectively. The examination was conducted in an effort to better understand the depleted zone noted⁽¹²⁾ in specimens of this heat following exposure in air at temperatures greater than 1600°F , (the depleted zone was not observed in specimens exposed at 1600°F , nor did it occur in specimens of low-cobalt material at any temperature). Carbon replicas were obtained from the above specimens and shadowed using Pt/Pd. The replicas were taken as close to the oxide-metal interface as possible consistent with the ability to remove sound (non-fragmented) impressions from the oxide film. The depleted zone was present in the tubing walls of this specimen to a depth of about 0.006 in. from the metal-oxide interface.

A micrograph taken of the specimen exposed at 1600°F is shown in Figure 17. Large M_6C carbide particles, oriented almost exclusively at the

FIGURE 17. ELECTRON MICROGRAPH OF HASTELLOY X
COMMERCIAL-COBALT TUBING AGED
10,000 hr IN AIR AT 1600°F

X 4800
C-REPLICA/Pt/Pd
SHADOWED

FIGURE 18. ELECTRON MICROGRAPH OF HASTELLOY X
COMMERCIAL-COBALT TUBING AGED
10,000 hr IN AIR AT 1750°F

X 6900
C-REPLICA/Pt/Pd
SHADOWED

- (a) RE-SOLUTIONED CARBIDE PARTICLE
- (b) PARTIALLY SOLUTIONED CARBIDES

171-67-343

at the grain boundaries, are evident. No unusual effects are apparent in the structure displayed. Very major effects are apparent, however, in the micrograph of the specimen exposed at 1750°F, shown in Figure 18. The grain boundary junction (labeled "a") is a site where (it appears) a carbide particle has diffused back into solid-solution. In addition, the two M_6C particles at the top of the micrograph (labeled "b") are elongated along a grain boundary, and also appear to be diffusing back into solution. Based on past observations, this area is representative of the structure on that portion of the specimen where the carbide particles should normally be larger than those which occur at 1600°F. The carbide depletion which occurs is believed to be associated with the oxidation process, and is assumed to be caused by diffusion gradient/chemical imbalance phenomena unique to the commercial-cobalt material. This effect will be explored further during subsequent investigations.

2.1.3 Task A-3, High Temperature Oxidation Studies

2.1.3.1 Metallographic Evaluation

Metallographic examination of sheet and tubing specimens aged for 7500 hr in air at 1900 and 2000°F was completed. The microstructures and mode of oxidation observed, as a function of exposure temperature, are summarized below.

- The appearance of the low-cobalt tubing structures aged at 1900°F is shown at low magnification in Figure 19-a, and at higher magnification in Figure 19-b. The carbide particles have coalesced somewhat and are oriented primarily at the grain boundaries. The main mode of oxidation is in the form of a layer of fine internal oxides, which penetrate to a depth of 0.0030 in. A relatively uniform duplex oxide film with an average thickness of 0.0010 in. is present on the outside diameter. An appreciable number of large internal oxide sites, which penetrate to a maximum depth of 0.0073 in., are apparent.
- The structure of the low-cobalt material aged at 2000°F was similar to that which occurred after aging at 1900°F (Figure 20), but the oxidation effects were much more severe. The internal oxide layer penetrated to a depth of 0.009 in. although the isolated large internal oxides were observed only to a depth of 0.0065 in. The surface of these

(a) X 100

(b) X 250

FIGURE 19. TYPICAL MICROSTRUCTURES OF HEAT E 9517 (LOW-COBALT TUBING) SPECIMENS AGED 7500 hr IN AIR AT 1900°F (SCHANTZ ETCH)

AGN-8224

(a) X 100

(b) X 250

FIGURE 20. TYPICAL MICROSTRUCTURES OF HEAT E 9517 (LOW-COBALT TUBING) SPECIMENS AGED 7500 hr IN AIR AT 2000°F (SCHANTZ ETCH)

171-67-345

specimens was appreciably attacked and it appeared that considerable spallation had occurred. The average oxide thickness in areas where the film was intact was 0.0013 in. The duplex oxide was also present, but was not as well defined as that observed on the commercial-cobalt specimens.

• The structure and oxidation mechanism characteristics of the commercial-cobalt tubing aged at 1900°F are similar to those of the low-cobalt material, with the exception that the earlier mentioned depleted zone was present to a depth of 0.0060 in. (Figure 21). The layer of internal oxides penetrated to a depth of 0.0060 in., while isolated large internal oxides were observed at depths up to 0.0073 in. The average thickness of the duplex oxide was 0.0010 in.

• Dramatic changes were observed in the specimens aged at 2000°F, as shown in Figure 22. Considerable grain growth has occurred within the 0.0090 in. depleted zone, and appreciable annealing twins are evident. The layer of internal oxides penetrated to a depth of 0.0090 in.; large isolated internal oxide sites were present to a maximum depth of 0.0135 in. The duplex oxide was again observed (total oxide film thickness is 0.0013 in.) and is shown in Figure 23. The outer layer of the duplex oxide (shown as the fragmented darker phase in Figure 23-a) was normally observed as a somewhat uniform and continuous phase, although a few areas were revealed where a large mass of the outer oxide (previously identified as MnCr_2O_4) formed well within the inner oxide layer (see Figure 23-b).

• The structure and mode of oxidation for all sheet heat specimens aged at 1900 and 2000°F were very similar. The appearance of the 1900°F specimens of Heats X4762, E9505 and X34381 are shown in Figures 24, 25, and 26, and the 2000°F specimens of the same heats are shown in Figures 27, 28 and 29. Specimens of all heats aged at 1900°F revealed an internal oxide layer 0.004 in. deep, and isolated large internal oxides to a depth of 0.005 in. The exposed surfaces were attacked quite noticeably, and it appeared that appreciable spallation had occurred. The carbides were quite large and oriented primarily at the grain boundaries. No unusual microstructural effects were noted in any of the specimens examined.

(a) X 100

(b) X 250

FIGURE 21. TYPICAL MICROSTRUCTURES OF HEAT X14593
(COMMERCIAL-COBALT TUBING) SPECIMENS
AGED 7500 hr IN AIR AT 1900°F (SCHANTZ ETCH)

171-67-346

AGN-8224

(a) X 100

(b) X 250

FIGURE 22. TYPICAL MICROSTRUCTURES OF HEAT X14593 (COMMERCIAL-COBALT TUBING) SPECIMENS AGED 7500 hr IN AIR AT 2000°F (SCHANTZ ETCH)

17.1-67-347

(a)

(b)

FIGURE 23. APPEARANCE OF DUPLEX OXIDE (DARKER PHASE) OBSERVED ON SPECIMENS OF HEAT X 14593 AGED 7500 hr IN AIR AT 2000°F

- (a) SHOWING SEMI-CONTINUOUS OUTER LAYER OF MnCr_2O_4
- (b) SHOWING MASSIVE DEPOSIT OF MnCr_2O_4 WITHIN UNIFORM LAYER OF INNER OXIDE (Cr_2O_3)

17.1-67-348

(a) X 250

(b) X 500

FIGURE 24. TYPICAL MICROSTRUCTURES OF HEAT X4762 (COMMERCIAL-COBALT SHEET) SPECIMENS AGED 7500 hr IN AIR AT 1900°F (SCHANTZ ETCH)

17.1-67-349

AGN-8224

INCHES
.002
.004
.006
.008
.010
250X

(a) X 250

INCHES
.001
.002
.003
.004
.005
.006
500X

(b) X 500

FIGURE 25. TYPICAL MICROSTRUCTURES OF HEAT E 9505 (LOW-COBALT SHEET) SPECIMENS AGED 7500 hr IN AIR AT 1900°F (SCHANTZ ETCH)

171-67-350

AGN-8224

(a) X 250

(b) X 500

FIGURE 26. TYPICAL MICROSTRUCTURES OF HEAT X34381 (MEDIUM-COBALT SHEET) SPECIMENS AGED 7500 hr IN AIR AT 1900°F (SCHANTZ ETCH)

171-67-351

AGN-8224

(a) X 250

(b) X 500

FIGURE 27. TYPICAL MICROSTRUCTURES OF HEAT X4762
(COMMERCIAL-COBALT SHEET) SPECIMENS
AGED 7500 hr IN AIR AT 2000°F (SCHANTZ ETCH)

171-67-352

AGN-8224

(a) X 250

(b) X 500

FIGURE 28. TYPICAL MICROSTRUCTURES OF HEAT E 9505 (LOW-COBALT SHEET) SPECIMENS AGED 7500hr IN AIR AT 2000°F (SCHANTZ ETCH)

12.1-67-353

AGN-8224

(a) X250

(b) X500

FIGURE 29. TYPICAL MICROSTRUCTURES OF HEAT X34381 (MEDIUM-COBALT SHEET) SPECIMENS AGED 7500 hr IN AIR AT 2000°F (SCHANTZ ETCH)

17.1-67-354

Although the general oxidation mode was analogous to that noted in the specimens aged at 1900°F, the effects observed in the 2000°F specimens were considerably more pronounced. The fine internal oxides penetrated to a depth of 0.008 in. in all specimens while the average depth of large isolated oxides was 0.015 in. It was apparent that severe surface spallation had occurred, although a measure of the total wall thickness reduction resulting from the spallation was not available at the time this report was prepared; these data will be determined and reported at a later date. The carbide precipitates were quite large and oriented at the grain boundaries. In addition, appreciable grain growth occurred across the thickness of all specimens examined.

2.1.3.2 Room and Elevated Temperature Tensile Tests

Room temperature tensile tests of tubing specimens aged for 7500 hr in air at 1900 and 2000°F, and of sheet specimens aged at 1900°F were completed.

The results of tests of the 1900°F sheet specimens, together with results obtained earlier for specimens aged for 100, 1000, 2500 and 5000 hr, are summarized in Table 15 and plotted in Figure 30. The ultimate tensile strengths are comparable for all heats and the strength decreases generally with increasing exposure time. None of the three heats exhibit significant ductility maxima or minima (with the possible exception of heat X34381 which shows a slight minimum after 5000 hr), and all have nearly the same percentage elongation after 7500 hr exposure.

The results of the tubing tests are presented in Table 16 for both exposure temperatures and plotted in Figure 31 for specimens aged at 1900°F.

The ultimate tensile strength of specimens from both heats aged at 1900°F were consistent; the strength decreased with increasing exposure up to 5000 hr, followed by a slight increase in strength to 7500 hr. Both heats approached the same percentage elongation after 7500 hr exposure. The low-cobalt material (Heat E9517) had minimum ductility at 100 hr, but the commercial-cobalt material (Heat X14593) exhibited no distinct ductility maximum or minimum.

The data obtained from specimens of both heats exposed at 2000°F were too limited to permit accurate comparisons but, generally, both heats exhibited decreasing strength and elongation with increasing exposure time.

TABLE 15- ROOM TEMPERATURE TENSILE PROPERTIES OF HASTELLOY X SHEET
SPECIMENS AGED IN AIR AT 1900° F

<u>Heat No.</u>	<u>Exposure Time, Hrs</u>	<u>UTS, psi</u>	<u>Tensile Properties</u>	
			<u>0.2% Offset YS, psi</u>	<u>% Elong. in 1-inch</u>
X4762	As-received	114,400	60,000	40.4
E9505	"	109,700	59,000	35.5
X34381	"	123,000	77,800	35.8
X4762	100	104,400	47,400	40.3
E9505	100	102,700	-	43.3
X34381	100	107,900	28,300	40.1
X4762	1000	103,400	39,600	39.6
E9505	1000	98,900	31,700	43.0
X34381	1000	101,600	33,500	-
X4762	2500	92,000	29,300	44.5
E9505	2500	91,100	38,600	40.8
X34381	2500	91,500	34,900	37.5
X4762	5000	88,600	34,700	42.8
E9505	5000	89,600	41,300	43.7
X34381	5000	88,600	41,800	33.5
X4762	7500	90,693	37,624	38.6
E9505	7500	88,372	39,457	39.0
X34381	7500	90,943	35,849	39.3

FIGURE 30. ROOM TEMPERATURE TENSILE PROPERTIES OF VARIOUS HASTELLOY X SHEET HEATS EXPOSED IN AIR AT 1900°F

171-67-355

TABLE 16- ROOM TEMPERATURE TENSILE PROPERTIES OF HASTELLOY X TUBING HEATS
AGED AT 1900 and 2000 °F IN AIR FOR VARIOUS TIMES

Heat No.	Exposure History		Tensile Properties		%Elong. in 1-inch
	Temp. °F	Time, Hrs	UTS, psi	0.2% Offset YS, psi	
E9517		As-Received	109,600	56,600	42.0
E9517	1900	100	102,400	38,600	25.3
E9517	1900	5000	80,000	39,100	27.6
E9517	1900	7500	86,057	35,068	31.6
E9517	2000	5000	84,100	42,500	38.4
E9517	2000	7500	81,290	32,480	32.9
X14593		As-Received	118,500	59,600	46.0
X14593	1900	100	110,300	46,900	39.9
X14593	1900	5000	88,800	40,500	38.2
X14593	1900	7500	91,600	46,190	32.5
X14593	2000	5000	88,600	40,700	46.4
X14593	2000	7500	85,900	38,620	36.6

FIGURE 31. ROOM TEMPERATURE TENSILE PROPERTIES OF TWO TUBING HEATS AGED IN AIR AT 1900°F

Correlations between tubing and sheet heat data will be presented in a later report following a detailed evaluation of the data.

2.1.3.3 Microconstituent Extraction and Characterization

Specimens from all sheet heats aged for 7500 hr at 1900°F and 2000°F in air were electrolytically digested in 10% HCl/methanol, and X-ray diffraction analyses were performed on the resultant residues. The only microconstituent detected in all samples analyzed was M_6C carbides. No evidence of $M_{23}C_6$ carbide formation was found, which is consistent with literature⁽¹³⁾ which indicates that, in nickel-base super alloy systems, the $M_{23}C_6$ goes back into solution at about 1900°F. Based on data discussed previously for the tubing heats, however, it appears that the re-solution temperature of $M_{23}C_6$ in Hastelloy X-type systems is somewhere near 1800°F.

Typical X-ray patterns for all specimens are compared with published values for M_6C in Table 17. The calculated lattice parameter for M_6C at 1900°F is 10.950Å; the corresponding value at 2000°F is 10.985Å.

2.1.3.4 X-Ray Analysis of Surface Oxides

Surface oxides for specimens of three sheet heats aged for 7500 hr in air at 1900 and 2000°F were analyzed by X-ray diffraction. Identification of the oxide species present in typical specimens are shown in Table 18. All specimens had a duplex oxide, consisting of Cr_2O_3 and $MnCr_2O_4$, after exposure at 1900°F. Specimens aged at 2000°F displayed only the most intense peak for $MnCr_2O_4$ and the strong Cr_2O_3 pattern based on earlier metallographic observations; however, it is assumed that most of the outer oxide spalled off or was otherwise broken in a manner which precluded obtaining representative patterns for $MnCr_2O_4$.

2.1.3.5 Thermo-Gravimetric Tests

The continuous-weight change apparatus was modified and assembled and the furnace was profiled. A trial run was performed using alumina samples. At the end of the report period, thermo-gravimetric testing of tubing and sheet specimens at 1900°F had been initiated.

TABLE 17 - TYPICAL X-RAY PATTERN OF PRODUCTS ELECTROLYTICALLY
DIGESTED FROM HASTELLOY X SHEET HEATS AGED IN AIR
FOR 7500 HOURS AT 1900 AND 2000°F

Heat X4762 (2000°F)		Heat E9505 (1900°F)		M ₆ C*		Other**	Indexed Intensity
<u>d(Å)</u>	<u>I/I₀</u>	<u>d(Å)</u>	<u>I/I₀</u>	<u>d(Å)</u>	<u>I/I₀</u>	<u>Phase</u>	
3.63	15	3.62	10			Cr ₂ O ₃	75
2.747	8	2.739	20	2.72	50		
2.660	22	2.667	13			Cr ₂ O ₃	100
2.521	25	2.508	20			CrO ₃	100
2.475	22	2.475	22			Cr ₂ O ₃	96
2.237	44	2.227	68	2.22	80		
2.173	8	2.169	8			Cr ₂ O ₃	38
2.106	100	2.097	100	2.099	100		
		2.074	25			γ	100
1.809	12	1.928	33	1.924	80		
		1.819	12	1.810	40		
		1.796	10			γ	80
1.667	15	1.667	8			Cr ₂ O ₃	90
1.538	15	1.532	15	1.521	50		
1.462	8	1.462	10			Cr ₂ O ₃	25
1.340	10	1.336	12	1.340	20		
1.293	29	1.289	45	1.280	80		
1.268	10	1.264	10	1.270	20		
		1.098	15	1.090	65		

* ASTM Index Card #11-546

** Surface oxide products (Cr₂O₃) probably not completely removed before extraction, and γ resulting from incomplete dissolution of matrix.

TABLE 18 - REPRESENTATIVE X-RAY PATTERNS OF SURFACE OXIDES FOR HASTELLOY X
SHEET SPECIMENS AGED IN AIR FOR 7500 HOURS AT 1900 AND 2000°F

Heat E9505 (1900°F)		Heat X4762 (2000°F)		hkl		Others
<u>d (Å)</u>	<u>I/I_o</u>	<u>d (Å)</u>	<u>I/I_o</u>	<u>Cr₂O₃*</u> (a _o = 5.36 Å)	<u>MnCr₂O₄**</u> (a _o = 8.4265 Å)	
3.650	50	3.65	60	(012)		
2.990	23				(220)	
2.675	57	2.674	60	(104)		
2.542	23	2.550	12		(311)	
2.489	100	2.495	100	(110)		
2.184	30	2.184	25	(113)		
2.116	10				(400)	
2.079	57	2.074	22			γ(matrix)
1.815	23	1.822	35	(024)		
1.799	27					γ(matrix)
1.670	70	1.685	55	(116)		
1.622	20				(511,333)	
1.489	30				(440)	
1.466	43	1.465	25	(214)		
1.432	50	1.438	28	(300)		γ(matrix)
1.085	50	1.089	8			

* ASTM Index Card #6-0504

** Pattern for MnCr₂O₄ presented in Section A-1-b.

2.2 TASK B - MECHANICAL PROPERTIES STUDIES, R. Baciarelli, A. R. Miller

2.2.1 Task B-2, Phase II, 1800°F Tests

2.2.1.1 Completion of 1800°F Centrifugal Creep Test

The centrifugal creep testing of specimens from Hastelloy X Heats 4793, 4787 and 4902 for 1000 hr in air at 1800°F was completed and the data reduced by a computer program.

The computer program was revised during the report period, to present the output in a more usable form, to provide additional output, and to refine some of the original approximations. During the revision, the program was converted from FORTRAN II to FORTRAN IV (a somewhat faster and more convenient language) and three of the original approximations were refined. The relationship between deflection and strain, originally taken to be

$$d = \frac{H/2}{\epsilon} \quad (1)$$

is now calculated according to the relation:*

$$d = \frac{H/2}{e^{\epsilon} - 1} \quad (1a)$$

The gravitational contribution to the strain is small compared to that from centrifugal force at small deflections and, as a consequence, was neglected in the original program. The revised program accounts for gravity by inclusion of the term:

$$\frac{\ell_1}{2} \sin \frac{(2\ell(e^{\epsilon} - 1))}{H} \quad (2)$$

in the pseudo-elastic stress formula.

The specimen deflection is measured from the outer edge of the sample, rather than at the centerline. This difference amounts to:

$$\frac{H}{2} \left[1 - \cos \frac{2\ell(e^{\epsilon} - 1)}{H} \right] \quad (3)$$

* The derivation is given in Appendix A.

This term was included in the strain-deflection formula, which becomes:

$$d = \frac{H}{2} \left[1 + \frac{1}{e^{\epsilon} - 1} \right] \left[1 - \cos \frac{2\ell(e^{\epsilon} - 1)}{H} \right] + \ell_1 \sin \frac{2\ell(e^{\epsilon} - 1)}{H} \quad (4)$$

The measured deflections and corresponding times are input to the program, along with constants describing the sample shape (Fig. 32), the creep machine rotational velocity and head radius, and a deflection-correction factor accounting for plastic strain in the specimen load section. The program corrects the measured deflections according to the deflection-correction factor, then solves Equation (4) for the strain. Since this equation is non-linear, it is solved by Newton's method using SUBROUTINE NEWT.* This subroutine, which contains the equation-solving iteration procedure, calls SUBROUTINE FUNCT which contains the desired equation. Iteration is continued until two successive values are within 0.1% or until 10 iterations have been performed. The first approximation of $DH/2\ell\ell_1$ was usually close enough to produce an acceptable solution in 2 or 3 iterations. At this point, the program prints out the correction constants for the particular specimen and lists, for each test time, the measured deflection, the corrected deflection, the calculated strain, the pseudo-elastic stress, and the gage-section radius of curvature. The mean pseudo-elastic stress for the specimen is computed from these data and tabulated as a final step.

At least squares fit of the strain-time data is calculated in the second part of the program. The degree of the polynomial (linear, quadratic, or cubic) is specified on the control card; second degree has been found to yield the best fits. The polynomial matrix is generated in the main program and solved by SUBROUTINE MLRB. The program then writes the test time, the strain and (from the least-squares fit) the calculated strain, the calculated strain rate (the time derivative of strain), the log of strain and the pseudo-elastic stress and its logarithm.

*The FORTRAN IV source programs for the main program and all subroutines (NEWT, MLRB, SORT, OSORT, FUNCT and FEDOT are given in Appendix B.

FIGURE 32. TYPICAL CENTRIFUGAL CREEP TEST SPECIMEN

The strain and pseudo-elastic stress at constant strain-to-strain rate ratios are determined in the third part of the program. These ratios are obtained by dividing the time-strain polynomial by its time drivative. Test times (which are extrapolated 200 hr beyond the last experimental point) for which the strain-to-strain rate ratio is an even multiple of 100 are found by solving the equation:

$$X_1 - X_2 \left(\frac{\epsilon}{\dot{\epsilon}}\right) + t (X_2 - 2X_3)\left(\frac{\epsilon}{\dot{\epsilon}}\right) + t^2 (X_3 - 3X_4)\left(\frac{\epsilon}{\dot{\epsilon}}\right) + X_4 t^3 = 0 \quad (5)$$

where X_1 are the polynomial coefficients and t is the test time.

This non-linear equation is solved by SUBROUTINE NEWT, which calls SUBROUTINE FEDOT. Iteration is continued until two successive values are within 0.1% or until 10 iterations have been performed. The resultant time is then used to calculate the strain, strain rate, and the pseudo-elastic stress, since these are functions of temperature. The first approximation for time was chosen to be 0.9 times the strain-to-strain rate ratio. For the smaller strain-to-strain rate ratios, an acceptable value is normally found after two or three iterations. For high ratios, additional iterations are necessary and the differential-halving procedure in SUBROUTINE NEWT is needed. This procedure is designed to prevent overshoot. For every iteration except the first, SUBROUTINE NEWT compares the residual $f(x_2)$ with the value for the previous iteration $f(x_1)$. If $f(x_2)$ is smaller than $f(x_1)$, the program continues; if it is equal or larger, the previous change in x is halved and the process repeated.

The final phase of the program uses the standard CALCOMP plotter sub-routines to plot the strain-time data and the polynomial strain-time curve. One plot is produced for each specimen.

Figures 33, 34 and 35 are the plots of time vs total strain developed by the computer for the specimens of three heats of Hastelloy X tested for 1000 hr in air at 1800°F at four different stress levels. It can be seen that, where the applied stress was such that the total strain reached after 1000 hr of test was less than 1% (lower stress levels), a linear relationship existed between strain and time, but, where the strain exceeded about 1% (higher stress levels), the linear relationship did not exist (Specimens 1-5, 5-5, 35-5, 31-5, 32-5). This situation was a matter of concern

FIGURE 33. CENTRIFUGAL CREEP DATA - STRAIN VERSUS TIME FOR HASTELLOY X HEAT 4902

171-67-358

FIGURE 34. CENTRIFUGAL CREEP DATA - STRAIN VERSUS TIME FOR HASTELLOY X HEAT 4793

17.1-67-359

FIGURE 35. CENTRIFUGAL CREEP DATA - STRAIN VERSUS TIME FOR HASTELLOY X HEAT 4787

171-67-360

and was discussed with Dr. J. Dorn, a consultant in this field. The following conclusions were reached:

- All three heats behave differently but in a consistent manner at the higher stress levels.
- This behavior can be attributed to one or a combination of the following mechanisms:
 - stress recovery
 - short range order-disordering
 - multiplication of dislocations

It does not appear that short range ordering or multiplication of dislocations will account for the observed difference since these mechanisms are, primarily, temperature dependent and would not extend over such long periods of time. Stress recovery is considered the most probable explanation for the differences. It is quite possible that the 2150°F solution heat treatment performed by the manufacturer did not completely transform the substructure, so that all of the cold work had not recovered. If this were the case, stress recovery caused by the residual cold work would occur during the test and the recovery rate would be dependent on the applied stress and temperature. In such an event one would expect to observe the effects of the phenomena to a greater extent in the higher stress specimens, since it is well known that applied stress increases the rate of cold work recovery and that stress recovery causes an increase in creep rate.^(14,15,16) This would explain the shape of the curves in Figures 33, 34 and 35.

Curves for the higher applied stress show an increasing creep rate in the early stages of creep (while stress recovery was occurring) which changes to a constant creep rate in the later stages (after all stress recovery had occurred). This effect was less noticeable at the intermediate stress levels and practically absent at the lower stress levels. This situation emphasises the importance of the initial condition of the materials to the behavior of material under stress; in the future, consideration will be given to annealing of all specimens after machining and prior to any testing.

The total strain in each specimen at the end of the test is listed in Table 19, together with the mean pseudo-elastic stress ($\bar{\sigma}_{pe}$) and the calculated

TABLE 19 - STRESS-STRAIN DATA FOR HASTELLOY X TESTED
IN CENTRIFUGAL CREEP AT 1800°F IN AIR

<u>Heat No.</u>	<u>Specimen No.</u>	<u>ϵ_t (%)</u>	<u>σ_{pe_i} (psi)</u>	<u>$\overline{\sigma_{pe}}$ (psi)</u>	<u>n</u>	<u>1/n</u>	<u>n'</u>	<u>σ_c</u>
4902	1-5	2.415	1520.4	1572.5	1.33	.752	.9176	1442.9
	2-5	.814	1012.1	1027.8	1.33	.752	.9176	943.1
	3-5	.579	791.3	800.7	1.33	.752	.9176	734.7
	4-5	.437	666.8	673.1	1.33	.752	.9176	617.6
4793	5-5	2.895	1520.4	1580.3	1.48	.676	.8918	1409.3
	35-5	1.348	1012.1	1034.9	1.48	.676	.8918	922.9
	36-5	.755	791.3	803.4	1.48	.676	.8918	716.5
	6-5	.576	666.8	675.7	1.48	.676	.8918	602.6
4787	31-5	3.075	1521.9	1583.7	1.66	.602	.8675	1373.8
	32-5	1.953	1015.1	1047.3	1.66	.602	.8675	853.3
	33-5	.953	792.8	808.3	1.66	.602	.8675	701.2
	34-5	.749	666.8	677.9	1.66	.602	.8675	588.1

$\dot{\epsilon}$ = strain rate

ϵ_t % = total strain (%)

σ_{pe_i} = initial pseudo elastic stress (psi)

$\overline{\sigma_{pe}}$ = average pseudo elastic stress (psi)

$$\frac{1}{n} = \left(\frac{d \ln \sigma_{pe}}{d \ln \dot{\epsilon}} \right)_{\epsilon/\dot{\epsilon}}$$

$$n' = \frac{2}{3} + \left(\frac{1}{3} \frac{1}{n} \right)$$

$$\sigma_c = \sigma_{pe} \left[\frac{2}{3} + \frac{1}{3} \left(\frac{d \ln \sigma_{pe}}{d \ln \dot{\epsilon}} \right)_{\epsilon/\dot{\epsilon}} \right] = \sigma_{pe} \cdot n' = \text{calculated tensile creep stress.}$$

tensile creep stress (σ_c). The creep stress for each specimen (σ_c) was calculated from the relation

$$\sigma_c = \sigma_{pe} \left[\frac{2}{3} + \frac{1}{3} \frac{d \ln \sigma_{pe}}{d \ln \epsilon} \right]_{\epsilon/\dot{\epsilon}} \quad (6)$$

The value in brackets of Equation 6 is given by the reciprocal of the slope of a plot of ϵ vs σ_{pe} at constant $\epsilon/\dot{\epsilon}$ values (i.e., 100, 200, 300, etc) for each group of specimens of the same heat of material. These plots are shown in Figures 36, 37 and 38 as plotted from the data output of the computer program.

2.2.1.2 Tensile Creep Tests

During the report period, two existing tensile creep machines were equipped with improved temperature control instrumentation and checked-out. This instrumentation included proportional power controllers coupled with null-point temperature controllers. A Pt-Pt-10%Rh thermocouple provides the signal to the temperature controller. The check-out revealed that the system will control the temperature to within $\pm 0.5^\circ\text{F}$ of the selected value.

The test program involves the conduct of tensile creep tests of two specimens of each heat of Hastelloy X at creep rates corresponding to the highest and the lowest stress levels developed during centrifugal creep testing. The preparation of specimens of Heat 4762 was initiated; these specimens will be tested for 1000 hr at 1800°F in air. The specimens were machined to a thickness of 0.120" in the gage section to duplicate the thickness, type and amount of machining performed on the gage section of the centrifugal creep specimens. The tensile creep specimens will also be subjected to the same heat treatment as the centrifugal creep specimens prior to test loading. The tests are scheduled to commence operation in mid-April.

FIGURE 36. STRAIN VERSUS STRESS FOR CONSTANT ϵ/ϵ' - HASTELLOY X HEAT 4902

FIGURE 37. STRAIN VERSUS STRESS FOR CONSTANT ϵ/ϵ' - HASTELLOY X HEAT 4793

171-67-362

FIGURE 38. STRAIN VERSUS STRESS FOR CONSTANT ϵ/ϵ' - HASTELLOY X HEAT 4787

2.2.2 Task B-3 - Adaptation of Centrifugal and Tensile Creep Apparatus for Inert Atmosphere Testing

2.2.2.1 Adaptation of Centrifugal Creep Apparatus

The design and fabrication of the modified centrifugal creep machine (described in the previous quarterly report) was completed. During initial check-out operations, it was found that the oxygen content of the system could be controlled to less than 4 ppm and that the moisture content could be controlled at a level less than the lower limit of detectability. These impurity measurements were performed using a CEC Moisture Monitor (Model 26-303) and an Analytical System Company oxygen trace analyzer (Model 306).

The apparatus is shown in Figure 39. Some design changes were made to improve the performance of the machine and to facilitate operation. Four reinforcing cross bars were added inside the atmosphere retort to prevent inward motion of the walls due to thermal expansion. A heat baffle (reflector), consisting of a Hastelloy X sheet packed with 5" of thermal insulation, was placed over the retort to prevent upward heat flow and to reduce the temperature at the cover seals. The oxygen and moisture analyzers were connected in such a manner that both inlet and outlet argon streams can be monitored to provide a continuous analysis for control of the atmosphere. The argon exit line is connected to a mercury manometer and an oil bubbler so that pressure within the retort can be controlled to < 1 in. Hg (0.05 psi) above atmospheric pressure.

2.2.2.2 Adaptation of Tensile Creep Apparatus

Two vacuum retort-argon furnaces, complete with optical readout and instrumentation, are required to perform tensile creep tests in argon atmosphere. These furnaces have been ordered and are scheduled for delivery in mid-June. Electrical connections to accommodate the new furnaces were completed and the new temperature controlling instrumentation installed.

2.2.3 Task B-4, 1300°F Creep Test in Argon Atmosphere

The specimens for this test were designed and fabricated. These consist of two sets of five specimens each of Heats X4793 and E9505 and five specimens of vacuum-melted Hastelloy X. These specimens are designed to accumulate

FIGURE 39. MODIFIED CENTRIFUGAL CREEP MACHINE FOR INERT ATMOSPHERE TESTING

171-67-364

total strains of 0.1, 0.2, 0.5, 1.0 and 3.0% after 3000 hr of testing at 1300°F in a high-purity argon atmosphere. It was planned that specimens of four vanadium alloys (provided by the USAEC) would be included in this test. A significant delay in the delivery of this material has resulted in postponement of the initiation of the test.

14
125
18

REFERENCES

1. Evaluation of Hastelloy X as a Nuclear Cladding, Quarterly Progress Report 1 October through 31 December 1966, AGN-8214.
2. Isothermal Oxidation of Hastelloy X at 1750 and 1850°F in Air, Army Gas-Cooled Reactor Systems Program Report AGN-TM-413, December 1965.
3. S. T. Wlodek, "The Oxidation of Hastelloy Alloy X," Trans. of Met. Soc. of AIME, V. 230, p. 177, Feb 1964.
4. G. E. Wasielewski, "Nickel-Base Superalloy Oxidation," General Electric Technical Report AFML-TR-67-30, January 1967.
5. H. J. Beattie, Jr. and L. R. Woodyatt, General Electric Research Laboratories, Schenectady, New York, Personal Communication to J. S. Brunhouse, Aerojet-NEMO, June 29, 1965.
6. L. R. Woodyatt, H. J. Beattie, C. T. Sims, "Application of Periodic Group Effects and Phase Relationships to Stability of Nickel- and Cobalt-Base Superalloys and Stainless Steels," General Electric Co., presented at Fall AIME Meeting, October 20, 1964.
7. Symposium on the Nature, Occurrence and Effects of Sigma Phase, ASTM Special Pub. No. 110, 1951.
8. F. A. Comprelli, "Stability of High-Nickel Alloys in Superheated Steam", GEAP-4745, Nov. 1964.
9. H. J. Goldschmidt, "Occurrence of the Beta-Manganese Structure in Transition Metals Alloys and Some Observations on Chi-Phase Equilibria," Metallurgia, July, 1957, p. 17.
10. J. G. Mullin, S. F. Reiter and D. G. Ebeling, "Equilibrium Structures in Fe-Cr-Mo Alloys," Trans. of ASM, V. 46, 1954, p. 799.
11. H. Thielsch, "Physical Metallurgy of Austenitic Stainless Steels," Weld Res. Comm., Suppl. to Weld. Journ., Dec. 1950, p. 5775.
12. Evaluation Study of Hastelloy X as a Nuclear Cladding, Quarterly Progress Report 5 July through 30 September 1966 (Nov.) AGN-8205.
13. C. H. Lund and J. Wagner, "Identification of Microconstituents in Superalloys", DMIC Memo 160, Nov. 15, 1962.
14. L. Raymlnd and J. Dorn, "Recovery of Creep Resistant Substructure," Trans. of AIME, 230, April 1964.
15. R. E. Frenkel, O. D. Sherby & J. Dorn, "Effect of Cold Work on the High Temperature Creep Properties of Dilute Aluminum Alloys," 36th Annual Convention of the AIME Society, Chicago, Nov. 1954.

16. N. Jaffe and J. Dorn, "Effect of Stress and Recovery on the Creep Properties of High Purity Polycrystalline Alumina at Intermediate Temperatures," Trans. of AIME, Vol. 227, Dec. 1963.

APPENDIX A

DERIVATION OF THE DEFLECTION-STRAIN RELATION FOR CIRCULAR BENDING

$$l_o = 2R\theta$$

$$l = 2\theta(R + H/2) = l_o \frac{(R + H/2)}{R}$$

$$dl = - \frac{l_o H/2}{R^2} dR$$

Outer-fiber strain:

$$\begin{aligned}
 \epsilon &= \int_{l_0}^l \frac{dl}{l} = - \int_{R=\infty}^{R=0} \frac{l_0 (H/2) dR}{R^2 l_0 \left(\frac{R + H/2}{R} \right)} = - \int_{\infty}^R \frac{H/2 dR}{R(R + H/2)} \\
 &= \ln \left| \frac{R + H/2}{R} \right| = \ln \left| 1 + \frac{H/2}{R} \right| \\
 e^{\epsilon} &= 1 + \frac{H/2}{R} \\
 R &= \frac{H/2}{e^{\epsilon} - 1}
 \end{aligned}$$

where:

l_0 = length of unstrained element (it is assumed that the central fiber is always unstrained).

l = length of outer fiber.

APPENDIX B

COMPUTER PROGRAM

The FORTRAN computer program used for the reduction of the centrifugal creep data is presented in this Appendix.

BLANK

```

C PROGRAM TO REDUCE CENTRIFUGAL-CREEP DATA
C
C USE WITH SUBROUTINES NEWT,FUNCT,EDOT, AND CALCOMP SUBROUTINES
C
C FOR CONTROL CARD --
C   CCL 1-3  NUMBER OF TIME-DEFLECTION PAIRS (250 MAXIMUM)
C   CCL 5    DEGREE OF POLYNOMIAL FOR TIME-STRAIN
C   CCL 7    REFIT OPTION--
C             0= READ CONSTANTS, TIMES, DEFLECTIONS
C             1= READ DEFLECTIONS ONLY
C             2= REFIT PREVIOUS TIME-STRAIN DATA TO A POLYNOMIAL
C                   OF LOWER DEGREE
C             3= SAME AS 0 BUT SORT DATA IN ORDER OF INCREASING
C                   TIMES FIRST
C             4= SAME AS 1 BUT SORT DATA FIRST
C   CCL 9    PLOT OPTION--
C             0= NO PLOT
C             1= PLOT TIME-STRAIN DATA AND POLYNOMIAL FIT
C             2= LAST PLOT
C   CCL 10-14 SPECIMEN WIDTH, INCHES
C   CCL 15-18 DEFL. CORR. FACTOR, MICRONS/HR.
C   CCL 19-72 TITLE
C
C D= CORR. DEFLECTION, INCHES, PRINTED AS MILS
C D1= MEASURED DEFLECTION, READ AS MILS, STORED AS INCHES
C H= SPECIMEN THICKNESS, INCHES
C E= STRAIN
C AL= GAUGE-SECTION LENGTH
C AL1=LOADING-SECTION LENGTH
C N= NUMBER OF SAMPLES
C T= TIME, MIN.
C EY= FIRST APPROXIMATION FOR STRAIN
C MP= NUMBER OF POLYNOMIAL TERMS
C MP1=DEGREE OF POLYNOMIAL
C NI= NUMBER OF ITERATIONS
C CFAC1= CORRECTION FACTOR FOR DEFL., READ AS MICRO INCHES/HR
C CEDOT= CALCULATED STRAIN RATE
C
C   DIMENSION T(100),NJ(100), TITLE(9),NI(100),SCALC(100),SIGPE(100)
C   1,EY2(100),EY(100),AE(100,5),SEN(100),ECALC(100),D1(100)
C   2,DUM(100),LEN(100),DAT1(1024),CUMB(200),CMBT(200),XSAVE(10)
C   3,K(11),IT(10),LE(10),FOUT(10),ECFOUT(10),CEDOT(100)
C   COMMON DUMMY(700),X(5),R(100),D(100),H,HL,AL,AL1,RAD(100),
C   1,ROE(100),COZL(100),SZL(100),CCANG,C(100),AT(100,5)
C   EXTERNAL FUNCT,FEDOT
C   XY=9.
C   EXY=XY+2.0
C   CALL PLOTS(DAT1(1),1024)
C   CALL PLOT (0.0,1.0,-3)
C 4 REAL (5,101) N,MP1,IFIT,IPLCT,w, CFAC1,TITLE
C   MF=MF1+1
C   IFIT2=IFIT+1
C   DO 60 I=1,4
C 60 X(I)=0.0
C   GO TO (7,6,17,7,6),IFIT2
C 7 REAL (5,100) H,AL,AL1,RZER,ANGLE,wT,RPM
C   ANGR =ANGLE*0.017453
C   CCANG=(OS(ANGR)
C   SIANG=SIN(ANGR)

```



```

RZERO=RZER+H/2.0*COANG+SIANG*(1.0+AL+AL1/2.0)
RHO=C.297
SIGNCW=RHO*RPM*RPM*RZERO*AL1*AL1 / (WT*H*5.867E3*2.0)
REAL (5,102) (T(I),I=1,N)
IF (IFIT.LT.3) GO TO 61
DO 55 I=1,N
55 DUM(I)=T(I)
CALL SORT (T,COMB,N)
C TIME POLYNOMIAL MATRIX
61 DO 2 I=1,N
AT(I,1)=1.0
DO 2 J=2,MP
2 AT(I,J)=AT(I,J-1)*T(I)
HL=2.0*AL/H
HLAL1=HL*AL1
AL12=AL1/2.0
RCC=RPM*RPM/35181.
HALR=H*AL1*RHO
6 READ (5,114) (D1(I),I=1,N)
C SORT DEFLECTIONS
IF (IFIT.GT.2) CALL CSORT(N,DUM,D1,COMB)
SIGNCT=SIGNCW*W
SRL=SIGNCT/RZERO
WRITE (6,103) TITLE,N,H,AL,AL1,SIGNCT,RZERO,CFACT,W,RPM,WT,ANGLE
C CALCULATE STRAIN FROM DEFLECTION BY NEWTON'S METHOD
WHAL=W*HALR
WH6=6.0/(WT*H*H)
SIGSM=0.0
DO 3 I=1,N
D(I)=D1(I)-(CFACT*T(I))
EY(I)=D(I)/HLAL1
EY2(I)=EY(I)
CALL NEWT (E(I),FUNCT,EY2(I),1.E-3,10,1.0,IER,I,NI(I),NJ(I))
IF (IER.NE.0) WRITE (6,201) IER,D(I)
SIGPE(I)=WH6*WHAL*(RCC*(RZERO+RAD(I))*(1.0-CO2L(I))+AL12*SI2L(I))
1 *AL12*CO2L(I)+AL12*SI2L(I))
SIGSM=SIGSM+SIGPE(I)
3 CONTINUE
C WRITE TIME,DEFL.,STRAIN, PSEUDO-ELASTIC STRESS
WRITE (6,104) (T(I),D(I),E(I),SIGPE(I),EY(I),NI(I),D1(I),
1 RAD(I),EY2(I),NJ(I),I=1,N)
SIGAV=SIGSM/FLOAT(N)
WRITE (6,109) SIGAV
17 CONTINUE
C STRAIN-VS.-TIME POLYNOMIAL FIT
WRITE (6,105) MP1,N,TITLE
CALL MLRA (N,MP,IE)
IF (IE.EQ.1) GO TO 8
SRS=C.0
DO 9 I=1,N
ECALC(I)=E(I)-R(I)
C NON-STANDARD ENTRY TO FUNCT
CALL RADIUS (ECALC(I),I)
SIGPE(I)=WH6*WHAL*(RCC*(RZERO+RAD(I))*(1.0-CO2L(I))+AL12*SI2L(I))
1 *AL12*CO2L(I)+AL12*SI2L(I))
SLN(I)=ALOG(SIGPE(I))
ELN(I)=ALOG(ECALC(I))
CECCT(I)=0.0
DO 43 J=2,MP

```

```

43 CEDCT(I)=CEDOT(I)+FLOAT(J-1)*X(J)*T(I)**(J-2)          CREEP119
9  SRS=SKS+R(I)*K(I)                                         CREEP120
  SDN=SQRT(SRS/FLOAT(N-1))                                   CREEP121
  WRITE (6,106) (T(I),E(I),R(I),ECALC(I),CEDOT(I),ELN(I),SLN(I), CREEP122
  ISIGPE(I),I=1,N)                                           CREEP123
  WRITE (6,107) SKS,(X(I),I=1,MP)                             CREEP124
  WRITE (6,108) SDN                                           CREEP125
  PUNCH 101,N,MP1,IFIT,IPL0T,w ,CFACT,TITLE                 CREEP126
  PUNCH 111, (D(I),I=1,N)                                     CREEP127
  PUNCH 112, (E(I),I=1,N)                                     CREEP128
  IF(IPL0T.EQ.0) GO TO 8                                       CREEP129
  N2=2*N                                                       CREEP130
  N2P1=N2+1                                                    CREEP131
  N2P2=N2+2                                                    CREEP132
  NP1=N+1                                                       CREEP133
  NF2=N+2                                                       CREEP134
  CCMBT(N2P1)=0.0                                              CREEP135
  COMBT(N2P2)=133.33333                                         CREEP136
  CUMB(N2P1)=0.0                                               CREEP137
  CCMB(N2P2)=0.004                                             CREEP138
  CALL PLOT (0.,0.,3)                                          CREEP139
  CALL PLCT (XY,0.,2)                                          CREEP140
  CALL PLOT (0.,0.,3)                                          CREEP141
  CALL PLOT (0.,XY,2)                                          CREEP142
  XO=C.                                                         CREEP143
  YO=C.                                                         CREEP144
  DO 70 I=1,10                                                 CREEP145
  CALL SYMBOL (XC,YO,0.1,13,9C.,-1)                           CREEP146
70  YO=YO+1.                                                    CREEP147
  CALL NUMBER (-.2,0.0,0.1,0.C,9C.,1)                         CREEP148
  YO=C.8                                                        CREEP149
  FPN=C.004                                                     CREEP150
  DO 71 I=1,9                                                    CREEP151
  CALL NUMBER (-.2,YO,0.1,FPN,9C.,3)                           CREEP152
  YO=YO+1.                                                       CREEP153
71  FPN=FPN+0.004                                               CREEP154
  CALL SYMBOL (-.4,4.0,0.14,CHSTRAIN,9C.,6)                  CREEP155
  XU=C.0                                                         CREEP156
  YO=C.0                                                         CREEP157
  DO 57 I=1,13                                                  CREEP158
  CALL SYMBOL (XC,YO,0.1,13,0.C,-1)                             CREEP159
57  XU=XO+0.75                                                  CREEP160
  CALL NUMBER (0.,-.2,0.1,0.,(-.1)                             CREEP161
  XU=C.65                                                        CREEP162
  FPN=100.                                                       CREEP163
  DO 58 I=1,12                                                  CREEP164
  CALL NUMBER (XU,-0.2,0.1,FPN,0.C,-1)                         CREEP165
  XG=XO+0.75                                                    CREEP166
58  FPN=FPN+100.                                                CREEP167
  CALL SYMBOL (4.,-.4,0.14,SHTIME,HRS.,0.,9)                 CREEP168
  TSAVE1=T(NP1)                                                 CREEP169
  TSAVE2=T(NP2)                                                 CREEP170
  ECSVE1=ECALC(NP1)                                             CREEP171
  ECSVE2=ECALC(NP2)                                             CREEP172
  ESAVE1=E(NP1)                                                 CREEP173
  ESAVE2=E(NP2)                                                 CREEP174
  T(NP1)=CCMBT(N2P1)                                           CREEP175
  T(NP2)=CCMBT(N2P2)                                           CREEP176
  ECALC(NP1)=CCMB(N2P1)                                         CREEP177

```

```

      ECALC(NP2)=CCMB(N2P2)
      CALL LINE (T,ECALC,N,1,0,0,N2P2)
      E(NP1)=ECALC(NP1)
      E(NP2)=ECALC(NP2)
      CALL LINE (T,E,N,1,-1,0,N2P2)
      CALL SYMBOL (0.3,XY,0.14,TITLE,0.0,54)
      T(NP1)=TSAVE1
      T(NP2)=TSAVE2
      E(NP1)=ESAVE1
      E(NP2)=ESAVE2
      ECALC(NP1)=ECSVE1
      ECALC(NP2)=ECSVE2
      CALL PLOT (EXY,0.0,-3)
8  K(1)=100
      NED=10
      DO 50 I=1,NED
      CALL NEWT(TT(I),FEDOT,90.*FLCAT(I),.001,10,1.,IER,K(I),NI(I),NJ(I))
      IF (IER.EQ.0) GO TO 51
      WRITE (6,501) IER,K(I)
      GO TO 50
51 IF (TT(I).GT.(T(N)+200.)) GO TO 52
      EE(1)=X(1)
      EDOT(1)=0.0
      DO 44 J=2,MP
      EE(J)=EE(1)+X(J)*TT(I)**(J-1)
44 EDOT(J)=EDOT(1)+FLOAT(J-1)*X(J)*TT(I)**(J-2)
C  NCN-STANDARD ENTRY TO FUNCT
      CALL RADIUS (EF(I),I)
      SIGPE(I)=WH6*WHAL*(RCC*(RZERO+RAD(I)*(1.0-CO2L(I))+AL12*SI2L(I))
      I *AL12*CO2L(I)+AL12*SI2L(I))
      EOEDOT(I)=EE(I)/EDOT(I)
50 K(I+1)=K(I)+100
      GO TO 53
52 NED=I-1
      IF (NED.EQ.0) NED=1
53 WRITE (6,500) TITLE,(TT(I),EE(I),EDOT(I),EOEDOT(I),K(I),NI(I),
      ISIGPE(I),NJ(I),I=1,NED)
33 IF (IPL0T.NE.2) GO TO 4
      CALL PLOT (EXY,0.0,-3)
      CALL PLOT (0.0,1.,995)
      GO TO 4
100 FORMAT (3E12.0,2E6.0,2E12.0)
101 FORMAT (I3,I12,F5.1,6PF4.1,5A6)
102 FORMAT (6E12.5)
103 FORMAT (1H1,5X,35HREDUCTION OF CENTRIFUGAL-CREEP DATA, // 6X,9A6//
      13X14,11H DATA SETS,1X11H THICKNESS =,F12.3,3HIN.5X14H GAUGE LENGTH =
      2F5.2,3HIN.5X14H LOAD. LENGTH =F9.2,3HIN./19X13HINIT.STRESS =F10.3,
      33HPSI5X8H RADIUS =F11.2,3HIN.5X18HDEFL.CORR.FACTOR =3PF7.4,
      48HMILS/HR./19X16H SPECIMEN WIDTH =OPF8.4,3HIN.4X5HRPM =F14.2,
      58X,13HGAUGE WIDTH =,F12.4,3HIN./19X15HINITIAL ANGLE =F7.2,4HDEG.
      6 //7X5H TIME,6X10HDEFL/CIION,8X6HSTRAIN,11X8HPSEUDO-E,9X6HSTRAIN,
      7 17X5HMEAS.,6X6H RADIUS/11HPENULTIMATE/
      8 7X4HHRS.,9X4HMILS,29X6HSTRESS,9X11H1ST APPROX.,
      9 5X5HITER.,4X5HDEFL.,6X6HINCHES9X6HSTRAIN)
104 FORMAT(OPF13.2,3PF12.1,1PE20.5,OPF15.2,1PE19.5,19,3PF10.1,1PE14.3,
      11PE16.5,14)
105 FORMAT (1H1,4X24HPOLYNOMIAL FIT OF DEGREE,I3,1H,I4,10H DATA SETS,
      1//6X5A6//7X5H TIME,7X6HSTRAIN,
      210X,8HRESIDUAL,7X10HCALCULATED,5X11HCALC STRAIN40X5HCALC./7X,

```

```

      34FHRS.25X6FSTRAIN5X6HSTRAIN12X4HRATE5X9HLN STRAIN7X9HLN STRESS9X  CREEP237
      45HSICPE) CREEP238
106 FORMAT(GPF12.2,1P7E16.4) CREEP239
107 FORMAT (///11X8HSUM K SQ10X12HCOEFFICIENTS/1P2E20.4/(E40.4)) CREEP240
108 FORMAT (//5X15HSTD DEVIATION =,1PE12.5) CREEP241
109 FORMAT (53X7(1H-)/44X6HAVER.=,F10.2) CREEP242
111 FORMAT (2X25F-CORRECTED DEFLECTION,MILS/ 6(3PF10.2,2X)) CREEP243
112 FORMAT (2X,6FSTRAIN/ 6(1PE11.4,1X)) CREEP244
114 FORMAT (3P6F12.5) CREEP245
201 FORMAT (//5X,21HERROR STATEMENT, 1ER=13,3X, 6HFCR D=,E12.5//) CREEP246
500 FORMAT (1H1,5X9A6//6X10TIME HOURS,6X6HSTRAIN,8X11HSTRAIN RATE,6X CREEP247
      1 6HE/EDOT, 8X,1HK,3X,4HITER3X,15HPSEUDO-E STRESS// CREEP248
      2 (2X,6PF12.2,3X,1P2E15.5,6PF12.2,110,16,1PE17.5,16)) CREEP249
501 FORMAT (//19H EDOT ERKOR 1ER =,13,5H K =,15) CREEP250
      END CREEP251

      SUBROUTINE SORT (A,B,N) SORT 01
C   SORTS 2 ARRAYS IN INCREASING ORDER OF MATRIX A SORT 02
      DIMENSION A(N),B(N) SORT 03
      N2=N-1 SORT 04
      DO 2 I=1,N2 SORT 05
        I2=I+1 SORT 06
        DO 2 J=I2,N SORT 07
          IF(A(I).LE.A(J)) GO TO 2 SORT 08
          A2=A(I) SORT 09
          B2=B(I) SORT 10
          A(I)=A(J) SORT 11
          B(I)=B(J) SORT 12
          A(J)=A2 SORT 13
          B(J)=B2 SORT 14
        2 CONTINUE SORT 15
      RETURN SORT 16
      END SORT 17

      SUBROUTINE OSORT(N,A,B,C) OSORT 01
C   SORTS ARRAY B IN INCREASING ORDER OF ARRAY A OSORT 02
C   C IS A DUMMY ARRAY OSORT 03
      DIMENSION A(N),B(N),C(N) OSORT 04
      DO 3 J=1,N OSORT 05
        3 C(J)=A(J) OSORT 06
      N2=N-1 OSORT 07
      DO 2 I=1,N2 OSORT 08
        I2=I+1 OSORT 09
        DO 2 J=I2,N OSORT 10
          IF(C(I).LE.C(J)) GO TO 2 OSORT 11
          C2=C(I) OSORT 12
          B2=B(I) OSORT 13
          C(I)=C(J) OSORT 14
          B(I)=B(J) OSORT 15
          C(J)=C2 OSORT 16
          B(J)=B2 OSORT 17
        2 CONTINUE OSORT 18
      RETURN OSORT 19
      END OSORT 20

      SUBROUTINE NEWT (X,FUNCT,Y,EPS,ITEND,RTORD,1ER,K,N,M) NEWT 001
C   NEWT 002
C   TO SOLVE GENERAL NON-LINEAR EQUATIONS BY NEWTON'S ITERATION NEWT 003
C   SCHEME, WHICH REFINES THE INITIAL GUESS Y OF A ROOT X OF A NEWT 004

```

C	GENERAL EQUATION F(X)=0.	NEWT 005
C		NEWT 006
C	DESCRIPTION OF PARAMETERS	NEWT 007
C	X - SOLUTION OF THE NON-LINEAR EQUATION.	NEWT 008
C	FUNCT - THE NAME OF AN EXTERNAL SUBROUTINE WHICH COMPUTES	NEWT 009
C	THE FUNCTION FY AND ITS DERIVATIVE DFY.	NEWT 010
C	Y - THE INITIAL GUESS OF A ROOT X. (DESTROYED)	NEWT 011
C	Y BECOMES THE PENULTIMATE VALUE OF X.	NEWT 012
C	EPS - ITERATION STOPS IF RELATIVE ERROR LESS THAN EPS.	NEWT 013
C	ITEND - MAXIMUM NUMBER OF ITERATION STEPS.	NEWT 014
C	N - ACTUAL NUMBER OF ITERATIONS.	NEWT 015
C	M - NUMBER OF TIMES THAT DIFFERENTIAL VALUE WAS	NEWT 016
C	LARGER THAN THE PREVIOUS VALUE. (VALUE IS HALVED	NEWT 017
C	EACH TIME THIS OCCURS.)	NEWT 018
C	RTORD - THE ORDER OF THE ROOT X. RTORD MUST BE GREATER	NEWT 019
C	THAN OR EQUAL TO 1.0. IF NOTHING IS KNOWN ABOUT	NEWT 020
C	THE ROOT ORDER, ITS VALUE SHOULD BE 1.0.	NEWT 021
C	IER - RESULTANT ERROR CODE WHERE	NEWT 022
C	IER=0 NO ERROR	NEWT 023
C	IER=1 NO CONVERGENCE IN ITEND ITERATIONS	NEWT 024
C	IER=2 ITERATION IS NOT POSSIBLE BECAUSE THE	NEWT 025
C	DERIVATIVE APPROACHES ZERO	NEWT 026
C		NEWT 027
C	THE EXTERNAL SUBROUTINE SUBPROGRAM FUNCT(X,F(X),DF(X),INDEX)	NEWT 028
C	MUST BE FURNISHED BY USER.	NEWT 029
C		NEWT 030
C	IF (RTORD.LT.1.0) RTORD=1.0	NEWT 031
C	M=C	NEWT 032
C	N=1	NEWT 033
C	IER=C	NEWT 034
C	Z=Y	NEWT 035
C	CALL FUNCT (Z,FZ,DFZ,K)	NEWT 036
C	DETERMINE IF DERIVATIVE IS NEARLY ZERO.	NEWT 037
C	IF (ABS(DFZ).LT.1.E-20) GO TO 120	NEWT 038
C	AFZ=ABS(FZ)	NEWT 039
C	DZ=FZ/DFZ*RTORD	NEWT 040
C	X=Z-DZ	NEWT 041
C	DETERMINE IF SOLUTION IS NEARLY ZERO	NEWT 042
C	R=Y	NEWT 043
C	IF (ABS(R).LT.1.E-20.AND.ABS(X).LT.1.E-20) RETURN	NEWT 044
C	DETERMINE IF CURRENT VALUE ACCEPTABLY CLOSE TO PREVIOUS VALUE.	NEWT 045
C	IF (ABS(R).LT.1.E-20) R=X	NEWT 046
C	IF (ABS(DZ/R).LT.EPS) RETURN	NEWT 047
C	Y=X	NEWT 048
C	GO TO 110 N=2,ITEND	NEWT 049
C	CALL FUNCT (Y,FY,DFY,K)	NEWT 050
C	DETERMINE IF DERIVATIVE IS NEARLY ZERO.	NEWT 051
C	IF (ABS(DFY).LT.1.E-20) GO TO 120	NEWT 052
C	AFY=ABS(FY)	NEWT 053
C	DETERMINE IF CURRENT RESIDUAL IS SMALLER THAN PREVIOUS VALUE.	NEWT 054
C	IF (AFY.LT.AFZ) GO TO 2	NEWT 055
C	DZ=DZ/2.0	NEWT 056
C	M=M+1	NEWT 057
C	Y=Z-DZ	NEWT 058
C	GO TO 110	NEWT 059
C	2 DX=FY/DFY*RTORD	NEWT 060
C	ITERATED VALUE	NEWT 061
C	X=Y-DX	NEWT 062
C	DETERMINE IF SOLUTION IS NEARLY ZERO	NEWT 063

```

      R=Y
      IF (ABS(R).LT.1.E-20.AND.ABS(X).LT.1.E-20) RETURN
C   DETERMINE IF CURRENT VALUE ACCEPTABLY CLOSE TO PREVIOUS VALUE.
      IF (ABS(R).LT.1.E-20) R=X
      IF (ABS(CX/P).LT.EPS) RETURN
      Z=Y
      Y=X
      AFZ=AFY
      LZ=CX
110  CONTINUE
C   NO CONVERGENCE APPEARS AFTER ITEND ITERATIONS.
      IER=1
      N=ITEND
      RETURN
120  IER=2
      X=Y
      RETURN
      END

```

NEWT 064
NEWT 065
NEWT 066
NEWT 067
NEWT 068
NEWT 069
NEWT 070
NEWT 071
NEWT 072
NEWT 073
NEWT 074
NEWT 075
NEWT 076
NEWT 077
NEWT 078
NEWT 079
NEWT 080
NEWT 081

```

      SUBROUTINE FUNCT (S,FY,DFY,I)
      COMMON DUMM(805),D(100),H,HL,AL,AL1,RAD(100),ROD(100),CO2L(100),
1  SI2L(100),COANG
C   FL=2*LENGTH/H
      Z=EXP(S)
      Y=Z-1.0
      FLY=FL*Y
      CO2L(I)=COS(FLY)
      SI2L(I)=SIN(HLY)
      RCL(I)=(COANG+1.0/Y)*H/Z.0
      RAD(I)=F/(2.0*Y)
      FY=RCL(I)*(1.0-CO2L(I))+AL1*SI2L(I)-D(I)
      DFY=(FL*ROD(I)*SI2L(I)-RAD(I)/Y*(1.-CO2L(I))+HL*AL1*CO2L(I))*Z
      RETURN
      ENTRY RADCLS (S,I)
      Y=EXP(S)-1.0
      FLY=FL*Y
      CO2L(I)=COS(FLY)
      SI2L(I)=SIN(HLY)
      RAD(I)=F/(2.0*Y)
      RETURN
      END

```

FUNC 01
FUNC 02
FUNC 03
FUNC 04
FUNC 07
FUNC 08
FUNC 09
FUNC 10
FUNC 11
FUNC 12
FUNC 13
FUNC 14
FUNC 15
FUNC 16
FUNC 17
FUNC 18
FUNC 19
FUNC 20
FUNC 21
FUNC 22
FUNC 23
FUNC 24

```

      SUBROUTINE FECDT (Y,FY,DFY,K)
      COMMON DUMPY(700),X(5)
      CAY=FLCAT(K)
      Y2=Y*Y
      X23=X(2)-2.0*CAY*X(3)
      X34=X(3)-3.0*CAY*X(4)
      X4Y=X(4)*Y2
      FY=X(1)-CAY*X(2)+Y*X23+Y2*X34+X4Y*Y
      LFY=X23+2.0*Y*X34+3.0*X4Y
      RETURN
      END

```

FECOT 01
FECOT 02
FECOT 03
FECOT 04
FECOT 05
FECOT 06
FECOT 07
FECOT 08
FECOT 09
FECOT 10
FECOT 11

```

      SUBROUTINE MLRA (M,N,IE)
      COMMON B(500),W(100),V(100),X(5),R(100),CUMPY(505),Y(100),A(100,5)
C   DESCRIPTION OF PARAMETERS --
C   M= NUMBER OF ROWS IN MATRIX

```

MLRA 001
MLRA 002
MLRA 003
MLRA 004
MLRA 005

C	N=	NUMBER OF COLUMNS IN MATRIX	MLRA 006
C	IE=	ERROR CODE-- 0=NO ERROR, 1= ERROR STATEMENT WRITTEN	MLRA 007
C	A=	TWO-DIMENSIONAL ARRAY	MLRA 008
C	Y=	CONSTANT VECTOR	MLRA 009
C	X=	RESULTANT COEFFICIENTS	MLRA 010
C	R=	RESIDUALS	MLRA 011
C			MLRA 012
	IE=C		MLRA 013
	IF (N.LT.M) GO TO 304		MLRA 014
	IF (N.LT.2) GO TO 308		MLRA 015
	DO 10 I=1,M		MLRA 016
	DO 10 J=1,N		MLRA 017
	LL = (J-1)*M+1		MLRA 018
10	B(LL) = A(I,J)		MLRA 019
	DO 70 I=1,N		MLRA 020
	IIA=(I-1)*M		MLRA 021
	T = C.		MLRA 022
	DO 20 K=I,M		MLRA 023
	LL=IIA+K		MLRA 024
20	T=T+B(LL)*B(LL)		MLRA 025
	IF (T.EQ. 0.0) GO TO 300		MLRA 026
	ST=SQRT(T)		MLRA 027
	LL=IIA+I		MLRA 028
	W(I)=SIGN(ST,B(LL))		MLRA 029
	B(LL) = B(LL) + W(I)		MLRA 030
	V(I) = - B(LL) * W(I)		MLRA 031
	IF(I.EQ.N) GO TO 75		MLRA 032
	IP = I + 1		MLRA 033
	DO 70 J=IP,N		MLRA 034
	JIA=(J-1)*M		MLRA 035
	T = C.		MLRA 036
	DO 40 K=I,M		MLRA 037
	LL=IIA+K		MLRA 038
	LLL=JIA+K		MLRA 039
40	T = T + B(LL) * B(LLL)		MLRA 040
	T = T/V(I)		MLRA 041
	DO 70 L=I,M		MLRA 042
	LL=JIA+L		MLRA 043
	LLL=IIA+L		MLRA 044
70	B(LL) = B(LL) + T * B(LLL)		MLRA 045
300	WRITE (6,1004)		MLRA 046
	GO TO 103		MLRA 047
308	WRITE (6,1002)		MLRA 048
	GO TO 103		MLRA 049
304	WRITE (6,1001)		MLRA 050
103	IE=1		MLRA 051
75	S=C.C		MLRA 052
	DO 100 L=1,M		MLRA 053
	R(L)=Y(L)		MLRA 054
100	S=S+R(L)*R(L)		MLRA 055
	DO 90 I=1,N		MLRA 056
90	X(I) = 0.		MLRA 057
	YE = S		MLRA 058
105	DO 110 I=1,N		MLRA 059
	IIA=(I-1)*M		MLRA 060
	T = C.		MLRA 061
	DO 110 K=I,M		MLRA 062
	LL=IIA+K		MLRA 063
110	T = T + B(LL) * R(K)		MLRA 064

T = T/V(I)	MLRA 065
DO 120 L=1,M	MLRA 066
LL=IIA+L	MLRA 067
120 R(L) = R(L) + T * B(LL)	MLRA 068
130 CONTINUE	MLRA 069
IN = N	MLRA 070
DO 150 I=1,N	MLRA 071
140 R(IN) = R(IN)/w(IN)	MLRA 072
INM=IN-1	MLRA 073
LLIN=INM*M	MLRA 074
J=INM	MLRA 075
DO 155 L=1,INM	MLRA 076
LL=LLIN+J	MLRA 077
R(J) = R(J) + R(IN) * B(LL)	MLRA 078
155 J = J - 1	MLRA 079
190 IN = IN - 1	MLRA 080
DO 210 I=1,N	MLRA 081
210 X(I)=X(I)-R(I)	MLRA 082
DO 230 I=1,M	MLRA 083
RD = Y(I)	MLRA 084
DO 220 J=1,N	MLRA 085
220 RD=RD-A(I,J)*X(J)	MLRA 086
R(I) = RD	MLRA 087
230 CONTINUE	MLRA 088
RE = 0.	MLRA 089
DO 240 I=1,M	MLRA 090
240 RE=RE+R(I)*R(I)	MLRA 091
IF(RE.GE.S) GO TO 270	MLRA 092
S = RE	MLRA 093
GO TO 105	MLRA 094
270 IF (RE.LT.YE) RETURN	MLRA 095
WRITE (6,1003)	MLRA 096
IE=1	MLRA 097
RETURN	MLRA 098
1001 FORMAT (24HOMORE UNKNOWN THAN EQNS /	MLRA 099
1 2X,30H(OR MORE TERMS THAN DATA SETS))	MLRA 100
1002 FORMAT (27HONLY ONE UNKNOWN SPECIFIED)	MLRA 101
1003 FORMAT (16HERROR, R .GE. Y)	MLRA 102
1004 FORMAT (48H0 ERROR, EQUATIONS ARE NOT LINEARLY INDEPENDENT.)	MLRA 103
END	MLRA 104

DISTRIBUTION LIST

CONTRACT NO. AT(04-3)-368, PROJECT AGREEMENT NO. 6 WITH AEROJET

U. S. Atomic Energy Commission
San Francisco Operations Office
2111 Bancroft Way
Berkeley, California

U. S. Atomic Energy Commission (2)
Division of Reactor Development
and Technology
Washington, D. C.
Attn: J. M. Simmons

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: A. Van Echo

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: Dr. J. A. Lieberman

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: S. A. Szawlewicz

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: M. J. Whitman

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: F. D. Haines

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: F. C. Schwenk

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: R. T. Carpenter

U. S. Atomic Energy Commission
Office of Space Nuclear Systems
Washington, D. C.
Attn: C. E. Johnson

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: R. E. Pahler

U. S. Atomic Energy Commission
Division of Reactor Development
and Technology
Washington, D. C.
Attn: D. E. Bailey

U. S. Atomic Energy Commission (3)
Division of Technical Information
Extension
Box 62
Oak Ridge, Tennessee 37831
Attn: R. L. Shannon

U. S. Atomic Energy Commission
Document Library
Germantown, Maryland 20545

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: R. E. Macheley

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: L. Kelman

Argonne National Laboratory
9700 South Cass Avenue
Argonne, Illinois
Attn: J. H. Kittel

Distribution List for Contract AT(04-3)-368 (continued)

Brookhaven National Laboratory
Upton, Long Island, New York 11973
Attn: D. Gurinsky

Brookhaven National Laboratory
Upton, Long Island, New York 11973
Attn: C. Klamut

Los Alamos Scientific Laboratory (2)
P. O. Box 1663
Los Alamos, New Mexico
Attn: D. B. Hall

Oak Ridge National Laboratory (2)
P. O. Box Y
Oak Ridge, Tennessee
Attn: J. Cunningham

Oak Ridge National Laboratory
P. O. Box Y
Oak Ridge, Tennessee
Attn: P. Patriarca

Oak Ridge National Laboratory
P. O. Box Y
Oak Ridge, Tennessee
Attn: J. Weir

Pacific Northwest Laboratory (2)
Battelle Memorial Institute
P. O. Box 999
Richland, Washington
Attn: J. J. Cadwell

Pacific Northwest Laboratory
Battelle-Memorial Institute
P. O. Box 999
Richland, Washington
Attn: T. T. Claudson

U. S. Air Force
Code MATB
Wright-Patterson AFB, Ohio
Attn: G. Glenn

Army Materials Research Agency
Watertown Arsenal
Watertown 72, Massachusetts
Attn: S. V. Arnold

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: G. M. Ault

NASA-Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135
Attn: T. Moss

NASA
Code RRM
Washington, D. C. 20546
Attn: J. Maltz

Bureau of Naval Air Systems
Department of the Navy
Washington, D. C.
Attn: I. Machlin

Atomics International
Division of North American Aviation
P. O. Box 309
Canoga Park, California
Attn: C. E. Weber

Babcock and Wilcox Company
1201 Kemper Street
Lynchburg, Virginia
Attn: C. Baroch

Combustion Engineering, Inc.
P. O. Box 5000
Windsor, Connecticut 06095
Attn: W. P. Chernock, Asst. Mgr.,
Nuclear Laboratories

Combustion Engineering, Inc.
P. O. Box 5000
Windsor, Connecticut 06095
Attn: S. S. Christopher
Nuclear Laboratories

General Atomic
Division of General Dynamics
P. O. Box 1111
San Diego, California 92112
Attn: A. Weinberg

Distribution List for Contract AT(04-3)-368 (continued)

General Electric Company
Nuclear Materials & Propulsion Op.
Evendale, Ohio
Attn: J. McGurty

General Electric Company
Nuclear Materials & Propulsion Op.
Evendale, Ohio
Attn: C. Brassfield

General Electric Company (3)
310 DeGuigne Drive
Sunnyvale, California 94086
Attn: K. P. Cohen, Gen. Mgr.,
Advanced Products Operation

MSA Research Corporation
Callery, Pennsylvania
Attn: C. H. Staub

MSA Research Corporation
Callery, Pennsylvania
Attn: R. C. Werner

Nuclear Materials and
Equipment Corporation
609 N. Warren Avenue
Apollo, Pennsylvania 15613
Attn: Z. M. Shapiro, President
& General Manager

United Nuclear Corporation
5 New Street
White Plains, New York 10601
Attn: Dr. K. Goldman

United Nuclear Corporation
P. O. Box 1583
365 Winchester Avenue
New Haven 4, Connecticut
Attn: A. Strasser

Westinghouse Electric Corporation
Atomic Power Division
P. O. Box 355
Pittsburgh, Pennsylvania 15230
Attn: Dr. J. H. Wright, Mgr.,
Advanced Reactor Systems

Westinghouse Electric Corporation
Atomic Power Division
P. O. Box 355
Pittsburgh, Pennsylvania 15230
Attn: R. J. Allio, Mgr.
Advanced Materials

Westinghouse Electric Corporation
P. O. Box 10864
Pittsburgh, Pennsylvania 15236
Attn: D. Goldberg
Astro Nuclear Laboratory

Battelle-Memorial Institute
Columbus, Ohio
Attn: DMIC

Battelle-Memorial Institute
Columbus, Ohio
Attn: S. Paprocki

Lockheed Aircraft Company
Palo Alto, California
Attn: R. A. Perkins

Boeing Airplane Company
Aero-Space Division
P. O. Box 3707
Seattle, Washington
Attn: J. T. Stacey

McDonnell Aircraft Company
Department 272
P. O. Box 516
St. Louis, Missouri
Attn: H. Siegel

Union Carbide Satellite Company
Kokomo, Indiana
Attn: W. Schussler

Sandia Corporation
P. O. Box 5800
Albuquerque, New Mexico 87115
Attn: R. P. Stromberg
Division 9333