~~C-92a-92b~~ 93b

UNCLASSIFIED

SECURITY INFORMATION
Classification: U
Class: U Date: 3-16-82

NOTICE

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness or usefulness of any information, apparatus, product or process disclosed, or represents that its use would not infringe privately owned rights.

Classification cancelled (or changed to) _____
by authority of Doc _____
by H.A.C. TIG, Date 1988 1973

RESTRICTION OF THE ELEMENTS LIMITED
To Government and its contractors

~~CONFIDENTIAL~~

DISCLAIMER

This report was prepared as an account of work sponsored by an agency of the United States Government. Neither the United States Government nor any agency Thereof, nor any of their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States Government or any agency thereof. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States Government or any agency thereof.

DISCLAIMER

Portions of this document may be illegible in electronic image products. Images are produced from the best available original document.

Blank Page

~~CONFIDENTIAL~~

Astronuclear
Laboratory

PREFACE

This report is submitted according to the terms of Atomic Energy Commission Contract AT(29-2)-2638, Phase II-C, Compact Thermoelectric Converter Program. The Phase II-C Program, which spanned from July 1, 1968 through June 30, 1969, was conducted by the Astronuclear Laboratory of the Westinghouse Electric Corporation under the direction of the Atomic Energy Commission.

This Final Report for Phase II-C presents the significant progress on the Compact Thermoelectric Converter Program for the period from July 1, 1968 through June 30, 1969. Also included are pertinent results of certain other programs being performed in parallel with the contract. Such items are noted as they are reported.

~~CONFIDENTIAL~~

~~DISTRIBUTION OF THIS DOCUMENT IS LIMITED
To Government Contractors~~

Blank Page

TABLE OF CONTENTS

<u>Section No.</u>		<u>Page</u>
	PREFACE	iii
	LIST OF ILLUSTRATIONS	vii
	LIST OF TABLES	xiii
	ABSTRACT	xv
	INTRODUCTION AND SUMMARY	xvii
I	DESIGN AND ANALYSIS	1-1
	A. Introduction	1-1
	B. Module Development for Reactor Systems: TEM-9 Series Modules	1-4
	C. Module Development for Heat Pipe Application	1-28
	D. Module Development for Centerline Fueled Isotope	1-48
	E. Engineering Analysis Technique Development	1-60
	F. Summary	1-65
II	MATERIALS AND PROCESS DEVELOPMENT	2-1
	A. Materials Development	2-1
	B. Process Development	2-62
	C. Summary	2-64
III	MODULE DEVELOPMENT	3-1
	A. Introduction	3-1
	B. Module Fabrication	3-2
	C. Test Results	3-12
	D. Summary	3-33

~~CONFIDENTIAL~~

TABLE OF CONTENTS (CONTINUED)

<u>Section No.</u>	<u>Page</u>
APPENDIX A NOMENCLATURE	A-1
APPENDIX B SUMMARY OF MODULE DESIGN DEVELOPMENT	B-1
APPENDIX C STATISTICAL TREATMENT OF TUNGSTEN DISPERSED BAR DATA	C-1

~~CONFIDENTIAL~~

LIST OF ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1-1	A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data from Thin Washer Module Experiments	1-7
1-2	A Comparison of Calculated and Experimental Internal Resistance Data from Thin Washer Module Experiments	1-8
1-3	A Comparison of Calculated and Experimental Thermal Impedance Data from Thin Washer Module Experiments	1-9
1-4	TEM-9U Pressure Profiles at Operating Temperature	1-11
1-5	Sectioned View of TEM-9U S/N-21	1-15
1-6	A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data Measured During Heatup of Split Conductor Ring Modules	1-17
1-7	A Comparison of Calculated and Experimental Internal Resistance Data Measured During Heatup of Split Conductor Ring Modules	1-19
1-8	A Comparison of Calculated and Experimental Thermal Impedance Data Measured During Heatup of Split Conductor Ring Modules	1-20
1-9	A Comparison of Three Module End Closure Designs	1-26
1-10	Heat Pipe - TEM-10 Test Unit	1-29
1-11	Schematic of WANL Heat Pipe	1-31
1-12	Sodium Heat Pipe Startup Test Data	1-34
1-13	Heater/Heat Pipe/Module Assembly	1-36
1-14	A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data Measured During Heatup of Two TEM-10 Series Modules	1-38

~~CONFIDENTIAL~~

LIST OF ILLUSTRATIONS (CONTINUED)

<u>Figure</u>		<u>Page</u>
1-15	A Comparison of Calculated and Experiment Internal Resistance Data Measured During Heatup of TEM-10 Series Modules	1-39
1-16	Calculated End Closure Heat Flow Rate Distribution for the TEM-10 S/N-3 Module	1-46
1-17	Calculated End Closure Heat Flow Rate Distribution for a TEM-10 S/N-8 Module Design	1-47
1-18	TEM-12 Internal Pressure Profiles	1-50
1-19	Calculated Circuit Efficiency for the TEM-12B Design	1-53
1-20	Calculated Power Output for the TEM-12B Design	1-54
1-21	Calculated Fuel Power Density Requirements to Produce Assumed Clad Temperatures in the TEM-12B Design	1-55
2-1	Electron Beam Microprobe Photos Showing Back-Scattered Electron Pattern of EXC Capsule With TEGS/2P Interface Tested for 1500 Hours at 1202°F (650°C), (500X).	2-4
2-2	Electron Microprobe Horizontal Line Scan for Te and Pb Over Nb/TEGS-2P Interface of EXC Capsule, Tested for 1500 Hours at 1202°F (650°C). Trace Taken Over Same Area as Shown in Figure 2-1.	2-6
2-3	Resistance Versus Time at Test Conditions for EXC Capsules Containing Tungsten Contacts - 2800 Hours at 1382°F (750°C)	2-8
2-4	Seebeck Coefficient Versus Distance Along Pellet Axis for EXC Capsules Containing Tungsten Contacts - 2800 Hours at 1382°F (750°C)	2-9
2-5	Electrical Properties of Lead Telluride Bars Before Annealing	2-11
2-6	Electrical Properties of Lead Telluride Bars Before and After Annealing	2-12

LIST OF ILLUSTRATIONS (CONTINUED)

<u>Figure</u>		<u>Page</u>
2-7	Seebeck Coefficient Versus Distance from Inner Conductor Ring for Section 1, TEM-9U S/N-7 p-Type Washer. Average of Six Probe Traces. $T_H \approx 1193^\circ\text{F}$ (645°C).	2-15
2-8	Electron Microprobe Trace for Te, W, and Pb from p-Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Begun in Lead Telluride Matrix and Moved to p-Type/W Interface.	2-16
2-9	Seebeck Coefficient Versus Distance from Inner Conductor Ring for n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Taken in a Plane 79 Mils in an Axial Direction from Large Mica Washer.	2-17
2-10	Electron Microprobe Trace for Te, W, and Pb from n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Begun in Lead Telluride Matrix and Moved to n-Type/W Interface.	2-19
2-11	Schematic of Axial Position of Seebeck Probe Traces Taken on n-Type Washers of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C).	2-20
2-12	Seebeck Coefficient Versus Distance from Inner Conductor Ring for n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Taken in a Plane 14 Mils in an Axial Direction from Large Mica Washer.	2-21
2-13	Schematic Representation of Contamination of n-Type Washers of TEM-9U S/N-7	2-23
2-14	Seebeck Coefficient Versus Radial Distance from Inner Conductor Ring for Various TEM Modules.	2-29
2-15	Comparison of Seebeck Coefficients of Unaffected TEGS-3N and TEGS-2N and PbTe Material from TEM-1 S/N-4.	2-30
2-16	Seebeck Voltage Versus Distance Along Axial Length for EXC 52, Tested for 2800 Hours at 650°C (1202°F).	2-32

~~CONFIDENTIAL~~

LIST OF ILLUSTRATIONS (CONTINUED)

<u>Figure</u>		<u>Page</u>
2-17	Resistivity of Heat Treated Phlogopite Mica Versus Reciprocal Temperature	2-35
2-18	Seebeck Probe of the End n-Type PbTe Pellet from EXC 65.	2-39
2-19	Mica Tested in Capsule EXC 70 for 1000 Hours at 1202°F (650°C), 100X	2-40
2-20	n-Type Pellets Removed From Capsule EXC 66 After 1000 Hours at 1202°F (650°C)	2-42
2-21	Mica/W/Mica Tested in Capsule EXC 82 for 1000 Hours at 1202°F (650°C), 100X	2-43
2-22	Positions of Seebeck Probe Traces Taken on Pellets No. 240 and No. 234.	2-44
2-23	Seebeck Coefficient Versus Distance Along TEGS-2N Pellets	2-45
2-24	Specimen Location and Sodium Concentration Obtained by Neutron Activation Analysis	2-47
2-25	Seebeck Coefficient Versus Average Temperature for Heat Treated n-Type Bars Containing Excess Tellurium.	2-50
2-26	Seebeck Coefficient Versus Average Temperature for Non-heat Treated n-Type Bars Containing Excess Tellurium.	2-52
2-27	Seebeck Coefficient and Resistivity Versus Average Temperature for Center n-Type Pellet from EXC 52. Tested for 2800 Hours at 1202°F (650°C).	2-54
2-28	Electrical Resistivity Versus Average Temperature for Heat Treated n-Type Bars Containing Excess Tellurium.	2-55
2-29	Electrical Resistivity Versus Average Temperature for Non-Heat Treated n-Type Bars Containing Excess Tellurium.	2-56

~~CONFIDENTIAL~~

LIST OF ILLUSTRATIONS (CONTINUED)

<u>Figure</u>		<u>Page</u>
2-30	Seebeck Coefficient Versus Distance from P/N Interface	2-58
2-31	Hall Coefficient of TEGS-2P Lead Telluride at 4.2°K Versus Magnetic Field	2-60
3-1	Axial Compression of Module with Low Heat Loss End Design	3-4
3-2	Typical Liquid Penetrant Defect Indications in Inconel 718 Inner Clad/304 Stainless Steel End Cap Weld Specimen	3-6
3-3	Crack Locations, Weld Metal/Base Metal Transition Zone, and Heavy Incipient Melting in Heat Affected Zone Grain Boundaries in Inconel 718 Inner Clad/304 Stainless Steel End Cap Weld Specimens.	3-8
3-4	Reduced Transition Zone and Very Limited Incipient Melting in Heat Affected Zone Grain Boundaries in Inconel 718 Inner Clad/304 Stainless Steel End Cap Specimens Welded with Copper Chill Plug.	3-9
3-5	TEM-9U S/N-12 Negative End Cap Showing Oxide Stringers Penetrating Wall, As-Polished, 50X	3-11
3-6	TEM-1 S/N-1: Circuit Efficiency Versus Time on Test	3-13
3-7	TEM-9C Series Module Data: Circuit Efficiency Versus Time at Test Conditions	3-16
3-8	TEM-9E and -9I Series Module Data: Circuit Efficiency Versus Time at Test Conditions	3-18
3-9	TEM-9Q Series Data: Circuit Efficiency Versus Time at Test Conditions	3-20
3-10	Life Test Circuit Efficiency Data for TEM-9Q S/N-5, -6, and -7	3-22
3-11	Circuit Efficiency of High Voltage Modules: TEM-9AE Series	3-23

~~CONFIDENTIAL~~

LIST OF ILLUSTRATIONS (CONTINUED)

<u>Figure</u>		<u>Page</u>
3-12	Comparison of Barrier With Non-Barrier Module Static Test Circuit Efficiency Data for 1000°F Operation	3-26
3-13	High Temperature Circuit Efficiency Data from TEM-9U Series Modules	3-29
3-14	Electrical Power Output Versus Time on Test Recorded for the TEM-10/Heat Pipe/Radiator System	3-32

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

LIST OF TABLES

<u>Table</u>		<u>Page</u>
1-1	Axial Dimensions of TEM-9AE and -9Q Series Modules	1-5
1-2	TEM-9U S/N-9 Thermal Cycle Test Results	1-13
1-3	Module Axial Measurement Summary	1-22
1-4	Results of Weld Penetration Experiments	1-23
1-5	Calculated TEM-10 End Heat Loss Rates in Watts Per End	1-45
1-6	TEM-12 Large Bore Module Characteristics	1-52
2-1	Results of Statistical Treatment	2-13
2-2	Nominal Carrier Concentration from Hall Data	2-61
2-3	T/E Washer Designs Successfully Fabricated to Date	2-63
3-1	TEM-1 S/N-1 Performance Summary	3-14
3-2	TEM-9C S/N-2 Performance Trend Summary	3-15
3-3	A Comparison of Lead Telluride and Mica Washer Thicknesses for TEM-9Q and TEM-9AE Series Modules	3-21

~~CONFIDENTIAL~~

Blank Page

~~CONFIDENTIAL~~

ABSTRACT

Tubular thermoelectric module technology was advanced during Phase II-C of the Compact Converter Program to the extent that the baseline temperature for module testing was raised from 1000°F to 1100°F. A module incorporating material and design changes was tested in excess of 2000 hours at a peak temperature of 1150°F without any observable power degradation. Significant development work was performed to produce a system utilizing a heat pipe that transmitted thermal energy from an external heat source to a tubular module. During this phase of the program a complete conversion system consisting of a simulated heat source coupled to a tubular module with a Westinghouse heat pipe and a planar radiator was designed, fabricated, and placed on test. End closure designs on subsequent modules of this type improved the thermal cycling capabilities so that module performance remained unchanged after twenty-one cycles. Additional materials work has identified a secondary degradation diffusion mechanism at temperatures above 1100°F. Experiments have shown that techniques can be employed to prevent detrimental diffusion and, hence, allow successful operation at even higher temperatures.

~~CONFIDENTIAL~~

Blank Page

~~CONFIDENTIAL~~

INTRODUCTION AND SUMMARY

INTRODUCTION

The Compact Converter Program was initiated at the Westinghouse Astronuclear Laboratory by the Atomic Energy Commission in mid-1965. As defined in the Request for Proposal - Compact Converter Development Program - the original objective of the program was to develop and qualify a reliable, high performance thermoelectric module and other converter hardware (if required) for use in 1 to 20 Kwe compact thermoelectric converters. These units would be used with radioisotope and SNAP reactor (uranium-zirconium hydride core) heat sources in a number of space applications. Consistent with these objectives the converter would operate with hot (heat source) and cold (radiator) loops, and would be compatible with loop components currently available or under development. The converter module was to be designed to provide maximum flexibility over current state-of-the-art.

Phase I of the program was a 6-month system study and hardware demonstration program. Phase II-A, which spanned 1966, was primarily a tubular thermoelectric module technology program devoted to the materials and component development work required to solve problems identified during or anticipated as a result of the Phase I effort. Phase II-B, which ran from January 1, 1967 through June 30, 1968, was primarily a technology program devoted to the process and module development work required to improve the module operating performance. As such, many of the programs initiated in Phase II-A carried over into Phase II-B. Midway through the Phase II-B program, the mode of module performance degradation was identified and some practical solutions were developed. Cyclic testing accomplished during Phase II-B provided graphic demonstration that the tubular module is insensitive to severe thermal shocks and repeated over-temperature cycles.

The objectives of Phase II-C, which spanned the 1-year period ending June 30, 1969 were redefined from those initially identified in the RFP. The Phase II-C objectives were as follows:

- 1) Continue the development of tubular module technology for two-loop reactor or isotope heated systems.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

2) Develop tubular module technology for centerline heated (radioisotope capsules) isotope systems.

3) Develop tubular module/heat pipe technology integration.

SUMMARY

During Phase II-C, the major factors contributing to observed performance degradation during operation at elevated temperatures (above 1100°F) were isolated. A design fix was developed in order to control the degradation phenomenon. Successful integration of various design fixes into Phase II-C modules resulted in the ability to test at increasingly higher temperatures. Accordingly, the baseline temperature for module evaluation was increased to 1100°F from 1000°F. Even at this elevated temperature, testing times in excess of 2000 hours were accrued before any reduction in power output was observed in TEM-9U S/N-19, the first module fabricated with one of the degradation controlling design fixes.

During Phase II-C two materials study modules were fabricated and placed on test. The first of these modules contained only GE n-type lead telluride washers; the second employed only TEGS-2P lead telluride washers. In all other respects these modules were identical to standard TEM-9 power-producing modules. No degradation (as evidenced by constant internal circuit resistance) has been observed after 3600 hours of testing at average hot clad temperatures of 1200°F (peak temperatures up to 1250°F). Performance of these modules indicates that stable operation will be obtained at temperatures at least as high as 1250°F when a positive barrier to p- and n-type lead telluride migration is developed.

Materials experiments to define electrical contacts which would be compatible with lead telluride proved that tungsten was the only material which would not react detrimentally with p-type material. Contacts acceptable for use with n-type lead telluride were tungsten, molybdenum, and iron. The compatibility of these contacts was demonstrated by examination of capsule and die tests at temperatures up to 1382°F (750°C).

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Elimination of lead telluride reactions with the conductor rings allowed testing at higher temperatures than previously possible. A second-order degradation mode, at the elevated temperatures, was caused by contaminant diffusion from the p-type to the n-type washer in the module. As a result, deleterious changes were produced in the electrical properties of the n-type material. These changes caused a conversion of the n-type to p-type material in the region, at room temperature, near the hot conductor and particularly near the mica butt joint. Capsule tests designed to produce completely converted material showed that thermal conversion back to n-type material occurred at higher temperatures. The net result, however, would be a decrease in voltage and an increase in resistance during operation. This diffusion phenomenon was found to some degree in all modules examined to date. In earlier modules containing iron the effect was heavily masked by the reaction of the p-type lead telluride with the iron and the lower test temperature.

All evidence compiled indicated that tellurium diffusion from the p-type lead telluride into n-type lead telluride was probably responsible for degradation. A retardation of this diffusion was accomplished by a design change of the inner conductor rings which eliminated the butt joint and, thus, a probable diffusion path between washers. Diffusion of the contaminant could still occur through the mica washer because of mica deformation during module processing. Capsule experiments with a thin tungsten foil between thin mica insulators successfully halted contamination of n-type lead telluride at 1202°F (650°C) for the test time of 1000 hours. Work was begun to coat thin films onto mica which would act as diffusion barriers to contaminants.

In addition to the work on the isolation and elimination of module degradation, significant advances were made in the development of a system utilizing a heat pipe for transmitting thermal energy from an external heat source to a tubular module. During Phase II-C a conversion system consisting of a simulated heat source coupled to a tubular module (TEM-10 S/N-3) with a Westinghouse heat pipe and a planar radiator was designed, fabricated, and placed on test. The system exhibited a BOL overall efficiency level of 5.4 percent operating at a module hot side temperature of 1000°F. Even higher efficiencies are predicted for

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

systems incorporating modules designed for higher temperature operation. End closure improvements were made and incorporated into subsequent TEM-10 series modules, resulting in improved thermal cyclic capabilities. To date, modules incorporating the improved end closure design have been thermal cycled twenty-one times with no measurable effect on module performance.

The objective to design a large bore module suitable for use in a centerline isotope fueled application was also met during Phase II-C. A 1.85-inch ID module, TEM-12A S/N-1, was successfully designed, fabricated, and processed during the past year. This particular module was a mechanical experiment which demonstrated that such a module could be properly compacted using existing technology. This experiment has shown the feasibility of extrapolating present-day design and processing techniques over wide ranges of dimensions.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

I. DESIGN AND ANALYSIS

A. INTRODUCTION

The principal objectives of the thermoelectric module design and analysis effort during Phase II-C were to isolate factors contributing to module degradation, to continue the development and confirmation of existing design tools and computer programs capable of optimizing the tubular module, to identify the materials properties and experimental information required to effectively implement these design tools, and to complete the design of a tubular module reflecting the attainment of these objectives. During the past year all of these objectives were met.

Significant advancements in tubular module technology were achieved during Phase II-C. The program was directed toward development of modules designed for use in three modes of operation, as discussed below. These modes are concerned with the method by which thermal energy is transferred from a heat source in the inner bore of the module to generate a thermal gradient, the driving force, across the thermoelectric washers. The system requirements associated with the various modes of operation require different module radial dimensions for each application. The three modes of operation are as follows:

1. Reactor System Operation

In this configuration heat is transferred from a reactor system to the tubular module, using flowing liquid NaK as a transfer medium. The tubular design lends itself to this application since the inner cladding of the module acts as the flow channel and hot heat transfer surface for the flowing NaK. Small bore modules (ID ranging from 0.5 to 0.75 inch) are desired for this application since large heat fluxes can be easily achieved and weight is minimized.

The majority of all technology improvements attained in the Compact Converter Program since its inception have been demonstrated through experiments on 0.5 inch ID TEM-9 series modules suitable for reactor system applications. During Phase II-C major emphasis was directed toward design improvements aimed at enhancing the high temperature performance stability (reducing degradation) of tubular modules.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

A new and effective inner conductor ring design evolved from efforts in this area. In addition, significant component dimensional variations were incorporated successfully within the TEM-9 envelope, resulting in modules with voltages three times the level of previous modules. As a result of these improvements, significant advances were made in a parallel program having as one of its objectives the design of a reactor tubular power module.

2. Heat Pipe Operation

In this mode of operation the tubular module is coupled to a heat source by means of a cylindrical heat pipe inserted into the bore of the module. The heat pipe has proved to be a very effective means of transporting heat with a minimum axial temperature gradient. Preliminary heat pipe/tubular module integration studies have indicated that the optimum module ID for such an application is about 1 inch. Accordingly, the TEM-10 module was designed for use in a heat pipe system.

During Phase II-C an integrated energy conversion system utilizing a simulated isotope heater source, a Westinghouse designed and fabricated heat pipe, a TEM-10 module, and a planar radiator was fabricated and placed on test. Additional heat pipe studies were conducted and design improvements to the TEM-10 end closure to enhance its cyclic capability were developed and successfully incorporated into TEM-10 series modules.

3. Centerline Fueled Isotope Operation

In this configuration a radioactive isotope is loaded directly into the bore of a tubular module. Heat generated by the fuel produces the necessary thermal gradient to operate the module. For this mode of operation, modules with a larger bore are required, allowing the use of an adequate amount of fuel to generate the desired amount of heat. This mode of operation is particularly suited to the tubular design because of the simplicity and compactness of the resulting system. In addition, the complete encapsulation of the heat source within the thermoelectric module greatly reduces system heat losses.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

During Phase II-C the basic design of a module suitable for use in a centerline-fueled configuration was developed. This module, designated as TEM-12, has a 1.85 inch inner diameter, a significant departure from the demonstrated technology of Phase II-B.

The first TEM-12 series module, TEM-12A S/N-1, was successfully designed, fabricated, processed, and destructively examined. The module was built for process evaluation, and the results of the destructive examination illustrate the successful application of current technology to modules having a wide range of radial dimensions.

Significant advancements also were made during Phase II-C in the development of analytical techniques used in the design and analysis of tubular modules. TEMØD, the tubular thermoelectric module performance code, was revised to allow direct calculation of module performance in the centerline isotope fueling configuration. A technique for calculating the deposition of gamma heat generated within the lead telluride washers during operation in the centerline fueled mode, using a gamma emitter heat source such as cobalt 60, was also developed and incorporated into TEMØD. A model was developed to calculate the temperature dependence of the degradation rates of modules. The model was then verified, using data from three barrier modules tested at average temperatures ranging from 1000°F to 1200°F. In addition, an analytical technique to remove the effects of small temperature variations in experimental data was developed. This adjustment technique was of significant value in statistically evaluating modules whose degradation rates are small with respect to performance changes caused by small variations in testing temperatures.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

B. MODULE DEVELOPMENT FOR REACTOR SYSTEMS: TEM-9 SERIES MODULES

Since the inception of the Compact Converter Program, the technology experimental development program has concentrated primarily on the development of a small bore (0.5-inch ID, 7.2-inch circuit length) tubular module. All basic design improvements were initiated through experiments on modules of this size. The TEM-9 series of modules, with the above dimensions, served as the vehicle through which the various technology advancements were demonstrated. In Phase II-C the basic technology associated with the small bore TEM-9 series modules was extended to tubular modules with considerably larger radial and axial dimensions. In addition, the ability to successfully vary internal dimensions within the TEM-9 module envelope, in order to vary such operating parameters as voltage and resistance over wide ranges, was demonstrated.

Development of the TEM-9 series modules, basically designed for operation in a reactor system utilizing liquid metal as a heat transfer medium from the reactor, was continued. During Phase II-C the basic objective of the tubular module technology program was the development of techniques designed to produce stable high temperature operation.

Various barrier configurations were developed and tested during the past year. Results of the tests incorporating these barriers have been very encouraging. As a result of the improvements the baseline temperature for tubular module operation was increased from $\bar{T}_H = 1000^\circ\text{F}$ to 1100°F . Results of materials study module experiments indicate the potential of degradation-free operation at peak temperatures in excess of 1250°F .

High Voltage Module Experiments (TEM-9AE Series Modules)

The successful fabrication of modules employing ultra-thin (0.030 inch) thermoelectric washers in conjunction with 0.0015-inch mica insulators is a prerequisite for all lower power (less than 40 watts) applications. Because of the lower power requirements, short-length modules are necessary for these applications. Since the module output voltage is proportional to the number of thermoelectric couples (p- and n-leg pairs), it is necessary to employ thin thermoelectric and mica washers in order to achieve a usable voltage level.

~~CONFIDENTIAL~~

During Phase II-C of the Compact Converter Program, heatup cycles were completed for a series of modules (TEM-9AE series) of standard TEM-9 length. This series of experiments was conducted to demonstrate the ability to fabricate parts, to build, and to successfully predict the performance of modules with varying mica and thermoelectric washer thickness combinations. Three modules, TEM-9AE S/N-1, S/N-2, and S/N-3, were fabricated with three different combinations of thin thermoelectric (TEGS-2N and TEGS-3P material) washer and mica insulator thicknesses. Table 1-1 lists the axial dimensions of a typical module fabricated under the Compact Converter Program, TEM-9Q S/N-1, employing the same type of thermoelectric material but with lead telluride washers of standard thickness.

Each of the modules listed in Table 1-1 was subjected to a standard heatup cycle using static test stands in which the modules were heated from ambient (room temperature) conditions to operating conditions. Operating conditions for each of these modules were set at $\bar{T}_H = 1000^\circ\text{F}$ and $\bar{T}_C = 392^\circ\text{F}$.

The data generated during heatup tests afford a vehicle by which the effects of module-to-module variations can be evaluated. In this analysis the experimental data from each of the modules are compared to calculated curves, using the module dimensions as input. Because effective Seebeck coefficient, internal resistance, and circuit thermal impedance are strong functions only of average module temperature, each of the above mentioned parameters is presented as a function of average module temperature.

TABLE 1-1

AXIAL DIMENSIONS OF TEM-9AE AND -9Q SERIES MODULES

<u>Module</u>	<u>No. of Couples</u>	<u>p-Leg Thickness (in.)</u>	<u>n-Leg Thickness (in.)</u>	<u>Mica Thickness (in.)</u>
TEM-9AE S/N-1	109	0.032	0.030	0.0015
TEM-9AE S/N-2	98	0.032	0.030	0.005
TEM-9AE S/N-3	63	0.053	0.050	0.005
TEM-9Q S/N-1	38	0.090	0.088	0.005

~~CONFIDENTIAL~~

Figure 1-1 presents effective Seebeck coefficient data from each of the modules along with the calculated curves corresponding to each design. It must be noted here that TEM-9Q S/N-1 was tested under open circuit conditions, whereas the three TEM-9AE modules were tested under load. The calculations were made using the appropriate operating conditions for each module. Each module exhibited Seebeck data correlating extremely well with the calculated values. Minor deviations in the low temperature ranges are not uncommon and are of little significance.

Internal resistance heatup data are compared with calculated curves for each module design in Figure 1-2. Once again, the data from all modules correlate extremely well with the calculated curves, particularly in the higher temperature ranges of primary interest.

In Figure 1-3 comparisons of experimental and calculated circuit thermal impedance data for each design are presented. Because the circuit length of each module is approximately the same, the TEM-9AE thermal impedance data and calculations do not vary widely from module-to-module. However, TEM-9Q S/N-1 data are significantly different from the data for TEM-9AE series modules. This is because the 9Q module was heated under open circuit conditions, whereas the other modules were tested under load. Additional power is necessary to maintain a module under load conditions because the presence of an electrical current increases the heat transported across the lead telluride washers. This phenomenon is caused primarily as a result of the Peltier heat pumping at the hot junction.

One possible mode of failure for modules fabricated using thin thermoelectric washers and thin mica washers is through the development of inter-couple shorting. The occurrence of this phenomenon would manifest itself as a simultaneous reduction in open circuit voltage (hence, effective Seebeck coefficient) and internal resistance from the predicted levels. However, examination of Figures 1-1 and 1-2 indicates no such reduction.

Analysis of experimental data from the three TEM-9AE modules indicates that modules with 0.030 inch lead telluride washers and 0.0015 inch mica insulators can be successfully fabricated and operated at performance levels very close to predicted levels.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Figure 1-1. A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data from Thin Washer Module Experiments

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-2. A Comparison of Calculated and Experimental Internal Resistance Data from Thin Washer Module Experiments

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-3. A Comparison of Calculated and Experimental Thermal Impedance Data from Thin Washer Module Experiments

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Solid Tungsten Conductor Ring Modules

Eight TEM-9 series modules fabricated with TEGS-2P and GE-NL lead telluride in conjunction with solid tungsten inner conductor rings were built and placed on test during Phase II-C. These modules, TEM-9U S/N-7 through S/N-12, TEM-9U S/N-15, and TEM-9U S/N-16, were built with dimensions quite similar to those of previous TEM-9I series modules except for the use of tungsten in place of iron for the inner conductor rings. TEM-9U S/N-7 through S/N-12 were fabricated with 0.001 inch tungsten foil diffusion barriers between the lead telluride washers and iron outer conductor rings. The latter two modules, S/N-15 and 16, incorporated molybdenum cold side conductor rings with no barriers.

The solid tungsten inner conductor rings were substituted for the tungsten foil/iron conductor ring assemblies incorporated in earlier TEM-9U series modules. This change was made to ensure isolation of iron from p-type lead telluride. A reaction between these materials was identified during Phase II-B as the primary cause of module performance degradation, and the foil/iron rings were used to expedite test results.

The Tubular Module Stress Code was updated by the addition of tungsten and molybdenum mechanical properties to the materials library section. An analysis was made to determine the effect of the change in inner conductor ring material (to tungsten) in the later TEM-9U modules. The contact pressure profiles with iron and tungsten rings are shown in Figure 1-4. The curves show that the pressure profile with tungsten rings is somewhat higher than that with iron rings.

It should be noted that the stress code assumes that material fracture does not occur. It computes stresses and strains during the entire processing and operating history of the module. The maximum plastic strain calculated in the tungsten ring is 2.64 percent at a stress level of 197,000 psi. These values are compressive and they occur during cold autoclaving. If the material cannot withstand this stress and strain at room temperature, fracture occurs. Ring fracture would, of course, invalidate the rest of the calculation. A destructive examination of TEM-9U S/N-7, which was tested for 3526 hours, indicated that ring fracture had not occurred, thereby validating the stress code assumption.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

612643-6B

Figure 1-4. TEM-9U Pressure Profiles at Operating Temperature

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TEM-9U S/N-7 through S/N-10 were tested at temperature conditions simulating those of a typical two-loop reactor system, $\bar{T}_H = 1125^\circ\text{F}$ (607°C) and $\bar{T}_C = 570^\circ\text{F}$ (299°C), under a parallel program. TEM-9U S/N-11 and S/N-12 were endurance tested at an average cold side temperature of 392°F (200°C) and average hot side temperatures of 1100°F (593°C) and 1200°F (649°C), respectively. TEM-9U S/N-15 and -16 were tested at $\bar{T}_H = 1000^\circ\text{F}$ and $\bar{T}_H = 1035^\circ\text{F}$ with $\bar{T}_C = 392^\circ\text{F}$ (200°C) (both modules). All of these modules exhibited degradation rates approximately a factor of ten lower than rates measured for modules fabricated with TEGS-2P material and no barrier configuration. However, the experimental data showed clearly that module degradation had not been completely eliminated as a result of the use of solid tungsten conductor rings. A major effort during Phase II-C was directed toward the isolation of the cause of the residual degradation and the identification of a design fix to eliminate the problem. This effort will be discussed later.

A series of tests was completed on a module incorporating solid tungsten inner conductor rings, TEM-9U S/N-9, to establish the thermal cyclic capabilities of the design. The thermal cycle tests were conducted in a static test stand at WANL. In each cycle the main heater power was reduced, cooling the module from standard hot side conditions, $\bar{T}_H = 1125^\circ\text{F}$ (607°C) down to $\bar{T}_H = 500^\circ\text{F}$ (260°C) at a rate of 20°F (11°C) per minute. After a 58-minute soak period the module was reheated to standard conditions, again with a ramp rate of 20°F per minute. During the tests the guard heater power and test stand cooling fan speed were held at constant levels. Including a 58-minute soak period at standard operating conditions, $\bar{T}_H = 1125^\circ\text{F}$ (607°C) and $\bar{T}_C = 570^\circ\text{F}$ (299°C), the duration of each complete thermal cycle was 3 hours.

Ten thermal cycles were conducted consecutively after the module had accrued 2368 hours at life test conditions. Eleven cycles were conducted consecutively after the module had accrued a total of 3383 hours on test. Table 1-2 lists a compilation of experimental parameters measured at BOL as well as before and after each set of thermal cycles.

These results show the module performance to be unaffected by the twenty-one thermal cycles. Within the accuracy to which clad temperatures can be controlled, there was no measurable change in module parameters during either set of thermal cycles.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TABLE 1-2
TEM-9U S/N-9 THERMAL CYCLE TEST RESULTS

<u>Time on Test (Hours)</u>	<u>Circuit Heat Input Rate (Watts)</u>	<u>V_{oc}, ML (Volts)</u>	<u>R_g (Ohms)</u>	<u>P_e (Watts)</u>	<u>η (Pct)</u>
BOL (Zero Hours)	1277	4.93	0.0948	64.0	5.01
2368 (Before Thermal Cycles)	1258	4.82	0.0998	58.7	4.67
2417 (After 10 Cycles)	1269	4.81	0.0988	58.6	4.62
3378 (Before Second Cycle Set)	1247	4.74	0.1049	53.6	4.30
3425 (After 21 Cycles)	1252	4.77	0.1055	53.9	4.30

~~CONFIDENTIAL~~

An examination of experimental TEM-9U S/N-9 performance parameters revealed that there was no discontinuity in the level of the efficiency data or in the rate of degradation as a result of the thermal cycling. The data exhibit the ability of the tubular module to withstand repeated thermal cycles with no observable effect on module performance.

Stepped Inner Conductor Ring Modules

During destructive examination of TEM-9U S/N-7, it was observed that the assembly clearance between the large mica and the inner conductor ring was not eliminated during cold compaction and gas pressure sintering. The resulting radial gap between these components provided a direct path for p-type lead telluride material to diffuse and poison the n-type material. Seebeck probe examination of the n-type washer indicated that the poison caused a portion of the n-type washer near the mica to be converted to p-type material. A more positive method of ensuring a barrier between the p-type and n-type lead telluride washers was therefore required.

Figure 1-5 is a photograph of a sectioned module incorporating a new inner conductor ring design which provides a positive mica barrier between the p- and n-type lead telluride washers. The inner conductor assembly is fabricated in two pieces. The large mica is sandwiched between the two inner conductor ring components at assembly and therefore eliminates the possibility of an imperfect seal between the mica and the inner conductor ring. The two-piece inner conductor ring design concept also provides flexibility in material selection which can be used to minimize chemical reactions and therefore module degradation at the lead telluride washer/conductor ring interface. Therefore, a different conductor ring material can be used adjacent to the n-type material than is used adjacent to the p-type material.

TEM-9U S/N-19, -21 and -22 were the first modules to use the new inner conductor ring design. TEM-9U S/N-22, which was fabricated first, used stepped iron inner conductor rings adjacent to the n-type washers and tungsten stepped rings adjacent to the p-type washers. Materials experiments have shown iron to be compatible with GE n-type lead telluride. TEM-9U S/N-19 and -21 were identical to S/N-22 except molybdenum was substituted for iron in the

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure 1-5. Sectioned View of TEM-9U S/N-21

CONFIDENTIAL

~~CONFIDENTIAL~~

inner conductor ring, eliminating all iron in the proximity of the hot junctions. Solid molybdenum outer conductors were used in all three modules.

TEM-9U S/N-21 was destructively examined after processing. Figure 1-5 shows an 8X magnification of a section of this module. The destructive examination indicated that a positive seal between the n- and p-type lead telluride materials was established at the inner conductor ring interface and that good radial alignment and radial contact were established between the two inner conductor ring components. TEM-9U S/N-20, which is identical to TEM-9U S/N-19 and -22, was fabricated for another program.

Heatup data from the first three modules placed on test and incorporating the split conductor ring concept have been analyzed. As noted above, TEM-9U S/N-19 and S/N-20 incorporate molybdenum/tungsten stepped inner conductors, and TEM-9U S/N-22 was fabricated with iron/tungsten stepped conductors. Heatup data from TEM-9U S/N-20 are presented in this report to provide a correlation with data from TEM-9U S/N-19.

Effective Seebeck coefficient data from the modules are compared with a calculated curve in Figure 1-6. Calculations were obtained using the thermoelectric module performance code, TEMØD. The data and calculations are presented as functions of average module temperature. Since the radial temperature drops across the iron and molybdenum conductor represent small fractions of the total module radial temperature gradient, the analytical module calculates essentially identical effective Seebeck results for both module designs.

Although the Seebeck data for the iron conductor ring module agree very closely with the calculated curve, data for both modules containing molybdenum conductor rings fall approximately 5 percent below the curve near the design operating conditions. The reason for this is not yet understood but actions to investigate this deviation from predicted performance are being considered.

Internal resistance data from the same modules are presented in Figure 1-7. At operating conditions, $\bar{T}_H = 1100^\circ\text{F}$ (593°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C), the calculated internal resistance for the two configurations varies by less than 1 milliohm (the resistance for the

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-6. A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data Measured During Heatup of Split Conductor Ring Modules

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

molybdenum conductor ring module is slightly lower). As a result, calculated results for both modules are shown as a single curve. Although there is very close correlation of experimental data between modules, in all cases the data fall between 5 and 10 percent below the calculated curve. This also will be investigated further.

Figure 1-8 presents a comparison of thermal impedance data from the modules with two-piece inner conductor rings. Data from all modules correlate well with the corresponding calculated parameters.

Power outputs recorded at the beginning-of-life test for TEM-9U S/N-19 and S/N-20 (modules incorporating molybdenum stepped inner conductor rings) were both within 1 percent of the calculated level for the respective design operating temperature levels. The fact that both modules exhibited internal resistance and effective Seebeck coefficient (hence, open circuit voltage) data below the predicted level while the measured power levels correlated closely with the predicted levels resulted from the relationship between these parameters. That is,

$$P_e = \frac{\alpha_{ML}^2}{(\Delta T)^2 R_g}.$$

TEM-9U S/N-22, on the other hand, exhibited a BOL power output level approximately 15 percent higher than calculated (133 watts versus 115 watts). The cause of this deviation is not yet understood but will be investigated.

Endurance test data from TEM-9U S/N-19 and S/N-22, presented in a subsequent section of this report, indicate that degradation rates are greatly reduced as a result of the incorporation of the stepped conductor ring design into the module.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-7. A Comparison of Calculated and Experimental Internal Resistance Data Measured During Heatup of Split Conductor Ring Modules

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-8. A Comparison of Calculated and Experimental Thermal Impedance Data Measured During Heatup of Split Conductor Ring Modules

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Mica Distortion and Weld Shrinkage Reduction

Destructive analysis of various modules processed prior to this contract year indicated mica distortion in the first ten couples on each end. The distortion was normally limited to the large mica insulators and showed an inboard bending of the mica due to movement of the PbTe washers relative to the conductor rings. Although the movement dampened out within three to five couples, such a phenomenon was not predictable and in some instance may have been sufficient to cause mica fracture resulting in inter-couple shorting. Tests of weld samples and axial measurements taken prior to and after processing of various modules indicated a length change of 0.060 inch and greater. It was concluded that the axial shrinkage and subsequent mica distortion could be reduced by decreasing the amount of welding at the outer clad to the retaining ring joint.

After examination of the TEM-10 S/N-1 weld section it was felt that the weld could be reduced on the modules and still maintain its structural integrity during processing and test. An etched section of the weld indicated that the weld penetration resulted in a load carrying shear area less than the full thickness of the outer clad. Consequently, TEM-10 S/N-8 and -9 were fabricated with a reduced weld radial thickness of 0.100 inch.

The inner and outer clads of the tubular thermoelectric module yield at test conditions because of the differential expansion of the circuit components and clads. Therefore, each of the welds for the modules of various sizes was scaled from the radial thickness of the clads. All modules fabricated after January 1969 had the new weld configuration.

Several axial measurements were taken across the retainer ring and end outer clad faces at various stages of assembly and processing for TEM-9U modules. A summary of the measurements taken are given in Table 1-3. Earlier TEM-9U modules are included to show the differences and effect of the decrease in weld size. Although there is a definite decrease in the shrinkage, a more positive indication was noted in a section taken of TEM-9U S/N-2 after processing. The mica shift was apparent only in the first couple and was obviously improved over the distortion condition previously observed.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Other methods of possibly reducing the effect of welding were investigated. One such method involved the use of electron beam welds with a revised welding sequence which could conceivably decrease the axial shrinkage by 50 percent. cursory examination of dimensional data taken of weld samples that were electron beam welded showed virtually no radial or axial shrinkage after a weld penetration of approximately 0.10 inch.

TABLE 1-3

MODULE AXIAL MEASUREMENT SUMMARY

<u>Module</u>	<u>9U S/N-7</u>	<u>9U S/N-8</u>	<u>9U S/N-9</u>	<u>9U S/N-20</u>	<u>9U S/N-21</u>	<u>9U S/N-22</u>
Average Distance Across Retainer Ring (in.) (Assy)	9.240	9.245	9.245	9.247	9.250	9.247
Average Distance Across Retainer Ring (in.) (After Processing)	9.155	9.172	9.173	9.189	9.189	9.188
Average Shrinkage (in.)	0.085	0.072	0.072	0.058	0.061	0.059

In addition to the module weld samples, an experiment was devised where a series of electron beam welds were produced to simulate the attachment of the outer clad to the retainer ring. The results of this experiment indicated that this welding technique is the most promising method for reducing axial shrinkage and mica distortion. Several samples were produced which demonstrated that axial shrinkage could be essentially eliminated. Further experiments were performed to evaluate weld penetration and its repeatability. Sections of each weld were examined in two places (noted as Sections A and B in Table 1-4). The depth of penetration measured for each weld is shown in Table 1-4.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TABLE 1-4
RESULTS OF WELD PENETRATION EXPERIMENTS

<u>Sample No.</u>	<u>Weld Penetration (inches)</u>	
	<u>Section A</u>	<u>Section B</u>
1	0.140	0.140
2	0.125	0.125
3	0.150	0.150
4	0.120	0.125
5	0.135	0.125

Weld No. 5 was purposely designed with the retaining ring offset axially from the outer clad by 0.020 inch. It can be seen that this had no appreciable effect on weld penetration. This last sample was produced to assure that if such an offset did materialize due to stackup of module axial tolerances, the weld could still be effectively accomplished. The inclusion of EB welding into the various assembly operations dictates a redesign of the end cap to allow a circumferential butt joint. Such a weld may cause some minor axial shrinkage in the module (approximately 0.004 inch).

A redesigned collector ring included on the negative end of TEM-10 S/N-8 which had no cutout sections proved that such a stiffened component could effectively reduce displacement noted on the mica insulator OD. Measurements taken using radiographs of the modules showed that the maximum displacement on the positive end averaged 0.0075 inch compared to 0.002 inch on the negative end immediately after completion of all welding on the modules. After completion of processing the maximum shifts on the positive end and negative end were 0.015 inch and 0.005 inch, respectively.

Transmittal of axial loads through the solid collector ring requires bending of the ring flange section. Prior designs with scallops permitted loads transmitted through the open areas to move the kidney-shaped Alsimag insulators directly into the lead telluride washers. In addition, the weakened structural configuration allowed deformation and rotation

~~CONFIDENTIAL~~

of the ring. Thus, solid collector rings were included in later designs. If further design studies indicate that the EB method can be successfully used, scalloped rings will again be considered to reduce the heat loss penalties realized with a solid ring.

Materials Compatibility Module Experiments

Three TEM-9 size modules were designed, fabricated, and placed on test during Phase II-C to determine long-term compatibility of various materials used in thermoelectric modules. Two modules, TEM-9A and TEM-9Q, incorporated solid tungsten inner and solid molybdenum outer conductor rings. The other module, TEM-9M, used molybdenum in inner and outer rings.

The first two modules, TEM-9A S/N-3 and TEM-9M S/N-2, were designed as non-power producing materials experiments. These modules were fabricated with all TEGS-2P and all GE-N material, respectively. The objective of these experiments was to demonstrate the compatibility of the two types of lead telluride with the proper conductor rings at temperatures up to 1250°F (peak). Internal resistance and thermal impedance data recorded during the first 3000 and 1600 hours of testing, respectively, for these two modules have shown that there has been no degradation. These experiments are discussed in detail in Section II of this report.

The third materials compatibility experiment was performed in a TEM-9Q series, (TEGS-3P/GE-N) material power module (S/N-7). This module differed from all previous TEM-9Q series modules only in the use of tungsten inner and molybdenum outer conductor rings in place of iron. The purpose of this experiment was to observe possible variations in beginning-of-life performance as a result of compaction differences, and to obtain long-term compatibility data for TEGS-3P material in contact with tungsten and molybdenum.

During Phase II-C TEM-9Q S/N-7 was placed on test along with two other TEM-9Q series modules fabricated during Phase II-B, but not previously tested. These three modules, TEM-9Q S/N-5, -6, and -7, were endurance tested at $\bar{T}_H = 1125^\circ\text{F}$ (607°C) and $\bar{T}_C = 570^\circ\text{F}$ (299°C), nominal operation for a two-loop reactor system.

Analysis of heatup and beginning-of-life test data indicated agreement to within 2 percent between calculated and experimental internal resistance data for the two modules incorporating iron conductor rings. Effective Seebeck coefficient data (hence, open circuit

voltage data) of TEM-9Q S/N-5 were 1.0 percent below the calculated level, whereas TEM-9Q S/N-6 data were 3.5 percent above the calculated level. The tungsten and molybdenum solid conductor ring module, TEM-9Q S/N-7, exhibited internal resistance data 7 percent below the calculated level and effective Seebeck (hence, voltage) data 7 percent below the calculated level.

Although 7 percent deviation between calculated and measured parameters is normally considered significant, it must be remembered that this is a one-lot sample. It is not clear, at this time, whether the use of tungsten and molybdenum in the conductor rings produces effects which are not taken into account in the mathematical model. Life test data from these three modules indicate that all are operating in an essentially identical manner.

Design of a Shortened End Closure

Preliminary design of a new module end closure was completed during Phase II-C. Figure 1-9 shows a comparison of the new closure with end closures of the TEM-9S module, designed to reduce end heat loss, and with that of the TEM-9I baseline module.

The earlier module end closures incorporate a thin stretch-neck designed to yield during module operation as axial differential expansion occurs between inner and outer clads. The new closure is basically a flat washer welded at the outside to the outer clad and at the inside to the inner clad. The weld joints are arranged to permit slight rotation of the closure to accommodate differential expansion between the clads.

The maximum calculated plastic strain in the TEM-9S module stretch-neck, including the end effect, is about 6.3 percent for operation at $\bar{T}_H = 1000^\circ\text{F}$ (538°C), $\bar{T}_C = 392^\circ\text{F}$ (200°C). The stretch-neck should be able to withstand about fifty cycles at this strain level. This is considered satisfactory for a device of this type, but it should be noted that some specifications may require a greater cyclic life with a safety margin. The stretch-neck strain is a direct function of module length, so that increased module length means increased stretch-neck length for a given strain level.

~~CONFIDENTIAL~~

612643-10B

Figure 1-9. A Comparison of Three Module End Closure Designs

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

The maximum calculated plastic strain in the new design is 1.6 percent. In addition, the module overall length is approximately 5 inches less than that of previous modules with the same circuit length. The total path for radial conduction losses in the closure consists of 0.025 inch of Alsimag or lead telluride, 0.015 inch of mica, and 0.025 inch of Inconel 718. In addition, the module length can be increased by a factor of 4 before the strain level reaches that of the "conventional" closure with the stretch-neck.

A preliminary thermal analysis of the end closure heat losses associated with the redesigned end closure indicated heat losses of 65 watts per end for $\bar{T}_H = 1000^\circ\text{F}$ (538°C), $\bar{T}_C = 392^\circ\text{F}$ (200°C) module operation. This compares with calculated end closure heat loss rates of 104 watts and 230 watts for the TEM-9S and TEM-9I type end closures (shown in Figure 1-9), respectively, with the same module operating conditions.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

C. MODULE DEVELOPMENT FOR HEAT PIPE APPLICATION

A basic problem of any power conversion system is the coupling of the heat source to the conversion unit. Conventional heat transfer systems employ either conduction, radiation, or a convection loop to transport thermal energy. A recent addition to this list of heat transfer mechanisms is the "heat pipe," which uses vaporization and condensation of a working fluid for heat delivery and a capillary filled wick structure for working fluid circulation. In 1964 G.M. Grover* of the Los Alamos Scientific Laboratory began developing this self-contained structure which exhibits an extraordinarily high value of thermal conductance. This property is achieved within the containing envelope of the heat pipe by the nearly isothermal processes of evaporation and condensation of a liquid and vapor. The fact that a heat pipe can transfer large quantities of heat while operating with nearly isothermal conditions makes it well suited for use with tubular thermoelectric power conversion devices.

During Phase II-B, a preliminary study of a heat pipe-tubular module integration was completed. Based on the results of this study, a 1.1 inch ID module (TEM-10) designed for operation with a heat pipe was developed. A primary objective of the Compact Converter Program during Phase II-C was to demonstrate that heat pipes can be effectively coupled to a heat source using a heat pipe. During the past year a system comprised of a heater block, Westinghouse fabricated heat-pipe, a TEM-10 module (S/N-3), and planar radiator assembly was fabricated and placed on test. A photograph of the unit is presented in Figure 1-10. An overall system efficiency (including all heat losses) of 5.4 percent was recorded for $\bar{T}_H = 1000^\circ\text{F}$ (538°C), $\bar{T}_C = 392^\circ\text{F}$ (200°C) operation. Except for two temporary shutdowns caused by laboratory power failures, the TEM-10 S/N-3 heat pipe assembly has been operated continuously for over 7000 hours.

Heat Pipe Studies

The simplest geometric configuration for a heat pipe and the one most suitable for

* Grover, G.M., T.P. Cotter, and G.F. Erickson, "Structures of Very High Thermal Conductance," Journal of Applied Physics, Vol. 35, No. 6, 1990-1991, June 1964.

~~CONFIDENTIAL~~

CONFIDENTIAL

Astronuclear
Laboratory

Figure 1-10. Heat Pipe - TEM-10 Test Unit

CONFIDENTIAL

~~CONFIDENTIAL~~

applications with tubular modules is that of an enclosed hollow circular cylinder. The capillary structure (wick) is located adjacent to the inner wall of the cylinder and is saturated with the working fluid. The wick can be formed from layers of screen mesh or from any porous material capable of supporting capillary action. The heat pipe evaporator section is defined as the length of the cylinder over which heat is added to the pipe, while the condensing section is defined as the length of the cylinder over which heat is removed.

Heat pipe efforts have been directed toward a detailed definition of the heat pipe performance limits for the optimum heat pipe wick design as discussed in previous reports.* The optimum heat pipe for use with the most promising liquid metal working fluids for the 1000 to 1400°F range appears to be one having an annular liquid return passage with a fine pore size cover. A description of the advantages afforded by the liquid annulus design is also presented. The in-house funded experimental portion of the heat pipe program generated additional test data confirming the previously studied sonic vapor velocity limit for the sodium heat pipe.

Figure 1-11 presents a schematic illustration of the annular liquid return passage wick structure for the heat pipe, and shows a fine mesh cover screen attached to a perforated retainer tube. The screen/retainer combination is then enclosed by the heat pipe wall and the gap between the screen mesh and the inner diameter of the heat pipe wall serves as the liquid return passage. The retainer serves a twofold purpose. First, the cover screen is attached to the perforated retainer to ensure a complete separation of the liquid passage from the vapor passage. Thus, the largest pore size between liquid and vapor space is the pore size of the cover screen. This is essential for a high level of heat pipe operation so that a large adverse pressure gradient, which may appear in the vapor, can be overcome by the differential pressure provided by the surface tension forces generated by the liquid adhering to the cover screen. The second function of the retainer is to support the cover screen and hold it circular to maintain the vapor passage. LASL has reported an analysis which shows that the concentricity is not necessary for this design. Concentricity can readily be accomplished by suitable construction

* NYOO-3584-10, Compact Converter Quarterly Report, April 1968
NYOO-3584-11, Compact Converter Final Phase II-B Report, July 1968

~~CONFIDENTIAL~~

Figure 1-11. Schematic of WANL Heat Pipe

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

of end caps and, if necessary for the materials and loads encountered, by inserting locating guides in the annulus as the structural analysis may require.

Several observations to be noted regarding this design and the advantages it offers are as follows:

- 1) Fabrication of the heat pipe is straightforward and provides a well-positioned wick structure. In brief, the fabrication procedure is to spot-weld the fine-pore-size cover screen securely to the OD of the retainer and to weld the seam of the cover screen so that no unacceptable large openings remain. The necessary aligning guides are then attached to the cover screen and the assembly is inserted into the containing heat pipe wall. The heat pipe ends are then welded to the wick-retainer structure and this assembly is welded to the heat pipe wall.
- 2) The heat pipe can withstand larger body forces (multi-g) without the liquid being torn from the wick structure. This results from the large surface tension force that holds the liquid in the wick when a fine-pore-size cover screen is used.
- 3) The presence of the retainer in the vapor space acts as a buffer zone which separates the relatively high speed vapor flow from the liquid return passage. This separation may avert a heat pipe limit due to liquid entrainment by the high speed vapor flow.
- 4) Using a liquid annulus permits a minimum radial thickness for the wick structure. This affords a minimum radial temperature drop (e.g., from the heat pipe outer surface to the evaporating liquid-vapor interface), both for heat input and heat removal, and thereby results in the minimum temperature drop between the evaporator surface and the condenser surface.

In summary, the annulus wick heat pipe represents an optimized wick design because the minimization of the frictional drag in the wick structure permits maximum axial heat transport capability and because the minimum radial thickness of the wick structure provides the most nearly isothermal axial temperature profile between evaporator and condenser.

The experimental study of sodium heat pipe performance has demonstrated that a sonic vapor velocity can occur in the region between evaporator and condenser sections and produce a limit to the axial heat transfer rate. This limit, which was experimentally examined

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

using a sodium heat pipe, was verified as presented in a previous report.* Additional test data for an identically constructed heat pipe (five turns of 60 mesh screen as the wick structure) are shown in Figure 1-12 along with the previously reported results. The axial heat transport rate as a function of the temperature at the adiabatic section (where the Mach number is unity) is compared with the analytical prediction. It can be seen in Figure 1-12 that each set of heat pipe data could be fitted with a curve having the same shape as that predicted by the sonic vapor velocity limit. The position of the test data for each heat pipe with respect to the predicted results is shifted slightly. Similarly, the test data for the two identical heat pipes are also shifted from each other. These small discrepancies represent the magnitude of the uncertainty which occurs in the prediction and test measurements to establish the sonic velocity limit.

Design of a Heat Pipe/Module/Radiator Assembly Unit

Part of the effort to develop technology for future module applications included investigating the integration of tubular module/heat pipe systems. Various studies were undertaken to prove the feasibility of coupling these components into a prototype packaged unit. The TEM-10 module with its larger inner clad inner diameter (1.09 inch) presented an attractive candidate for use in such systems. During the latter part of Phase II-B, heat pipe tests conducted under a Westinghouse-funded program successfully demonstrated the capability of a 1.1-inch diameter heat pipe to deliver the necessary heat to the TEM-10 module at an operating temperature of 1100°F (593°C).

Studies were performed to assist in the design of interfaces between adjacent components of the heat pipe/module/radiator assembly unit which would assure adequate thermal contact.

Interface schemes which facilitate dismantling such assemblies and permit their reuse without subsequent modifications were investigated. It was determined that a boron nitride

* WANL-PR(CC)-035, Monthly Compact Converter Report, May 1968

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-12. Sodium Heat Pipe Startup Test Data

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

sleeve should be used at the interface in order to ensure successful disassembly and reassembly of hardware after operation. The sleeve was positioned in the active section of the module between the module and heat pipe and was designed and fabricated to provide minimum assembly clearances and maintain intimate contact between adjacent surfaces at operating temperature.

The design utilized the thermal expansion differential between the Inconel 718 inner clad of the module and the stainless steel jacket of the heat pipe. Sizing of diameters was accomplished to provide good interface contact at operating temperature.

Initially, a similar arrangement was proposed for the evaporator end of the heatpipe at the heater block interface. However, testing indicated that a better interface could be achieved with a flame sprayed copper surface applied to the outer diameter of the heat pipe. The design philosophy here was to obtain good thermal contact by clamping a heater block directly to the heat pipe.

The energy conversion system designed, fabricated, and tested during Phase II-C of the Compact Converter Program was developed to demonstrate the feasibility of utilizing a heat pipe to transport heat from a simulated radioisotope heat source to a TEM-10 size module. A planar radiator was designed to fit the outside surface of the module to dissipate the waste heat. The radiator was sized to maintain a module cold side average temperature of $\bar{T}_C = 392^\circ\text{F}$ (200°C) in a laboratory environment. Hence, the radiator utilizes both radiation and natural convective heat transfer mechanisms. The module fabricated for use in the first conversion system fabricated for the Compact Converter Program was TEM-10 S/N-3. Figure 1-13 shows the heater, heat pipe, and module assembled. Figure 1-10, presented previously, shows the unit with the planar radiator installed.

Analysis of TEM-10 Module Heatup Data

During Phase II-C, three TEM-10 (1.1 inch ID) modules were placed on test under the Compact Converter Program. TEM-10 S/N-3 was tested as the primary component of an assembly unit comprised of a heater block, coupled to the module by a heat pipe and using a planar radiator for cooling. The other two modules were fabricated with end closure modifications designed to improve the thermal cycling capability of the TEM-10 module. These design changes are discussed below.

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure 1-13. Heater/Heat Pipe/Module Assembly

CONFIDENTIAL

~~CONFIDENTIAL~~

Figure 1-14 presents effective Seebeck Coefficient data recorded during heatup of these three modules along with a solid line representing the calculated value of this parameter as a function of average module temperature. TEM-10 S/N-3 data lie approximately 5 percent above the curve near operating conditions. Data scatter during the initial portion of the heatup are felt to be caused by transient conditions encountered during heat pipe startup.

TEM-10 S/N-8 and S/N-9 Seebeck data, although agreeing closely with each other, fall about 1.5 percent below the calculated curve throughout the temperatures encountered during module heatup. This deviation is felt to be a direct result of a low circuit-to-clad resistance measured in these modules. TEM-10 S/N-8 was fabricated as a mechanical experiment to evaluate the effectiveness of the end closure design improvements. TEGS-2N material, with excess lead, was used in the fabrication of n-type washers for this module. Use of this material has, in the past, resulted in circuit-to-clad shorting problems as a result of lead migration through the boron nitride insulating sleeves. TEM-10 S/N-9, containing GE-NL n-type material, also exhibited a low circuit-to-clad resistance. A destructive examination, to be performed after completion of thermal cycle tests, will be conducted to investigate this phenomenon.

Figure 1-15 presents internal resistance data from the same three modules presented as functions of average module temperature. TEM-10 S/N-3 data are approximately 3 percent above the calculated curve, TEM-10 S/N-8 data correlate very well with the curve, and TEM-10 S/N-9 data fall about 3 percent below the curve. Resistance data from the latter two modules are reduced as a result of the low circuit-to-clad resistance.

Despite the low circuit-to-clad resistance in TEM-10 S/N-8 and -9, all three modules exhibit performance which correlates reasonably well with predicted levels.

TEM-10 Thermal Cycle Tests

During Phase II-C, the first heat pipe-size module, TEM-10 S/N-1 (1.1 inch ID), was subjected to a series of thermal cycles. These tests were performed prior to removing the module from the static test stand in which the module had been endurance tested. The purpose of the thermal cycle tests was to identify potential mechanical failure modes associated with rapid thermal transient conditions imposed on the module. Similar tests conducted on TEM-9 size

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

612969-4B

Figure 1-14. A Comparison of Calculated and Experimental Effective Seebeck Coefficient Data Measured During Heatup of Two TEM-10 Series Modules

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-15. A Comparison of Calculated and Experiment Internal Resistance Data Measured During Heatup of TEM-10 Series Modules

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

(0.5 inch ID) modules produced results indicating that the smaller modules are very insensitive to thermal cycling.

Five complete thermal cycles were performed on TEM-10 S/N-1. In each cycle the hot clad temperature was taken from the initial operating conditions ($\bar{T}_H = 1000^\circ\text{F}$) to room temperature and then returned to $\bar{T}_H = 1000^\circ\text{F}$ (538°C). Each cycle required approximately 5 hours, including 1 hour per cycle allowed for stabilization at $\bar{T}_H = 1000^\circ\text{F}$.

In contrast to the TEM-9U S/N-9 results discussed previously, TEM-10 S/N-1 experienced reductions in power output and efficiency after each thermal cycle. An analysis of the data indicated the development of intercouple shorts during each thermal cycle. This conclusion arose from the observation that both the open circuit voltage and internal resistance data were reduced after successive thermal cycles. A reduction in interface pressures would be accompanied by a reduction in open circuit voltage along with an increase in internal resistance. Since the lead telluride in the module is fully compacted and the interface resistances are negligibly small with respect to the bulk resistances, the only phenomenon which could cause a reduction in internal resistance is the development of intercouple shorting.

In order to study the mode by which the intercouple shorts developed, TEM-10 S/N-1 was removed from test for destructive examination after the completion of five thermal cycles.

The destructive examination indicated severe distortion of both the mica and PbTe washers within the entire length of the active section. The small inboard movement of the OD of the large mica washer, which was observed in previous sections and X-rays taken of other modules, was also apparent in TEM-10 S/N-1. However, there was a large outboard displacement of the small mica and PbTe washers relative to the conductor rings which had not been previously noted. The shorting paths resulting from tearing of the mica insulating rings adversely affected the performance of the module after successive temperature cycles.

The entire length of the module was sectioned and photographed at 7X magnification. A montage of the pictures of each section was made to determine the pattern of circuit deformation along the length of the module. The observations indicated a definite pattern along the entire module. The greatest displacement was noted several couples away from each end, with a dampening toward the axial center of the module.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Starting at the negative end, no movement of the washers was noted; however, as each couple was examined moving toward the positive end, outboard displacement on the ID of the washer relative to the conductor rings was noted. This displacement increased for approximately six couples, but decreased after ten with no movement noted after the fifteenth or sixteenth couple from the negative end. The pattern repeated toward the positive side, with a maximum displacement occurring approximately eight couples from the end and reducing to little or no movement at the last couple.

Although many TEM-9 size modules were cycled in a manner similar to that for TEM-10 S/N-1, no measurable degradation of performance occurred. There are a number of design differences, however, between the larger TEM-10 module and TEM-9. These differences in TEM-10, which may have contributed to the reduction in performance, include 1) a proportionately weaker inner and outer clad, and 2) a proportionately less stiff collector ring and retainer ring. In addition, the TEM-10 end closure Alsimag spacers were fabricated as concentric rings rather than solid components. This spacer design could conceivably permit axial movement on the hot side of the lead telluride washers. The greater thermal coefficient of expansion of the thermoelectric material as compared to the metal components indicates that the differential axial growth would permit relative axial displacement between the circuit elements if the end closure is not stiff enough to provide a strong back. Subsequently, an additional 1.1-inch ID module, TEM-10 S/N-8, was fabricated with end closure design modifications and placed on test to assess the improvements in thermal cycling capability. The design change incorporated in TEM-10 S/N-8 involved deleting the scallops in the retainer rings. This relatively minor design change was made to determine the influence of the scalloped retainer on end stiffness. TEM-10 S/N-9 was redesigned to incorporate an additional Alsimag spacer, thereby increasing the length of insulating components to that of TEM-9U modules. The retainer ring outer flange thickness also was increased and the stretch-neck diameter reduced to provide a stiffness equal to that of the TEM-9U end closure.

Radiographs taken after welding, cold autoclaving, and hot autoclaving of TEM-10 S/N-8 indicated mica distortion of 0.015 inch at the positive end couples and a maximum distortion of 0.005 inch at the negative end. Although only the positive end collector ring

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

was scalloped, this was not necessarily the cause of the difference in distortion. The distortion may have resulted from the welding sequence, since the negative end was welded last. The radiographs taken after hot autoclaving also showed a diffusion of PbTe into the outer boron nitride sleeve, which is attributed to the use of TEGS-2N material. The room temperature circuit-to-clad resistance was measured at 0.1 ohm, which is typical of this mode of shorting-to-clad.

TEM-10 S/N-8 was heated to nominal operating conditions of $\bar{T}_H = 1000^\circ\text{F}$ (538°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C). The beginning-of-life power output was measured at 104.5 watts compared to a calculated level of 112.6 watts. Measured internal resistance was 2 percent higher than predicted, whereas the measured open circuit voltage was 2 percent low. The discrepancy between measured and calculated voltage and power is attributed primarily to losses through the circuit-to-clad resistance path. Because of the technique used to measure module circuit resistance, the existence of circuit-to-clad shorting paths does not affect the determination of this parameter.

TEM-10 S/N-8 was subjected to a series of ten thermal cycles, conducted identically to those of TEM-10 S/N-1. Power out reduced by 2 percent during the period of the cycling. Internal resistance remained constant and voltage dropped by 1 percent. In TEM-10 S/N-1 cycling tests, both internal resistance and voltage were reduced after each thermal cycle as a result of inter-couple shorting. Since no reduction in internal resistance was observed in TEM-10 S/N-8 thermal cycle tests, the slight reduction in power output was attributed primarily to an increase in the severity of the circuit-to-clad shorting problem, which had resulted from the use of TEGS-2N material in the thermoelectric circuit.

The TEM-10 S/N-8 thermal cycle data revealed a significant improvement in the thermal cyclic capabilities of the TEM-10 module as a result of the end closure modification. TEM-10 S/N-1 showed a significant reduction in power output during the first five thermal cycles, and TEM-10 S/N-8 remained essentially stable for ten cycles.

TEM-10 S/N-9, incorporating further increases in stiffness of the end components, was fabricated and tested in parallel with TEM-10 S/N-8 to provide additional information relating to the influence of end stiffness on circuit containment. This module was subjected

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

to a series of twenty-one thermal cycles in the same manner as described above for TEM-10 S/N-1. The post-cyclic data indicated that the performance remained stable, thereby providing additional confirmation that the cyclic failures of earlier modules could be attributed to unacceptable flexibility of the ends.

During the final months of Phase II-C two additional TEM-10 modules, S/N-4 and S/N-7, were fabricated and prepared for testing. These modules incorporated selected end design features from TEM-10 S/N-8 and S/N-9, and split conductor rings. Testing of these modules will be conducted early in the next contract period.

TEM-10 End Closure Heat Loss Analysis

An end closure heat flow analysis was completed for various TEM-10 end closure designs, using the digital heat transfer computer code TØSS. Cases investigated included both actual designs and models that show the thermal effects of individual design changes. Boundary conditions were chosen to simulate module operation in the heat pipe/module/radiator assembly unit for several end closure configurations. Hence, the results of this study are directly applicable only to modules utilizing this mode of operation.

Physical models were made for the TEM-10 S/N-3, S/N-8, and S/N-9 designs. The models consist of a network of nodes on which a heat balance is performed utilizing the basic heat transfer code.

The temperatures on the inner surface of the inner clads of the TEM-10 TØSS computer models were fixed at 1000°F (538°C) along the entire length. Very uniform inner clad temperatures have been measured on all modules operated using heat pipes. Along the active region of the outer clad where the planar radiator contacts the module, the temperature was fixed at 392°F (200°C). End closure surface conductances were calculated to account for Fiberfrax insulation packed to a diameter 1 inch greater than the module OD. The outer "surface" of the Fiberfrax was then assumed to be at 392°F, a conservative assumption.

The end closure heat flow rate for the TEM-10 S/N-3 end closure design was calculated to be 170.5 watts/end. For TEM-10 S/N-8 operating at matched load conditions, the end heat flow rate was calculated to be 185.5 watts for the end incorporating the scalloped

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

collector ring and 198.1 watts for the solid collector ring end. Removing the scallops in the retainer ring was found to cause a relatively insignificant increase in end losses. This is logical for modules operating in heat pipe systems where the end closures are maintained at elevated temperatures by the enclosing can.

The TEM-10 S/N-9 design, which increased the axial length of Alsimag and used a thicker retainer ring, has an additional heat flow rate of 19 watts per end.

End closure heat loss rates for the various TEM-10 designs investigated are summarized in Table 1-5. The internal heat flow rate distribution for the TEM-10 S/N-3 design is presented in Figure 1-16. Similarly, heat flow rates for the TEM-10 S/N-8 design, employing a solid retainer ring and solid collector ring (a TEM-10 S/N-4 design), are presented in Figure 1-17.

End closure heat loss rate is defined as the summation of heat flows represented by the four large arrows at the top of each drawing. As can be seen, at least 95 percent of the end heat in all cases investigated flows axially along the outer clad, the outer boron nitride, and through the collector ring. The smaller arrows indicate the breakdown of the internal radial heat flow. Examination of several TEM-10 S/N-8 heat flow diagrams reveals that removing the scallops in the collector ring results in a much larger increase in end heat flow than is caused by removing the scallops in the retainer ring.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TABLE 1-5
CALCULATED TEM-10 END HEAT LOSS RATES IN WATTS PER END

<u>Module</u>	<u>Scalloped Collector/ Scalloped Retainer</u>	<u>Scalloped Collector/ Solid Retainers</u>	<u>Solid Collector/ Solid Retainer</u>
TEM-10 S/N-3	170.5		
TEM-10 S/N-8		185.5	198.1
TEM-10 S/N-9		204.6	218.1

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-16. Calculated End Closure Heat Flow Rate Distribution
for the TEM-10 S/N-3 Module

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-17. Calculated End Closure Heat Flow Rate Distribution
for a TEM-10 S/N-8 Module Design

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

D. MODULE DEVELOPMENT FOR CENTERLINE FUELED ISOTOPE

One mode of operation particularly well-suited to the tubular design of thermoelectric modules under development in the Compact Converter Program is the centerline fueled isotope. In this mode of operation, a radioactive isotope is loaded into the bore of the module, providing a direct coupling of the heat source with the energy conversion device. This type of operation has the advantage of simplicity and system compactness and, hence, low weight and high reliability. In addition, the complete encapsulation of the heat source within the thermoelectric unit greatly reduces system heat losses.

One of the primary objectives during Phase II-C of the Compact Converter Program was to demonstrate the capability to successfully fabricate large bore modules suitable for centerline isotope fueling applications. In order to demonstrate the state-of-the-art of analysis, fabrication, and processing of large diameter modules, a 1.86 inch bore module, designated TEM-12A S/N-1, was fabricated and destructively examined during this phase of the program. Analysis of the results of the destructive examination indicated that proper compaction and alignment of parts was successfully achieved in the first module sized for internal fueling with an isotope capsule. This experiment confirms the program's ability to successfully extend the tubular module technology over a wide range of sizes.

Design and Performance Analysis of TEM-12

The optimum design of TEM-12 modules is predicated on the choice of fuel since this, in turn, determines the range of hot side clad temperatures which may be achieved. The design of TEM-12, therefore, was not optimized for a particular application, but was arbitrarily chosen to be representative of a centerline fueled configuration. The OD of the module is nominally 4 inches, making this module the largest (in terms of radial dimensions) thus far in this program. In most respects, the module is a simple extension of existing module technology.

The outer clad thickness of the module was initially selected to produce internal module pressures similar to those calculated for TEM-9F (approximately 1500 psi). The 0.150-inch clad thickness was determined by a direct scaleup of both the TEM-9F and TEM-10 modules and should prove adequate for anticipated module temperatures. A radial thickness of 0.185 inch

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

was selected for the Inconel 718 inner clad based on the previous studies conducted for thin clad modules, namely TEM-9Y. Calculations indicate that the contract pressure level would still be acceptable after 10,000 hours of operation. The compaction values for the lead telluride and boron nitride sleeves were selected on the basis of TEM-10 design and fabrication experience. The TEM-10 modules were designed assuming 8.5 percent compaction for the thermoelectric material and 7.4 percent for the boron nitride insulating sleeves. The after-processing dimensions of the TEM-10 and TEM-12A modules compared quite well with the predicted values estimated from compaction information and from predicted stress code numbers. The calculated post-processing TEM-12A outer diameter was 3.990 inches, whereas the measured dimension was 3.985 inches.

A stress analysis was completed to evaluate the compaction of the active section, using the dimensions for the circuit components. The resulting internal pressures after processing, for both room temperature and operating temperature, are indicated in Figure 1-18. The minimum pressure at the outer boron nitride sleeve and outer clad interface of approximately 1800 psi falls within those values calculated for TEM-9F and indicates that adequate contact pressure at all interfaces will exist to permit satisfactory module performance.

The decrease in interface pressure from room temperature to operating conditions indicated in Figure 1-18 is a result of the yielding of the outer clad and internal components to relieve the interface pressures which increase initially on heatup.

The circuit of the TEM-12 module incorporates the stepped conductor ring concept, as discussed in a previous section. The stepped inner conductor ring assures positive containment of the small mica washer and eliminates the direct path of interaction between the p- and n-type washers at the hot side conductors.

The end closure design incorporates the shortened stretch-neck of the TEM-9S low heat loss configuration and the same axial length of Alsimag insulation sandwiched between the collector ring and retainer ring as in the TEM-9U modules. A conservative approach was taken in the design of the retainer ring and collector ring to ensure that they would provide a "strong back" for the circuit components to preclude axial movement of the lead telluride. The retainer ring outer flange was thickened axially to make it as stiff as that of the TEM-9U modules. As

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-18. TEM-12 Internal Pressure Profiles

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

in the latest TEM-10 designs, the scalloped sections were deleted from both the collector ring and retainer ring.

The retainer ring was designed for 6 percent elongation in the stretch-neck at operating temperatures and to withstand fifty temperature cycles without failure of the retainer ring in this reduced section. A modification was also added to improve the structural integrity of the stretch-neck member at the retainer ring inner flange joint. A thickened section was incorporated and tapered to the stretch-neck section for a length of 0.2 inch where the effect of shearing action is considerably dampened. The configuration chosen permits 0.080-inch radial movement of the stretch-neck section and ensures that there is no shear failure at the discontinuity joint between the retainer ring inner flange and the stretch-neck.

A temperature parametric analysis was performed using the module characteristics of TEM-12B as shown in Table 1-6. The circuit efficiency and the power output of the module were determined for a range of hot and cold clad temperatures. The hot clad temperatures were varied from 800°F (404°C) to 1300°F (704°C), and the cold clad temperatures varied from 200°F (93°C) to 600°F (316°C).

The computed circuit efficiencies for the TEM-12 design are shown in Figure 1-19. The efficiency peaked in the vicinity of 1200°F (649°C), hot clad average temperature. The efficiency curve for a hot clad temperature of 1300°F (704°C) was between the 1100°F and 1200°F temperature curves and was omitted from the figure to preserve clarity. The reduction of efficiency with temperature is a consequence of the decrease of material figure-of-merit with temperature in this region. Module power output is shown in Figure 1-20 for the temperature ranges considered.

An important parameter for isotope-fueled modules is the power density of fuel required to attain a particular hot side clad temperature. This parameter for the module under discussion is shown in Figure 1-21. The power density requirements for the chosen design are well within the capability of most candidate radioisotope materials. For instance, Pu²³⁸ has the lowest power density (3-4 watts/cc) of the candidate materials.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TABLE 1-6
TEM-12 LARGE BORE MODULE CHARACTERISTICS

Design Features

Inner Diameter = 1.862 inch
Outer Diameter = 3.988 inches
Active Circuit Length = 7.26 inches (nominal)
TEM-9S Type End Closures

Radial Dimensions

<u>Component</u>	<u>Inner Radius (inches)</u>	<u>Radial Thickness (inches)</u>
Inner Clad (Inconel 718)	0.931	0.185
Inner Boron Nitride Sleeve	1.116	0.040
Tungsten Conductor Ring	1.156	0.025
Lead Telluride Washers	1.181	0.602
Molybdenum Conductor Ring	1.783	0.020
Outer Boron Nitride Sleeve	1.803	0.037
Outer Clad (316 Stainless Steel)	1.840	0.154

Axial Dimensions

<u>Component</u>	<u>Axial Length (inches)</u>	
	<u>TEM-12A</u>	<u>TEM-12B</u>
TEGS-2P p-type Washers	0.091	0.050
GE-NL n-type Washers	0.089	0.050
Mica Insulator	0.005	0.005

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-19. Calculated Circuit Efficiency for the TEM-12B Design

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-20. Calculated Power Output for the TEM-12B Design

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 1-21. Calculated Fuel Power Density Requirements to Produce Assumed Clad Temperatures in the TEM-12B Design

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Description of an Experimental Cobalt-60 Test Program

Operation of a tubular module in the centerline isotope fueled configuration using an isotope which is a gamma emitter presents a situation not previously evaluated. A portion of the electromagnetic energy emitted by the isotope is converted to thermal energy within the thermoelectric material, thus increasing the heat available to the converter and reducing the external shielding required. Any calculational model used to determine radial dimensions of an optimum centerline fueled tubular module must accurately handle heat deposition as a result of gamma heating within the lead telluride washers.

During Phase II-C of the Compact Converter Program, a test program was developed to generate data that could be correlated with parameters to verify the validity of the calculation model.

A module, identical to the previously designed, fabricated, and tested TEM-10 modules, was considered for use in a test program to study the effects of internal gamma heat generation. This module would be placed on test in a static test stand. Short-term static testing would be conducted to generate test data at various input power levels while holding the module outer clad at a preset temperature level. The data accrued with conventional heating techniques could then be compared to data generated after cobalt fuel was placed within the bore of the module.

For both static and centerline fueling tests, the module would be equipped with ten thermocouples on both the inner and outer clad in a manner identical to the present instrumentation technique used for static tests conducted at WANL. Data to be recorded include open circuit voltage, load voltage, load current, circuit-to-clad resistance, and heat input rate (for the static test only) as well as the clad temperature data.

An extensive analysis of the test data would be necessary in order to determine the effects of internal gamma heat generation on module performance. The output of a thermoelectric device is determined by the temperatures at which the hot and cold junctions are operated. To maintain the containment of the lead telluride in the tubular module, it is necessary to completely encapsulate the thermoelectric material. For this reason it is impossible to instrument a tubular module with thermocouples located at the hot and cold junctions

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

without affecting the performance of the module. It is necessary, then, to determine junction temperatures, using inner and outer clad temperature data along with thermoelectric data.

As a result of the internal gamma heat generation, a module internally fueled with an isotope such as cobalt-60 would have a unique radial temperature profile as compared to a conventionally tested module for a given set of hot and cold clad temperatures. Because of the differing temperature profiles, the module fueled with an isotope would perform differently than a conventionally tested module. It would be the purpose of this test to generate data using one module, operated first using conventional electrical heaters and later using centerline cobalt-60 fueling to determine the effects of internal gamma heat generation.

Experimental data from all modules tested under the Compact Converter Program have verified that there are three parameters, each a function only of the average temperature of the thermoelectric material in the module, which taken together completely specify module performance. These three parameters are the average Seebeck coefficient, internal resistance, and circuit thermal impedance.

Average Seebeck coefficient α is defined by the expression

$$\alpha = \frac{V_{oc}}{\Delta T_{TE}},$$

where V_{oc} is the module open circuit voltage and ΔT_{TE} is the radial temperature drop across the thermoelectric material. Internal resistance R_g is calculated using the expression

$$R_g = \frac{V_{oc} - V_L}{I_L},$$

where V_L and I_L are the load voltage and load current, respectively. Circuit thermal impedance TI is defined by the expression

$$TI = \frac{\Delta T_{MOD}}{Q_{TE}}.$$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Here, ΔT_{MOD} is the radial temperature drop across the module and Q_{TE} is the heat input to the thermoelectric material.

During module operation under static test conditions (heat supplied by electrical heaters placed within the module bore), a determination of the average temperature of the thermoelectric material is straightforward. Hot and cold junction temperatures are determined by a calculation of the temperature drop across the module cladding, boron nitride, and conductor rings. This calculation can be made very precisely using the experimentally determined heat input and output along with the thermal conductivities of the appropriate materials. The average thermoelectric material temperature, then, is the arithmetic mean of the hot and cold junction temperatures.

The relationship of average Seebeck coefficient, internal resistance, and thermal impedance with average thermoelectric material temperature, $\bar{T}_{TE}$, for this TEM-10 module would be established from the experimental data from the static test.

After the module had been fueled with cobalt-60 and allowed to reach an equilibrium condition, the open circuit voltage, internal resistance, and clad temperature data would be recorded. From the internal resistance data recorded under cobalt fueling conditions, the average temperature of the thermoelectric material can be established using the experimental data from the static test. The average Seebeck coefficient of the module under cobalt fueling conditions would then be determined from the static test.

From the experimental open circuit voltage and the average Seebeck data obtained as explained above, the temperature drop across the thermoelectric material can be determined using the expression

$$\Delta T_{TE} = \frac{V_{oc}}{\alpha}.$$

This relationship is obtained by solving the expression given previously defining average Seebeck coefficient for the temperature drop.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Having determined the average temperature and temperature drop across the thermoelectric material, it is possible to solve for the average hot and cold junction temperatures. These are the junction temperatures associated with operation using a gamma emitter as a heat source. TEMØD, the mathematical model used to calculate performance parameters for a tubular module, has been revised to include the effects of gamma heat generated within the lead telluride washers. The lead telluride gamma heating is handled in a manner similar to the Joule heat generated within the thermoelectric washers. That is, half of the heat is assumed to return to the hot junction and half is lost to the cold junction. In the case of Joule heating, if it is assumed that the effects of Joule heating can be handled independently of the Thompson heating, the relationship between Joule heat returned to the hot and cold junctions can be obtained analytically. For this reason, the gamma heating is handled in an identical manner.

Using the average hot and cold junction temperatures determined from experimental data as explained above, along with the temperature, voltage, and resistance data, the validity of the model can be checked. The relatively low cost of this experiment should warrant such a test prior to performing a parametric study to determine the dimensions of an optimum centerline-fueled tubular module design using the present model for handling gamma heat deposition.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

E. ENGINEERING ANALYSIS TECHNIQUE DEVELOPMENT

Improvements in the Module Performance Analysis Code

TEMØD*, the digital computer code used to perform parametric studies of tubular modular performance, was developed and refined during Phase II-B of the Compact Converter Program. The code has undergone constant expansion during Phase II-C to facilitate the requirements of the numerous parametric studies conducted as a part of the program.

The code was initially written to perform tubular module performance calculations, using hot and cold clad temperatures as boundary conditions. During Phase II-C, however, a significant modification to the code was completed to permit performance calculations for specifying heat input rate and cold side temperature. From these boundary conditions, the code determines the module hot side temperature.

This modification is extremely useful in performing parametric studies of centerline isotope fueled modules. In this mode of operation, the total heat generation rate is determined by the fuel activity level or power density and module inner diameter. With the modification described above, TEMØD calculates the equilibrium hot clad temperature as well as all performance parameters corresponding to the steady-state operating conditions.

In addition, a modification was made to the TEMØD code to handle gamma heating effects within the lead telluride washers. The lead telluride gamma heating is handled in a manner similar to that used for the Joule heat generated within the thermoelectric washers. That is, half of the heat is assumed to return to the hot junction and half is lost to the cold junction. In the case of Joule heating, if it is assumed that the effects of Joule heating can be handled independently of the Thompson heating, the relationship between Joule heat returned to the hot and cold junctions can be obtained analytically. For this reason, the gamma heating is handled in an identical manner. An outline of a test which could be performed to verify the validity of the assumptions made in handling the gamma heat deposition within the lead telluride washers was discussed previously.

* Rose, C. M., "A Numerical Model for Tubular Thermoelectric Generator Performance Analysis," WANL-TME-1906, April 1969

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

An option was added to the code that provides the capability for load curve calculations either at constant clad temperature or at constant heat input rate. Load curve calculations performed under the latter operating conditions are required to determine the operating point (i.e., load resistance) to be used for operation in the centerline isotope fueling configuration. With a module operating at specified clad temperatures, maximum power output to the load resistance is achieved when the load resistance equals the module internal resistance (i.e., matched load). Maximum efficiency is achieved at some load resistance greater than module resistance (about 20 percent greater). Modules are generally designed to deliver maximum power, so that for operation at prespecified clad temperature conditions matched load operation is assumed.

However, for operation with total available heat specified, as is the case in the centerline isotope fueling mode, maximum power output and maximum efficiency are achieved at the same load condition (normally at a load resistance level approximately 20 percent higher than the general resistance). Since the optimum load resistance is not known prior to determining a module design, this parameter R must be determined using a load curve calculation after choosing the module design.

Mathematical Temperature Adjustments to Data

As a result of numerous design improvements, module degradation rates have been reduced by several orders of magnitude since the inception of the program. Because of the low degradation rates, long periods of time are required to evaluate further design improvements. In addition, the presence of unavoidable experimental "noise" caused by random minor fluctuations in operating temperature has become extremely important in evaluating module performance.

In order to eliminate the effects of these temperature variations, a technique was developed to adjust experimental data. For each data point the experimentally measured parameters are mathematically adjusted to reflect any deviations from the design operating temperature conditions.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

The three basic parameters that completely specify module performance are effective Seebeck coefficient, internal resistance, and circuit thermal impedance. These three parameters are functions of operating temperatures, and all other performance parameters can be calculated from combinations of these parameters and design operating temperatures.

Since the three basic parameters are functions of operating clad temperatures, the following expressions apply to total derivatives of the parameters:

$$d\bar{\alpha} = \frac{\partial \bar{\alpha}}{\partial \bar{T}_H} d\bar{T}_H + \frac{\partial \bar{\alpha}}{\partial \bar{T}_C} d\bar{T}_C$$

$$dR_g = \frac{\partial R_g}{\partial \bar{T}_H} d\bar{T}_H + \frac{\partial R_g}{\partial \bar{T}_C} d\bar{T}_C$$

$$dTI = \frac{\partial TI}{\partial \bar{T}_H} d\bar{T}_H + \frac{\partial TI}{\partial \bar{T}_C} d\bar{T}_C$$

These derivatives can be approximated by the appropriate finite differences for small variations in temperatures. The above expressions written in terms of finite differences, then, become:

$$\Delta \bar{\alpha} = \frac{\partial \bar{\alpha}}{\partial \bar{T}_H} \Delta \bar{T}_H + \frac{\partial \bar{\alpha}}{\partial \bar{T}_C} \Delta \bar{T}_C$$

$$\Delta R_g = \frac{\partial R_g}{\partial \bar{T}_H} \Delta \bar{T}_H + \frac{\partial R_g}{\partial \bar{T}_C} \Delta \bar{T}_C$$

$$\Delta TI = \frac{\partial TI}{\partial \bar{T}_H} \Delta \bar{T}_H + \frac{\partial TI}{\partial \bar{T}_C} \Delta \bar{T}_C$$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

The expressions can be written in terms of measured and design operating conditions as follows:

$$\bar{\alpha}' = \bar{\alpha} + \frac{\partial \bar{\alpha}}{\partial \bar{T}_H} (\bar{T}_{H,D} - \bar{T}_{H,M}) + \frac{\partial \bar{\alpha}}{\partial \bar{T}_C} (\bar{T}_{C,D} - \bar{T}_{C,M})$$

$$R_g' = R_g + \frac{\partial R_g}{\partial \bar{T}_H} (\bar{T}_{H,D} - \bar{T}_{H,M}) + \frac{\partial R_g}{\partial \bar{T}_C} (\bar{T}_{C,D} - \bar{T}_{C,M})$$

$$TI' = TI + \frac{\partial TI}{\partial \bar{T}_H} (\bar{T}_{H,D} - \bar{T}_{H,M}) + \frac{\partial TI}{\partial \bar{T}_C} (\bar{T}_{C,D} - \bar{T}_{C,M})$$

Here, the subscripts D and M refer to design and experimentally measured operating temperatures, respectively, the unprimed parameters are the experimentally measured parameters, and the primed parameters are the "temperature adjusted" parameters. The partial derivatives are evaluated about the design operating temperatures for each module design configuration using TEMØD, the analytic performance calculational model.

From the above expressions, the experimental data are adjusted to eliminate fluctuations caused by temperature variations. The temperature variations on both the hot and cold side are held to less than $\pm 6^\circ\text{F}$ and the adjusted parameters typically agree to within ± 5 percent of the measured parameters.

Additional temperature adjusted parameters are calculated from the basic parameters through the following relationships:

$$V_{oc}' = \alpha' (\bar{T}_{H,D} - \bar{T}_{C,D})$$

$$Q_T' = \frac{\bar{T}_{H,D} - \bar{T}_{C,D}}{TI'}$$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

$$P_e' = \frac{(V_{oc}')^2}{4R_g}$$

and

$$\eta' = \frac{P_e'}{Q_T'}$$

DAHA, the data reduction computer code, was modified to include the calculation of temperature adjusted parameters from the measured parameters. The DAHA output sheets were also modified so that the temperature adjusted as well as the as-recorded parameters are listed for each data point.

An additional least mean-square curve fitting computer code was developed to evaluate degradation rates for each parameter, using the temperature adjusted parameters. This code fits each parameter to a polynomial in terms of elapsed testing times. A linear relationship was found adequate to describe the time rate of change of all parameters for modules incorporating various barrier mechanisms. The degradation rate of each parameter, then, is simply the slope of the fitted curve. This code was useful in making statistical comparisons of degradation rates for various modules.

~~CONFIDENTIAL~~

F. SUMMARY

During Phase II-C of the Compact Converter Program, design and analysis effort resulted in significant advancements in the tubular module technology. These advancements are associated with modules designed for use in three basic modes of operation: reactor systems, heat pipe applications, and centerline fueled isotope applications.

As a result of isolating the major cause of performance degradation during Phase II-B, that of an interaction between p-type lead telluride and the iron inner conductor rings, a series of modules were designed utilizing various barrier configurations. The barriers proved very effective for module operation at $\bar{T}_H = 1000^\circ\text{F}$, but analysis of data from these barrier modules tested at elevated temperatures indicated a secondary degradation mode. During Phase II-C the contributing factors of the high temperature degradation were isolated. A design fix was identified to eliminate the possibility of assembly gaps between the large mica insulating washers and the inner conductor rings. A two-piece stepped inner conductor ring was designed to entrap the mica insulators, thus ensuring separation of adjacent lead telluride washers.

Success of the first modules incorporating the redesigned inner conductors resulted in increased temperature testing of nearly all modules fabricated in Phase II-C. It was found desirable to raise the baseline temperature for module operation from $\bar{T}_H = 1000^\circ\text{F}$ to 1100°F . Even at this elevated temperature, testing times in excess of 2000 hours were necessary before any reduction in power output was observed in one of the first modules fabricated with the two-piece inner conductor ring, TEM-9U S/N-19. Power modules fabricated prior to the beginning of Phase II-B exhibited substantial degradation at these temperature conditions, commencing immediately after the modules were brought to test temperature.

The cause of the residual performance degradation was also isolated. At higher operating temperatures, p-type lead telluride (or a constituent of this thermoelectric material) diffuses through the imperfections in the mica insulating washers and contaminates the n-type material. This conclusion is drawn based on two conclusions: (1) contaminated regions in the n-type lead telluride washer adjacent to the small mica insulators at the hot junction were observed during destructive analysis, and (2) materials experiment modules incorporating only

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

p-type or only n-type lead telluride were tested at peak temperatures above 1250°F with no noticeable change in internal resistance or heat input data. Various schemes for eliminating this diffusion of material through the mica insulators were devised.

In addition to the work on the isolation and elimination of module degradation, significant advancements were made in the development of a system utilizing a heat pipe for transmitting thermal energy from an external heat source to a tubular module. During Phase II-C a conversion system consisting of a simulated heat source coupled to a tubular module (TEM-10 S/N-3) with a Westinghouse heat pipe and a planar radiator was designed, fabricated, and placed on test under Compact Converter funding. The system exhibited a BOL overall efficiency level of 5.4 percent operating at a module average hot side temperature of 1000°F. Even higher efficiencies are predicted for systems incorporating modules designed for higher temperature operation.

An objective to design a large bore module suitable for use in a centerline isotope fueled application was also met during Phase II-C. A 1.85-inch ID module, TEM-12A S/N-1, was successfully designed, fabricated, processed, and destructively examined during the past year. TEM-12A S/N-1 was a mechanical experiment module which demonstrated that such a module could be properly fabricated using existing technology. This experiment proved the feasibility of extrapolating present-day design and processing techniques over wide ranges of dimensions.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

II. MATERIALS AND PROCESS DEVELOPMENT

The objectives of the Materials and Process Development effort in Phase II-C were to achieve an understanding of the materials and processes used during the fabrication of modules, to investigate new materials, and develop new processes as required for the solution of module fabrication problems to assure confidence in the behavior of modules fabricated for qualification in later phases of the program. The principal materials effort was directed toward the determination of the degradation model of the thermoelectric circuit materials.

During this phase of the program experiments were directed toward materials compatibility investigations. Particular emphasis was placed on mica behavior and n/p lead telluride reactions. Destructive examination of EXC capsules and thermoelectric modules was performed, using metallographic examination, electrical measurements, and the electron microprobe analyzer.

A. MATERIALS DEVELOPMENT

Electrical Contacts

At the close of Phase II-B of the present program, various contact materials were still under consideration for use as electrical contacts in modules as a replacement for iron. Among these were tantalum, molybdenum, niobium, zirconium, and tungsten. EXC capsule tests conducted during Phase II-B showed that tantalum and molybdenum were unacceptable as a contact material when used with TEGS-2P lead telluride. They were not ruled out, however, as an electrical contact with n-type lead telluride. If molybdenum could be used as an electrical contact with n-type lead telluride and could be kept away from direct contact with the p-leg of the couple, molybdenum would be an excellent electrical conductor because its volume resistivity is lower than that of iron. To test its compatibility with GE-N lead telluride, three EXC capsules were made and placed on test at 750°C (1382°F). After 2900 hours at test conditions, all three capsules exhibited a flat curve (slope = 0) on the resistance versus time plot, indicating that no detrimental reaction had occurred. Supporting these results is the performance of TEM-9M S/N-2. This module contains all GE-N lead telluride

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

with molybdenum inner conductor rings. After 3000 hours at $\bar{T}_H = 1202^\circ\text{F}$ (650°C) and $\bar{T}_C = 382^\circ\text{F}$ (200°C) the internal resistance of the module has not increased, thus indicating that molybdenum is an acceptable contact material when used with n-type lead telluride. By examination of the split-ring design for conductor rings discussed below, it becomes apparent how molybdenum may be used as an electrical contact for n-type lead telluride without coming into intimate contact with the p-type lead telluride.

Other materials selected for testing for use as a substitute electrical contact were niobium and zirconium. These materials were selected, as was tungsten, on the basis of die tests which demonstrated their compatibility with p-type lead telluride at high temperatures for short time intervals. Accordingly, capsules were fabricated using niobium and zirconium in contact with GE-N and TEGS-2P lead tellurides and TEGS-3P lead-tin telluride.

Two capsules containing niobium (Nb) contacts were removed from test during this reporting period. EXC 11S containing niobium contacts against single phase n-type lead telluride and EXC 12S with niobium against TEGS-3P lead-tin telluride were taken off test after 3200 hours at 650°C (1202°F). The capsule containing the n-type material exhibited a slight decrease in resistance versus time on test. This decrease was noted in other capsules containing n-type lead telluride in contact with various materials. The capsule with TEGS-3P material exhibited a flat curve (slope = 0) on the resistance versus time plot. Destructive examination of these capsules revealed that the niobium contacts had reacted with both the GE-N and TEGS-3P thermoelectric materials, forming a reaction layer at the thermoelectric material/contact interface. Also, the boron nitride insulating sleeve was heavily penetrated near the interface, giving the boron nitride a mottled appearance similar to that formerly noted in modules made with lead-rich TEGS-2N lead telluride.

It has been established by examination with the electron microprobe that niobium reacts with lead telluride to form a reaction product which contains Nb and Te. This reaction frees lead from the lead telluride matrix. This lead could penetrate into the boron nitride insulating sleeve.

~~CONFIDENTIAL~~

Seebeck probe traces across the entire pellet of both EXC 11S (Nb/GE-N) and EXC-12S (Nb/3P) revealed that the pellets exhibited slight electrical changes. The capsule containing GE-N lead telluride exhibited a decrease in Seebeck voltage near the contact interface to a distance of approximately 0.040 inch from the contact. The reaction layer formed, while it does not appear to affect the bulk properties of the thermoelectric material, could conceivably create a high thermal impedance in the area of the reaction layer, thus reducing the average temperature of the thermoelectric material. This phenomenon would in turn reduce the total Seebeck voltage.

The Seebeck probe trace on the capsule containing niobium against TEGS-3P lead-tin telluride revealed that the thermoelectric material was affected to a distance of approximately 0.150 inch from the contact interface. The probe trace showed a rise in the Seebeck coefficient rather than a decrease as noted in the previous capsule. The reaction layer between the niobium and the TEGS-3P material was not as thick as in the capsule containing GE-N lead telluride.

Electron microprobe examination was repeated on a sample examined previously on the microprobe at Sandia.* The sample is a Nb/TEGS-2P contact interface from an EXC capsule test that had accumulated 1500 hours at a test temperature of 1202°F (650°C). The previous examination disclosed a reaction layer of Nb_xTe_y which had consumed approximately one-half of the original niobium foil contact. In addition, large lead rich tellurium deficient areas were found in the lead telluride matrix in the region immediately adjacent to the contact. Examination of the same sample with the microprobe at WANL revealed another phenomenon. Figures 2-1A and 2-1B are the photographs of back-scattered electron traces, using different contrasting techniques, of the interface between TEGS-2P lead telluride, and the niobium contact. Figure 2-1A shows the PbTe matrix and the Nb_xTe_y reaction layer along with the remaining unreacted Nb foil contact. Figure 2-1B is the same area photographed under different contrast conditions. A high density layer is apparent at the Nb_xTe_y /PbTe interface

* NYOO-3584-12, 12 October 1968.

CONFIDENTIAL

Figure 2-1A

TEGS-2P PbTe Nb_xTe_y Nb

Figure 2-1B

Figure 2-1. Electron Beam Microprobe Photos Showing Back-Scattered
Electron Pattern of EXC Capsule With TEGS/2P Interface Tested
for 1500 Hours at 1202°F (650°C), (500X).

CONFIDENTIAL

~~CONFIDENTIAL~~

and the PbTe matrix. Additional microprobe traces for Pb and Te over the same area showed the layer to be rich in lead and deficient in tellurium. Figure 2-2 is a horizontal line scan for tellurium and lead, traced over the same area covered by the photographs in Figures 2-1A and -B. Note that in the region where the lead is highest, the tellurium concentration is at its lowest point. This same type of phenomenon was noted previously during the examination of a Mo hot side conductor ring, $\bar{T}_H = 1202^\circ\text{F}$ (650°C)/TEGS-2P, interface from TEM-9AC S/N-2. The lead-rich region was not as clearly defined as the Nb/TEGS-2P interface.

Another capsule (EXC 6S) containing TEGS-2P lead telluride with niobium contacts was removed from test after 2800 hours at 1382°F (750°C). The capsule exhibited an initial resistance rise for the first 400 hours, which then decreased until after 1800 hours at 1382°F (750°C) it reached a value of 2.2 milliohms. This value was about one-fourth the internal resistance of the capsule at $t = 0$. After 1800 hours and until the test was terminated at 2800 hours, the capsule maintained this low resistance. Destructive examination of the capsule revealed that a reaction layer of approximately 0.150 inch had formed between the niobium contact and the lead telluride. About half of the original 0.1 inch contact had been reacted during the process. The reaction layer was similar to those noted in other capsules containing niobium and TEGS-2P lead telluride that were tested at lower temperatures. There was a large void present in the remaining lead telluride pellet. A probable explanation of this void is as follows. It is known from previously examined capsules with niobium contacts that the layer formed between niobium and TEGS-2P lead telluride has a composition of Nb_xTe_y . This layer extracts tellurium from the TEGS-2P matrix and leaves behind areas rich in lead. The capsule under consideration here (EXC 6S) was tested for a longer time and at a higher temperature than any previous capsules with niobium contacts. It is conceivable that enough tellurium was removed from the lead telluride by the reaction layer formation to leave behind a large amount of pure lead. Since the density of lead is greater than the density of lead telluride, it was possible for a void to form in the TEGS-2P matrix.

The results obtained from this capsule conclusively demonstrated that the use of niobium as a contact material for p-type lead telluride (TEGS-2P) was not feasible and no further tests were conducted using this material.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-2. Electron Microprobe Horizontal Line Scan for Te and Pb Over Nb/TEGS-2P Interface of EXC Capsule, Tested for 1500 Hours at 1202°F (650°C). Trace Taken Over Same Area as Shown in Figure 2-1.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

EXC 10S was removed from test after 3200 hours at 1202°F (650°C). This capsule contained zirconium in contact with TEGS-2P lead telluride. As noted in capsules with niobium contacts, a reaction layer between zirconium and TEGS-2P had formed. The layer thickness was considerably less than noted in Nb/2P capsules tested for similar times and temperatures. Seebeck probe traces taken across the pellet from contact to contact showed the entire pellet had a Seebeck voltage higher than normal. Since the rise in Seebeck voltage is associated with a resistivity increase, zirconium was rejected as an alternate contact material for thermoelectric modules.

All work concerning electrical contact compatibility with p-type lead telluride showed that tungsten was the only material that could be used at temperatures near 1200°F (650°C). Accordingly, test capsules were fabricated and tested to evaluate both n- and p-type lead telluride compatibility with tungsten. The test temperature chosen was 1382°F (750°C) since the high temperature should accelerate any reactions that occur more slowly at lower temperatures. Two capsules containing p-type lead telluride/tungsten contacts and one capsule containing single-phase n-type lead telluride/tungsten contacts were on test for 2800 hours at 1382°F (750°C). The measured resistance as a function of time is shown in Figure 2-3. The capsules containing p-type lead telluride showed a small but finite rise in resistance with time. The resistance of the capsule containing the n-type material, on the other hand, was constant over the time tested. Because of inconsistency between module and capsule results and also because of the results obtained during module examination, the capsules were removed from test.

Capsules EXC 13S (n-type) and EXC 9S (p-type) were sectioned axially and polished for metallographic examination. The metallographic results for both samples were identical. No optically visible reaction products were found in either type of lead telluride, nor was any reaction zone observed at the contact/lead telluride interface. Seebeck probes were also made along the axis of the capsule from one contact to the other. The resulting Seebeck coefficient value versus axial distance is shown in Figure 2-4. Despite some experimental scatter in the data, it was quite evident that the tungsten had not adversely affected the electrical properties of either the n-type or p-type material. It appears that tungsten does not

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~ ~~CONFIDENTIAL~~

Figure 2-3. Resistance Versus Time at Test Conditions for EXC Capsules Containing Tungsten Contacts - 2800 Hours at 1382°F (750°C)

~~CONFIDENTIAL~~

Figure 2-4. Seebeck Coefficient Versus Distance Along Pellet Axis for EXC Capsules Containing Tungsten Contacts - 2800 Hours at 1382°F (750°C)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

affect the bulk properties of lead telluride even at 1382°F (750°C), approximately 270°F (150°C) higher than the average temperature at which marked changes occur in TEM-type modules currently under test.

Along with the capsule data outlined above are the results obtained from a materials module currently on test at $\bar{T}_H = 1202^\circ\text{F}$ (650°C), $\bar{T}_C = 392^\circ\text{F}$ (200°C). TEM-9A S/N-3 containing TEGS-2P lead telluride with tungsten inner conductor rings has accumulated more than 3300 hours at test conditions without any significant increase in internal resistance.

Tests to determine if any slight tungsten-lead telluride reaction occurred in p-type lead telluride were performed. Electrical measurement bars were prepared with 5 mole percent tungsten dispersed throughout the bar. The bars provide a means for accurate measurement of Seebeck and resistivity changes that could occur but could not be detected via capsule examination. The first group, which contains three tungsten dispersed bars and three control bars, was hydrogen heat treated and the electrical properties measured as a function of temperature. The bars were sealed in individual Vycor tubes which had been evacuated and back-filled with argon. The tubes were annealed at $1092^\circ\text{F} \pm 18^\circ\text{F}$ ($592^\circ\text{C} \pm 10^\circ\text{C}$). After 1850 hours at temperature, the tubes were removed from testing. The electrical properties of the bars were measured over the temperature range from ambient to 1112°F (600°C). The data were then treated statistically to determine the effect, if any, of the W dispersion. The statistical methods used are described in Appendix C.

The results of the statistical treatment are shown in Table 2-1. The significance of the information in Table 2-1 is evident from examination of Figures 2-5 and 2-6.

Figure 2-5 shows the electrical resistivity and Seebeck coefficient of the control test bars and the tungsten dispersed bars as a function of temperature. The Seebeck coefficient was not affected at all by the tungsten addition. The electrical resistivity, however, showed a slight increase due to the dispersed tungsten. The initial measurements and those obtained after annealing are shown for the control bars in Figure 2-6. The Seebeck coefficient and electrical resistivity were altered slightly as a result of the annealing treatment, but both were affected in the same way. There is no significant statistical difference between the electrical

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-5. Electrical Properties of Lead Telluride Bars Before Annealing.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-6. Electrical Properties of Lead Telluride Bars Before and After Annealing.

~~CONFIDENTIAL~~

TABLE 2-1

RESULTS OF STATISTICAL TREATMENT

Testing A Difference and Between B		Statistically Significant Difference	
		Seebeck Coefficient	Electrical Resistivity
Control Data Before Soak	5% W Dispersed Data Before Soak	No	Yes
Control Data After 1849 hours at 590°C	5% W Dispersed Data After 1849 hours at 590°C	No	No
Control Data Before Soak	Control Data After 1849 hours at 590°C	Yes	Yes
5% W Dispersed Data Before Soak	5% W Dispersed Data After 1849 hours at 590°C	Yes	Yes

properties of the control bars and the bars which contained tungsten. Regardless of the reason for the slight shift in electrical properties of the bars, the experiment demonstrated that tungsten per se is compatible with p-type material. However, testing in environments other than in the total void-free volume of compacted modules is always difficult because of possible atmospheric contamination and the high vapor pressure of lead telluride.

The results from the capsule, module, and tungsten dispersion tests outlined above indicated that the problem of module degradation during life testing was not due to a detrimental reaction with the inner conductor rings. Power modules fabricated with inner conductor rings of tungsten continued to degrade, although the degradation rate was considerably reduced below the values obtained when iron conductors were used. The reasons for this remaining degradation are described below.

~~CONFIDENTIAL~~

Module Examination

TEM-9U S/N-7, containing tungsten inner conductor rings, was removed from test after 3500 hours at $\bar{T}_H = 1125^\circ\text{F}$ (607°C), $\bar{T}_C = 575^\circ\text{F}$ (302°C). The module resistance increased during the test, but the open circuit voltage did not exhibit any increase. In contrast, modules containing iron inner conductor rings have shown considerably more of an increase in internal resistance and open circuit voltage. Two sections were removed from the center of the module where the hot side temperature was approximately 1193°F (645°C). Section 1 was polished to expose a p-type (TEGS-2P) washer. The washer and the tungsten/TEGS-2P interface was examined metallographically, with the Seebeck probe, and with the electron microprobe. Metallographic examination revealed no reaction either in the p-type lead telluride or at the interface region. Seebeck probe traces were taken on a radial line from the inner conductor ring to the outer conductor ring. The Seebeck coefficient at the hot junction showed a very slight rise, Figure 2-7. The curve shown is an average of six probes taken every 45 degrees. The increase in the value of the Seebeck coefficient is much less than would be necessary to produce the measured increase in the internal resistance of the module.

The W/lead telluride interface of the p-type washer was also examined using the electron microprobe. Figure 2-8 is a step-scan taken over the interface measuring the W, Te, and Pb X-ray intensity. The steps were taken in 2-micron intervals. The traces revealed no apparent diffusion of W, Te, or Pb across the contact interface. Section 1 was then polished to expose the n-type washer immediately adjacent to the previously examined p-type washer. Metallographic examination of the W/n-type interface revealed the same result as found at the W/2P interface in the preceding washer, no interdiffusion of the major constituents.

Seebeck probe traces, however, revealed a considerable Seebeck coefficient change in the n-type PbTe near the hot inner conductor ring. Figure 2-9 is a plot of the Seebeck coefficient versus distance from the inner conductor ring. Immediately following the Seebeck probe examination, and without repolishing, the sample was examined in the electron microprobe. A step-scan was performed across the W/n-type interface in 2-micron steps.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-7. Seebeck Coefficient Versus Distance from Inner Conductor Ring for Section 1, TEM-9U S/N-7 p-Type Washer. Average of Six Probe Traces.
 $T_H \approx 1193^\circ\text{F} (645^\circ\text{C})$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-8. Electron Microprobe Trace for Te, W, and Pb from p-Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Begun in Lead Telluride Matrix and Moved to p-Type/W Interface

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Figure 2-9. Seebeck Coefficient Versus Distance from Inner Conductor Ring for n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Taken in a Plane 79 Mils in an Axial Direction from Large Mica Washer

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-10 is a plot of the step-scans for W, Te, and Pb. This figure shows the same results as those obtained from the examination of the W/2P interface, i.e., no apparent interdiffusion of materials across the interface. The sample was then ground away in 0.015-inch steps and radial Seebeck probe traces were taken at 90 degrees intervals around the washer. Figure 2-11 is a schematic showing the axial position of the traces taken in the n-type washer. As the washer was ground away and the mica washer between the n- and p-type lead telluride washers was approached, the Seebeck probe traces exhibited a marked change. The n-type lead telluride began to show p-type electrical characteristics near the hot side conductor ring. Traces were taken at intervals down to a plane whose axial distance was approximately 0.014 inch from the large mica washer. The large mica washer is defined as the one that, acting as a barrier between the n- and p-type lead telluride, touches the OD of the inner conductor ring and separates the outer conductor rings. For simplicity, two of the four traces taken on this plane that was 0.014 inch from the large washer are shown in Figure 2-12.

Section 1 was then polished to expose the next p-type washer immediately adjacent to the n-type washer discussed above. This washer was examined in a similar manner to that used in the previous n-type washer, i.e., Seebeck probe traces were taken every 90 degrees and then ground away in 0.015-inch steps and the Seebeck examination repeated. The washer was examined at five axial positions ranging from 0.013 inch to 0.074 inch from the large mica washer. There was no apparent Seebeck rise near the hot inner conductor ring in any of the five axial positions.

Section 1 was then polished to expose a second n-type washer which was exactly one couple length distant from the first n-type washer examined. The initial Seebeck probe traces taken on this washer were approximately 0.005 inch from the small mica washer. The probe traces revealed that some of the n-type lead telluride near the hot inner conductor ring had been converted to p-type material. This conversion phenomenon was not present in the trace taken at the next axial position examined, 0.015 inch from the small mica washer. The washer was ground away in 0.015-inch steps and Seebeck probe traces were taken at each interval. The washer exhibited a rise in the Seebeck coefficient at the hot junction at each step but no conversion to p-type material was encountered until a plane 0.009 inch away from

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Figure 2-10. Electron Microprobe Trace for Te, W, and Pb from n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Begun in Lead Telluride Matrix and Moved to n-Type/W Interface

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

612833-18B

Figure 2-11. Schematic of Axial Position of Seebeck Probe Traces Taken on
n-Type Washers of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-12. Seebeck Coefficient Versus Distance from Inner Conductor Ring for n-Type Washer of TEM-9U S/N-7, $T_H \approx 1193^\circ\text{F}$ (645°C). Trace Taken in a Plane 14 Mils in an Axial Direction from Large Mica Washer

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

the large mica washer was reached. In this plane the n-type lead telluride was converted to p-type in a manner similar to that observed in the first n-type washer examined.

From the data obtained by the examination of the three washers (two n-type and one p-type), it was evident that (1) only the n-type washers seemed to be affected, and (2) the n-type washers were contaminated at both extremes of their axial dimension. Further, it appeared that the extent of the gross contamination (conversion to p-type) was greater at the axial end of the washer where the large mica washer separated the n- and p-type washers. In the first n-type washer examined, the gross contamination extended at least to an axial position 0.031 inch from the large mica washer. Conversion was not evident in traces taken 0.079 inch from the large mica washer (0.011 inch from the small mica washer). In the second n-type washer from Section 1, the gross contamination was not present at an axial distance of 0.070 inch from the large mica washer but was found again at a distance of 0.085 inch (0.005 inch from the small mica washer). Possible contaminants of the n-type material could have come from the p-type lead telluride, the mica washer separating the lead telluride washers, and/or the tungsten conductor ring.

Evidence that the contamination was not due to the mica washer was obtained by making Seebeck probe traces on TEM-9K S/N-1. This module was an all n-type module built to determine the effect of iron on n-type lead telluride. The module was tested for 2200 hours at $\bar{T}_H = 1000^\circ\text{F}$ (538°C), 2500 hours at $\bar{T}_H = 1100^\circ\text{F}$ (593°C), and 800 hours at $\bar{T}_H = 1202^\circ\text{F}$ (650°C). This module exhibited a zero slope on the resistance versus time curve over the life test. Seebeck probe traces taken in a radial line from the inner conductor ring to the outer conductor ring at various axial positions showed no significant contamination of the n-type lead telluride washers. Capsule tests described above showed that the n-type material is electrically and chemically inert to tungsten and, thus, conductor ring contamination was ruled out.

The present evidence indicates that the contamination of the n-type washers in TEM-9U S/N-7 was due to transport of material around and/or through the mica washers which separate the p- and n-type lead telluride. The extent of contamination is shown schematically in Figure 2-13, where two n-type washers are shown with the converted contaminated areas

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-13. Schematic Representation of Contamination of n-Type Washers of TEM-9U S/N-7

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

as well as those areas which have a Seebeck coefficient greater than normal n-type material. It is evident from this figure that the contamination, as evidenced by p-type conversion, was greater near the mica which makes the butt joint at the hot side conductor ring. It is possible that some contamination could occur in the region adjacent to the small mica washer by means of p-type material penetrating the mica. However, surface diffusion along the inner diameter and along the sides of the n-type washer could be a factor. Since the axial conversion contamination depth at the small mica washer is only about 15 to 20 mils, a comparable radial distance would be difficult to detect since the contact surfaces are cylindrical rather than plane. TEM-9U S/N-22 was designed to prevent interdiffusion via the butt joint region by extending the large mica washer between split conductor rings. The module is on test and the data described elsewhere give an indication as to the success of the proposed solution.

The diffusion of the p-type material that contaminates the n-type lead telluride is temperature dependent, as evidenced by data obtained by examining n-type washers from sections of the module that experienced lower temperatures. Three successive n-type washers from the negative end of the module were examined and found to be free of any contamination, i. e., the Seebeck trace was flat from the inner to the outer conductor ring. The hot side temperature of these washers was about 752°F (400°C). Seebeck probe traces on n-type washers from the positive end showed that contamination occurred in the first n-type washer and became greater in successive washers. The third n-type washer was the first washer to show p-type conversion. The temperature at this end of the module ranged from approximately 932°F (500°C) at the first n-type washer to 1022°F (550°C) at the third n-type washer where conversion was observed.

Sections from TEM-9U S/N-7 were examined in the electron microprobe to determine if any compositional differences could be detected between the contaminated and unaffected zones in the n-type washers. Electron beam traces and counting techniques were conducted on axial sections. No differences were observed between contaminated and unaffected portions of the n-type washer or between the n- and p-type washers.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

TEM-9T S/N-1 was also examined destructively to evaluate the degradation mode. This module, which contained TEGS-2N and TEGS-2P lead telluride, iron inner contacts, and 0.0015 inch mica, was tested at 1202°F (650°C) for 812 hours. Destructive examination disclosed that the p-type material exhibited the characteristic contamination due to the iron conductors. The n-type washer showed gross contamination (conversion to p-type) in the region adjacent to the large mica washer where it butts with the hot conductor, which was at a temperature of about 1292°F (700°C). However, unlike the results obtained on TEM-9U S/N-7, the effect damped out as the small mica washer was approached. In fact, the material was unaffected at a distance of approximately 0.018 inch from the small mica washer. Traces on single-phase n-type washers at comparable distances from the small mica washer showed definite contamination in TEM-9U S/N-7. Traces taken on the surface of the TEM-9I S/N-1 n-type washers, where the small diameter mica washers had been removed, showed no conversion to p-type material and minimal contamination.

The results on the TEGS-2N washers obtained from TEM-9T S/N-1 were completely different from those obtained from TEM-9U S/N-7. For some reason no conversion of the n-type washer was observed near the small mica washer in TEM-9T S/N-1, while definite conversion was noted in TEM-9U S/N-7. There is definite conversion in the n-type lead telluride at the hot side butt joint in both modules. This latter result precludes any differences due to the two types of n-type lead telluride used (TEGS-2N versus single-phase n-type lead telluride). The only other differences between the two modules are the conductor rings (iron versus tungsten), and the mica thickness (0.005 inch versus 0.0015 inch). That the iron is more significant than the mica thickness becomes more apparent in the discussion of TEM-9U S/N-3 that follows.

Seebeck probe traces were taken on a section from the center portion of TEM-9U S/N-3. This module had a 0.001-inch tungsten foil barrier between the iron inner conductor ring and the n- and p-type thermoelectric washers. The ends of the foil did not meet and, as a result, a 0.035-inch gap was left so that the lead telluride was in contact with iron at this gap. Data from the Seebeck traces showed two phenomena. TEM-9U S/N-3 was tested at similar times and temperatures as TEM-9T S/N-1. However, although there was some

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

contamination of the n-type washer, no conversion to p-type material was observed in the butt joint region near the hot side conductor. This was the axial position where the greatest contamination occurred in TEM-9U S/N-7 and TEM-9T S/N-1. Second, at the position where the tungsten foil did not cover the iron inner ring, the Seebeck probe trace revealed that the contamination of the n-type washers appeared to be less than in other portions of the washers. This latter result coupled with the fact that there is no contamination at the small mica end of the n-type washer in TEM-9T S/N-1 seems to indicate that the iron conductor plays some role in suppressing the contamination of the n-type washers in thermoelectric modules.

The conversion of n-type material had not been observed during examination of modules prior to those discussed above. The reason for this could be twofold, with both factors interrelated. The test temperature of previous modules was lower, 1000°F (538°C), and all contained iron conductor rings. Thus, interdiffusion would be slower and, since iron diffuses into both n- and p-type material, the presence of iron in the n-type material could suppress the contamination and conversion reaction. The iron, however, caused a detrimental reaction in p-type lead telluride which was the major cause for module degradation at 1000°F (538°C). At higher temperatures the use of iron contacts resulted in extremely large degradation rates due to iron contamination of the p-type lead telluride. The elimination of iron contacts has solved the p-type problem. The question yet to be answered is whether n-type contamination now shows up because of the higher temperature and absence of iron.

In addition to the possibility that sodium diffusion caused the conversion, the doping mechanisms which produce excess carriers could cause the n-type degradation. The dopants used to produce n- and p-type material are iodine and sodium, respectively. The achievement of high carrier concentrations requires an excess of lead for n-type and a tellurium excess for p-type material. Just as the loss of excess tellurium by formation of FeTe reduces the free hole concentration of p-type material, it is possible that the loss of excess lead could reduce the free electron density in n-type material. The loss could arise due to tellurium which diffuses from the p-type lead telluride and combines with the excess lead to form lead telluride. The iron would be a competing sink for the tellurium in the n-type material which would

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

explain the apparent beneficial effect of iron toward n-type material.

After the discovery of n-type washer contamination in TEM-9U S/N-7 and TEM-9T S/N-1, other modules made prior to the TEM-9U series were sectioned. These latter modules were examined to establish whether the contamination problem had always occurred at mica/n-type lead telluride interfaces or if it was a phenomenon brought about by design changes in the program.

TEM-9AC S/N-2, containing TEGS-2P and GE n-type lead telluride, had been tested for 1300 hours at $\bar{T}_H = 1200^\circ\text{F}$ (649°C). This module contained molybdenum conductor rings at the hot junction. A section was removed from the module where the hot side temperature was 1112°F (600°C). The large mica washer (butt joint at the inner conductor ring) was removed from the n-type washer. Seebeck probe traces taken on radial lines from the inner to the outer conductor ring showed a layer approximately 0.020 inch thick around the inner conductor ring where the n-type lead telluride exhibited gross contamination (conversion to p-type material). From 0.020 inch to approximately 0.080 inch from the inner conductor ring, the washer was contaminated so that above-normal Seebeck values were measured.

TEM-9Y S/N-1, containing TEGS-3P lead-tin telluride and TEGS-2N lead telluride, was sectioned. A portion was removed from the center of the module where the hot side temperature reached a maximum during the test cycle. The module was tested for 1050 hours at $\bar{T}_H = 1000^\circ\text{F}$ (538°C), 950 hours at $\bar{T}_H = 1150^\circ\text{F}$ (621°C), 2500 hours at $\bar{T}_H = 1170^\circ\text{F}$ (635°C), and 500 hours at $\bar{T}_H = 1200^\circ\text{F}$ (649°C). The section was ground to the large mica washer covering an n-type washer and the mica washer removed. Seebeck probe traces on the surface of the n-type washer showed contamination but no conversion to a radial distance of 0.120 inch from the inner conductor ring. The washer was ground away in 0.015-inch steps and Seebeck probe traces taken at each step. At an axial distance of 0.060 inch from the large mica washer, the contamination had almost vanished and diminished to a radial distance of approximately 0.050 inch from the inner conductor ring.

TEM-10 S/N-1 was removed from testing after 5000 hours at $\bar{T}_H = 1000^\circ\text{F}$ (538°C). The module contained iron inner conductor rings with 0.001-inch tungsten foil between the inner ring and the lead telluride washers. The module had experienced nine thermal cycles and degraded rapidly over the span of the several cycles. A section tested at 1022°F (550°C)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

was obtained and the large mica washer removed. The sample was Seebeck probed on the surface of the n-type washer. The washer was contaminated to a radial distance of approximately 0.100 inch from the inner conductor ring but no conversion to p-type material was observed.

TEM-9AE S/N-1 was removed from testing after 2560 hours at $\bar{T}_H = 1000^\circ\text{F}$ (538°C). The module had experienced a rapid resistance rise with time on test compared to other modules of the TEM-9AE series. This series contained TEGS-3P lead-tin telluride in the p-leg of the couple and single-phase n-type lead telluride in the n-leg. TEM-9AE S/N-1 contained 0.0015-inch mica washers and lead telluride washers that were 0.030 inch thick. Destructive examination of the module revealed axial displacement of the mica washers. A section of the module which had been at a hot side temperature of 866°F (475°C) was examined via Seebeck probes on the surface of the n-type washer where the small mica washers were stripped away. The probe traces revealed contamination of the n-type material which extended to a radial distance of 0.110 inch from the hot inner conductor ring. Because the mica was so severely deformed and in some cases completely parted where it separated the inner conductor rings, it is most likely that the contamination was via these openings rather than through the mica.

Figure 2-14 is a plot of Seebeck probes taken on TEM-9AC S/N-2, TEM-9Y S/N-1, TEM-10 S/N-1, and TEM-9AE S/N-1. The probe traces with the exception of that for TEM-9AE S/N-1 were taken on the surface of the n-type lead telluride washer where the surface was in contact with the large mica washer. This is the mica washer which forms a butt joint at the inner conductor ring and separates the p- and n-type washers. In the case of TEM-9AE S/N-1, the probe traces were taken at the opposite end of the n-washer where the small mica washer separates the inner conductor rings.

To further verify that the contamination of n-type lead telluride has been a secondary factor in module degradation, TEM-1 S/N-4 was examined using the Seebeck probe. This module contained a segmented n-washer, having TEGS-3N lead telluride against the inner conductor ring and TEGS-2N lead telluride against the outer conductor ring. The module had been tested for 602 hours at $\bar{T}_H = 1000^\circ\text{F}$ (538°C) and 5700 hours at $\bar{T}_H = 1100^\circ\text{F}$ (593°C). A section was removed from the center of the module where the hot side temperature was 1112°F (600°C). Figure 2-15 is a Seebeck probe trace of TEGS-3N and TEGS-2N lead telluride

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-14. Seebeck Coefficient Versus Radial Distance from Inner Conductor Ring for Various TEM Modules.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-15. Comparison of Seebeck Coefficients of Unaffected TEGS-3N and TEGS-2N and PbTe Material from TEM-1 S/N-4.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

tested in an EXC capsule in intimate contact at 1022°F (550°C) for 1250 hours. Superimposed on this trace is a Seebeck probe trace of TEM-1 S/N-4 taken at the surface where the large mica washer was removed. It is evident from this trace that the n-washer of the module was also affected by some form of contamination.

Subsequent Seebeck probe traces, taken in the n-type washer at axial distances further removed from the large mica washer, showed that the depth and magnitude of the contamination became less as the distance from the large mica washer increased. These results were in agreement with those obtained from TEM-9U S/N-3 and TEM-9T S/N-1, which also showed that the affected portion of the n-type washer became smaller as the axial distance from the large mica washer (butt joint at the inner conductor ring) was increased.

All of the modules examined thus far seem to point out that contamination of the n-type lead telluride has been present to some extent in all TEM modules. At test temperatures near 1000°F (538°C), the n-type contamination is confined to a relatively shallow layer near the mica washer and is not detectable when sections are obtained by grinding into the n-type washer. With increasing test temperature, the degree and extent of contamination increase, resulting in conversion of the n-type to p-type material. The cross-contamination of the n-type by the p-type material proceeds at a slower rate than the process whereby iron diffuses into p-type material.

N-P Reaction

A long-time test investigating the reaction between TEGS-2P and single-phase n-type lead telluride was conducted via an EXC capsule EXC 52, containing alternate pellets of each material. An n-type pellet was used at each end of the capsule to minimize reaction with the iron contacts. The capsule exhibited a slow, steady resistance rise over the testing period. After 2800 hours at 1202°F (650°C), the capsule was removed from test and sectioned axially for metallographic and Seebeck probe examination. There were no apparent reaction products present near the TEGS-2P/n-type interfaces. Figure 2-16 is a plot of Seebeck voltage versus distance along the entire axial length of the capsule. This trace reveals the same phenomenon noted in TEM-9U S/N-7, that a portion of the n-type pellet was converted to p-type material. The center pellet of the capsule, where p-type material

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-16. Seebeck Voltage Versus Distance Along Axial Length for EXC 52,
Tested for 2800 Hours at 650°C (1202°F)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

was in contact with both n-type ends, showed erratic readings. The readings showed mixed n- and p-type conduction indicative of almost intrinsic material. This heavily compensated behavior is similar to that observed in n-type washers obtained from the TEM-9U S/N-7. In the latter case, although the washers were only 0.090 inch thick, conversion of p-type material was confined to layers near the mica washers.

The Seebeck probe traces of the end pellets exhibited different behavior because the contamination source was only at one end of the pellet. The Seebeck voltage is normal near the iron contacts and becomes higher as the p-type pellet is approached. At an axial distance approximately half-way through the pellet, the n-type lead telluride was converted to p-type material with conduction-type behavior that is less erratic than that of the center pellet. The traces taken across the two p-type pellets show that the p-type lead telluride was relatively unchanged. The results suggest that whatever the contamination mechanism that affects the n-type material, it produces little effect in the p-type lead telluride. The data also suggest that the behavior noted in modules is due to the interaction between n-type and p-type lead telluride and the mica washer has no effect other than reducing the depth to which the penetration can occur.

The TEGS-2P/n-type interface was examined with the electron beam microprobe. No differences between the concentrations of tellurium and lead were detected. The erratic behavior of the n-type material when examined by the Seebeck probe suggests that whatever the contaminant may be, it was not spread throughout the n-pellet homogeneously. Thus, it is possible that detection of a concentration difference of lead or tellurium between the two pellets (n-type and p-type) would be very difficult to detect within the limited area covered by the electron beam.

Mica Experiments

As a result of capsule and module examination which showed that inter-couple diffusion was responsible for module degradation, experiments were designed to evaluate phlogopite mica with respect to its ability to effectively insulate p- and n-type material.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

As an initial starting point, a sheet of 0.005-inch heat treated, unprocessed mica was pressed between n- and p-type lead telluride. The electrical resistance of the resulting circuit was measured as a function of temperature from room temperature to 1382°F (750°C). The entire resistance of the circuit can be attributed to the mica since the resistances of the other components are negligible. Figure 2-17 is a plot of log resistivity of mica versus 1/T. From this plot it can be seen that the resistivity of heat treated mica (the same mica used in modules) was still 10^8 ohm-cm at 1382°F. The large value for the circuit indicates very little, if any, interaction between the lead telluride washers through the mica. The n-type/mica/p-type configuration was held for 165 hours at 1202°F (650°C) to determine if any resistance change occurred with time at temperature. No significant change in the resistance was noted over the life of the test, indicating that unprocessed mica for these test conditions is an effective electrical insulator and diffusion barrier between n- and p-type lead telluride. The test temperature was then raised to 1382°F.

After 100 hours at 1382°F the test was halted and the lead telluride pellets were removed and examined with the Seebeck probe. The pellets were probed on the face that was pressed against the mica insulator. The p-type pellet remained unaffected, but the n-type lead telluride exhibited high Seebeck values across its entire face. The relative value of the Seebeck coefficient was higher than any values measured on module washers, even for those that had been partially converted. The pellet was ground away in 0.005-inch steps and the Seebeck probe trace repeated after each removal of material. The Seebeck coefficient remained essentially unchanged, even after 0.020-inch of the pellet was ground away. The high value of the Seebeck coefficient, coupled with its even distribution throughout the pellet and also with the constant high value of the resistivity of the circuit (10^8 ohm-cm), leads to the conclusion that the contamination of the n-type pellet was probably due to some source other than solid state inter-couple diffusion.

One possible contamination source was tellurium vapor from the excess tellurium in the p-type pellet. To evaluate this possibility, an experiment is underway using n- and p-type bars of lead telluride sealed in the same Vycor vial. These vials will be annealed for long times at 1112°F (600°C) to determine if tellurium vapor will contaminate the n-type lead telluride to the same extent as found in the n-type pellet used in the mica experiment.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-17. Resistivity of Heat Treated Phlogopite Mica Versus Reciprocal Temperature

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

In order to measure the effect of processed mica between n- and p-type lead telluride, the experiment described above was repeated using mica removed from a processed module. The module selected was TEM-10 S/N-1. This module was chosen for two reasons. First, the mica in TEM-10 S/N-1 had a radial thickness of approximately 0.400 inch, making it possible to use larger specimens of lead telluride and thus bring mica containing more process deformation cracks into contact with the lead telluride. Second, the module was tested at a lower hot side temperature than most modules ($\bar{T}_H = 1000^\circ\text{F}$ (538°C)), and possible contamination of the mica should have been minimal. Seebeck probe traces were taken on the n-type washer from TEM-10 S/N-1 with the small mica washer removed. The results showed that the n-type washer was contaminated to a radial distance of approximately 0.100 inch from the inner conductor ring, but no converted regions were found.

After 377 hours at 1202°F (650°C), the test was terminated. During the life test, the resistance readings across the processed mica were erratic and no smooth curve could be plotted as was the case for the unprocessed mica experiment. It should be noted, however, that in no case did the resistance of the processed mica approach that of the unprocessed mica. Upon termination of the test, the pellets were examined via the Seebeck probe. Probe traces were taken on the pellet face that was pressed against the processed mica barrier. The traces revealed that the p-type pellet was affected very slightly as indicated by a rise in the Seebeck coefficient across its entire surface area. A large portion of the surface area of the n-type pellet, however, was converted to p-type lead telluride. Once again, it should be noted that contamination of the n-type pellet could come from the sources outlined previously, but the conversion of the n-type lead telluride to p-type material gives a strong indication that material transport through the processed mica could have been the main source of inter-couple contamination in thermoelectric modules.

To further evaluate unprocessed mica between n- and p-type lead telluride, a capsule was designed to press lead telluride pellets against mica under more controlled conditions. In the other experiments, described above, the pellets were compressed in a spring loaded apparatus and inserted into a 3-inch diameter Vycor tube. The test conditions allowed a large volume into which tellurium could vaporize and a large surface area of n-type lead

~~CONFIDENTIAL~~

telluride exposed to the tube atmosphere. In the capsule experiment discussed here, the pellets were inserted into a stainless steel capsule with threaded end caps. Inside this capsule are concentric boron nitride insulating sleeves with the inner sleeve split. The ID of the split sleeve was smaller in diameter than that of the mica insulator. Loading was achieved by applying a torque load of 50 foot-pounds to the end retaining bolts. No further compaction was used in order to reduce the possibility of radially deforming the mica.

The capsules were placed on test at 1202°F (650°C) in a Vycor tube which in turn was inserted into a tube furnace. A cover gas of high purity argon was used in the tube to ensure minimal contamination from oxygen. The resistance of each capsule was monitored as a function of time. Over the life of the test, 1000 hours, both capsules exhibited a decrease in their respective resistivities, the control capsule going from 8×10^8 ohm-cm at $t = 0$ to 2×10^6 ohm-cm at $t = 1000$ hours, and the p/n capsule from 8×10^7 ohm-cm at $t = 0$ to 2×10^5 ohm-cm at $t = 1000$ hours. The capsules were removed from test after 1000 hours and destructive examination was started to determine if the electrical properties of the lead telluride had been altered.

Mica Test Capsules

Capsules were fabricated using n- and p-type lead telluride pellets separated by mica discs. Three capsules, EXC 65 and EXC 67 with 5-mil thick mica, and EXC 69, with two 1.5-mil thick mica discs, were tested for 300 hours at 1382°F (750°C). These capsules were removed from test due to a rapid decrease in circuit resistance during the test period. The capsules were cut in half so that 2.5 pellets could be removed as a unit from each capsule, while the remaining section could be cut parallel to the capsule axis. Examination showed extensive cracking in the mica due to radial compaction. Allowing additional assembly clearances between the mica and BN could reduce the problem. Other experiments to investigate mica fracture are described elsewhere in this section.

Seebeck probes across pellet faces in contact with mica were run on the tested capsules and on EXC 68, which contained two 1.5-mil untested mica separators. Measurements on the end n-type pellets taken from EXC 65, 67, and 69 showed partial conversion at the center of the n-type face next to the mica/p-type interface. A typical Seebeck probe

~~CONFIDENTIAL~~

across the face of the pellet is shown in Figure 2-18. In contrast, measurements on the center n-type pellets from all three capsules showed complete conversion to p-type material at the face of the pellet.

Axial probes were also performed on the remaining half-sections of these capsules. The measurements showed that the center n-type pellets were considerably more affected than the end n-type pellets. The results are in agreement with those obtained on pellets from the other end of the capsule. It may be that the maximum compaction near the center of the capsule fragmented the central mica discs more than the end ones and, hence, more extensive diffusion could occur at the former locations. The conversion of the n- to p-type lead telluride does not appear to affect the p-type pellets. The p-type pellets exhibited normal Seebeck coefficient values along their axial length.

Capsule EXC 68, processed with two 1.5-mil mica discs but not tested, showed normal values for all pellets despite the badly cracked appearance of the mica. As expected, the contamination phenomenon is time and temperature dependent as well as being a function of the integrity of the mica. Allowing larger radial clearance in module mica washers so that most of the radial compaction occurs before stress is placed on the mica should eliminate some of the mica cracking problems.

In a continuing effort to evaluate mica insulators, three capsules with alternating n- and p-type PbTe pellets in sleeved BN and separated by mica were tested at 1202°F (650°C) for 1000 hours. Specific design features of these capsules were as follows: EXC 66, 5 mil thick mica; EXC 70, 2-1.5 mil thick mica; and EXC 82, 2-1.5 mil thick mica discs separated by 1-mil thick tungsten foil.

After testing, the capsules were cut in half so that pellets could be extracted intact from one half and the other sectioned axially. Metallographic and Seebeck probes were then made on the samples. A photomicrograph representative of both the 5 mil and 2-1.5 mil mica discs is shown in Figure 2-19. Delamination and cracking had occurred during processing and then these defects filled during testing. That the latter event occurred is based on the examination of EXC 68 which was not tested after autoclaving. Although mica separation occurred, there was no thermoelectric material in the cracks.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-18. Seebeck Probe of the End n-Type PbTe Pellet From EXC 65.

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure 2-19. Mica Tested in Capsule EXC 70 for 1000 Hours at 1202°F (650°C), 100X

CONFIDENTIAL

~~CONFIDENTIAL~~

Seebeck probes along the axis showed contamination similar to that observed in capsules tested at 1382°F (750°C). However, the extent and magnitude of the changes were greater for the samples tested at 1382°F . Seebeck probes were made on the faces adjacent to the mica/p-type PbTe interface. Figure 2-20 shows the results obtained on pellets 1657 and 1658 removed from capsule EXC 66. Dimensional measurements showed the mica next to pellet 1657 was reduced in diameter 3 mils more than the mica next to pellet 1658. The curves show that the surface contamination at the face center of pellet 1657 was affected more than for pellet 1658. Comparable examination of pellets from EXC 70 showed the same behavior. In fact, the pellet next to the more severely deformed mica was converted to p-type material at the face center. The results tend to indicate that reduction of the mica deformation in the module (such as by increasing clearance tolerances) would be beneficial toward reducing n-type contamination.

The results obtained on EXC 82 showed that 1-mil tungsten foil sandwiched between 1.5-inch mica discs was successful not only as a diffusion barrier, but also as a strengthening member for the mica. Figure 2-21 shows that even when the mica was deformed into a node of the type which causes cracking and delamination in other capsules, the tungsten appears to have prevented this undesirable behavior. The efficiency of the barrier was further demonstrated by the results of the Seebeck probes. In all cases, the data showed that the n- and p-type pellets were completely unaffected by any interdiffusion.

Capsules containing TEGS-2N lead telluride in contact with mica had been autoclaved previously at 1130°C - 10,000 psi and then annealed at 1130°F (610°C) for varying periods of time. The center pellet, No. 240, was removed from standard capsule S/N-47 after 12,400 hours at temperature. For comparative purposes, pellet 234 was used because it came from capsule S/N-41 which was autoclaved and not heat treated. Seebeck probe traces were taken on these pellets as shown in Figure 2-22. The corresponding resulting traces are shown in Figures 2-23A, B, and C. The upturn in Seebeck coefficient, Figure 2-23A, at the ends of the diameter in the end trace appears to be a surface reaction caused either by lead rejection at the surface, the old problem of lead penetration of the boron nitride caused by high temperature autoclaving of n-type lead telluride which contains second-phase free

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-20. n-Type Pellets Removed From Capsule EXC 66 After 1000 Hours at 1202°F (650°C)

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure 2-21. Mica/W/Mica Tested in Capsule EXC B2 for
1000 Hours at 1202°F (650°C), 100X

CONFIDENTIAL

~~CONFIDENTIAL~~

Figure 2-22. Positions of Seebeck Probe Traces Taken on Pellets No. 240 and No. 234.

~~CONFIDENTIAL~~

CONFIDENTIAL

- TEGS-2N Pellet After 12,400 Hours At 625°C
- TEGS-2N Pellet After Gas Pressure Sintering

Figure 2-23. Seebeck Coefficient Versus Distance Along TEGS-2N Pellets

CONFIDENTIAL

~~CONFIDENTIAL~~

lead, or by a surface reaction with boron nitride. The surface longitudinal trace, Figure 2-23B, shows a higher Seebeck coefficient along the entire axial length. However, an interior trace, Figure 2-23C, clearly demonstrates that no reaction occurred at the mica/n-type lead telluride interface, which just about eliminates mica as a possible source of contamination for n-type lead telluride.

Neutron Activation Analysis for Sodium

Seebeck probes of TEM-9U S/N-7, TEM-9AC S/N-1, and experimental capsules EXC 65, 66, and 69 have shown converted n- to p-type regions in the n-type PbTe components. The explanation of the conversion mechanism requires identification of the product that diffuses through or around the fractured mica during testing. A determination of the sodium concentration in affected regions of TEM-9U S/N-7 was made using neutron activation analysis to determine if sodium diffuses into the n-type material.

Eight uncontaminated lead telluride (n- and p-type) samples were irradiated to establish a sodium base level present in normal material. The neutron activation analysis was calibrated for sodium by first irradiating a 10 ± 1 ppm sodium standard. The iodine (131) isotope which is the decay product of ^{131}Te was used as a neutron flux monitor. The average sodium concentration was 635 ppm for the p-type PbTe and 1.9 ppm for the n-type PbTe. The doping level of p-type PbTe was previously determined by flame photometry to be approximately 620 ppm, in good agreement with the neutron activation analysis.

The results of the neutron activation analysis for sodium content in 28 samples from n- and p-type washers are shown in Figure 2-24. For clarification, the large mica washer butts against the inner, hot-side conductor ring and extends through the outer conductor components. The small mica washer divides the inner hot-side conductor components and butts against the outer, cold side conductor ring. The results show that some sodium diffused to the n-type washer from the p-type lead telluride. Qualitatively, the largest concentrations are found in the vicinity of the hot conductor ring and next to the large mica washer. Near the center of the washer and at the cold conductor ring, the sodium levels are close to background. The results are not surprising since most of any diffusion has to take place at higher temperatures

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

n-Type PbTe Washer

Butt-Joint Mica Washer

p-Type PbTe Washer

612897-16

Figure 2-24. Specimen Location and Sodium Concentration Obtained by Neutron Activation Analysis.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

and the large mica washer does not make a perfect seal. Accompanying the diffusion of sodium into the n-type material is a decrease in sodium content of the p-type lead telluride near the hot side conductor. It should be noted that all samples taken from points near the hot conductor ring do not yield the same sodium content. While some variation may be expected due to sample procurement methods and the analysis itself, the results are probably more indicative of variations along the circumference of the mica/lead telluride interfaces. Dependence on how the mica is deformed affects the diffusion pattern, much in the same manner that the measured electrical properties change along different radii.

Preliminary neutron activation analysis of uncontaminated PbTe specimens determined the average sodium concentrations to be 635 ppm and 1.9 ppm for p- and n-type lead telluride, respectively. Comparison with the contaminated specimens from TEM-9U S/N-7 shows the sodium concentration of the p-type washer specimens ranged from 12-30 percent below normal levels. Not all of the decrease in sodium content can be due to n-type pickup, since some sodium may be trapped in the mica. At any rate, the decrease in sodium content of the p-type material did not significantly alter its electrical properties which were measured during the destructive examination of TEM-9U S/N-7. Sodium contamination of the n-type washer was highest near the washer hot side but decreased to slightly greater than uncontaminated levels from the midpoint outward.

Heat treated mica specimens were analyzed for sodium content by a two-irradiation neutron activation technique. Irradiations were made with and without Cd liners at the core face to isolate higher energy reactions (> 0.025 ev). Magnesium and aluminum present in the mica reacted with high energy neutrons to yield Na^{24} which is the same isotope activated from naturally occurring sodium. Flux monitoring was made by an internal potassium activity and an external calibrated sodium source of 10 ppm. The sodium contents determined by the described method on four mica specimens were 126.5, 124, 110, and 116 ppm. The average sodium base level of 119 ppm for heat treated mica was determined to be tightly bound in the structure as shown by mica/n-type PbTe compatibility experiments.

~~CONFIDENTIAL~~

Tellurium Diffusion

Based on the chemical composition of p-type lead telluride, it appeared likely that either sodium and/or tellurium could be the contamination diffusant. Both are present in the p-type PbTe, with sodium as a p-type dopant and tellurium present in excess of stoichiometry. To establish the effects of tellurium diffusion on the electrical properties of n-type lead telluride, two separate experiments were initiated.

Varying amounts of tellurium (0.25, 0.50, and 1.0 weight percent) were mixed with n-type lead telluride powder which was pressed into a series of electrical measurement bars. The bars were processed using the standard hydrogen heat treatment. The electrical characteristics of one bar from each series plus a control bar containing no excess tellurium were measured as a function of temperature. Figure 2-25 shows the relative Seebeck coefficient versus temperature for these bars.

It was apparent that as the amount of tellurium increased, the material changed from n- to p-type, with increasingly higher values for the p-type Seebeck coefficient. With increasing temperature the material eventually changed back to n-type material. The data clearly showed that as the excess tellurium concentration increased, the crossover from p- to n-type material occurred at higher temperatures. For the bar into which 0.25 weight percent excess tellurium had been added, the material became n-type at 171°F (350°K), but the bar containing 1.0 weight percent excess tellurium did not become n-type until 495°F (530°K). After these preliminary measurements were completed, the bars were sealed in Vycor vials under a partial pressure of high purity argon and annealed at 1094°F (590°C). After 500 hours at 1094°F a bar from each concentration set of excess tellurium was removed and the resistivity and Seebeck coefficient remeasured. The Seebeck coefficient data obtained for the annealed bars were quite similar to that measured prior to the anneal. The results indicated that most of the changes in the Seebeck coefficient of the n-type lead telluride probably occurred during the heat treating cycle.

It was noted, after the heat treating cycle, that the bars containing excess tellurium additions exhibited some evidence of melting. Since tellurium melts at 845°F (452°C) and the bars are heat treated at 1067°F (575°C), it seemed likely that some of the excess tellurium,

~~CONFIDENTIAL~~

Figure 2-25. Seebeck Coefficient Versus Average Temperature for Heat Treated n-Type Bars Containing Excess Tellurium.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

present in each bar in powder form, could have melted before it combined in the solid state with the PbTe. Also, a portion of the excess tellurium could have been lost during the dynamic hydrogen heat treatment. Accordingly, a similar series of bars was prepared, but these bars were not given the hydrogen heat treatment. Instead, immediately after pressing, they were inserted and sealed into Vycor vials with an atmosphere of high-purity argon. Preliminary electrical measurement data of these bars were erratic because n-type telluride that is not heat treated exhibits high resistivity and high Seebeck values which are probably due to oxygen contamination. Heat treatment in hydrogen removes the excess oxygen but, as noted above, the treatment would also melt the excess tellurium additions. The vials were annealed for 100 hours at 725°F (400°C) and 100 hours at 932°F (500°C) in an attempt to assure that most of the excess tellurium would diffuse and form a tellurium-rich lead telluride with some second-phase tellurium and a minimum of melting. Examination of the bars after this preliminary anneal showed no evidence of melting. The vials then received the same 500 hour, 1094°F (590°C) anneal given the heat treated excess-tellurium bars. Figure 2-26 shows the results of the Seebeck voltage as a function of temperature for the bars not heat treated, with 0.25, 0.50, and 1.0 weight percent excess tellurium. A single curve is shown because there was essentially no difference in the values of the three bars measured. The results of the measurements on the non-heat-treated bars containing excess tellurium seem to indicate that a limit of excess tellurium exists above which further additions have no effect on the electrical properties of the material. This limit is postulated to be in the range below 0.25 weight percent excess tellurium. However, it should be noted that the presence of oxygen in these samples could alter the results to some extent.

It is of interest to compare the results obtained on the n-type bars containing excess tellurium to those measurements taken on a contaminated pellet. The pellet was n-type material and occupied the center position between two p-type pellets in capsule EXC 52. The capsule had been heated to 1202°F (650°C) and held for 2800 hours, during which time the circuit resistance increased in value. Upon removal from test the capsule was sectioned axially and electrically probed. The center pellet was completely contaminated and was converted to p-type material. Electrical resistivity and Seebeck coefficient measurements were made as a

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-26. Seebeck Coefficient Versus Average Temperature for Non-heat Treated n-Type Bars Containing Excess Tellurium.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

function of temperature, Figure 2-27. The resulting Seebeck coefficient curve is quite similar to the curves obtained on bars containing excess tellurium. The material starts as p-type at room temperature and converts over to n-type at about 622°F (600°K). Complete agreement of the curves does not occur, but this is to be expected because of the difference in the way the specimens arrived at the final state. The bar had a homogeneous distribution of excess tellurium, whereas the pellet probably had a concentration gradient of contaminant from the ends to the center.

A marked increase in the electrical resistivity accompanied the drastic changes in the Seebeck coefficient of the n-type bars. Figure 2-28 is a plot of the electrical resistivity of the heat treated bars after annealing for 500 hours at 1094°F (590°C). These bars are the ones in which melting was observed after the heat treating cycle. It should be noted that as the apparent excess tellurium concentration increased, the electrical resistivity also changed. These data are consistent with the changes that occurred in the corresponding Seebeck coefficient.

Figure 2-29 is a plot of the electrical resistivity of the non-heat-treated bars annealed at 752°F (400°C) for 100 hours and 932°F (500°C) for 100 hours prior to the 500 hour anneal at 1094°F (590°C). The latter curves do not show the same electrical property dependence on excess tellurium concentration. With the exception of the bar containing 0.25 weight percent excess tellurium at low temperatures, below 260°F (400°K), the curves are essentially the same. This too is consistent with the results of the Seebeck coefficient measurements on these bars, i. e., no change with different excess tellurium concentration.

The significant results are that in all cases observed the electrical resistivity was considerably increased above the normal values for n-type material. In addition, the Seebeck voltage over any module operating temperature range, $S.V. = \int \alpha dT$, would be reduced if the washer were completely contaminated. However, the contamination is not homogeneous for a washer; hence, the results would not be completely comparable. In any case, the data show that n-type material can be contaminated by excess tellurium (without any sodium present) so that the electrical properties are similar to those obtained on a pellet that was contaminated by contact with p-type lead telluride.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-27. Seebeck Coefficient and Resistivity Versus Average Temperature for Center n-Type Pellet from EXC 52. Tested for 2800 Hours at 1202°F (650°C)

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

Figure 2-28. Electrical Resistivity Versus Average Temperature for Heat Treated n-Type Bars Containing Excess Tellurium.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-29. Electrical Resistivity Versus Average Temperature for Non-Heat Treated n-Type Bars Containing Excess Tellurium.

~~CONFIDENTIAL~~

To further define the effects of excess tellurium as a possible diffusing contaminant, p-type material was mixed with additional amounts of excess tellurium (0.25, 0.50, and 1.0 weight percent). These mixtures were melted in quartz tubes to assure homogeneity of the batch. The material was then processed in the same manner as normal p-type material. Pellets were pressed from each batch of material along with control pellets from normal p-type lead telluride. A pellet from each batch (0.25, 0.50, and 1.0 weight percent excess tellurium) was inserted into a graphite die along with a pellet of normal n-type material. This arrangement formed a diffusion couple, with the amount of excess tellurium varying from the amount present in normal p-type lead telluride to, in the extreme case, 1.0 weight percent over the normal amount. The dies were inserted into an inert atmosphere furnace and compacted for 7 hours at 1472°F (800°C) under a load of 5000 psi. Immediately following the compaction, the dies were sectioned axially and ground and polished for Seebeck probe examination. The Seebeck probe traces were taken in an axial direction, starting in the p-type lead telluride and proceeding into the n-type material.

It was postulated that, if tellurium diffusion was responsible for contamination of the n-type material, the affected portion of the n-type pellet should become greater as the tellurium concentration increased. Figure 2-30 is a plot of the Seebeck coefficient versus distance from the interface of the p-/n-type couple for the three alloys considered. This figure shows that as the tellurium concentration of the p-type material increased, the affected distance and magnitude of the contamination also increased.

The results of this die experiment support the possibility that tellurium diffusion through or around the mica insulators in TEM modules could be responsible for contamination of the n-type lead telluride and the subsequent degradation of module performance during life testing.

Hall Effect Measurements of TEGS-2P PbTe

Establishment of the doping level in TEGS-2P can be used as a basis for investigating radial dopant migration under a temperature gradient in the couple leg. Problems of this nature, if they exist, were previously obscured by the diffusion of iron from the conductor ring into the TEGS-2P PbTe washers.

~~CONFIDENTIAL~~

Figure 2-30. Seebeck Coefficient Versus Distance from P/N Interface

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

The Hall effect, a majority carrier mechanism, directly measures the extrinsic carrier concentration and, in the case of TEGS-2P, the hole concentration of the material.

The Hall coefficient is defined as

$$R_H = \frac{rf(K)}{p^*e},$$

where $rf(K)$ is the Hall factor, the nominal carrier concentration is p^* , and the carrier charge is e . The assumption that $rf(K) = 1$ is valid only for carrier concentrations less than $10^{19}/\text{cm}^3$ and high-field (>250 kg) measurements. Calculation of the nominal carrier concentration using the above assumption gives the approximate number of carriers present in the sample.

Two TEGS-2P samples (batch 185-0-1) were cut from pressed and sintered bars to approximate dimensions of 2 millimeters square by 1 centimeter long. Hall data were taken with the magnetic field and sample current in both directions to eliminate errors due to misalignment of the probes.

The results of the first measurement are given in Table 2-2. The nominal carrier concentration p^* was calculated from the expression

$$p^* = \frac{1}{R_{77^\circ\text{K}}e},$$

where $R_{77^\circ\text{K}}$ is the weak field (6.1 kg) Hall coefficient measured at 77°K .

The second sample was measured at 4.2°K as a function of the magnetic field to 55 kg. The results of the run are shown in Figure 2-31. The Hall coefficient at 4.2°K was consistent with the measurements at 77 and 297°K . Attempts to saturate the Hall coefficient to a constant value were unsuccessful as indicated by the positive slope of the R_H versus H curve.

TEGS-2P material has a sodium concentration near the maximum solubility limits, $\approx 1.30 \times 10^{20}$ Na atoms/ cm^3 (0.062 weight percent), as determined by flame photometry. The nominal carrier concentration calculated from the weak field Hall coefficient at 77°K shows agreement with flame photometry data.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 2-31. Hall Coefficient of TEGS-2P Lead Telluride at 4.2°K Versus Magnetic Field

~~CONFIDENTIAL~~

Astronuclear
Laboratory

TABLE 2-2

NOMINAL CARRIER CONCENTRATION FROM HALL DATA

Temperature °K	Hall Coefficient (cm ³ /coulomb)	Nominal Carrier Concentration (cm ⁻³)	Carrier Mobility (cm ² /v-sec)	Electrical Resistivity (ohm - cm)
297	0.083	7.57×10^{19}	154	5.36×10^{-4}
77	0.049	1.30×10^{20}	278	1.76×10^{-4}

TEGS-2P material has a sodium concentration near the maximum solubility limits, $\approx 1.30 \times 10^{20}$ Na atoms/cm³ (0.062 weight percent), as determined by flame photometry. The nominal carrier concentration calculated from the weak field Hall coefficient at 77°K shows agreement with flame photometry data.

Although this measurement technique could possibly be applied to establish directly the number of free carriers lost due to contamination mechanisms, no further effort in this area was attempted.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

B. PROCESS DEVELOPMENT

Thermoelectric Washer Fabrication

A milestone in the Phase II-C project was the completion of an investigation of methods for fabricating thermoelectric washers with different diameters and axial lengths. Table 2-3 is a tabulation of all the T/E washer designs successfully fabricated for module use to date. The same general technique was used for fabrication of all of these designs. The washers were cold pressed from powders, using precision carbide dies mounted in an automatic hydraulic press. Double-action pressing and forced die float techniques were used to eliminate axial density gradients. A $-35 + 270$ mesh powder was used for all washers having axial lengths greater than 0.080 inch and $-50 + 270$ powder was used for all washers shorter than 0.080 inch. All TEGS-2P powder was heat treated in hydrogen for 1 hour at 1022°F (550°C) prior to pressing in order to eliminate excessive dimensional distortion in the TEGS-2P washers during subsequent heat treating. All other materials were pressed in the as-received condition. Nearly all module washers were pressed to 91 percent of theoretical density.

After pressing, all washers were heat treated in hydrogen for 2 hours at 1067°F (575°C) to achieve surface cleaning and some strengthening resulting from interparticle bonding. P- and n-type washers were heat treated separately to avoid cross-contamination. After heat treating, each washer was inspected for conformance with its dimensional requirements and with a low temperature p-n polarity test. In all cases it was possible, when required, to maintain dimensional tolerances as low as ± 0.0005 inch on the outer diameter, inner diameter, and axial length.

One item not attempted at this time was the development of a fabrication technique for TEGS-2P PbTe washers corresponding to the n-type washers of Design Number 7 in Table 2-3. Because of press capacity limitations, it was necessary to fabricate two concentric washers that would be assembled together either before or after heat treating. No problem was encountered in pressing these washers, using the approach indicated previously. However, several approaches to heat treating were unsuccessful. Heat treating them (either singly or assembled into concentric pairs) on flat, non-restraining graphite trays resulted in unacceptably

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~ Astronuclear
Laboratory

severe dimensional changes and distortion. Heat treating of assembled concentric pairs in recessed graphite trays machined to restrain the outer washer OD and inner washer ID resulted in fracture of many of the washers. No further work on this problem was performed. The only Phase II-C module fabricated using washers of this design (TEM-12A S/N-1) was assembled with TEGS-2P washers that were not heat treated.

TABLE 2-3

T/E WASHER DESIGNS SUCCESSFULLY FABRICATED TO DATE

<u>Basic Design Number</u>	<u>Material(s)</u>	<u>Outer Diameter (inches)</u>	<u>Inner Diameter (inches)</u>	<u>Axial Length (inches)</u>
1	TEGS-2P) TEGS-3N)	1.070	0.792	(0.091 0.089
2	TEGS-2P) TEGS-2N)	1.290	1.072	(0.091 0.089
3	TEGS-2P) TEGS-2N, -3N:GE-N) TEGS-3P	1.290 1.292	0.792 0.073	(0.0945, 0.091, 0.089, 0.091, 0.089, 0.050, 0.030 0.091, 0.089, 0.053, 0.032
4	TEGS-2P) GE-N) TEGS-3P	1.361 1.363	1.055 1.057	(0.093, 0.053, 0.036 0.087, 0.050, 0.033 0.036
5	TEGS-2P) GE-N)	1.690	1.474	(0.172 0.174
6	TEGS-2P) GE-N) TEGS-3P	2.270 2.272	1.412 1.413	(0.091, 0.030 0.089 0.091
7	TEGS-2N, GE-N	3.678	2.391	0.089

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

C. SUMMARY

Tungsten and molybdenum were proven to be acceptable materials for use as electrical contacts with n-type lead telluride. Tungsten was the only material compatible with p-type lead telluride. The compatibility of these contact materials was shown by examination of capsule and die tests at temperatures up to 1382°F (750°C). Materials modules containing tungsten and molybdenum electrical contacts demonstrated high temperature stability at 1202°F (650°C) during 3600 hours of performance testing.

Eliminating lead telluride reactions with the conductor rings allowed testing at higher temperatures than previously used. A second-order degradation mode was noted at the elevated temperatures. Contaminant diffusion from the p-type to the n-type washer resulted in deleterious changes to the electrical properties of the n-type material. These changes produced (at room temperature) a conversion of the n-type to p-type material in the region near the hot conductor, particularly near the mica butt joint. Capsule tests designed to produce completely converted material showed that thermal conversion back to n-type material occurred at higher temperatures. The net result, however, would be a decrease in voltage and an increase in resistance during operation. This diffusion phenomenon was found to some degree in all modules examined to date. In earlier modules containing iron the effect was heavily masked by the reaction of the p-type lead telluride with the iron at the lower test temperature.

All evidence compiled to date indicates that tellurium diffusion from the p-type lead telluride into n-type lead telluride is probably responsible for degradation. A retardation of this diffusion was accomplished by a design change of the inner conductor rings which eliminate the butt joint and, thus, a probable diffusion path between washers. Diffusion of the contaminant still may occur through the mica washer because of deformation of the mica during module processing. Capsule experiments with a thin tungsten foil between thin mica insulators successfully halted contamination of n-type lead telluride at 1202°F (650°C) for 1000 hours. Work was begun on coating thin films onto the mica to act as diffusion barriers to contaminants.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

III. MODULE DEVELOPMENT

A. INTRODUCTION

The objectives of the module development program during Phase II-C of the Compact Converter Program were to provide means of evaluating the combined results of the design, analysis, materials, and process development efforts through the study of modules subjected to pre-performance testing, destructive evaluation, and long-term life testing. During Phase II-C thirty-three modules were endurance tested over extended periods of time.

The major effort during this phase of the program was directed toward the evaluation of the performance of modules incorporating various design modifications aimed at achieving stable performance at high temperatures. One such design utilizing a two-piece inner conductor ring resulted in a module with a degradation rate too low to accurately measure at an operating temperature level of 1100°F.

Continued testing of modules incorporating TEGS-3P material demonstrates the high temperature capabilities of this material.

Evaluation of test data from an energy conversion system incorporating a TEM-10 (1-inch ID) module coupled to a heat source using a heat pipe was completed. Results of this test demonstrated the high efficiency capabilities of such a system.

~~CONFIDENTIAL~~

B. MODULE FABRICATION

Fabrication of twenty experimental modules was completed during Phase II-C. These fall into three geometric design classes on the basis of overall module diameters, which are the TEM-9 series (1.700 inch OD x 0.500 inch ID), the TEM-10 series (2.717 inch OD x 1.092 inch ID), and the TEM-12 series (4.100 inch OD x 1.864 inch ID). From the design viewpoint, the twenty modules represent fifteen separately definable designs, with most of the variations (aside from overall module size) being concerned with conductor rings, mica insulators, and end assembly configurations. Improvements and innovations were made in fabrication technology, stemming mainly from materials development work, from various problems which occurred, and from module design changes. The various aspects of Phase II-C module fabrication are discussed in the following sections of this report.

Component Fabrication and Processing

New aspects of thermoelectric washer fabrication have already been discussed in Section II. An all-graphite heat treating rack was introduced for hydrogen heat treatment of p-type PbTe; this was necessary to eliminate a scaling problem which occurred with the previous Inconel 600 rack/graphite tray system.

Fabrication technology of boron nitride insulating sleeves, Alsimag 222 insulating components, mica insulating washers, iron conductors, and stainless steel and Inconel 718 structural components remained essentially unchanged from Phase II-B, except for some tightening of dimensional tolerances and more stringent inspection requirements. Fabrication of molybdenum and tungsten conductors was performed by vendors, with WANL performing final inspection and surface cleaning operations.

Module Assembly and Welding

An improved scheme of thermoelectric circuit assembly was developed and instituted during Phase II-C. This involved the reduction of all axial length tolerances on couple components to ± 0.0005 inch (versus the previous standard ± 0.001 inch), and dimensional categorization and combination of couple components on a per module rather than per couple

basis. The results included a very large reduction (about 50 percent) in the overall circuit length tolerance stackup and a slight improvement in the dimensional relationships within a given couple. TEM-9Q S/N-7; TEM-9U S/N-13, -14, -19, -21, and -22; TEM-9AF S/N-1; TEM-10 S/N-4, -7, -8, and -9; and TEM-12A S/N-1 were assembled according to this improved scheme.

Toward the end of Phase II-C, a potential problem was discovered in the method employed to axially preload assembled modules prior to structural welding. In certain modules having low-heat-loss end closure designs, typified by TEM-10 S/N-3 and shown schematically in Figure 3-1, the following procedure was in use:

- 1) The "loose" module assembly was placed in an axial compression fixture with load transmittal end fittings as shown in Figure 3-1A. The (+) end load transmittal fitting had a lip overlapping the retaining ring to locate the (+) end of the outer clad prior to welding.
- 2) Axial loading was applied to the load transmittal fittings as shown in Figure 3-1B, and takeup of the axial clearance in the loose circuit stack occurred.
- 3) When the specified load of 1100 pounds was reached, one of two conditions had been achieved:
 - a) All of the axial clearance in the circuit stack was taken up, leaving a zero-to-positive gap at the (-) end of the outer BN sleeve, as shown in Figure 3-1C. This is the desired condition prior to welding.
 - b) A zero gap was established at the (-) end of the outer BN sleeve, but some axial clearance remained in the circuit stack, as shown in Figure 3-1D. This condition is undesirable, since the module would then be welded and the structural envelope "frozen" around a loose circuit stack.

Although it could not be proved that the undesirable condition (3- b above) had ever actually existed in a module, the possibility of such a condition existing was judged unacceptable in view of the circuit distortion and component curvature problems experienced with the early modules.

~~CONFIDENTIAL~~

(A) LOOSE MODULE ASSEMBLY WITH LOAD TRANSMITTAL END FITTINGS

(B) MODULE ASSEMBLY WITH PARTIAL AXIAL LOAD APPLIED

(C) DESIRABLE FINAL CONDITION AT FULL AXIAL LOAD

(D) UNDESIRABLE FINAL CONDITION AT FULL AXIAL LOAD

612969-1B

Figure 3-1. Axial Compression of Module with Low Heat Loss End Design

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

A partial correction for this situation was applied to the last few modules assembled in Phase II-C, i. e., to TEM-10 S/N-4 and -7, and TEM-12 S/N-1. This consisted simply of removing the lip from the (+) end load transmittal fitting, thus adding the length of the previously designed-in gap at the (+) end of the outer BN sleeve to the total possible amount of axial circuit compression. This amounted to an additional 0.015 ± 0.007 inch of possible axial compression in the TEM-10 case. However, it was still dimensionally possible (but considerably less likely) to have an undesirable condition similar to that shown in Figure 3-1D except for zero gaps at both ends of the outer BN sleeve. In future designs, this last possibility will be eliminated by shortening the outer BN sleeve (or making equivalent changes in other end components) to an extent which makes the existence of the condition impossible.

Only one significant problem occurred during Phase II-C in the area of module welding. In two cases, the fillet weld joining the outboard end of the 304 stainless steel end cap to the Inconel 718 inner clad was located extremely close (~ 0.185 inch) to the end of the inner clad. After welding, liquid penetrant inspection disclosed numerous cracks in the inner clad end, apparently outboard of the weld fusion zone.

Numerous test welds were made on specimens simulating this joint in order to establish causes and preventative measures. Attempts to reproduce the defects were completely successful; Figure 3-2 shows two such specimens after liquid penetrant inspection, and the defect indications are clearly visible. Visual observations during welding indicated that excessive heat buildup was occurring in the very short section between the weld fillet and the inner clad end, and it was felt that this could be the cause of the cracking. Similar samples were then made, using the same weld power settings but with the fillet-to-inner clad end distance increased to 0.875 and 2.5 inches. In these cases excessive heatup was not observed, and all of these samples passed the liquid penetrant inspection with zero defects. This confirmed recent hardware experience on successful welding of modules with the 0.875 and 2.5 inch distances and with inner clads made from the same heat of Inconel 718 as those in which the defects occurred.

~~CONFIDENTIAL~~

CONFIDENTIAL

Figure 3-2. Typical Liquid Penetrant Defect Indications in Inconel 718 Inner Clad/304 Stainless Steel End Cap Weld Specimen

CONFIDENTIAL

~~CONFIDENTIAL~~

In order to prevent heat buildup when welding at the 0.185-inch distance, samples were welded with a close-fitting copper chill plug in the inner clad bore. These welds, again performed at the same power settings, also passed the liquid penetrant inspection with zero defects. It thus appears that, if the short distance cannot be avoided in future designs, satisfactory welds can be made by utilizing a close-fitting copper chill plug in the inner clad bore.

Metallographic analysis of the defective sample welds showed that the cracking was intergranular in nature and that the cracks followed paths of what appears to be incipient melting along the grain boundaries. The crack locations, weld metal/base metal transition zones, and incipient melting paths in typical samples are shown in Figure 3-3.

Figure 3-4 shows corresponding regions in short-distance samples welded with a copper chill plug. The much narrower weld metal/base metal transition zone and very-limited-extent incipient melting are obvious in these photographs.

The results of the above work indicate that close-fitting copper chill plugs must be used in the module bore when the fillet-to-inner clad end distance is small (say ~ 0.4 inch). More preferably, however, this distance should be maintained at 0.8 inch or greater in future designs.

Hydrogen Purge-Vacuum Degassing Process

The standard process defined in Phase II-B was used throughout Phase II-C. A new equipment system featuring improved automatic cycle controls and capacity for much larger modules was designed and built. Checkout of the equipment will be accomplished in the next contract year.

Module Compaction Processes

Cold isostatic compaction at 50,000 psi was performed on all Phase II-C modules following seal welding of the module degassing tubes at the end of the purge-degassing process. Following this, all modules were additionally compacted in an elevated temperature, high pressure isostatic compaction process in the WANL 30,000-psi helium autoclave facility.

~~CONFIDENTIAL~~

CONFIDENTIAL

50X

Fusion Zone Centerline

250X

Figure 3-3. Crack Locations, Weld Metal/Base Metal Transition Zone, and Heavy Incipient Melting in Heat Affected Zone Grain Boundaries in Inconel 718 Inner Clad/304 Stainless Steel End Cap Weld Specimens

CONFIDENTIAL

CONFIDENTIAL

50X

Fusion Zone Centerline

250X

Figure 3-4. Reduced Transition Zone and Very Limited Incipient Melting in Heat Affected Zone Grain Boundaries in Inconel 718 Inner Clad/304 Stainless Steel End Cap Specimens Welded with Copper Chill Plug

CONFIDENTIAL

~~CONFIDENTIAL~~

Compaction parameters of 650°C and 20,000 psi were used for all modules except TEM-9S S/N-2 and TEM-9U S/N-15 and -16, which were compacted at 750°C and 30,000 psi.

Only one significant problem occurred during hot isostatic compaction in Phase II-C. Upon removing TEM-9U S/N-12 from the autoclave following its 650°C - 20,000 psi cycle, helium was found to be leaking out of the module through the Type 304 stainless steel end cap at the negative end. This component was removed, sectioned, polished, and examined metallographically. As shown in Figure 3-5, a series of oxide stringers was found running completely through the end wall section of the end cap. Stringer formations of this type are quite common in Type 316 stainless steel, and as a result the standard TEM module end cap material was changed from Type 316 to Type 304 about 2 years ago.

To determine whether an accidental material substitution had been made, an X-ray fluorescence analysis was performed on the end cap and on samples of certified 316 and 304 stainless steel from the module materials inventory. On this basis, the TEM-9U S/N-12 end cap material was definitely identified as Type 304 (the correct grade). This led to the conclusion that a rare material defect had been encountered, i.e., massive stringer formation in Type 304 stainless steel of a type that cannot be dealt with using existing quality control procedures.

All dimensional and volumetric measurements and room temperature electrical tests indicated that the TEM-9U S/N-12 module was completely compacted and normal in every sense. It thus appeared that the end cap leak did not develop until compaction of the module in the cycle was essentially complete. On this basis, the module was released for normal static testing.

~~CONFIDENTIAL~~

CONFIDENTIAL

Astronuclear
Laboratory

Figure 3-5. TEM-9U S/N-12 Negative End Cap Showing Oxide Stringers Penetrating Wall,
As-Polished, 50X

CONFIDENTIAL

3-11

~~CONFIDENTIAL~~

C. TEST RESULTS

Thirty-three modules were endurance tested during Phase II-C. Of this number, fifteen were fabricated with barriers or non-ferrous conductor rings. A TEGS-3P non-power producing materials experiment continued on test at $\bar{T}_H = 1300^\circ\text{F}$ (704°C).

Endurance testing of three high voltage standard length modules continued during this phase of the program. These three modules along with six other standard 38-couple modules on test have TEGS-3P material in the module p-legs. Three non-barrier modules were operated satisfactorily during the past year in separate legs of the WANL liquid metal loop system.

TEM-1 Module Performance

The first TEM module built in the Compact Converter Program, TEM-1 S/N-1, is continuing in its fourth year of successful operation. Since being placed on test in October of 1965, this module has accrued 35,850 continuous hours of matched load operation at an average hot clad temperature of 1000°F . The circuit efficiency data of this module are presented as a function of time at test conditions in Figure 3-6.

A summary of performance parameters recorded after completion of major testing milestones for TEM-1 S/N-1 is given in Table 3-1. As shown in the table, power output and circuit efficiency have decreased at a rate lower than 2 percent per year for the past 3 years.

It is very significant to note that this module, designed and fabricated before the causes of module degradation low circuit-to-clad resistance problems were identified, has operated in a very stable manner for the past 24,000 hours. Although many improvements have been incorporated into module designs and processing techniques since the fabrication of this module, TEM-1 S/N-1 continues to exhibit the long-term capabilities of the tubular thermoelectric module.

~~CONFIDENTIAL~~

Figure 3-6. TEM-1 S/N-1: Circuit Efficiency Versus Time on Test

~~CONFIDENTIAL~~

TABLE 3-1

TEM-1 S/N-1 PERFORMANCE SUMMARY

Time on Test	Open Circuit Voltage (Volts)	Internal Resistance (Milliohms)	Power Output (Watts)	Circuit Efficiency (Percent)
BOL	5.70	92.2	88.1	5.56
1 Month	5.52	115.3	66.1	4.54
1 Year	5.86	152.5	56.3	4.04
2 Years	5.95	158.7	55.8	3.99
3 Years	5.98	163.7	54.6	3.94
3.7 Years	6.07	170.4	54.0	3.89

TEM-9C Module Performance

TEM-9C series modules were fabricated with two-piece (radially segmented) thermoelectric washers. TEGS-2P material was used in both segments of the p-leg and TEGS-3N/TEGS-2N segments were incorporated in the n-leg. The segmenting is done to more effectively match the thermoelectric material to the temperature range in which each portion of the segmented washer operates. Two TEM-9C series modules continued on test during Phase II-C.

TEM-9C S/N-2, the first TEM-9 series module placed on life test, successfully completed over 2 years (20,665 hours) of operation under open circuit test conditions during Phase II-C. This module was tested in a static test stand with the input power and average cold clad temperature maintained at constant levels. Due to degradation, the average hot clad temperature increased from 1000°F (538°C) at BOL to the most recent level of 1043°F (562°C). This phenomenon was common to all non-barrier modules incorporating TEGS-2P material in conjunction with iron conductor rings. The performance trends of TEM-9C S/N-2 are presented in Table 3-2. After the first month of testing, increases in open circuit voltage tended to offset increases in module internal resistance, resulting in an efficiency degradation

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

rate of only 0.2 percent (absolute) per year. The rapid initial reduction in power output is a result of the interaction between the TEGS-2P material and the inner iron conductor ring. The module was eventually removed from test in order to free testing facilities for more recent modules.

TABLE 3-2

TEM-9C S/N-2 PERFORMANCE TREND SUMMARY

<u>Time on Test</u>	<u>Circuit Efficiency (Percent)</u>	<u>Open Circuit Voltage (Volts)</u>	<u>Internal Resistance (Milliohms)</u>
BOL	5.80	5.32	73.2
1 Month	5.05	5.75	105.4
1 Year	4.80	6.38	141.0
2 Years	4.60	6.52	156.3
2.3 Years	4.50	6.47	158.3

TEM-9C S/N-9, also on test during Phase II-C, was tested under static test conditions for 8328 hours before being removed from test and installed into one leg of the WANL liquid metal loop system. An additional 6017 hours were accrued by this module in the loop system.

Figure 3-7 presents circuit efficiency data accrued by these two modules. Similar data from two additional TEM-9C series modules are presented to illustrate the high degree of performance reproducibility achieved in these modules.

The increase in efficiency observed in TEM-9C S/N-9 after installation in the liquid metal loop system is related to uncertainties in determining circuit heat throughput rates during testing under dynamic conditions.

~~CONFIDENTIAL~~

612969-5B

Figure 3-7. TEM-9C Series Module Data: Circuit Efficiency Versus Time at Test Conditions

TEM-9E and TEM-9I Module Performance

TEM-9E series modules were built to investigate processing and performance characteristics of modules made with one-piece TEGS-2N and 2P lead telluride washers. In all other respects the TEM-9E series modules are identical to the TEM-9C series modules. TEM-9I series modules were the first modules built with an Inconel 718 inner clad replacing the duplex 316 stainless steel/Inconel X-750 inner clad assembly of all previous modules. In all other respects the TEM-9I series modules were fabricated identically to the TEM-9E series modules. The use of the single-piece Inconel 718 inner clad resulted in an improved design from a fabrication standpoint but had no measurable effect on overall performance levels.

Since TEM-9E and -9I series modules were fabricated in a nearly identical manner, life test circuit efficiency data from these modules can be compared to demonstrate reproducibility. Although none of these modules contains a diffusion barrier (hence, all have experienced considerable efficiency degradation during test), the good reproducibility of operation of these modules with similar thermoelectric circuits is continuing throughout extended life testing, as shown in Figure 3-8. The TEM-9E and -9I life test circuit efficiency data fall in a narrow band.

TEM-9E S/N-1 and TEM-9I S/N-1 were static tested for 8103 and 6180 hours, respectively, before being placed on test in the WANL liquid metal loop system along with TEM-9C S/N-9. These modules accrued an additional 5500 hours of loop testing with no change in performance trends established during static testing. Circuit efficiency, internal resistance, and open circuit voltage data from the two modules on test in the liquid metal loop system have remained within the band of data formed by the modules on static test.

TEM-9I S/N-4 was removed from test after 2900 hours, delivered to Boeing Corporation for a series of tests, and subsequently restarted at WANL with no adverse effect on module performance. This module accrued a total of 8175 hours at static test conditions prior to being removed from test to provide testing facilities for additional modules.

~~CONFIDENTIAL~~

612969-6B

Figure 3-8. TEM-9E and -9I Series Module Data: Circuit Efficiency Versus Time at Test Conditions

~~CONFIDENTIAL~~

TEM-9E S/N-2, which remains on test in a static test stand at WANL, has accrued a total testing time of 22,919 hours. This module, currently operating at a circuit efficiency level of 4.4 percent, will remain on test to demonstrate long-term operating capabilities of the tubular module.

TEM-9Q Module Performance

TEM-9Q series modules were built to determine the effect of using TEGS-3P thermoelectric material on module degradation. Although TEGS-2P material has a higher figure of merit (hence, higher efficiency) than the 3P material, an iron/TEGS-2P lead telluride reaction was isolated in Phase II-B as the chief cause of module degradation. TEGS-3P thermoelectric material, however, is highly stable in an iron environment at elevated temperatures. Therefore, TEGS-3P material was investigated as an alternate material for high temperature testing.

Seven TEM-9Q series modules were built and tested under the Compact Converter Program. Six of these modules were on test during Phase II-C. All modules followed the design of TEM-9I, except that TEGS-3P thermoelectric material was used in place of TEGS-2P material. TEM-9Q S/N-7 differed from the other six modules since it was fabricated with tungsten inner and molybdenum outer conductor rings replacing iron.

Life test circuit efficiency data from the first four TEM-9Q series modules are presented in Figure 3-9. These data represent testing at average hot clad temperatures ranging from 1000 to 1200°F (538 to 649°C), with the average cold clad temperature held at 392°F (200°C) for all modules.

After 16,367 hours of static testing at $\bar{T}_H = 1000^\circ\text{F}$ (538°C), TEM-9Q S/N-1 exhibited a circuit efficiency of 5.4 percent compared to a BOL efficiency of 5.7 percent. TEM-9Q S/N-2, on test for 15,694 hours at $\bar{T}_H = 1100^\circ\text{F}$ (593°C), experienced a circuit efficiency drop from the BOL level of 6.0 percent to 5.6 percent. Both of these modules continued throughout the testing time to exhibit a rate of module degradation far lower than that of the non-barrier TEGS-2P material module tested at $\bar{T}_H = 1000^\circ\text{F}$. Similarly, S/N-3, tested at $\bar{T}_H = 1150^\circ\text{F}$ (621°C), and S/N-4, tested at $\bar{T}_H = 1100^\circ\text{F}$ and 1200°F (593°C and 649°C), experienced very little reduction in circuit efficiency during life testing.

Figure 3-9. TEM-9Q Series Data: Circuit Efficiency Versus Time at Test Conditions

~~CONFIDENTIAL~~

TEM-9Q S/N-5, -6, and -7 were tested at operating temperatures simulating those of a typical two-loop reactor system: $\bar{T}_H = 1125^\circ\text{F}$ (607°C) and $\bar{T}_C = 570^\circ\text{F}$ (299°C). Life test circuit efficiency data from these three modules are presented in Figure 3-10. The highly stable and reproducible performance of these modules fabricated with TEGS-3P thermoelectric material is evident from the figure. The substitution of tungsten and molybdenum for iron in TEM-9Q S/N-7 conductor rings has had no effect on performance levels and degradation trends for this module.

TEM-9AE series modules were built to demonstrate the capability of fabricating and successfully testing modules with high voltage to power ratios. The axial thicknesses of the lead telluride and mica washers of TEM-9AE modules are compared to the TEM-9Q design in Table 3-3.

TABLE 3-3

A COMPARISON OF LEAD TELLURIDE AND MICA WASHER THICKNESSES FOR TEM-9Q AND TEM-9AE SERIES MODULES

<u>Module</u>	<u>Axial T/E Washer Thickness (Inches)</u>	<u>Axial Mica Thickness (Inches)</u>
TEM-9Q	0.090	0.005
TEM-9AE S/N-1	0.030	0.0015
TEM-9AE S/N-2	0.030	0.005
TEM-9AE S/N-3	0.050	0.005

Life test circuit efficiency data for the three TEM-9AE series modules are presented in Figure 3-11. All of these modules were initially tested at nominal clad temperatures, $\bar{T}_H = 1000^\circ\text{F}$ (538°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C). The overall effects of varying thermoelectric and mica washer axial thicknesses are readily apparent in this figure. TEM-9AE S/N-1, with the highest BOL efficiency, 6.07 percent, was fabricated with the least amount of mica (216 washers of 0.0015-inch thickness). TEM-9AE S/N-3, with a BOL efficiency of 5.6 percent, was fabricated with 126 mica washers of 0.005-inch thickness. In the TEM-9AE S/N-3

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 3-10. Life Test Circuit Efficiency Data for TEM-9Q S/N-5, -6, and -7

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Figure 3-11. Circuit Efficiency of High Voltage Modules: TEM-9AE Series

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

design, then, the amount of mica is approximately twice that used for S/N-1 and half that for S/N-2. The circuit efficiency of S/N-3, as a result, was midway between the BOL levels of the other two TEM-9AE series modules.

Figure 3-11 shows that TEM-9AE S/N-1 has exhibited measurable degradation during the first 1500 hours of operation, whereas the later two TEM-9AE series modules have operated in a completely stable manner. Since all of these modules employ TEGS-3P material, very low degradation rates such as those measured for TEM-9Q series modules were anticipated. A further examination of TEM-9AE S/N-1 data revealed that the primary cause for the reduction in circuit efficiency of this module was steadily increasing internal resistance. No module employing TEGS-3P material had previously displayed an increase in internal resistance during testing at $\bar{T}_H = 1000^\circ\text{F}$ (538°C).

During the processing of TEM-9AE S/N-1, considerable difficulty was encountered in the hydrogen purge cycle for this module. This problem was not encountered in previous TEM-9 series modules. It is felt that contaminants (such as oxygen and water vapor) were not removed during the purging cycle. These contaminants, in turn, can have deleterious effects on module performance, acting as catalysts to chemical reactions or participating in reactions which affect the properties of the thermoelectric material.

The resistance of this module to hydrogen flow prompted an effort to ensure that this problem was remedied in later modules. Minor tolerance adjustments were made in the end closure region of the module to allow the free passage of hydrogen through the end closures and into the circuit region of the module.

Performance trends of these TEM-9AE series modules are very similar to those of the TEM-9Q series modules, fabricated with the same types of lead telluride. After 1750 hours of operation at the initial temperature conditions, TEM-9AE S/N-3 was shifted to $\bar{T}_H = 1125^\circ\text{F}$ (607°C) and $\bar{T}_C = 570^\circ\text{F}$ (299°C). The latter temperatures simulate those of a typical two-loop reactor system. These data are directly comparable to data from TEM-9Q S/N-5, S/N-6, and S/N-7 discussed previously. Although a reduction in efficiency, power, and voltage level resulted from the change in operating conditions, these effects had been predicted by per-

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

formance calculations and are a direct result of the reduction in operating radial temperature drop. No increase in degradation rate was observed despite the increase in operating temperature level of TEM-9AE S/N-3.

TEM-9U Module Performance

Because of the high performance capabilities of TEGS-2P material, a major effort has continued into Phase II-C of the Compact Converter Program to develop conductor ring barrier materials and configurations for use in conjunction with TEGS-2P lead telluride. Tungsten foil barrier placed between the iron conductor rings and the thermoelectric washers reduced initial degradation rates by an order of magnitude. Additional reduction in degradation, especially for high temperature operation, has been achieved by replacing the inner conductor ring with molybdenum or tungsten.

TEM-9U S/N-1 was designed and fabricated during Phase II-B as a single-piece (TEGS-2N/2P) washer module identical in every respect to TEM-9I series modules except for a 0.001-inch tungsten barrier placed between the lead telluride washer and the iron conductor ring at each module hot junction. This junction foil was incorporated as a diffusion barrier to combat the iron/TEGS-2P lead telluride reaction isolated in Phase II-B as the chief cause of module degradation.

The significant difference between the operation of TEM-9U S/N-1 and other single-piece (TEGS-2N/2P) washer modules is that the TEM-9U module evidenced almost no measurable reduction in efficiency during the first 500 hours of operation, the time period in which other modules containing TEGS-2P material degrade most rapidly. TEM-9U S/N-1 accrued a total of 11,420 hours of successful static testing and was subsequently removed from test in February 1969 for destructive examination. In Figure 3-12 life test circuit efficiency data for TEM-9U S/N-1 are presented along with that of TEM-9U S/N-4 and S/N-5, tungsten foil barrier modules tested during Phase II-C at $\bar{T}_H = 1000^\circ\text{F}$ (538°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C). These efficiency data are compared with similar data from a non-barrier module, TEM-9I S/N-2, to illustrate the effects of the diffusion barrier on module performance. The effect of the

~~CONFIDENTIAL~~

Figure 3-12. Comparison of Barrier With Non-Barrier Module Static Test Circuit Efficiency Data for 1000°F Operation

tungsten foil barrier in reducing module degradation rates is evident in Figure 3-12. After 10,000 hours of testing, TEM-9U S/N-1 exhibited an efficiency level 1 percent higher (5.9 percent compared to 4.9 percent) than that of TEM-9I S/N-1.

Fabrication of two additional TEM-9U series modules, S/N-4 and S/N-5, was identical to that of the first TEM-9U series modules except for the addition of tungsten foil barriers incorporated at the cold junction of the later modules. The inner foil liners were designed to permit overlapping to eliminate the gaps at the ends of the foil, through which iron diffused quite extensively.

After 6932 and 6592 hours of operation with constant input power at open circuit conditions, respectively, TEM-9U S/N-4 and -5 exhibited an extremely low rate of efficiency degradation, as seen in Figure 3-12. However, an examination of internal resistance and open circuit voltage data indicates that the degradation was not completely eliminated. Both of these parameters have been observed to be increasing linearly with time. Both of these modules closely reproduced the performance of TEM-9U S/N-1.

A subsequent TEM-9U series module, S/N-16, was fabricated in Phase II-C, identical to S/N-4 and S/N-5, with the exception that a solid tungsten inner conductor ring replaced the iron ring/tungsten foil assembly. This design eliminates completely the possibility of iron/lead telluride contacts near the hot junction. In addition, the Phase II-C module was gas-pressure-sintered at 30,000 psi to ensure proper compaction.

After 4940 hours of static testing at the nominal temperatures of $\bar{T}_H = 1000^\circ\text{F}$ (538°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C), TEM-9U S/N-16 displayed a circuit efficiency of 5.8 percent. Circuit efficiency data for this module are presented in Figure 3-12. It can be seen that S/N-16 data fall within the band of data formed by other TEM-9U modules tested at $\bar{T}_H = 1000^\circ\text{F}$. Since this module did not contain the newly designed conductor ring fix to prevent the interaction of n- and p-type materials, it was expected to degrade at the same rate as the other TEM-9U modules tested at $\bar{T}_H = 1000^\circ\text{F}$.

~~CONFIDENTIAL~~

Two-Piece Conductor Ring Module Performance

During Phase II-C, as a result primarily of Seebeck probe experiments performed during destructive examination of various modules, the underlying cause of the residual performance degradation was isolated. The p-type lead telluride was found to be interacting with adjacent n-type washers predominantly in the vicinity of the butt-joint between the large mica insulating washers and the inner conductor rings. A stepped conductor ring configuration was subsequently designed to entrap the mica insulators and eliminate the possibility of assembly gaps that allow contact of the p- and n-type lead telluride washers. Details of the new design were presented and discussed in Section I of this report.

The first module fabricated with the stepped conductor ring design was TEM-9U S/N-22. This module incorporates a two-piece iron/tungsten conductor ring assembly. In this design the p-type washer contacts only the tungsten step, whereas the n-type washer contacts the iron. Materials experiments have shown GE-NL n-type material to be compatible with iron.

Heatup data from this module, presented and discussed in Section I of this report, showed that the module had a power output level approximately 10 percent higher than predicted, primarily as a result of a lower than predicted internal resistance. Figure 3-13 presents circuit efficiency data from TEM-9U S/N-22 along with similar data from two Phase II-B state-of-the-art modules. All of these modules were tested at $\bar{T}_H = 1100^\circ\text{F}$ (593°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C) to measure performance stability at elevated temperatures. The Phase II-B modules, TEM-9U S/N-2 and TEM-9U S/N-11, were fabricated similarly to TEM-9U S/N-1 and TEM-9U S/N-16, respectively, both discussed above.

After 1350 hours of testing, TEM-9U S/N-22 was subjected to a series of five thermal cycles. As can be seen, the cyclic tests had no measurable effect on the module performance level or rate of degradation. The degradation observed in TEM-9U S/N-22 is not presently understood. After 3700 hours of operation, TEM-9U S/N-22 is operating at an efficiency level of 7.0 percent.

~~CONFIDENTIAL~~

Figure 3-13. High Temperature Circuit Efficiency Data from TEM-9U Series Modules

~~CONFIDENTIAL~~

An additional split conductor ring module, TEM-9U S/N-19, was designed, fabricated, and placed on test at $\bar{T}_H = 1100^\circ\text{F}$ (593°C) and $\bar{T}_C = 392^\circ\text{F}$ (200°C) during this phase. This module is identical to TEM-9U S/N-22 except that the stepped inner conductor rings were fabricated of molybdenum. This configuration precludes the possibility of any iron-lead telluride interaction within the module. Heatup data from this module are presented and discussed in Section I of this report.

Circuit efficiency data from TEM-9U S/N-19 are presented in Figure 3-13 along with similar data from modules tested at the same temperatures and discussed previously. Because of the high degree of performance stability achieved by this module, degradation rates for this design are extremely difficult to infer. In 3359 hours of testing power output has fallen from the beginning-of-life level of 119 watts to 116 watts. Circuit efficiency has dropped only slightly from 7.39 percent to 7.15 percent. These reductions are smaller in magnitude than the accuracy to which the measurements can be made. Nonetheless, a statistical analysis of circuit efficiency data from this module indicates an overall degradation rate of 8 percent per 10,000 hours for testing at $\bar{T}_H = 1100^\circ\text{F}$. This achievement represents a substantial advancement in tubular module technology as a result of the Phase II-C effort.

Development of more perfect means to isolate n-type and p-type lead telluride offers the potential of degradation free performance at operating temperatures above $\bar{T}_H = 1200^\circ\text{F}$. Completely stable performance of materials study modules tested at peak temperatures above 1250°F (discussed in Section II of this report) afford data to substantiate this high temperature operation of the tubular module design. Various schemes for achieving complete isolation are presently being investigated.

TEM-10 Module Performance

During Phase II-C of the Compact Converter Program, a complete energy conversion system incorporating a simulated isotope heat source coupled to a tubular module (TEM-10 S/N-3) and using a Westinghouse developed heat pipe and planar radiator was designed and placed on test. This system, described in detail in Section I of this report, was the first of its type to successfully utilize a heat pipe in an energy conversion system.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

An overall beginning-of-life system efficiency level of 5.38 percent was realized with the module operating at $\bar{T}_H = 1001^\circ\text{F}$ and $\bar{T}_C = 378^\circ\text{F}$. The heater was set at a 2200-watt level and the module output power was measured at 118.5 watts. Hence, this efficiency level includes all system losses.

TEM-10 S/N-3 continued on test in the heater/heatpipe/module/planar radiator test assembly where it has accrued a total of 6900 hours at constant input power and constant electrical load conditions. Unlike modules on static test, no attempt was made in testing this system to ensure constant module cold side temperatures. Variations in ambient temperature conditions in the laboratory induce similar changes in the module cold side temperatures. The system experienced four heatups and three shutdowns. Figure 3-14 presents power output data recorded during this test. Presently, the system is operating at an efficiency level of 4.4 percent and a power output level of 96 watts. During the 6900 hours of testing the system has undergone four thermal cycles caused by laboratory power failures.

The results of this test demonstrate the feasibility of operating a tubular module coupled to an external heat source using a heat pipe. Incorporation of module design improvements made during Phase II-C would result in a system with increased operating temperature capabilities, increased efficiency levels, and increased performance stability over the present system. Such a system could be used effectively in many applications.

~~CONFIDENTIAL~~

Figure 3-14. Electrical Power Output Versus Time on Test Recorded for the TEM-10/Heat Pipe/Radiator System

D. SUMMARY

The first TEM module built in the Compact Converter Program, TEM-1 S/N-1, is continuing in its fourth year of successful operation and has accrued 35,850 hours of continuous matched load operation at life test conditions. Although many improvements have been incorporated in module design and processing since the fabrication of this module, TEM-1 S/N-1 continues to exhibit the long-term capabilities of the tubular thermoelectric module. Power output and circuit efficiency have decreased at rates lower than 2 percent per year for the past three years of operation at $\bar{T}_H = 1000^\circ\text{F}$ and $\bar{T}_C = 392^\circ\text{F}$.

All Phase II-A and Phase II-B modules tested during Phase II-C have continued to operate with performance trends established during earlier phases of the program. In addition, the high degree of performance reproducibility in identically fabricated modules has continued over long periods of testing.

During Phase II-B, a major cause of module performance degradation was isolated and identified as an interaction between TEGS-2P lead telluride and iron at the module hot junctions. Barrier configurations were developed which proved very effective in reducing this degradation during $\bar{T}_H = 1000^\circ\text{F}$ operation. However, during Phase II-C another degradation mode prevalent during high temperature testing of barrier modules was observed. This mode was associated with an interaction between p-type and n-type lead telluride.

An effective means to control this interaction was developed. A design fix was incorporated into several Phase II-C modules, utilizing a stepped conductor ring configuration which eliminates assembly gaps during fabrication. One of the primary objectives of the testing program during Phase II-C was to evaluate the effectiveness of this design fix for operation at high temperatures.

One module, TEM-9U S/N-19, fabricated with a two-piece molybdenum/tungsten inner conductor ring assembly, has operated for 3359 hours at an average hot clad temperature of 1100°F . The reductions in power output and circuit efficiency data for this module during life testing have been less than the accuracy to which these parameters can be measured. A statistical evaluation indicates a degradation rate of 8 percent per 10,000 hours associated with this module.

~~CONFIDENTIAL~~

Two TEM-9AE series modules designed with thermoelectric washers as thin as 0.030 inch to achieve high voltage to power ratios have remained on test during Phase II-C. Test data indicate no performance variations as a result of this design change.

In addition, an energy conversion system comprised of a simulated isotope heat source coupled to a TEM-10 series module (S/N-3) using a heat pipe was tested throughout Phase II-C. Performance data from this system exhibit the potential of such a system in a high efficiency conversion system.

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

Astronuclear
Laboratory

APPENDIX A
NOMENCLATURE

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NOMENCLATURE

α	Seebeck Coefficient (Volts/ $^{\circ}$ F)
$\bar{\alpha}$	Effective Seebeck Coefficient (Volts/ $^{\circ}$ F)
BOL	"Beginning-of-Life" in reference to the first data point taken at life test conditions
$^{\circ}$ C	Degrees Centigrade
η	Circuit Efficiency, defined as $\frac{100 P_e}{Q_{ML}}$ (in percent)
η_T	Overall Efficiency, defined as $100 P_e / (Q_H + 2Q_G)$ (in percent)
η_c	Carnot Efficiency, defined as $100 (1 - \frac{\bar{T}_C}{\bar{T}_H})$ (in percent); temp. in $^{\circ}$ K
η_d	Device Efficiency, defined as $\frac{100}{\eta_c}$ (in percent)
$^{\circ}$ F	Degrees Fahrenheit
GE-NL	Code Name for Single-Phase n-type Heat Telluride produced by General Electric, doped at level of TEGS-2N.
HEP	High Efficiency Prototype: a code selected by WANL to identify one of the thermoelectric module designs which was designed and tested by WANL prior to beginning the Compact Thermoelectric Converter Program.
ID	Inside Diameter
OD	Outside Diameter
$^{\circ}$ K	Degrees Kelvin
k	Thermal Conductivity, watts/cm/ $^{\circ}$ K
k_n	Thermal Conductivity of n-type Thermoelectric Material, watts/cm/ $^{\circ}$ K

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

NOMENCLATURE (CONTINUED)

k_p	Thermal Conductivity of p-type Thermoelectric Material, watts/cm/ $^{\circ}$ K
P_e	Electrical Power Output, watts
P_o	Electric Power Output, corrected for constant clad temperature tests
Q_G	Guard Heater Power (watts)
Q_H	Main Heater Power (watts)
Q_E	Power Loss to End Closure (watts)
Q_T	Power Throughput to Module Thermoelectric Circuit ($Q_T = Q_H - Q_E$) (watts)
Q_{ML}	Power Throughput to Module Thermoelectric Circuit Required at Matched Load (watts)
ρ	Electrical Resistivity, ohms-cm
ρ_n	Electrical Resistivity of the n-type Thermoelectric Material, ohms-cm
ρ_p	Electrical Resistivity of the p-type Thermoelectric Material, ohms-cm
ρ_{intf}	Electrical Interface Contact Resistivity between the Thermoelectric Material and the Electrical Conductor, ohms-cm ²
TEGS-2P	3M Company Code Name for Sodium Doped Lead-Telluride
TEGS-3P	3M Company Code Name for Lead-Tin-Telluride Containing Manganese and Sodium
TEGS-2N	3M Company Code Name for Lead Iodine Doped Lead-Telluride
TEGS-3N	3M Company Code Name for Lead-Telluride with a Higher Lead Iodide Dopant Concentration than Used in the 2N Material
n-Type	Designation given to a material with an excess of negative charge carriers (electrons)
p-Type	Designation given to a material with an excess of positive charge carriers (holes)
R	Radius (in.)
R_c	Resistance Measured from Electrical Circuit-to-Clad (ohms)

~~CONFIDENTIAL~~

NOMENCLATURE (CONTINUED)

R_i	Inside Radius (in.)
R_o	Outside Radius (in.)
$^{\circ}R$	Degrees Rankine
R_g	Internal Resistance of a Module (ohms)
R_L	Load Resistance Applied to Module (ohms)
T	Temperature
$\bar{T}$	Average Temperature defined as $\frac{T_H + T_C}{2}$
$\bar{T}_C$	Mean Cold Side Temperature
$\bar{T}_H$	Mean Hot Side Temperature
$\Delta\bar{T}$	Mean Hot side to Cold Side Radial Temperature Drop Across Module
ΔT_H	Axial Temperature Drop on the Hot Side of the Module
ΔT_C	Axial Temperature Drop on the Cold Side of the Module
T/E	Thermoelectric
TI	Thermal Impedance
TEM	Thermoelectric Module: a code selected by WANL to identify all tubular modules to be fabricated under the Compact Thermoelectric Converter Program
V_{oc}	Open-Circuit Voltage (volts)
V_L	Voltage Measured at Module Terminals with Load Resistor R_L Applied (volts)
V_{ML}	Voltage Measured at Module Terminals with Load Resistance $R_L = R_G$ (Matched Load) Applied (volts)
$V_{oc, ML}$	Open Circuit Voltage at Matched Load Heat Throughput Conditions $V_{oc, ML} = 2 V_{ML}$
I_L	Current Drawn Through Load Resistor R_L

~~CONFIDENTIAL~~

APPENDIX B

SUMMARY OF MODULE DESIGN DEVELOPMENT

~~CONFIDENTIAL~~

CONFIDENTIAL

TEM Series	Series Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
1	1, 2, 4	2-piece washers of standard n- and p-type PbTe, Inconel X-750 inner clad	Rotary swage; GPS at 750°C/10,000 psi with bore open	Demonstrate state-of-the-art of modules in Phase I, using parts remaining from another program.	Testing initiated in Phase I continuing into Phase II-B: S/N-1 continuing at 35850 hours; S/N-2 terminated after 10,000 hours for destructive examination; S/N-4 terminated at 5735 hours for destructive examination.
2*	1, 2	Same as TEM-1	Rotary swage; GPS at 750°C/10,000 psi with bore plugged	Investigate influence of plugged bore during hot autoclave processing (TEM-1 modules processed with bores open to hot autoclave pressure).	Non-destructive examination indicated no measurable effect. Modules removed from program.
3*	1, 2, 3, 4	Same as TEM-1	Same as TEM-1	Investigate effect of hydrogen heat treatment of PbTe powder prior to washer fabrication.	S/N-1 tested for 2100 hours, then sent to JPL for test system development and module evaluation. After 2400 test hours at JPL, module returned to WANL; 1600 additional test hours accumulated. Module held in bond room for program developments. S/N-2, -3, -4 destructively examined in Phase I to evaluate effects of processing.
4*	1	Same as TEM-1	40,000 psi, room temperature hydraulic compaction, followed by rotary swage; GPS at 650°C/7500 psi with bore open	Evaluate compaction and performance of modules processed as noted.	Dimensional, electrical, and performance characteristics verified lack of full compaction, indicating that substantially higher pressures would be required for modules hot autoclaved at 650°C. Module destructively examined after short test period to evaluate initial performance.
4A	1, 2	Same as TEM-1, except ends slightly redesigned to reduce stiffness.	45,000 psi, hydraulic compaction; GPS at 750°C/7500 psi with bore open	Evaluate effects of more flexible end design and eliminate swaging on BN cracking and module performance.	S/N-1 was removed from test at 8581 hours to create test stand availability for a new module design. S/N-2 was destructively examined after processing.
5	1	Essentially a TEM-1 thermoelectric circuit with module ends completely redesigned to reduce stiffness, and several seal experiments incorporated between the circuit and inner clad.	45,000 psi, hydraulic compaction; GPS at 750°C/10,000 psi with bore open	Module experiment designed to evaluate the effectiveness of seals for retarding lead movement. Evaluate more flexible ends with new electrical conductor rings.	Destructive examination used to select design features in TEM-6, -7, and -8 modules.
6	1, 2	Essentially a TEM-4A module with ends slightly redesigned to reduce stiffness and a metal barrier to prevent circuit-to-clad shorting inserted between dual inner BN insulating sleeves.	45,000 psi, hydraulic compaction; GPS at 750°C/10,000 psi with bore open	Module experiment designed to evaluate more flexible ends, effectiveness of metal barrier in preventing system shorts and performance loss due to extra interface.	Tooling problems caused metal barrier to be ineffective; however, initial performance was established. Metal barrier used as basis for TEM-7 and -8 designs. Both modules destructively examined.
7	1, 2	Redesigned TEM-5 type design except TEM-6 metal barrier used in place of sealing experiments	50,000 psi, hydraulic compaction; GPS at 750°C/10,000 psi with bore open	Module experiment designed for further evaluation of flexible end design with new style electrical end conductor rings.	S/N-1 was removed from test at 8321 hours to create test stand availability for a new module design. S/N-2 was performance tested for 382 hours after which the module was destructively examined.
7A	1	Same as TEM-7 modules without the metal barrier inserted between the inner BN insulating sleeves.	Same as TEM-7	Initial experiment using dual inner sleeves of BN to minimize shorting through lead-filled cracks.	Non-destructive examination indicated no improvement in resistance-to-cladding. Module removed from program.

*From another program

CONFIDENTIAL

TEM Series	Serial Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
B*	1, 2	Essentially a TEM-6 design	50,000 psi, hydraulic compaction, GPS at 650°C 15,000 psi followed by GPS at 750°C 10,000 psi with bore open	Initial experiment to achieve modules suitable for life testing without evidence of system shorting	Dimensional and electrical conditions indicated lack of full compaction after being autoclaved at 650°C. Accordingly the TEM-8 modules were autoclaved at 750°C. S/N-1 performance testing terminated at 2470 hours and the module was used for successful shock and vibration testing. Module being held in bond room for possible further use. S/N-2 was performance tested for 982 hours on a static test stand after which it was inserted into a NaK loop for additional testing. After having accumulated 8,588 hours of loop testing, and successfully withstanding severe thermal cycling tests, the module testing was terminated. The module is in storage
8A*	1, 2	TEM-8 modules, without the metal barrier inserted between the inner BN insulating sleeves.	45,000 psi, hydraulic compaction, GPS at 650°C/15,000 psi with bore open	Initial experiment to achieve modules suitable for life testing without evidence of shorting by autoclaving at reduced temperature	Although dimensional and electrical measurements indicated lack of full compaction, the operational characteristics of such modules were not well defined. Accordingly, both modules were placed on test. S/N-1 removed from test at 4190 hours and destructively examined. S/N-2 removed from test and delivered to JPL for test and evaluation
TEM-9 series Sets of modules essentially identical in design to investigate the effects of materials and processing changes on dimensional and performance characteristics. The baseline module within the TEM-9 series is the TEM-9C					
9	1, 2, 3	Same as TEM-9C	50,000 psi hydraulic compaction, processed at 750°C 10,000 psi with bore open	Demonstrate that the TEM-9C design processed at 750°C 10,000 psi, will exhibit same dimensional and shorting characteristics as prior designs similarly processed.	Destructive examination of all three modules showed reduced BN cracking but some massive lead penetration of BN experienced in previous module experiments.
9A	1	Same as TEM-9C except one-piece washers all of 2P material	50,000 psi hydraulic compaction, GPS at 750°C 10,000 psi with bore open	Confirmation that p-type material does not cause shorting, even when processed at 750°C. Investigation of performance characteristics of module with p-type material	Materials experiment module was tested at $T_H = 1000^\circ\text{F}$ for 5538 hours for evaluation of p-type material performance. Module is being stored in bond room.
9A	2	Same as TEM-9C except one-piece washers all of 2P material	50,000 psi hydraulic compaction, GPS at 650°C 20,000 psi with bore plugged	Investigate performance characteristics of a module with 2P material processed same as TEM-9C	Materials experiment module was tested 1600 hours at $T_H = 1000^\circ\text{F}$ followed by 2088 hours at $T_H = 1100^\circ\text{F}$. The module testing was terminated by 200 hours testing at $T_H = 1200^\circ\text{F}$ after which the module was stored in the bond room.
9A	3	Same as 9A S/N-1 except tungsten and molybdenum substituted for iron inner and outer conductor rings, respectively	Same as TEM-9A S/N-2	Investigate high temperature compatibility of TEGS-2P material with conductor rings	S/N-3 on test for 3585 hours at $T_H = 1200^\circ\text{F}$, $T_C = 392^\circ\text{F}$. No measureable increase in internal resistance.
9B	1, 2	Same as TEM-9C except n-type washers have reduced lead content	Same as TEM-9C	Investigate performance and shorting characteristics of modules made with reduced lead content material processed to 'preferred' cycle parameters	Destructive examination of S/N-1 revealed NaK penetration into module through a cladding defect, S/N-2 held in bond room
9B	3, 4	Same as TEM-9C except n-type washers have reduced lead content	Same as TEM-9C except GPS at 650°C 15,000 psi, S/N-3 bore open, S/N-4 bore plugged	Investigate reduced lead content material processed at 15,000 psi to determine if acceptable modules could be achieved, thereby relieving dependency on the single high-pressure autoclave or BMF	Processing completed. Both modules being held in bond room.
9C	1, 2	Essentially a TEM-1 module incorporating the more flexible ends developed in TEM-8, increased thickness of BN insulating sleeves and processed under the preferred conditions developed in Phase II-A	50,000 psi hydraulic compaction GPS at 650°C 20,000 psi, bore open	Baseline for comparison of modules in TEM-9 series and for evaluation of performance improvements due to the preferred process developed in Phase II-A, since thermoelectric circuits are essentially the same in all TEM modules	S/N-1 destructively examined. S/N-2 successfully accrued 20,665 hours of open circuit life testing at $T_H = 1000^\circ\text{F}$ and was removed to free test stands for newer module designs. Module is being held in storage.

*From another program

TEM Series	Serial Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
9C	3, 4	Same as above	50,000 psi hydraulic compaction GPS at 650°C 15,000 psi S/N-3 bore open S/N-4 bore plugged	Same as 9B S/N-3 and -4.	S/N-3 and S/N-4 tests have been terminated at 5,807 hours and 6,237 hours, respectively to provide testing space for more recently fabricated modules. Both modules being held in storage.
9C	5	Same as 9C S/N-1, -2 except shroud weld made on clad	50,000 psi hydraulic compaction GPS at 650°C. 20,000 psi bore plugged	Determine effects of clad weld on module performance	Analysis of heatup data indicates clad weld caused no module damage. Module being held in storage
9C	6, 8, 9, 10	Same as 9C S/N-1, -2	Same as 9C S/N-5	Same objectives as TEM-9C S/N-1 and -2 except these and all subsequent modules have bores plugged during GPS cycles.	TEM-9C S/N-6 testing was terminated after 6,212 hours of testing, which included three severe thermal shocks which did not change performance. TEM-9C S/N-9 on static test for 8328 hours, subsequently tested in liquid metal loop system for 6017 hours. S/N-8, S/N-9 and S/N-10 are being held in storage. TEM-9C S/N-6 has been sent to LASL for use in their heat pipe development program.
9C	7	Same as above	50,000 psi, hydraulic compaction only, no GPS	Investigate performance characteristics of a module known to be less than fully compacted	Performance test of this module, which was not gas-pressure-sintered, was terminated at 1,484 hours. The module is being held in the band room for program developments.
9D	1, 2	Same as TEM-9C except one-piece 2N and 2P washers	Same as TEM-9C S/N-5	Investigate processing and performance characteristics of modules made with one-piece PbTe washers.	S/N-1 was destructively examined after processing. S/N-2 was subjected to elevated isothermal testing for evaluation of material properties and is presently being held in band room.
9E	1, 2	Same as TEM-9C except one-piece 2N and 2P washers of reduced lead content	Same as TEM-9C S/N-5	Same as TEM-9D	TEM-9E S/N-1, on static test for 8103 hours, subsequently on test in liquid metal loop system for 6017 hours. S/N-2 static test continuing at 22919 hours. S/N-1 being held in band room.
9F	1, 2	Same as TEM-9C except outer clad thickness reduced to 0.051 inch from 0.147 inch.	Same as TEM-9C except S/N-1 first GPS at 650°C. 15,000 psi prior to standard GPS. 650°C/20,000 psi	Evaluate difference in compaction behavior of S/N-1 as a result of two GPS cycles. Compare S/N-1 and S/N-2 after 20,000 psi cycle, compare thin clad compaction against standard clad compaction.	After 20,000 psi GPS both modules showed similar compaction. S/N-1 showed significant additional compaction between 15,000 and 20,000 psi GPS cycles. Thin clad equivalent to 3,000 psi additional pressure relative to standard thickness clad. S/N-1 removed from test for destructive examination after 3,452 hours at a performance level indicating that reduced operating interface pressures do not adversely affect initial module operation. S/N-2 held in band room.
9I	1, 2, 3, 4, 5	Same as TEM-9C except one-piece 2N and 2P washers and Inconel 718 inner clad.	Same as TEM-9C S/N-5 except S/N-3, -4 were GPS successively at 650°C. 20,000 psi and 30,000 psi	Investigate processing and performance characteristics of modules having Inconel 718 inner clad.	S/N-1 static tested for 6180 hours. S/N-2 for 13913 hours. S/N-4 for 8175 hours. All at $T_H = 1000^\circ\text{F}$ and $T_C = 392^\circ\text{F}$. S/N-1 loop tested for additional 6017 hours. S/N-1 -2 and -4 are being held in band room. S/N-3 destructively examined. S/N-5 tested for 598 hours at $T_H = 1200^\circ\text{F}$ destructively examined.
9K	1	Same as TEM-9C except one-piece washers of all 2N material	Same as TEM-9C S/N-5	Investigate performance characteristics of a module with 2N material processed same as TEM-9C	Materials experiment module tested at $T_H = 1000^\circ\text{F}$ for 2,272 hours, following which the average hot side temperature, T_H , was raised to 1100°F for evaluation of n-type material performance in the higher temperature environment. After 2,416 hours of very stable operation at 1100°F , the temperature was again raised to 1200°F . Total testing time was 5,624 hours, after which the module was destructively examined.
9L	1, 2	Same as TEM-9I except 150 inch SS outer clad replaced with 0.020 inch Inconel	S/N-1 GPS cycle at 30,000 and S/N-2 at 20,000 psi	Evaluate compaction of module with thin Inconel 718 outer clad, provide elastic behavior of outer clad, minimize effect of additional compaction due to long-term operation, improve overtemperature behavior of cladding	TEM-9L S/N-1 being held in band room. TEM-9L S/N-2 was tested for 2,100 hours during which time it was subjected to thermal cycling tests. The module was destructively examined.

CONFIDENTIAL

Series	Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
9M	1	Same as TEM-9I except all washers are GE n-type material	Same as TEM-9C S N-5	Materials experiment to evaluate the properties of GE n-type material	Tested for 1314 hours at $\bar{T}_H = 1100^\circ\text{F}$, 572 hours at $\bar{T}_H = 1200^\circ\text{F}$ and 2738 hours at $\bar{T}_H = 1300^\circ\text{F}$. No increase of internal resistance due to module degradation or signs of circuit-to-clad shorting noted at any of above temperature levels. Module presently being held in bond room.
9M	2	Same as 9M S N-1 except tungsten and molybdenum substituted for iron inner and outer conductor rings, respectively	Same as TEM-9C S N-5	Materials experiment to evaluate high temperature compatibility of GE-n-type material with conductor rings.	Materials experiment module tested for 3723 hours at $\bar{T}_H = 1200^\circ\text{F}$ and $\bar{T}_C = 392^\circ\text{F}$. Negligible degradation in internal resistance.
9N	1	Same as TEM-9I except n-type washers of GE material (2P washers of 3M material)	Same as TEM-9C S N-5	Evaluate GE n-type material effect on module performance.	Tested for 1263 hours at $\bar{T}_H = 1000^\circ\text{F}$. Operation of module identical to that of TEM-9I series. Tested for 1589 hours at $\bar{T}_H = 1100^\circ\text{F}$ and 1325 hours at $\bar{T}_H = 1200^\circ\text{F}$. No circuit-to-clad shorting problems encountered and module was removed from test and has been sent to LASL for use in thin heat pipe development program.
9Q	1, 2, 3, 4, 5, 6	Same as TEM-9I except 3P material used in place of 2P material	Same as TEM-9C S N-5	Determine effect of 3P material on module degradation. Study high temperature capability of TEGS-3P material.	S/N-1, -2, and -3 tested at $\bar{T}_H = 1000^\circ\text{F}$, 1100°F and 1150°F , respectively. S/N-4 tested 1581 hours at $\bar{T}_H = 1100^\circ\text{F}$ and for 3193 hours at $\bar{T}_H = 1200^\circ\text{F}$. S/N-4 being held in storage. S/N-5 and -6 tested at $\bar{T}_H = 1125^\circ\text{F}$ and $\bar{T}_C = 570^\circ\text{F}$. S/N-1 and -2 remain on test, all other modules being held in bond room. 9Q S/N-1 circuit efficiency 5.40 percent.
9Q	7	Same as 9Q S/N-1 except tungsten and molybdenum substituted for iron inner and outer conductor rings.	Same as TEM-9C S/N-5	Determine compatibility of TEGS-3P material with new conductor rings.	S/N-7 tested for 3241 hours at $\bar{T}_H = 1125^\circ\text{F}$ and $\bar{T}_C = 570^\circ\text{F}$. Identical in performance to TEM-9Q S/N-5 and -6.
9S	1, 2	Same as TEM-9L except fabricated with redesigned end closure	Same as TEM-9C S/N-5	Determine effectiveness of redesigned end closure.	S/N-1 tested at $\bar{T}_H = 1000^\circ\text{F}$ and then destructively examined. Test data revealed a 50% reduction in end closure heat losses. S/N-2 held in bond room.
9S	3, 4	Same as TEM-9S S N-1 except fabricated with 0.050 inch stainless steel outer clad	Same as TEM-9C S N-5	Same as 9S S N-1	Both modules tested at $\bar{T}_H = 1000^\circ\text{F}$. S/N-3 BOL overall efficiency measured at 5.84 percent including end closure heat loss. S/N-3 replaced on test for thermal cycling and S/N-4 being held in bond room.
9T	1	Same as TEM-9I except 1.5-mil mica washers used replacing 5-mil washers	Same as TEM-9C S/N-5	Reduce mica shunt heat loss.	Highest efficiency for any module previously tested at $\bar{T}_H = 1000^\circ\text{F}$. Tested for 812 hours at $\bar{T}_H = 1200^\circ\text{F}$ and removed for destructive examination of mica washers.
9U	1	Same as TEM-9I except thin foil of tungsten barrier material inserted between 2P washer and inner iron conductor ring	Same as TEM-9C S/N-5	Reduce 2P washers - iron conductor ring interaction, thus reducing degradation.	Module was on static test for 11420 hours at $\bar{T}_H = 1000^\circ\text{F}$. Latest circuit efficiency 0.9 percent higher than TEM-9I modules (5.6 percent compared to 4.7 percent). Module being held in bond room.
9U	2, 3	Same as TEM-9U S N-1 except n-leg washers of GE n-type material	Same as TEM-9C S N-5	Determine effectiveness of foil barrier for high temperature operation	S N-2 was tested for 4080 hours at $\bar{T}_H = 1100^\circ\text{F}$. Module removed from test and is being held in bond room. S/N-3 removed from test for destructive examination after 978 hours at $\bar{T}_H = 1200^\circ\text{F}$.
9U	4, 5	Same as 9U S/N-2 except tungsten liner incorporated at cold junction. Gap in tungsten liner eliminated	Same as TEM-9C S/N-5	Determine effectiveness of tungsten foil with no gap at hot junction. Also to determine extent of module degradation at cold junction during hot autoclave cycle.	S/N-4 on test for 6932 hours at $\bar{T}_H = 1000^\circ\text{F}$. S/N-5 on test at $\bar{T}_H = 1000^\circ\text{F}$ for 6592 hours. Increase in BOL efficiency measured as a result of cold junction tungsten barriers. No reduction in degradation rate measured as a result of cold junction barrier. Both modules being held in bond room.

CONFIDENTIAL

Astronuclear
Laboratory

Series	Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
9U	6	Same as 9AC S/N-1 except vapor deposited tungsten to act as barriers between molybdenum and PbTe.	Same as TEM-9C S/N-5	Determine effectiveness of vapor deposited tungsten barrier	Tested for 4686 hours at $\bar{T}_H = 1200^\circ\text{F}$. Module exhibited less degradation than any previous TEGS-2P module tested at temperature. Module removed from test and being held in bond room.
9U	7, 8, 9, 10, 11, 12	Same as 9U S/N-4 except inner conductor ring fabricated with tungsten rather than iron	Same as TEM-9C S/N-5	Completely isolate PbTe from iron in the vicinity of module hot junction.	S/N-7 through -10 tested at $\bar{T}_H = 1125^\circ\text{F}$ and $\bar{T}_C = 570^\circ\text{F}$ as a part of another program. S/N-11 and S/N-12 were tested at $\bar{T}_H = 1100^\circ\text{F}$ and 1200°F , respectively, with $\bar{T}_C = 392^\circ\text{F}$. Degradation rates reduced by a factor of two as compared to S/N-2 and S/N-3. S/N-11 and S/N-12 being held in bond room.
9U	13, 14	Same as TEM-9N except with molybdenum tungsten split inner conductors and moly cold side conductors	Same as TEM-9C S/N-5	Eliminate diffusion path from p-type material to n-type material through assembly clearances.	Both modules placed on test at $\bar{T}_H = 1100^\circ\text{F}$ and $\bar{T}_C = 392^\circ\text{F}$. No data reduced prior to end Phase II-C.
9U	15, 16, 17, 18	Same as 9U S/N-7 except molybdenum cold side conductors substituted for iron and tungsten foil	GPS at 750°C , 30,000 psi	Eliminate diffusion path from p-type material to n-type material through assembly clearances.	Testing of S/N-15 and S/N-16 indicated no effect of autoclave conditions on module performance. Both modules being held in bond room. S/N-17 and S/N-18 eliminated from program.
9U	19, 20, 21	Same as 9U-13	Same as TEM-9C S/N-5	Same as TEM-9U S/N-13	Negligible degradation in power output for S/N-19 after 3359 hours of operation at $\bar{T}_H = 1100^\circ\text{F}$. S/N-20 built and tested as part of another program. S/N-21 destructive examination after processing revealed excellent alignment of components.
9U	22	Same as 9U-13 except iron tungsten inner conductor ring assembly employed.	Same as TEM-9C S/N-5.	Same as 9U-13.	S/N-22 on test at $\bar{T}_H = 1100^\circ\text{F}$ at significantly increased B. O. L. power output.
9X-1	1	Same as TEM-9Q except TEGS-3P material used in p- and n-legs	Same as TEM-9C S/N-5	Determine high temperature capability of TEGS-3P material.	Tested for 524 hours at $\bar{T}_H = 1200^\circ\text{F}$, 1195 hours at $\bar{T}_H = 1250^\circ\text{F}$ and 7728 hours at $\bar{T}_H = 1300^\circ\text{F}$ with no signs of shorting or degradation. Testing continuing at $\bar{T}_H = 1300^\circ\text{F}$. Peak temperature of 1376°F .
9Y	1	TEM-9Q design with GE-nl material. Inner clad thickness reduced from .090" to .050".	Same as TEM-9C S/N-5	Obtain performance and clad creep and relaxation data at various temperatures.	5100 hours of test data indicate module performance is unaffected by the thin inner clad for temperatures up to 1200°F . Module presently being held in bond room.
9Z	1	Same as TEM-9U except n-leg cascaded optically with Zn and 3N material.	Same as TEM-9C S/N-5	Obtain improved high temperature performance over a noncascaded 9U-type module.	Module dropped from program.
9AC	1, 2	Same as TEM-9I except molybdenum hot side conductor rings.	Same as TEM-9C S/N-5	Study degradation in a module using molybdenum hot side conductor rings.	S/N-1 accumulated 5537 hours at $\bar{T}_H = 1000^\circ\text{F}$ with degradation reduced by an order of magnitude over nonbarrier (TEM-9I) modules. S/N-2 on test for 120 hours at $\bar{T}_H = 1200^\circ\text{F}$. S/N-1 being held in bond room and S/N-2 destructively examined.
9AD	1	Same as 9U S/N-4 with circuit length increased to 15 inches.	Same as TEM-9C S/N-5	Study module performance for a 15 inch module.	Tested at $\bar{T}_H = 1000^\circ\text{F}$ and $\bar{T}_C = 392^\circ\text{F}$ as a part of another program.

Series	Number	Design Features	Processing Conditions	Program Objectives	Status and/or Results
9AE	1	Same as 9Q S/N-1 with 0.030 inch lead telluride washers and 0.0015 inch mica washers.	Same as TEM-9C S/N-5	Produce a high voltage module and verify feasibility of thin T/E washer operation.	Increased module degradation observed at $\bar{T}_H = 1000^\circ\text{F}$ as a result of imperfect hydrogen purge during processing. BOL performance correlated to within $\pm 2\%$ with calculations. Removed from test and destructively examined.
9AE	2	Same as S/N-1 except for use of 0.005 inch mica washers.	Same as TEM-9C S/N-5	Same as TEM-9AE S/N-1	BOL performance correlated to within $\pm 2\%$ with calculations. Tested 5948 hours at $\bar{T}_H = 1000^\circ\text{F}$, presently held in bond room. Performance trends identical to TEM-9Q S/N-1.
9AE	3	Same as S/N-2 except for use as 0.050 inch T/E washers.	Same as TEM-9C S/N-5	Same as TEM-9AE S/N-1	Tested for 1697 hours at $\bar{T}_H = 1000^\circ\text{F}$ and then shifted to $\bar{T}_H = 1125^\circ\text{F}$. Performance trends at 1125/570 identical to TEM-9Q S/N-5, -6, -7. Module being held in bond room.
9AF	1	TFM-9S S/N-3 end closures TEM-9F 0.050 in. SS outer clad TEM-9U S/N-19 conductors TEM-9T 0.0015 in. mica insulators	Same as TEM-9C S/N-5	Demonstrate increased performance by utilizing various Phase II-B design improvements	Overall efficiency level of 5.85% recorded for $\bar{T}_H = 1100^\circ\text{F}$, $T_C = 392^\circ\text{F}$ operation. Module destructively examined to determine cause of inter-couple shorting.
10	1, 2	Large bore (1.0" I.D.) Module with scaled up TEM-9S S/N-3 dimensions.	Same as TEM-9C S/N-5	Advance tubular module technology by increasing size to develop a module suitable for use in conjunction with a heat pipe.	S/N-1 static tested for 5533 hours with very low degradation. Destructive examination after thermal cycle tests revealed need for end closure design modifications. S/N-2, fabricated as part of another program.
10	3	Identical to S/N-1 except solid tungsten inner conductor rings substituted for Fe/W foil con-	Same as TEM-9C S/N-5	Demonstrate high efficiency of a heater/heat pipe/module/planar radiator assembly unit.	Overall B.O.L. unit efficiency of 5.38% at $\bar{T}_H = 1000^\circ\text{F}$. Unit has accrued 6900 hours with present overall efficiency level of 4.4%.
10	4, 7	Molybdenum/tungsten split inner conductors and moly cold side conductors. End closures similar to S/N-8 design with solid collector and retainer rings.	Same as TEM-9C S/N-5	Demonstrate improved performance of 1.0 inch I.D. module with inner conductor ring fix.	Modules fabricated. To be tested in next Phase of program.
10	5, 6	Same as TEM-10 S/N-4 and 7.	Same as TEM-9C S/N-5	S/N-5, -6 to be incorporated in a cascaded SiGe PbTe system as part of another program.	S/N-5 and S/N-6 awaiting program developments.
10	8, 9	Identical T/E circuit as TEM-10 S/N-3. End closure modifications defined to enhance thermal cycling capabilities.	Same as TEM-9C S/N-5	To identify an end closure configuration assuring maximum stability during thermal cycling.	S/N-8 thermally cycled 10 times and S/N-9 thermal cycled 21 times with no effect on module performance. Both modules removed from test for destructive examination.
12	1	Large bore module suitable for use in a centerline isotope fueling configuration	Same as TEM-9C S/N-5	Demonstrate capability to fabricate large modules for isotope fueling.	Module fabricated, processed and destructively examined. Results indicate proper compaction and alignment of parts.

~~CONFIDENTIAL~~

APPENDIX C

STATISTICAL TREATMENT OF TUNGSTEN DISPERSED BAR DATA

A polynomial of the form $C_1 + C_2 X + C_3 X^2 + \dots + C_n X^{n-1}$ was fitted to the data points for each case of the experiment. The optimum values for the coefficients were obtained by means of a least squares calculation. It was determined that a third degree equation was adequate for the Seebeck coefficient data and a fourth degree equation for the resistivity data. The standard error of fit, $s(y)$, was also calculated in each case from

$$s(y) = \left[\frac{\sum (Y - \hat{Y})^2}{\text{d.f.}} \right]^{1/2},$$

where

Y is the observed value

$\hat{Y}$ is the value calculated from the polynomial

d.f. is the degrees freedom = (number of observations - number of coefficients)

An estimate of the variance of the polynomial $S^2(\hat{y})$ can now be calculated from this standard error of fit by:

$$s^2(\hat{y}) = s^2(y) \left[\frac{1}{n} + \sum_i \sum_{j=1}^n C_{ij} x'_i x'_j \right]$$

To simplify the task, it was noted that in the above expression $x'_i = X'_i - \bar{X}_i$,

where

X'_i is the observed value of the independent variable

$\bar{X}_i$ is the average of all observed independent variables $\bar{X} = \frac{\sum X_i}{n}$.

Thus, if one chooses to evaluate the above expression at the value $X'_i = \bar{X}_i$, then $x'_i = 0$ and the last term drops out.

The variance of the polynomial at $\bar{X}$ is simply:

$$s^2(\hat{y}) = s^2(y) \frac{1}{n}$$

~~CONFIDENTIAL~~

~~CONFIDENTIAL~~

For each case the average of the independent variables, $\bar{X}_i$, was computed; the polynomial was evaluated at $\bar{X}_i$ to obtain $Y_{(\bar{x})}$; and the variance $s^2(\hat{y})$ was calculated at the same point. It is now possible to place a confidence interval about the value of the polynomial at that point as follows:

$$Y_{(\bar{x})} - t_{\alpha} s(\hat{y}) < Y_{(\bar{x})} < Y_{(\bar{x})} + t_{\alpha} s(\hat{y}),$$

where t_{α} is a constant, dependent upon the confidence level desired and the number of degrees of freedom used to determine the polynomial.

As a test for significance of difference between two polynomials, such a confidence interval was constructed about the value of the first polynomial at $\bar{X}$; then the second polynomial was evaluated at the same $\bar{X}$. If the value of the second polynomial was included in the confidence interval of the first, it was accepted as being identical. If, however, it was outside the confidence interval, it was considered significantly different. The results of several such comparisons made on the data at a 95 percent confidence level are documented in the text.

~~CONFIDENTIAL~~